

PERFORMANCE OF CONCRETE CONTAINING METAKAOLIN AS
CEMENT REPLACEMENT MATERIAL

ONG CHEE HUAT

A project report submitted in partial fulfillment of
the requirements for the award of the degree of
Master of Engineering (Civil - Structure)

Faculty of Civil Engineering
Universiti Teknologi Malaysia

NOVEMBER, 2006

ABSTRACT

Concrete is probably the most extensively used construction material in the world. However, environmental concerns both in terms of damage caused by the extraction of raw material and CO₂ emission during cement manufacture have brought pressures to reduce cement consumption by the use of supplementary materials. The utilization of calcined clay, in the form of metakaolin (MK) in concrete has received considerable attention in recent years. On this matter, a study has been conducted to look into the performance of metakaolin as cement replacement material in concrete. The study focuses on the compressive strength performance of the blended concrete containing different percentage of metakaolin. The cement is replaced accordingly with the percentage of 5 %, 10%, 15%, 20% and 30% by weight. Concrete cubes are tested at the age of 1, 3, 7, and 28 days. In addition, the effect of calcination temperature to the strength performance is included in the study. Finally, the strength performance of metakaolin-concrete is compared with the performance of concrete blended with silica fume and slag. The results show that the strength development of concrete blended with metakaolin is enhanced. It was found that 10% replacement appears to be the optimum replacement where concrete exhibits enhanced compressive strength at all ages comparable to the performance of SF and GGBS. The study also reveals that optimum calcination temperature of 750°C is important to improve the performance of metakaolin-concrete.

ABSTRAK

Konkrit merupakan salah satu bahan binaan yang paling banyak digunakan dalam dunia. Akan tetapi, terdapat masalah pencemaran persekitaran yang disebabkan oleh penggunaan simen dalam konkrit. Pencemaran berlaku semasa pengekstrakan bahan mentah dan penghasilan karbon dioksida semasa pemrosesan simen. Hal ini telah menimbulkan tekanan untuk mengurangkan penggunaan simen dan diganti oleh bahan gantian. Penggunaan tanah liat terbakar dalam bentuk *metakaolin* (MK) dalam konkrit telah mendapat perhatian yang lebih kebelakangan ini. Dalam hal ini, satu kajian telah dijalankan untuk mengkaji prestasi *metakaolin* sebagai bahan gantian simen dalam konkrit. Kajian ditumpukan ke atas kekuatan mampatan konkrit yang mengandungi *metakaolin* dalam peratusan yang berbeza. Simen digantikan dalam peratusan 5 %, 10%, 15%, 20% dan 30% mengikut berat. Kekuatan konkrit diuji pada hari ke-1, 3, 7 dan 28. Pada masa yang sama, pengaruh suhu bakaran ke atas kekuatan mampatan turut dikaji. Prestasi kekuatan konkrit-*metakaolin* juga dibandingkan dengan prestasi konkrit yang mengandungi wasap silika dan sanga relau bagas. Keputusan eksperimen menunjukkan gantian *metakaolin* dalam konkrit telah meningkatkan perkembangan kekuatan mampatan konkrit di mana gantian 10% merupakan peratusan gantian yang paling optima. Kajian juga mendapati *metakaolin* adalah setara dengan bahan gantian simen yang lain seperti wasap silika dan sanga relau bagas dalam perkembangan dan peningkatan kekuatan mampatan konkrit. Suhu bakaran didapati mempunyai pengaruh yang ketara terhadap kekuatan mampatan konkrit-*metakaolin*. Kajian menunjukkan Suhu bakaran setinggi 750°C merupakan suhu yang paling sesuai bagi meningkatkan prestasi konkrit-*metakaolin*.

CONTENTS

CHAPTER	SUBJECT	PAGE
	THESIS TITLE	i
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	CONTENTS	vii
	LIST OF TABLES	xi
	LIST OF FIGURES	xii
	LIST OF SHORTFORMS	xvi
	LIST OF APPENDICES	xv
CHAPTER I	INTRODUCTION	1
	1.0 Introduction	1
	1.1 Objective of Study	3
	1.2 Significant of the Study	3
	1.3 Scope of Study	4

CHAPTER II	LITERATURE REVIEW	6
2.0	Concrete	6
2.1	Cement	8
2.2	Cement Replacement Material	10
2.2.1	Pozzolanic Behavior	10
2.2.2	Types of Material	11
2.3	Kaolin	14
2.3.1	Classification	15
2.3.2	Mineralogy	16
2.4	Physical and Chemical Properties of Kaolin	16
2.4.1	Particle Size	17
2.4.2	Color and Brightness	18
2.4.3	pH	19
2.4.4	Chemical Composition	19
2.5	Application and Specification	20
2.5.1	Paper	20
2.5.2	Ceramic and Refractory	21
2.5.3	Rubber	22
2.5.4	Paints	22
2.5.5	Others Uses	23
2.6	Calcination	24
2.6.1	Temperature	26
2.6.2	Method of Calcination	28
2.7	Metakaolin	29
2.7.1	Sources for Metakaolin	30
2.7.2	High Reactivity Metakaolin	31
2.8	The Pozzolanic Reaction	33
CHAPTER III	RESEARCH METHODOLOGY	35
3.0	Introduction	35
3.1	Materials	36

3.1.1	Cement	36
3.1.2	Kaolin	37
3.1.3	Silica Fume	37
3.1.4	Ground Granulated Blast Furnace Slag	37
3.1.5	Sand and Aggregate	40
3.1.6	Water	40
3.2	Calcining Kaolin	41
3.3	Concrete Mixes	42
3.4	Mixing Procedure	43
3.5	Preparing Test Cubes	44
3.6	Curing	44
3.7	Compression Test	46
CHAPTER IV RESULT AND DISCUSSION		48
4.0	Introduction	48
4.1	Effect of MK to Compressive Strength	49
4.1.1	5% and 15% Replacement	49
4.1.2	10% Replacement	53
4.1.3	20% and 30% Replacement	55
4.2	Effect of Calcination Temperatures to Strength Development	60
4.2.1	Effect of Calcination	60
4.3	Effect of Calcination Temperature (10% Replacement)	61
4.4	Effect of Calcination Temperature (20% Replacement)	67
4.5	Comparison between MK and Others Pozzolans to the Strength Performance of Concrete	71
4.6	Further Discussion	75

CHAPTER V	CONCLUSIONS AND RECOMMENDATIONS	80
5.1	Conclusion	80
5.2	Recommendations	81
	REFERENCE	83
	APPENDIX	86

LIST OF TABLES

TABLE NO.	TITLE`	PAGE
2.1	Typical Properties of Normal-Strength Portland Cement Concrete.	7
2.2	Properties of Kaolin.	17
2.3	Chemical Properties of Kaolin	19
3.1	Properties of Cement, Kaolin, SF and GGBS	38
3.2	Mix Proportions	43
4.1	Cube Test Results for Different Mix Ratios	51
4.2	Cube Test Results for Mixes with Different Calcination Temperatures	62
4.3	Cube Test Results for Mixes with Different Calcination Temperatures	67
4.4	Strength Comparison between MK, SF and GGBS Concrete	71
4.5	Compression Test Results for Cubes Cured In Water	75
4.6	Compression Test Results for Cubes Cured Using Sacks	76

LIST OF FIGURES

FIGURE NO.	TITLE`	PAGE
2.1	Fly Ash.	11
2.2	Silica Fume.	13
2.3	Kaolin.	14
2.4	Structure of Kaolinite.	15
2.5	Kaolin Particle Size.	18
2.6	Crystalline of Kaolinite.	24
2.7	DTA Curve.	25
2.8	SEM Photographs of Calcined Kaolin at Temperature (a) 550°C, (b) 650°C, (c) 800°C and (d) 900°C.	27
2.9	Rotary Kiln.	28
2.10	Metakaolin Particle.	30
3.1	Flow Chart of the Study.	36
3.2	Kaolin.	39
3.3	Silica Fume.	39
3.4	Ground Granulated Blast Furnace Slag.	39
3.5	Oven for Heating the Aggregates.	40
3.6	Calcining Kaolin.	41
3.7	Kaolin Before Calcination and After Calcination.	42
3.8	Curing Using Sacks.	45
3.9	Covering the Sacks with Plastic Sheets.	45
3.10	Concrete Cubes.	46
3.11	Compression Test	47
3.12	The Tested Cubes	47

4.1	Compressive Strength For 5% And 15% Replacement Compared to Control	52
4.2	Compressive Strength For 10% Replacement Compared to Control	54
4.3	Compressive Strength For 20% And 30% Replacement Compared to Control	56
4.4	Strength Development for Various Mixes	59
4.5	Strength Performance With 10% MK Calcined at Various Temperatures	63
4.6	XRD Pattern of Kaolin	64
4.7	Strength Performance With 20% MK Calcined at Various Temperatures	68
4.8	Strength Comparison for MK, SF and GGBS Concrete	72
4.9	Compression Test Results For Cubes Cured In Water and Cured Using Sacks	77
4.10	White Sediment Forming On The Top of the Cube	78
4.11	Bubbles on the Surface of the Cube	79

LIST OF SHORTFORMS

%	- percentage
°C	- Celcius
GGBS	- Ground Granulated Blast Furnace Slag
kg	- kilograms
m	- meter
m ³	- meter cubes
MK	- Metakaolin
MPa	- Mega Pascal
SF	- Silica Fume

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Silica Fume	86

CHAPTER 1

INTRODUCTION

1.0 Introduction

Concrete is one of the most common materials used in the construction industry. In the past few years, many research and modification has been done to produce concrete which has the desired characteristics. There is always a search for concrete with higher strength and durability. In this matter, blended cement concrete has been introduced to suit the current requirements. Cementitious materials known as pozzolans are used as concrete constituents, in addition to Portland cement. Originally the term pozzolan was associated with naturally formed volcanic ashes and calcined earths will react with lime at ambient temperatures in the presence of water. Recently, the term has been extended to cover all siliceous/aluminous materials which, in finely divided form and in the presence of water, will react with calcium hydroxide to form compounds that possess cementitious properties. The current area of research in the concrete is introducing clay (metakaolin) in the concrete.

Clays have been and continue to be one of the most important industrial minerals. Clays and clay minerals are widely utilized in our society. They are important in geology, agriculture, construction, engineering, process industries, and environmental applications. Traditional applications of clay including ceramics,

paper, paint, plastics, drilling fluids, chemical carriers, liquid barriers, and catalysis. Research and development activities by researchers in higher education and industry are continually resulting new and innovative clay products.

Metakaolin is one of the innovative clay products developed in recent years. It is produced by controlled thermal treatment of kaolin. Metakaolin can be used as a concrete constituent, replacing part of the cement content since it has pozzolanic properties. The use of metakaolin as a partial cement replacement material in mortar and concrete has been studied widely in recent years. Despite of the recent studies, there are still many unknowns with the use of metakaolin. Study is needed to determine the contribution of metakaolin to the performance of hardened concrete. There are great concerns on the strength and durability of metakaolin-concrete when used as construction materials in the construction industries. If it is proven that the concrete is durable and strong, this will lead to the use of metakaolin to replace part of the cement.

1.1 Objective of Study

This study is conducted to accomplish some predefined objectives. These objectives are:

- i) To study the performance of concrete containing different percentages of metakaolin and to identify the optimum replacement percentage.
- ii) To investigate the effect of calcination temperatures to the strength performance of metakaolin-concrete.
- iii) To compare the performance of metakaolin with other cement replacement materials (CRMs).

1.2 Significant of the Study

Concrete has been used in the construction industry for centuries. Many modifications and developments have been made to improve the performance of concrete, especially in terms of strength and durability.

The introduction of pozzolans as cement replacement materials in recent years seems to be successful. The use of pozzolan has proven to be an effective solution in enhancing the properties of concrete in terms of strength and durability. The current pozzolans in use are such as fly ash, silica fume and slag. Development and investigation of other sources of pozzolan such as kaolin will be able to provide more alternatives for the engineer to select the most suitable cement replacement

material for different environments.

Unlike other pozzolans, metakaolin is not a by-product which means its engineering values are well-controlled. Therefore, using metakaolin should promise some advantages compared to other cement replacement materials. In this case, studies are needed to study the performance of concrete using metakaolin. The performance of metakaolin-concrete will be compared to the cost of production of metakaolin to determine whether metakaolin is worthy to be developed as a new cement replacement material.

In addition, the use of metakaolin is not common in the Malaysian construction sector. This study will be able to enhance the understanding on the suitability of metakaolin as cement replacement material.

1.4 Scope of Study

This study focuses on the strength performance of concrete with metakaolin. Strength is the most important property of concrete since the first consideration in structural design is that the structural elements must be capable of carrying the imposed loads. Strength characteristic is also important because it is related to several other important properties which are more difficult to measure directly.

With regard to this matter, the development of compression strength of metakaolin concrete is studied. Cement replacements by 5%, 10%, 15%, 20% and 30% with metakaolin are studied. Concrete tests are conducted on the concrete samples at the specific ages. All the strength tests are limited to the ages of 28 days.

In the study of the effect of calcination temperatures to the strength performance of metakaolin, the temperatures is set within the range of 600°C-800°C. The temperatures interval used is 50°C.

For the performance comparison study, the cement replacement materials used are silica fume and ground granulated blast furnace slag. These two cement replacement materials are chosen as they are the most common replacement materials nowadays and will be good comparisons to metakaolin. The comparison is made on the compressive strength performance of metakaolin, silica fume and slag concrete.

REFERENCE

Ambroise, J., Murat, M. and Pera J. (1985), *Hydration Reaction and Hardening of Calcined Clays and Related Minerals: V. Extension of the Research and General Conclusions*. Cement Concrete Res. 15, pp. 261–268.

Changling, He (1994). *Thermal Stability and Pozzolanic Activity of Calcined Kaolin*, Applied Clay Science.

Dunster, A.M., Parsonage, J.R. and Thomas, M.J.K. (1999). *Pozzolanic Reaction of Metakaolinite and Its Effects on Portland Cement Hydration*. J. Mater. Sci: 1345–1350.

Hamer, Frank (1977), *Clays*, Watson Guptill: 15-36.

Hewlett, Peter (1998). *Lea's Chemistry of Cement and Concrete*, Elsevier Butterworth Heinemann.

Kaloumenou, E., Badogiannis, S.T. and Kakali, G. (1999). *The Effect of Kaolinite Particle Size on Its Conversion to Metakaolinite*. J. Thermal Anal. 56: 901–907.

Kosmatka, S.H. (1999). *Mechanical Engineering Handbook*, CRC Press LLC:12-43

Kostuch, J.A., Walters V. and Jones, T.R. (2000) *High Performance Concretes Incorporating Metakaolin: A Review*. University of Dundee.

Lea F.M (1970). *The Chemistry of Cement and Concrete*, 3rd Ed, Edward Arnold Ltd.

Malhotra, V.M. (1983). *Fly Ash, Silica Fume, Slag, & Other Mineral By-product in Concrete*, Publication SP-79, American Concrete Institute.

Malhotra, V.M. (1986). *Fly Ash, Silica Fume, Slag, and Natural Pozzolans In Concrete, Proceedings Second International Conference, Madrid, Spain.*

Malhotra, V.M. (1995). *Characteristics of A Thermally Activated Alumino-silicate Pozzolanic Material and Its Use in Concrete*, Cement Concrete Res 25: 1713–1725

Marwan, T., Pera, J. and Ambroise J. (1992). *The Action of Some Aggressive Solutions on Portland and Calcined Laterite Blended Cement Concretes. Proceedings of the Fourth International Conference on Fly Ash, Silica Fume, Slag and Natural Pozzolans in Concrete*, vol. I. Istanbul, Turkey.

Murat, M. (1995). *Hydration Reaction and Hardening of Calcined Clays and Related Minerals: II. Influence of Mineralogical Properties of the Raw Kaolinite on the Reactivity of Metakaolinite*. Cem. Concr. Res.

Murray, H.H. (1991). *Overview: Clay Mineral Applications*. Applied Clay Science, Volume 5, Issues 5-6: 379-395.

Murray, H.H. (2000). *Traditional and New Applications for Kaolin, Smectite, and Palygorskite: A General Overview*. Applied Clay Science Volume 17, Issues 5-6: 207-221

Neville, A.M. (1987). *Concrete Technology*. Longman Scientific & Technical.

Poon, C.S., Kou, S.C. and Lam, L (2005). *Compressive Strength, Chloride Diffusivity and Pore Structure of High Performance Metakaolin and Silica Fume Concrete*. Construction and Building Materials:223-239.

Pera, J. and Amrouz, K. (1998) *Development of Highly Reactive Metakaolin from Paper Sludge*. Adv. Cement Based Material: 49–56

Prasad, M. S., Reid, K. J. and Murray, H. H. (1991). *Kaolin: Processing, Properties and Applications*. Applied Clay Science. Volume 6, Issue 2: 87-119

Sabir, S.W. and Bai, J. (2001). *Metakaolin and Calcined Clays As Pozzolans for Concrete: A Review*. Cement and Concrete Composites. Volume 23, Issue 6: 441-454

Salvador, S. (1995). *Pozzolanic Properties of Flash-calcined Kaolinite: A Comparative Study With Soak-calcined Products*. Cement Concrete Res. 25: 102–112.

Swamy, R.N. (1986). *Cement Replacement Materials*, Surrey University Press:1-72.

APPENDIX A