

**EFFECT OF SILICA FUME TO THE STRENGTH AND PERMEABILITY
OF HIGH PERFORMANCE GROUND GRANULATED BLASTFURNACE
SLAG CONCRETE**

AZLI SHAH BIN ALI BASHAH

UNIVERSITI TEKNOLOGI MALAYSIA

**EFFECT OF SILICA FUME TO THE STRENGTH AND PERMEABILITY
OF HIGH PERFORMANCE GROUND GRANULATED BLASTFURNACE
SLAG CONCRETE**

AZLI SHAH BIN ALI BASHAH

**A project report submitted in partial fulfillment of the
requirements for the award of the degree of
Master of Engineering (Civil – Structure)**

**Faculty of Civil Engineering
Universiti Teknologi Malaysia**

MAY 2006

ABSTRACT

A durable concrete is one that has the ability to withstand the damaging effects of the environment and of its service conditions without undue deterioration and excessive unforeseen maintenance over the design life of a structure. The use of high performance concrete is an alternative in producing high – strength concrete, durable and construction friendly. This paper study the effect of silica fume to the properties of high performance ground granulated blastfurnace slag concrete to reveal the potential outmost. It was found by compressive strength test, that high-strength concrete can be achieved. At the age of 28 days, concretes containing 5, 7.5, and 10% silica fume gave compressive strengths of 65.6, 64.6, and 67.1 Mpa, respectively. At aged 56 days concrete containing 10% of silica fume had the highest strength. However the concrete containing 5% of silica fume had low permeability thus may enhance the durability.

ABSTRAK.

Konkrit yang tahan lasak adalah kebolehan konkrit tersebut daripada mengalami kerosakan akibat dari kesan alam sekitar dan kemerosotan semasa perkhidmatan serta penyelenggaraan yang kurang sepanjang hayat rekabentuk sesuatu struktur. Penggunaan konkrit berprestasi tinggi digunakan sebagai bahan alternatif untuk menghasilkan konkrit yang tahan lasak, berkekuatan tinggi dan memudahkan kerja pembinaan. Sehubungan itu kajian kesan bahan tambah silika peluwap terhadap sifat konkrit sangga relaubagas berbutir untuk mendedahkan potensi yang wujud. Dalam kajian ini melalui ujian mampatan, konkrit berkekuatan tinggi boleh dicapai. Pada konkrit berusia 28 hari yang mengandungi 5, 7.5 dan 10 % silika peluwap mencapai kekuatan mampatan 65.6, 64.6 dan 67.1 Mpa. Manakala konkrit pada usia 56 hari yang mengandungi 10% silika peluwap mencapai kekuatan yang paling tinggi. Walaubagaimanapun konkrit yang mengandungi 5% silika peluwap mempunyai ketelapan yang rendah dan secara tidak langsung ianya menambah nilai ketahananlasakan.

TABLE OF CONTENT

CHAPTER	TITLE	PAGE
	Title Page	i
	Declaration	ii
	Dedication	iii
	Acknowledgement	iv
	Abstract	v
	Abstrak	vi
	Table of Content	vii
	List of Tables	x
	List of Figure	xii
	List of Symbols	xiv
1	INTRODUCTION	
	1.1 Foreword	1
	1.2 Objectives	2
	1.3 Scope of study	3
2	LITERATURE REVIEW	
	2.1 Introduction	4
	2.1.1 Definitions Of High Performance Concrete (HPC)	4
	2.2 Development Of High Performance Concrete	5
	2.3 Materials For High Performance Concrete	6
	2.3.1 Supplementary Cementing Materials	7

	2.3.2	Silica Fume	8
	2.3.3	Ground Blastfurnace Slag Cements	10
	2.4	Aggregates	15
	2.5	Superplastizer/High Range Water Reducers	16
	2.5.1	Superplasticizer Dosage	18
	2.6	Water	19
	2.7	Supplementary Cementing Materials For Proposal Concrete Mix	19
	2.7.1	Mix Selection For High Performance Concrete	19
3		METHODOLOGY	
	3.1	Introduction	30
	3.2	Experimental For The High Performance Concrete	30
	3.3	Material for testing	31
	3.4	Water	31
	3.5	Admixtures	32
	3.6	Cube Compressive Strength	32
	3.6.1	Preparation of Concrete Cube Grade 60 with Free W/ C Ratio 0.32	33
	3.7	Permeability Testing	34
4		RESULT AND ANALYSIS	
	4.1	Introduction	47
	4.2	The Results of Concrete Cubes Strength	47
	4.2.1	Analysis from the Results	48
	4.2.1.1	Analysis in respect to strength	48
	4.3	The Results of Permeability Test (ISAT)	50

5 DESIGN RECOMMENDATION

5.1	Introduction	68
5.2	Discussion about the Concrete Cube Strength.	68
5.2.1	1 day cube strength	69
5.2.2	3 and 7 days cube strength	69
5.2.3	28 and 56 days cube strength.	70
5.3	Permeability of Concrete Cube.	71

6 SUMMARY AND CONCLUSION

6.1	Conclusion	75
6.2	Recommendation	76

REFERENCES	77
-------------------	----

APPENDIX A	81
-------------------	----

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Typical Composition	21
2.2	Some Major Projects That Used Blastfurnace Slag Cement In Malaysia	22
2.3	Mix Proportions of Some High Performance Concrete	23
3.1	Mixture Proportions	36
3.2	Program for casting and testing of Concrete Cube	37
4.1	The Results Of Cubes Test	52
4.2	Comparison the compressive strength of Y2, Y3, Y4 for 1 day to YI	53
4.3	Comparison the compressive strength of Y2, Y3, Y4 for 3 days to YI	54
4.4	Comparison the compressive strength of Y2, Y3, Y4 for 7 days to YI	55
4.5	Comparison the compressive strength of Y2, Y3, Y4 for 28 days to YI	56
4.6	Comparison the compressive strength of Y2, Y3, Y4 for 56 days to YI	57
4.7	The Result Of Cube Strength Grade 60 Relate To JKR Specification	58
4.8	The Test Result Of Permeability ISAT For The Cube Y1 At Age 28 Days	60
4.9	The Test Result Of Permeability ISAT For The Cube Y2 At Age 28 Days	61
4.10	The Test Result Of Permeability ISAT For The Cube Y3 At Age 28 Days	62
4.11	The Test Result Of Permeability ISAT For The Cube Y4 At Age 28 Days	63
4.12	The Test Result Of Permeability ISAT For The Cube Y1 At Age 56 Days	64
4.13	The Test Result Of Permeability ISAT For The Cube Y2 At Age 56 Days	65
4.14	The Test Result Of Permeability ISAT For The Cube Y3 At Age 56 Days	66

LIST OF TABLES

TABLE NO.	TITLE	PAGE
4.15	The Test Result Of Permeability ISAT For The Cube Y4 At Age 56 Days	67
4.15	The result for Comparisons Relative To Permeability And Compressive Strength For The Same Specimen	68
5.1	Reference For Permeability (ISAT) Test	74

LIST OF FIGURES.

FIGURE NO	TITLE	PAGE
2.1	Factors which influences high performance concrete	24
2.2	Typical Strength Development	25
2.3	Higher Resistance to Chloride Diffussion	26
2.4	Higher resistance to sulphate attack	27
2.5	Protection Against Alkali-Silica Reaction	28
2.6	Temperature Profile Of Slagcem (contain 70 % ggbs& OPC)	29
3.1	Silica Fume(SF)	38
3.2	Ground Granulated Blast-Furnace Slag(GGBS)	38
3.3	Admixtures P322N And R1100H	39
3.4	Step for preparation the 150x150x150 concrete cube	40
3.5	Procedure In Preparation Of Concrete Cube	41
3.6	Compacting The Fresh Concrete	41
3.7	Measuring The Slump Of Fresh Concrete	42
3.8	Preparation of Concrete Cube for compressive testing	43
3.9	Cubes In The Tank For Curing Purpose	44
3.10	The procedures carried for the cubes test as in accordance to BS 1881:Part 116	45
3.11	Initial Surface Absorption Apparatus	46
3.12	Plastic Cap	46
4.1	Concrete cube strength in normal water for I day	53
4.2	Concrete cube strength in normal water for 3 days	54
4.3	Concrete cube strength in normal water for 7 days	55
4.4	Concrete cube strength in normal water for 28 days	56
4.5	Concrete cube strength in normal water for 56 days	57
4.6	Comparison Between The Cube Strength At 1,3,7,28,56 Days	59
4.7	The Graph Pattern For The Cube Y1 At Age 28 Days	60
4.8	The Graph Pattern For The Cube Y2 At Age 28 Days	61

LIST OF FIGURES.

FIGURE	NO	TITLE	PAGE
4.9		The Graph Pattern For The Cube Y3 At Age 28 Days	62
4.10		The Graph Pattern For The Cube Y4 At Age 28 Days	63
4.11		The Graph Pattern For The Cube Y1 At Age 56 Days	64
4.12		The Graph Pattern For The Cube Y2 At Age 56 Days	65
4.13		The Graph Pattern For The Cube Y3 At Age 56 Days	66
4.14		The Graph Pattern For The Cube Y4 At Age 56 Days	67

LIST OF SYMBOLS

BS	-	British Standard
HPC	-	High Performance Concrete
ACI	-	American Concrete Institute
w/c	-	water/cement
Mpa	-	Mega pascal
ISAT	-	Initial Surface Absorption Test
C-S-H	-	Calcium Silicate Hydrates
AASHTO	-	American Association of State Highway and Transportation Officials
MS	-	Malaysian Standard
OPC	-	Ordinary Portland Cement
C ₃ A	-	Tricalcium Aluminate
Psi	-	Pound/square inch
GGBS	-	Ground Blastfurnace Slag Cements
SF	-	Silica Fume
ASTM	-	American Society for Testing And Materials
S.O.	-	Superintendent Officer
UTM	-	University Technology Malaysia
JKR	-	Jabatan Kerja Raya
mm	-	millimeter
N/mm ²	-	newton per millimetres square
ml/m ² /s	-	milliliters per square metre per second
SiO ₂	-	Silicon Dioxide
Ca(OH)	-	Calcium Hydroxide
FM	-	Figgs Method
m ² /kg	-	metre square per kilogram
>	-	More than
<	-	Less than

CHAPTER 1

INTRODUCTION

1.1 Foreword

Most conventional concrete structures deteriorate rapidly and require costly repairs before their expected service life is reached. Four major types of environmental distress affect concrete structures. They are corrosion of the reinforcement, alkali-aggregate reactivity, freeze-thaw deterioration, and attack by sulfates (Ozyildirim, 1998). In each case, water or chemical solutions may penetrate the concrete and initiate or accelerate damages. By using high-performance concrete (HPC), durability and are enhanced strength, resulting in long-lasting and economical structure (Lerning and Ahmed, 1993).

American Concrete Institute(ACI) defined high performance concrete as: “High performance concrete (HPC) defined as concrete which meets special performance and uniformity requirements that cannot always be achieved routinely by using only conventional materials and normal mixing, placing and curing practices”

The high performance concrete mixes designed for low permeability resist this infiltration of aggressive liquids and, therefore, are more durable. One important issue need to be addressed in the use of high performance concrete are the development of the mixes.

Low-permeability concretes are made with a low (0.45 and less) water-cementations material ratio (w/cm). Pozzolanic material such as fly ash, silica fume, or slag be used as cementation materials. These modifications to the mixes results in higher compressive strengths than conventional concretes, above 41 Mpa (6,000 psi). The initial economic benefit arises from the ability to use fewer borepiles, columns, beams resulting in lower costs in materials, labour, transportation, and construction. The structural benefits include increased rigidity because of the increased elastic modulus and increased concrete strength that raise the allowable design stresses (Lane, S.N, and Podolny, W. 1993). This project paper emphasis will be directed mainly to the applications of ground granulated blastfurnace slag and silica fume.

1.2 Objectives

- i) To develop the concrete mix and study the effect of silica fume between the matrix which consist of ground granulated blastfurnace slag with gradually added percentage f silica fume with minimum cube strength of 60 Mpa.
- ii) To develop concrete early age strength of more than 1 Mpa within 24 hour.
- ii) To test concrete mix for compressive strength and preliminary study on permeability by Initial Surface Absorption Test (ISAT).

1.3 Scope of study

This study focuses on investigating the properties of the proposal concrete mix of high performance concrete. Among the properties investigated for such designed mixes are compressive strength, and permeability for durability while maintaining the high workability.