

MODIFICATION OF POLYETHERSULFONE INCORPORATED WITH  
POLYVINYLPIRROLIDONE-IODINE VIA PHASE INVERSION AND  
ULTRAVIOLET PHOTO-GRAFTING FOR ANTIBACTERIAL APPLICATIONS

DEVANAI A/P KANNAN

A thesis submitted in partial fulfillment of the requirements for the award of the  
degree of Master of Engineering (Bioprocess)

Faculty of Chemical  
Universiti Teknologi Malaysia

October 2012

## ACKNOWLEDGEMENT

First and foremost, I would like to thank God for giving me the strength and good health in completing my thesis. I would like to express my sincere gratitude and appreciation to my supervisor, Dr Abdul Halim Bin Mohd Yusof for all his support and guidance throughout the completion of this project.

My sincere appreciation and special thank to Mr Yakoob Sabudin for his assistance, support and help throughout the completion of my lab work. I am grateful to my senior, Khairul Anuar for his guidance and assistance towards the accomplishment of the project. My special thank to my dear friend, Nur Dianaty for her sincere help, support and encouragement throughout the year.

Last but not least, my utmost appreciation to my parents, brothers and sisters for their love, support and motivation. Thank you for the support and everything done for me, I would not be here without encouragement from you.

## ABSTRACT

Incorporation of antibacterial agents into polymeric membrane is one the widely studied surface modification. Polyethersulfone (PES) membrane incorporated with polyvinylpyrrolidone-iodine (PVP-I) were prepared using phase inversion and UV induced photo-grafting techniques. The modified PES-PVP-I membranes were characterized in term of gravimetric analysis, FT-IR analysis, FESEM analysis, water flux, contact angle, porosity measurement and antibacterial effect against *Escherichia coli* (*E.coli*) and *Bacillus subtilis* (*B.subtilis*). The high water flux indicated by PES-4 and PES-7 show an improvement by the addition of PVP-I by 52 % to 62% higher compared to original PES membrane. For the UV method, the water flux decline with the increasing of irradiation time by 31 to 35% compared to the commercial original PES membrane. PES-PVP-I membranes with 10 wt% of iodine concentration developed by phase inversion and UV photo-grafting show strong antibacterial properties using halo zone test. The highest inhibition zone of PES-PVP-I membranes produced using UV photo-grafting and phase inversions against *E.coli* were 2.30cm<sup>2</sup> and 1.88cm<sup>2</sup> and against *B.subtilis* were 0.41cm<sup>2</sup> and 0.48cm<sup>2</sup>. The results indicated that both methods used were favorable towards antibacterial properties with high inhibition zone and as well as in the improvement in water flux, contact angle and porosity of PES-PVP-I membranes compared to the original PES. This study shows that PES-PVP-I membrane suitable to be used in wide variety of antibacterial applications.

## ABSTRAK

Kemasukan antibakteria ke dalam membran polimer adalah modifikasi permukaan yang luas dikaji. Pengubahsuaian permukaan polyethersulfone (PES) membran menggunakan polyvinylpyrrolidone-iodine (PVP-I) disediakan dengan menggunakan penukaran fasa dan melalui sinaran ultraviolet (UV) photografting teknik. PES-PVP-I membran yang diubahsuai diuji dari segi gravimetrik analisis, FT-IR analisis, FESEM analisis, ketelapan air, keseimbangan isi air, keporosan dan keberkesanan antibakteria dinilai terhadap *Escherichia coli* (*E.coli*) dan *Bacillus subtilis* (*B.subtilis*). Ketelapan air yang tinggi ditunjukkan oleh PES-4 dan PES-7 menunjukkan peningkatan dengan penambahan PVP-I sebanyak 52% hingga 62% lebih tinggi daripada PES membran asal. Dengan kaedah UV, ketelapan air menurun dengan peningkatan masa sinaran sebanyak 31% hingga 35% berkurangan berbanding PES membran asal. PES-PVP-I membran dengan kepekatan 10 wt% iodine dibentuk menggunakan fasa penukaran dan sinaran UV menunjukkan ciri-ciri antibakteria yang tinggi. Zon perencatan yang tertinggi dihasilkan melalui sinaran UV dan fasa penukaran terhadap *E.coli* adalah  $2.30\text{cm}^2$  dan  $1.88\text{cm}^2$  dan *B.subtilis* adalah  $0.41\text{cm}^{-1}$  dan  $0.48\text{cm}^{-1}$ . Kedua-dua teknik menunjukkan ciri-ciri antibakteria menggalakkan dengan zon perencatan yang tinggi dan juga perubahan PES-PVP-I membran dari segi ketelapan air, keseimbangan air dan keporosan berbanding PES asal. Ini menunjukkan ia sesuai digunakan untuk pelbagai aplikasi antibakteria.

**TABLE OF CONTENTS**

<b>CHAPTER</b>	<b>TITLE</b>	<b>PAGE</b>
	<b>DECLARATION</b>	ii
	<b>ACKNOWLEDGEMENT</b>	iii
	<b>ABSTRACT</b>	iv
	<b>ABSTRAK</b>	v
	<b>TABLE OF CONTENTS</b>	vi
	<b>LIST OF TABLES</b>	ix
	<b>LIST OF FIGURES</b>	xi
	<b>LIST OF ABBREVIATIONS</b>	xiii
	<b>LIST OF APPENDICES</b>	xiv
<b>1</b>	<b>INTRODUCTION</b>	
	1.1 Research Background	1
	1.2 Problem Statement	5
	1.3 Objective of the study	6
	1.4 Scope of research	6
<b>2</b>	<b>LITERATURE REVIEW</b>	
	2.1 Membrane Definitions	8
	2.2 Membrane Classifications	10

2.3	Membrane Processes	11
2.4	Antibacterial Membrane	13
	2.4.1 Current Progress in Antibacterial Membrane	14
2.5	Method of Development and Modification of membrane	18
	2.5.1 Phase Inversion	18
	2.5.2 UV- Induced Surface Graft Polymerization	21
2.6	Materials Used	24
	2.6.1 Polyethersulfone (PES)	24
	2.6.2 Polyvinylpyrrolidone-Iodine (PVP-I)	25
2.7	Antimicrobial activity of PVP-I	28
2.8	Applications of Membrane	29
<b>3</b>	<b>MATERIAL AND METHODS</b>	
3.1	Material	30
3.2	Equipment	31
3.3	Preparation of Polyethersulfone (PES) Membrane	32
	3.3.1 Dope preparation for the phase inversion method	32
	3.3.2 Casting of membrane	33
	3.3.3 Preparation of commercial PES for UV photo-grafting	34
	3.3.4 Surface photo-grafting of PVP onto PES membrane	34
	3.3.5 Immersion in Iodine Solution	35
3.4	Characterizations of PES-PVP-I Membranes	37
	3.4.1 Degree of Modifications (DM)	37
	3.4.2 Fourier Transform Infrared Spectroscopy (FT-IR) Analysis	38

	3.4.3 Morphology of membranes	38
	3.4.4 Water Flux	39
	3.4.5 Contact angle (CA)	40
	3.4.6 Porosity	41
	3.4.7 Antibacterial activity test	41
	3.4.7.1 Preparation of culture medium	41
	3.4.7.2 Preparation of membrane antibacterial test	42
<b>4</b>	<b>RESULTS AND DISCUSSION</b>	
	4.1 Introduction	44
	4.2 Grafting analysis of PVP	45
	4.3 Morphology study	50
	4.4 Water Flux	54
	4.5 Contact angle	59
	4.6 Porosity	61
	4.7 Antibacterial activity test	63
<b>5</b>	<b>CONCLUSION</b>	
	5.1 Overall conclusion	68
	5.2 Future recommendations	69
	<b>REFERENCES</b>	70-79
	<b>APPENDICES</b>	

**LIST OF TABLES**

<b>TABLE NO</b>	<b>TITLE</b>	<b>PAGE</b>
2.1	Summary of PVP-I properties and use (International Specialty Products., 2004)	27
3.1	Equipment used for the development and characterization of membranes	31
3.2	Compositions of casting solution	33
3.3	Compositions of membrane and time exposure to UV	35
4.1	Degree of Modifications of PES-PVP at different time	45
4.2	Iodine weight percent of EDX result	53
4.3	Water flux, contact angle and porosity test of membranes developed via phase inversion	54



4.4	Water flux, contact angle and porosity test of original PES and membranes developed via UV by 5 minute exposure	56
4.5	Water flux, contact angle and porosity test of membranes developed via UV by 10 minute exposure	57
4.6	Water flux, contact angle and porosity test of membranes developed via UV by 15 minute exposure	57
4.7	Halo zone test against E.coli and B.subtilis of the unmodified and PES-PVP (2%)-I membranes developed via phase inversion	64
4.8	Halo zone test against E.coli and B.subtilis of the unmodified and PES-PVP (5%)-I membranes developed via phase inversion	64
4.9	Halo zone test against E.coli and B.subtilis of the unmodified and PES-PVP-I membranes via UV photo-grafting	65

**LIST OF FIGURES**

<b>FIGURE NO.</b>	<b>TITLE</b>	<b>PAGE</b>
2.1	Separation process by membrane (Rosmainiza, 2008)	9
2.2	Type of membrane process with different pore diameter (Richard, 2004)	12
2.3	Mechanism of formation of phase inversion membranes: a) solution 1; b) solution 2; c) primary gel; d) secondary gel; e) air-solution interface; f) skin (Kesting, 1985)	19
2.4	Mechanism of UV-irradiation and graft polymerization of a PES membrane (Zhang <i>et al.</i> ,2009).	23
2.5	Chemical structure of Polyethersulfone(Cao <i>et al.</i> , 2010)	24

2.6	Chemical structure of Polyvinylpyrrolidone-iodine (Zamora, 1986)	26
3.1	Flowchart of methodology by UV photo-grafting	36
3.2	Schematic of contact angle (Goddard et al., 2007)	40
3.3	The inhibition circle calculation (Takanobu <i>et al.</i> ,2000)	43
4.1	FT-IR spectra of a.)Commercial PES membrane b.) Grafted PES-PVP (15min grafting) c.)Grafted PES-PVP (10min grafting) d.)Grafted PES-PVP(5min grafting)	49
4.2	FESEM image of a.)200x cross section of PES b.) 200x cross section PVP flat sheet membrane, c.)200x cross section of PES-PVP(2%)-I(10%), d.)200x cross section of PES-PVP(5%)-I(10%), e.) 200x cross section of commercial PES f.) 200x cross section of PES-PVP-I modified via UV	50

**LIST OF ABBREVIATIONS**

BP	Benzophenone
CA	Contact angle
EDX	Energy Dispersive X-ray
FESEM	Field Emission Scanning Electron Microscopy
FT-IR	Fourier Transform Infrared Spectroscopy
I <sup>-</sup>	Iodide
I <sub>2</sub> <sup>-</sup>	Iodine
IO <sup>-</sup>	Hypoiodite
KBr	Kalium Bromide
L	Liter
MF	Microfiltration
MW	Molecular Weight
NA	Nutrient agar
NF	Nanofiltration
NMP	N-methyl-2-pyrrolidone
PES	Polyethersulfone
PS	Polysulfone
PVP	Polyvinylpyrrolidone
PVP-I	Polyvinylpyrrolidone-Iodine
RO	Reverse Osmosis
UF	Ultrafiltration
UV	Ultraviolet

**LIST OF APPENDICES**

<b>APPENDIX</b>	<b>TITLE</b>	<b>PAGE</b>
A.1	EDX spectrum of Iodine (a.) Phase Inversion Membrane (b.) UV modified membrane	80
A.2	FESEM image of a.)200x cross section of PES b.)1000x cross section of PES, c.)200x cross section of PES-PVP(2%)-I(10%), d.) 1000x cross section of PES-PVP(2%)-I(10%), e.)200x cross section of PES-PVP(5%)-I(10%), f.)200x cross section of PES-PVP (5%)-I(10%), g.) 200x cross section of commercial PES h.) 1000x cross section of commercial PES, i.) 200x cross section of PES-PVP-I modified via UV, j.) 1000x cross section of PES-PVP-I modified via UV	81

- A.3 Antibacterial activity PES-PVP-I membrane produced via phase inversion against *E.coli* a.) PES-1 (original PES) b.) PES-2 (PES-PVP(2 wt%)-I(2 wt%), c.)PES-3(PES-PVP(2 wt%)-I(5 wt%), d.)PES-4(PES-PVP(2 wt%)-I(10 wt%), e.) PES-5 (PES-PVP(5 wt%)-I(2 wt%), f.) PES-6 (PES-PVP(5 wt%)-I(5 wt%) and g.) PES-7(PES-PVP(5 wt%)-I(10 wt%) 83
- A.4 Antibacterial activity PES-PVP-I membrane produced via phase inversion against *B.subtilis* a.)PES-1 (original PES) b.)PES-2 (PES-PVP(2 wt%)-I(2 wt%), c.)PES-3(PES-PVP(2 wt%)-I(5 wt%), d.)PES-4(PES-PVP(2 wt%)-I(10 wt%), e.) PES-5 (PES-PVP(5 wt%)-I(2 wt%), f.)PES-6 (PES-PVP(5 wt%)-I(5 wt%) and g.) PES-7(PES-PVP(5 wt%)-I(10 wt%). 85
- A.5 Antibacterial activity of PES-PVP-I membranes modified via UV photo-grafting against *E.coli* a.) PES-8 (original PES) b.) PES-9 (PES-PVP-I(2 wt%), c.)PES-10 (PES-PVP-I(2 wt%), d.)PES-11(PES-PVP-I(2 wt%), e.) PES-12 (PES-PVP-I(5 wt%), f.) PES-13 (PES-PVPI(5 wt%) g.) PES-14(PES-PVP-I(5 wt%) h.) PES-15 (PES-PVP-I(10 wt%) i.) PES-16 (PES-PVP-I(10 wt%) j.) PES-17 (PES-PVP-I(10 wt%) 87

A.6	Antibacterial activity of PES-PVP-I membranes modified via UV photo-grafting against <i>B.subtilis</i> a.)PES-8 (original PES) b.) PES-9 (PES-PVP-I(2 wt%), c.)PES-10 (PES-PVP-I(2 wt%), d.)PES-11(PES-PVP-I(2 wt%), e.) PES-12 (PES-PVP-I(5 wt%), f.) PES-13 (PES-PVPI(5 wt%) g.) PES-14(PES-PVP-I(5 wt%) h.) PES-15 (PES-PVP-I(10 wt%) i.) PES-16 (PES-PVP-I(10 wt%) j.) PES-17 (PES-PVP-I(10 wt%)	89
A.7	Halo zone test results a.)Halo zone test against <i>E.coli</i> and <i>B.subtilis</i> of the unmodified and PES-PVP-I membranes developed via phase inversion b.) Halo zone test against <i>E.coli</i> and <i>B.subtilis</i> of the unmodified and PES-PVP-I membranes via UV photo-grafting	91

**REFERENCES**

- Abu Seman, M.N., Khayet, M., and Hilal, N. (2012). Comparison of two different UV-grafted nanofiltration membranes prepared for reduction of humic acid fouling using acrylic acid and N-vinylpyrrolidone. *Desalination*. 287, 19-29.
- Ahmad, A.L., Sarif, M., and Ismail, S. (2005). Development of an integrally skinned ultrafiltration membrane for wastewater treatment: effect of different formulations of PSf/NMP/PVP on flux and rejection. *Desalination*. 179, 257-263.
- Al-Malek, S.A., Abu Seman, M.N., Johnson, D., and Hilal, N. (2012). Formation and characterization of polyethersulfone membranes using different concentrations of polyvinylpyrrolidone. *Desalination*. 288, 31-39.
- Amirilargani, M., Sadrzadeh, M and Mohammadi, T. (2010). Synthesis and characterization of polyethersulfone membranes. *Journal of Polymer Research* 17, 363-377.
- Astaire, J.C (2002). *Microfiltration and Supercritical Fluid Extraction of Buttermilk to Concentrate Biological Lipid Messengers*. Master of Science, Faculty of the Agricultural Sciences Department California Polytechnic State University, San Luis Obispo.
- Baker, R.W. (2004). *Membrane Technology and Applications*. (2nd ed) Menlo Park, California, USA: John Wiley & Sons Ltd.



- Basri, H., Ismail, A.F., and Aziz, M. (2008). Effect of different solvent in the preparation of Polyethersulfone (PES)-Ag polymer composite. *Journal of Technology*. 49, 133-140.
- Basri, H., Ismail, A.F., Aziz, M., Nagai, K., Matsuura, T., Abdullah, M.S., and Ng, B.C. (2010). Silver-filled polyethersulfone membranes for antibacterial applications - Effect of PVP and TAP addition on silver dispersion. *Journal of Desalination* 261, 264–271.
- Bhagat, P.R., Pandey, A.K., Acharya, R., Nair, A.G.C., Rajurkar, N.S. and Reddy, A.V.R. (2008). Molecular iodine preconcentration and determination in aqueous samples using poly(vinylpyrrolidone) containing membranes. *Journal of Talanta* 74, 1313–1320.
- Bhattacharya, A., Rawlins, J.W., And Ray, P. (2009). *Polymer Grafting and Crosslinking*. (1<sup>st</sup> ed). Hoboken, New Jersey: John Wiley & Sons, Inc.
- Black, A.P., Keirn, Smith, J.J., Dykes, G.M., and Harlan, F.E. (1970). The Disinfection of Swimming Pool Water. Part II. A Field Study of the Disinfection of Public Swimming Pools. *A.J.P.H.* 60, 740-750.
- Bonilla, A.M and Garcia, M.F. (2012). Polymeric materials with antimicrobial activity. *Journal of Progress in Polymer Science* 37, 281-339.
- Boom, R.M., Wlenk, I.M., Boomgaard, T.V.D., and Smolders, C.A. (1992). Microstructures in phase inversion membranes. Part 2. The role of a polymeric additive. *Journal of Membrane Science*. 73, 277-292.

- Bruggen, B.V. (2009). Chemical Modification of Polyethersulfone Nanofiltration Membranes: A Review. *Journal of Applied Polymer Science*. 114, 630–642.
- Cao, X.L., Tang, M., Liu, F., Nie, Y.Y., and Zhao, C.S. (2010). Immobilization of silver nanoparticles onto sulfonated polyethersulfone membranes as antibacterial materials. *Journal of Colloids and Surfaces B: Biointerfaces* 81, 555–562.
- Chakrabarty, B., Ghoshal, A.K., and Purkait, M.K. (2008). Preparation, characterization and performance studies of polysulfone membranes using PVP as an additive. *Journal of Membrane Science*. 315, 36-47.
- Cheryan, M. (1998). *Ultrafiltration and Microfiltration Handbook*. (2nd ed). Lancaster : Technomic Publishing Corporation.
- Cloete, T.E., and Brözel, V.S. (1992). Practical Aspects of Biofouling Control in Industrial Water Systems. *Journal of International Biodeterioration & Biodegradation*. 29, 299-341.
- Deng, J.P., Wang, L., Liu, L.Y., and Yang, W. (2009). Developments and new applications of UV-induced surface graft polymerizations. *Journal of Progress in Polymer Science*. 34, 156 -193
- Fang, B.H., Ling, Q., Zhao, W.F., Ma, Y., Bai, P., Wei, Q., Li, H.F., and Zhao, C.S. (2009). Modification of polyethersulfone membrane by grafting bovine serum albumin on the surface of polyethersulfone/ poly(acrylonitrile-co-acrylic acid) blended membrane. *Journal of Membrane Science* 329, 46–55.

- Flores, C.Y., Diaz, C., Rubert, A., Benitez, G.A., Moreno, M.S and Fernandez Lorenzoe de Mele, M.A., Salvarezza, R.C., Schilardi, P.L. and Vericat, C. (2010). Spontaneous adsorption of silver nanoparticles on Ti/TiO<sub>2</sub> surfaces. Antibacterial effect on *Pseudomonas aeruginos*. *Journal of Colloid and Interface Science*, 350, 402-408.
- Gao, B.J., Wang, Z.B., Liu, Q., and Du, R.K. (2010). Immobilization of povidone-iodine on surfaces of silica gel particles and bactericidal property. *Journal of Colloids and Surfaces B: Biointerfaces*. 79, 446-451.
- Goddard, J.M., and Hotchkiss, J.H. (2007). Polymer surface modification for the attachment of bioactive compounds. *Journal of Progress in Polymer Science*. 32, 698-725.
- Homayoonfal, M., Akbari, A., and Mehrnia, M.R. (2010). Preparation of polysulfone nanofiltration membranes by UV-assisted grafting polymerization for water softening. *Desalination*. 263, 217-225.
- He, D., Susanto, H., and Ulbricht, M. (2009). Photo-irradiation for preparation, modification and stimulation of polymeric membranes. *Journal of Progress in Polymer Science*. 34, 62-98.
- Hu, B., Liu, L., Matar, O.K., Angeli, P., Hewitt, G.F., and Perez de Ortiz, E.S. (2006). Investigation of Phase Inversion of Liquid-Liquid Dispersions in Agitated Vessels. *Journal of Tsinghua Science and Technology*. 11(2): 202-206

- Ibrahim S.I., Adham, A., and Gilbert,P. (1986). Effect of polyvinylpyrrolidone molecular weight upon the antimicrobial activity of povidone-iodine antiseptics. *International Journal of Pharmaceutics*. 34, 45-49.
- Idris, A. and Ahmed, I. (2007). A production of polyethersulfone asymmetric membranes using mixture of two solvents and lithium chloride as additive. *Journal of Technology*. 47, 25-34.
- Idris, A., Zain, N.M., and Noordin, M.Y. (2007). Synthesis, characterization and performance of asymmetric polyethersulfone (PES) ultrafiltration membranes with polyethylene glycol of different molecular weights as additives. *Desalination*. 207, 324-339.
- International Specialty Product. (2004). PVP-IODINE, Povidone Iodine Antiseptic Agent. U.S.A.: International Specialty Product
- Kaeselev, B., Kingshottb, P. and Jonsson, G. (2002). Influence of the surface structure on the filtration UV-modified PES membranes. *Desalination*. 146, 265-271.
- Kenawy, E., Worley, S.D. and Broughton, R. (2007). The Chemistry and Applications of Antimicrobial Polymers: A State-of-the-Art Review. *Journal of Biomacromolecules*. 8(5), 1359-1384.
- Kesting, R.E. (1985). *Synthetic Polymeric Membranes*. 2nd ed. New York: McGraw Hill.

- Madaeni, S.S. (1998). The Applications of Membrane Technology for Water Disinfection. *Water Research*. 33(2), 301-308.
- Mahendra, S., Li, Q., Lyon, D.Y., Brunet, L and Alvarez, P.J.J. (2009). Nanotechnology- Enabled Water Disinfection and Microbial Control: Merit and Limitations. *Journal of Nanotechnology Applications for Clean Water*. 157 – 166.
- Marchese, J., Ponce, M., Ochoa, N.A., Pradanos, P., Palacio, L., and Hernandez, A. Fouling behaviour of polyethersulfone UF membranes made with different PVP. *Journal of Membrane Science*. 211, 1–11.
- Mizukami, Y., and Yokoyama, T. (1993). A Study on the Bactericidal Activity. of Povidone-Iodine- Morphological Changes in *Eseherichia coli* Caused by Povidone-Iodine. *Journal of Medical Electron Microscopy*. 26 (2), 111-11.
- Mu, L.J., and Zhao, W.Z. (2009). Hydrophilic modification of polyethersulfone porous membranes via a thermal-induced surface crosslinking approach. *Journal of Applied Surface Science*. 255, 7273–7278.
- Ng, L.Y., Mohammad, A.W., Leo, C.P., and Hilal, N. (2010). Polymeric membranes incorporated with metal/metal oxide nanoparticles: A comprehensive review. *Desalination*. 1-19.
- Nigmatullin, R., Konovalova, V. and Pobigay, G. (2008), Development of Antimicrobial Membranes via the Surface Tethering of Chitosan. *Journal of Applied Polymer Science*. 111, 1697–1705.

- Peeva, P.D., Pieper, T. and Ulbricht, M. (2010). Tuning the ultrafiltration properties of anti-fouling thin-layer hydrogel polyethersulfone composite membranes by suited crosslinker monomers and photo-grafting conditions. *Journal of Membrane Science*. 362, 560-568.
- Porter, M.C. (1990). Ultrafiltration. In: Porter, M.C. *Handbook of Industrial Membrane Technology*. New Jersey: Noyes Publication. 136-259.
- Rabea, E.I., Badawy, M.E.T., Stevens, C.V., Smagghe, G., and Steurbaut, W. (2003). Chitosan as Antimicrobial Agent: Application and Mode of Actions. *Journal of Biomacromolecules*. Vol 4 (6), 1457 -1465.
- Rahimpour, A., and Madaeni, S.S. (2010). Improvement of performance and surface properties of nano-porous polyethersulfone (PES) membrane using hydrophilic monomers as additives in the casting solution. *Journal of Membrane Science*. 360, 371–379.
- Rahimpour, A. (2011). UV photo-grafting of hydrophilic monomers onto the surface of nano-porous PES membranes for improving surface properties. *Desalination*. 265, 93-101.
- Ranran, F., Chanchan, W., Xiaochen, X., Fenglin, Y., Guangjing, X. and Tao, J. (2011). Highly effective antifouling performance of N-vinyl-2-pyrrolidone modified polypropylene non-woven fabric membranes by ATRP method. *Journal of Membrane Science* 369. 233–242.

- Ravindra, S., Murali Mohan, Y., Narayana Reddy, N., and Mohana Raju, K. (2010). Fabrication of antibacterial cotton fibres loaded with silver nanoparticles via “Green Approach”. *Journal of Colloids and Surfaces A: Physicochem. Eng. Aspects*. 367, 31–40.
- Ritchie, S.M.C. (2003). Polymer grafted membranes. *Polymeric and Biofunctional Membranes*. 299-327.
- Ridway, H.F. (1988). *Microbial Adhesion and Biofouling of Reverse Osmosis*. In *Reverse Osmosis Technology*. Parekh, B.S. (ed.), Marcel Dekker, Inc., United States of America, 429–476.
- Sarif, M. (2005). Development of Integrally Skinned Polysulfone Ultrafiltration Membrane : Effect of Casting Parameters. Thesis Master of Science.
- Scott, K., and Hughes, R. (1996). *Industrial Membrane Separation Technology*. (1st ed). Bishopbriggs Glasgow, UK: Blackie Academic & Profesional.
- Susanto, H., Balakrishnan, M. and Ulbricht, M. (2007). Via Surface Functionalization by Photograft Copolymerization to Low-Fouling Polyethersulfone-Based Ultrafiltration Membranes. *Journal of Membrane Science*. 288, 157-167.
- Selvaggi, G., Monstrey, S., Landuyt, K.V., Hamdi, M., and Blondeel, Ph. (2003). The Role of Iodine in Antisepsis and Wound Management : A Reappraisal. *Acta chir belg*, 103, 241-247.

- Taniguchi, M., Pieracci, J., Samsonoff, W.A., and Belfort, G. (2003). UV-assisted graft polymerization of synthetic membranes: mechanistic studies. *Journal of Chemistry Materials*. 15, 3805–3812.
- Xing, C.M., Deng, J.P., and Yang, W.T. (2005). Synthesis of Antibacterial Polypropylene Film with Surface Immobilized Polyvinylpyrrolidone-Iodine Complex. *Journal of Applied Polymer Science*. 97, 2026–2031.
- Wang, H., Yu, T., Zhao, C., and Du, Q. (2009). Improvement of Hydrophilicity and Blood Compatibility on Polyethersulfone Membrane by Adding Polyvinylpyrrolidone. *Fibers and Polymers*. 10(1), 1-5.
- Yamagishi, H., Crivello, J.V., and Belfort, G. (1995). Development of a novel photochemical technique for modifying poly(arylsulfone) ultrafiltration membranes. *Journal of Membrane Science*. 105, 237-247.
- Yang, Y.F., Hu, H.Q., Li, Y., Wan, L.S and Xu, Z.K. (2011). Membrane Surface with antibacterial property by grafting polycation. *Journal of Membrane Science*. 1-10.
- Yean, L.S. (2008). Effect Of Bore Fluid And Post Treatment On Polyethersulfone Ultrafiltration Hollow Fiber Membrane. Thesis Master of Engineering (Bioprocess).
- Yi, G.W., Wei, J.J., An, Q., Yuan, F.L., Jin, C.C. and Guang, T.L. (2009). Multi-action antibacterial nanofibrous membranes fabricated by electrospinning: an excellent system for antibacterial applications. *Journal of Nanotechnology*. 20, 245101.



- Zamora, J.L. (1986). Chemical and Microbiologic Characteristics Povidone-Iodine Solutions. MD, Department of Surgery, State University of New York. *American Journal of Surgery*. 151, 400-406.
- Zeman, L.J. and Zydney, A.L. (1996). *Microfiltration and Ultrafiltration, Principle and Applications*. (1st ed). New York: Marcel Dekker Inc.
- Zhang, M., Nguyen, Q.T., and Ping, Z. (2009). Hydrophilic modification of poly (vinylidene fluoride) microporous membrane. *Journal of Membrane Science*. 327, 78-86.
- Zhao, Z.P., Li, J., Wang, D., and Chen, C.X. (2005). Nanofiltration membrane prepared from polyacrylonitrile ultrafiltration membrane by low temperature plasma: grafting of N-vinylpyrrolidone in aqueous solution. *Desalination*. 184, 37-44.
- Zhao, S., Z. Wang, X. Wei, X. Tian, J. Wang, S. Yang, and S. Wang. Comparison study of the effect of PVP and PANI nanofibers additives on membrane formation mechanism, structure and performance. *Journal of Membrane Science*, 2011. 385-386(0): 110-122.