

An Economical Production of Polyethersulfone Asymmetric Membranes Using Mixture of Two Solvents and Lithium Chloride as Additive

Ani Idris* and Iqbal Ahmed

*Department of Bioprocess Engineering, Faculty of Chemical and Natural Resources Engineering,
Universiti Teknologi Malaysia, 81310 UTM Skudai, Johor, Malaysia.*

Abstract

Polyethersulfone (PES) asymmetric membranes were prepared by the wet/dry phase inversion process. Membrane dope formulation consisting of commercial-grade PES resin and a mixture of two different solvents dimethyleformamide (DMF) and commercial grade acetone with control ratio 3.47 were prepared. Tap water was used as the coagulant bath at room temperature. With a focus on the PES solvent mixtures DMF/acetone economical system, the effect of lithium chloride anhydrous (LiClH₂O) as additive on the membrane's performance was investigated. The performance of the PES membranes were evaluated in terms of PEG separation and its molecular weight determined. The PES membranes prepared from the two solvent mixture systems with LiClH₂O additive possess excellent hydrophilic properties exhibited by the high permeation rates. Its solute rejection rates were also superior compared to the membrane prepared from single solvent without LiClH₂O additive.

Key Words: Asymmetric membranes, dry/wet phase inversion, lithium chloride anhydrous.

1.0 Introduction

Ultrafiltration, a novel and powerful pressure-driven separation technology, has been widely used in wastewater treatment and food industry [1, 2] to concentrate or fractionate protein and aqueous solutions. During ultrafiltration, the smaller suspended particles and dissolved macromolecules (surface pore size in the range of 50 to 1 nm) pass through the membranes [3], while the bigger molecules are mostly rejected. Some of the rejected molecules adsorb or deposit on membrane surface causing considerable membrane fouling [4].

The efficiency as well as the economics of the various industrial processes can be greatly improved if the membrane processes are suitably integrated in the exiting process, particularly, to control membrane structure and membrane performance. This objective is not easy to achieve because membrane structure and performance depend on different factors such as polymer choice, solvent and nonsolvent choice, composition and temperature of coagulant, and casting solution [5]. Solvent/non-solvent mixture changes the solubility parameter of the solvent system thus changing the polymer-solvent interaction in the ternary-phase polymer system, which changes the polymer morphology of surface layer and sub-layer [6, 7].

* Corresponding author: Tel: +607-5535603, Fax: 607-5581463, Email: ani@fkkksa.utm.my

The physical factors in the ternary polymer system [6, 7] responsible for the change in morphology are heat of mixing of solvent and non-solvent, and polymer–solvent interaction which depends on the difference in solubility parameter. Moreover, a mixture of polar, aprotic solvent and volatile solvent such as dioxane and acetone causes rapid evaporation on the surface, leading to the formation of a dense layer on the surface [8]. The physical factors include solvents evaporation time, temperature and humidity [9].

Currently there is a possibility of enhancing membrane performance beyond the generally recognized intrinsic value for the amorphous polymer. This has been accomplished in a number of different ways for various polymers: polysulfone (PSf), polyethersulfone (PES), polycarbonate (PC), polyimide (PI), polyamide (PA) and cellulose acetate (CA) [10, 11]. Hydrophobic materials show excellent mechanical stability in aqueous environment. This attribute is very attractive for them to be used as membrane materials and should exhibit enough affinity to water so that it can be preferentially adsorbed into the membrane, leading to good membrane performance in terms of a high productivity and high selectivity. [12]. PES, an important engineering thermoplastic possessing favorable mechanical properties and thermo oxidative stability [13], is a closely related derivative of polysulfone which is totally devoid of aliphatic hydrocarbon groups and has a high glass transition temperature of 230°C [14]. It is an excellent UF membrane material because of its film and membrane forming properties and high mechanical and chemical stability. In addition to being commercially available and relatively inexpensive, it is one of the most widely used polymers for making UF membranes [15].

In order to obtain membranes with special properties, additional additives can be dissolved in the casting solution [16]. The role of these additives is to create a spongy membrane structure but prevents the formation of macrovoid, enhances pore formation, improves pore interconnectivity and/or introduces hydrophilicity. Generally, hydrophilic structures are obtained by the addition polyvinylpyrrolidone (PVP). Other frequently used additives are: glycerol, alcohols, dialcohols, water, polyethylene glycols (PEG), polyethylene oxide (PEO), LiCl and ZnCl₂ [17, 18, 19].

Qualitatively addition of lithium chloride to the casting solution of poly(amic-acid) solution in DMF results in complexes between lithium chloride and DMF, resulting in reduced solvent power and increased viscosity and transient cross-links, as shown by dynamic light scattering [20]. Inorganic salts are known to form complexes with the carbonyl group in polar aprotic solvent via ion–dipole interaction [21]. The polymer aggregates which form due to reduced solvent power result in sponge-like structure and hinder macro-void formation during phase-inversion. In most cases, the concentration of LiClH₂O is kept less than 3%.

In this study the effect of LiClH₂O additive greater than 3% using a two solvent system is investigated. The polymer solution, which consists of polyethersulfone in a mixture of polar aprotic solvents DMF and volatile solvent acetone; additive lithium chloride anhydrous is prepared. The performances of these membranes were compared with those prepared without volatile acetone and LiClH₂O. The performances of the membranes were evaluated using various molecular weight polyethylene glycols, PEG. Its molecular weight cut off and flux rates are determined [21].

2.0 Experimental

2.1 Materials

Commercial grade Polyethersulfone (PES) in resin form is obtained from BASF. Analytical grade N, N-dimethyleformamide DMF [HCON (CH₃)₂, M=73.10 g/mol] were analytical grade purchased from Merck (Merck Germany). Inorganic salt additive Lithium Chloride (42.4) analytical grade, were procured from BDH and commercial grade acetone was used without further purification. Tap water was used as the coagulation bath. For UF experiments, PEG with various molecular weights (PEG200, PEG 400, PEG 600, PEG 1000, PEG 3000, PEG 6000 and PEG 10,000), were obtained from Fluka.

2.2 Dope Preparation

Different dope solutions were prepared. The polymer concentration was fixed at 20% as shown in Table 1. In this study, Sharp domestic microwave oven model: R-4A53 with the following specifications: rated power out put of 850 watts (240V~50 Hz), operation frequency of 2450 MHz is used. A 500 ml Schott Duran is used as the sample reaction vessel at atmospheric pressure. Mercury thermometer was used manually to control the temperature at every 20 sec. The temperature of the dope solutions was kept at 85-95 °C for dope solutions 1 and 3, 65-70 °C for dope solution 2 as shown in Table 2. Heating time by microwave was 10 minutes. The absolute viscosities of dope solutions 1, 2 and 3 were measured using Brookfield Viscometer (DV-II) at 28 °C

Table 1: Dope solution compositions.

| Dope Solution | Composition in Wt. % | | | |
|---------------|----------------------|-----|---------|----------------------|
| | PES | DMF | Acetone | LiClH ₂ O |
| 1 | 20 | 80 | 0 | 0 |
| 2 | 20 | 59 | 17 | 4 |
| 3 | 20 | 76 | 0 | 4 |

2.3 Determination of Permeation Flux and Solutes Rejection

The performances of the various membranes were evaluated in terms of pure water permeation fluxes (PWP), solvent permeation fluxes (PR) and solute rejection rate (SR) in a test cell described elsewhere [22]. A minimum of three flat sheet samples was prepared for each technique and the average data are tabulated. Pure water permeation fluxes (PWP) and solutes water permeation fluxes (PR) of membranes were obtained as follows:

$$J = \frac{Q}{\Delta T \times A} \quad (1)$$

where J is the permeation flux of membrane for PEG solution (L m⁻² h⁻¹) or pure water and Q is the volumetric flow rate of permeate solution.

Solute rejection of membranes were evaluated with various molecular weight PEG solutions ranging from 600 to 10000 kDa at 4.5 bar. The concentration PEG solution used is 500ppm. The concentration of the feed and permeate solution were determined by the method described as follows:

Reagent A: 5% (w/v) BaCl₂ in 1 N HCl (100 ml)

Reagent B: 2% (w/v) KI diluted 10 times + 1.27g I₂.

Four milliliters of sample solution was added to 1 ml reagent A. To this mixture 1 ml of reagent B was added. Color was allowed to develop for 15 min at room temperature, and adsorption was read using a spectrophotometer at 535 nm against a reagent blank [21]. The membrane rejection (*R*) is defined as

$$SR = 1 - \frac{C_p}{C_f} \times 100 \quad (2)$$

where *C_f* and *C_p* are the polyethylene glycol concentration in the feed solution and permeate solution, respectively. The concentration of PEG was determined based on absorbency in a UV-spectrophotometer at a wavelength of 535 nm.

2.4 Scanning Electron Microscope

For morphology study, the membranes were immersed in liquid nitrogen and fractured to obtain neat cross- sections. These samples were then attached to a carbon holder and sputtered with gold to prevent charging up of the surface by the electron beam. A narrow beam of electrons with kinetics energies in order of 1 – 25kV hits the membrane sample, and low- energy electrons were liberated from the atoms in the surface to create the image on the micrograph. Cross sections of the hollow fiber membranes images were obtained using the SUPRA 35VP FE- SEM.

3.0 Results and Discussion

3.1 Effect of lithium chloride (LiClH₂O) and acetone on viscosity of dope solution

Viscosity is considered as one of the important parameters influencing the exchange rate between solvent and non-solvent during the phase inversion process [22]. Therefore, the absolute viscosities of dope solutions 1, 2 and 3 are listed in Table 2. Absolute viscosities of PES solutions in a single solvent without additive (1) is the lowest compared to those prepared in a mixture of solvents (2) and that containing additives. The presence of 4 % additive lithium chloride has increased the viscosity by almost 6 times. However when part of the DMF is replaced by acetone the viscosity of the dope solution decreases. The presence of salts concentration used was kept to 4 wt% because of the solubility of salts in aprotic solvents and organic solvents [23].

Table 2 Dope solution preparation time and viscosities.

| Dope solution | Preparation time (hrs) | Viscosity at 28 °C (cps) |
|---------------|------------------------|--------------------------|
| 1 | 0.5 at 85-95 °C | 175 |
| 2 | 0.5 at 65-75 °C | 800 |
| 3 | 0.5 at 85-95 °C | 1100 |

3.2 Performance of the membranes

The performances of the membranes produced from the various solutions were depicted in Figures 1 and 2. It is observed that the membranes produced from dope solution 3 containing LiClH₂O exhibits highest pure water permeation (J_{pw}) and permeate flux (J_s) rates compared to those produced by from dope solutions 1 and 2. The use of acetone has also a positive influence on the membrane performance shown by the improved permeation rates compared to dope solution 1. However its permeation rates are slightly lower compared to those prepared from dope solution 3. The pure water permeation and permeation flux for membranes 2 and 3 were approximately 50 % higher than membrane 1 which means increase in productivity.




Figure 1 Pure water permeation flux (J_{pw}), permeate rates (J_s) versus molecular weights of PEG of the various membranes

Apparently membranes produced from the dope solution 2 containing both the acetone and additive exhibits highest rejection rate with molecular cut off (MWCO) at 90% of approximately 2000 kDa. Membrane 3 has rejection rates higher than membrane 1 with MWCO close to 6000 kDa. Membrane 1 that does not contain any acetone and additive shows MWCO of about 8000kDa and very low flux rates.

It appears that the presence of LiClH₂O has improved the hydrophilic properties of the membrane thus improving the permeation flux of the membranes. It seems that LiClH₂O acts as a pore reducer observed by the reduction in the MWCO of the membranes. In addition the presence of acetone has not only improved the membranes performance in terms of both flux and rejection rates but also reduce the production cost of the membranes because it is a cheaper solvent compared to DMF.




Figure 2 PEG rejection rate versus molecular weights of PEG of the various membranes


3.3 Membrane Morphologies

The cross section structures of the membranes produced from the various dope solutions are shown in Figure 3 at a magnification of 500X. Previous investigations have shown that casting solution characteristics and formulations have a direct influence on asymmetric membrane formation and structure [8, 9]. An examination of the cross-sectional structures revealed that asymmetric membrane 1 has a thick skin dense skin layer with many macrovoids. The very fine finger like structure developed into large macrovoids towards the bottom. The thick skin layer creates high resistance in flow thus explaining for the low flux rates.


Upon comparing this morphology with membrane 2, the presence of LiClH₂O has obviously altered and affects the membranes. Membrane 2 has a very fine and consistent spongy structure with a very thin skin layer which is hardly visible thus explaining for the high rejection rates and improved permeation flux rates. No finger like structure is observed except for some isolated macrovoids. A slightly coarse spongy structure which appears to be very well interconnected is also observed in Figure 3 and this explains for the high permeation rates. However the skin layer is not as thin as membrane 2 thus explaining for the lower rejection rates.

Hydrophilic structures are obtained by the addition of additives LiClH₂O. The presence of the nonsolvent additives acetone in the polyethersulfone membranes also affects the separation properties of membranes. It is believed that that during the dope preparation process in the


microwave oven; the irradiation process could have caused some breakages in the bonds and realign the molecular structure of polymer. The presence of the free chlorine molecules could have improved the hydrophilic structure of the membranes thus influenced the permeation properties of membrane performance. With the addition of both acetone and lithium chloride the permeation rates are only slightly reduced but the rejection rates improved tremendously.



Membrane 1



Membrane 2



Membrane 3

Figure 3 Scanning electronic micrographs at 500 X magnification of cross section structure of the PES flat sheet membranes prepared from the three dope solutions

4.0 Conclusion

In summary membranes produced from dope solutions containing lithium chloride salts and acetone are superior in terms of permeation flux rates, rejection rates and quality of membranes compared to those membranes prepared without these additives. The addition of LiClH_2O and acetone to PES-DMF casting solutions has a significant effect on both solution properties as observed from its viscosities. The disappearance of the macrovoids in the membrane structure have improved the membranes performance and its mechanical strength. The results indicate that LiClH_2O interacts very strongly with DMF and acetone under microwave radiation leading to the formation of LiClH_2O -DMF-acetone complexes and, hence, retain in the solvation power of DMF for PES. With the addition of LiClH_2O additive alone in the casting solution, membrane porosity increases producing high permeation rate membranes. However with the addition of both LiClH_2O and acetone, membrane porosity

decreases, asymmetric skin layer becomes very thin, producing membranes with slightly lower permeation rates but excellent the rejection rate.

Acknowledgements

Financial support from the Ministry of Science, Technology and Environment through the IRPA funding vote no 74246 and 74170 is gratefully acknowledged.

References

- [1] Jönsson, A. S. and Trägårdh, G. 1990. Ultrafiltration applications. *Desalination* 77 (1): 135–179
- [2] Afonso, M. D and Bohórquez, R. 2002. Review of the treatment of seafood processing wastewaters and recovery of proteins therein by membrane separation processes - prospects of the ultrafiltration of wastewaters from the fish meal industry. *Desalination* 142 (1): 29–45
- [3] Chaturvedi, B. K., Ghosh, A. K., Ramachandran, V., Trivedi, M. K., Hanra, M. S. and Misra, B. M. 2001. Preparation, characterization and performance of polyethersulfone ultrafiltration membranes *Desalination* 133 (1): 31-40
- [4] Huisman, I. H., Prádanos, P. and Hernández, A. 2000. The effect of protein–protein and protein–membrane interactions on membrane fouling in ultrafiltration. *Journal of Membrane Science*. 179 (1-2): 79–90.
- [5] Xu, Z. L. and Qusay, F. A. 2004 Effect of polyethylene glycol molecular weights and concentrations on polyethersulfone hollow fiber ultrafiltration membranes. *Journal of Applied Polymer Science*. 91(5): 3398–3407
- [6] Yanagishita, H., Nakane, T. and Yoshitome, H. 1994. Selection criteria for solvent and gelation medium in the phase inversion process. *Journal of Membrane Science*. 89(3): 215-221,
- [7] Matsumoto, K., Xu, P. and Nishikimi, T. 1994. Gas permeation of aromatic polyimides. I. Relationship between gas permeabilities and dielectric constants *Journal of Membrane Science* 81(1-2): 15-22.
- [8] Baker, R.W. 1971. Process for making high flow anisotropic membranes. *US Patent*. 3567810
- [9] Mulder, M. 1999. Basic Principles of Membrane Technology, Kluwer Academic Publishers, Dordrecht,
- [10] Sivakumar, M., Mohan, D. R., and Rangarajan, R. 2006. Studies on cellulose acetate-polysulfone ultrafiltration membranes: II. Effect of additive concentration. *J. Membrane Science*, 268(2): 208–219
- [11] Cheng, Kwok-Shun; Gates, T. Dean; Yen, Larry Y. and Patel, Rajnikant B. 2000. Skinned hollow fiber membrane and method of manufacture. *United States Patent* 6921482
- [12] Huang, R. Y. M., Shao, P., Feng, X. and Burns, C. M. 2001. Pervaporation separation of water/isopropanol mixture using sulfonated poly(ether ether ketone) (SPEEK) membranes: transport mechanism and separation performance. *Journal of Membrane Science* 192 (1-2): 115–127
- [13] Guan, R., Cuihua, H. D., Jianhong, L., Liu and Xu, J. 2006. Effect of casting solvent on the morphology and performance of sulfonated polyethersulfone membranes. *J. Membrane Science* 277 (1-2): 148–156
- [14] Coplan, M. J.; Gotz, G. 1983 *U. S. Patent*. 4,413,106
- [15] Kim, I. C. J., Choi, G. and Tak, T. M. 1999. Sulfonated polyethersulfone by heterogeneous method and its membrane performances. *Journal of Applied Polymer Science*. 74(8): 2046–2055
- [16] Barth, C., Gonçalves, M. C., Pires, A. T. N., Roeder, J. and Wolf, B. A. 2000. Asymmetric polysulfone and polyethersulfone membranes: effects of thermodynamic conditions during formation on their performance. *Journal of Membrane Science* 169 (2): 287–299
- [17] Kesting, R. E. 198). Synthetic Polymeric Membranes: A Structure Perspective, 2nd ed; Wiley: New York.
- [18] Munari, S., Bottino, A., Capannelli, G., Moretti, P. and Bon, P. P. 1988. Preparation and characterization of polysulfone-polyvinylpyrrolidone based membranes. *Desalination*. 70(1-3): 265-275.
- [19] Kraus, M. A.; Nemas, M.; Frommer, M. A. 1979. The effect of low molecular weight additives on the properties of aromatic polyamide membranes. *Journal of Applied Polymer Scienc* 23(2): 445-452.
- [20] Lee, H. J., Won, J., Lee, H. and Kang, Y. S., 2002. Solution properties of poly (amic acid)–NMP containing LiCl and their effects on membrane morphologies. *Journal of Membrane Science*. 196 (2): 267–277.
- [21] Ashutosh D. Sabde, M.K.Trivedi, V. Ramachandran, M.S. Hanra. 1997. Casting and characterization of cellulose acetate butyrate based UF membranes. *Desalination* 114(3): 223-232
- [22] Park, J. S., Kim, S. K. And Lee, K. H. 2000. Effect of ZnCl₂ on Formation of Asymmetric PEI Membrane by Phase Inversion Process. *Journal of Industrial and Engineering Chemistry*. 6(2): 93-99
- [23] Guiver, Michael D.; Tremblay, Andre Y.; Tam, Chung M. 1990. Method of manufacturing a reverse osmosis membrane and the membrane so produced. *US Pat#*. 8494159.