

MECHANICAL AND THERMAL PROPERTIES OF POLY(METHYL
METHACRYLATE)-GRAFTED-OIL PALM EMPTY FRUIT BUNCH /TALC
HYBRID FILLED POLY(VINYL CHLORIDE) COMPOSITES

NOOR IZYAN SYAZANA BINTI MOHD YUSOFF

A thesis submitted in fulfillment of the
requirements for the award of the degree of
Master of Engineering (Polymer)

Faculty of Chemical Engineering
Universiti Teknologi Malaysia

MARCH 2013

*For my beloved ayah, ibu, kak yong, abg ngah, adik and al hafiz who have been
supporting me all this time.....*

ACKNOWLEDGMENT

First and foremost I would like to offer my unreserved gratitude and praises to Almighty Allah S.W.T for His generous blessing and the undying strength bestowed upon me throughout the course of this research. Thank you to my supervisor, Associate Prof. Dr. Aznizam Bin Abu Bakar and my co-supervisor Prof. Dr. Haji Azman Bin Hassan for the constant encouragement, guidance, support and ideas offered.

My special appreciation goes to my beloved parents; Tn Haji Mohd Yusoff Bin Omar and Pn Hajjah Bariah Binti Maun, and my siblings for their endless love, inspiration, motivation and help during the research. I also like to thank my fellow colleagues especially Al Hafiz, Nadia, Waqina, Salisa and Nurul Nadiah who have been such a wonderful supporters and motivators.

This study will not be accomplished without finance and therefore I would like to express my appreciation to the Malaysia government, Ministry of Higher Education under the FRGS grant (vote 78612) and Universiti Teknologi Malaysia.

I also gratitude to all the laboratory staffs of Polymer Engineering Department, Faculty of Chemical Engineering especially Encik Azri, Encik Izad, Encik Suhee Tan, Cik Zainab and Encik Nordin for helping me throughout the research. My sincere appreciation also extends to all my colleagues, lecturers and those who are not mentioned here that had provided guidance and assistance through the entire research period.

ABSTRACT

The aim of this study is to investigate the mechanical and thermal properties of single and hybrid fillers filled poly(vinyl chloride) (PVC) composites. Graft copolymerization of poly(methyl methacrylate) (PMMA) onto oil palm empty fruit bunch (OPEFB) was carried out under nitrogen environment using the free radical initiation technique. Soxhlet extraction was used to remove the PMMA homopolymer from the grafted copolymer. The presence of PMMA functional groups in Fourier transform infra red (FTIR) spectra of grafted OPEFB at peak around 1730 cm^{-1} proved that grafting process was successfully done. The single fillers (grafted OPEFB, ungrafted OPEFB and talc) and hybrid fillers (grafted OPEFB/talc and ungrafted OPEFB/talc) loadings from 0 to 20 phr were pre-mixed with PVC using a high speed mixer. Methyl butadiene styrene (MBS) impact modifier was also added at 10 phr for the impact strength study. The dried blend formulations were milled into sheets using a two roll mill at $170\text{ }^{\circ}\text{C}$ and then hot pressed at $190\text{ }^{\circ}\text{C}$. The tensile, flexural, impact strength and elongation at break of hybrid composites decreased as the filler content increased. Both, the tensile and flexural modulus of the hybrid composites are increased tremendously compared to the single composites. Adding MBS increased the impact strength of the single and hybrid composites. Differences in surface morphology between the grafted and ungrafted OPEFB were observed. The glass transition temperature (T_g) of the hybrid composites shifted to higher temperature compared to single composites. The storage modulus of talc filled PVC showed the highest storage modulus compared to other composites. Hybrid PVC composites had better thermal stability than single composites. The increase of water resistance of the hybrid composites proved good filler-matrix interaction. Overall, the study showed that the hybrid PVC composites had good mechanical and thermal properties compared to the single filler PVC composites.

ABSTRAK

Tujuan kajian ini adalah untuk mengkaji sifat-sifat mekanikal dan terma komposit poli(vinil klorida) (PVC) berpengisi tunggal dan hibrid. Pempolimeran cangkukan poli(metil metakrilat) (PMMA) ke atas tandan kosong buah kelapa sawit (OPEFB) telah dijalankan dalam keadaan nitrogen dengan menggunakan teknik permulaan radikal bebas. Penyarian Soxhlet digunakan untuk membuang homopolimer PMMA. Kehadiran kumpulan berfungsi PMMA pada spektra infra merah transformasi Fourier (FTIR) OPEFB tercangkuk sekitar 1730 cm^{-1} membuktikan cangkukan telah berjaya dilakukan. Kandungan pengisi tunggal (pengcangkukan OPEFB, tanpa pengcangkukan OPEFB dan talkum) dan hibrid (pengcangkukan OPEFB/talkum dan tanpa pengcangkukan OPEFB/talkum) dari 0 sehingga 20 phr telah dicampurkan dengan PVC menggunakan pengisar berkelajuan tinggi. Pengubahsuaian impak metil butadiena stirena (MBS) dicampur sebanyak 10 phr bagi kajian kekuatan hentaman. Campuran formulasi adunan kering kemudiannya dijadikan kepingan menggunakan pengguling berkembar pada suhu $170\text{ }^{\circ}\text{C}$ dan dimampatkan pada $190\text{ }^{\circ}\text{C}$. Kekuatan tegangan, lenturan dan hentaman komposit PVC berpengisi hibrid menurun dengan pertambahan kandungan pengisi. Kedua-dua, modulus tegangan dan lenturan komposit hibrid meningkat berbanding komposit tunggal. MBS meningkatkan kekuatan hentaman komposit berpengisi tunggal dan hibrid. Perbezaan morfologi permukaan antara OPEFB cangkukan dan tanpa cangkukan OPEFB telah diperhatikan. Suhu peralihan kaca (T_g) komposit hibrid meningkat berbanding komposit tunggal. Modulus simpanan menunjukkan PVC berpengisi talkum mempunyai nilai modulus simpanan yang tertinggi. Hibrid pengisi menunjukkan kestabilan terma yang lebih baik berbanding komposit berpengisi tunggal. Peningkatan rintangan air komposit berpengisi hibrid membuktikan interaksi yang baik antara pengisi-matrik. Secara keseluruhannya, kajian menunjukkan bahawa komposit PVC berpengisi hibrid menunjukkan sifat-sifat mekanikal dan terma yang lebih baik berbanding komposit PVC berpengisi tunggal.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xi
	LIST OF FIGURES	xii
	LIST ABBREVIATIONS	xiv
	LIST OF APPENDICES	xv
1	INTRODUCTION	1
	1.1 Background of Study	1
	1.2 Problem Statement of Study	6
	1.3 Objective of Study	8
	1.4 Scope of Study	9
2	LITERATURE REVIEW	10
	2.1 Poly(vinyl chloride) (PVC)	10
	2.1.1 Properties of PVC	11

2.2	PVC and Additives	12
2.2.1	Heat Stabilizer	13
2.2.2	Lubricant	14
2.2.3	Processing Aid	16
2.2.4	Pigment	17
2.3	Impact Modifier	18
2.3.1	Methyl Butadiene Styrene (MBS)	19
2.4	Natural Fiber	20
2.5	Oil Palm Empty Fruit Bunch (OPEFB)	21
2.6	Poly(methyl methacrylate) (PMMA)	23
2.7	Surface Modification	24
2.7.1	PMMA as Surface Modification	25
2.8	Copolymer Grafting	26
2.8.1	Graft Copolymerization of OPEFB	27
2.8.2	Reaction Mechanism	28
2.8.3	Initiator	30
2.8.4	Co-catalyst	31
2.9	Minerals filler	31
2.9.1	Talc Minerals	31
2.10	Filled PVC Composite	33
2.10.1	OPEFB Fiber Filled PVC Composite	33
2.10.2	Impact Modifier Filled PVC Composite	35
2.10.3	Talc Filled PVC Composite	36
2.10.4	PVC Hybrid Composite	37
3	METHODOLOGY	39
3.1	Materials	39
3.1.1	Poly(vinyl chloride)	39
3.1.2	Methyl Butadiene Styrene (MBS)	40
3.1.3	Oil Palm Empty Fruit Bunch (OPEFB)	40
3.1.3.1	Preparation of OPEFB	41

3.1.4	Talc	42
3.1.5	Methyl methacrylate (MMA)	43
3.1.6	Initiator and Co-catalyst	43
3.2	Purification of MMA Monomer	44
3.3	Dilution of Hydrogen Peroxide	45
3.4	Preparation of PMMA- <i>grafted</i> -OPEFB	45
3.5	Removal of Homopolymer by Using Soxhlet Extraction	48
3.6	Determination of Grafting Percentage and Grafting Efficiency	50
3.7	Preparation of Single and Hybrid Fillers Filled PVC Composites	51
3.7.1	Dry Blending	51
3.7.2	Preparation of PVC Composite Sheets	54
3.8	Testing and Characterization techniques	54
3.8.1	Fourier Transform Infrared (FTIR)	54
3.8.2	Tensile Test	55
3.8.3	Flexural Test	55
3.8.4	Izod Impact Test	55
3.8.5	Dynamic Mechanical Analysis(DMA)	56
3.8.6	Thermogravimetric Analysis (TGA)	56
3.8.7	Scanning Electron Microscopy (SEM)	57
3.8.8	Water Absorption	57
4	RESULTS AND DISCUSSIONS	58
4.1	Characterization of Graft Copolymerization Reaction	58
4.2	Fourier Transform Infrared Analysis	60
4.3	Mechanical Properties	62
4.3.1	Tensile Properties	62
4.3.2	Flexural Properties	66

4.3.3	Impact Strength	70
4.4	Thermal Properties	74
4.4.1	Dynamic Mechanical Analysis (DMA)	74
4.4.1.1	Storage Modulus (E')	74
4.4.1.2	Damping Factor (tan δ)	76
4.4.2	Thermogravimetry Analysis (TGA)	78
4.5	Scanning Electron Microscopy (SEM)	84
4.6	Water Absorption	88
5	CONCLUSIONS AND RECOMMENDATIONS	90
5.1	Conclusions	90
5.2	Recommendations	91
	REFERENCES	92
	Appendices A - G	106-116

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Physical properties of molding PVC products and compounds	12
2.2	Different chemical composition from the study of Oil Palm Fibers in Malaysia	22
3.1	Specification of PVC resin	39
3.2	Types of Additives	40
3.3	Optimum condition for graft copolymerization of PMMA onto 1g of OPEFB	46
3.4(a)	Blend formulation of PVC composites	52
3.4(b)	Blend formulation of MBS impact modified filled PVC composites	53
3.5	Data of impact testing machine	56
4.1	Characterization of graft copolymerization reaction	59
4.2	Tg value of PVC compound, single and hybrid fillers at 20 phr loading content	78
4.3	The degradation temperature of PVC compound, single and hybrid filler at 20 phr loading content from DTG curves	81
4.4	Thermal degradation temperature at 30% weight loss charred residue of the single and hybrid filled PVC composites	83

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
3.1	Cumulative curve	41
3.2	Morphology of OPEFB	42
3.3	Morphology of talc mineral	43
3.4	Apparatus arrangement for removal inhibitor (hydroquinone)	44
3.5	Arrangement of apparatus for graft copolymerization	46
3.6	Step-by-step procedure for graft copolymerization	47
3.7	Arrangement of apparatus for Soxhlet extraction	48
3.8	Step-by-step procedure of Soxhlet extraction	49
4.1	Physical interactions between PMMA and PVC	59
4.2	FTIR spectra of ungrafted OPEFB fiber and PMMA- <i>g</i> -OPEFB fiber	60
4.3	FTIR spectra of single and hybrid fillers filled PVC composites	60
4.4	Effects of single and hybrid fillers on the tensile strength of PVC composites	65
4.5	Effects of single and hybrid fillers on the tensile modulus of PVC composites	65
4.6	Effects of single and hybrid fillers on the elongation at break of PVC composites	66
4.7	Effects of single and hybrid fillers on the flexural strength of PVC composites	69
4.8	Effects of single and hybrid fillers on the flexural modulus of PVC composites	69

4.9	Effects of single and hybrid fillers on the impact strength of PVC composites	71
4.10	Effects of 10 phr MBS impact modifier on the impact strength of PVC composites	73
4.11	Temperature dependence Storage Modulus (E') of PVC, single and hybrid filler at 20 phr filled PVC composites	75
4.12	Temperature dependence tan delta of PVC, single and hybrid filler at 20 phr loading content filled PVC composites	77
4.13	TG curves of PVC, single and hybrid fillers at 20 phr loading content filled PVC composites	80
4.14	DTG curves of PVC, single and hybrid fillers at 20 phr loading content filled PVC composites	81
4.15	SEM micrographs of (a) OPEFB fiber and (b) PMMA-g-OPEFB fiber	85
4.16	SEM micrographs of fractured surface of (a) ungrafted OPEFB filled PVC, (b) grafted OPEFB filled PVC, (c) ungrafted OPEFB/talc filled PVC, (d) grafted OPEFB/talc filled PVC	87
4.17	Effects of single and hybrid fillers filled PVC composites on water absorption	89

LIST OF ABBREVIATIONS

CaCO ₃	-	Calcium carbonate
Fe ²⁺	-	Ferrous ion
FTIR	-	Fourier transformed infrared
<i>g</i>	-	Grafted
GE	-	Grafting efficiency
H ₂ O ₂	-	Hydrogen peroxide
Mg	-	Magnesium
MgO	-	Magnesium oxide
MMA	-	Methyl methacrylate
NH ₄	-	Ammonium
OPEFB	-	Oil palm empty fruit bunch
PG	-	Percentage of grafting
phr	-	Part per hundred resins
PMMA	-	Poly(methyl methacrylate)
SiO ₂	-	Silica
T _g	-	Glass transition temperature
ZnO	-	Zinc oxide

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Preparation of hydrogen peroxide	106
B	Conversions amount of monomer, initiator and co-catalyst from molar basis to the respective volumetric or mass basis	108
C	Characterization of graft copolymerization	111
D	Value of water absorption of single and hybrid filler filled PVC composites	113
E	Conference proceeding (Malaysian Polymer International Conference 2011 (MPIC))	114
F	Conference proceeding (National Symposium of Polymeric Material 2011 (NSPM))	115
G	Conference proceeding (Asian International Conference on Materials, Minerals and Polymer 2012 (MAMIP))	116

CHAPTER 1

INTRODUCTION

1.1 Background of Study

PVC resin has become one of the major components for polymer composites manufacturing especially for construction parts, pipes, hoses, electric cables, and packaging material. PVC offers several unique properties and advantages which include excellent chemical and weathering properties, nonflammable, and also cheaper compared to other plastics (Abu Bakar *et al.*, 2008). PVC resin can be made into products with a wide range of properties from soft and flexible to light and rigid by the addition of additives. Other ingredients must typically be added to convert PVC into a finished product. Another ways to improve the PVC properties is by introducing the organic and inorganic fillers.

Natural fiber as organic filler or reinforcement into thermoplastic has attracted many researchers since natural fiber showed an excellent alternative of filler into plastic industry. According to Stokke (2002), the demand of natural fillers for plastic composite applications will grow at least six-fold in the next 5 to 7 years. There are many types of natural fiber that have been introduced as filler in PVC such as wood flour (Mengeloglu *et al.*, 2000, Sombatsompop *et al.*, 2003, Jiang *et al.*, 2004 and Zhoa *et al.*, 2006), rice straw (Kamel, 2004), sugarcane bagasse (Zheng *et al.*, 2007), rice husk (Sivaneswaran, 2002) and pineapple leaf (Mohanty *et al.*, 2000).

Oil Palm Empty Fruit Bunch (OPEFB) fiber is one of the applied natural fibers to be used as reinforcing filler in polymer composite. OPEFB consists of three main parts; hemicelluloses, cellulose and lignin which known as lignocellulosic (Hassan *et al.*, 2010). The seed oil from the oil palm is being extracted and the waste materials after the extraction are known as OPEFB. OPEFB is generally used as mulch for oil palms, converted to bunch ashes or discarded as waste.

The by-product from the palm oil, OPEFB has now become commercially used in Malaysia and also other countries in Asia since OPEFB has been planted in large amount. In order to minimize the abundance of this industrial waste, new applications are required for OPEFB to be more useful. Therefore, due to its low cost and availability factors, OPEFB has been utilized as fillers in many polymer composite technologies. Hence, OPEFB is selected as filler into the polymer composites due to the several benefits offered by this organic material such as less abrasiveness to equipment, low density, low cost, environmentally friendly and biodegradable (Raju *et al.*, 2008).

OPEFB has been used extensively as filler in the polymer composites. Many studies have been conducted on OPEFB filled thermoplastics polymer such as polypropylene (Rozman *et al.*, 2000 & 2001 and Khalid *et al.*, 2008), polyurethane (Rozman *et al.*, 2001 & 2002 and Badri *et al.*, 2002 & 2007), polyesters (Hill and Khalil, 2000 and Khalil *et al.*, 2007 & 2008) and others. However, there were limited studies that have been done on OPEFB filled PVC composites (Abu Bakar *et al.*, 2005a, 2005b & 2010). Most of these researchers focused on the effect of fiber loading on the mechanical behavior.

Abu Bakar *et al.* (2005a and 2005b) showed that there are new trends in PVC composite technology by adding OPEFB as filler. In these researches it has been reported that upon increasing of OPEFB fillers loading, the impact strength of composites decreased linearly. The reasons of the low strength properties were due to the poor adhesion and/or dispersion of OPEFB due to the incompatibility between hydrophobic of the polymer and hydrophilic OPEFB during mixing.

Thus, modification has to be done onto the surface of the natural fiber to increase the compatibility of phases between the thermoplastics and natural fiber. Previous studies have reported that a grafting technique can be used to overcome this problem. OPEFB may be grafted with various types of polymers which includes poly (butyl acrylate) (PBA), poly (methyl methacrylate) (PMMA) and poly (acrylamide) (PAM) (Das *et al.*, 1999). This hydrophobic property exhibits solubility similarities with most thermoplastic matrix and expects to allow the grafted copolymer to improve the interaction between thermoplastic matrix and OPEFB.

In accordance, the copolymer grafting technique has been widely used and becoming more popular currently (Prasanth *et al.*, 2005). PMMA which consists of carbonyl compound has good compatibility with PVC (CHCl) due to the hydrogen bonding (Chen *et al.*, 2006). Abu Bakar *et al.* (2008) found and reported that PMMA has successfully been grafted onto OPEFB by using the optimum conditions. The percentage of grafting that has been achieved by using these optimum conditions was 173%.

Recently, there was a study conducted in comparing between the loading of 20 phr of ungrafted and grafted OPEFB fiber filled PVC composite. The elongation at break and tensile strength increased while the stiffness (Young's modulus) of the composites was decreased (Abu Bakar *et al.*, 2010). Kee (2010), showed that the incorporation of the same loading amount (20 phr) of grafted and ungrafted OPEFB has reduced the impact strength of the composites. For the flexural testing, ungrafted OPEFB filled PVC reduced the flexural strength while grafted OPEFB composites showed otherwise results. The Young's modulus showed the same trend from the previous study done by Abu Bakar *et al.* (2010) where the stiffness of the composites of grafted OPEFB decreased compared to the ungrafted OPEFB.

Inorganic fillers are being used extensively in thermoplastics such as polyethylene, polypropylene, nylon and also poly(vinyl chloride) To improve the applicability of the PVC composites, the composite should achieve good combination properties, therefore many types of inorganic filler are being introduced into PVC such as glass fibers, calcium carbonate and talc (Wiebking, 1986 and Xie

et al., 2001). Inorganic fillers play an important role to improve and enhance the Young's modulus of the PVC composites.

Talc is a natural product that is widely used in industry. It is a phyllosilicate mineral, $Mg_3Si_4O_{10}(OH)_2$ with a tri-octahedral layered structure. Because of its plate-like structure with a high aspect ratio material, the composite filled with talc give certain good properties, such as good strength and stiffness (Bee *et al.*, 2012b). Talc is being used as reinforcing filler in various PVC formulations to achieve higher strength, stiffness, and dimensional stability (Radosta and Trivedi, 1987). The use of talc filler into PVC as flow aid/dusting agent to impart a slick surface to the calendered flexible film and to reduce plate out in the extrusion process (Wilkes *et al.*, 2005). Talc filler is commonly employed in PVC compounds in order to reduce cost.

Several studies have been done on hybrid filler between organic filler and inorganic fillers into PVC composite. From the previous study by Maldas and Kokta (1991) showed that the outstanding and superior results on the strength and also modulus of treated wood fiber/mica compared to the untreated composites. Study on the mechanical properties of PVC/wood flour/glass fiber hybrid composites showed that the impact strength of hybrid composites increased without losing flexural properties (Jiang *et al.*, 2003).

The use of OPEFB fiber as filler in PVC composites has been studied extensively. There is no single study focusing on hybrid OPEFB/inorganic filler into PVC. There were only few studies of hybrid filler between the OPEFB and inorganic filler onto other thermoplastics. Natural rubber hybrid composites using OPEFB and glass fiber in PP matrix was done by Rozman *et al.* (2001a and 2001b) and Anuar *et al.* (2006).

The addition of natural fiber as filler into PVC increased the stiffness of the PVC composite but decreased the toughness of the composites. To achieve good mechanical properties, the composites need to strike balance of the strength, toughness and also stiffness (Mohd Ishak *et al.*, 2000). Therefore, by adding impact modifier into the PVC blend improved the toughness and ductility of the composites. The enhancement of the impact strength is due to the phase of rubbery particle of the impact modifier. Some of the common impact modifiers used in PVC are acrylic, chlorinated polyethylene (CPE), ethylene-vinyl acetate (EVA) and methyl butadiene styrene (MBS).

Based on the previous studies by Abu Bakar *et al.* (2005a, 2005b and 2005c), untreated OPEFB with any chemical surface reagents into PVC matrix was impact modified with acrylic impact modifier in order to improve the mechanical properties of OPEFB filled PVC composites. From these studies, the ability of acrylic impact modified PVC to shear yield before fracture has improved the impact and flexural strength. A recent study by Abu Bakar *et al.* (2012) showed that the addition of impact modifier into the treated OPEFB with PMMA filled PVC enhanced in the impact strength properties.

Core-shell acrylic impact modifier was selected as an impact modifier in the previous studies to improve the impact strength of the PVC composites (Abu Bakar *et al.*, 2005a, 2005b, 2005c and 2012). In this study, core shell MBS impact modifier was selected. This is because, MBS provides a step-change in PVC impact modification, as MBS allowed compounder to efficiently handled and incorporate into the blending system. Besides that, MBS dispersibility in the melt showed less process dependence than other type of modifiers (Wilkes *et al.*, 2005).

1.2 Problem Statement of Study

Poly (vinyl chloride) has been used for a long time ago because of its low cost, chemical inertness, and also good in heat resistivity. But, PVC also has many other imperfections like brittleness, limited strength and stiffness. Adding various types of fillers such as organic, inorganic, impact modifier and others (e.g. heat stabilizer, lubricant, processing aid and pigment) into the PVC can improve the mechanical properties.

According to Rahman *et al.* (2006) more than 55 million tons of oil palm biomass was generated annually in Malaysia, with all of this waste was not used and discarded. To avoid this problem, polymeric technology has offered some new technique to produce new material using the natural fiber. This can reduce the waste banishment to landfill. OPEFB as filler in PVC has become a new attraction in polymer composite technology, especially when PVC is widely used in plastic and building industry, strengthening the mechanical properties of the composite will bring more benefits into those industries (Zaini *et al.*, 1996).

From the previous study by Abu Bakar *et al.* (2008), the OPEFB fiber was grafted with methyl methacrylate (MMA) for the purpose of improving the compatibility of hydrophilic OPEFB with hydrophobic polymer matrix by using the optimum condition (Abu Bakar *et al.*, 2008). Recently a study on ungrafted and grafted OPEFB filled PVC by Abu Bakar *et al.* (2010 and 2012) showed that the stiffness and impact strength of the composites decreased while the tensile strength and elongation at break increased with the incorporation of 20 phr PMMA-*g*-OPEFB fiber into the PVC matrix. The grafted OPEFB filled acrylic-impact modified composites showed better properties compared to the ungrafted composites. The size of the fiber used in these previous studies was less than 75 μ m.

For the polymeric materials development, the most important things are to achieve a good combination of mechanical properties at a relatively low cost. With this in mind, the talc filler was used as reinforcement to enhance the stiffness of PMMA-grafted-OPEFB filled PVC composites. Many research works have been done on the flexural, tensile and impact properties of ungrafted and grafted OPEFB filled PVC composite but not much on the use of hybrid filler system in PVC composites. In this study, the combination of ungrafted OPEFB/talc and grafted OPEFB/talc fiber was used as hybrid fillers on PVC composites.

In order to achieve good properties of the PVC composites, PVC needs to be toughened. Since from the previous study showed that the addition of ungrafted and grafted OPEFB into PVC produced more brittle than PVC, therefore, the conventional approach by incorporating impact modifier into the composites is introduced (Wilkes *et al.*, 2005). In this study, the main reason for the addition of impact modifier is to achieve good toughness properties of the single and hybrid composite without losing the good stiffness properties of the composites.

In this study, OPEFB with the size less than 50 μ m was grafted with MMA by using the optimum conditions from the previous study by Abu Bakar *et al.* (2008). This research was conducted to investigate the effect of single filler (ungrafted OPEFB, grafted OPEFB or talc) and hybrid filler (ungrafted OPEFB/talc and grafted OPEFB/talc) filled PVC composites on the mechanical and thermal properties.

1.3 Objectives of Study

The overall aim of this research is to discover how the single filler (ungrafted OPEFB, grafted OPEFB, talc) and hybrid filler (ungrafted OPEFB/talc, grafted OPEFB/talc) can enhance the mechanical and thermal properties of PVC composites.

The overall objectives can be sub-divided into the followings:

- 1) To prepare the grafted oil palm empty fruit bunch fibers (PMMA-*g*-OPEFB) using optimum conditions grafting reaction .
- 2) To determine the ability of the ungrafted OPEFB, grafted OPEFB, talc, ungrafted OPEFB/talc and grafted OPEFB/talc content in affecting the PVC composites such as tensile, flexural and impact properties.
- 3) To study the effect on the thermal properties of ungrafted OPEFB, grafted OPEFB, talc, ungrafted OPEFB/talc and grafted OPEFB/talc content filled PVC composites.
- 4) To determine the effect of MBS impact modifier on the ungrafted OPEFB, grafted OPEFB, talc, ungrafted OPEFB/talc and grafted OPEFB/talc in affecting impact properties of the PVC composites.

1.4 Scope of the Study

- 1) Preparation of PMMA-*g*-OPEFB fiber in bulk. The reaction conditions gained from the study by Abu Bakar *et al.* (2008) were used to prepare the grafted OPEFB.
- 2) Preparation of single filler (ungrafted OPEFB, grafted OPEFB, talc) and hybrid filler (ungrafted OPEFB/talc, grafted OPEFB /talc) and MBS impact modified filled PVC composites.
- 3) The blended samples were roll-milled and molded into testing specimens using a compression molding.
- 4) The ungrafted OPEFB, grafted OPEFB and talc filler content were varied in order to formulate the best formulation. While the MBS impact modifier were fixed at optimum content.
- 5) Characterization of the OPEFB fiber with the OPEFB-*g*-PMMA and hybrid OPEFB-*g*-PMMA/talc-filled PVC composites using FTIR analysis.
- 6) Mechanical properties were determined based on tensile, flexural and impact properties.
- 7) Thermal properties determination based on DMA and TGA.
- 8) Surface morphology was examined using SEM.
- 9) Physical properties determination based on water absorption.

REFERENCES

- Abdul Khalil, H. P. S., Siti Alwani, M. and Mohd Omar, A. K. (2006). Chemical Composition, Anatomy, Lignin Distribution, and Cell Wall Structure of Malaysian Plant Waste Fibers. *BioResources*. 1(2), 220-232.
- Abu Bakar, A., Hassan, A. and Mohd Yusof, A. F. (2005a). Mechanical and Thermal Properties of Oil Palm Empty Fruit Bunch-Filled Unplasticized Poly (Vinyl Chloride) Composites. *Polymer and Polymer Composites*. 13(6), 1-8.
- Abu Bakar, A., Hassan, A. and Mohd Yusof, A.F. (2005b). Effect of Oil Palm Empty Fruit Bunch and Acyclic Impact Modifier on Mechanical Properties and Processability of Unplasticized Poly(Vinyl Chloride) Composites. *Polymer-Plastics Technology and Engineering*. 44, 1125-1137.
- Abu Bakar, A., Hassan, A. and Mohd Yusof, A. F. (2005c). Effect of Accelerated Weathering on the Mechanical Properties of Oil Palm Empty Fruit Bunch Filled UPVC Composites. *Iran Polymer Journal*. 14 (7), 627-635.
- Abu Bakar, A. and Baharulrazi, N. (2008). Mechanical Properties of Benzoylated Oil Palm Empty Fruit Bunch Short Fiber Reinforced Poly(vinyl chloride) Composites. *Polymer-Plastics Technology and Engineering*. 47, 1072-1079.
- Abu Bakar, A., Tham, B. K. and Hassan, A. (2010). Tensile Properties of a Poly(vinyl chloride) Composites Filled with Poly(methyl methacrylate) Grafted to Oil Palm Empty Fruit Bunches. *Journal of Applied Polymer Science*. 115, 91-98.

- Abu Bakar, A., Kee, W. C. and Abdul Ghani, S.W. (2012). Flexural and Impact Properties of Poly(Vinyl Chloride) and Acrylic-Impact Modified Poly (Vinyl Chloride) Composite Filled with Poly (Methyl Methacrylate) Grafted to Oil Palm Empty Fruit Bunches. *International Journal of Polymeric Materials*. 61: 263–275.
- Abu-Iilawi F. A., Ahmad M, B., Ibrahim, N. A., Rahman, M. Z. A., Dahlan, K. Z. M. and Wan Yunus W. M. Z. (2004). Optimized conditions for the grafting reaction of poly(methyl acrylate) onto rubberwood fiber. *Polymer International*. 53, 386-391.
- Ahmad, Z., Al-Awadi, N. A., and Al-Sagheer, F. (2007). Thermal Degradation Studies in Poly (vinyl chloride)/Poly (methyl methacarylate) Blends. *Polymer Degradation and Stability*. 92(6), 1025-1033.
- Anuar, H., Ahmad, S.H., Rasid, E. and Nik Daud, N.S. (2006). Tensile and Impact Properties of Thermoplastic Natural Rubber Reinforced Short Glass Fiber and Empty Fruit Bunch Hybrid Composites. *Polymer-Plastic Technology and Engineering*. 45(9), 1059-1063.
- Badri, K.H., Amin, K.A.M., Othman, Z., Manaf, H.A. and Khalid, N.K. (2005). Mechanical Properties of Polyurethane Composites from Oil Palm Resources. *Iran Polymer Journal*. 14(5), 441-448.
- Bakar, M.B.A., Leong, Y.W., Ariffin, A. and Mohd Ishak, Z.A. (2008). Effect of Chemical Treatments on the Mechanical, Flow and Morphological Properties of Talc and Kaolin Filled Polypropylene Hybrid Composites. *Journal of Applied Polymer Science*. 110, 2770-2779.
- Bee, S.T. (2007). *Mechanical Properties and Processability of Hybrid Talc and Calcium Carbonate Filled Poly(vinyl Chloride)*. Degree. Universiti Teknologi Malaysia.

- Bee, S.T., Abu Bakar, A., Hassan, A. (2012a). Mechanical Properties of Talc- and (Calcium Carbonate)-Filled Poly(vinyl chloride) Hybrid Composites. *Journal of Vinyl and Additive Technology*. 18(2), 76-86.
- Bee, S.T., Abu Bakar, A., Hassan, A. (2012b). Thermal Properties and Processability of Talc- and (Calcium Carbonate)-Filled Poly(vinyl chloride) Hybrid Composites. *Journal of Vinyl and Additive Technology*. 18, 87-94.
- Bower, J.D. (1986). The Function of Lubricants in Processing of Rigid PVC. *Journal of Vinyl Technology*. 8(4), 179-182.
- Brydson, J.A. (1989). *Plastics Materials (5th ed.)*. London : Anchor Press Ltd, Triptree, Essex.
- Butters, G. (1982). *Particulate Nature of PVC-Formation, Structure, and Processing*. New York : Marcel Dekker.
- Campo, E.A. (2007). *Industrial Polymer*, Cincinnati, Ohio, USA: Hanser Garden Publication, Inc.
- Chand, N. and Fahim, M. (2008). *Tribology of Natural Fiber Polymer Composites*. Boca Raton: CRC Press, Taylor and Francis.
- Chen, X.H., Li, C.Z., Xu, S.H., Zhang, L., Shao, W. and Du, H. L. (2006). Interfacial Adhesion and Mechanical Properties of PMMA-Coated CaCO₃ Nanoparticles Reinforced PVC Composites. *China Particuology*. 4, 25-30.
- Coaker, A. W. and Wypart, R. W. (1993). Vinyl Chloride Resins: Suspension, Emulsion, Microsuspension and Bulk (Mass). In: Wickson, E.J. *Handbook of Polyvinyl Chloride Formulating*. New York: John Wiley and Sons. 15-55.
- Das, R. K., Basu D., and Banerjee, A. (1999). Study of Methyl-Methacrylate-Viscose Fiber Graft Copolymerization and the Effect of Grafting on Thermal Properties. *Journal of Applied Polymer Science*. 72, 135-140.

- Dunkelberger, D.L., Lutz, J. and Szamborski, E.C. (1993). Processing Aids. In: Wickson, E.J. *Handbook of Polyvinyl Chloride Formulating*. New York : John Wiley and Sons Inc: 639-647.
- Gangopadhyay, R. and Ghosh, P. (1999). Uncatalyzed Photografting of Polyacrylamide from Functionalized Cellulosic and Lignocellulosic Materials. *Journal of Applied Polymer Science*. 71, 1623-1634.
- Gupta, K. C., Sahoo, S. and Khandekar, K. (2002). Graft Copolymerization of Ethyl Acrylate onto Cellulose Using Ceric Ammonium Nitrate as Initiator in Aqueous Medium. *European Polymer Journal*. 43, 3865–3872.
- Hameed, N., Sreekumar P.A., Francis, B., Yang, W. and Thomas, S. (2007). Morphology, Dynamic Mechanical and Thermal Studies on Poly(styrene-co-acrylonitrile) Modified Epoxy Resin/Glass Fibre Composites. *Composite Part A: Applied Science and Manufacturing*. 38(12), 2422–32.
- Hassan, A., Salema, A. A., Ani, F. N. and Abu Bakar, A. (2010). A review on Oil Palm Empty Fruit Bunch Fiber-Reinforced Polymer Composite Materials. *Polymer Composites*.
- Hassan, A. and Haworth, B. (2005). Impact Properties of Acrylate Rubber-Modified PVC: Influence of Temperature. *Journal of Materials Processing Technology*. 172, 341-345.
- Hiltner, A., Siegmann, A. and Bear, E. (1984). Impact Modification of PVC with Chlorinated Polyethylene, *ANTEC'84*. 555-557.
- Hill. C.A.S. and Abdul Khalil, H.P.S. (2000). Effect Fibre Treatments on Mechanical Properties of Coir or Oil Palm Fibre Reinforced Polyester Composites. *Journal of Applied Polymer Science*. 78(9), 1685-1697.

- Huang, Y., Zhao, B., Zheng, G., He, S. and Gao, J. (1992). Graft Copolymerization of Methyl Methacrylate on Stone Ground Wood Using the $\text{H}_2\text{O}_2\text{-Fe}^{2+}$ Method. *Journal of Applied Polymer Science*. 45, 71-77.
- Ibrahim, N. A., Wan Yunus, W. M. Z., Abu-Ilaiwi, F. A., Rahman, M. Z. A., Ahmad, M. B. and Dahlan K. Z. M. (2003a). Graft Copolymerization of Methyl Methacrylate onto Oil Palm Empty Fruit Bunch Fiber Using $\text{H}_2\text{O}_2/\text{Fe}^{2+}$ as an Initiator. *Journal of Applied Polymer Science*, 89, 2233 – 2238.
- Ibrahim, N. A., Wan Yunus, W. M. Z., Abu-Ilaiwi, F. A. F., Rahman, M. Z. A., Ahmad, M. B. and Dahlan, K. Z. M. (2003b). Optimized condition for grafting reaction of poly(butyl acrylate) onto Oil Palm Empty Fruit Bunch Fiber. *Polymer International*. 52, 1119-1124.
- Ibrahim, N. A., Wan Yunus, W. M. Z., Abu-Ilaiwi, F. A. F., Rahman, M. Z. A., Ahmad, M. B., Dahlan, K. Z. M. and Wan Yunus, W. M. Z. (2005). Graft Copolymerization of Acrylamide onto Oil Palm Empty Fruit Bunch (OPEFB) Fiber. *Polymer Research*. 12, 173-179.
- Isnin, M. K. (2007). *Optimized Conditions for the Grafting Reaction of Poly(methyl methacrylate) onto Oil-Palm Empty Fruit Bunch Fibers (Part II)*. Degree. Universiti Teknologi Malaysia.
- Iulianelli, G., Tavsres, M.B. and Luetkmeyer, L. (2010). Water Absorption Behavior and Impact Strength of PVC/Wood Flour Composites. *Chemistry and Chemical Technology*. 4(3), 225-229.
- Jacob, M., Francis B, Thomas, S. and Varughese, K.T. (2006). Dynamical Mechanical Analysis of Sisal/Oil Palm Hybrid Fiber-Reinforced Natural Rubber Composites. *Polymer Composite*. 27(6),671–80.
- Jawaid, M., Abdul Khalil, H. P. S. and Alattas, O.S. (2012). Woven Hybrid Biocomposites: Dynamic Mechanical and Thermal Properties. *Composites: Part A: Applied Science and Manufacturing*. 43, 288–293.

- Jiang, H., Kamden, D. P., Bezubic, B. and Ruede, P. (2003). Mechanical Properties of Poly(vinyl chloride)/ Wood Flour/ Glass Fiber Hybrid Composites. *Journal of Additive Technology*. 9(3), 138-145.
- Jiang, H. and Kamden, D. P. (2004). Development of Poly(vinyl chloride)/Wood Composites. A literature Review. *Journal of Vinyl and Additive Technology*. 10(2), 59-69.
- John, M. J., and Thomas, S. (2008). Review: Biofibres and Biocomposites. *Carbohydrate Polymers*. 71, 343-364.
- Joseph, S., Appukuttan, S. P., Kenny, J. M., Puglia, D., Thomas, S. and Joseph, K. (2010). Dynamic Mechanical Properties of Oil Palm Microfibril-Reinforced Natural Rubber Composites. *Journal of Applied Polymer Science*. 117(3), 1298–308.
- Kamel, S. (2004). Preparation and Properties of Composite Made From Rice Straw and Poly(vinyl chloride) (PVC). *Polymers for Advance Technologies*. 15, 612-616.
- Khalid, M. (2008). Effect of Trimethylolpropane Triacrylate (TMPTA) on the Mechanical Properties of Palm Fibre Empty Fruit Bunch and Cellulose Fibre Biocomposite. *Journal of Engineering Science and Technology*. 3(2), 153-162.
- Khalil, H. P. S. A., Hanida, S., Kang, C.W. and Fuaad, N. A. N. (2007). Agro-Hybrid Composites: The Effects on Mechanical and Physical Properties of Oil Palm Fiber (EFB)/ Glass Hybrid Reinforced Polyester Composites. *Journal Reinforced Plastic Composites*. 26(2), 203-217.
- Khalil, H. P. S. A, Siti, M. A., Ridzuan, R., Kamarudin, H. and Khairul, A. (2008). Chemical Composition, Morphological Characteristic, and Cell Wall Structure of Malaysian Oil Palm Fibers. *Polymer Plastic Technology Engineering*. 47, 273-280.

- Khan, F. and Ahmad, S. R. (1997). Graft Copolymerization of Water Emulsified Methyl Methacrylate With Preirradiated Jute Fiber. *Journal of Applied Polymer Science*. 65, 459- 468.
- Khan, F., Ahmad, S. R. and Kronfli, E. (2002). γ -Radiation- Induced Emulsion Graft Copolymerization of MMA onto Jute Fiber. *Advantages in Polymer Technology*. 21(2), 132-140.
- Kee, W. C. (2009). *Flexural and Impact Properties of Oil Palm Empty Fruit Bunch grafted Poly(methyl methacrylate)filled Poly(vinyl chloride) Composites*. Degree. Universiti Teknologi Malaysia.
- Kiani, H., Ashori, A., and Mozaffari, S.A. (2011). Water Resistance and Thermal Stability of Hybrid Lignocellulosic Filler-PVC Composites. *Polymer Bulletin*. 66, 797-802.
- Kickelbick, G. (2003). Effect of Surface Properties on the Adhesion between PVC and Oil Palm Empty Fruit Bunch. *Progress Polymer Science*. 28, 83-95.
- Kovacic, T., Klaric, I., Nardelli, A. and Baric, B. (1993). Thermal Degradation of Poly(vinyl chloride) / Poly(α -methylstyrene-acrylonitrile) Blends. *Polymer Degradation and Stability*. 40, 91-96.
- Lee, J. S. and Chang, F. C. (2004). Effects of the Core-Shell Impact Modifier Shell Thickness on Toughening PVC. *Polymer Engineering and Science*. 44(10), 1885-1889.
- Leong, Y. W., Mohd Ishak, Z. A. and Ariffin, A. (2004). Mechanical and Thermal Properties of Talc and Calcium Carbonate Filled Polypropylene Hybrid Composites. *Journal of Applied Polymer Science*. 91, 3327-3336.

- Leong, Y. W., Mohd Ishak, Z.A., and Ariffin, A. (2005). Effects of Filler Treatments on the Mechanical, Flow, Thermal, and Morphological Properties of Talc and Calcium Carbonate Filled Polypropylene Hybrid Composites. *Journal of Applied Polymer Science*. 98, 413-426.
- Lulianelli, G., Tavares, M. B. and Luetkmeyer, L. (2010). Water Absorption Behavior and Impact Strength of PVC/Wood Flour Composites. *Chemistry and Chemical Technology*. 4(3), 225-229.
- Lutz, J. T. and Dunkelberger, D. L. (1992). *Impact Modifiers for PVC; The History and Practice*. United States of Amerika:John Wiley & Sons, Inc.
- Lutz, J.T. (1993). Impact Modifiers for PVC. *Journal of Vinyl Technology*. 15(2), 82-98.
- Maldas, D. and Kokta, B. V. (1991). Composites of Poly Vinyl Chloride-Wood Fibers. III. Effect of Silane as Coupling Agent. *Vinyl Technology*. 29-119.
- Mandal, S. and Alam, S. (2012). Dynamic Mechanical Analysis and Morphological Studies of Glass/Bamboo Fiber Reinforced Unsaturated Polyester Resin-Based Hybrid Composites. *Journal of Applied Polymer Science*. 125, 382-387.
- Matuana, L. M., Balatinecz, J. J. and Park, C. B. (1998). Effect of Surface Properties on the Adhesion between PVC and Wood Veneer Laminates. *Polymer Engineering and Science*. 38(5), 765-773.
- Marshall, B.I. (1969). *Lubrication of Rigid PVC*. British plastics. August. 70-78.
- Marthur, K. K. and Vanderheiden, D.B. (1982). Precipitated Calcium Carbonate as Ultraviolet Stabilizers and Impact Modifiers in Poly(vinyl chloride) Siding and Profiles. *Proceeding of International Symposium on Polymer Additives*. 371-338.

- Matuana, L.M., Kamdem, D.P. and Zhang, J. (2001). Photoaging and Stabilization of Rigid PVC/Wood Fibers. *Journal of Applied Polymer Science*. 80(11), 1943-1950.
- Mehdi, B., Mehdi, T., Ghanbar, E. and Robert, H.F. (2004). Dynamic Mechanical Analysis of Compatibilizer Effect on the Mechanical Properties of Wood Flour–High Density Polyethylene Composites. *IJE Transactions B: Applications*. 17(1), 95.
- Mengeloglu (2001). *Rigid Poly (vinyl chloride)/Wood-Flour Composites and Their Foams*. Doctor Philosophy. Michigan Technological University.
- Mohd Ishak, Z. A., Ishiaku, U.S. and Kocsic, J.K. (2000). Hygrothermal Aging and Fracture Behaviour of Short-Glass Fibre-Reinforced Rubber Toughened Poly(butylenes terephthalate) Composites. *Composite Science and Technology*. 60, 803-815.
- Mohanty, A. K., Tripathy, P. C., Misra, M., Parija, S. and Sahod S. (2000). Chemical Modification of Pineapple Leaf Fiber: Graft Copolymerization of Acrylonitrile onto Defatted Pineapple Leaf Fibers. *Journal of Applied Polymer Science*. 77, 3035-3043.
- Mondal, M. I. H., Uraki, Y., Ubukata, M. and Itoyama, K. (2008). Graft Copolymerization of Vinyl Monomers onto Cotton Fibres Pretreated with Amines: Mechanical Property and Moisture Absorption. *Cellulose*. 15(4), 581-592.
- Murphy, J. (2001). *Additives for Plastics Handbook (2nd ed.)*. The Boulevard, Langford Lane, Kidlington, Oxford, United Kingdom: Elsevier Advanced Technology.
- Nik Mat, N. S. (2007). *Optimized Conditions for the Grafting Reaction of Poly(methyl methacrylate) onto Oil-Palm Empty Fruit Bunch Fibers (Part I)*. Degree. Universiti Teknologi Malaysia.

- Penn, W. S. (1971). Titow, W.V. and Lanham, B.J. (Ed) *PVC Technology (3rd ed.)*. England : Applied Science Publisher Ltd.
- Pothan, L. A., Oommen, Z. and Thomas, S. (2003). Dynamic Mechanical Analysis of Banana Fiber Reinforced Polyester Composites. *Composites Science and Technology*. 63(2), 283-293.
- Prashanth, K. V. H., Lakshman, K., Shamala, T. R. and Tharanathan, R. N. (2005). Biodegradation of chitosan-graft-polymethylmethacrylate films. *International Biodeterioration & Biodegradation*. 56, 115–120.
- Radosta, J. A. and Trivedi, N. C. (1987). Talc. Katz, H. S. and Milewski, J.V. (Ed) *Handbook of Fillers for Plastic* (pp. 216-231). United State of America: Van Nostrand Reinhold.
- Rahman, S. H. A., Choudhury, J. P., Ahmad, A. L. and Kamaruddin, A. H. (2006). Optimization Studies on Acid Hydrolysis of Oil Palm Empty Fruit Bunch Fiber for Production of Xylose. *Bioresources Technology*. 98, 554-559.
- Raju, G., Ratnam, C. T., Ibrahim, N. A., Ab. Rahman, M. Z. and Wan Yunus, M. Z. (2008). Enhancement of PVC/ENR Blend Properties by Poly(methyl acrylate) Grafted Oil Palm Empty Fruit Bunch Fiber. *Journal of Applied Polymer Science*. 110 (1), 368-375.
- Robinovic, E. B., Lacatus, E. and Summers, J. W. (1984). The Lubrication Mechanism of Calcium Stearate/Paraffin Wax Systems in PVC Compounds. *Journal of Vinyl Technology*. 6(3), 98-103.
- Rowell, R. M. and Stout, H. P. (2008). Jute and Kenaf. Lewin, M. (Ed). *Handbook of Fibers Chemistry* (pp.453). Boca Raton: CRC Press, Taylor and Francis.

- Rozman H.D., Lai C.Y., Ismail H. and Mohd Ishak Z. A. (2000). The Effect of Coupling Agents on the Mechanical and Physical Properties of Oil Palm Empty Fruit Bunch-Polypropylene Composites. *Polymer International*. 49, 1273-1278.
- Rozman, H. D., Tay, G. S., Kumar, R. N., Abu samah, A., Ismail, H. and Mohd Ishak, Z. A. (2001a). Polypropylene-Oil Palm Empty Fruit Bunch-Glass Fibre Hybrid Composites: A Preliminary Study on the Flexural and Tensile Properties. *European Polymer Journal*. 37, 1283-1291.
- Rozman, H. D., Tay, G. S., Kumar, R. N., Abu samah, A., Ismail, H. and Mohd Ishak, Z. A. (2001b). The Effect of Oil Extraction of Oil Palm Empty Fruit Bunch on the Mechanical Properties of Polypropylene- Oil Palm Empty Fruit Bunch-Glass Fibre Hybrid Composites. *Polymer-Plastic Technology and Engineering*. 40(2), 103-115.
- Saheb, D. N. and Jog, J. P. (1999). *Natural Fiber Polymer Composites: A Review*. John Wiley and Sons, Inc. Adv. In Polymer Techn. 18, 351-363.
- Sain, M., Suhara, P., Law, S. and Bouilloux, A. (2005). Interface Modification and Mechanical Properties of Natural Fiber-Polyolefin Composite Products. *Journal of Reinforced Plastics and Composites*. 24(2), 121-130.
- Singha, A. S. and Thakur, V. K. (2008). Mechanical Properties of Natural Fibre Reinforced Polymer Composites. *Material Sciences*. 31(5), 791-799.
- Sivaneswaran, K. K. (2002). *Effect of Rice Husk Fillers on Mechanical Properties of ABS Impact Modified PVC-U*. Master. Universiti Teknologi Malaysia.
- Sombatsompop, N., Chaochanchaikul, K., Phromchirasuk, C. and Thongsang, S. (2003). Effect of Wood Sawdust Content on Rheological and Structural Changes, and Thermo-Mechanical Properties of PVC/Sawdust Composites. *Polymer International*. 52, 1847-1855.

- Sombatsompop, N. and Phromchirasuk, C. (2004). Effects of Acrylic Based Processing Aids on Processability, Rheology, Thermal and Structural Stability, and Mechanical Properties of PVC/Wood-Sawdust Composites. *Journal of Applied Polymer Science*. 492, 782-790.
- Sreekala, M. S., Kumaran, M. G. and Thomas, S. (1997). Oil Palm Fibers: Morphology, Chemical Composition, Surface Modification, and Mechanical Properties. *Journal of Applied Polymer Science*. 66, 821- 835.
- Stevenson, J. C. (1995). Impact Modifiers: Providing a Boost to Impact performance. *Journal of Vinyl and Additive Technology*. 1(11), 41-45.
- Stokke, D. D. (2002). Fiber Plastics Composite Materials: An Open House Biocomposite Group, Centre for Crops Utilization Research. , January 23. Iowa State University, Ames, Iowa.
- Tajvidi, M. (2005). Static and Dynamic Mechanical properties of a Kenaf Fiber-Wood Flour/ Polypropylene hybrid Composites. *Journal of Applied Polymer Science*. 98(2), 655-672.
- Takaki, A., Hasegawa, T., Isogawa, M. and Narisawa, I. (1994). Fracture Behavior of Poly(vinyl chloride) / Methyl Methacrylate / Butadiene / Styrene Polymer Blends. *Polymer Engineering and Science*. 38(8), 680-690.
- Titow, W. V. (1991). *PVC Plastics: Properties, Processing and Applications*. New York: Elsevier Applied Science Publisher.
- Whisson, R. R. (1971). Mineral Powders. Wake, W.C. (Ed) *Fillers for Plastic* (pp. 13-37). England : Page Bros (Norwich) Ltd.
- Wiebking, H. E. (1996). The Performance of Ultrafine Talc in Rigid PVC. *Journal of Vinyl and Additive Technology*. 2(3), 187-189.

- Wiebking, H. E. (2006). Increasing the Flexural Modulus of Rigid PVC at Elevated Temperatures. . *Journal of Vinyl and Additive Technology*. 12, 37-40.
- Witenhafer, D. E. (1986). Resin Structure and Properties. Nass, L. I. and Heiberger, C. A. (Ed) *Encyclopedia of PVC* (2nd ed.) (pp : 309-342). New York : Marcel Dekker Ltd.
- Wilkes, C.E., Summers, J.W., and Daniels, C.A. (2005). *PVC Handbook*. (1st Edition). Munchen Germany: Hanser Gardner Publications, Inc.
- Wypych, J. (1985). Polyvinyl Chloride Degradation. New York/; Elsevier Science Publisher.
- Xiao, L. X., Robert, K. Y. L., Qing, X. L. and Yiu, W. M. (2004). Structure Property Relationships of In-Situ PMMA Modified Nano-Sized Antimony Trioxide Filled Poly (vinyl chloride) Nanocomposites. *Journal of Polymer*. 45, 2793-2802.
- Xie, X. L., Li, B. G., Pan, Z. R., Li, R. K. Y. and Tjong S. C. (2001). Effect of Talc/MMA *In Situ* Polymerization on Mechanical Properties of PVC-Matrix Composites. *Journal of Applied Polymer Science*. 80, 2105-2112.
- Xu, D. C., Jia, S. W. and Jia, R. S. (2006). Effect of Shell Thickness of Methacrylate-Butadiene-Styrene Core-Shell Impact Modifier on Toughening Polyvinyl chloride. *Journal of Polymer Research*. 13(4), 335-341.
- Yunos, M. Z. and Jamaluddin, J. (2007). *Preparation of Coconut Shell Fiber Grafted Poly(butyl acrylate) Using H₂O₂/Fe²⁺ as an Initiator*. Degree Thesis, Universiti Teknologi Malaysia.
- Zaini, M. J., Fuad, M .Y. A., Ismail, Z., Mansor, M. S. and Mustafah, J. (1996). The Effect of Filler Content and Size on the Mechanical Properties of Polypropylene/Oil Palm Wood Flour Composites. *Polymer International*. 40(1), 51-55.

- Zhao, Y., Wang, K., Zhu, F. and Jia, M. (2006). Properties of Poly(vinyl chloride)/Wood Flour/ Montmorillonite Composites: Effects of Coupling Agents and Layered Silicate. *Polymer Degradation and Stability*. 2748-2883.
- Zheng, Y. T., Cao, D. R., Wang, D. S. and Chen, J. J. (2007). Study on the Interface Modification of Baggasse Fibre and the Mechanical properties of its Composites with PVC. *Composites Part A: Applied Science and Manufacturing*. 38, 20-25.
- Zhu, A., Cai, A., Zhang, J., Jia, H. and Wang, J. (2008). PMMA-grafted-Silica/PVC Nanocomposites: Mechanical Performance and Barrier Properties. *Journal of Applied Polymer Science*. 108, 2189–2196.