PROPERTIES OF SELF-COMPACTING CONCRETE INCORPORATING PALM OIL FUEL ASH

ABDUL HAQ EHSAN

A project report submitted in partial fulfillment of the requirements for the award of the degree of Master of Engineering (Civil-Structures)

> Faculty of Civil Engineering Universiti Teknologi Malaysia

> > AUGUST 2014

This project report is dedicated to my parents for their endless support and encouragement

ACKNOWLEDGEMENT

I would like to express my gratitude to all those who gave me a helping hand to complete this project report. Special thanks go to my supervisor, Assoc. Prof. Dr. A.S.M. Abdul Awal for his support in this research project. Many thanks are also due to technicians of UTM Structures and Materials Laboratory and individuals who offered their helps directly or indirectly. Gratitude also dedicated to all my friends. Thanks for all the help and support during all the way upon completing project report.

Last but not least, I would like to extend my deepest and sincere appreciation to my beloved family, especially my mother, who is always supporting me, and encouraging me. She is my source of inspiration and my greatest refuge.

ABSTRACT

Self-compacting concrete (SCC) is a concrete which can be placed and compacted under its self-weight with little or no vibration effort, and is at the same time, cohesive enough to be handled without segregation or bleeding. SCC is used to facilitate and ensure proper filling and good structural performance of restricted areas and heavily reinforced structural members. SCC is a flowing concrete with high workability. To achieve flowing concrete low volume of coarse aggregates is used, but the reduction in volume of coarse aggregates require high volume of paste, i.e. cement and fine aggregates, and use of super-plasticizers. Increased volume of cement and addition of super-plasticizer leads to higher cost. The cost of cement can be reduced by using supplementary cementitious materials. One of the potential recycle materials from palm oil industry is palm oil fuel ash (POFA). Palm oil is extracted from the fruit and copra of the palm oil tree. Self-Compacting concrete using POFA has been one of the researching focuses in Malaysia. This study outlines laboratory tests conducted for fresh and hardened properties of SCC incorporating POFA. This study determines the feasibility of replacing cement in SCC with POFA in percentages of 0%, 30% and 60% by weight of cement, with water/binder ratios of 0.40, 0.45 and 0.50. The fresh properties of SCC were tested for filling ability, passing ability and segregation resistance. Slump-flow and Orimet flow time tests were conducted for filling ability, J-ring and L-box tests for passing ability and Vfunnel at T_{5minute} for segregation resistance. The hardened properties like compressive strength, split tensile strength, flexural strength and Ultrasonic pulse velocity were determined. Test specimens comprising of cube, cylinder and beams were prepared and tested at 1, 7 and 28 days of curing. The results and observations revealed that high volume POFA can be utilized in the development of SCC in terms of flow and strength gain.

ABSTRAK

Diri pemadatan konkrit (SCC) adalah konkrit yang boleh diletakkan dan dipadatkan di bawah berat badan sendiri dengan sedikit atau tidak ada usaha getaran, dan pada masa yang sama, cukup padu untuk dikendalikan tanpa pengasingan atau pendarahan. SCC digunakan untuk memudahkan dan memastikan pengisian yang betul dan prestasi baik struktur kawasan terhad dan anggota struktur banyak bertetulang. SCC adalah konkrit mengalir dengan kebolehkerjaan yang tinggi. Untuk mencapai mengalir jumlah konkrit rendah agregat kasar digunakan, tetapi pengurangan dalam jumlah agregat kasar memerlukan kelantangan yang tinggi pes, iaitu simen dan batu baur halus, dan penggunaan super-plasticizers. Dagangan meningkat simen dan penambahan super plasticizer membawa kepada kos yang lebih tinggi. Kos simen boleh dikurangkan dengan menggunakan bahan-bahan bersimen tambahan. Salah satu daripada bahan-bahan kitar semula yang berpotensi daripada industri minyak sawit adalah abu bahan api kelapa sawit (POFA). Minyak sawit yang diekstrak daripada buah-buahan dan kelapa kering daripada pokok kelapa sawit. Diri pemadatan konkrit yang menggunakan POFA telah salah satu penyelidikan yang memberi tumpuan di Malaysia. Kajian ini menggariskan ujian makmal dijalankan untuk hartanah segar dan mengeras SCC menggabungkan POFA. Kajian ini menentukan kemungkinan menggantikan simen di SCC dengan POFA dalam peratusan 0%, 30% dan 60% mengikut berat simen, dengan nisbah air / pengikat 0.40, 0.45 dan 0.50. Sifat-sifat segar SCC telah diuji untuk mengisi kemampuan, lulus keupayaan dan rintangan pengasingan. Slump flow dan Orimet flow time aliran telah diadakan untuk mengisi keupayaan, J-Ring dan L-Box untuk lulus ujian kebolehan dan V-Funnel di T_{5minute} untuk rintangan pengasingan. Sifat-sifat keras seperti kekuatan mampatan, kekuatan tegangan berpecah, kekuatan lenturan dan Ultrasonik denyutan halaju ditentukan. Spesimen ujian yang terdiri daripada kiub, silinder dan rasuk telah disediakan dan diuji pada 1, 7 dan 28 hari pengawetan. Keputusan dan pemerhatian mendedahkan bahawa kelantangan yang tinggi POFA boleh digunakan dalam pembangunan SCC dari segi aliran dan kekuatan keuntungan.

TABLE OF CONTENTS

CHAPTER	TITLE		PAGE	
	DECLARATION			ii
	DEDI	CATION	ſ	iii
	ACK	NOWLEI	DGEMENT	iv
	ABST	TRACT		V
	ABST	TRAK		vi
	TABI	LE OF CO	DNTENTS	vii
	LIST OF TABLES			x xi
	LIST OF FIGURES			
	LIST	OF ABB	REVIATION	xiv
1	INTR	ODUCTI	ION	1
	1.1	Backgr	ound of Study	1
	1.2	Problem	n Statement	3
	1.3	Objecti	ves	4
	1.4	Signifi	cance of Study	4
	1.5	Scope	of Study	5
2	LITE	RATURE	E REVIEW	6
	2.1	Introdu	ction	6
	2.2	Concre	te as a Structural Material	6
	2.3	Admix	tures in Concrete	7
		2.3.1	Air-Entraining Agents	7
		2.3.2	Chemical Admixtures	7
		2.3.3	Mineral Admixtures	8
		2.3.4	Miscellaneous Admixtures	8

2.4	Palm Oil Fuel Ash (POFA)8		8
	2.4.1	Use of POFA as SCM	9
2.5	Self-Com	pacting Concrete	10
	2.5.1	History of Self-Compacting Concrete	10
	2.5.2	Advantages of Self-Compacting Concrete	11
	2.5.3	Effects of Mineral Admixtures on Properties	of
		SCC	12
2.6	Character	istics of Fresh Self-Compacting Concrete	14
	2.6.1	Filling Ability	15
	2.6.2	Passing Ability	15
	2.6.3	Segregation Resistance	16
2.7	Character	istics of Hardened Self-Compacting Concrete	16
	2.7.1	Compressive Strength	17
	2.7.2	Tensile and Shear Strength	17
	2.7.3	Elastic Modulus and Toughness	18
	2.7.4	Ultrasonic pulse velocity	18
2.8	Mix Prop	ortioning Objectives	19
	2.8.1	The European Guidelines for SCC	20
	2.8.2	EFNARC Proposal	22
	2.8.3	Examples of SCC Mixes	23
2.9	Test Meth	nods For Fresh SCC	25
	2.9.1	Slump Flow Test	26
	2.9.2	Orimet Test	27
	2.9.3	J-Ring Test	29
	2.9.4	L-Box Test	30
	2.9.5	V-Funnel at T _{5minutes}	32
2.10	Acceptan	ce Criteria For Fresh SCC	33
METH		۲V	35
3 1	Introducti	ion	35
3.2	Experime	ental Investigation	35
3.3	Materials		36
	3.3.1	Cement	37
	3.3.2	Fine Aggregate	38

	3.3.3	Coarse Aggregate	38
	3.3.4	Water	39
	3.3.5	Super-plasticizer	39
	3.3.6	Palm Oil Fuel Ash (POFA)	40
3.4	Mix Pro	oportions	41
3.5	Specim	ens Preparation	42
	3.5.1	Mixing Process	42
	3.5.2	Specimens	43
	3.5.3	Curing Process	43
3.6	Fresh S	CC Properties	44
	3.6.1	Slump Flow Test	44
	3.6.2	Orimet Test	45
	3.6.3	J-Ring Test	45
	3.6.4	L-Box Test	46
	3.6.5	V-Funnel at T _{5minutes}	47
3.7	Harden	ed SCC Properties	48
	3.7.1	Compressive Strength Test	48
	3.7.2	Split Tensile Strength Test	49
	3.7.3	Flexural Strength Test	50
	3.7.4	Ultrasonic Pulse Velocity Test	51
RESU	JLTS ANI	D DISCUSSION	53
4.1	Introdu	ction	53
4.2	Fresh S	CC Properties	53
	4.2.1	Slump Flow Test	54
	4.2.2	Orimet Flow Test	55
	4.2.3	J-Ring Test	56
	4.2.4	L-Box Test	56
	4.2.5	V-Funnel at T _{5minutes} Test	57
4.3	Harden	ed SCC Properties	58
	4.3.1	Compressive Strength Test	58
	4.3.2	Split Tensile Strength Test	60
	4.3.3	Flexural Strength Test	62
	4.3.4	Ultrasonic Pulse Velocity	64

4

ix

5	CONCLUSIONS AND RECOMMENDATIONS		
	5.1	Conclusions	65
	5.2	Recommendations For Future Study	66
RE	FERENCI	ES	67
APPENDICES 7			70

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Chemical compositions of POFA	9
2.2	Mixture proportions used	13
2.3	Typical range of constituent materials in SCC	22
2.4	Examples of SCC Mixes in Japan	23
2.5	Examples of SCC Mixes in Europe	24
2.6	Examples of SCC Mixes in U.S	24
2.7	Test methods for fresh SCC	25
2.8	Requirements for SCC	34
3.1	Chemical composition of cement (%)	37
3.2	Mixture Proportions	42
4.1	Fresh SCC Properties	54
4.2	Compressive Strength (MPa)	58
4.3	Split Tensile Strength (MPa)	60
4.4	Flexural Strength (MPa)	62
4.5	Ultrasonic Pulse Velocity of SCC at 28 days	64

LIST OF FIGURES

TTO		110
FIG	URE	NO.

TITLE

PAGE

2.1	Comparison between SCC and conventional concrete	20
2.2	Design process for SCC	21
2.3	Standard Apparatus for Slump-Flow Test	26
2.4	Orimet Flow time apparatus	28
2.5	J-Ring in-conjunction with Slump-Flow	29
2.6	Apparatus for L-Box Test	31
2.7	V-Funnel apparatus	32
3.1	Flow chart of the methodology	36
3.2	Cement	37
3.3	Fine Aggregate (Sand)	38
3.4	Coarse Aggregate (Crushed Granite)	38
3.5	RHEOBUILD 1100 Super-plasticizer	39
3.6	Raw POFA	40
3.7	Los Angeles abrasion machine	40
3.8	Ground POFA	41
3.9	Cube Moulds	43
3.10	Beam Moulds	43
3.11	Compressive Strength Test	49
3.12	Split Tensile Strength Test	50
3.13	Flexural Strength Test	51
3.14	Ultrasonic Pulse Velocity Test	52
4.1	Slump Flow Test	55
4.2	Orimet Flow Time	55
4.3	J-Ring Test	56
4.4	L-Box Test	57

4.5	V-Funnel at T _{5minutes}	57
4.6	Compressive Strength of SCC with 0.40 water/binder ratio	59
4.7	Compressive Strength of SCC with 0.45 water/binder ratio	59
4.8	Compressive Strength of SCC with 0.50 water/binder ratio	59
4.9	Split tensile strength of SCC with 0.40 water/binder ratio	61
4.10	Split tensile strength of SCC with 0.45 water/binder ratio	61
4.11	Split tensile strength of SCC with 0.50 water/binder ratio	61
4.12	Flexural strength of SCC with 0.40 water/binder ratio	63
4.13	Flexural strength of SCC with 0.45 water/binder ratio	63
4.14	Flexural strength of SCC with 0.50 water/binder ratio	63
4.15	Correlation between the Compressive Strength and UPV	64

LIST OF ABBREVIATIONS

ASTM	-	American Society for Testing and Materials
BS	-	British Standards
EFB	-	Empty fruit bunches
HRWRA	-	High range water reducing
POFA	-	Palm oil fuel ash
SCC	-	Self-Compacting Concrete
SCM	-	Supplementary cementitious material
UPV	-	Ultrasonic pulse velocity
VEA	-	Viscosity enhancing admixtures
VMA	-	Viscosity Modifying Admixture

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Concrete is without any doubt a fascinating building material. In one way, it is very simple and anyone can mix water, cement and aggregates, cast it in moulds of almost any shape and finally obtain an artificial stone with strength. In other way, it is an extremely difficult material: no one completely understands its complex behavior both when fresh and when hardened. This ambiguity makes concrete both the most used building material in the world and a material which creates many problems, when not properly designed or placed.

One of the key issues for traditional concrete is that external energy has to be provided to compact it. This can be obtained on site from vibrating pokers and in factories from vibrating tables or alternative methods. In factories there is more time and proper supervision can be done during the process of vibration but on site the conditions are not the same. The concrete which is not properly vibrated can be harmful to the quality of final structure. The quality of non-vibrated concrete is far lower than its intrinsic quality when properly compacted. This may be in forms of loss in strength and decrease in durability. Decrease in durability can often be much more significant, leading to accelerated degradation process such as reinforcement corrosion, frost damage, sulfate attack etc.

This problem can be overcome by the use of Self Compacting Concrete. The concept of self-compacting concrete came into being in 1980's in japan [1]. The high

seismicity of this geographical region requires the use of high levels of steel reinforcement in construction. The use of self-compacting concrete appeared as a solution to improve the filling up of the zones which are not very accessible to conventional methods of concrete compaction. This solution also has the advantage of overcoming the gradual decline in the number of workers qualified to handle and place concrete.

Self-compacting concrete (SCC) is a fluid mixture, which is suitable for placing difficult conditions and also in congested reinforcement, without vibration. In principle, a self- compacting must have a fluidity that allows self-compaction without external energy; remain homogeneous in a form during and after the placing process and flow easily through reinforcement. Self-compacting concrete has recently been used in the pre-cast industry and in some commercial applications. However, the relatively high material cost still hinders the wide spread use of such specialty concrete in various segments of the construction industry, including commercial and residential construction. Compared with conventional concrete of similar mechanical properties, the material cost of self-compacting concrete is more due to the relatively high demand of cementation materials and chemical admixtures including high range water reducing admixtures (HRWRA) and viscosity enhancing admixtures (VEA). SCC targeted for the filling of highly restricted areas and for repair works requires low aggregate volume to facilitate flow among restricted spacing without blockage and ensure the filling of the formwork without consolidation. The incorporation of high volumes of finely ground powder materials is necessary to enhance cohesiveness and increase the paste volume required for successful casting of Self-compacting concrete.

Self-compacting concrete has many advantages over conventional concrete; eliminating the need for vibration; decreasing the construction time and labor cost; reducing the noise pollution; improving the interfacial transitional zone between cement paste and aggregate or reinforcement; decreasing the permeability and improving durability of concrete, and facilitating constructability and ensuring good structural performance.

Proper selection of finely ground materials can enhance the packing density of solid particles and enable the reduction of water or HRWRA demand required to achieve high deformability. It can also reduce viscosity for a given consistency; especially in the case of SCC made with relatively low water/binder ratio. Reducing the free water can decrease the VEA dosage necessary for stability. SCC can also include supplementary cementing material (SCM) mainly to improve the strength and durability of concrete [2]. However, SCM can influence the fresh properties of SCC such as filling ability, passing ability and segregation resistance [3]. Depending on the type and properties of SCM, this effect can be positive or negative for the fresh properties of SCC. The literature review revealed that several SCM's, such as silica fume, ground granulated blast-furnace slag, fly ash and rice husk ash were used to produce SCC with good workability properties, strength and durability [2, 4-6]. Similarly, palm oil fuel ash (POFA) can be used in SCC. Previous studies have been done to produce different SCC mixtures incorporating POFA in the range of 0–15% of cement by weight. The effects of POFA on the filling ability, passing ability and segregation resistance of SCC were examined. It was found that POFA can be used to produce SCC possessing the aforementioned fresh properties within the acceptable ranges [7]. In another study concrete was produced using a particular level of POFA replacement and same or more strength was achieved as compared to OPC concrete. About 30% of cement replacement with POFA showed no significant strength reduction [8].

1.2 Problem Statement

Self-compacting concrete is a flowing concrete with high workability. To achieve flowing concrete low volume of coarse aggregates is used, but the reduction in volume of coarse aggregates require high volume of paste, i.e. cement and fine aggregates, and use of super-plasticizers. Increased volume of cement and addition of super-plasticizer leads to higher cost. The cost of cement can be reduced by using supplementary cementitious materials. Fly ash, silica fumes and Ground blastfurnace slag has been used in SCC. Malaysia has a high production rate of POFA, and previous studies have been conducted using low volume of POFA as supplementary cementitious material in SCC. This study intends to provide fresh and hardened properties of SCC using high volume of POFA, and determining its practicality.

1.3 Objectives

Following are the objectives of study:

- i. To determine the fresh properties of self-compacting concrete incorporating palm oil fuel ash.
- ii. To investigate the hardened properties of self-compacting concrete incorporating palm oil fuel ash.
- iii. To study the effect of different water/binder ratios on fresh and hardened properties of self-compacting concrete incorporating palm oil fuel ash.

1.4 Significance of Study

The advantages of SCC are already recognized by the concrete industry. Design and construction specifications are urgently needed to give designers another option in meeting the demands of high performance concrete in construction. The use of POFA as cement replacement material in SCC will fully utilize the natural resource instead of becoming an industrial waste material. The replacement can reduce the cost of concrete, since the increase in the cost of cement. SCC using POFA has a good potential for greater acceptance and wider applications in civil infrastructure works in Malaysia and other parts of the world.

1.5 Scope of Study

The study is based on laboratory work and it focuses on the use of high volume of Palm oil fuel ash in the development of self-compacting concrete. Percentages of palm oil fuel ash are 0%, 30% and 60% by weight of cement content and water/binder ratio of 0.40, 0.45 and 0.50. Super-plasticizer is added from 2% to 4%. Fresh properties of Self-compacting concrete are examined by Slump-flow test, Orimet test, J-Ring test, L-box and V-funnel at T_{5minutes}. Also hardened properties are determined in terms of compressive strength, flexural strength, split tensile strength and ultrasonic pulse velocity test.

REFERENCES

- 1. Okamura, H., K. Ozawa, and M. Ouchi, *Self-compacting concrete*. structural Concrete, 2000. **1**(1): p. 3-17.
- 2. Safiuddin, M., J. West, and K. Soudki, *Hardened properties of self-consolidating high performance concrete including rice husk ash.* Cement and Concrete Composites, 2010. **32**(9): p. 708-717.
- 3. Safiuddin, M., J. West, and K. Soudki, *Flowing ability of the mortars formulated from self-compacting concretes incorporating rice husk ash.* Construction and Building Materials, 2011. **25**(2): p. 973-978.
- 4. Safiuddin, M., *Development of self-consolidating high performance concrete incorporating rice husk ash.* 2008, University of Waterloo.
- 5. Lachemi, M., Development of cost-effective self-consolidating concrete incorporating fly ash, slag cement, or viscosity-modifying admixtures. ACI Materials Journal, 2003. **100**(5).
- 6. Khayat, K., *Optimization and performance of air-entrained, self-consolidating concrete*. ACI Materials Journal, 2000. **97**(5).
- 7. Safiuddin, M. and M. Jumaat, *Fresh properties of self-consolidating concrete incorporating palm oil fuel ash as a supplementary cementing material.* Chiang Mai Journal of Science, 2011. **38**(3): p. 389-404.
- 8. Karim, M., *Strength of Concrete as Influenced by Palm Oil Fuel Ash.* Australian Journal of Basic & Applied Sciences, 2011. **5**(5).
- 9. Li, Z., *Advanced concrete technology*. 2011: John Wiley & Sons.
- 10. Sata, V., C. Jaturapitakkul, and K. Kiattikomol, *Utilization of palm oil fuel* ash in high-strength concrete. Journal of Materials in Civil Engineering, 2004. **16**(6): p. 623-628.
- 11. Shehu, I. and A. Awal, *Mechanical properties of concrete incorporating high volume palm oil fuel ash.* Advanced Materials Research, 2012. **599**: p. 537-540.
- 12. Awal, A. and S.I. Abubakar, *Properties of concrete containing high volume palm oil fuel ash: ashort-term investigation*. Malaysian Journal of Civil Engineering, 2011. **23**(2): p. 164-176.
- 13. Shehu, I., *Durability and thermal gravimetic analysis of high volume palm oil fuel ash.* 2014, University Technology Malaysia.
- 14. Gagne, R. and M. Pigeon, *Deicer salt scaling resistance of high-performance concrete*. ACI Special Publication, 1990. **122**.

- Ye, G., Influence of limestone powder used as filler in SCC on hydration and microstructure of cement pastes. Cement and Concrete Composites, 2007. 29(2): p. 94-102.
- 16. Poppe, A.-M. and G. De Schutter, *Cement hydration in the presence of high filler contents*. Cement and Concrete Research, 2005. **35**(12): p. 2290-2299.
- Assie, S., G. Escadeillas, and V. Waller, *Estimates of self-compacting concrete 'potential'durability*. Construction and Building Materials, 2007. 21(10): p. 1909-1917.
- 18. Felekoğlu, B., et al., *The effect of fly ash and limestone fillers on the viscosity and compressive strength of self-compacting repair mortars.* Cement and concrete research, 2006. **36**(9): p. 1719-1726.
- 19. Türkmen, İ., Influence of different curing conditions on the physical and mechanical properties of concretes with admixtures of silica fume and blast furnace slag. Materials letters, 2003. **57**(29): p. 4560-4569.
- 20. Uysal, M. and K. Yilmaz, *Effect of mineral admixtures on properties of self-compacting concrete*. Cement and Concrete Composites, 2011. **33**(7): p. 771-776.
- 21. De Schutter, G., et al., *Self-compacting concrete*. 2008: Whittles Publishing.
- 22. Grauers, M., Rational production and improved working environment through using self-compacting concrete. EC Brite-EuRam Contract No. BRPR-CT96-0366, 1997.
- 23. Gibbs, J. and W. Zhu. Strength of hardened self-compacting concrete. in Proceedings of First international RILEM Symposium on Self-Compacting Concrete (PRO 7), Stockholm, Suede. 1999.
- 24. Klug, Y., Comparison of the hardened properties of self-compacting and normal vibrated concrete. in 3rd RILEM Symposium on Self Compacting Concrete, Reykjavik. 2003.
- 25. Sonebi, M. and P. Bartos. Hardened SCC and its bond with reinforcement. in Proceeding of First International RILEM Symposium on Self-Compacting Concrete (PRO 7), Stockholm, Sweden. 1999.
- 26. Parra, C., Mechanical properties of self-compacting concretes. in 5th International RILEM symposium on self-compacting concrete. 2007. RILEM Publications SARL.
- 27. Domone, P., A review of the hardened mechanical properties of selfcompacting concrete. Cement and Concrete Composites, 2007. **29**(1): p. 1-12.
- 28. Shetty, M., *Concrete Technology: Theory & Practice*. 2005: Chand & Company.
- 29. Concrete, S.-C., *The European Guidelines for Self-Compacting Concrete*. 2005.
- 30. EFNARC, Specifications and Guidelines for Self-Consolidating Concrete. 2002, European Federation of Suppliers of Specialist Construction Chemicals (EFNARC): Surrey, UK.

- 31. Ouchi, M., Applications of self-compacting concrete in Japan, Europe and the United States. in International Symposium on High Performance Computing (ISHPC). 2003.
- 32. Bartos, P. An appraisal of the Orimet Test as a Method for On-site Assessment of Fresh SCC Concrete. in International Workshop on Self-Compacting Concrete, Japan. 1998.
- 33. ASTMC1621/C1621M, Standard Test Method for Passing Ability of Self-Consolidating Concrete by J-Ring. 2009, American Society for Testing Materials: Philadelphia, USA.
- 34. Ozawa, K., N. Sakata, and H. Okamura. *Evaluation of self-compactibility of* fresh concrete using the funnel test. in *PROCEEDINGS-JAPAN SOCIETY OF CIVIL ENGINEERS*. 1994. DOTOKU GAKKAI.
- 35. ASTMC618, Standard Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete. 2012, American Society for Testing Materials: Philadelphia, USA.
- 36. BS-1881:116, *Method for determination of compressive strength of concrete cubes*. 1983, British Standards Institution.
- 37. ASTMC496/C496M, Standard Test Method for Splitting Tensile Strength of *Cylindrical Concrete Specimens*. 2011, American Society for Testing and Materials: Philadelphia,USA.
- 38. ASTMC293/C293, Standard Test Method for Flexural Strength of Concrete (Using Simple Beam With Center-Point Loading). 2010, American Society for Testing and Materials: Philadelphia, USA.
- 39. ASTMC597, *Standard Test Method for Pulse Velocity Through Concrete*. 2009, American Society for Testing and Materials: Philadelphia,USA.
- 40. Grünewald, S., *Test methods for filling ability of SCC. Summary report of work package 3.1.* Delft University of Technology and Betongindustri, Delft, The Netherlands, 2004.
- 41. ASTMC192/C192M, Standard Practice for Making and Curing Concrete Test Specimens in the Laboratory. 2013, American Society for Testing and Materials: Philadelphia,USA.