

INFLUENCE OF ULTRASONIC VIBRATION ON TIN COATED BIOMEDICAL
TI-13Zr-13Nb ALLOY

ARMAN SHAH BIN ABDULLAH

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy (Mechanical Engineering)

Faculty of Mechanical Engineering
Universiti Teknologi Malaysia

OCTOBER 2015

Dedicated to

My wife, Siti Nurul Fasehah Binti Ismail

My father, Abdullah Bin Ahamad

My mother, Saadiyah Binti Ismail

And

My mother-in-law, Siti Khadijah Binti Draman

ACKNOWLEDGEMENT

First and foremost, i would like to thank Allah Almighty for His guidance, helping and giving me the strength to complete this thesis. A special thanks to my supervisor Assoc. Prof. Dr. Izman bin Sudin for his advice, encouragement and continuous assistance whenever required and the same goes to my co supervisor Prof. Dr.Mohammed Rafiq bin Dato' Abdul Kadir for his assistance and advice.

I would like also to dedicate my sincere thanks to all technical staffs at Production and Material Science Laboratories, UTM for their helps and supports in completing this project. Their time and patience helping me throughout this project execution are very much appreciated. My gratitude goes to Universiti Teknologi Malaysia (UTM) for research funding through research grant (GUP Q.J130000.7124.02H60). Special thanks to Universiti Pendidikan Sultan Idris (UPSI) and Ministry of Education (MOE) for sponsoring my postgraduate studies.

I am also forever indebted to my parents Abdullah bin Ahamad and Saadiah binti Ismail, and my wife Siti Nurul Fasehah binti Ismail who give me real love, pray, moral support, and all their doa have. The magnitude of their contribution cannot be expressed in a few words, so it is to them that this thesis is dedicated. Finally, I would like to thank to all my friends and others who have contributed directly or indirectly towards the success of this PhD project.

ABSTRACT

Biomedical grade of titanium alloys are prone to undergo degradation in body fluid environment. Surface coating such as Physical Vapor Deposition (PVD) can serve as one of the alternatives to minimize this issue. Past reports highlighted that coated PVD layer consists of pores, pin holes and columnar growth which act as channels for the aggressive medium to attack the substrate. Duplex and multilayer coatings seem able to address this issue at certain extent but at the expense of manufacturing time and cost. In the present work, the effect of ultrasonic vibration parameters on PVD-Titanium Nitride (TiN) coated Ti-13Zr-13Nb biomedical alloy was studied. Disk type samples were prepared and coated with TiN at various conditions: bias voltage (-125V), substrate temperature (100 to 300 °C) and nitrogen gas flow rate (100 to 300 sccm). Ultrasonic vibration was then subsequently applied on extreme high and low conditions of TiN coated samples at two different frequencies (8 kHz, 16 kHz) and three set of exposure times (5 min, 8 min, 11 min). Encouraging results of PVD coating are observed on the samples coated at higher polarity of nitrogen gas flow rate (300 sccm) and substrate temperature (300 °C) in terms of providing better surface morphology and roughness, coating thickness and adhesion strength. All TiN coated samples treated with ultrasonic vibration exhibit higher corrosion resistance than the untreated ones. Microstructure analysis under (Field Emission Scanning Electron Microscopy (FESEM) confirms that the higher ultrasonic frequency (16 kHz) and the longer exposure time (11 minutes) produce the most compact coating. It is believed that hammering effect from ultrasonic vibration reduces the micro channels' size in the coating and thus decelerates the corrosion attack. Nano indentation test conducted on the ultrasonic treated samples provides a higher Hardness/Elasticity (H/E) ratio than untreated ones. This suggests that the ultrasonic vibration treated samples could also have a lower wear rate.

ABSTRAK

Gred bioperubatan aloi titanium lebih cenderung mengalami kakisan dalam persekitaran cecair badan. Salutan permukaan seperti *Physical Vapor Deposition* (PVD) boleh digunakan sebagai salah satu alternatif untuk mengurangkan masalah ini. Hasil kajian sebelum ini menunjukkan bahawa lapisan salutan PVD terdiri daripada liang-liang, lubang pin, dan pertumbuhan kolumnar yang bertindak sebagai salah satu saluran untuk cecair menyerang substrat. Substrat yang disalut dengan dua lapisan atau lebih dilihat dapat mengatasi masalah ini pada kadar tertentu tetapi ianya melibatkan kos pembuatan yang tinggi dengan masa yang panjang. Dalam kajian ini, kesan parameter getaran ultrasonik ke atas PVD- *Titanium Nitride* (TiN) yang disalut ke atas aloi bioperubatan Ti-13Zr-13Nb telah dikaji. Sampel berbentuk cakera disediakan dan disalut dengan TiN pada voltan pincang (-125V), suhu substrat (100 hingga 300 °C) dan kadar aliran gas nitrogen (100-300 sccm). Getaran ultrasonik kemudiannya dikenakan ke atas sampel yang disalut dengan TiN dalam keadaan dua frekuensi yang berbeza (8 kHz, 16 kHz) dan tiga masa pendedahan (5 min, 8 min, 11 min). Hasil kajian salutan PVD yang menggalakkan diperolehi ke atas sampel yang dikenakan pada kadar aliran gas nitrogen dan suhu substrat yang tinggi dari segi morfologi dan keserataan permukaan, ketebalan salutan dan kekuatan lekatan yang lebih baik. Semua sampel yang dirawat dengan salutan TiN menggunakan getaran ultrasonik menunjukkan ketahanan kakisan yang tinggi jika dibandingkan dengan sampel tanpa rawatan. Analisis struktur mikro menggunakan *Field Emission Scanning Electron Microscopy* (FESEM) mengesahkan bahawa ultrasonik frekuensi yang tinggi dengan masa yang lama menghasilkan lapisan yang paling padat. Ini adalah disebabkan kesan ketukan yang dihasilkan oleh getaran ultrasonik yang mana dapat mengecilkan saiz saluran pada salutan tersebut dan dengan itu mengurangkan serangan kakisan. Ujian lekukan nano yang dijalankan ke atas sampel yang dirawat dengan getaran didapati menghasilkan nilai nisbah *Hardness/Elasticity* H/E yang tinggi jika dibandingkan dengan sampel tanpa rawatan. Ini menunjukkan bahawa sampel yang dikenakan rawatan getaran ultrasonik juga boleh menghasilkan kadar kehausan yang lebih rendah.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENTS	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xi
	LIST OF FIGURES	xiii
	LIST OF ABBREVIATIONS	xx
	LIST OF APPENDICES	xxii
1	INTRODUCTION	1
	1.1 Background of the problem	1
	1.2 Problem statements	3
	1.3 Objectives of the study	3
	1.4 Scopes of the Study	4
	1.5 Significance of the Study	4
	1.6 Thesis organization	5
2	LITERATURE REVIEW	6
	2.1 Introduction	6
	2.2 Implant biomaterials	6
	2.3 Titanium and its alloys	10

2.3.1	Unalloyed titanium	11
2.3.2	Alpha and near alpha alloy	11
2.3.3	Alpha- beta alloy	12
2.3.4	Beta alloy	12
2.3.5	Ti-13Zr-13Nb	13
2.4	Issues in biomaterials	16
2.5	Overview of surface modification techniques	20
2.6	Physical vapour deposition	25
2.6.1	Principle of arc vapour deposition and typical issues	34
2.6.2	TiN coating via PVD technique	37
2.7	Ultrasonic and its types	39
2.7.1	Ultrasonic machining	40
2.7.2	Principle of ultrasonic machining	42
2.8	Evaluation of coating performance	43
2.8.1	Overview of corrosion theory and fundamental	43
2.8.2	Corrosion principle and mechanism	44
2.8.3	Types of corrosion	46
2.8.3.1	Uniform corrosion	46
2.8.3.2	Galvanic corrosion	46
2.8.3.3	Crevice corrosion	49
2.8.3.4	Pitting corrosion	49
2.8.3.5	Selective leaching or dealloying	50
2.8.3.6	Erosion corrosion	50
2.8.3.7	Intergranular corrosion (IGC)	50
2.8.4	Corrosion testing techniques	52
2.8.4.1	Tafel plot	52
2.8.4.2	Electrochemical impedance spectroscopy (EIS)	54
2.8.5	Coating adhesion strength measurement	55
2.8.6	Nanoindentation testing	58
2.9	Summary of literature review	62

3	METHODOLOGY	64
3.1	Introduction	64
3.2	Overview of methodology	64
3.3	Substrate material and preparation	65
3.3.1	Cutting process	65
3.3.2	Grinding and polishing of substrate metal	67
3.3.3	Cleaning of the substrate	70
3.4	CAPVD coating procedure-stage I preliminary experiment	70
3.5	Experiment setup for stage II and III	72
3.5.1	CAPVD coating procedure – stage II	72
3.5.2	Ultrasonic assisted ball impingement procedure	73
3.6	Analytical and material characterizations	75
3.6.1	Surface morphology and compound analysis	75
3.6.2	TiN coating adhesion strength analysis	77
3.6.3	Corrosion test procedure	78
3.6.3.1	Tafel plot	78
3.6.3.2	Electrochemical impedance spectroscopy (EIS)	79
3.6.3.3	Hardness-elasticity (H/E) analysis	80
4	RESULTS AND DISCUSSION	81
4.1	Introduction	81
4.2	Stage I - Preliminary experimental results and discussion	81
4.3	Stage II – Experimental results and discussion	86
4.3.1	Introduction	86
4.3.2	Effect of CAPVD parameters on properties of TiN coating	86
4.4	Stage III – Experimental results and discussion	96
4.4.1	Ultrasonic treatment (8 kHz) on TiN coated	

	samples (extreame high condition)	96
4.4.2	Ultrasonic treatment (8 kHz) on TiN coated samples (extreame low condition)	106
4.4.3	Ultrasonic treatment (16 kHz) on TiN coated samples (extreame high condition)	114
4.4.4	Ultrasonic treatment (16 kHz) on TiN coated samples (extreame low condition)	122
4.4.5	Effect of ultrasinic treatment on corrosion properties of TiN coated sample	130
4.5	Summary of findings	139
5	CONCLUSIONS AND RECOMMENDATIONS	140
5.1	Introduction	140
5.2	Conclusions	140
5.3	Recommendations for future works	141
	REFERENCES	143
	Appendices A-B	162-167

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Surgical use of biomaterial	8
2.2	Class of materials used in the body	9
2.3	Chemical composition range of Ti-13Nb-13Zr	13
2.4	Classification of biomaterials based on its interaction with its surrounding tissue	18
2.5	Surface modification methods used for titanium and its alloys implants	21
2.6	Steady state electrode material potential, volts referenced to saturated calomel half-cell	48
2.7	Advantages and disadvantages of scratch test methods	57
2.8	Comparison of critical load values obtained by scratch testing	58
3.1	Mechanical properties of Ti-13Zr-13Nb	65
3.2	CAPVD parameters used in preliminary experiment	71
3.3	CAPVD parameters used in stage II	72
3.4	Parameters for ultrasonic milling	75
4.1	Summary of output data from nanoindentation test for ultrasonic treated on TiN at 8 kHz for different exposure times (extreme high condition)	102

4.2	Corrosion parameters calculated from Tafel and EIS for ultrasonic treated on TiN coating at 8 kHz for different holding times (extreme low condition)	105
4.3	Summary of output data from nanoindentation test for ultrasonic treated at 8 kHz for deferent exposure times(extreme low condition)	110
4.4	Corrosion parameters calculated from Tafel and EIS for ultrasonic treated on TiN coating at 8 kHz for different times (extreme low condition)	113
4.5	Summary of output data from nanoindentation test for ultrasonic treated at 16 kHz for deferent exposure times (extreme high condition)	118
4.6	Corrosion parameters calculated from Tafel and EIS for ultrasonic treated on TiN coating at 16 kHz for different exposure times (extreme high condition)	121
4.7	Summary of output data from nanoindentation test for ultrasonic treated at 16 kHz for deferent exposure times (extreme low condition)	126
4.8	Corrosion parameters calculated from Tafel and EIS for ultrasonic treated on TiN coating at 16 kHz for different holding times (extreme low condition)	130

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	Elastic modulus of metallic biomaterials	10
2.2	Cross sectioned views for multilayer Ti ₂ N ceramic coating on NdFeB substrate (a) crater with thin layer of ceramic coating (b) and pin hole in the ceramic coating.	30
2.3	Schematic diagram of CAPVD process.	37
2.4	Main elements of an ultrasonic machining system.	41
2.5	Material removal mechanisms in USM.	43
2.6	Electric double layers at metal-electrolyte interface in the presence of chemisorbed anions	45
2.7	The electrochemical reactions associated with the corrosion of ferum in an acid solution.	45
2.8	Excitation waveform for tafel plot.	53
2.9	Excitation measurement tafel plot.	54
2.10	Schematic of the nanoindentation of an elasto-plastic solid by a conical cone at full load and unload	60
2.11	Schematic of the load–displacement curve corresponding to the nanoindentation depicted by Figure 2.10	61
2.12	Wear behaviour versus Si content in CrN-based coating systems. on specific wear rate and H^3/E^2	62

3.1	Flow chart of overall research methodology	66
3.2	Buehler Isomet 4000 precision cutter machine	67
3.3	Sample after cutting	67
3.4	Strues Tegramin 25 polishing machine	68
3.5	Summarize of grinding and polishing step on Titanium substrate	69
3.6	Substrate cleaning equipment (a) Bransonic 2500 (b) Steam cleaner	70
3.7	Cathodic Arc Evaporation machine.	71
3.8	Sonic mill ultrasonic machine AP-10001X)	74
3.9	Steel ball used for impinging the TiN coated substrate	74
3.10	Field Emission Scanning Electron Microscopy available at faculty of mechanical engineering	76
3.11	X Ray Diffraction available at AMREC, SIRIM	76
3.12	Scratch tester machine available at UniMAP, Perlis	77
3.13	(a) Overall set-up of corrosion test on potential machine (b) Enlargement of corrosion cell set-up	79
3.14	Nanoindenter testing machine	80
4.1	SEM micrographs of TiN coating on Ti-13Zr 13Nb at different substrate temperatures and nitrogen gas flow rates.	82
4.2	Cross sectional views of TiN coating thickness obtained at different substrate temperatures and nitrogen gas flow rates	83
4.3	Effect of substarte temperature and nitrogen gas flow rate on coating thickness	84
4.4	Surface roughness of TiN coated at different nitrogen gas flow rate and substrate temperature	85

4.5	XRD patterns of TiN coating deposited at 100 sccm (a) 100°C (b) 200°C, (c) 300°C of substrate temperature, at 200sccm (d) 100°C (e) 200°C (f) 300°C, and at 300sccm, (g) 100°C, (h) 200°C. (i) 300°C	87
4.6	SEM micrograph for TiN coated at different substrate temperature and nitrogen gas flow rate	88
4.7	Size distribution of TiN coating microdroplets at various nitrogen gas flow and substrate temperatures	89
4.8	Cross section view of TiN after coated at different nitrogen gas flow and substrate temperature	91
4.9	Effect of substrate temperature and nitrogen gas flow rate on coating thickness.	92
4.10	Effect of substrate temperature and nitrogen gas flow rate on surface roughness	93
4.11	Optical image of scratch tracks along with graphs of friction coefficient, friction force and normal forces at bias voltage, substrate temperature and nitrogen gas flow rate,	95
4.12	Critical load of TiN coated at various substrate temperature and nitrogen gas flow rate.	96
4.13	Surface morphology of extreme high conditions of TiN after ultrasonic treated at 8 kHz for exposure time (a) 5 minute (b) 8 minute and (c) 11 minute (extreme high condition)	98
4.14	Cross sectional view of TiN after ultrasonic treated at 8 kHz for exposure times (a) 5 minute (b) 8 minute and (c) 11 minute (extreme high condition)	99
4.15	Effect of ultrasonic treatment on TiN at 8 kHz for different exposure times (extreme high condition)	100

4.16	Load vs. displacement curve of TiN coated after ultrasonic treated at 8 kHz for exposure times (a) 5 min, (b) 8 min, and (c) 11 min (extreme high condition)	101
4.17	Tafel plots of TiN coated after ultrasonic treated at 8 kHz for exposure times a) 5 min (b) 8 min, and (c) 11 min, 16 kHz (extreme high condition)	103
4.18	Nyquist plots for of TiN coated after ultrasonic treated at 8 kHz for various exposure times (extreme high condition)	104
4.19	Bode Plots (a) $\log z $ Vs $\log f$ and (b) Phase angle Vs $\log f$ for ultrasonic treated on TiN coating at 8 kHz for various exposure times (extreme high condition)	105
4.20	Surface morphology of TiN after ultrasonic treated at 8 kHz for exposure time (a) 5 minute (b) 8 minute and (c) 11 minute (extreme low condition)	107
4.21	Cross sectional view of TiN after ultrasonic treated at 8 kHz for exposure times (a) 5 minute (b) 8 minute and (c) 11 minute (extreme low condition)	108
4.22	Effect of ultrasonic treatment on TiN at 8 kHz for different exposure times (extreme low condition)	109
4.23	Load vs. displacement curve of TiN coated after ultrasonic treated at 8 kHz for times (a) 5 min, (b) 8 min, and (c) 11 min (extreme low condition)	110
4.24	Tafel plots of TiN coated after ultrasonic treated at 8 kHz for exposure times a) 5 min (b) 8 min, and (c) 11 min, (extreme low condition)	111
4.25	Nyquist plots for of TiN coated after ultrasonic treated at 8 kHz for various exposure times (extreme low condition)	112
4.26	Bode Plots (a) $\log z $ Vs $\log f$ and (b) Phase angle Vs	

	log f for ultrasonic treated on TiN coating at 8 kHz for various holding times	113
4.27	Surface morphology of TiN after ultrasonic treated at 16 kHz for exposure time (a) 5 minute (b) 8 minute and (c) 11 minute (extreme high condition)	115
4.28	Cross sectional view of TiN after ultrasonic treated at 16 kHz for exposure times (a) 5 minute (b) 8 minute and (c) 11 minute (extreme high condition)	116
4.29	Effect of ultrasonic treatment on TiN at 16 kHz for different exposure times (extreme high condition)	117
4.30	Load vs. displacement curve of TiN coated after ultrasonic treated at 16 kHz for holding times (a) 5 min, (b) 8 min, and (c) 11 min	118
4.31	Tafel plots of TiN coated after ultrasonic treated at 8 kHz for exposure times a) 5 min (b) 8 min, and (c) 11 min, (extreme high condition)	119
4.32	Nyquist plots for of TiN coated after ultrasonic treated at 16 kHz for various exposure times (extreme high condition)	120
4.33	Bode Plots (a) $\log z $ Vs $\log f$ and (b) Phase angle Vs $\log f$ for ultrasonic treated on TiN coating at 16 kHz for various exposure times (extreme high condition)	121
4.34	Surface morphology of TiN after ultrasonic treated at 16 kHz for exposure times (a) 5 minute (b) 8 minute and (c) 11 minute (extreme low condition)	123
4.35	Cross sectional view of TiN after ultrasonic treated at 16 kHz for exposure times (a) 5 minute (b) 8 minute and (c) 11 minute (extreme low condition)	124
4.36	Effect of ultrasonic treatment on TiN at 16 kHz for different holding times (extreme low condition)	125

4.37	Load vs. displacement curve of TiN coated after ultrasonic treated at 16 kHz for exposure times (a) 5 min, (b) 8 min, and (c) 11 min (extreme low condition)	126
4.38	Tafel plots of TiN coated after ultrasonic treated at 16 kHz for exposure times (a) 5 min (b) 8 min, and (c) 11 min, (extreme low condition)	127
4.39	Nyquist plots for of TiN coated after ultrasonic treated at 16 kHz for various holding times (extreme low condition)	128
4.40	Bode Plots (a) $\log z $ Vs $\log f$ and (b) Phase angle Vs $\log f$ for ultrasonic treated on TiN coating at 16 kHz for various holding times (extreme low condition)	129
4.41	Equivalent circuit to fit electrochemical impedance data	130
4.42	SEM micrographs of TiN coated samples (extreme high PVD coating condition) after being treated under ultrasonic vibration at different frequency and exposure times	132
4.43	SEM micrographs of TiN coated samples (extreme low PVD coating condition) after being treated under ultrasonic vibration at different frequency and exposure times	133
4.44	Effect of TiN coated samples after subjected with ultrasonic vibration a) before (b) after ultrasonic vibration	134
4.45	Effect of ultrasonic frequencies on coating thickness at different exposure times on (a) high and (b) low extreme conditions	135
4.46	Schematic diagram for coated sample before and after subjected with ultrasonic vibration	135
4.47	Effect of ultrasonic frequencies on coating hardness at	

	different exposure times on (a) high and (b) low extreme conditions	136
4.48	Effect of ultrasonic frequencies on current density at different holding time on (a) high and (b) low extreme conditions	137
4.49	Effect of ultrasonic frequencies on charge transfer resistance at different holding time on (a) high and (b) low extreme conditions	138
4.50	Schematic diagrams representing the phenomena occur when sample coated with TiN immersed in Kokubo solution along with their equivalent circuits	138

LIST OF ABBREVIATIONS

A	-	Area
a-C	-	Amorphous carbon
CA-PVD	-	Cathodic arc physical vapour deposition
C_{dl}	-	Double layer capacitance
Cp-Ti	-	Commercial pure titanium
CVD	-	Chemical vapour deposition
DLC	-	Diamond like carbon
E_{corr}	-	Corrosion potential
EIS	-	Electrochemical vapour deposition
FESEM	-	Field emission scanning electron microscope
FRA	-	Frequency response analyser
H/E	-	Hardness/Elasticity
HFCVD	-	Hot filament chemical vapour deposition
I_{corr}	-	Corrosion current density
IGC		Intergranular corrosion

OCP	-	Open circuit potential
PVD	-	Physical vapor deposition
R_{ct}	-	Charge transfer resistance
SCE	-	Saturated calomel electrode
sccm	-	Standard cubic centimetres per minute
SiC	-	Silicon carbide
TiN	-	Titanium nitride
TiAlN	-	Titanium aluminum nitride
UBM	-	Unbalanced magnetron sputtering
USM	-	Ultrasonic machining
XRD	-	X-ray Diffraction Spectroscopy

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Output images of microdroplets counting using image analyser	162
B	Effect of CAPVD parameters adhesion strength of TiN coating	163

CHAPTER 1

INTRODUCTION

1.1 Background of the problem

The field of biomaterial has caught attention of researchers because it can increase the length and quality of human life. Natural and artificial biomaterials are used to make implants or structures that replace biological structures lost to diseases or accidents. The application of biomaterial in musculoskeletal implants include dental implants, artificial hips, and knees prostheses and incorporate the screws, plates, and nails in these devices [1]. The materials used in surgical implants include stainless steel (316LSS), Co-Cr-based alloys, and Ti alloys. Titanium based alloys are preferable due to their excellent biocompatibility, outstanding corrosion resistance, relatively good fatigue resistance, and lower elastic modulus [2, 3].

Several types of titanium alloys have been developed and one of them is Ti-6Al-4V. Ti-6Al-4V was the first standard alloys employed as a biomaterial for implants. Although this alloy has an excellent reputation in terms of its biocompatibility and corrosion resistance, studies have shown that the release of aluminium and vanadium ions from this alloy causes long term problem, such as peripheral neuropathy, osteomalacia, and Alzheimer diseases [4]. Consequently other titanium alloys group have been developed as alternatives to the Ti-6Al-4V

alloy. Among them, Ti-13Zr-13Nb is the most attractive biomaterial due to its low Young's modulus and non-toxic composition. It has been reported that Ti-13Zr-13Nb alloy is preferred for biomedical applications due to its superior corrosion resistance and biocompatibility. The good biocompatibility of this alloy is due to the corrosion products of the minor alloying elements (niobium and zirconium) that are less soluble than those of aluminium and vanadium. This material also has good tensile and corrosion resistance compared to Ti-6Al-4V and Ti-6Al-7Nb alloys [5].

Although the Ti-13Zr-13Nb alloy has excellent corrosion resistance and biocompatibility under normal conditions, it is still subject to corrosion, especially when it is in contact with body fluids. The environment found in the human body is very harsh owing to the presence of chloride ions and proteins. As an implant corrodes, it releases toxic ions and causes inflammation, which may require further surgery [6]. This issue can be addressed by using a surface coating or surface modification techniques. Several studies have been conducted that attempt to increase of Ti-13Zr-13Nb. Techniques including thermal oxidation [2, 7-12], anodic oxidation [13-16], thermal spray [17], laser nitriding [18], plasma spray [19, 20], Chemical Vapour Deposition (CVD) [21], and Ion Implantation [22] have all been investigated. The processing temperature of surface modification techniques in these studies are relatively high (600 – 2000 °C), which restricts the type of substrates that can be used, as well as causing unexpected phase transitions and excessive residual stresses. Nevertheless, a few studies use surface modification techniques with low processing temperatures. Other surface modification techniques such as Physical Vapour Deposition (PVD) offer promising results using low processing temperatures (<500° C) over a wide range of coating thickness. In this thesis, PVD coating on Ti-13Zr-13Nb was proposed as a way to improve the corrosion resistance of medical implants.

1.2 Problem statements

Surface coatings, such as PVD, can minimize the corrosion rate of titanium alloys that are exposed to body fluids. Past reports indicated that coated PVD layers have pores, pin holes, and columnar growths that act as channels for aggressive mediums to attack the substrate [23-26]. Duplex and multilayer coatings address this issue but at the expense of manufacturing time and cost. Therefore, an alternative method is needed to reduce the penetration of body fluids and react with bare substrate. One of possible surface modifications to PVD coatings uses a mechanical treatment. Several studies have demonstrated that sand blasting PVD coatings increases the compactness and hardness of the coating, which leads to lower wear rates [27-34]. However, very limited literature exists on surface mechanical treatment especially on the application of ultrasonic vibration to reduce corrosion attack of TiN coated Ti based implants. Most researchers have reported the behaviour of mechanical treatment on wear rate mechanism only. Therefore, a detailed study is needed to evaluate the effect of ultrasonic treatments on PVD-TiN coated Ti-13Zr-13Nb alloys in terms of corrosion resistance.

1.3 Objectives of the study

The objectives of this study were:

- i. To analyse the effect of PVD coating parameters on the surface morphology, coating thickness, and adhesion strength of TiN coated biomedical grade Ti alloys.
- ii. To investigate the effect of ultrasonic vibration treatment on the hardness and coating thickness of TiN coated samples.
- iii. To compare the corrosion performance of ultrasonic treated and untreated TiN coating samples under simulated body fluids.

1.4 Scopes of the study

The study was conducted using the following limits:

- i. Ti-13Zr-13Nb was used as the substrate material.
- ii. The variable CAPVD parameters included nitrogen gas flow rates (100-300 sccm) and substrate temperature (100-300° C). The bias voltage was fixed at -125V.
- iii. An ultrasonic machine (Sonic mill AP-10001X) was used to hammer the TiN coated samples using micro steel balls.
- iv. Ultrasonic parameters varied from 8 to 16 kHz for 5, 8, and 11 minutes of exposure time.
- v. FESEM was used to characterize surface morphology and coating thickness. A nano-indenter was used to determine TiN hardness.
- vi. Tafel plot and EIS were used to evaluate corrosion on untreated and treated TiN coated samples.
- vii. A Kokubo solution was used to simulate body fluids during corrosion resistance testing.

1.5 Significance of the study

The use of ultrasonic vibrations as a post treatment on TiN coated layers was expected to reduce corrosion when the implant was subjected to body fluids. The hypothesis was that ultrasonic vibration would provide micro-steel ball impingement that would result in a TiN coated layer with higher hardness and less porosity. The technique applied was less expensive than the multilayer and duplex coatings suggested by other researchers. The application of TiN coated Ti-13Zr-13Nb is appropriate for orthopaedic plates that are commonly used in bone surgery. The success of this method will improve the life of prosthesis and reduce implant revision costs. In addition, this study will help manufacturers produce more

sustainable biomedical implants by increasing the surface hardness of the implant and thus providing better wear resistance capabilities. This study will also add to the knowledge and understanding of the behaviour of TiN coatings on biomedical implants.

1.6 Thesis organization

This thesis consists of five chapters. Chapter 1 is the introduction, which covers the background of research, the problem statement, and the objectives, scope, and significance of study. Chapter 2 provides an overview of general implant materials, a review of surface modification techniques, PVD, ultrasonic vibration, and an evaluation of coating performances. At the end of this chapter, the literature is summarized and gaps in the research are discussed.

In Chapter 3, the experimental approach adopted in this study is discussed including the substrate material and its preparation, and an explanation of the procedure for testing CAPVD and ultrasonic treatments. The analytical equipment used in this study is also discussed in this chapter, including a corrosion test, adhesion strength, nano indenter, FESEM, and XRD.

In Chapter 4, the results of Experiment Stages I, II and III are described and discussed. Experiment Stage I discusses the preliminary trials conducted before the actual experiment began. In Stage II, the effects of CAPVD parameters on surface morphology, coating thickness, and adhesion strength are discussed. Stage III describes the effect of ultrasonic treatments under extreme PVD conditions on corrosion resistance and hardness. Chapter 5 presents the conclusions from this study and recommendations for future work.

REFERENCES

1. Pazos, L., Corengia, P., and Svoboda, H. Effect of surface treatments on the fatigue life of titanium for biomedical applications. *Journal of the Mechanical Behavior of Biomedical Materials*, 2010. 3 (6): 416-424.
2. Niemeyer, T.C., Grandini, C.R., Pinto, L.M.C., Angelo, A.C.D., and Schneider, S.G. Corrosion behavior of Ti–13Nb–13Zr alloy used as a biomaterial. *Journal of Alloys and Compounds*, 2009. 476 (1–2): 172-175.
3. Zhang, B.B., Wang, B.L., Li, L., and Zheng, Y.F. Corrosion behavior of Ti–5Ag alloy with and without thermal oxidation in artificial saliva solution. *Dental Materials*, 2011. 27 (3): 214-220.
4. Lin, C.-W., Ju, C.-P., and Chern Lin, J.-H. A comparison of the fatigue behavior of cast Ti–7.5Mo with c.p. titanium, Ti–6Al–4V and Ti–13Nb–13Zr alloys. *Biomaterials*, 2005. 26 (16): 2899-2907.
5. Müller, F.A., Bottino, M.C., Müller, L., Henriques, V.A.R., Lohbauer, U., Bressiani, A.H.A., and Bressiani, J.C. In vitro apatite formation on chemically treated (P/M) Ti–13Nb–13Zr. *Dental Materials*, 2008. 24 (1): 50-56.
6. Geetha, M., Singh, A.K., Asokamani, R., and Gogia, A.K. Ti based biomaterials, the ultimate choice for orthopaedic implants - A review. *Progress in Materials Science*, 2009. 54 (3): 397-425.
7. Ossowska, A., Sobieszczyk, S., Supernak, M., and Zielinski, A. Morphology and properties of nanotubular oxide layer on the “Ti–13Zr–13Nb” alloy. *Surface and Coatings Technology*, 2014. 258 (0): 1239-1248.
8. Duarte, L.T., Biaggio, S.R., Rocha-Filho, R.C., and Bocchi, N. Surface characterization of oxides grown on the Ti–13Nb–13Zr alloy and their corrosion protection. *Corrosion Science*, 2013. 72 (0): 35-40.

9. López, M.F., Gutiérrez, A., Jiménez, J.A., Martinesi, M., Stio, M., and Treves, C. Thermal oxidation of vanadium-free Ti alloys: An X-ray photoelectron spectroscopy study. *Materials Science and Engineering: C*, 2010. 30 (3): 465-471.
10. Munuera, C., Matzelle, T.R., Kruse, N., López, M.F., Gutiérrez, A., Jiménez, J.A., and Ocal, C. Surface elastic properties of Ti alloys modified for medical implants: A force spectroscopy study. *Acta Biomaterialia*, 2007. 3 (1): 113-119.
11. Gutiérrez, A., Munuera, C., López, M.F., Jiménez, J.A., Morant, C., Matzelle, T., Kruse, N., and Ocal, C. Surface microstructure of the oxide protective layers grown on vanadium-free Ti alloys for use in biomedical applications. *Surface Science*, 2006. 600 (18): 3780-3784.
12. López, M.F., Jiménez, J.A., and Gutiérrez, A. Corrosion study of surface-modified vanadium-free titanium alloys. *Electrochimica Acta*, 2003. 48 (10): 1395-1401.
13. Sowa, M., Piotrowska, M., Widziolek, M., Dercz, G., Tylko, G., Gorewoda, T., Osyczka, A.M., and Simka, W. Bioactivity of coatings formed on Ti–13Nb–13Zr alloy using plasma electrolytic oxidation. *Materials Science and Engineering: C*, 2015. 49 (0): 159-173.
14. Simka, W., Socha, R.P., Dercz, G., Michalska, J., Maciej, A., and Krzakała, A. Anodic oxidation of Ti–13Nb–13Zr alloy in silicate solutions. *Applied Surface Science*, 2013. 279 (0): 317-323.
15. Saji, V.S. and Choe, H.C. Electrochemical corrosion behaviour of nanotubular Ti–13Nb–13Zr alloy in Ringer's solution. *Corrosion Science*, 2009. 51 (8): 1658-1663.
16. Oliveira, N.T.C., Ferreira, E.A., Duarte, L.T., Biaggio, S.R., Rocha-Filho, R.C., and Bocchi, N. Corrosion resistance of anodic oxides on the Ti–50Zr and Ti–13Nb–13Zr alloys. *Electrochimica Acta*, 2006. 51 (10): 2068-2075.
17. Richard, C., Kowandy, C., Landoulsi, J., Geetha, M., and Ramasawmy, H. Corrosion and wear behavior of thermally sprayed nano ceramic coatings on

- commercially pure Titanium and Ti-13Nb-13Zr substrates. *International Journal of Refractory Metals and Hard Materials*, 2010. 28 (1): 115-123.
18. Sathish, S., Geetha, M., Pandey, N.D., Richard, C., and Asokamani, R. Studies on the corrosion and wear behavior of the laser nitrided biomedical titanium and its alloys. *Materials Science and Engineering: C*, 2010. 30 (3): 376-382.
 19. Sathish, S., Geetha, M., Aruna, S.T., Balaji, N., Rajam, K.S., and Asokamani, R. Sliding wear behavior of plasma sprayed nanoceramic coatings for biomedical applications. *Wear*, 2011. 271 934- 941.
 20. Sathish, S., Geetha, M., Aruna, S.T., Balaji, N., Rajam, K.S., and Asokamani, R. Studies on plasma sprayed bi-layered ceramic coating on bio-medical Ti-13Nb-13Zr alloy. *Ceramics International*, 2011. 37 (4): 1333-1339.
 21. Durgalakshmi, D., Chandran, M., Manivasagam, G., Ramachandra Rao, M.S., and Asokamani, R. Studies on corrosion and wear behavior of submicrometric diamond coated Ti alloys. *Tribology International*, 2013. 63 (0): 132-140.
 22. Mohan, L. and Anandan, C. Wear and corrosion behavior of oxygen implanted biomedical titanium alloy Ti-13Nb-13Zr. *Applied Surface Science*, 2013. 282 (0): 281-290.
 23. Ali, A., Ahmad, A., and Deen, K.M. Multilayer ceramic coating for impeding corrosion of sintered NdFeB magnets. *Journal of Rare Earths*, 2009. 27 (6): 1003-1007.
 24. Tian, R. Chromium nitride/Cr coated 316L stainless steel as bipolar plate for proton exchange membrane fuel cell. *Journal of Power Sources*, 2011. 196 (3): 1258-1263.
 25. Bobzin, K., Bagcivan, N., Theiß, S., Weiß, R., Depner, U., Troßmann, T., Ellermeier, J., and Oechsner, M. Behavior of DLC coated low-alloy steel under tribological and corrosive load: Effect of top layer and interlayer variation. *Surface and Coatings Technology*, 2013. 215 (0): 110-118.

26. Fenker, M., Balzer, M., and Kappl, H. Corrosion protection with hard coatings on steel: Past approaches and current research efforts. *Surface and Coatings Technology*, 2014. 257 (0): 182-205.
27. Bouzakis, K.D., Michailidis, N., Hadjiyiannis, S., Efstathiou, K., Pavlidou, E., Erkens, G., Rambadt, S., and Wirth, I. Improvement of PVD coated inserts cutting performance, through appropriate mechanical treatments of substrate and coating surface. *Surface and Coatings Technology*, 2001. 146–147 (0): 443-450.
28. Bouzakis, K.D., Skordaris, G., Michailidis, N., Asimakopoulos, A., and Erkens, G. Effect on PVD coated cemented carbide inserts cutting performance of micro-blasting and lapping of their substrates. *Surface and Coatings Technology*, 2005. 200 (1–4): 128-132.
29. Bouzakis, K.D., Skordaris, G., Mirisidis, I., Mesomeris, G., Michailidis, N., Pavlidou, E., and Erkens, G. Micro-blasting of PVD Films, an Effective Way to Increase the Cutting Performance of Coated Cemented Carbide Tools. *CIRP Annals - Manufacturing Technology*, 2005. 54 (1): 95-98.
30. Bouzakis, K.D., Skordaris, G., Mirisidis, I., Michailidis, N., Mesomeris, G., Pavlidou, E., and Erkens, G. Cutting performance improvement through micro-blasting on well-adherent PVD films on cemented carbide inserts. *Surface and Coatings Technology*, 2005. 200 (5–6): 1879-1884.
31. Bouzakis, K.D., Gerardis, S., Skordaris, G., Katirtzoglou, G., Makrimallakis, S., Klocke, F., and Bouzakis, E. Effect of dry micro-blasting on PVD-film properties, cutting edge geometry and tool life in milling. *Surface and Coatings Technology*, 2009. 204 (6–7): 1081-1086.
32. Bouzakis, K.D., Bouzakis, E., Skordaris, G., Makrimallakis, S., Tsouknidas, A., Katirtzoglou, G., and Gerardis, S. Effect of PVD films wet micro-blasting by various Al₂O₃ grain sizes on the wear behaviour of coated tools. *Surface and Coatings Technology*, 2011. In Press, Accepted Manuscript.
33. Bouzakis, K.D., Klocke, F., Skordaris, G., Bouzakis, E., Gerardis, S., Katirtzoglou, G., and Makrimallakis, S. Influence of dry micro-blasting grain quality on wear behaviour of TiAlN coated tools. *Wear*, 2011. 271 (5–6): 783-791.

34. Bouzakis, K.D., Skordaris, G., Bouzakis, E., Tsouknidas, A., Makrimalakis, S., Gerardis, S., and Katirtzoglou, G. Optimization of wet micro-blasting on PVD films with various grain materials for improving the coated tools' cutting performance. *CIRP Annals - Manufacturing Technology*, 2011. In Press, Corrected Proof.
35. Williams, D.F. On the nature of biomaterials. *Biomaterials*, 2009. 30 (30): 5897-5909.
36. Shadanbaz, S. and Dias, G.J. Calcium phosphate coatings on magnesium alloys for biomedical applications: A review. *Acta Biomaterialia*, 2012. 8 (1): 20-30.
37. Nakai, M., Niinomi, M., Zhao, X., and Zhao, X. Self-adjustment of Young's modulus in biomedical titanium alloys during orthopaedic operation. *Materials Letters*, 2011. 65 (4): 688-690.
38. Fukuda, A., Takemoto, M., Saito, T., Fujibayashi, S., Neo, M., Yamaguchi, S., Kizuki, T., Matsushita, T., Niinomi, M., Kokubo, T., and Nakamura, T. Bone bonding bioactivity of Ti metal and Ti-Zr-Nb-Ta alloys with Ca ions incorporated on their surfaces by simple chemical and heat treatments. *Acta Biomaterialia*, 2011. 7 (3): 1379-1386.
39. Suresh, K.S., Geetha, M., Richard, C., Landoulsi, J., Ramasawmy, H., Suwas, S., and Asokamani, R. Effect of equal channel angular extrusion on wear and corrosion behavior of the orthopedic Ti-13Nb-13Zr alloy in simulated body fluid. *Materials Science and Engineering: C*, 2012. 32 (4): 763-771.
40. Wei, Q., Wang, L., Fu, Y., Qin, J., Lu, W., and Zhang, D. Influence of oxygen content on microstructure and mechanical properties of Ti-Nb-Ta-Zr alloy. *Materials & Design*, 2011. 32 (5): 2934-2939.
41. Park, J.B. and Lakes, R.S. *Biomaterials An Introduction*. 3th ed. 2010. New York: Springer Science.
42. Lütjering, G. and Williams, J.C. *Titanium*. 2nd ed. 2007. New York: Springer.
43. Davis, J.R. *Metals handbook*. 2nd ed. 2006. New York: The Material Information Society.

44. Zhao, C., Zhang, X., and Cao, P. Mechanical and electrochemical characterization of Ti-12Mo-5Zr alloy for biomedical application. *Journal of Alloys and Compounds*, 2011. 509 (32): 8235-8238.
45. Askeland, D.R. and Phule, P.P. *Essentials of Material Science & Engineering*. 2nd. ed. 2009. Canada: Cengage learning.
46. Atapour, M., Pilchak, A.L., Frankel, G.S., and Williams, J.C. Corrosion behavior of [beta] titanium alloys for biomedical applications. *Materials Science and Engineering: C*, 2011. 31 (5): 885-891.
47. Miura, K., Yamada, N., Hanada, S., Jung, T.-K., and Itoi, E. The bone tissue compatibility of a new Ti-Nb-Sn alloy with a low Young's modulus. *Acta Biomaterialia*, 2011. 7 (5): 2320-2326.
48. Geetha, M., Kamachi Mudali, U., Gogia, A.K., Asokamani, R., and Raj, B. Influence of microstructure and alloying elements on corrosion behavior of Ti-13Nb-13Zr alloy. *Corrosion Science*, 2004. 46 (4): 877-892.
49. Majumdar, P., Singh, S.B., and Chakraborty, M. Wear properties of Ti-13Zr-13Nb (wt.%) near [beta] titanium alloy containing 0.5 wt.% boron in dry condition, Hank's solution and bovine serum. *Materials Science and Engineering: C*, 2010. 30 (7): 1065-1075.
50. Nag, S., Banerjee, R., and Fraser, H.L. Microstructural evolution and strengthening mechanisms in Ti-Nb-Zr-Ta, Ti-Mo-Zr-Fe and Ti-15Mo biocompatible alloys. *Materials Science and Engineering: C*, 2005. 25 (3): 357-362.
51. Khan, M.A., Williams, R.L., and Williams, D.F. The corrosion behaviour of Ti-6Al-4V, Ti-6Al-7Nb and Ti-13Nb-13Zr in protein solutions. *Biomaterials*, 1999. 20 (7): 631-637.
52. Cvijović-Alagić, I., Cvijović, Z., Mitrović, S., Panić, V., and Rakin, M. Wear and corrosion behaviour of Ti-13Nb-13Zr and Ti-6Al-4V alloys in simulated physiological solution. *Corrosion Science*, 2011. 53 (2): 796-808.
53. Sarandha, D.L. *Textbook of complete denture prosthodontics* 1st ed. 2007. New Delhi.

54. Ramsden, J.J., Allen, D.M., Stephenson, D.J., Alcock, J.R., Peggs, G.N., Fuller, G., and Goch, G. The Design and Manufacture of Biomedical Surfaces. *CIRP Annals - Manufacturing Technology*, 2007. 56 (2): 687-711.
55. Kent, D., Wang, G., Yu, Z., Ma, X., and Dargusch, M. Strength enhancement of a biomedical titanium alloy through a modified accumulative roll bonding technique. *Journal of the Mechanical Behavior of Biomedical Materials*, 2011. 4 (3): 405-416.
56. Niinomi, M. Mechanical biocompatibilities of titanium alloys for biomedical applications. *Journal of the Mechanical Behavior of Biomedical Materials*, 2008. 1 (1): 30-42.
57. Majumdar, P., Singh, S.B., and Chakraborty, M. The influence of heat treatment and role of boron on sliding wear behaviour of [beta]-type Ti-35Nb-7.2Zr-5.7Ta alloy in dry condition and in simulated body fluids. *Journal of the Mechanical Behavior of Biomedical Materials*, 2011. 4 (3): 284-297.
58. Luo, Y., Jiang, H., Cheng, G., and Liu, H. Effect of Carburization on the Mechanical Properties of Biomedical Grade Titanium Alloys. *Journal of Bionic Engineering*, 2011. 8 (1): 86-89.
59. Jouanny, I., Labdi, S., Aubert, P., Buscema, C., Maciejak, O., Berger, M.H., Guipont, V., and Jeandin, M. Structural and mechanical properties of titanium oxide thin films for biomedical application. *Thin Solid Films*, 2010. 518 (12): 3212-3217.
60. Guelcher, S.A. and Hollinger, J.O. *An Introduction to biomaterials*. 2006. New York: Taylor & Francis.
61. Ratner, B.D., Hoffman, A.S., Schoen, F.J., and Lemons, J.E. Biomaterials Science: A Multidisciplinary Endeavor. In: Buddy D. Ratner, A.S.H., Frederick J. Schoen, Jack E. Lemons, *Biomaterials Science: An Introduction to Materials in Medicine*. London: Elsevier, 1-19; 2004
62. Izman, S., Abdul-Kadir, M.R., Anwar, M., Nazim, E.M., Rosliza, R., Shah, A., and Hassan, M.A. Surface Modification Techniques for Biomedical Grade of Titanium Alloys: Oxidation, Carburization and Ion Implantation

- Processes. In: Amin, A.K.M.N., *Titanium Alloys – Towards Achieving Enhanced Properties for Diversified Applications*. Rijeka: In Tech, 201-228; 2012
63. Diomidis, N., Mischler, S., More, N.S., Roy, M., and Paul, S.N. Fretting-corrosion behavior of [beta] titanium alloys in simulated synovial fluid. *Wear*, 2011. 271 (7-8): 1093-1102.
 64. Nolan, D., Huang, S.W., Leskovsek, V., and Braun, S. Sliding wear of titanium nitride thin films deposited on Ti-6Al-4V alloy by PVD and plasma nitriding processes. *Surface and Coatings Technology*, 2006. 200 (20-21): 5698-5705.
 65. Gispert, M.P., Serro, A.P., Colaço, R., Pires, E., and Saramago, B. Wear of ceramic coated metal-on-metal bearings used for hip replacement. *Wear*, 2007. 263 (7-12): 1060-1065.
 66. Hoseini, M., Jedenmalm, A., and Boldizar, A. Tribological investigation of coatings for artificial joints. *Wear*, 2008. 264 (11-12): 958-966.
 67. Subramanian, B., Ananthakumar, R., and Jayachandran, M. Structural and tribological properties of DC reactive magnetron sputtered titanium/titanium nitride (Ti/TiN) multilayered coatings. *Surface and Coatings Technology*, 2011. 205 (11): 3485-3492.
 68. Rautray, T.R., Narayanan, R., and Kim, K.-H. Ion implantation of titanium based biomaterials. *Progress in Materials Science*, 2011. 56 (8): 1137-1177.
 69. Liu, X., Chu, P.K., and Ding, C. Surface modification of titanium, titanium alloys, and related materials for biomedical applications. *Materials Science and Engineering: R: Reports*, 2004. 47 (3-4): 49-121.
 70. Al-Radha, A.S.D., Dymock, D., Younes, C., and O'Sullivan, D. Surface properties of titanium and zirconia dental implant materials and their effect on bacterial adhesion. *Journal of Dentistry*, 2012. 40 (2): 146-153.
 71. Robber H. Todd, D.K.A., Leo Alting. *Manufacturing Processes References Guide*. 1st ed. 2004. New York: Industrial press Inc.

72. Citeau, A., Guicheux, J., Vinatier, C., Layrolle, P., Nguyen, T.P., Pilet, P., and Daculsi, G. In vitro biological effects of titanium rough surface obtained by calcium phosphate grid blasting. *Biomaterials*, 2005. 26 (2): 157-165.
73. Jiang, X.P., Wang, X.Y., Li, J.X., Li, D.Y., Man, C.S., Shepard, M.J., and Zhai, T. Enhancement of fatigue and corrosion properties of pure Ti by sandblasting. *Materials Science and Engineering: A*, 2006. 429 (1–2): 30-35.
74. Bacchelli, B., Giavaresi, G., Franchi, M., Martini, D., De Pasquale, V., Trirè, A., Fini, M., Giardino, R., and Ruggeri, A. Influence of a zirconia sandblasting treated surface on peri-implant bone healing: An experimental study in sheep. *Acta Biomaterialia*, 2009. 5 (6): 2246-2257.
75. Brinker, C.J. and Scherer, G.W. *The Physics and Chemistry of Sol–Gel Processing*. 1990. San Diego: American Press.
76. Piveteau, L.-D., Brunette, D.M., Tengvall, P., M.Textor, and P.Thomsen. *Titanium in Medicine*. 2001. Berlin: Springer.
77. Metikos-Hukovic, M., Tkalcec, E., Kwokal, A., and Piljac, J. An in vitro study of Ti and Ti-alloys coated with sol-gel derived hydroxyapatite coatings. *Surface and Coatings Technology*, 2003. 165 (1): 40-50.
78. Kumar, S., Narayanan, T.S.N.S., Ganesh Sundara Raman, S., and Seshadri, S.K. Surface modification of CP-Ti to improve the fretting-corrosion resistance: Thermal oxidation vs. anodizing. *Materials Science and Engineering: C*, 2010. 30 (6): 921-927.
79. Ou, S.-F., Lin, C.-S., and Pan, Y.-N. Microstructure and surface characteristics of hydroxyapatite coating on titanium and Ti-30Nb-1Fe-1Hf alloy by anodic oxidation and hydrothermal treatment. *Surface and Coatings Technology*, 2011. 205 (8–9): 2899-2906.
80. Shahzad, M., Chaussumier, M., Chieragatti, R., Mabru, C., and Rezai-Aria, F. Surface characterization and influence of anodizing process on fatigue life of Al 7050 alloy. *Materials & Design*, 2011. 32 (6): 3328-3335.
81. Khanna, A.S. *Introduction to High Temperature Oxidation and Corrosion*. 2004. California: ASM International.

82. Kofstad, P. *High Temperature Corrosion*. 1988. New York: Elsevier Applied Science Publisher Ltd.
83. Izman, S., Shah, A., Abdul-Kadir, M.R., Nazim, E.M., Anwar, M., Hassan, M.A., and Safari, H. Effect of Thermal Oxidation Temperature on Rutile Structure Formation of Biomedical TiZrNb Alloy. *Advanced material research*, 2012. 393-395: 704-708.
84. Pierson, H.O. *Handbook of Chemical Vapor Deposition, principles, technology and application*. 2nd ed. 1999. Norwich: Noyes.
85. Liu, H. and Dandy, D.S. *Diamond Chemical Vapor Deposition Nucleation and early growth Stages*. 1995. New Jersey: Noyes.
86. Amaral, M., Gomes, P.S., Lopes, M.A., Santos, J.D., Silva, R.F., and Fernandes, M.H. Cytotoxicity evaluation of nanocrystalline diamond coatings by fibroblast cell cultures. *Acta Biomaterialia*, 2009. 5: 755–763.
87. Swain, B.P. and Pattanayak, D.K. Simulated body fluid (SBF) adsorption onto a-SiC:H thin films deposited by hot wire chemical vapor deposition (HWCVD). *Materials Letters*, 2008. 62 (20): 3484-3486.
88. Mattox, D.M. *Handbook of Physical Vapor Deposition (PVD) Processing*. 2nd ed. 2010. Burlington: Elsevier.
89. Costa, M.Y.P., Cioffi, M.O.H., Venditti, M.L.R., and Voorwald, H.J.C. Fatigue fracture behavior of Ti-6Al-4V PVD coated. *Procedia Engineering*, 2010. 2 (1): 1859-1864.
90. LeClair, P., Berera, G.P., and Moodera, J.S. Titanium nitride thin films obtained by a modified physical vapor deposition process. *Thin Solid Films*, 2000. 376 (1–2): 9-15.
91. Ananthakumar, R., Subramanian, B., Kobayashi, A., and Jayachandran, M. Electrochemical corrosion and materials properties of reactively sputtered TiN/TiAlN multilayer coatings. *Ceramics International*, (0).
92. Paldey, S. and Deevi, S.C. Single layer and multilayer wear resistant coatings of (Ti,Al)N: a review. *Materials Science and Engineering: A*, 2003. 342 (1-2): 58-79.

93. William D, S. Physical vapor deposition tool coatings. *Surface and Coatings Technology*, 1996. 81 (1): 1-7.
94. Lin, C.-C., Lee, J.-W., Chang, K.-L., Hsieh, W.-J., Wang, C.-Y., Chang, Y.-S., and Shih, H.C. The effect of the substrate bias voltage on the mechanical and corrosion properties of chromium carbide thin films by filtered cathodic vacuum arc deposition. *Surface and Coatings Technology*, 2006. 200 (8): 2679-2685.
95. Flores, M., Huerta, L., Escamilla, R., Andrade, E., and Muhl, S. Effect of substrate bias voltage on corrosion of TiN/Ti multilayers deposited by magnetron sputtering. *Applied Surface Science*, 2007. 253 (17): 7192-7196.
96. Sui, J.H. and Cai, W. Effect of bias voltage on the structure and the electrochemical corrosion behavior of hydrogenated amorphous carbon (a-C:H) films on NiTi alloys. *Surface and Coatings Technology*, 2007. 201 (15): 6906-6909.
97. Caicedo, J.C., Amaya, C., Yate, L., Aperador, W., Zambrano, G., Gómez, M.E., Alvarado-Rivera, J., Muñoz-Saldaña, J., and Prieto, P. Effect of applied bias voltage on corrosion-resistance for $TiC_{1-x}N_x$ and $Ti_{1-x}Nb_xC_{1-y}N_y$ coatings. *Applied Surface Science*, 2010. 256 (9): 2876-2883.
98. Hsu, C.-H., Lee, C.-Y., Lin, Z.-H., Ho, W.-Y., and Lin, C.-K. Bias effects on microstructure, mechanical properties and corrosion resistance of arc-evaporated CrTiAlN nanocomposite films on AISI 304 stainless steel. *Thin Solid Films*, 2011. 519 (15): 4928-4932.
99. Persson, A., Bergström, J., Burman, C., and Hogmark, S. Influence of deposition temperature and time during PVD coating of CrN on corrosive wear in liquid aluminium. *Surface and Coatings Technology*, 2001. 146-147 (0): 42-47.
100. Khun, N.W. and Liu, E. Effect of substrate temperature on corrosion performance of nitrogen doped amorphous carbon thin films in NaCl solution. *Thin Solid Films*, 2009. 517 (17): 4762-4766.

101. Afshar, A., Yari, M., Larijani, M.M., and Eshghabadi, M. Effect of substrate temperature on structural properties and corrosion resistance of carbon thin films used as bipolar plates in polymer electrolyte membrane fuel cells. *Journal of Alloys and Compounds*, 2010. 502 (2): 451-455.
102. Roman, D., Bernardi, J., Amorim, C.L.G.d., de Souza, F.S., Spinelli, A., Giacomelli, C., Figueroa, C.A., Baumvol, I.J.R., and Basso, R.L.O. Effect of deposition temperature on microstructure and corrosion resistance of ZrN thin films deposited by DC reactive magnetron sputtering. *Materials Chemistry and Physics*, 2011. 130 (1–2): 147-153.
103. Choi, H.S., Han, D.H., Hong, W.H., and Lee, J.J. (Titanium, chromium) nitride coatings for bipolar plate of polymer electrolyte membrane fuel cell. *Journal of Power Sources*, 2009. 189 (2): 966-971.
104. Lavigne, O., Alemany-Dumont, C., Normand, B., Berger, M.H., Duhamel, C., and Delichère, P. The effect of nitrogen on the passivation mechanisms and electronic properties of chromium oxide layers. *Corrosion Science*, 2011. 53 (6): 2087-2096.
105. Zhang, M., Lin, G., Wu, B., and Shao, Z. Composition optimization of arc ion plated CrN_x films on 316L stainless steel as bipolar plates for polymer electrolyte membrane fuel cells. *Journal of Power Sources*, 2012. 205 (0): 318-323.
106. Park, M.J., Leyland, A., and Matthews, A. Corrosion performance of layered coatings produced by physical vapour deposition. *Surface and Coatings Technology*, 1990. 43–44, Part 1 (0): 481-492.
107. Massiani, Y., Gravier, P., Crousier, J.P., Fedrizzi, L., Dapor, M., Micheli, V., and Roux, L. Effects of ion beam implantation on the corrosion behaviour of TiN-coated Ti-6Al-4V alloy. *Surface and Coatings Technology*, 1992. 52 (2): 159-167.
108. Massiani, Y., Medjahed, A., Gravier, P., and Crousier, J.P. Effect of a titanium underlayer on the corrosion behaviour of physically vapour deposited titanium nitride films. *Thin Solid Films*, 1992. 217 (1–2): 31-37.

109. Ries, L.A.S., Azambuja, D.S., and Baumvol, I.J.R. Corrosion resistance of steel coated with Ti/TiN multilayers. *Surface and Coatings Technology*, 1997. 89 (1–2): 114-120.
110. Creus, J., Idrissi, H., Mazille, H., Sanchette, F., and Jacquot, P. Corrosion behaviour of Al/Ti coating elaborated by cathodic arc PVD process onto mild steel substrate. *Thin Solid Films*, 1999. 346 (1–2): 150-154.
111. Lakatos-Varsanyi, M. and Hanzel, D. Cyclic voltammetry measurements of different single-, bi- and multilayer TiN and single layer CrN coatings on low-carbon-steel substrates. *Corrosion Science*, 1999. 41 (8): 1585-1598.
112. Rossi, S., Fedrizzi, L., Leoni, M., Scardi, P., and Massiani, Y. (Ti,Cr)N and Ti/TiN PVD coatings on 304 stainless steel substrates: wear-corrosion behaviour. *Thin Solid Films*, 1999. 350 (1–2): 161-167.
113. Rudenja, S., Leygraf, C., Pan, J., Kulu, P., Talimets, E., and Mikli, V. Duplex TiN coatings deposited by arc plating for increased corrosion resistance of stainless steel substrates. *Surface and Coatings Technology*, 1999. 114 (2–3): 129-136.
114. Chen, J.-Y., Yu, G.-P., and Huang, J.-H. Corrosion behavior and adhesion of ion-plated TiN films on AISI 304 steel. *Materials Chemistry and Physics*, 2000. 65 (3): 310-315.
115. Vacandio, F., Massiani, Y., Gergaud, P., and Thomas, O. Stress, porosity measurements and corrosion behaviour of AlN films deposited on steel substrates. *Thin Solid Films*, 2000. 359 (2): 221-227.
116. Vacandio, F., Massiani, Y., Gravier, P., Rossi, S., Bonora, P.L., and Fedrizzi, L. Improvement of the electrochemical behaviour of AlN films produced by reactive sputtering using various under-layers. *Electrochimica Acta*, 2001. 46 (24–25): 3827-3834.
117. Liu, C., Leyland, A., Bi, Q., and Matthews, A. Corrosion resistance of multi-layered plasma-assisted physical vapour deposition TiN and CrN coatings. *Surface and Coatings Technology*, 2001. 141 (2–3): 164-173.

118. Hovsepian, P.E., Lewis, D.B., Luo, Q., and Farinotti, A. Corrosion resistance of CrN/NbN superlattice coatings grown by various physical vapour deposition techniques. *Thin Solid Films*, 2005. 488 (1–2): 1-8.
119. Reinhard, C., Ehasarian, A.P., and Hovsepian, P.E. CrN/NbN superlattice structured coatings with enhanced corrosion resistance achieved by high power impulse magnetron sputtering interface pre-treatment. *Thin Solid Films*, 2007. 515 (7–8): 3685-3692.
120. Subramanian, B. and Jayachandran, M. Electrochemical corrosion behavior of magnetron sputtered TiN coated steel in simulated bodily fluid and its hemocompatibility. *Materials Letters*, 2008. 62 (10-11): 1727-1730.
121. Xiaohong Yao, B.T., Linhai Tian, Xiaofang Li, Yong Ma. microstructure and corrosion resistance of TiN coating on HSS by Pulse Bias Cathodic Arc Ion Plating. *Material science forum*, 2011. 675-677 (1307-1310).
122. Sultana, T., Newaz, G., Georgiev, G.L., Baird, R.J., Auner, G.W., Patwa, R., and Herfurth, H.J. A study of titanium thin films in transmission laser micro-joining of titanium-coated glass to polyimide. *Thin Solid Films*, 2010. 518 (10): 2632-2636.
123. Miyano, R., Kimura, K., Izumi, K., Takikawa, H., and Sakakibara, T. Preparation of metal nitride and oxide thin films using shielded reactive vacuum arc deposition. *Vacuum*, 2000. 59 (1): 159-167.
124. Takikawa, H., Izumi, K., Miyano, R., and Sakakibara, T. DLC thin film preparation by cathodic arc deposition with a super droplet-free system. *Surface and Coatings Technology*, 2003. 163–164 (0): 368-373.
125. Mashiki, T., Hikosaka, H., Tanoue, H., Takikawa, H., Hasegawa, Y., Taki, M., Kumagai, M., and Kamiya, M. TiAlN film preparation by Y-shape filtered-arc-deposition system. *Thin Solid Films*, 2008. 516 (19): 6650-6654.
126. Kamiya, M., Yanagita, T., Tanoue, H., Oke, S., Suda, Y., Takikawa, H., Taki, M., Hasegawa, Y., Ishikawa, T., and Yasui, H. T-shape filtered arc deposition system with built-in electrostatic macro-particle trap for DLC film preparation. *Thin Solid Films*, 2009. 518 (5): 1498-1502.

127. Tai, C.N., Koh, E.S., and Akari, K. Macroparticles on TiN films prepared by the arc ion plating process. *Surface and Coatings Technology*, 1990. 43–44, Part 1 (0): 324-335.
128. Mubarak, A., Hamzah, E., Abbas, T., Toff, M.R.M., and QaziI, I.A. Macrodroplet reduction and growth mechanisms in cathodic arc physical vapor deposition of tin films. *Surface Review and Letters*, 2008. 15 (5): 653–659.
129. Akari, K., Tamagaki, H., Kumakiri, T., Tsuji, K., Koh, E.S., and Tai, C.N. Reduction in macroparticles during the deposition of TiN films prepared by arc ion plating. *Surface and Coatings Technology*, 1990. 43–44, Part 1 (0): 312-323.
130. Mubarak, A., Hamzah, E., and Toff, M.R.M. Review Of Physical Vapour Deposition (Pvd) Techniques For Hard Coating. *Jurnal Mekanikal*, 2005. 20 42 - 51.
131. Koerner, R.J., Butterworth, L.A., Mayer, I.V., Dasbach, R., and Busscher, H.J. Bacterial adhesion to titanium-oxy-nitride (TiNOX) coatings with different resistivities: a novel approach for the development of biomaterials. *Biomaterials*, 2002. 23 (14): 2835-2840.
132. Scarano, A., Piattelli, M., Vrespa, G., Caputi, S., and Piattelli, A. Bacterial adhesion on titanium nitride-coated and uncoated implants: an in vivo human study. *Journal of Oral Implantology*, 2003. 29: 80-85.
133. Pham, V.-H., Jun, S.-H., Kim, H.-E., and Koh, Y.-H. Deposition of titanium nitride (TiN) on Co–Cr and their potential application as vascular stent. *Applied Surface Science*, 2012. 258 (7): 2864-2868.
134. Kim, W.-G. and Choe, H.-C. Effects of TiN coating on the corrosion of nanostructured Ti–30Ta–xZr alloys for dental implants. *Applied Surface Science*, 2012. 258 (6): 1929-1934.
135. Subramanian, B., Muraleedharan, C.V., Ananthakumar, R., and Jayachandran, M. A comparative study of titanium nitride (TiN), titanium oxy nitride (TiON) and titanium aluminum nitride (TiAlN), as surface

- coatings for bio implants. *Surface and Coatings Technology*, 2011. 205: 5014–5020.
136. J. Blitz and Simpson, G. *Ultrasonic Methods of Non-destructive Testing*. 1996. London ,UK: Chapman & Hall.
 137. V.K. Astashov and V. I. Babitsky. *Ultrasonic Processes and Machines: Dynamics, Control and Applications*. 2007. New York,USA: springer-verlag Berlin Heidelberg.
 138. El-Hofy, H. *Advanced Machining Processes Nontraditional and Hybrid Machining Processes*. 2005. USA: McGraw-Hill
 139. Callister, W.D. *Fundamental of Materials Scinece and Engineering*.8th ed. 2010. New York: John Wiley & Sons, Inc.
 140. Okazaki, Y. and Gotoh, E. Comparison of metal release from various metallic biomaterials in vitro. *Biomaterials*, 2005. 26 (1): 11-21.
 141. Landolt, D. *Corrosion and Surface Chemistry of Metals*. 2010: Taylor & Francis.
 142. Barsoukov, E. and Macdonald, J.R. *Impedance Spectroscopy Theory, Experiment, and Applications*.second edition ed. 2005. USA: John Wiley & Sons.
 143. Fontana, M.G. *Corrosion Engineering*.3 rd ed. 1987. New York: McGraw-Hill, Inc.
 144. Bommaraju, T.V., O'Brien, T.F., and Hine, F. *Handbook of Chlor-Alkali Technology: Volume I: Fundamentals, Volume II: Brine Treatment and Cell Operation, Volume III: Facility Design and Product Handling, Volume IV: Operations, Volume V: Corrosion, Environmental Issues, and Future Developments*. 2005: Springer.
 145. Jonnes, D.A. *Principles and Prevention of Corrosion*. 1996. USA: Prentice-Hall, Inc.
 146. A.Groysman. Corrosion Phenomena. In: A.Groysman, *Corrosion for Everybody*. Netherlands: Springer; 2009
 147. Davis, J.R. *Corrosion of Weldment*. 2006. USA,: ASM International.

148. Revie, R.W. Uhlig's Corrosion handbook. In: Heidersbach, R., *Dealloying*. New Jersey, USA.: John Wiley & Son; 2011
149. Tait, W.S. *An Introduction of electrochemical corrosion testing for practicing engineers and scientists* 1994. Wisconsin, United States of America: Paiproductpublication.
150. Kirkland, N.T., Birbilis, N., and Staiger, M.P. Assessing the corrosion of biodegradable magnesium implants: A critical review of current methodologies and their limitations. *Acta Biomaterialia*, 2012. 8 (3): 925-936.
151. Ghali, E. *Corrosion resistance of aluminium and magnesium alloys: understanding, performance and testing*. . 2010. New Jersey, USA: John Wiley & Sons.
152. Macdonald, J. and Barsoukov, E. *Impedance spectroscopy: theory, experiment, and applications*. 2005. New York, USA: Wiley-Interscience.
153. Materials, T.A.S.f.T.a. Standard Terminology of Adhesives. USA, D907. 2012
154. Rickerby, D.S. A review of the methods for the measurement of coating-substrate adhesion. *Surface and Coatings Technology*, 1988. 36 (1–2): 541-557.
155. Mittal, K.L. *Adhesion aspect of thin film*. 2001. Netherland: VSP BV.
156. Lacefeld, W.R. Hydroxylapatite coatings. In: Hench, L.L. and Wilson, J.L., *Introduction to Bioceramics*. London World Scientific Publishing Co.Pte.Ltd., 223–238.; 1999
157. Blees, M.H., Winkelman, G.B., Balkenende, A.R., and den Toonder, J.M.J. The effect of friction on scratch adhesion testing: application to a sol–gel coating on polypropylene. *Thin Solid Films*, 2000. 359 (1): 1-13.
158. Lacombe, R. *Adhesion Measurement Methods: Theory and Practice*. 2006. New York, USA: Taylor & Francis.

159. Bull, S.J. and Rickerby, D.S. Failure modes in scratch adhesion testing: Some observations. in *Proceedings of the 3rd International Conference, Minerals, Metals and Materials Society*,. 1990. Warrendale.
160. Je, J.H., Gyarmati, E., and Naoumidis, A. Scratch adhesion test of reactively sputtered TiN coatings on a soft substrate. *Thin Solid Films*, 1986. 136 (1): 57-67.
161. Perry, A.J. Adhesion studies of ion-plated TiN on steel. *Thin Solid Films*, 1981. 81 (4): 357-366.
162. Bull, S.J., Rickerby, D.S., Matthews, A., Leyland, A., Pace, A.R., and Valli, J. The use of scratch adhesion testing for the determination of interfacial adhesion: The importance of frictional drag. *Surface and Coatings Technology*, 1988. 36 (1-2): 503-517.
163. Farè, S., Lecis, N., Vedani, M., Silipigni, A., and Favoino, P. Properties of nitrified layers formed during plasma nitriding of commercially pure Ti and Ti-6Al-4V alloy. *Surface and Coatings Technology*, 2012. 206 (8-9): 2287-2292.
164. Sattler, K.D. *Handbook of Nanophysics: Functional Nanomaterials*. 2011. Boca Raton: CRC Press.
165. Masuo Hosokawa, Kiyoshi Nogi, Naito, m., and yokoyama, T. *Nanoparticle technology handbook*. 2008. Amsterdam, Nethaland: Elsevier.
166. Gdoutos, E.E. *Fracture Mechanics*. 2nd. ed. 2005. Dordrecht, The Netherlands: Springer.
167. Musil, J., Kunc, F., Zeman, H., and Poláková, H. Relationships between hardness, Young's modulus and elastic recovery in hard nanocomposite coatings. *Surface and Coatings Technology*, 2002. 154 (2-3): 304-313.
168. Cai, F. Tribological behaviors of titanium nitride- and chromium-nitride-based physical vapor deposition coating systems. *Journal of engineering for gas turbines and power*, 2012. 134 (11): 112504.
169. Chang, C.-L., Huang, C.-S., and Jao, J.-Y. Microstructural, mechanical and wear properties of Cr-Al-B-N coatings deposited by DC reactive magnetron

- co-sputtering. *Surface and Coatings Technology*, 2011. 205 (8–9): 2730-2737.
170. Subramanian, B., Ashok, K., and Jayachandran, M. Effect of substrate temperature on the structural properties of magnetron sputtered titanium nitride thin films with brush plated nickel interlayer on mild steel. *Applied Surface Science*, 2008. 255 (5, Part 1): 2133-2138.
171. Kim, H.T., Park, J.Y., and Park, C. Effects of nitrogen flow rate on titanium nitride films deposition by DC facing target sputtering method. *Korean Journal of Chemical Engineering*, 2012.
172. Mubarak, A., Hamzah, E., and Toff, M.R.M. Study of macrodroplet and growth mechanisms with and without ion etchings on the properties of TiN coatings deposited on HSS using cathodic arc physical vapour deposition technique. *Materials Science and Engineering: A*, 2008. 474 (1-2): 236-242.
173. Krishnan, V., Krishnan, A., Remya, R., Ravikumar, K.K., Nair, S.A., Shibli, S.M.A., Varma, H.K., Sukumaran, K., and Kumar, K.J. Development and evaluation of two PVD-coated β -titanium orthodontic archwires for fluoride-induced corrosion protection. *Acta Biomaterialia*, 2011. 7 (4): 1913-1927.
174. Zhanga, T.Y. and Xu, W.H. Surface Effects on Nanoindentation. *Journal of Materials Research*, 2002. 17 (7): 1715-1720.
175. Nam, N.D., Kim, J.G., and Hwang, W.S. Effect of bias voltage on the electrochemical properties of TiN coating for polymer electrolyte membrane fuel cell. *Thin Solid Films*, 2009. 517 (17): 4772-4776.
176. Ali, R., Alkhateeb, E., Kellner, F., Virtanen, S., and Popovska-Leipertz, N. Chemical vapor deposition of titanium based ceramic coatings on low carbon steel: Characterization and electrochemical evaluation. *Surface and Coatings Technology*, 2011. 205 (23–24): 5454-5463.
177. Pedrosa, P., Alves, E., Barradas, N.P., Fiedler, P., Haueisen, J., Vaz, F., and Fonseca, C. TiN_x coated polycarbonate for bio-electrode applications. *Corrosion Science*, 2012. 56 (0): 49-57.