

PREPARATION AND CHARACTERIZATION OF TERNARY BLEND  
POLYMER SOLAR CELLS USING SOLVENT AND THERMAL  
ANNEALING TREATMENT

FARHANA BINTI AZIZ

A thesis submitted in fulfilment of the  
requirements for the award of the degree of  
Doctor of Philosophy (Gas Engineering)

Faculty of Petroleum and Renewable Energy Engineering  
Universiti Teknologi Malaysia

MAY 2015

**DEDICATION**

To my beloved husband, Iruan Shahrulnizam Mat Hussin,  
dearly sons, Afiq Asyraf, Afiq Amsyar, Afiq Afzan and also to my  
beloved mother and father, brothers and sisters.

## **ACKNOWLEDGEMENT**

First and foremost, Alhamdulillah and thank to Allah S.W.T, the most Gracious, the Most Merciful for giving me direction in my life that brought me to the level of successful completion of this PhD study.

My special gratitude to my supervisor, Professor Dr. Ahmad Fauzi Ismail for the constant encouragement and inspiration he has unhesitatingly given, financial support for this project, for the keen interest he has taken in the progress of the project, and the learned guidance he has provided at every stage of the project and preparation of the thesis.

My fellow postgraduate students should also be recognized for their support. My sincere appreciation also extends to all my colleagues and AMTEC members who have provided assistance at various occasions. Their views and tips are useful indeed. I am also grateful to all my family members.

## ABSTRACT

The main objective of this study is to fabricate ternary blend polymer solar cells (PSC) with an optimized morphology of an active layer using solvent annealing with subsequent thermal annealing treatment. Three phases of experimental works have been designed in order to achieve the above objective. In phase I, the influences of spray coating time on the optical and morphological properties of the thin films were investigated. It was found that 10s to be the most suitable deposition time to produce thin films with an acceptable roughness, root means square (RMS):17.5nm, together with good absorption properties and crystallinity. In order to improve the performance of the PSC, ternary blends of the active layer which consists of poly (2, 5-dihexyloxy-1, 4-phenylenevinylene) (PDHeOPV), poly (3-hexylthiophene) (P3HT) and phenyl-C<sub>61</sub>-butyric acid methyl ester (PCBM) were prepared in phase II. The effects of PDHeOPV weight ratio on the optical and morphological properties of the thin films were investigated by varying the weight ratio from 0.5 to 2. The addition of PDHeOPV at higher weight ratio has further disrupted the chain packing of P3HT and thus reduced the crystallinity of P3HT. Nevertheless, the addition of PDHeOPV improved the light harvesting property of the ternary blend as there was an increment in absorbance area. In phase III, the effects of different post treatments on the performance of spray coated P3HT: PDHeOPV: PCBM for an active layer in PSC were studied. The annealing temperatures were varied from 130°C to 150°C while the annealing time was fixed at 10 min. The atomic force microscopy (AFM) results revealed that the samples that underwent solvent and thermal annealing treatment had higher crystallinity of P3HT or phase separation in these samples was mostly favored. The peak absorption for P3HT: PDHeOPV: PCBM thin film was higher compared to P3HT: PCBM thin film. The x-ray diffractometer (XRD) spectra showed that the structure of the samples would evolve at high thermal annealing temperature (150°C) due to weak intermolecular force in P3HT molecules. This contributed to the low crystallinity of the films which consequently affects the absorption properties of the films. The PSC devices were prepared in inverted structure using 1:0.5:1 (P3HT: PDHeOPV: PCBM) active layers in order to observe the performance of the PSC. It was found that, thermal annealing at 130°C lead to an improvement in short circuit current ( $I_{sc} = 4.08 \pm 0.061 \text{ mA/cm}^2$ ) and slightly increased open circuit voltage ( $V_{oc} = 0.49 \pm 0.03 \text{ V}$ ) compared to the ambient PSC. Interestingly, the thermal annealed (150°C) ternary blends PSC demonstrated a significant performance enhancement under continuous illumination (120 min) without any sign of degradation. Thus, it is concluded that the P3HT: PDHeOPV: PCBM coupled with thermal annealing has a great potential for the fabrication of PSC with improved power conversion efficiency (PCE) and stability at simplicity and shorter manufacturing time compared to a tandem structure.

## ABSTRAK

Objektif utama kajian ini adalah untuk menghasilkan campuran pertigaan sel solar polimer (*PSC*) dengan morfologi optimum lapisan aktif menggunakan rawatan penyepuhlindapan pelarut diikuti dengan penyepuhlindapan haba. Tiga fasa eksperimen telah direka bentuk bagi mencapai objektif di atas. Dalam fasa I, pengaruh masa salutan semburan terhadap ciri-ciri optik dan morfologi filem nipis telah dikaji. Keputusan menunjukkan bahawa 10 saat merupakan masa yang paling sesuai untuk menghasilkan filem nipis dengan kekasaran yang boleh diterima, *root mean square (RMS)* 17.5nm, bersama-sama dengan ciri-ciri penyerapan dan penghabluran yang baik. Dalam usaha untuk meningkatkan prestasi *PSC*, adunan pertigaan lapisan aktif yang terdiri daripada poli (2,5-diheksiloksi-1,4-fenilinvinilin) (PDHeOPV) dan poli (3-heksiltiofen (P3HT) dan fenil- C<sub>61</sub>- butirik metil ester asid (PCBM) telah disediakan pada fasa II. Kesan nisbah berat PDHeOPV kepada sifat optik dan morfologi filem nipis telah dikaji dengan mengubah nisbah berat dari 0.5 hingga 2. Penambahan PDHeOPV pada nisbah berat yang lebih tinggi, mengganggu susunan rantai P3HT dan oleh itu mengurangkan penghabluran P3HT. Namun begitu, penambahan PDHeOPV telah menambah baik ciri-ciri penuaan cahaya kerana terdapat kenaikan dalam kawasan serapan. Kesan pasca-rawatan yang berbeza pada filem nipis P3HT: PDHeOPV:PCBM juga telah dikaji pada fasa III. Suhu penyepuhlindapan telah diubah dari 130°C hingga 150°C dan masa penyepuhlindapan ditetapkan pada 10 minit. Keputusan daya atom mikroskopi (AFM) mendedahkan bahawa sampel yang menjalani rawatan penyepuhlindapan pelarut dan haba mempunyai penghabluran P3HT dan pemisahan antara fasa yang lebih tinggi. Puncak penyerapan bagi filem nipis P3HT: PDHeOPV: PCBM adalah lebih tinggi berbanding dengan P3HT: PCBM. Spektrum pembelauan sinar-x (XRD) menunjukkan bahawa struktur sampel akan berubah dengan suhu penyepuhlindapan haba yang tinggi (150°C) disebabkan oleh daya antara molekul yang lemah di dalam molekul P3HT. Ini akan menyumbang kepada penghabluran yang rendah dan seterusnya memberi kesan kepada ciri-ciri penyerapan filem. Peranti *PSC* telah disediakan dalam struktur terbalik menggunakan 1: 0.5: 1 (P3HT: PDHeOPV: PCBM) sebagai lapisan aktif untuk mengkaji prestasi *PSC*. *PSC* dengan penyepuhlindapan haba pada suhu 130°C menunjukkan arus litar pintas ( $I_{sc} = 4.08 \pm 0.061 \text{ mA/cm}^2$ ) yang baik dan terdapat sedikit peningkatan pada voltan litar terbuka ( $V_{oc} = 0.49 \pm 0.03 \text{ V}$ ) berbanding *PSC* ambien. Menariknya, sampel *PSC* yang menjalani rawatan haba pada suhu 150°C menunjukkan peningkatan prestasi yang signifikan di bawah pencahayaan yang berterusan (120 minit) tanpa sebarang tanda kemerosotan. Oleh itu, dapat disimpulkan bahawa adunan pertigaan P3HT: PDHeOPV: PCBM dan rawatan penyepuhlindapan haba mempunyai potensi yang besar untuk membangunkan *PSC* dengan kecekapan (*PCE*) yang lebih baik, kestabilan yang tinggi serta masa pembuatan yang singkat berbanding dengan struktur seiring.

## **TABLE OF CONTENTS**

| <b>CHAPTER</b> | <b>TITLE</b>                       | <b>PAGE</b> |
|----------------|------------------------------------|-------------|
|                | <b>DECLARATION</b>                 | ii          |
|                | <b>DEDICATION</b>                  | iii         |
|                | <b>ACKNOWLEDGEMENT</b>             | iv          |
|                | <b>ABSTRACT</b>                    | v           |
|                | <b>ABSTRAK</b>                     | vi          |
|                | <b>TABLE OF CONTENTS</b>           | vii         |
|                | <b>LIST OF TABLES</b>              | xii         |
|                | <b>LIST OF FIGURES</b>             | xiii        |
|                | <b>LIST OF ABBREVIATIONS</b>       | xx          |
|                | <b>LIST OF SYMBOLS</b>             | xxii        |
|                | <b>LIST OF APPENDICES</b>          | xxiii       |
| <b>1</b>       | <b>INTRODUCTION</b>                | <b>1</b>    |
|                | 1.1 Research Background            | 1           |
|                | 1.2 Problem Statement              | 2           |
|                | 1.3 Objectives of the Study        | 4           |
|                | 1.4 Scopes of the Study            | 5           |
|                | 1.5 Significance of the Study      | 6           |
|                | 1.6 Organization of the Thesis     | 7           |
| <b>2</b>       | <b>LITERATURE REVIEW</b>           | <b>9</b>    |
|                | 2.1 A Short History of Solar Cells | 9           |
|                | 2.2 Polymer Solar Cells            | 10          |
|                | 2.3 Operational Principles         | 14          |
|                | 2.4 Binary Blends                  | 17          |

|          |   |           |
|----------|---|-----------|
| 2.5      | Ternary Blends  | 21        |
| 2.5.1    | Polymer: Polymer: Fullerene Ternary Blend                         | 23        |
| 2.5.2    | Charge Transfer and Transport Mechanism in<br>Ternary Solar Cells | 27        |
| 2.6      | Controlling the Active Layer Morphology                           | 28        |
| 2.6.1    | Solvent Effects   | 29        |
| 2.6.2    | Annealing Treatment   | 31        |
| 2.6.3    | Donor to Acceptor Ratio   | 36        |
| 2.7      | Processing of the Devices   | 39        |
| 2.7.1    | Coating Methods   | 42        |
| 2.7.1.1  | Spray Coating   | 42        |
| <b>3</b> | <b>RESEARCH METHODOLOGY</b>                                       | <b>51</b> |
| 3.1      | Research Design and Procedure                                     | 51        |
| 3.2      | Material Selection  | 54        |
| 3.2.1    | Active Layer  | 54        |
| 3.2.2    | Solvents  | 55        |
| 3.2.3    | Electron Transport Layer and Hole Transport Layer                 | 56        |
| 3.3      | Fabrication of Thin Films   | 57        |
| 3.4      | Fabrication of Polymer Solar Cells                                | 58        |
| 3.5      | Spray Coating and Spin Coating Methods                            | 59        |
| 3.6      | Post-deposition Treatment   | 61        |
| 3.7      | Characterization and Performance Testing                          | 63        |
| 3.7.1    | UV-Vis Spectrophotometer  | 65        |
| 3.7.2    | Photoluminescence (PL) Spectroscopy                               | 65        |
| 3.7.3    | Atomic Force Microscopy   | 66        |
| 3.7.4    | Optical Microscopy  | 67        |
| 3.7.5    | X-ray Diffractometer  | 67        |
| 3.7.6    | Surface Profilometer  | 68        |
| 3.7.7    | Differential Scanning Calorimeter (DSC)                           | 68        |
| 3.7.8    | Thermo Gravimetric Analysis (TGA)                                 | 68        |
| 3.7.9    | Semiconductor Characterization System                             | 69        |

|          |   |           |
|----------|---|-----------|
| <b>4</b> | <b>EFFECT OF SPRAY DEPOSITION TIME ON OPTICAL<br/>AND MORPHOLOGICAL PROPERTIES OF P3HT: PCBM<br/>THIN FILMS</b>   | <b>71</b> |
| 4.1      | Introduction  | 71        |
| 4.2      | Experimental Work   | 72        |
| 4.3      | Results and Discussion  | 73        |
| 4.3.1    | Macro-morphology of the Spray-Coated<br>P3HT: PCBM films  | 73        |
| 4.3.2    | Nano-Morphology of the Spray Coated<br>P3HT: PCBM Films   | 77        |
| 4.3.3    | Absorption Properties   | 80        |
| 4.4      | Conclusions   | 82        |
| <b>5</b> | <b>EFFECTS OF POLY (2, 5-DIHEXYLOXY-1, 4-<br/>PHENYLENEVINYLENE) (PDHEOPV) WEIGHT RATIO<br/>ON THE PROPERTIES OF POLY-3, HEXYLTHIOPHENE<br/>(P3HT): POLY (2, 5-DIHEXYLOXY-1, 4-<br/>PHENYLENEVINYLENE) (PDHEOPV): PHENYL-C<sub>61</sub>-<br/>BUTYRIC ACID METHYL ESTER (PCBM) TERNARY<br/>BLEND FILMS</b> | <b>83</b> |
| 5.1      | Introduction  | 83        |
| 5.2      | Experimental Work   | 84        |
| 5.3      | Results and Discussion  | 85        |
| 5.3.1    | Miscibility Properties  | 85        |
| 5.3.2    | Topographical Properties  | 87        |
| 5.3.3    | Ultraviolet/Visible Light Spectroscopy (UV/Vis)   | 89        |
| 5.3.4    | Crystallinity Properties of the Ternary Blend Films   | 91        |
| 5.3.5    | Photoluminescence Properties of the Thin Films  | 94        |
| 5.3.6    | The Stokes Shift  | 97        |
| 5.4      | Conclusions   | 101       |

|          |  |            |
|----------|--|------------|
| <b>6</b> | <b>EFFECTS OF SOLVENT ANNEALING AND THERMAL<br/>ANNEALING ON THE PROPERTIES OF POLY-3,<br/>HEXYLTHIOPHENE (P3HT): POLY (2,5-DIHEXYLOXY-1,4-<br/>PHENYLENEVINYLENE) ( PDHEOPV ) : PHENYL-C<sub>61</sub>-<br/>BUTYRIC ACID METHYL ESTER (PCBM) TERNARY<br/>BLEND FILMS</b> | <b>102</b> |
| 6.1      | Introduction   | 102        |
| 6.2      | Experimental Work  | 103        |
| 6.3      | Results and Discussion   | 104        |
| 6.3.1    | 1:0.5:1 P3HT:PDHeOPV:PCBM (20wt % of<br>PDHeOPV)   | 104        |
| 6.3.1.1  | Optical and Photo Physical Properties  | 104        |
| 6.3.1.2  | Morphological Properties   | 111        |
| 6.3.1.3  | Crystallinity Properties   | 114        |
| 6.3.2    | 1:1:1 P3HT:PDHEOPV: PCBM (33.33wt % of<br>PDHeOPV)   | 116        |
| 6.3.2.1  | Optical and Photo Physical Properties  | 116        |
| 6.3.2.2  | Morphological Properties   | 123        |
| 6.3.2.3  | Crystallinity Properties of the Ternary<br>Blend Systems   | 127        |
| 6.3.3    | 1:2:1 P3HT: PDHeOPV: PCBM (50wt% of<br>PDHeOPV)  | 130        |
| 6.3.3.1  | Optical and Photo Physical Properties  | 130        |
| 6.3.3.2  | Morphological Properties   | 136        |
| 6.3.3.3  | Crystallinity Properties   | 139        |
| 6.4      | Conclusions  | 141        |
| <b>7</b> | <b>PHOTOVOLTAIC PROPERTIES OF INVERTED<br/>POLYMER SOLAR CELLS DEVICES BASED ON P3HT:<br/>PDHEOPV: PCBM TERNARY BLENDS</b>   | <b>143</b> |
| 7.1      | Introduction   | 143        |
| 7.2      | Experimental Work  | 145        |
| 7.3      | Results and Discussion   | 146        |

|                   |  |            |
|-------------------|--|------------|
| 7.3.1             | Photovoltaic Properties of Inverted<br>P3HT: PDHeOPV: PCBM PSC Devices | 146        |
| 7.3.2             | Effects of Illumination Time   | 151        |
| 7.5               | Conclusions  | 157        |
| <b>8</b>          | <b>GENERAL CONCLUSIONS AND RECOMMENDATIONS</b>                         | <b>159</b> |
| 8.1               | General Conclusions  | 159        |
| 8.2               | Recommendations for Future Works                                       | 161        |
| <b>REFERENCES</b> |  | <b>163</b> |
| Appendices A-D    |  | 187-196    |

## LIST OF TABLES

| TABLE NO. | TITLE   | PAGE |
|-----------|---|------|
| 2.1       | List of previous researches on binary blends polymer solar cells                        | 18   |
| 2.2       | Previous researches on polymer: polymer: fullerene ternary blends                       | 25   |
| 2.3       | Properties of typical solvents for active layer in polymer solar cells                  | 30   |
| 2.4       | List of previous researches on PSC prepared using different methods                     | 41   |
| 2.5       | List of previous researches on spray coated PSC   | 45   |
| 3.1       | Solvents properties   | 56   |
| 3.2       | Composition of P3HT, PDHeOPV and PCBM used in this study                                | 57   |
| 3.3       | Variable parameter in spray coating process   | 60   |
| 6.1       | Crystallinity of 20wt% PDHeOPV thin films in dependence on annealing temperature        | 115  |
| 6.2       | Crystallinity of the thin film with different annealing temperature                     | 129  |
| 6.3       | Crystallinity of the thin film with different annealing temperature                     | 140  |
| 7.1       | Photovoltaic parameters of P3HT: PDHeOPV: PCBM PSC with different annealing temperature | 148  |

## LIST OF FIGURES

| FIGURES NO. | TITLE  | PAGE |
|-------------|--|------|
| 2.1         | Classification of solar cells  | 10   |
| 2.2         | Schematic diagram of polymer solar cell structure for a) a standard BHJ device and b) an inverted BHJ device   | 11   |
| 2.3         | Summary of main research areas in polymer solar cells  | 13   |
| 2.4         | Schematic illustration of operational mechanism in polymer solar cells (a) absorption of light, (b) charge separation and (c) charge collection  | 15   |
| 2.5         | <i>I-V</i> characteristics of a <i>p-n</i> junction in the dark and under illumination   | 16   |
| 2.6         | Number of scientific publications contributing to the subject “ternary blends solar cells” a) by year and b) by country. Search done through Scopus website in January 2015  | 22   |
| 2.7         | Simple structure of ternary blends solar cells with different types of active layers:a) polymer: polymer: acceptor b) polymer: dye: acceptor c) polymer: acceptor/small molecules BHJ bilayer and d) acceptor/donor/donor trilayer | 23   |
| 2.8         | Schematic diagram of P3HT:F8TBT: PCBM ternary blends morphology of (a) as-spun and (b) thermal annealed  | 26   |
| 2.9         | Schematic of the photovoltaic in the parallel-linkage ternary device   | 28   |

|      |  |    |
|------|--|----|
| 2.10 | Schematic diagram of vertical phase separation during solvent evaporation  | 29 |
| 2.11 | Schematic diagram of the microscopic change of active layer in the process of additional solvent spraying and thermal annealing (a) CB solution of P3HT:PCBM spray coating (ref.) (b) ref./annealed (c) ref./DCB solvent spraying (d) ref./DCB solvent spraying/annealed | 34 |
| 2.12 | AFM images and RMS roughness of the three different layers in the inverted organic solar cell coated by (a) spin- and (b) spray coating process. AFM image scans are $5 \times 5 \mu\text{m}$  | 35 |
| 2.13 | AFM height images of AnE-PVstat: PCBM solar cells with different weight ratios of PCBM: (a) 50wt% (b) 67wt% (c) 75wt% and (d) 80wt%  | 38 |
| 2.14 | Schematic diagram of the distribution of the polymer and fullerene components in the blends for the different ratios. The gray cells indicate the polymer volume fraction in %, whereas the white cells represent the PC <sub>70</sub> BM volume                         | 38 |
| 2.15 | Influences of PCPDTBT addition on morphology of the P3HT: PCBM binary blends   | 39 |
| 2.16 | Spray-coating apparatus  | 43 |
| 2.17 | Optical micrographs of P3HT: PCBM active layers prepared from (a) chloroform, (b) toluene, (c) chlorobenzene, (d) p-xylene   | 49 |
| 2.18 | Optical microscope images ( $0.1 \times 0.1 \text{ mm}^2$ ) of the e-sprayed P3HT: PCBM films achieved with various amounts of added DIO:(a) 0 vol%; (b) 3 vol%; (c) 6 vol% and (d) 8 vol%   | 49 |
| 2.19 | UV-vis spectra of spray coated PSC with and without annealing  | 50 |
| 3.1  | Research methodology   | 52 |

|      |   |    |
|------|---|----|
| 3.2  | Molecular structure of (a) P3HT (b) PDHeOPV and (c)<br>PCBM   | 55 |
| 3.3  | Schematic diagram of thin films preparation   | 58 |
| 3.4  | Schematic diagram of the inverted structure of BHJ<br>device  | 59 |
| 3.5  | Experimental setup for spray coating of PSC devices   | 60 |
| 3.6  | Spray coating process (left) and spin coater machine<br>(right)   | 61 |
| 3.7  | Post treatment procedure  | 62 |
| 3.8  | Instrumentation and data analysis   | 64 |
| 3.9  | Typical experimental setup for PL measurements  | 66 |
| 3.10 | The set-up of I-V measurements for solar cells  | 69 |
| 3.11 | Typical <i>I-V</i> curves of the solar cell   | 70 |
| 3.12 | Determining $R_s$ and $R_{sh}$  | 70 |
| 4.1  | Optical images of spray coated P3HT: PCBM layers on<br>top of glass substrate at a) 10s b) 15s and c) 20s<br>spraying deposition time   | 75 |
| 4.2  | Edges-view images of spray coated P3HT: PCBM<br>layers on top of glass substrate at a) 10s b) 15s and c)<br>20s spraying duration. Edges of the droplets can be seen<br>clearly in 15 and 20s samples while the edges for 10s<br>samples is in smaller scales | 76 |
| 4.3  | Surface topography of P3HT: PCBM film at different<br>spray deposition times a) 10s b) 15s and c) 20s   | 78 |
| 4.4  | Schematic representation of surface film formation at<br>10s and above 10s deposition times   | 80 |
| 4.5  | Absorption spectra of thin films of P3HT: PCBM spray<br>coated at different spray deposition time   | 81 |
| 5.1  | DSC second heating curves for different PDHeOPV<br>weight rati  | 86 |
| 5.2  | Tapping mode AFM topography images ternary blend<br>films (P3HT:PDHEOPV: PCBM) at a) 1:0:1 b) 1:0.5:1<br>c) 1:1:1 and d) 1:2:1  | 87 |

|     |  |     |
|-----|--|-----|
| 5.3 | Schematic representation of the proposed morphology<br>in a) binary blend of P3HT: PCBM b) ternary blend of<br>P3HT: PDHeOPV: PCBM   | 88  |
| 5.4 | Absorption properties of ternary blends at different<br>PDHeOPV weight ratio   | 90  |
| 5.5 | XRD spectra of ternary blends at different P3HT:<br>PDHeOPV: PCBM weight ratio   | 92  |
| 5.6 | Fullerene intercalation in polymer: fullerene systems a)<br>There is insufficient space for PCBM intercalation<br>between the side-chains of amorphous PDHeOPV b)<br>There is insufficient room for PCBM intercalation<br>between the side-chains of P3HT. Dense side chain<br>prevent intercalation | 94  |
| 5.7 | Photoluminescence of P3HT pristine films and binary<br>blends films of P3HT:PCBM   | 95  |
| 5.8 | Photoluminescence of ternary blends at different<br>PDHeOPV weight ratio   | 97  |
| 5.9 | Stokes shift data for ternary blends films of P3HT:<br>PDHeOPV: PCBM at a) 1:0:1, b) 1:0.5:1, c) 1:1:1 and<br>d) 1:2:1   | 100 |
| 6.1 | Absoprtion spectra for ternary blends P3HT:<br>PDHeOPV:PCBM (1:0.5:1) thin films at different<br>annealing temperature   | 105 |
| 6.2 | PL emission spectra of 1:0.5:1 (P3HT: PDHEOPV:<br>PCBM) at different annealing treatment   | 106 |
| 6.3 | Stokes shift data for 1:0.5:1 P3HT: PDHeOPV: PCBM<br>a) Ambient, b) Solvent annealing c) 130°C, d) 140°C<br>and e) 150°C   | 108 |
| 6.4 | Tapping mode AFM topography images of 1:0.5:1<br>(P3HT:PDHeOPV:PCBM) thin films dried at a)<br>ambient, b) solvent annealing, c) 130°C, d) 140°C and<br>e) 150°C   | 112 |

|      |   |     |
|------|---|-----|
| 6.5  | Phase images of 1:0.5:1 P3HT: PDHeOPV: PCBM thin films dried at a) ambient, b) solvent annealing, thermal annealed at c) 130°C, d) 140°C and e) 150°C<br>(Magnification: 10k size $5\mu\text{m}$ x $5\mu\text{m}$ ) | 113 |
| 6.6  | XRD diffraction patterns of the untreated and treated samples with different annealing temperature for 20 wt% of PDHeOPV  | 115 |
| 6.7  | Absorption spectra for ternary blends P3HT: PDHeOPV: PCBM (1:1:1) thin films at different annealing temperature   | 117 |
| 6.8  | PL spectra for solvent and thermal annealing P3HT: PDHeOPV:PCBM (1:1:1) thin films  | 119 |
| 6.9  | Stokes shift data for P3HT: PDHEOPV:PCBM (1:1:1)<br>a) Ambient, b) Solvent annealing films and thermal annealing at b) 130°C, c) 140°C and d) 150°C   | 120 |
| 6.10 | Tapping mode AFM topography images of 1:1:1 (P3HT: PDHEOPV:PCBM) thin films dried at a) ambient, b) solvent annealing, and thermal annealing at c) 130°C, d) 140°C and e) 150°C                                     | 124 |
| 6.11 | Phase images for 1:1:1 P3HT: PDHeOPV:PCBM ternary blend films dried at a)ambient, b) solvent annealing, thermal annealing at c) 130°C d) 140°C and e) 150°C   | 126 |
| 6.12 | XRD diffraction patterns of the untreated and treated samples with different annealing temperature for 33.33 wt% of PDHeOPV   | 128 |
| 6.13 | Absorption spectra for ternary blends P3HT: PDHeOPV: PCBM (1:2:1) thin films at different annealing temperature   | 131 |
| 6.14 | PL spectra for solvent and thermal annealing P3HT: PDHeOPV:PCBM (1:2:1) thin films  | 132 |

|      |   |     |
|------|---|-----|
| 6.15 | Stokes shift data for P3HT: PDHeOPV:PCBM 1:2:1 a)<br>Ambient, b) Solvent annealing films and thermal<br>annealing at c) 130°C, d) 140 °C e) 150°C   | 133 |
| 6.16 | Tapping mode AFM topography images of 1:1:1<br>(P3HT: PDHeOPV:PCBM) thin films dried at a)<br>ambient b) solvent annealing and thermal annealing c)<br>130°C d) 140°C and e) 150°C  | 137 |
| 6.17 | Phase images for 1:2:1 P3HT: PDHeOPV:PCBM<br>ternary blend films dried at a) ambient, b) solvent<br>annealing and thermal annealing at c) 130°C d) 140°C<br>and e) 150°C  | 138 |
| 6.18 | XRD diffraction patterns of the untreated and treated<br>samples with different annealing temperature for 50<br>wt% of PDHeOPV  | 140 |
| 7.1  | The schematic energy level diagram of the ternary<br>blends polymer solar cells devices   | 146 |
| 7.2  | <i>I-V</i> curves measured a) under illumination and b) in<br>dark for inverted PSC at different annealing<br>temperature.  | 148 |
| 7.3  | a) An equivalent circuit diagram of typical photovoltaic<br>cells illustrates the presence of shunt resistance ( $R_{sh}$ )<br>and series resistance ( $R_s$ ) b) Variation of the shunt<br>resistance ( $R_{sh}$ ) and series resistance ( $R_s$ ) with the heat<br>treatment temperature                    | 150 |
| 7.4  | The <i>I-V</i> curves of an inverted PSC device under<br>different illumination time a) ambient and solvent<br>annealing with subsequent thermal annealing at b)<br>130°C c) 140°C d) 150°C. Devices illuminated by<br>xenon lamp as the light source at an irradiation<br>intensity of 100mW/cm <sup>2</sup> | 153 |
| 7.5  | Relationship between the short circuit current and the<br>illumination time for ambient and thermal annealed<br>PSC devices. $I_{sc,0}$ is the initial $I_{sc}$   | 156 |

|     |  |     |
|-----|--|-----|
| 7.6 | Relationship between the open circuit voltage and the illumination time for ambient and thermal annealed PSC devices. $V_{oc,0}$ is the initial $V_{oc}$ | 156 |
| 7.7 | Relationship between the fill factor and the illumination time for ambient and thermal annealed PSC devices. $FF_0$ is the initial $FF$                  | 157 |

## LIST OF ABBREVIATIONS

|                     |   |   |
|---------------------|---|---|
| AFM                 | - | Atomic force microscopy   |
| Au                  | - | Gold  |
| BHJ                 | - | Bulk heterojunction   |
| CF                  |   | Chloroform  |
| CN                  | - | 1-chloronaphthalene   |
| DIO                 | - | 1,8-diiodooctane  |
| DSC                 | - | Differential scanning calorimetry   |
| ETL                 | - | Electron transport layer  |
| F8BT                | - | Poly (9,9-dioctylfluorene-co-benzothiadiazole)  |
| HOMO                | - | Highest occupied molecular orbital  |
| HTL                 | - | Hole transport layer  |
| LUMO                | - | Lowest unoccupied molecular orbital   |
| MDMO-PPV            | - | Poly [2-methoxy-5-(3',7'-dimethyl-octyloxy)]- <i>p</i> -phenylene vinylene                          |
| MEH-PPV             | - | Poly(2-methoxy-5-(2'-ethyl)-hexyloxy- <i>p</i> -phenylene vinylene)                                 |
| Mw                  | - | Molecular weight  |
| ODCB                | - | Ortho-dichlorobenzene   |
| ODT                 | - | 1,8-octanedithiol   |
| P3HT                | - | Poly (3-hexylthiophene)   |
| P3HT- <i>b</i> -PEO | - | Poly (3-hexylthiophene)- <i>b</i> -poly (ethylene oxide)  |
| PBDTTPD             | - | Poly (benzo[1,2- <i>b</i> :4,5- <i>b</i> ']dithiophene–alt–thieno[3,4- <i>c</i> ]pyrrole-4,6-dione) |
| PCBM                | - | Phenyl-C <sub>61</sub> -butyric acid methyl ester   |
| PCE                 | - | Power conversion efficiency   |
| PCPDTBT             | - | Poly [2,6-(4,4-bis-(2-ethylhexyl)-4 <i>H</i> -cyclopenta [2,1- <i>b</i> ;3,4-                       |

|           |   |   |
|-----------|---|---|
|           | - | <i>b'</i> ] dithiophene)- <i>alt</i> -4,7(2,1,3-benzothiadiazole)]  |
| PDHeOPV   | - | Poly (2,5-dihexyloxy-1,4-phenylenevinylene)   |
| PEDOT:PSS | - | Poly (3,4-ethylenedioxythiophene)-poly(styrenesulfonate)  |
| PL        | - | Photoluminescence   |
| PPV       | - | Poly (p-phenylenevinylene)s   |
| PSBTBT    | - | Poly[(4,42-bis(2-ethylhexyl) dithieno [3,2-b:22,32-d] silole)-2,6-diylalt-(2,1,3- benzothiadiazole)-4,7-diyl] |
| PSC       | - | Polymer solar cells   |
| PTE       | - | Poly (oxyethylene tridecyl ether)   |
| PV        | - | Photovoltaic  |
| RMS       | - | Root-mean-square  |
| TCB       | - | Trichlorobenzene  |
| TGA       | - | Thermogravimetric analysis  |
| THN       | - | 1,2,3,4-Tetrahydronaphthalene   |
| UV-Vis    | - | Ultraviolet-Visible   |
| XRD       | - | X-ray diffraction   |

**LIST OF SYMBOLS**

|                       |   |   |
|-----------------------|---|---|
| <i>a.u</i>            | - | Arbitrary unit                              |
| <i>eV</i>             | - | Electron volt (joules)                      |
| <i>FF</i>             | - | Fill factor                                 |
| <i>I<sub>sc</sub></i> | - | Short circuit current (mA/cm <sup>2</sup> ) |
| <i>P<sub>in</sub></i> | - | Input power (mA/cm <sup>2</sup> )           |
| <i>R<sub>s</sub></i>  | - | Series resistance (ohms)                    |
| <i>R<sub>sh</sub></i> | - | Shunt resistance (ohms)                     |
| <i>V<sub>oc</sub></i> | - | Open circuit voltage (V)                    |
| $\theta$              | - | Theta                                       |

**LIST OF APPENDICES**

| <b>APPENDIX</b> | <b>TITLE</b>  | <b>PAGE</b> |
|-----------------|---|-------------|
| A               | Photoluminescence Spectra for Pristine PDHeOPV Films        | 187         |
| B               | Example of Gaussian Fittting for Crystallinity Measurements | 188         |
| C               | DSC and TGA Analysis for Neat PDHeOPV                       | 191         |
| D               | Example of Photovoltaic Properties Calculations             | 193         |
| E               | X-Ray Diffraction Peaks for Pristine PDHeOPV Films          | 195         |

## **CHAPTER 1**

### **INTRODUCTION**

#### **1.1 Research Background**

Nowadays, most of the developing countries such as China, India and Malaysia are moving towards renewable energy. The main purpose of the shift from fossil fuel (such as petroleum, natural gas and coal) to renewable energy sources is to decrease the emission of greenhouse gases. Renewable energy may refer to any energy that comes from natural resources such as sunlight, rain, wind, geothermal heat and tides which are renewable. In Malaysia, the government had announced the National Renewable Energy Policy and Action Plan with a goal of increasing renewable energy from 1% to 5.5% of electricity supply by 2015 [1, 2]. By looking at the geographical location of Malaysia which situated in the equatorial region with an average radiation of 4,500 kilowatt hour (kWh) per square meter, it is an ideal location for large scale solar power installations [3]. Thus, solar power technologies are one of the renewable sources with great potential in Malaysia. During this decade, the field on solar energy has seen a near exponential growth by looking at the number of published scientific articles and citations [4].

Photovoltaic provides some clear advantages to other renewable sources of energy and is an option for energy generation. At present, most of the commercial photovoltaic cells are based on inorganic crystalline such as crystalline silicon [5]. These types of solar cells can harvest up to as much as 24% of the received solar

energy and this value is very close to the theoretically predicted upper limit of 30% [6]. However, the production of these solar cells still requires many energy intensive processes at high temperatures (400-1400°C) and high vacuum conditions with numerous lithographic steps leading to relatively high manufacturing costs [6]. This demonstrates that the technologies which allow low fabrication costs with acceptable conversion efficiencies (up to 10% power conversion efficiency) are now desired.

Polymer solar cells (PSC) have potential advantages such as low manufacturing cost, light-weight and flexibility [7]. Based on these advantages, a lot of researches on polymer solar cells have been conducted to make this type of solar cell competitive as the photovoltaic technology [8-10]. Bulk heterojunction (BHJ) structure which consists of the intermixing of a conjugated polymer and fullerene in blend films has brought about a significant enhancement of the dissociation interface, leading to high power conversion efficiency (PCE) up to 6% [11, 12]. Based on the performance that has been showed by BHJ PSC, extensive research has been conducted in these types of solar cells concentrating on the various process parameters that affects its performance such as the blending ratio of donor and acceptor materials, processing conditions and annealing conditions [11, 13].

## 1.2 Problem Statement

Normally, polymer solar cells (PSC) consists of binary blends of electron-donor material and electron acceptor material (D: A). Most of the current researches in binary blends PSC focusing on the polymer: fullerene blends due to their impressive performance in photovoltaic efficiency. Among the reported PSC systems in the literature, the poly (3-hexylthiophene) (P3HT): phenyl-C<sub>61</sub>-butyric acid methyl ester (PCBM) systems currently represent the state-of-art in PSC [14]. New devices structure such as tandem structure [15-18] and ternary blends PSC [19-21] have also been developed to further enhance the performance and stability of PSC.

Ternary blends active layer consists of two electron-donor polymer and one electron-acceptor polymer (D1: D2: A) or one electron-donor polymer and two electron-acceptor polymer (D: A1:A2) have been recognized as an efficient strategy to further enhance efficiency and/or enhanced stability of the polymer bulk heterojunction (BHJ) solar cells [22]. This approach may lead to the optimization of both short circuit current ( $I_{sc}$ ) and open circuit voltage ( $V_{oc}$ ) through proper choice of the materials. This method is interesting since it does not involve complex design and fabrication as tandem cell approach [23]. Somehow, it is quite surprising that there are limited published results focused on ternary blend active layer particularly by adding an additional electron donor or electron acceptor in polymer: fullerene systems.

Based on the extensive literature review, it can be seen that one of the critical parameters to achieve efficient devices is the morphology of the active layer of BHJ thin films. Kim et al. [19] added an additional electron donor, MDMO-PPV to P3HT:F8BT systems which has higher highest occupied molecular orbital (HOMO) level than P3HT. They observed a very low PCE which attributed to charge blocking resistance that exist in the bulk phase of ternary blends. They suggested that the performance of the ternary blend solar cells can be further improved by controlling the morphology of the active layer via thermal or electrical approach. Machui et al. [24] introduced an amorphous polymer, PCPDTBT to a P3HT:PCBM blend and observed a dramatic reduction of device efficiency due to the deterioration of electron transport in the ternary system [24]. Khlyabich et al. [23] study the influence of polymer miscibility on the open-circuit voltage ( $V_{oc}$ ) in ternary blend BHJ solar cells. They found that the miscibility of polymers had a major impact on the evolution of the  $V_{oc}$ .

Different ternary blends systems will produce different morphology depending on the types of materials used, donor to acceptor ratio, solvent, post-deposition treatment and the processing of the thin films or devices. Nevertheless, the morphology formations of such ternary system are generally not well

documented and understood. To date, different approach has been taken by previous researchers to produce nano-scaled interpenetrating networks within the whole active layer to ensure efficient exciton dissociation and charge transport [25]. The methods that have been previously applied by the researchers to control morphology are by adding the processing additives [25, 26], thermal annealing at specific temperature [27-29], and controlling the solvent evaporation rate [30].

By considering the current issues in ternary blend systems, the study conducted in this work focuses on the modification of the morphology of the active layer by implementing the solvent annealing with subsequent thermal annealing treatment. Both treatments are proven efficient in optimizing the phase separation between donor and acceptor materials [27]. For the first times, poly (2,5-dihexyloxy-1,4-phenylenevinylene) (PDHeOPV) was used as an additional electron donor in poly (3-hexylthiophene) (P3HT): phenyl-C<sub>61</sub>-butyric acid methyl ester (PCBM) binary blends systems. It is worthy to describe the effects of PDHeOPV weight ratio on the photo physical, morphological, optical and crystalline properties of the ternary blends thin films. In addition, the understanding on the effects of ternary blends and thermal annealing towards the photovoltaic properties of polymer solar cells devices is crucial.

### **1.3 Objectives of the Study**

The objectives of this study are:

- 1) To prepare and characterize the spray coated ternary blend P3HT: PDHeOPV: PCBM thin films in terms of photo physical, morphological and optical properties.

- 2) To investigate the influence of P3HT: PDHeOPV: PCBM weight ratio on the spray coated ternary blend films in terms of photo physical, morphological and optical properties.
- 3) To study the effects of solvent annealing and thermal annealing on the photo physical, optical and morphological properties of the P3HT: PDHeOPV: PCBM ternary blends systems.
- 4) To fabricate the inverted ternary blends of P3HT: PDHeOPV: PCBM as an active layer in polymer solar cell devices

#### **1.4 Scopes of the Study**

In order to achieve the above objectives, few scopes have been drawn.

- i. Conducting a preliminary study to obtain the optimum spray deposition time by varying the spray deposition time from 10s to 20s to fabricate the P3HT: PCBM thin films. Substrate to nozzle distance and air pressure were set at 7 cm and 1 bar, respectively.
- ii. Characterizing the spray coated thin films using optical microscope, atomic force microscope (AFM) and UV-Vis spectrophotometer.
- iii. Fabricating P3HT: PDHeOPV: PCBM bulk heterojunction (BHJ) thin films using spray coating method with different PDHeOPV weight ratio (0.5-2).
- iv. Characterizing the fabricated ternary blend thin films using differential scanning calorimeter (DSC), UV-Vis spectrophotometer, atomic force microscope (AFM), X-ray diffractometer (XRD), and photoluminescence (PL) spectroscope.

- v. Performing post-deposition treatment (solvent annealing and thermal annealing) on the P3HT: PDHeOPV: PCBM thin films by varying the thermal annealing temperature from 130 °C- 150 °C. The solvent annealing treatment was done inside a petri dish for 15 min. The thermal annealing time were kept constant at 10 min.
- vi. Characterizing the annealed thin films using UV-Vis spectrophotometer, AFM, XRD and PL spectroscope.
- vii. Identifying the optimum P3HT: PDHeOPV: PCBM weight ratio in ternary blends under post-deposition treatment in order to produce the ideal thin films in active layer of polymer solar cells.
- viii. Fabricating the ternary blend polymer solar cells in inverted structure. The inverted structure used for this study was ITO/TiO<sub>x</sub>/P3HT: PDHeOPV: PCBM/PEDOT: PSS/PTE/Au.
- ix. Investigating the photovoltaic performance of the inverted devices using semiconductor characterization systems. Devices illuminated by xenon lamp as the light source at an irradiation intensity of 100mW/cm<sup>2</sup> and air mass 1.5 filters (AM 1.5).
- x. Investigating the effect of continuous illumination to inverted devices performance. The light illumination times are varied from 0-120 min and the I<sub>sc</sub> and V<sub>oc</sub> values were obtained for every 30 min.

## **1.5 Significance of the Study**

This study is expected to provide a better understanding on the relationship between physicochemical properties (e.g. crystallinity, roughness, optical) and performance of the PSC, hereby improving the device performance by finer

controlling the thin film morphology. It is known that the blend morphology can be controlled through post-deposition treatments such as thermal annealing and solvent annealing. These treatments are able to increase the relative crystallinity of the blend phases and consequently resulting in enhancing optical properties and transport properties. Thus, attempts are made to investigate the optimum post-deposition parameter for the formation of thin film in active layer of PSC. To the best of my knowledge, there is no published researches investigate on the effect of solvent annealing with subsequent thermal annealing to the photo physical, morphological, optical, crystalline properties and photovoltaic properties of ternary blends films, particularly by using PDHeOPV as an additional electron donor in P3HT:PCBM systems. The effect of illumination time on the photovoltaic properties of ternary blend devices which is rarely reported is also investigated in this study. The findings of this study are important to discover the mechanism of the annealing treatment in the molecular level. The outputs of this study have the potentials for developing PSC with enhanced PCE and are useful for future studies towards commercialization of PSC technologies.

## **1.6 Organization of the Thesis**

The thesis consists of 8 chapters. Chapter 1 outlines brief information on the polymer solar cells and its current issues that leads us to conduct this research. The objectives, scopes and the significance of this study also been highlighted in this chapter. In Chapter 2, detailed information on the types of polymer solar cells, its operational principles and previous research on enhancing the PSC performance and stability were elaborated. Additionally, the method that has been employed by previous researchers to fabricate PSC is also discussed. Chapter 3 focuses on the experimental methods and characterization techniques that were used during this study.

Results and discussion were deliberated in Chapter 4 - Chapter 7. Chapter 4 describes in detail the effects of spray deposition time on the optical and morphological properties of P3HT: PCBM thin films. The spray deposition times were varied from 10s, 15s and 20s. The optimum deposition time were selected and were used to fabricate the thin film in Chapter 5. Chapter 5 discusses on the effect of P3HT: PDHeOPV: PCBM weight ratio on the optical and morphological properties of the thin films. The miscibility of the blends with the PDHeOPV weight ratio variation was investigated using differential scanning calorimeter (DSC).

The effects of solvent annealing and thermal annealing on the optical, morphological and crystallinity properties of the blends films are addressed in Chapter 6. The obtained properties were analysed and the best weight ratio of P3HT: PDHeOPV: PCBM were chosen to fabricate the PSC devices in Chapter 7. In Chapter 7, the dependence of the performance of ternary blends polymer solar cells on thermal annealing temperature is addressed. The effects of continuous illumination on the photovoltaic properties of inverted devices were examined by exposing the devices under continuous illumination for 120min. Finally, the general conclusions of this study and some recommendation for future work were listed in Chapter 8.

## REFERENCES

1. Cai, W., Gong, X., and Cao, Y., Polymer solar cells: Recent development and possible routes for improvement in the performance. *Solar Energy Materials and Solar Cells*, 2010, 94(2): 114-127.
2. Chua, S.C., Oh, T.H., and Goh, W.W., Feed-in tariff outlook in Malaysia. *Renewable and Sustainable Energy Reviews*, 2011, 15(1): 705-712.
3. Sriram, S., *Solar Power in Malaysia – Impediments to Growth*, in Frost & Sullivan Market Insight. 2006.
4. Nielsen, T.D., Cruickshank, C., Foged, S., Thorsen, J., and Krebs, F.C., Business, market and intellectual property analysis of polymer solar cells. *Solar Energy Materials and Solar Cells*, 2010, 94(10): 1553-1571.
5. Kang-Shyang, L., Soniya, D.Y., Amrita, H., Nigel J. A., and C., S.A., Designs and Architectures for the Next Generation of Organic Solar Cells. *Energies*, 2010, 3: 1212-1250.
6. Petritsch, D.I.K., *Organic Solar Cell Architectures* in *Technisch-Naturwissenschaftliche Fakultät* 2010, Technischen Universität Graz (Austria).
7. Yamanari, T., Taima, T., Sakai, J., and Saito, K., Origin of the open-circuit voltage of organic thin-film solar cells based on conjugated polymers. *Solar Energy Materials and Solar Cells*, 2009, 93(6-7): 759-761.
8. C.Krebs, F., Fabrication and processing of polymer solar cells:A review of printing and coating techniques. *Solar Energy Materials & Solar Cells*, 2009, 93: 394-412.
9. Chang, C.-L., Liang, C.-W., Syu, J.-J., Wang, L., and Leung, M.-k., Triphenylamine-substituted methanofullerene derivatives for enhanced open-circuit voltages and efficiencies in polymer solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(8): 2371-2379.

10. Almantas, P., Helmut, N., and Niyazi Serdar, S., Influence of processing additives to nano-morphology and efficiency of bulk-heterojunction solar cells: A comparative review. *Solar Energy* 2011, 85: 1226-1237.
11. Kohji, M., Michihiro, O., Hideo, O., Hiroaki, B., and Shinzaburo, I., Hybrid solar cells of layer-by-layer thin films with a polymer/fullerene bulk heterojunction. *Solar Energy Materials & Solar Cells* 2009, 93: 762-767.
12. Zhu, H., Wei, J., Wang, K., and Wu, D., Applications of carbon materials in photovoltaic solar cells. *Solar Energy Materials and Solar Cells*, 2009, 93(9): 1461-1470.
13. Ray, B., Nair, P.R., and Alam, M.A., Annealing dependent performance of organic bulk-heterojunction solar cells: A theoretical perspective. *Solar Energy Materials and Solar Cells*, 2011, 95(12).
14. Li, G., Yao, Y., Yang, H., Shrotriya, V., Yang, G., and Yang, Y., "Solvent Annealing" Effect in Polymer Solar Cells Based on Poly(3-hexylthiophene) and Methanofullerenes. *Advanced Functional Materials*, 2007, 17(10): 1636-1644.
15. Bin Mohd Yusoff, A.R., Lee, S.J., Kim, J., Shneider, F.K., Da Silva, W.J., and Jang, J., High-performance inverted tandem polymer solar cells utilizing thieno[3,4-c ]pyrrole-4,6-dione copolymer. *ACS Applied Materials and Interfaces*, 2014, 6(15): 13079-13087.
16. Chen, C.C., Chang, W.H., Yoshimura, K., Ohya, K., You, J., Gao, J., Hong, Z., and Yang, Y., An efficient triple-junction polymer solar cell having a power conversion efficiency exceeding 11%. *Advanced Materials*, 2014, 26(32): 5670-5677.
17. Mitul, A.F., Mohammad, L., Venkatesan, S., Adhikari, N., Sigdel, S., Wang, Q., Dubey, A., Khatiwada, D., and Qiao, Q., Low temperature efficient interconnecting layer for tandem polymer solar cells. *Nano Energy*, 2015, 11: 56-63.
18. Shim, J.W., Fuentes-Hernandez, C., Zhou, Y., Dindar, A., Khan, T.M., Giordano, A.J., Cheun, H., Yun, M., Marder, S.R., and Kippelen, B., Inverted tandem polymer solar cells with polyethylenimine-modified MoO X/Al<sub>2</sub>O<sub>3</sub>:ZnO nanolaminate as the charge recombination layers. *Advanced Energy Materials*, 2014, 4(10).

19. Youngkyoo, K., Minjung, S., and Hwajeong, K., Polymer solar cells with ternary blend nanolayers. *J Nanosci Nanotechnol* 2008, 8(12): 6247-6252.
20. Aziz, F., Ismail, A.F., Aziz, M., and Soga, T., Effect of solvent annealing on the crystallinity of spray coated ternary blend films prepared using low boiling point solvents. *Chem. Eng. Process: Process Intensification*, 2014, 79: 48-55.
21. Sharma, G.D., Suresh, P., Sharma, S.S., Vijay, Y.K., and Mikroyannidis, J.A., Effect of Solvent and Subsequent Thermal Annealing on the Performance of Phenylenevinylene Copolymer:PCBM Solar Cells. *ACS Applied Materials & Interfaces*, 2010, 2(2): 504-510.
22. Lin, R., Wright, M., Puthen Veettil, B., and Uddin, A., Enhancement of ternary blend organic solar cell efficiency using PTB7 as a sensitizer. *Synthetic Metals*, 2014, 192: 113-118.
23. Khlyabich, P.P., Rudenko, A.E., Street, R.A., and Thompson, B.C., Influence of Polymer Compatibility on the Open-Circuit Voltage in Ternary Blend Bulk Heterojunction Solar Cells. *ACS Applied Materials & Interfaces*, 2014, 6(13): 9913-9919.
24. Machui, F., Rathgeber, S., Li, N., Ameri, T., and Brabec, C.J., Influence of a ternary donor material on the morphology of a P3HT:PCBM blend for organic photovoltaic devices. *Journal of Materials Chemistry*, 2012, 22(31): 15570-15577.
25. Jeong, S., Woo, S.-H., Lyu, H.-K., and Han, Y.S., Effects of a perfluorinated compound as an additive on the power conversion efficiencies of polymer solar cells. *Sol. Energ. Mat. Sol. C*, 2011, 95(7): 1908-1914.
26. Pivrikas, A., Neugebauer, H., and Sariciftci, N.S., Influence of processing additives to nano-morphology and efficiency of bulk-heterojunction solar cells: A comparative review. *Solar Energy*, 2011, 85(6): 1226-1237.
27. Cugola, R., Giovanella, U., Di Gianvincenzo, P., Bertini, F., Catellani, M., and Luzzati, S., Thermal characterization and annealing effects of polythiophene/fullerene photoactive layers for solar cells. *Thin Solid Films*, 2006, 511-512: 489-493.

28. Ryu, M.S., Cha, H.J., and Jang, J., Effects of thermal annealing of polymer:fullerene photovoltaic solar cells for high efficiency. *Curr Appl Phys*, 2010, 10(2, Supplement): S206-S209.
29. Chen, F.-C., Ko, C.-J., Wu, J.-L., and Chen, W.-C., Morphological study of P3HT:PCBM blend films prepared through solvent annealing for solar cell applications. *Sol. Energ. Mat. Sol. C.*, 2010, 94(12): 2426-2430.
30. Kittichungchit, V., Hori, T., Moritou, H., Kubo, H., Fujii, A., and Ozaki, M., Effect of solvent vapor treatment on photovoltaic properties of conducting polymer/C<sub>60</sub> interpenetrating heterojunction structured organic solar cell. *Thin Solid Films*, 2009, 518(2): 518-521.
31. Yilmaz Canli, N., Günes, S., Pivrikas, A., Fuchsbauer, A., Sinwel, D., Sariciftci, N.S., Yasa, Ö., and Bilgin-Eran, B., Chiral (S)-5-octyloxy-2-[{4-(2-methylbutyloxy)-phenylimino}-methyl]-phenol liquid crystalline compound as additive into polymer solar cells. *Solar Energy Materials and Solar Cells*, 2010, 94(6): 1089-1099.
32. Zhang, H., Wicht, G., Gretener, C., Nagel, M., Nüesch, F., Romanyuk, Y., Tisserant, J.-N., and Hany, R., Semitransparent organic photovoltaics using a near-infrared absorbing cyanine dye. *Solar Energy Materials and Solar Cells*, 2013, 118: 157-164.
33. Yang, P., Zhou, X., Cao, G., and Luscombe, C.K., P3HT:PCBM polymer solar cells with TiO<sub>2</sub> nanotube aggregates in the active layer. *Journal of Materials Chemistry*, 2010, 20(13): 2612-2616.
34. Gunduz, B., Yahia, I.S., and Yakuphanoglu, F., Electrical and photoconductivity properties of p-Si/P3HT/Al and p-Si/P3HT:MEH-PPV/Al organic devices: Comparison study. *Microelectronic Engineering*, 2012, 98: 41-57.
35. Hammed, W.A., Yahya, R., Bola, A.L., and Mahmud, H.N.M.E., Recent approaches to controlling the nanoscale morphology of polymer-based bulk-heterojunction solar cells. *Energies*, 2013, 6(11): 5847-5868.
36. Pathak, M.J.M., Girotra, K., Harrison, S.J., and Pearce, J.M., The effect of hybrid photovoltaic thermal device operating conditions on intrinsic layer thickness optimization of hydrogenated amorphous silicon solar cells. *Solar Energy*, 2012, 86(9): 2673-2677.

37. Huang, Q.L. and Li, H.X., Recent progress of bulk heterojunction solar cells based on small-molecular donors. *Chinese Science Bulletin*, 2013, 58(22): 2677-2685.
38. Wang, T., Pearson, A.J., Lidzey, D.G., and Jones, R.A.L., Evolution of Structure, Optoelectronic Properties, and Device Performance of Polythiophene:Fullerene Solar Cells During Thermal Annealing. *Advanced Functional Materials*, 2011, 21(8): 1383-1390.
39. Petr, P.K., Beate, B., and T., B.C., Efficient Ternary Blend Bulk Heterojunction Solar Cells with Tunable Open-Circuit Voltage. *Journal of the American Chemical Society*, 2011: 110819174839087.
40. Benanti, T. and Venkataraman, D., Organic Solar Cells: An Overview Focusing on Active Layer Morphology. *Photosynthesis Research*, 2006, 87(1): 73-81.
41. Scharber, M.C. and Sariciftci, N.S., Efficiency of bulk-heterojunction organic solar cells. *Progress in Polymer Science*, 2013, 38(12): 1929-1940.
42. Zimmermann, B., Würfel, U., and Niggemann, M., Longterm stability of efficient inverted P3HT:PCBM solar cells. *Solar Energy Materials and Solar Cells*, 2009, 93(4): 491-496.
43. Zhu, Y., Xu, X., Zhang, L., Chen, J., and Cao, Y., High efficiency inverted polymeric bulk-heterojunction solar cells with hydrophilic conjugated polymers as cathode interlayer on ITO. *Solar Energy Materials and Solar Cells*, 2012, 97: 83-88.
44. Yang, X. and Uddin, A., Effect of thermal annealing on P3HT:PCBM bulk-heterojunction organic solar cells: A critical review. *Renewable and Sustainable Energy Reviews*, 2014, 30: 324-336.
45. Chidichimo, G. and Filippelli, L., Organic Solar Cells: Problems and Perspectives. *International Journal of Photoenergy*, 2010.
46. Boland, P., Lee, K., Dean, J., and Namkoong, G., Design of organic tandem solar cells using low- and high-bandgap polymer:fullerene composites. *Solar Energy Materials and Solar Cells*, 2010, 94(12): 2170-2175.
47. Tore, N., Parlak, E.A., Usluer, O., Egbe, D.A.M., San, S.E., and Aydogan, P., Effect of blend ratio on poly(p-phenylene-ethynylene)-alt-poly(p-phenylene-

- vinylene) polymer solar cell. *Solar Energy Materials and Solar Cells*, 2012, 104: 39-44.
48. Tumbleston, J.R., Yang, L., You, W., and Ade, H., Morphology linked to miscibility in highly amorphous semi-conducting polymer/fullerene blends. *Polymer (United Kingdom)*, 2014, 55(19): 4884-4889.
49. Chen, L.-M., Hong, Z., Kwan, W.L., Lu, C.-H., Lai, Y.-F., Lei, B., Liu, C.-P., and Yang, Y., Multi-Source/Component Spray Coating for Polymer Solar Cells. *ACS Nano*, 2010, 4(8): 4744-4752.
50. Shih, C.-F., Hung, K.-T., Wu, H.-T., Fu, S.-W., Chen, H.-J., and Hsiao, C.-Y., In situ monitoring of photovoltaic properties in organic solar cells during thermal annealing. *Organic Electronics*, 2012, 13(3): 373-376.
51. Chen, L.-M., Xu, Z., Hong, Z., and Yang, Y., Interface investigation and engineering - achieving high performance polymer photovoltaic devices. *Journal of Materials Chemistry*, 2010, 20(13): 2575-2598.
52. Wang, H., Zheng, Y., Zhang, L., and Yu, J., Effect of two-step annealing on the performance of ternary polymer solar cells based on P3HT:PC<sub>71</sub>BM:SQ. *Sol. Energ. Mat. Sol. Cells*, 2014, 128: 215-220.
53. Wang, Y., Wei, W., Liu, X., and Gu, Y., Research progress on polymer heterojunction solar cells. *Sol. Energ. Mat. Sol. C.*, 2012, 98: 129-145.
54. Bian, L., Zhu, E., Tang, J., Tang, W., and Zhang, F., Recent progress in the design of narrow bandgap conjugated polymers for high-efficiency organic solar cells. *Prog. Polym. Sci.*, 37(9): 1292-1331.
55. Feng Lee, J., Hsu, S.L.C., Lee, P.I., Yi Chuang, H., Sue Chen, J., and Yang Chou, W., A new narrow bandgap polyfluorene copolymer containing 2,6-bis-(3-hexyl-thiophen-2-yl)-anthraquinone unit for solar cell applications. *Sol. Energ. Mat. Sol. C.*, 2012, 96: 218-225.
56. Nam, M., Kim, S., Kang, M., Kim, S.-W., and Lee, K.-K., Efficiency enhancement in organic solar cells by configuring hybrid interfaces with narrow bandgap PbSSe nanocrystals. *Org. Electron.*, 2012, 13(9): 1546-1552.
57. Hsiang-Yu, C., Hoichang, Y., Guanwen, Y., Srinivas, S., Ruben, Z., Gang, L., and Yang, Y., Fast-Grown Interpenetrating Network in Poly(3-hexylthiophene): Methanofullerenes Solar Cells Processed with Additive. *J. Phys. Chem. C*, 2009, 113: 7946-7953.

58. Ma, W., Yang, C., Gong, X., Lee, K., and Heeger, A.J., Thermally Stable, Efficient Polymer Solar Cells with Nanoscale Control of the Interpenetrating Network Morphology. *Adv. Funct. Mater.*, 2005, 15(10): 1617-1622.
59. Mekhilef, S., Saidur, R., and Safari, A., A review on solar energy use in industries. *Renewable and Sustainable Energy Reviews*, 2011, 15(4): 1777-1790.
60. Wurfel, P., ed. *Physics of solar cells: From principles to new concepts*. 2005, Wiley-WCH: Weinheim.
61. Ruderer, M.A., Guo, S., Meier, R., Chiang, H.-Y., and Korstgens, V., Solvent-induced morphology in polymer-based systems for organic photovoltaics. *Adv. Funct. Mater.*, 2011, 21: 3382-3391.
62. Zhong, H., Yang, X., deWith, B., and Loos, J., Quantitative Insight into Morphology Evolution of Thin PPV/PCBM Composite Films Upon Thermal Treatment. *Macromolecules*, 2006, 39: 218-223.
63. Eom, S.H., Park, H., Mujawar, S.H., Yoon, S.C., Kim, S.-S., Na, S.-I., Kang, S.-J., Khim, D., Kim, D.-Y., and Lee, S.-H., High efficiency polymer solar cells via sequential inkjet-printing of PEDOT:PSS and P3HT:PCBM inks with additives. *Org. Electron.*, 2010, 11(9): 1516-1522.
64. Martens, T., D'Haen, J., Munters, T., Beelen, Z., Goris, L., Manca, J., D'Olieslaeger, M., Vanderzande, D., De Schepper, L., and Andriessen, R., Disclosure of the nanostructure of MDMO-PPV:PCBM bulk hetero-junction organic solar cells by a combination of SPM and TEM. *Synthetic Metals*, 2003, 138(1-2): 243-247.
65. Jose M. Lobe, Trisha L. Andrew, Vladimir Bulovic, and Swager, T.M., Improving the Performance of P3HT Fullerene Solar Cells with Side-ChainFunctionalized Poly(thiophene) Additives: A New Paradigm for Polymer Design. *ACS Nano*, 2012, 6: 3044-3056.
66. Zhang, F., Xu, X., Tang, W., Zhang, J., Zhuo, Z., Wang, J., Wang, J., Xu, Z., and Wang, Y., Recent development of the inverted configuration organic solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(7): 1785-1799.
67. Oo, T.Z., Mathews, N., Tam, T.L., Xing, G.C., Sum, T.C., Sellinger, A., Wong, L.H., and Mhaisalkar, S.G., Investigation of photophysical,

- morphological and photovoltaic behavior of poly(p-phenylene vinylene) based polymer/oligomer blends. *Thin Solid Films*, 2010, 518(18): 5292-5299.
68. Bi, D., Wu, F., Yue, W., Qu, Q., Cui, Q., Qiu, Z., Liu, C., Shen, W., and Wang, M., Improved performance of MEH-PPV/ZnO solar cells by addition of lithium salt. *Sol. Energy*, 2011, 85(11): 2819-2825.
69. Cevik, E., İlcalı, D., Egbe, D.A.M., and Günes, S., Bulk heterojunction and inverted type solar cells using a CN-PPV derivative. *Solar Energy Materials and Solar Cells*, 2012, 98: 94-102.
70. Chatterjee, S., Banerjee, S., and Banerji, P., New polymer acceptor for solar cells application. *Synthetic Metals*, 2012, 162(7-8): 566-572.
71. Eerenstein, W., Slooff, L.H., Veenstra, S.C., and Kroon, J.M., Optical modeling as optimization tool for single and double junction polymer solar cells. *Thin Solid Films*, 2008, 516(20): 7188-7192.
72. Bundgaard, E., Shaheen, S.E., Krebs, F.C., and Ginley, D.S., Bulk heterojunctions based on a low band gap copolymer of thiophene and benzothiadiazole. *Solar Energy Materials and Solar Cells*, 2007, 91(17): 1631-1637.
73. de Freitas, J.N., Pivrikas, A., Nowacki, B.F., Akcelrud, L.C., Sariciftci, N.S., and Nogueira, A.F., Investigation of new PPV-type polymeric materials containing fluorene and thiophene units and their application in organic solar cells. *Synthetic Metals*, 2010, 160(15-16): 1654-1661.
74. Thomas, K., Hans-Heinrich, H., and Dieter, N., Efficient Polymer Solar Cells Based on M3EH-PPV. *Chem. Mater.*, 2005, 17: 6532-6537.
75. Li, G., Shrotriya, V., Huang, J., Yao, Y., Moriarty, T., Emery, K., and Yang, Y., High-efficiency solution processable polymer photovoltaic cells by self-organization of polymer blends. *Nat Mater*, 2005, 4(11): 864-868.
76. Lee, J.K., Ma, W.L., Brabec, C.J., Yuen, J., Moon, J.S., Kim, J.Y., Lee, K., Bazan, G.C., and Heeger, A.J., Processing Additives for Improved Efficiency from Bulk Heterojunction Solar Cells. *JASC Articles*, 2008.
77. Kawano, K., Sakai, J., Yahiro, M., and Adachi, C., Effect of solvent on fabrication of active layers in organic solar cells based on poly(3-hexylthiophene) and fullerene derivatives. *Sol. Energ. Mat. Sol. C.*, 2009, 93(4): 514-518.

78. Ouyang, J. and Xia, Y., High-performance polymer photovoltaic cells with thick P3HT:PCBM films prepared by a quick drying process. *Sol. Energ. Mat. Sol. C.*, 2009, 93(9): 1592-1597.
79. Keawprajak, A., Piyakulawat, P., Klamchuen, A., Iamraksa, P., and Asawapirom, U., Influence of crystallizable solvent on the morphology and performance of P3HT:PCBM bulk-heterojunction solar cells. *Solar Energy Materials and Solar Cells*, 2010, 94(3): 531-536.
80. Yasuda, T., Suzuki, T., Takahashi, M., and Han, L., Air-stable triarylamine-based amorphous polymer as donor material for bulk-heterojunction organic solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(12): 3509-3515.
81. De Sio, A., Madena, T., Huber, R., Parisi, J., Neyshtadt, S., Deschler, F., Da Como, E., Esposito, S., and von Hauff, E., Solvent additives for tuning the photovoltaic properties of polymer–fullerene solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(12): 3536-3542.
82. Dang, M.T., Wantz, G., Bejbouji, H., Urien, M., Dautel, O.J., Vignau, L., and Hirsch, L., Polymeric solar cells based on P3HT:PCBM: Role of the casting solvent. *Sol. Energ. Mat. Sol. C.*, 2011, 95(12): 3408-3418.
83. He, Y., Chen, H.-Y., Zhao, G., Hou, J., and Li, Y., Synthesis and photovoltaic properties of biindene-C70 monoadduct as acceptor in polymer solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(7): 1762-1766.
84. Kettle, J., Horie, M., Majewski, L.A., Saunders, B.R., Tuladhar, S., Nelson, J., and Turner, M.L., Optimisation of PCPDTBT solar cells using polymer synthesis with Suzuki coupling. *Solar Energy Materials and Solar Cells*, 2011, 95(8): 2186-2193.
85. Zhao, G., He, Y., He, C., Fan, H., Zhao, Y., and Li, Y., Photovoltaic properties of poly(benzothiadiazole-thiophene-co-bithiophene) as donor in polymer solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(2): 704-711.
86. Li, W., Zhou, Y., Viktor Andersson, B., Mattias Andersson, L., Thomann, Y., Veit, C., Tvingstedt, K., Qin, R., Bo, Z., Inganäs, O., Würfel, U., and Zhang, F., The Effect of additive on performance and shelf-stability of HSX-1/PCBM photovoltaic devices. *Organic Electronics*, 2011, 12(9): 1544-1551.

87. Chambon, S., Mens, R., Vandewal, K., Clodic, E., Scharber, M., Lutsen, L., Gelan, J., Manca, J., Vanderzande, D., and Adriaensens, P., Influence of octanedithiol on the nanomorphology of PCPDTBT:PCBM blends studied by solid-state NMR. *Solar Energy Materials and Solar Cells*, 2012, 96(0): 210-217.
88. Jang, S.K., Gong, S.C., and Chang, H.J., Effects of various solvent addition on crystal and electrical properties of organic solar cells with P3HT:PCBM active layer. *Synthetic Met.*, 2012, 162(5–6): 426-430.
89. Park, C.-D., Fleetham, T.A., Li, J., and Vogt, B.D., High performance bulk-heterojunction organic solar cells fabricated with non-halogenated solvent processing. *Organic Electronics*, 2011, 12(9): 1465-1470.
90. Aïch, B.R., Lu, J., Beaupré, S., Leclerc, M., and Tao, Y., Control of the active layer nanomorphology by using co-additives towards high-performance bulk heterojunction solar cells. *Organic Electronics*, 2012, 13(9): 1736-1741.
91. Boland, P., Lee, K., and Namkoong, G., Device optimization in PCPDTBT:PCBM plastic solar cells. *Solar Energy Materials and Solar Cells*, 2010, 94(5): 915-920.
92. Sun, Y., Welch, G.C., Leong, W.L., Takacs, C.J., Bazan, G.C., and Heeger, A.J., Solution-processed small-molecule solar cells with 6.7% efficiency. *Nat Mater*, 2012, 11(1): 44-48.
93. Yang, L., Yan, L., and You, W., Organic Solar Cells beyond One Pair of Donor–Acceptor: Ternary Blends and More. *The Journal of Physical Chemistry Letters*, 2013, 4(11): 1802-1810.
94. Hwang, I., McNeill, C.R., and Greenham, N.C., Evolution of phase separation upon annealing and the influence on photocurrent generation in ternary blend organic solar cells. *Synthetic Met.*, 2014, 189: 63-68.
95. Li, N., Machui, F., Waller, D., Koppe, M., and Brabec, C.J., Determination of phase diagrams of binary and ternary organic semiconductor blends for organic photovoltaic devices. *Solar Energy Materials and Solar Cells*, 2011, 95(12): 3465-3471.
96. Goubard, F. and Wantz, G., Ternary blends for polymer bulk heterojunction solar cells. *Polymer International*, 2014, 63(8): 1362-1367.

97. Cnops, K., Rand, B.P., Cheyns, D., Verreet, B., Empl, M.A., and Heremans, P., 8.4% efficient fullerene-free organic solar cells exploiting long-range exciton energy transfer. *Nat Commun*, 2014, 5.
98. Lu, K., Fang, J., Zhu, X., Yan, H., Li, D., Di, C.a., Yang, Y., and Wei, Z., A facile strategy to enhance the fill factor of ternary blend solar cells by increasing charge carrier mobility. *New Journal of Chemistry*, 2013, 37(6): 1728-1735.
99. Nesterov, A.E. and Lipatov, Y.S., Thermodynamics of Polymer Blends. 1998: Taylor & Francis.
100. Yan, H., Li, D., Zhang, Y., Yang, Y., and Wei, Z., Rational Design of Ternary-Phase Polymer Solar Cells by Controlling Polymer Phase Separation. *The Journal of Physical Chemistry C*, 2014, 118(20): 10552-10559.
101. Lu, L., Xu, T., Chen, W., Landry, E.S., and Yu, L., Ternary blend polymer solar cells with enhanced power conversion efficiency. *Nat Photon*, 2014, 8(9): 716-722.
102. Qin, D., Wang, W., Wang, M., Jin, S., and Zhang, J., The dependence of the cathode architecture on the photoactive layer morphology in bulk-heterojunction polymeric solar cells. *Semiconductor Science and Technology*, 2014, 29(12): 125011.
103. Chang, S.-Y., Liao, H.-C., Shao, Y.-T., Sung, Y.-M., Hsu, S.-H., Ho, C.-C., Su, W.-F., and Chen, Y.-F., Enhancing the efficiency of low bandgap conducting polymer bulk heterojunction solar cells using P3HT as a morphology control agent. *Journal of Materials Chemistry A*, 2013, 1(7): 2447-2452.
104. Lin, R., Wright, M., Chan, K.H., Puthen-Veettil, B., Sheng, R., Wen, X., and Uddin, A., Performance improvement of low bandgap polymer bulk heterojunction solar cells by incorporating P3HT. *Organic Electronics*, 2014, 15(11): 2837-2846.
105. Chen, J., Yu, X., Hong, K., Messman, J.M., Pickel, D.L., Xiao, K., Dadmun, M.D., Mays, J.W., Rondinone, A.J., Sumpter, B.G., and Kilbey Ii, S.M., Ternary behavior and systematic nanoscale manipulation of domain structures in P3HT/PCBM/P3HT-b-PEO films. *Journal of Materials Chemistry*, 2012, 22(26): 13013-13022.

106. Kim, Y., Cook, S., Choulis, S.A., Nelson, J., Durrant, J.R., and Bradley, D.D.C., Effect of electron-transport polymer addition to polymer/fullerene blend solar cells. *Synthetic Metals*, 2005, 152(1-3): 105-108.
107. Cooling, N., Burke, K.B., Zhou, X., Lind, S.J., Gordon, K.C., Jones, T.W., Dastoor, P.C., and Belcher, W.J., A study of the factors influencing the performance of ternary MEH-PPV:porphyrin:PCBM heterojunction devices: A steric approach to controlling charge recombination. *Solar Energy Materials and Solar Cells*, 2011, 95(7): 1767-1774.
108. Ameri, T., Khoram, P., Min, J., and Brabec, C.J., Organic Ternary Solar Cells: A Review. *Advanced Materials*, 2013, 25(31): 4245-4266.
109. Yang, F., Shtein, M., and Forrest, S.R., Controlled growth of a molecular bulk heterojunction photovoltaic cell. *Nat Mater*, 2005, 4(1): 37-41.
110. Thompson, B.C. and Fréchet, J.M.J., Polymer-fullerene composite solar cells. *Angewandte Chemie - International Edition*, 2008, 47(1): 58-77.
111. Hoppe, H., Glatzel, T., Niggemann, M., Hinsch, A., Lux-Steiner, M.C., and Sariciftci, N.S., Kelvin Probe Force Microscopy Study on Conjugated Polymer/Fullerene Bulk Heterojunction Organic Solar Cells. *Nano Letters*, 2005, 5(2): 269-274.
112. Zhokhavets, U., Erb, T., Hoppe, H., Gobsch, G., and Serdar Sariciftci, N., Effect of annealing of poly(3-hexylthiophene)/fullerene bulk heterojunction composites on structural and optical properties. *Thin Solid Films*, 2006, 496(2): 679-682.
113. Green, R., Morfa, A., Ferguson, A.J., Kopidakis, N., Rumbles, G., and Shaheen, S.E., Performance of bulk heterojunction photovoltaic devices prepared by airbrush spray deposition. *Appl. Phys. Lett.*, 2008, 92(3): 033301-3.
114. Pivrikas, A., Neugebauer, H., and Sariciftci, N.S., Influence of processing additives to nano-morphology and efficiency of bulk-heterojunction solar cells: A comparative review. *Sol. Energy*, 2011, 85(6): 1226-1237.
115. Hoppe, H., Niggemann, M., Winder, C., Kraut, J., Hiesgen, R., Hinsch, A., Meissner, D., and Sariciftci, N.S., Nanoscale Morphology of Conjugated Polymer/Fullerene-Based Bulk- Heterojunction Solar Cells. *Advanced Functional Materials*, 2004, 14(10): 1005-1011.

116. Smith, J., Hamilton, R., McCulloch, I., Stingelin-Stutzmann, N., Heeney, M., Bradley, D.D.C., and Anthopoulos, T.D., Solution-processed organic transistors based on semiconducting blends. *Journal of Materials Chemistry*, 2010, 20(13): 2562-2574.
117. Mikroyannidis, J.A., Tsagkournos, D.V., Balraju, P., and Sharma, G.D., Efficient bulk heterojunction solar cells using an alternating phenylenevinylene copolymer with dithenyl(thienothiadiazole) segments as donor and PCBM or modified PCBM as acceptor. *Solar Energy Materials and Solar Cells*, 2011, 95(11): 3025-3035.
118. Mikroyannidis, J.A., Stylianakis, M.M., Cheung, K.Y., Fung, M.K., and Djurišić, A.B., Alternating phenylenevinylene and thienylenevinylene copolymers with cyano groups: Synthesis, photophysics and photovoltaics. *Synthetic Metals*, 2009, 159(1–2): 142-147.
119. Mikroyannidis, J.A., Kabanakis, A.N., Sharma, S.S., and Sharma, G.D., Low band-gap phenylenevinylene and fluorenevinylene small molecules containing triphenylamine segments: Synthesis and application in bulk heterojunction solar cells. *Organic Electronics*, 2011, 12(5): 774-784.
120. Guan, Z., Yu, J., Huang, J., and Zhang, L., Power efficiency enhancement of solution-processed small-molecule solar cells based on squaraine via thermal annealing and solvent additive methods. *Solar Energy Materials and Solar Cells*, 2013, 109: 262-269.
121. Pandey, A.K. and Nunzi, J.-M., Impact of selective thermal annealing on rubrene-C<sub>60</sub> heterojunction solar cells. *Synthetic Metals*, 2012, 162(23): 2171-2175.
122. Chu, C.-W., Yang, H., Hou, W.-J., Huang, J., Li, G., and Yang, Y., Control of the nanoscale crystallinity and phase separation in polymer solar cells. *Applied Physics Letters*, 2008, 92(10).
123. Zhang, L., Xing, X., Zheng, L., Chen, Z., Xiao, L., Qu, B., and Gong, Q., Vertical phase separation in bulk heterojunction solar cells formed by in situ polymerization of fulleride. *Sci. Rep.*, 2014, 4.
124. Ho, C.-S., Huang, E.L., Hsu, W.-C., Lee, C.-S., Lai, Y.-N., Yao, E.-P., and Wang, C.-W., Thermal effect on polymer solar cells with active layer concentrations of 3–5wt%. *Synthetic Metals*, 2012, 162(13–14): 1164-1168.

125. Lee, J.-h., Sagawa, T., and Yoshikawa, S., Morphological and topographical characterizations in spray coated organic solar cells using an additional solvent spray deposition. *Org. Electron.*, 2011, 12(12): 2165-2173.
126. Kim, Y., Kim, G., Lee, J., and Lee, K., Morphology controlled bulk-heterojunction layers of fully electro-spray coated organic solar cells. *Sol. Energ. Mat. Sol. Cells*, 2012, 105: 272-279.
127. Colsmann, A., Reinhard, M., Kwon, T.-H., Kayser, C., Nickel, F., Czolk, J., Lemmer, U., Clark, N., Jasieniak, J., Holmes, A.B., and Jones, D., Inverted semi-transparent organic solar cells with spray coated, surfactant free polymer top-electrodes. *Solar Energy Materials and Solar Cells*, 2012, 98: 118-123.
128. Kang, J.-W., Kang, Y.-J., Jung, S., Song, M., Kim, D.-G., Su Kim, C., and Kim, S.H., Fully spray-coated inverted organic solar cells. *Sol. Energ. Mat. Sol. Cells*, 2012, 103: 76-79.
129. Yap, J.H., To, T.T., and Adams, S., Monte Carlo Morphological modelling of a P3HT:PCBM bulk heterojunction organic solar cell. *Journal of Polymer Science, Part B: Polymer Physics*, 2015, 53(4): 270-279.
130. Georgiou, D., Laskarakis, A., Morana, M., Karagiannidis, P.G., and Logothetidis, S., Non-destructive optical characterization of phase separation in bulk heterojunction organic photovoltaic cells. *Solar Energy Materials and Solar Cells*, 2014, 125: 190-197.
131. Yuan, J., Dong, H., Li, M., Huang, X., Zhong, J., Li, Y., and Ma, W., High polymer/fullerene ratio realized in efficient polymer solar cells by tailoring of the polymer side-chains. *Advanced Materials*, 2014, 26(22): 3624-3630.
132. Hu, Z., Zhang, J., Xiong, S., and Zhao, Y., Performance of polymer solar cells fabricated by dip coating process. *Sol. Energ. Mat. Sol. Cells*, 2012, 99: 221-225.
133. Lim, S.-L., Chen, E.-C., Chen, C.-Y., Ong, K.-H., Chen, Z.-K., and Meng, H.-F., High performance organic photovoltaic cells with blade-coated active layers. *Sol. Energ. Mat. Sol. Cells*, 2012, 107: 292-297.
134. Chang, Y.-H., Tseng, S.-R., Chen, C.-Y., Meng, H.-F., Chen, E.-C., Horng, S.-F., and Hsu, C.-S., Polymer solar cell by blade coating. *Org. Electron.*, 2009, 10(5): 741-746.

135. Lee, J.-h., Sagawa, T., and Yoshikawa, S., Thickness dependence of photovoltaic performance of additional spray coated solar cells. *Thin Solid Films*, 2013, 529: 464-469.
136. Steirer, K.X., Reese, M.O., Rupert, B.L., Kopidakis, N., Olson, D.C., Collins, R.T., and Ginley, D.S., Ultrasonic spray deposition for production of organic solar cells. *Sol. Energ. Mat. Sol. Cells*, 2009, 93(4): 447-453.
137. Park, S.-Y., Kang, Y.-J., Lee, S., Kim, D.-G., Kim, J.-K., Kim, J.H., and Kang, J.-W., Spray-coated organic solar cells with large-area of 12.25 cm<sup>2</sup>. *Sol. Energ. Mat. Sol. Cells*, 2011, 95(3): 852-855.
138. Jeong, J.-A., Lee, J., Kim, H., Kim, H.-K., and Na, S.-I., Ink-jet printed transparent electrode using nano-size indium tin oxide particles for organic photovoltaics. *Sol. Energ. Mat. Sol. Cells*, 2010, 94(10): 1840-1844.
139. Voigt, M.M., Mackenzie, R.C.I., King, S.P., Yau, C.P., Atienzar, P., Dane, J., Keivanidis, P.E., Zadrazil, I., Bradley, D.D.C., and Nelson, J., Gravure printing inverted organic solar cells: The influence of ink properties on film quality and device performance. *Sol. Energ. Mat. Sol. Cells*, 2012, 105: 77-85.
140. Krebs, F.C., Fabrication and processing of polymer solar cells: A review of printing and coating techniques. *Sol. Energ. Mat. Sol. Cells*, 2009, 93(4): 394-412.
141. Hu, Z., Zhang, J., Xiong, S., and Zhao, Y., Annealing-free, air-processed and high-efficiency polymer solar cells fabricated by a dip coating process. *Org. Electron.*, 2012, 13(1): 142-146.
142. Krebs, F.C., Pad printing as a film forming technique for polymer solar cells. *Sol. Energ. Mat. Sol. Cells*, 2009, 93(4): 484-490.
143. Jørgensen, M., Hagemann, O., Alstrup, J., and Krebs, F.C., Thermo-cleavable solvents for printing conjugated polymers: Application in polymer solar cells. *Sol. Energ. Mat. Sol. Cells*, 2009, 93(4): 413-421.
144. Krebs, F.C., Jørgensen, M., Norrman, K., Hagemann, O., Alstrup, J., Nielsen, T.D., Fyenbo, J., Larsen, K., and Kristensen, J., A complete process for production of flexible large area polymer solar cells entirely using screen printing—First public demonstration. *Sol. Energ. Mat. Sol. Cells*, 2009, 93(4): 422-441.

145. Girotto, C., Rand, B.P., Genoe, J., and Heremans, P., Exploring spray coating as a deposition technique for the fabrication of solution-processed solar cells. *Sol. Energ. Mat. Sol. Cells*, 2009, 93(4): 454-458.
146. Voigt, M.M., Mackenzie, R.C.I., Yau, C.P., Atienzar, P., Dane, J., Keivanidis, P.E., Bradley, D.D.C., and Nelson, J., Gravure printing for three subsequent solar cell layers of inverted structures on flexible substrates. *Sol. Energ. Mat. Sol. Cells*, 2011, 95(2): 731-734.
147. Dupont, S.R., Oliver, M., Krebs, F.C., and Dauskardt, R.H., Interlayer adhesion in roll-to-roll processed flexible inverted polymer solar cells. *Sol. Energ. Mat. Sol. Cells*, 2012, 97: 171-175.
148. Schrödner, M., Sensfuss, S., Schache, H., Schultheis, K., Welzel, T., Heinemann, K., Milker, R., Marten, J., and Blankenburg, L., Reel-to-reel wet coating by variation of solvents and compounds of photoactive inks for polymer solar cell production. *Solar Energy Materials and Solar Cells*, 2012, 107.
149. Saitoh, L., Babu, R.R., Kannappan, S., Kojima, K., Mizutani, T., and Ochiai, S., Performance of spray deposited poly [N-9"-hepta-decanyl-2,7-carbazole-alt-5,5-(4',7'-di-2-thienyl-2',1',3'-benzothiadiazole)]/[6,6]-phenyl-C61-butyric acid methyl ester blend active layer based bulk heterojunction organic solar cell devices. *Thin Solid Films*, 2012, 520(7): 3111-3117.
150. Susanna, G., Salamandra, L., Brown, T.M., Di Carlo, A., Brunetti, F., and Reale, A., Airbrush spray-coating of polymer bulk-heterojunction solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(7): 1775-1778.
151. Lewis, J.E., Lafalce, E., Toglia, P., and Jiang, X., Over 30% transparency large area inverted organic solar array by spray. *Sol. Energ. Mat. Sol. Cells*, 2011, 95(10): 2816-2822.
152. Vak, D., Kim, S.-S., Jo, J., Oh, S.-H., Na, S.-I., Kim, J., and Kim, D.-Y., Fabrication of organic bulk heterojunction solar cells by a spray deposition method for low-cost power generation. *Appl. Phys. Lett.*, 2007, 91(8): 081102-3.
153. Hoth, C.N., Steim, R., Schilinsky, P., Choulis, S.A., Tedde, S.F., Hayden, O., and Brabec, C.J., Topographical and morphological aspects of spray coated organic photovoltaics. *Org. Electron.*, 2009, 10(4): 587-593.

154. Kim, K.-J., Kim, Y.-S., Kang, W.-S., Kang, B.-H., Yeom, S.-H., Kim, D.-E., Kim, J.-H., and Kang, S.-W., Inspection of substrate-heated modified PEDOT:PSS morphology for all spray deposited organic photovoltaics. *Sol. Ener. Mat. Sol. Cells*, 2010, 94(7): 1303-1306.
155. Nie, W., Coffin, R., Liu, J., MacNeill, C.M., Li, Y., Noftle, R.E., and Carroll, D.L., Exploring Spray-Coating Techniques for Organic Solar Cell Applications. *Int. J. Photoenergy*, 2012, 2012: 7.
156. Guo, X., Zhang, M., Cui, C., Hou, J., and Li, Y., Efficient polymer solar cells based on poly(3-hexylthiophene) and indene-C60 bisadduct fabricated with non-halogenated solvents. *ACS Applied Materials and Interfaces*, 2014, 6(11): 8190-8198.
157. Perelaer, J., Smith, P.J., Wijnen, M.M.P., van den Bosch, E., Eckardt, R., Ketelaars, P.H.J.M., and Schubert, U.S., Droplet Tailoring Using Evaporative Inkjet Printing. *Macromolecular Chemistry and Physics*, 2009, 210(5): 387-393.
158. Kim, H., So, W.-W., and Moon, S.-J., Effect of Thermal Annealing on the Performance of P3HT/PCBM Polymer Photovoltaic Cells. *Journal of the Korean Physical Society*, 2006: 441-445.
159. Gfroerer, T.H., *Photoluminescence in Analysis of Surfaces and Interfaces*, in *Encyclopedia of Analytical Chemistry*, R.A.M. (Ed.), Editor. p. pp. 9209–9231.
160. Yavuz, N., Yuksel, S.A., Karsli, A., and Gunes, S., Inverted structure hybrid solar cells using CdS thin films. *Sol. Energ. Mat. Sol. Cells*, 2013, 116: 224-230.
161. Valdés, M.H., Berriuet, M., Goossens, A., and Vázquez, M., Spray deposition of CuInS<sub>2</sub> on electrodeposited ZnO for low-cost solar cells. *Surf. Coat. Tech.*, 2010, 204(24): 3995-4000.
162. Ju, J., Yamagata, Y., and Higuchi, T., Thin-Film Fabrication Method for Organic Light-Emitting Diodes Using Electrospray Deposition. *Adv. Mater.*, 2009, 21(43): 4343-4347.
163. Fukuda, T., Asaki, H., Asano, T., Takagi, K., Honda, Z., Kamata, N., Ju, J., and Yamagata, Y., Surface morphology of fluorene thin film fabricated by

- electrospray deposition technique using two organic solvents: Application for organic light-emitting diodes. *Thin Solid Films*, 2011, 520(1): 600-605.
- 164. Mario, P., Giovanni, P., and Rosaria, C., Flexible Solar Cells. Technology & Engineering. 2008, Germany: John Wiley & Sons
  - 165. Chu, T.-Y., Alem, S., Tsang, S.-W., Tse, S.-C., Wakim, S., Lu, J., Dennler, G., Waller, D., Gaudiana, R., and Tao, Y., Morphology control in polycarbazole based bulk heterojunction solar cells and its impact on device performance. *Appl. Phys. Lett.*, 2011, 98(25).
  - 166. Li, G., Shrotriya, V., Yao, Y., and Yang, Y., Investigation of annealing effects and film thickness dependence of polymer solar cells based on poly(3-hexylthiophene). *J. Appl. Phys.*, 2005, 98(4).
  - 167. Bolleddula, D.A., *Droplet impact and spreading of viscous dispersions and volatile solvents*, in *Department of Mechanical Engineering*. 2011, University of Washington.
  - 168. Wengeler, L., Schmidt-Hansberg, B., Peters, K., Scharfer, P., and Schabel, W., Investigations on knife and slot die coating and processing of polymer nanoparticle films for hybrid polymer solar cells. *Chem. Eng. Process: Process Intensification*, 2011, 50(5–6): 478-482.
  - 169. Kim, Y., Shin, M., Kim, H., Ha, Y., and Ha, C.-S., Influence of electron-donating polymer addition on the performance of polymer solar cells. *Journal of Physics D: Applied Physics*, 2008, 41(22): 225101.
  - 170. Campoy-Quiles, M., Kanai, Y., El-Basaty, A., Sakai, H., and Murata, H., Ternary mixing: A simple method to tailor the morphology of organic solar cells. *Organic Electronics*, 2009, 10(6): 1120-1132.
  - 171. Ruderer, M.A., Hinterstocker, M., and Müller-Buschbaum, P., Structure in ternary blend systems for organic photovoltaics. *Synthetic Metals*, 2011, 161(17–18): 2001-2005.
  - 172. Valadares, M., Silvestre, I., Calado, H.D.R., Neves, B.R.A., Guimarães, P.S.S., and Cury, L.A., BEHP-PPV and P3HT blends for light emitting devices. *Mat. Sci. Eng. C*, 2009, 29(2): 571-574.
  - 173. Fink, J.K., High Performance Polymers. 2014: Elsevier Science.

174. Uemura, T., Yanai, N., Watanabe, S., Tanaka, H., Numaguchi, R., Miyahara, M.T., Ohta, Y., Nagaoka, M., and Kitagawa, S., Unveiling thermal transitions of polymers in subnanometre pores. *Nat Commun*, 2010, 1: 83.
175. Cheremisinoff, N.P. and Cheremisinoff, P.N., Elastomer Technology Handbook. 1993: Taylor & Francis.
176. Ngo, T.T., Nguyen, D.N., and Nguyen, V.T., Glass transition of PCBM, P3HT and their blends in quenched state. *Advances in Natural Sciences: Nanoscience and Nanotechnology*, 2012, 3(4): 045001.
177. Kim, Y., Choulis, S.A., Nelson, J., Bradley, D.D.C., Cook, S., and Durrant, J.R., Device annealing effect in organic solar cells with blends of regioregular poly(3-hexylthiophene) and soluble fullerene. *Applied Physics Letters*, 2005, 86(6): 063502-063502-3.
178. Rodrigues, A., Castro, M.C.R., Farinha, A.S.F., Oliveira, M., Tomé, J.P.C., Machado, A.V., Raposo, M.M.M., Hilliou, L., and Bernardo, G., Thermal stability of P3HT and P3HT:PCBM blends in the molten state. *Polymer Testing*, 2013, 32(7): 1192-1201.
179. Aiman Eid Al-Rawajfeh, Hasan A. Al-Salah, and Al-Rhael, I., Miscibility, Crystallinity and Morphology of Polymer Blends of Polyamide-6/ Poly (b-hydroxybutyrate) *Jordan Journal of Chemistry*, 2006, 1(2): 155-170.
180. Tuladhar, S.M., Sims, M., Choulis, S.A., Nielsen, C.B., George, W.N., Steinke, J.H.G., Bradley, D.D.C., and Nelson, J., Influence of side chain symmetry on the performance of poly(2,5-dialkoxy-p-phenylenevinylene): fullerene blend solar cells. *Organic Electronics*, 2009, 10(4): 562-567.
181. Cho, S.-M., Bae, J.-H., Jang, E., Kim, M.-H., Lee, C., and Lee, S.-D., Solvent effect of the fibrillar morphology on the power conversion efficiency of a polymer photovoltaic cell in a diffusive heterojunction. *Semicond. Sci. Tech.*, 2012, 27(12): 125018.
182. Cho, C.-K., Hwang, W.-J., Eun, K., Choa, S.-H., Na, S.-I., and Kim, H.-K., Mechanical flexibility of transparent PEDOT:PSS electrodes prepared by gravure printing for flexible organic solar cells. *Solar Energy Materials and Solar Cells*, 2011, 95(12): 3269-3275.
183. Ayzner, A.L., Wanger, D.D., Tassone, C.J., Tolbert, S.H., and Schwartz, B.J., Room to Improve Conjugated Polymer-Based Solar Cells: Understanding

- How Thermal Annealing Affects the Fullerene Component of a Bulk Heterojunction Photovoltaic Device. *The Journal of Physical Chemistry C*, 2008, 112(48): 18711-18716.
184. Omer, B.M., Optical Properties of Poly (3-hexylthiophene-2,5-diyl) and Poly (3-hexylthiophene-2,5-diyl) / [6,6]-Phenyl C<sub>61</sub>-butyric Acid 3-ethylthiophene Ester Thin Films. *J. of Nano and Elec. Phy.*, 2013, 5(3): 4.
185. Ayzner, A.L., Tassone, C.J., Tolbert, S.H., and Schwartz, B.J., Reappraising the Need for Bulk Heterojunctions in Polymer–Fullerene Photovoltaics: The Role of Carrier Transport in All-Solution-Processed P3HT/PCBM Bilayer Solar Cells. *The Journal of Physical Chemistry C*, 2009, 113(46): 20050-20060.
186. Noebels, M., Cross, R.E., Evans, D.A., and Finlayson, C.E., Characterization of spray-coating methods for conjugated polymer blend thin films. *J Mater. Sci.*, 2014, 49(12): 4279-4287.
187. Zapunidy, S.A., Martyanov, D.S., Nechvolodova, E.M., Tsikalova, M.V., Novikov, Y.N., and Paraschuk, D.Y., Approaches to low-bandgap polymer solar cells: Using polymer charge-transfer complexes and fullerene metallocomplexes. *Pure Appl. Chem.*, 2008, 80: 2151-2161.
188. Sauer, M., Hofkens, J., and Enderlein, J., *Basic Principles of Fluorescence Spectroscopy*, in *Handbook of Fluorescence Spectroscopy and Imaging*. 2011, Wiley-VCH Verlag GmbH & Co. KGaA. p. 1-30.
189. Albani, J.R., Structure and Dynamics of Macromolecules: Absorption and Fluorescence Studies: Absorption and Fluorescence Studies. 2011: Elsevier Science.
190. Street, R.A., Carrier mobility, structural order, and solar cell efficiency of organic heterojunction devices. *Appl. Phys. Lett.*, 2008, 93(13): 133308-3.
191. Matsumi, N., Naka, K., and Chujo, Y., Extension of  $\pi$ -Conjugation Length via the Vacant p-Orbital of the Boron Atom. Synthesis of Novel Electron Deficient  $\pi$ -Conjugated Systems by Hydroboration Polymerization and Their Blue Light Emission. *Journal of the American Chemical Society*, 1998, 120(20): 5112-5113.

192. O'Neill, L. and Byrne, H.J., Structure–Property Relationships for Electron–Vibrational Coupling in Conjugated Organic Oligomeric Systems. *The Journal of Physical Chemistry B*, 2005, 109(26): 12685-12690.
193. Khenner, M., Morphologies and kinetics of a dewetting ultrathin solid film. *Physical Review B*, 2008, 77(24).
194. Zhokhavets, U., Erb, T., Gobsch, G., Al-Ibrahim, M., and Ambacher, O., Relation between absorption and crystallinity of poly(3-hexylthiophene)/fullerene films for plastic solar cells. *Chemical Physics Letters*, 2006, 418(4–6): 347-350.
195. Dong, G., Susumu, I., and Koichiro, S., Effect of annealing on the mobility and morphology of thermally activated pentacene thin film transistors. *Journal of Applied Physics*, 2006, 99(094502): 1-7.
196. Oklobia, O. and Shafai, T.S., A quantitative study of the formation of PCBM clusters upon thermal annealing of P3HT/PCBM bulk heterojunction solar cell. *Solar Energy Materials and Solar Cells*, 2013, 117: 1-8.
197. Bagienski, W. and Gupta, M.C., Temperature dependence of polymer/fullerene organic solar cells. *Sol. Energ. Mat. Sol. C.*, 2011, 95(3): 933-941.
198. Yoshihito, H., Akinori, S., and Shu, S., Effects of Molecular Structure on Intramolecular Charge Carrier Transport in Dithieno [3,2-b: 2',3'-d] Pyrrole-Based Conjugated Copolymers. *Int. J. Spectroscopy*, 2012, 2012: 7.
199. Hoke, E.T., Vandewal, K., Bartelt, J.A., Mateker, W.R., Douglas, J.D., Noriega, R., Graham, K.R., Fréchet, J.M.J., Salleo, A., and McGehee, M.D., Recombination in Polymer:Fullerene Solar Cells with Open-Circuit Voltages Approaching and Exceeding 1.0 V. *Advanced Energy Materials*, 2013, 3(2): 220-230.
200. Zhao, Z., Rice, L., Efstathiadis, H., and Haldar, P., Annealing and thickness related performance and degradation of polymer solar cells. *Microelectronics Reliability*, 2013, 53(1): 123-128.
201. Khan, A., Jimenez, C., and Deschanvres, J.-l., Annealing effects on surface morphology, thickness and chemical phases of Sr-Cu-O thin film deposited by MOCVD. *J. Pak. Mater. Soc.* , 2010, 4(2): 63-70.

202. Wang, X., Rein, M., and Vlassak, J.J., Crystallization kinetics of amorphous equiatomic NiTi thin films: Effect of film thickness. *Journal of Applied Physics*, 2008, 103(2): 023501-6.
203. Aziz, F. and Ismail, A.F., Preparation and characterization of cross-linked Matrimid® membranes using para-phenylenediamine for O<sub>2</sub>/N<sub>2</sub> separation. *Separation and Purification Technology*, 2010, 73(3): 421-428.
204. Bushroa, A.R., Rahbari, R.G., Masjuki, H.H., and Muhamad, M.R., Approximation of crystallite size and microstrain via XRD line broadening analysis in TiSiN thin films. *Vacuum*, 2012, 86(8): 1107-1112.
205. Hayashi, Y., Sakuragi, H., Soga, T., Alexandrou, I., and Amaralunga, G.A.J., Bulk heterojunction solar cells based on two kinds of organic polymers and fullerene derivative. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 2008, 313–314: 422-425.
206. Huang, Y.-C., Chia, H.-C., Chuang, C.-M., Tsao, C.-S., Chen, C.-Y., and Su, W.-F., Facile hot solvent vapor annealing for high performance polymer solar cell using spray process. *Solar Energy Materials and Solar Cells*, 2013, 114: 24-30.
207. M. Islam, M. Islam, and, A.I., and Baerwolff, H., Influence of Thickness and Annealing Temperature on the Optical Properties of Spin-Coated Photoactive P3HT:PCBM Blend. *Optics and Photonics Journal*, 2013, 3: 28-32.
208. T. Sakurai, S. Toyoshima, M. Kubota, T. Yamanari, T. Taima, K. Saito, and Akimoto, K., *Structural study of P3HT and P3HT:PCBM thin films by synchrotron x-ray diffraction*, in *Photon Factory Activity Report*. 2008.
209. Yang, Q., Song, H., Gao, B., Wang, Y., Fu, Y., Yang, J., Xie, Z., and Wang, L., High open-circuit voltage polymer/polymer blend solar cells with a polyfluorene copolymer as the electron acceptor. *RSC Advances*, 2014, 4(24): 12579-12585.
210. Ohori, Y., Hoashi, T., Yanagi, Y., Okukawa, T., Fujii, S., Kataura, H., and Nishioka, Y., Organic Solar Cells Based on Ternary Blend Active Layer of Two Donors PTB7, P3HT and Acceptor PCBM. *Journal of Photopolymer Science and Technology*, 2014, 27(5): 569-575.
211. Yamanari, T., Ogo, H., Taima, T., Sakai, J., Tsukamoto, J., and Yoshida, Y. Photo-degradation and its recovery by thermal annealing in polymer-based

- organic solar cells. in *Photovoltaic Specialists Conference (PVSC), 2010 35th IEEE*. 2010.
- 212. Lattante, S., Electron and Hole Transport Layers: Their Use in Inverted Bulk Heterojunction Polymer Solar Cells. *Electronics*, 2014, 3(1): 132-164.
  - 213. Jørgensen, M., Carlé, J.E., Søndergaard, R.R., Lauritzen, M., Dagnæs-Hansen, N.A., Byskov, S.L., Andersen, T.R., Larsen-Olsen, T.T., Böttiger, A.P.L., Andreasen, B., Fu, L., Zuo, L., Liu, Y., Bundgaard, E., Zhan, X., Chen, H., and Krebs, F.C., The state of organic solar cells—A meta analysis. *Solar Energy Materials and Solar Cells*, 2013, 119: 84-93.
  - 214. Kim, Y., Choulis, S.A., Nelson, J., Bradley, D.D.C., Cook, S., and Durrant, J.R., Composition and annealing effects in polythiophene/fullerene solar cells. *Journal of Materials Science*, 2005, 40(6): 1371-1376.
  - 215. Liu, J., Shi, Y., and Yang, Y., Solvation-Induced Morphology Effects on the Performance of Polymer-Based Photovoltaic Devices. *Advanced Functional Materials*, 2001, 11(6): 420-424.
  - 216. Stubhan, T., Salinas, M., Ebel, A., Krebs, F.C., Hirsch, A., Halik, M., and Brabec, C.J., Increasing the Fill Factor of Inverted P3HT:PCBM Solar Cells Through Surface Modification of Al-Doped ZnO via Phosphonic Acid-Anchored C60 SAMs. *Advanced Energy Materials*, 2012, 2(5): 532-535.
  - 217. Yang, P.-C., Sun, J.-Y., Ma, S.-Y., Shen, Y.-M., Lin, Y.-H., Chen, C.-P., and Lin, C.-F., Interface modification of a highly air-stable polymer solar cell. *Solar Energy Materials and Solar Cells*, 2012, 98: 351-356.
  - 218. Stubhan, T., Ameri, T., Salinas, M., Krantz, J., Machui, F., Halik, M., and Brabec, C.J., High shunt resistance in polymer solar cells comprising a MoO<sub>3</sub> hole extraction layer processed from nanoparticle suspension. *Applied Physics Letters*, 2011, 98(25).
  - 219. Lafalce, E., Toglia, P., Lewis, J.E., and Jiang, X., Photo annealing effect on p-doped inverted organic solar cell. *Journal of Applied Physics*, 2014, 115(24): 244511.
  - 220. Chambon, S., Destouesse, E., Pavageau, B., Hirsch, L., and Wantz, G., Towards an understanding of light activation processes in titanium oxide based inverted organic solar cells. *Journal of Applied Physics*, 2012, 112(9): 094503.

221. Schmidt, H., Zilberberg, K., Schmale, S., Flügge, H., Riedl, T., and Kowalsky, W., Transient characteristics of inverted polymer solar cells using titaniumoxide interlayers. *Applied Physics Letters*, 2010, 96(24): 243-305.
222. Hau, S.K., Yip, H.-L., and Jen, A.K.Y., A Review on the Development of the Inverted Polymer Solar Cell Architecture. *Polymer Reviews*, 2010, 50(4): 474-510.
223. Kim, C.S., Lee, S.S., Gomez, E.D., Kim, J.B., and Loo, Y.-L., Transient photovoltaic behavior of air-stable, inverted organic solar cells with solution-processed electron transport layer. *Applied Physics Letters*, 2009, 94(11): 113302.