


## Daftar Isi

Pengantar Redaksi.....	ii
Chemical Composition of Ijuk ( <i>Arenga pinnata</i> ) Fiber as Reinforcement for Polymer Matrix Composites <i>Dandi Bachtiar, S.M. Sapuan, Megat Mohd. Hamdan Megat Ahmad and H.Y. Sastra</i> .....	1
Thermal Properties Of Polypropylene <i>Teuku Rihayat and Saari B. Mustapha</i> .....	8
Pemanfaatan Ekstrak Kasar Umbi Gadung Racun ( <i>Dioscorea Hispida</i> Dennst) Sebagai Bioinsektisida <i>Abubakar, Muhammad Zaki, Windu Purba Komara dan Ahmad Sanusi</i> .....	15
Gender and Quality Circle Effectiveness in Five Malaysian Organizations <i>T. R. Abo-Alhol, M. Y. Ismail, S. M. Sapuan, and M. M. Hamdan</i> .....	21
Oxidation of Real Biotreated Textile Wastewater Using Advanced Oxidation Process <i>Luqman Chuah Abdullah, Adel Al-Kdasi, Azni Idris and Katayon Saed</i> .....	29
Production of Free Fatty Acid by <i>Candida cylindracea</i> DSM 2031 on Two Different Carbon Sources in Batch Fermentation <i>Ishenny M. Noor and Syahiddin Dahlan Said</i> .....	40
Oxygen Mass Transfer Coefficient During Pellet-form Growth of Biocontrol Agent <i>Trichoderma Harzainum</i> <i>Syahiddin Dahlan Said and Ishenny M. Noor</i> .....	45
Rheological Investigation Of Stainless Steel Powder In Bimodal Particle Size Distribution <i>Khairur Rijal Jamaludin, Norhamidi Muhamad, Sri Yulis M. Amin, Mohd Nizam Ab. Rahman dan Murtadhahadi</i> .....	51



## Rheological Investigation Of Stainless Steel Powder In Bimodal Particle Size Distribution

Khairur Rijal Jamaludin<sup>a</sup>, Norhamidi Muhamad<sup>b</sup>, Sri Yulis M. Amin<sup>c</sup>, Mohd Nizam Ab. Rahman<sup>b</sup>, Murtadhahadi<sup>d</sup>

<sup>a</sup>Department of Mechanical Engineering, College of Science and Technology, University of Technology Malaysia, City Campus, 54100 Kuala Lumpur, Malaysia

<sup>b</sup>Precision Process Research Group, Dept. of Mechanical and Materials Engineering, Faculty of Engineering, National University of Malaysia, 43600 Bangi, Selangor Darul Ehsan, Malaysia

<sup>c</sup>Department of Mechanical and Manufacturing, University of Tun Hussein Onn Malaysia, 86400 Batu Pahat, Johor, Malaysia

<sup>d</sup>Jurusan Teknik Mesin, Politeknik Negeri Lhokseumawe, Aceh, Indonesia

### ABSTRACT

The rheological properties of the monomodal and bimodal MIM feedstock are presented. Stainless steel powder with particle size of 31 and 16  $\mu\text{m}$  were mixed with PMMA/PEG and stearic acid to form a homogenous paste, which called feedstocks. Bimodal powders were blend at 30 to 70 % of the coarse powder distribution. Monomodal feedstock exhibits higher viscosity over the bimodal feedstocks. Binder separation is likely to occur in the monomodal feedstocks prepared with coarse powder especially at high temperature. Furthermore, bimodal feedstocks were less viscous than the monomodal but the particle size distribution had shown its influence to viscosity. The flow behavior index were decreasing when the temperature were increases. The investigation also discovered that the feedstock flow sensitivity was depends on the fine powder distributions in the feedstocks. Since all feedstocks demonstrate good pseudo plastic behavior, the feedstocks were suitable to be injection molded.

**Keywords:** Particle size distribution, Rheology, MIM feedstocks, flow sensitivity, bimodal.

### INTRODUCTION

Metal injection molding (MIM) is a near-net shape processing technique that permits manufacturing of complex components. Fabrication starts by compounding a thermoplastic binder and powder metal mixture, referred as feedstock, followed by injection molding, binder removal and sintering [1].

This advanced manufacturing process is a modification of the common injection molding process for plastics where a significant volume fraction of plastic is replaced by a fine metal powders with a plastic binder to form a paste form feedstock, injection molding a "green" part using the specific feedstock on a conventional thermoplastic molding equipment. The major advantages from this manufacturing process include high product density, more intricate shape, higher mechanical properties, and better surface finish over traditional powder metallurgy products. Moreover, an inherent advantage of MIM is that the molding parts are hard enough to meet any needs for secondary machining [2].

The requirement for small particle dimensions has lead to some concerns regarding the potential cost of the process, making MIM a relatively expensive route for the production of larger

components. Therefore, a primary motivation for adding coarser particles to fine powders is the important cost decrease that may be achieved. However, there are some disadvantages of the method that may lead to the non-homogeneity in the sintered structure. Thus, avoidance of component defects requires a quantitative understanding of the effects of process parameters on the rheological behavior of MIM feedstocks. This is an important topic in MIM where the desire is to minimize the binder content and the sintering shrinkage using bimodal mixture [3]. Besides, broad particle size distributions or bimodal distributions are desirable to maximize the solid content, since the small particles fill interstitial space and release binder to lubricate particle flow [4]. In addition, mixtures of powders with differing sizes give improved packing densities over that available from either powder itself [3, 5, 6].

The rheological investigation described below employed bimodal powder blends with polymethyl methacrylate (PMMA), polyethylene glycol (PEG) and stearic acid as a binder system. Capillary rheometry was employed to analyze the flow behavior of the feedstocks. The information obtained from the experiment provides measurement of feedstock viscosity at variable shear rate to evaluate the feedstock stability and prediction of separation phenomena, analysis of the viscosity and shear rate to obtain the flow behavior index, activation energy and general rheological index that indicate the stability of the feedstocks as well as its suitability to the process. The bimodal particle feedstocks rheology parameters are compared with the monomodal to show the significant to the injection parameters.

## METHODOLOGY

In this work, commercial gas atomized stainless steel powder 316L with particle sizes of 31  $\mu\text{m}$  and 16  $\mu\text{m}$  were mixed with PMMA, PEG and stearic acid. The rheological characteristic of the feedstocks were investigated using Shimadzu 500-D capillary rheometer.

Prior investigation, stainless steel powder were mixed with binders in the Sigma type blade mixer in 95 minutes at 70 °C. Four compositions of feedstocks consisting of different particles distribution were prepared for the investigation as shown in Table 1.

Table 1 Feedstock classification and the powder loading remains at 64 % V

Feedstock Abbreviation	Description
31_64	Monomodal: 31 $\mu\text{m}$
16_64	Monomodal: 16 $\mu\text{m}$
A1_64	Bimodal: 16:31 $\mu\text{m}$ at 70%:30%
B1_64	Bimodal: 16:31 $\mu\text{m}$ at 30%:70%

## RESULTS AND DISCUSSION

### *Viscosity dependence to shear rate*

Figures 1, 2 and 3 show the correlation of viscosity and shear rate at injection temperatures of 120 °C, 130 °C, and 140 °C. These temperatures were selected based on literature [7], which studies the injection parameters of the MIM feedstock prepared with the same materials as presented by this paper.






Figure 1 Correlation of viscosity and shear rate at 120 °C

The bimodal feedstock, A1\_64 as shown in Figure 1 exhibits highest viscosity while B1\_64 is the lowest at this injection temperature. Powder-binder separations occur at high shear rate on the monomodal feedstocks, 31\_64 and B1\_64. However, when the temperature was increased to 130 °C (Figure 2) the viscosity of A1\_64 is reducing.




Figure 2 Correlation of viscosity and shear rate at 130 °C

When the injection temperature was increased to 130°C, the bimodal feedstock, B1\_64 exhibits higher viscosity at shear rate less than 2000 s<sup>-1</sup> compared to the monomodal feedstocks. However, at shear rate lower than 8000 s<sup>-1</sup>, A1\_64 is more viscous compared to the B1\_64. However, the viscosity is almost the same at high shear rate.




Figure 3 Correlation of viscosity and shear rate at 140 °C

Moreover, when the temperature was increased to the maximum (Figure 3), the monomodal feedstock, 31\_64 became more viscous than 16\_64. This is possibly due to binder separation of the coarse powder. At the mean time, the bimodal feedstock A1\_64 is more viscous than B1\_64. However, the bimodal feedstocks were still dominant in term of viscosity compared to the monomodal feedstocks in every injection temperatures. The bimodal particles distribution does affect the feedstock viscosity where as seen in Figures 1, 2 and 3 that the viscosity of A1\_64 and B1\_64 is among the lowest.

Conversely, literature [8] discovered in their investigation using carbonyl iron powder that particle distribution does not affect viscosity for powder fraction of 60 % volume as the monomodal and bimodal distributions present the same viscosity as the shear rate was varied. As the powder fraction was increased from 60 % volume to 65 % volume in a bimodal distribution, the viscosity was less affected than when the powder fraction was increased from 55 % volume to 60 % volume in a monomodal distribution. Finally, literature [8] concluded that the bimodal distribution for carbonyl iron powder seems to be recommended only for very high powder loading.

Particle size ratio in the bimodal powder distribution system has its significant. A large particle size ratio can also provide higher packing density, better stability in debinding, good moldability, and lower shrinkage in sintering. However, there are a number of problems associated with such blends and these include larger clearances needed between screw and barrel in the molding machine, and the potential for non-homogeneity in the sintered structure, which can adversely affect the part's physical and mechanical properties [9].

Figures 1, 2 and 3 also indicate that the coarse powder (31\_64) exhibits lower viscosity than the fine powder (16\_64). This is due to the coarse particles in a system diffuse to a lesser extend than the fine powder and less energy is dissipated in flow. Therefore, the relative viscosity decreases with the increase of the particle size. Consequently, by adding coarse powder to the fine powder, feedstock with lower relative viscosity at the same solid loading content can be obtained [9].

Binder separation phenomena are likely to occur in the 31\_64 at all temperatures. Nevertheless, Figures 1, 2 and 3 does not indicate any occurrence of binder separation phenomenon in 16\_64. Modelling the binder separation phenomenon as flow through porous medium enables identification of the parameters influencing the separation that occurred during the tests. The following equations (Kozeny-Carman and the Blake Kozeny equation respectively) describe the permeability constant of a porous medium,  $k$

$$k = \frac{\varphi^3}{5S^2(1-\varphi)^2} \tag{1a}$$

$$k = \frac{D^2\varphi^3}{150(1-\varphi)^2} \tag{1b}$$

where  $\varphi$  is medium porosity; S is specific pore surface (pore surface exposed to the fluid per unit volume of porous material); D is particle diameter.

These two relations show that the permeability constant is low when the particle size is small and the pore surface area is large. The binder separation is less likely to occur when the flow through the porous medium is low, which is equivalent to a lower permeability value. Therefore, the tendency for binder separation would be less if fine powder and irregular shape were used.

### Temperature Influence

Figures 4 and 5 show the feedstock viscosity dependence to the temperature. The error bars indicates the maximum and minimum viscosities. As shown in Figure 4, A1\_64 has broad viscosity range at temperature 120 and 125 °C, when it was extruded at 29 bars from the rheology test barrel. Besides, in Figure 5, B1\_64 also shows wide viscosity range at 130 °C when pressures at 29 and 59 bars were applied.




Figure 4 Temperature influence to the viscosity for A1\_64




Figure 5 Temperature influence to the viscosity for B1\_64



In Figure 4, the viscosity was decreased when the extrusion pressure and the test temperature was increased. Regardless, in Figure 5 the viscosity was fluctuates with the increasing of temperatures. This is possibly due to the occurrence of binder separation as the feedstock in Figure 5 has broader coarse powder distribution compared to A1\_64.

#### Feedstock Pseudo Plasticity

A regression line of the scatter plot shown in Figures 1, 2 and 3 could be rewritten as

$$\eta = K \dot{\gamma}^{n-1} \quad (2)$$

where  $\eta$  is the viscosity at shear rate  $\dot{\gamma}$ ,  $K$  is a constant and,  $n$  is a flow behavior index. Equation (2) has been widely used to correlate the data of viscosity to shear rate for pseudo plastic and dilatant fluids, which is known as the power-law equation.

The flow behavior index,  $n$  of the power-law index indicates the shear sensitivity. Smaller  $n$  of feedstock indicates higher shear sensitivity and more pseudo plasticity of the feedstocks. Some molding defects such as jetting are associated with small  $n$ , i.e., higher shear sensitivity [10]. During the injection molding process, pseudo plastic behavior is desirable and, therefore, a decrease in viscosity with an increase in the shear rate. This dependent behavior of the viscosity against the shear rate is especially important when producing complex and delicate parts, which are important products in the MIM industry [11]. In Table 2, a comparison of the feedstocks is shown.

Generally, the feedstocks in Table 2 demonstrate pseudo plasticity as the index was smaller than one, thus it indicates shear thinning occur in the feedstock when applied to a shear stress. The flow behavior index of 16\_64 was smaller than 31\_64. This indicates that 16\_64 the more quickly the viscosity of the feedstock changes with the shear rate. The coarse powder was likelihood to become dilatant at low temperature, as a flow behavior index for 31\_64 seems inversely proportional to the temperature and is expected the value become higher than unity.

Table 2. Comparison of the Feedstocks

Feedstock	Temp	n	E	Viscosity	$\alpha_{STV}$
31_64	120	0.98	49.33	137.06	24.60
	130	0.95	49.33	71.62	117.68
	140	0.81	49.33	64.67	487.40
16_64	120	0.49	79.54	141.77	376.03
	130	0.23	79.54	94.44	852.24
	140	-0.22	79.54	35.76	3571.93
A1_64	120	-1.12	24.43	2544.20	284.15
	130	-1.00	24.43	2924.30	233.23
	140	-0.16	24.43	323.89	1222.24
B1_64	120	-0.95	36.54	2850.56	155.66
	130	0.41	36.54	177.69	755.55
	140	-1.06	36.54	2735.65	171.35

Furthermore, B1\_64 exhibit high sensitivity than A1\_64. However, the sensitivity of B1\_64 was reducing with the increase of temperature. The sensitivity of A1\_64 was high due to the high fine powder composition in the bimodal system compared to B1\_64. The B1\_64 shows inconsistency of the flow behavior index when temperature was increasing.

In addition, the controllability of viscosity within an injection molding barrel by controlling the temperature of barrel, nozzle and mold, the temperature dependence of viscosity may have an effect on the response of the material to the sudden non-uniform cooling within cavity. For example,

during the molding stage, the feedstock was forced into the mold where it immediately began to cool. If the cooling was accompanied by a rapid increase in the viscosity, the result may be incomplete filling the mold and introduced cracking or porosity in molded parts. Therefore, low temperature dependence was desired to minimize problems arising from fluctuating molding temperatures, thereby minimizing stress concentration, cracks and shape distortion [4, 12]. The value of flow activation energy, E as shown in Table 2 represent the influence of temperature on the viscosity of the feedstocks, is an important parameter for injection molding

$$\eta = \eta_0 \exp\left(\frac{E}{RT}\right) \quad (3)$$

where R is the gas constant, T the temperature and  $\eta_0$  the reference viscosity.

Taking nature logarithm at both sides, equation (4) was obtained

$$\ln \eta = \ln \eta_0 + \left(\frac{E}{R}\right) \frac{1}{T} \quad (4)$$

With a shear rate of  $1000 \text{ s}^{-1}$ , which fell in the normal range of shear rates for injection molding of MIM feedstocks, by plotting  $\ln \eta$  against the reciprocal temperature, the activation energies of viscous flow could be calculated and given in Table 2. The activation energies and the viscosities at shear rate  $1000 \text{ s}^{-1}$  in Table 2 could cast some lights on the nature of the feedstocks.

The monomodal feedstock, 16\_64 has low activation energy than 31\_64 while the activation energy of the bimodal feedstock, A1\_64 was lower than the B1\_64. Nevertheless, the bimodal feedstocks has low activation energies compared to the monomodal feedstocks thus, it indicates the bimodal feedstock was less sensitive to any temperature fluctuation during the injection molding process. This feedstock could thus be injection molded in a relatively wide temperature range. High activation energy of feedstock 31\_64 indicates a drastic viscosity increase upon cooling, and thus feedstock 31\_64 required a more accurate temperature control during injection molding. Otherwise, mold temperature distribution will cause non-uniform flow, which induced internal stresses.

In order to establish a general molding index, the model Weir proposed for polymers has been used including the main parameters as regards flow [11].

$$\alpha_{STV} = \frac{1}{\eta_0} \frac{\left| \frac{\partial \log \eta}{\partial \log \gamma} \right|}{\eta_0 \frac{\partial \log \eta}{\partial 1/T}} \quad (5)$$

where,  $\eta$ , is the viscosity  $\eta_0$  is a reference viscosity T is the temperature  $\gamma$  is the shear rate and  $\alpha_{STV}$  is the rheological index or moldability index [13]. Simplifying the equation:

$$\alpha_{STV} = \frac{1}{\eta_0} \frac{|n-1|}{E/R} \quad (6)$$

The higher the value of  $\alpha_{STV}$ , the better the rheological properties. In Table 2, 16\_64 has better rheological properties at  $140 \text{ }^\circ\text{C}$  while 31\_64 has poor rheological property at  $120 \text{ }^\circ\text{C}$ . In general, the rheological properties are proportional to the temperatures.



## CONCLUSIONS

The rheological behavior of monomodal and bimodal stainless steel MIM feedstock has been investigated in terms of injection temperature (120-140 °C) and particle size distributions, over wide range of shear rate.

All feedstocks are possible to be injection molded as the flow behavior index indicates pseudo plastic behavior. The bimodal particles distribution enables to increase the shear rate and thus reduce the feedstock viscosity. B1\_64 is less viscous compared to the A1\_64. In addition, the B1\_64 particles distribution was organized according to the Furnas model, which describes the ideal particle packing behavior of a binary powder system [13].

Furnas model suggested that the volume of fine particles is between 30 to 50 %. The bimodal feedstock also exhibit better pseudo plasticity compared to the monomodal feedstock. Further, the sensitivity of the viscosity to the temperature is also small thus; the bimodal feedstock is stable over wide range of temperature.

## REFERENCES

- [1]. Suri, P., Atre, S.V., German, R.M., Souza, J.P., "Effect of mixing on the rheology and particle characteristics of tungsten-based powder injection molding feedstock", *Materials Science and Engineering*, Vol A356, pp 337-344, 2003.
- [2]. Huang, B., Liang, S., Qu, X., "The rheology of metal injection molding", *Journal of Materials Processing Technology*, Vol. 137, pp 132-137, 2003.
- [3]. German, R.M., and Bulger, M., "A model for Densification by Sintering of Bimodal Particle Size Distributions", *International Journal of Powder Metallurgy*, Vol. 28, Num. 3, pp 301-311, 1992.
- [4]. German, R.M., and Bose, A., *Injection Molding of Metal and Ceramic*, Metal Powder Industries Federation, Princeton, N.J, 1997
- [5]. German, R.M., and Bulger, M., "The effects of bimodal particle size distribution on sintering of powder injection molded compacts", *Solid State Phenomena*, Vol. 25 & 26, pp 55-62, 1992.
- [6]. German, R.M., "Prediction of sintered density for bimodal powder mixtures", *Metallurgical Transactions A*, Vol. 23A, pp 1455-1465, 1992.
- [7]. Mohd Afian Omar, "Injection Molding of 316L Stainless steel and NiCrSiB alloy powder using a PEG/PMMA binder", PhD Thesis, University of Sheffield, U.K, 1999.
- [8]. Resende, L. M., Klein, A. N., and Prata, A. T., "Rheological properties of granulometric mixtures for Powder Injection Molding", *Key Engineering Materials*, Vol. 189-191, pp 598-603, 2001.
- [9]. Dihoru, L. V., Smith, L. N., and German, R. M., "Experimental analysis and neural network modeling of the rheological behavior of powder injection molding feedstocks formed with bimodal powder mixtures", *Powder Metallurgy*, Vol. 43, Num 1, pp 31-36, 2000.
- [10]. Yang, W. W., Yang, K. Y., and Hon, M. H., "Effects of PEG molecular weights on rheological behavior of alumina injection molding feedstocks", *Materials Chemistry and Physics*, Vol. 78, pp 416-424, 2002.
- [11]. Agote, I., Odriozola, A., Gutierrez, M., Santamaria, A., Quintanilla, J., Coupelle, P., and Soares, J., "Rheological study of waste porcelain feedstocks for injection moulding", *Journal of the European Ceramic Society*, Vol 21, pp 2843-2853, 2001.
- [12]. Hausnerova, B., Sedlacek, T., Slezak, R., and Saha, P., "Pressure-dependent viscosity of powder injection moulding compounds", *Rheological Acta*, Vol 45, pp 290-296, 2006.

- [13]. Yimin, L., H. Baiyun, and Q. Xuanhui. 1999. Improvement of rheological and shape retention properties of wax-based MIM binder by multi-polymer components. *Transactions of Nonferrous Metals Society of China*. 9(1):22-29.
- [14]. Zheng, J., Carlson, W. B., and Reed, J. S., "The packing density of binary powder mixtures", *Journal of the European Ceramic Society*, Vol 15, pp 479-483, 1995.

### Petunjuk dan Tata Cara Penulisan Naskah

Naskah dikirim dalam bentuk tercetak lengkap dan disertai dengan sebuah disket 3.5" HD atau CD. Pengiriman naskah ditujukan ke alamat redaksi. Naskah yang diterima merupakan hasil penelitian atau review artikel, yang belum pernah dipublikasikan dalam jurnal ilmiah lain.

Naskah dapat ditulis dalam bahasa Indonesia atau bahasa Inggris yang tepat dan

terdiri dari Judul, Nama Penulis lengkap tanpa gelar, instansi, e-mail jika ada, Kata Kunci, Pendahuluan, Bahan dan Metode, Hasil dan Pembahasan, Kesimpulan, Ucapan Terima Kasih (bila ada), Notaasi (bila ada matematika), dan Daftar Pustaka.

Naskah diketik dengan Microsoft Word pada kertas A4 (210mm x 297 mm) dalam format tunggal dengan 1 spasi dengan huruf Times New Roman 12 pitch dan satu kolom. Margin kiri 3 cm, margin kanan 2,5 cm, margin atas 3 cm, dan margin bawah 2,5 cm. Setiap halaman diberi nomor. Persamaan matematika diberikan

di awal kalimat. Kata 16 kata, ditulis dengan huruf Times New Roman bold 16 pitch. Jumlah kata minimal 5 halaman dan maksimal 8 halaman.

Jumlah kata tidak melebihi dari 250 kata dan tidak kurang dari 150 kata. Untuk persamaan matematika maksimal 7 buah.

Diagram dan Tabel harus diberi nomor dan keterangan secara berurutan. Gambar dan Tabel gunakan warna hitam untuk semua penulisan Naskah.

Daftar pustaka berdasarkan daftar pustaka nama penulis pertama dan tahun terbit. Contoh: Asnawi dkk., 2000). Penulisan daftar pustaka harus sesuai dengan nama penulis, Judul harus lengkap. Daftar pustaka disusun ke belakang berdasarkan tahun terbit nama penulis pertama.

Redaksi berhak memperbaiki naskah setelah diperiksa Tim Editor atau menolak naskah yang dianggap tidak mengikuti format maupun kelayakan isinya. Sekiranya naskah yang diterima mengalami kesalahan kecil dalam penulisan tanpa pemberitahuan sebelumnya akan dipertahankan.

#### Alamat Redaksi

Jurnal Teknologi Terpakai (Jurnal Teknologi Terpakai) Jurusan Teknik Kimia, Fakultas Teknik UNSYIAH  
Jl. Gayams Abjurnat No. 7, Dureunan, Banda Aceh 23111, Indonesia.  
Telp. +62-651-81977 ext. 4343, Fax: +62-651-52995,  
e-mail: jtt@unsyah.ac.id atau teknologika\_terpakai@yahoo.com