

**SYNTHESIS AND CHARACTERIZATION OF SAGO/POLYVINYL
ALCOHOL BLEND PERVAPORATION MEMBRANE FOR
ETHYL ACETATE RECOVERY**

ABDULHAKIM M. SALEM E-ALAMARIA

UNIVERSITI TEKNOLOGI MALAYSIA

SYNTHESIS AND CHARACTERIZATION OF SAGO / POLYVINYL
ALCOHOL BLEND PERVAPORATION MEMBRANE FOR
ETHYL ACETATE RECOVERY

ABDULHAKIM M. SALEM E-ALAMARIA

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy (Chemical Engineering)

Faculty of Chemical & Energy Engineering
Universiti Teknologi Malaysia

MARCH 2016

TO MY FATHER

ACKNOWLEDGEMENT

First of all, I am grateful to The Almighty ALLAH for allowing me to complete this thesis.

I would like to express my special appreciation and thanks to my advisor Professor Dr. Mohd Ghazali Mohd Nawawi, you have been a tremendous mentor to me. I would like to thank you for encouraging my research and for allowing me to grow as a research scientist. Your advice on both research as well as on my career have been priceless.

I take this opportunity to record our sincere thanks to all the faculty members and administrative staff of the Faculty of Chemical Engineering those whom are in charge of the postgraduate office for their help and encouragement.

To all my friends and coworkers I met while studying at the Universiti Teknologi Malaysia, thank you for your friendship and support, special thank to my lab mate Zafifah Zamrud for her help.

A special thanks to my family. Words cannot express how grateful I am to my mother and father for all of the sacrifices that you have made on my behalf. Your prayers for me sustained me thus far.

I would also like to thank all of my brothers and sisters who supported me in writing and incentivized me to strive towards my goal.

ABSTRACT

Pervaporation is a membrane separation technology with high selectivity, efficiency and energy saving benefits that make it the method of choice for separation of mixtures. The application for pervaporation includes removal of dilute organic compounds from aqueous solution and dehydration of organics such as dehydration of ethyl acetate-water mixture. The best successful application that has been used for pervaporation is dehydration of organic liquid from water using hydrophilic polymer membrane. In this work, material used for membrane separation was sago and polyvinyl alcohol. However, during the separation process, excessive affinity of water towards hydrophilic polymer membrane led to an increase in the swelling of the membrane. To control the degree of swelling the membranes were cross-linked to improve the intrinsic properties of hydrophilic polymer membranes. Sago starch was used as based polymer to prepare membranes with polyvinyl alcohol (PVA) with various morphologies such as homogenous, composite and blended ration of sago and PVA. Sago/PVA membranes were cross-linked using three different approaches: firstly, using glutaraldehyde, secondly using thermal treatment (80 °C) and thirdly by using both glutaraldehyde and thermal treatment. The effects of various cross-linking methods on the intrinsic properties of hydrophilic polymer membrane were investigated. Before applying the cross-linking to sago/PVA membranes for separation of ethyl acetate-water mixture, a physicochemical characterization was carried out using Fourier transform infrared spectroscopy, differential scanning calorimeter (DSC), thermogravimetric analysis (TGA), atomic force microscopy and swelling experiments. The investigation on the effect of cross-linking on the sago/PVA membranes showed an increase in surface hydrophobicity from contact angle measurements. DSC measurements showed an increase in melting temperature of the polymer membranes after cross-linking. In addition, TGA showed an increase in the stability of the polymer membranes after cross-linking. The effects of operating condition such as feed temperature and feed concentration on the permeation flux and separation factor were also investigated. For the pervaporation of ethyl acetate-water mixture, a decrease in flux and an increase in the separation factor were observed with chemical and combination of chemical and thermal cross-linking. Finally, central composite designs (CCD) of response surface methodology was applied to analyse pervaporation performance of thermal cross-linked membrane. Regression models were developed for permeation flux and separation factor as a function of feed temperature, feed concentration and permeate pressure.

ABSTRAK

Penelapesejatan adalah teknologi pemisahan membran dengan pemilihan yang tinggi, kecekapan dan tenaga manfaat penjimatan tenaga yang menjadikannya kaedah pilihan untuk pemisahan campuran. Aplikasi penelapesejatan termasuk penyingkiran sebatian organik cair daripada larutan akueus dan dehidrasi bahan organik seperti dehidrasi campuran etil asetat-air. Aplikasi terbaik yang digunakan untuk penelapesejatan adalah dehidrasi cecair organik dehidrasi daripada air menggunakan membran polimer hidrofilik. Dalam kajian ini, bahan yang digunakan sebagai pemisahan membran adalah sagu dan polivinil alkohol. Walau bagaimanapun, semasa proses pemisahan, afiniti lebih air ke arah membran polimer hidrofilik membawa kepada peningkatan dalam pembengkakan membran. Untuk mengawal tahap pembengkakan, membran dirangkai silang untuk meningkatkan sifat-sifat intrinsik membran polimer hidrofilik. Kanji sagu telah digunakan sebagai polimer asas bersama polivinil alkohol untuk menyediakan membran dengan pelbagai morfologi seperti homogen, komposit dan campuran nisbah sagu dan PVA. Membran sagu/PVA dirangkaisilang dengan menggunakan tiga pendekatan yang berbeza: pertama, menggunakan glutaraldehid, kedua menggunakan rawatan haba (80 °C) dan ketiga dengan menggunakan kedua-dua glutaraldehid dan rawatan haba. Kesan pelbagai kaedah silang kepada sifat-sifat intrinsik membran polimer hidrofilik telah disiasat. Sebelum aplikasi rangkai silang membran sagu/ PVA untuk pemisahan campuran etil asetat-air, pencirian fizikokimia telah dijalankan menggunakan spektroskopi inframerah transformasi Fourier, kalorimeter pengimbangan pembezaan (DSC), analisis termo-gravimetrik (TGA), mikroskopi daya atom dan eksperimen pembengkakan. Penyiasatan ke atas kesan rangkai silang membran sagu/ PVA menunjukkan peningkatan dalam permukaan hidrofobisiti daripada ukuran sudut bersentuhan. Pengukuran DSC menunjukkan peningkatan dalam suhu lebur membran polimer selepas rangkai silang. Di samping itu, TGA menunjukkan peningkatan dalam kestabilan membran polimer selepas dirangkai silang. Kesan daripada keadaan operasi seperti suhu makanan dan kepekatan suapan kepada faktor fluks penyerapan dan pemisahan juga telah disiasat. Untuk penelapesejatan campuran etil asetat air, penurunan fluks dan peningkatan dalam faktor pemisahan telah diperhatikan dengan bahan kimia dan gabungan kimia dan haba rangkai silang. Akhir sekali, kaedah gerak balas permukaan yang telah melalui reka bentuk komposit pusat (CCD) digunakan untuk menganalisis prestasi penelapesejatan membran yang dirangkai silang dengan haba. Model-model regresi telah dibangunkan untuk fluks penyerapan dan faktor pemisahan sebagai fungsi suhu suapan, kepekatan suapan dan resapan tekanan.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xiv
	LIST OF FIGURES	xvi
	LIST OF ABBREVIATIONS	xxiv
	LIST OF SYMBOLS	xxv
	LIST OF APPENDICES	xxvi
1	INTRODUCTION	1
	1.1 Research Background	1
	1.2 Problem Statement	6
	1.3 Objectives	7
	1.4 Scope of the Thesis	8
2	LITERATURE REVIEW	10
	2.1 Sago	10
	2.2 Sago Starch Copolymer	12
	2.3 Modification of Sago Starch by Acid Treatment in Alcohol	13

2.4	Applications of Sago Starch	14
2.4.1	Applications of Plasticized Sago Starch-Based Bio-Composites	15
2.4.1.1	Biodegradable Film	15
2.4.1.2	Bioplastics	16
2.4.1.3	Biopackaging	16
2.5	Membrane Technology	17
2.5.1	Historical Development of Membranes and Membrane Processes	18
2.5.2	Membrane Process	19
2.5.3	Membrane Materials	20
2.5.3.1	Types of Membrane	22
2.5.3.2	Sago and Polyvinyl Alcohol as Membrane Material	23
2.5.4	Membrane Fabrication	26
2.5.5	Definition of a Membrane	27
2.5.6	Membrane Modification	28
2.5.6.1	Crosslinking	28
2.5.6.2	Grafting	29
2.5.6.3	Blending	29
2.5.6.4	Copolymerization	29
2.5.7	Membrane Morphology	30
2.6	Pervaporation	32
2.6.1	Introduction to Pervaporation	32
2.6.2	Pervaporation Principles	34
2.6.3	Definition of Pervaporation Process	37
2.6.4	Specifications of Pervaporation Membranes	39
2.6.4.1	Membrane Selectivity	39
2.6.4.2	Permeate Flux	39
2.7	Ethyl Acetate	40
2.7.1	Recent Knowledge of Separation of Ethyl Acetate	41

2.8	Mass Transfer through a Pervaporation Membrane	42
2.8.1	Pore Flow Model	44
2.8.2	Solution-Diffusion Model	46
2.9	Separation Characterization Parameters	48
2.9.1	Effect of Process Condition	50
2.9.1.1	Feed Concentration	50
2.9.1.2	Effect of Feed Temperature	51
2.9.1.3	Effect of Feed Flow Rate	52
2.9.1.4	Feed Pressures	54
2.9.1.5	Permeate Pressure	55
3	MATERIALS AND METHOD	56
3.1	Materials	56
3.2	Preparing of Membranes	57
3.2.1	Preparation of Homogenous Sago/PVA Membranes	57
3.2.2	Preparation of Sago/PVA Blend Composite Membranes	59
3.2.3	Preparation of Blended Ratio Membrane	62
3.3	Membrane Characterization	64
3.3.1	FTIR Spectroscopy	64
3.3.2	Differential Scanning Calorimetry (DSC)	64
3.3.3	Thermo Gravimetric Analysis (TGA)	65
3.3.4	Scanning Electron Microscopy (SEM)	65
3.3.5	Atomic Force Microscopy (AFM)	65
3.3.6	Contact Angle Measurements	66
3.3.7	Degree of Swelling Measurements (DS) Experiments	66
3.3.8	Liquid Sorption Experiments	67
3.4	Pervaporation	68

4	DEVELOPMENT AND CROSSLINKING OF HOMOGENOUS SAGO/PVA BLENDED MEMBRANE FOR PERVAPORATION OF ETHYL ACETATE-WATER MIXTURES	70
4.1	Introduction	70
4.2	Result and Discussions	72
4.2.1	Membrane Characterizations	72
4.2.1.1	Liquid Sorption Characterization	72
4.2.1.2	Thermal Stability TGA	80
4.2.1.3	Fourier Transform Infrared (FTIR)	83
4.2.1.4	Differential Scanning Calorimeter (DSC)	84
4.2.1.5	Scanning Electron Microscopy (SEM)	84
4.2.2	Separation Behavior	86
4.2.2.1	Pervaporation	86
4.2.2.2	Cross-Linking Reaction	91
4.2.3	Effect of Feed Temperature	93
4.2.4	Effect of Feed Concentration	95
4.3	Pervaporation Dehydration Performance of Ethyl Acetate-Water Mixture Using Other Reported Membranes	97
4.4	Conclusion	99
5	CORRELATION OF PHYSICOCHEMICAL CHARACTERISTICS WITH PERVAPORATION PERFORMANCE OF SAGO/PVA COMPOSITE MEMBRANES	100
5.1	Introduction	100
5.2	Results and Discussions	104

5.2.1	Morphology of Composite Sago/PVA Membrane	104
5.2.2	Differential Scanning Calorimeter (DSC)	112
5.2.3	Atomic Force Microscopy Analysis of Membranes	113
5.2.4	Contact Angle Measurements: Surface Hydrophobicity	115
5.2.5	Fourier Transform Infrared (FTIR) Spectroscopy	116
5.2.6	Thermo Gravimetric Analysis (TGA)	117
5.3	Separation Behavior	119
5.3.1	Pervaporation	119
5.3.2	Non-cross-linked Composite sago/PVA Membrane vs. non-cross-linked Homogenous Membrane	121
5.3.3	Effect of Cross-Linking Reaction	124
5.3.4	Effect of Feed Concentration	127
5.3.5	Effect of Feed Temperature	129
5.4	Comparison of the Results with Other Work Using Different Material for Composite Membranes	131
5.5	Conclusions	132
6	EFFECT OF SAGO BLENDED RATION ON THE PERVAPORATION OF ETHYL ACETATE-WATER MIXTURE	134
6.1	Introduction	134
6.2	Results and Discussion	138
6.2.1	Fourier Transform Infrared (FTIR) Spectroscopy	138
6.2.2	Degree of swelling measurements (DS)	139
6.2.3	Contact Angle Measurements	141
6.2.4	Thermo gravimetric (TGA) Analysis	142

6.3	Pervaporation	143
6.3.1	Effect of Feed Temperature	149
6.3.2	Pervaporation Separation Index (PSI)	157
6.3.3	Effect of Sago Content on the Permeation Flux	159
6.3.4	The Effect of Permeate Pressure	160
6.4	Conclusions	163
7	PERVAPORATION SEPARATION OF ETHYL ACETATE-WATER MIXTURE: OPTIMIZATION OF OPERATING CONDITIONS FOR PERMEATION FLUX AND SEPARATION FACTOR USING CENTRAL COMPOSITE ROTATABLE DESIGN	164
7.1	Introduction	164
7.2	Theory	167
7.3	Experimental Procedure	168
7.3.1	Materials	168
7.3.2	Membrane Preparation	169
7.4	Experimental Setup and Analysis	169
7.5	Experimental Design	170
7.6	Results and Discussions	171
7.6.1	Statistical Model Analysis	171
7.6.2	Effect of Operating Variables on Permeation Flux	176
7.6.3	Effect of Operating Variables on Separation Factor	180
7.6.4	Optimal Condition and Verification of the Model	183
7.7	Conclusion	183
8	CONCLUSION AND RECOMMENDATIONS	184
8.1	Conclusions	184

8.2	Recommendations for Future Study	186
	REFERENCES	188
	Appendix A-C	208-232

LIST OF TABLES

TABLE NO	TITLE	PAGE
1.1	Membrane process (2001 ,Purchas and Sutherland)	5
2.1	(1997,Nawawi)Characteristics of membrane	19
2.2	Present the development of Pervaporation membrane materials	21
2.3	Presents the typical used of pervaporation membrane materials	22
2.4	Overview of chosen membrane separation processes	38
2.5	Physical properties of ethyl acetate	41
2.6	Use of ethyl acetate applications	42
2.7	Pervaporation dehydration performance of various Jiratanano) membranes <i>et al.</i> , 2002)	54
4.1	Effect of feed concentration on the separation factor	97
4.2	Comparison between different materials on the separation of ethyl acetate/water mixture	98
5.2	Result of the sago/PVA composite membranes from AFM experiment	114
5.3	Contact angle measurements results	116
5.4	Separation of non-cross-linked and cross-linked membranes at different feed temperature	131
5.5	Comparison and summary of separation alcohol-water using composite membrane	131
6.1	Contact angle of Sago/PVA membranes	142

7.1	Experimental independent variables	170
7.2	Experiment runs and response of pervaporation of ethyl acetate water mixture	171
7.3	Estimated coefficients of the regression model of flux and separation factor	172
7.1	Analysis of variance (ANOVA) FOR 2^3 full center composite design (CCD) for permeation flux of sago/PVA membrane	177
7.5	Analysis of variance (ANOVA) FOR 2^3 full center composite design (CCD) for separation factor of sago/PVA membrane	180

LIST OF FIGURES

FIGURE NO	TITLE	PAGE
2.1	Schematic drawing illustrating the various materials and structures of technically relevant synthetic membranes (Mashhadi, 2001)	23
2.2	Molecular structure of starch	24
2.3	Structure of polyvinyl alcohol	25
2.4	Schematic representation of a two-phase system separated by membrane (Abd-Aziz, 2002)	27
2.5	Configuration, morphology, transport, perm selectivity, and driving forces employed in membrane science and technology	31
2.6	Schematic diagram illustrating the operating principle of pervaporation	32
2.7	Mass transport through a solution diffusion membrane in pervaporation (Nawawi, 1997)	34
2.8	The pervaporation process (Schleiffelder and Staudt-Bickel, 2001)	36
2.9	Schema of pervaporation (A) and vapor permeation (B) processes	38
2.10	Chemical structure of ethyl acetate	40
2.11	Pore Flow Model for Evaporation	45
2.12	Pervaporation membrane based on solution diffusion model	46

2.13	Effect of feed flow rate on (a) flux and (b) separation factor and PSI in pervaporation of 90 wt% ethanol solution at 60 °C and permeate pressure 3 mmHg with CS/HEC: 3/1-CA composite membrane.	53
3.1	Reaction scheme of Sago/PVA cross-linking with GA	58
3.2	Sequence of homogenous Sago/PVA blend membrane preparation	59
3.3	Preparation of composite membrane	61
3.4	Procedure of preparing blended membranes	63
3.5	Schematic diagram of pervaporation process	69
4.1	Sorption data for ethyl acetate-water mixtures in homogenous sago/PVA membranes	75
4.2	Effect of water content on the degree of swelling of non-cross-linked and cross-linked sago/PVA membranes	76
4.3	Effect of time on the degree of swelling of non-cross-linked and cross-linked sago/PVA membranes	76
4.4	Weight percent of ethyl acetate in the membrane sorbed phase versus weight percent of ethyl acetate in the bulk liquid phase	77
4.5	Degree of swelling and sorption selectivity of non-cross-linked membrane versus weight percent of water in the bulk liquid	78
4.6	Degree of swelling and sorption selectivity of thermal-cross-linked membrane versus weight percent of water in the bulk liquid	78
4.7	Degree of swelling and sorption selectivity of chemical-cross-linked membrane versus weight percent of water in the bulk liquid	79

4.8	Degree of swelling and sorption selectivity of chemical+thermal-cross-linked membrane versus weight percent of water in the bulk liquid	79
4.9	TGA for non cross-linking sago/PVA membrane	81
4.10	TGA for chemical cross-linking membrane	81
4.11	TGA for thermal cross-linking membrane	82
4.12	TGA for chemical+thermal cross-linking membrane	82
4.13	FTIR for sago/PVA membranes (N, CH, CH+TH, TH)	83
4.14	SEM for (a) non-cross-linked membrane (b) thermal cross-linked membrane for chemical cross-linked membrane (c), chemical+thermal cross-linked membrane (d).	85
4.15	The total and partial permeation fluxes at various water weight percent in the feed for homogenous non-cross-linking sago/PVA membrane. Operating temperature of 50 °C and permeate pressure of 0.067 bar.	88
4.16	Weight percent of ethyl acetate in permeate versus weight percent of ethyl acetate in the feed for homogenous non-cross-linking sago/PVA membrane. Operating temperature of 50 °C and permeate pressure of 0.067 bar.	89
4.17	The total permeation flux and the separation factor for homogenous non-cross-linking sago/PVA membrane versus weight percent of water in the feed. Operating temperature of 50 °C and permeate pressure of 0.067 bar.	90
4.18	Variations of total flux, separation factor and PSI with feed concentration in sago/PVA membrane at 50 °C	91

4.19	Total flux (a) and separation factor (b) of various cross-linked membranes at 50 °C.	93
4.20	(a) Effect of feed temperature on the permeation flux for all membranes, (b) effect of feed temperature on the separation factor for all membranes	95
4.21	Effect of feed concentration on the permeation flux for all membranes	96
5.1	(a) Surface area of non-cross-linked membrane and (b) thermal cross-linked membrane	105
5.2	(c) surface area of chemical cross-linked membrane and (d) chemical +thermal cross-linked membrane	106
5.3	Morphology of (a) non-cross-linked membrane and (b) of thermal cross-linked membrane	107
5.4	Morphology of (C) chemical cross-linked membrane and (D) of chemical +thermal cross-linked membrane	108
5.5	The cross-sectional view of SEM micrograph for (a) non-cross-linked and (b) thermal cross-linked composite membranes	110
5.6	The cross-sectional view of SEM micrograph for (c) chemical cross-linked and (d) chemical+thermal cross-linked composite membranes	111
5.7	DSC of non-cross-linked and cross-linked composite membranes	113
5.8	3D AFM topographic images of the sago/PVE composite membrane surfaces of (a) non-cross-linked (b) thermal cross-linked, (c) chemical cross-linked and (d) chemical+thermal cross-linked membranes. AFM used in tapping mode at 25 °C.	115
5.9	ART-FTIR spectra of the PVA layers before and after cross-linking at 25 °C	117

5.10	the total and partial permeation flux versus feed concentration of water for non-cross-linked composite sago/PVA membrane at 30 °C	120
5.11	Separation factor and total permeation flux versus feed concentration of water for non-cross-linked composite sago/PVA membrane at 30 °C	120
5.12	Total permeation flux at different water weight percent for homogeneous and composite non-cross-linked membranes. Feed temperature is 50 °C.	121
5.13	The separation factor for homogeneous and composite sago/PVA membrane as function of feed concentration	122
5.14	Pervaporation separation index (PSI) for composite sago/PVA non-cross-linked membrane versus water weight percent in the feed, operating temperature is 30 °C	123
5.15	Total permeation flux of various cross-linking of sago/PVA membrane for pervaporation of ethyl acetate-water mixture at 3 wt% of water	125
5.16	Total separation factor of various cross-linking of sago/PVA membranes for pervaporation of ethyl acetate-water mixture at 3 wt% of water	125
5.17	Pervaporation separation index (PSI) under different cross-linked sago/PVA membranes	126
5.18	Total permeation flux of non-cross-linked and cross-linked membranes at 60 °C at different feed water concentration	128
5.19	Separation factor of non-cross-linked and cross-linked membranes at 60 °C at different feed water concentration	129
5.20	Total permeation flux of non-cross-linked and cross-linked membranes at different feed temperature	130

6.1	FTIR spectra of blended sago membrane and blended ration	139
6.2	Effect of degree of swelling on the blended ratio membranes (3 wt%, 5 wt% and 7 wt% of sago)	140
6.3	Effect of time and sago content on the degree of swelling of blended membrane	141
6.4	The total permeation flux for all membranes at different water content in the feed at 30 °C. Permeate pressure 0.067 bar.	145
6.5	The water permeation flux for all membranes at different water content in the feed at 30 °C. Permeate pressure 0.067 bar.	145
6.6	The ethyl acetate (EA) permeation flux for all membranes at different water content in the feed at 30 °C. Permeate pressure 0.067 bar.	146
6.7	Water permeation ratio vs weight percent of water in bulk feed	147
6.8	Ethyl acetate permeation ratio vs weight percent of water in bulk feed	147
6.9	The separation factor for homogenous sago/PVA blended membranes versus weight percent of water in the feed. Feed temperature 30 °C, permeate pressure 0.067 bar.	148
6.10	The effect of feed temperature on the permeation flux for all membranes	151
6.11	The effect of feed temperature on the separation factor for all membranes	151
6.12	Effect of feed temperature on permeation flux for the membrane contain 3 wt% of sago. Water in the feed 3 wt%. Permeate pressure 0.067 bar.	154
6.13	Effect of feed temperature on permeation flux for	155

	the membrane contain 5 wt% of sago. Water in the feed 3 wt%. Permeate pressure 0.067 bar.	
6.14	Effect of feed temperature on permeation flux for the membrane contain 7 wt% of sago. Water in the feed 3 wt%. Permeate pressure 0.067 bar.	155
6.15	Effect of feed temperature on water permeation flux for all sago/PVA membranes. Water in the feed 3 wt%. Permeate pressure 0.067 bar.	156
6.16	Effect of feed temperature on ethyl acetate permeation flux for all sago/PVA membranes. Water in the feed 3 wt%. Permeate pressure 0.067 bar.	157
6.17	Pervaporation separation index (PSI) for the membranes contain 3 wt%, 5 wt% and 7 wt% of sago in the blended membrane at different water weight percent in the feed. Permeate pressure 0.067 bar, feed temperature 30 °C.	158
6.18	Total permeation flux versus sago weight percent at different water concentration in the feed	159
6.19	Water permeation flux versus sago weight percent at different water concentration in the feed	160
6.20	Effect of permeate pressure on the total permeation flux for all homogenous sago/PVA membranes. Water content in feed 3 wt% operating temperature of 30 °C.	162
6.21	Effect of permeate pressure on the separation factor for all homogenous sago/PVA membranes. Water content in feed 3 wt% operating temperature of 30 °C.	162
7.1	Significance of estimated parameters on (a) Flux and (b) separation factor	173
7.2	Actual responses against predicted responses for (c) flux and (d) separation factor	174

7.3	Plots of residuals against predicted responses for (e) flux and (f) separation factor	175
7.4	Effect of (a) feed temperature and concentration on the permeation flux at permeate pressure 0.064 bar; (b) feed temperature and permeate pressure on the permeation flux at 2.7 wt% of water in the feed concentration.	178
7.5	Effect of permeate pressure and concentration on the permeation flux at permeate pressure	179
7.6	Effect of feed temperature and concentration on the separation factor at permeate pressure 0.064 bar	181
7.7	Effect of feed temperature and permeate pressure on the separation factor at 2.7 wt% of water in the feed concentration	182
7.8	Effect of permeate pressure and feed concentration on the separation factor	182

LIST OF ABBREVIATIONS

DMAC	-	N,N-dimethylacetamide
EA	-	Ethyl acetate
ME	-	Microfiltration
PS	-	Polysulfone
PTFE	-	Poly(tetrafluoroethylene)
PTMS	-	poly[1- (trimethylsilyl)- 1-propyne]
PV	-	Pervaporation
PVA	-	Polyvinyl alcohol
PVDF	-	Polyvinylidene difluoride
RO	-	Reverse osmosis
S	-	Sago
UF	-	Ultrafiltration

LIST OF SYMBOLS

α	-	Membrane selectivity
c_i	-	Concentration of component which has lower volatility
c_j	-	Concentration of component which has higher volatility
X_i, X_j	-	feed mole/ weight fraction of species i and j
y_i, y_j	-	permeate mole/ weight fraction of species i and
A	-	Effective membrane area
J	-	Permeation flux
T	-	Absolute temperature
W	-	Weight of permeate
Δt	-	Permeation time
θ	-	advancing contact angle

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Publications	212
B	Result's Data	213
C	Materials and Apparatus	228

CHAPTER 1

INTRODUCTION

1.1 Research Background

Pervaporation is a membrane separation process used to separate mixture of dissolved solvents. In recent years there has been increased interest in the use of pervaporation membrane separation techniques for the selective separation of organic liquid mixtures, because of its high separation efficiency and flux rates coupled with potential savings in energy costs and environmentally friendly (Zhu *et al.*, 2005). Two applications of pervaporation have been commercialized to date. The first application is the separation of the dilute dissolved organics such as trichloroethylene and phenol from the wastewater stream. The second and most important application is water removal from aqueous alcohol solutions such as removal water from ethyl acetate (Shao and Huang, 2007). Conversion of biomass into an energy source by fermentation processes to yield chemicals and fuels like bioethanol, to be used as fossil energy resources has been receiving increasing attention in recent years. Ethyl acetate is an organic compound with formula produced from liquid phase esterification of ethanol and acetic acid (Yuan *et al.*, 2011). Ethyl acetate is extensively used in many chemical industry processes like solvent of essence, pharmacy, printing ink and paint (Parvez *et al.*, 2012).

Sago starch can be developed to be a membrane for separation of ethyl acetate from aqueous solution. Sago starch is an important biopolymer and has been used in various applications such as in food, textile and paper. In recent years, production by fermentation of biomass has greatly increased. Sago is present in South East Asia and it could be produced from sago palm, and it is known as rumbia. Sago palm is an important resource especially to the people in rural areas because it has various uses especially in the production of starch either as sago flour or sago pearl (Rishabha 2010). In recent times, interest in the production of sago palm starch has improved extensively. The sago palm is felled, the trunk is split lengthwise and the pith is separated, the pith is crushed to release the starch, washed and strained to remove the starch from the fibrous residue (Abdorrezza *et al.*, 2012).

The sago palm is a crop par excellent for sustainable agriculture. It is interesting to note that sago palms are economical acceptable, environmentally friendly, and promotes a socially stable agroforestry system. It is an extremely hardy plant, thriving in swampy, acidic peat soils, submerged and saline soils where few other crops survive, growing more slowly in peat soil than in mineral soil. The palm is immune to floods drought, fire, and strong winds. The large fibrous root system traps silt loads and removes pollutants. Starch is found to accumulate in the trunk of the sago palm until the flowering stage with maximum starch content occurring just before the onset of the palm flowers (Singhal *et al.*, 2007).

Application of sago starch (i.e., thickeners, sizing and coating papers, sizing textile, adhesive formulations, fluid loss additive in drilling mud and other applications) always involves gelatinization of starch that breaks the inter-chains hydrogen bonding such that the rheological properties of starch paste can be utilized effectively. The non-pith parts of the sago palm trunk can be utilized in a variety of ways: as an excellent building material for local and urban houses, sheds, or other buildings; as a resource for cornposting (biofertiliser); as a resource for gasification and energy production; and as an animal feed (Singhal *et al.*, 2007).

The choice of a particular membrane material is dictated by the kind of application such as dehydration of alcohol/water and filtration of waste products in pharmaceutical industries, and the operating condition like temperature, concentration and thickness. In pervaporation dehydration of alcohol/water, the highly hydrophilic polymer such as polyvinyl alcohol is preferred due to its affinity for water. Hydroxy terminated polybutadiene (HTPB-PU) membrane has been used for the recovery of ethyl acetate from water, but the separation factor decreased significantly from 575 to 320 with increase in the operating temperature from 25 to 65 oC; this is due to the weak resistance to the high temperature of physical cross-linking (Bai et al., 2008).

Membrane technology is considered as an efficient and economic separation process in the chemical industry. We can divide the process into three stages according to the mechanism of the separation; the first stage is the sieving mechanism, ultrafiltration, and microfiltration, the second stage is the electrochemical mechanism and electro-dialysis, and the third stage is the solubility mechanism, and pervaporation (Baker, 2004b).

Recently, the extractive distillation and azeotropic distillation have been completely investigated, and was used for the separation and concentration of ethyl acetate. Yet, the two processes are still facing hardship from high operating costs and low concentration of the products because entrainers are required, while pervaporation has a good advantage because it has a low cost, easy operation and no entrainers are required (Zhang *et al.*, 2009b).

Currently, pervaporation, characterized by high separation efficiency, is one of the best alternative processes for the separation of volatile organic materials (such as ethyl acetate) (Konakom *et al.*, 2011) from dilute aqueous solutions. A mixture containing solution of ethyl acetate-water can be made to diffuse from the inside to the outside of non-porous membranes by using a vacuum to the outside of the

membrane. The driving force of the pressure differential combined with a membrane selective for ethanol makes ethanol concentration possible (Hasanoğlu *et al.*, 2005).

In pervaporation, a variety of membrane materials have been developed to cater for mainly two types of industrial liquid separations: organic-water and organic-organics separations. For water selective membranes, the most important factor responsible for the separation is the specific interaction between water and the polymer.

Pervaporation has a high potential for separations where the more conventional techniques, such as distillation, are not possible to be realized or too expensive. The pervaporation, for separation of several components from a liquid mixture cannot be only determined by changes in their vapor pressure but can be determined by their permeation rate through the membrane. The actual driving force for the permeation of the different components through the membrane is the difference between the two phases separated by the membrane. Concentration polarization in pervaporation is usually controlled by decreasing the laminar boundary layer's thickness through hydrodynamic measures. This situation can lead to problems if the flux is high and thin film composite membranes are used for the separation process. The laminar boundary layer at the permeate side is always as thick as the porous substructure and severe concentration polarization as well as capillary condensation may occur on the permeate side of the membrane (Nagy, 2012). Table 1.1 shows the list of the most important membrane process, the major field of application and the driving force for the preferentially permeating component.

Table 1.1 Membrane processes (Purchas and Sutherland, 2001)

Membrane process	Separation potential for	Driving force realized	Preferably permeating component
Reverse osmosis	Aqueous low molecular mass solutions, aqueous organic solutions	Pressure difference (≤ 100 bar)	Solvent
Ultrafiltration	Macromolecular solutions, emulsions	Pressure difference (≤ 10 bar)	Solvent
Microfiltration (Cross-flow)	Suspensions, emulsions	Pressure difference (≤ 5 bar)	Continuous phase
Gas permeation	Gas mixtures, water vapour-gas mixtures	Pressure difference (≤ 80 bar)	Preferably permeating component
Pervaporation	Organic mixtures, aqueous-organic mixtures	Permeate side: Ratio of partial pressure to saturation pressure	Preferably permeating component
Liquid membrane technique	Aqueous low molecular mass solutions, Aqueous-organic solutions	Concentration difference	Solute (ions)
Osmosis	Aqueous-organic solutions	Concentration difference	Solvent
Dialysis	Aqueous-organic solutions	Concentration difference	Solute (ions)
Electrodialysis	Aqueous-organic solutions	Concentration difference	Solute (ions)

Pervaporation is a membrane separation process used to separate mixtures of dissolved solvents. In recent years there has been an increased interest in the use of pervaporation membrane separation techniques for the selective separation of organic liquid mixtures; this is due to its high separation efficiency and flux rates coupled with potential savings in energy costs. In pervaporation, volatile organic components are removed from a liquid feed mixture through a semipermeable membrane into a gas phase.

In pervaporation the chemical potential gradient is usually induced by either applying a vacuum on the permeate side of a membrane or by using a sweep gas to remove the permeating component and by applying a temperature difference between

the liquid feed mixture and permeate gas phase. Most of the pervaporation membranes are composites formed by solution-coating of the selective layer onto a micro-porous support (Nagy, 2012).

1.2 Problem Statement

Sago and polyvinyl alcohol are highly hydrophilic material. Sago based membrane should be very selective to water; potentially effective for separation dehydration of aqueous solution. In general, the hydrophilic containing polymers have high solubility parameters and show relatively large water solubility. However, the introduction of hydrophilic groups sometimes swells the membranes significantly under aqueous mixture due to its plasticization action that results in poor selectivity. Malaysia is one of the largest producers of sago starch which covers around 7% of Sarawak total area. The production capacity of the sago palm varies from 10-25 tons/ha in dry starch. With the growing concern about the renewable energy especially the conversion of biomass to the biofuel. Potential industrial applications include the recovery of ethanol from fermentation process and the esterification of ethanol and acetic acid to produce the ethyl acetate which is attracting increasing attention due to its low toxicity. Ethyl acetate is an important solvent for antibiotics, paint, printing ink; solvent of essence and it's also use in the manufacture of various drugs. Removal of ethyl acetate from ethanol and water mixture or from isooctane mixture is difficult because of the proximity of boiling point. Currently the industrial methods for the recovery of ethyl acetate from water depends on the extractive distillation, and this process contained several practical problems, such as technology complexity and high energy consumption, thus an eco-friendly and concise separation process is being demanded. Sago starch is a highly hydrophilic material and an important biopolymer, it has been widely used in various industrial applications. Highly hydrophilic, sago based membranes can be specially effective for the recovery of azeotropic mixtures such as ethyl acetate - water solution. The separation dehydration of ethyl acetate -water mixtures is an example for such

application where sago based membranes is expected to be effective to remove the water content and purify the ethyl acetate. The efficiency of the pervaporation process depends mainly on the intrinsic properties of the polymers used to prepare the membrane.

Since the sago is highly hydrophilic polymer and polyvinyl alcohol too, there is need for the decrease of the degree of swelling; thus, cross-linking will be important. Cross-linking were affects the physicochemical properties of a membrane, the diffusion and sorption process will be affected by the membrane surface. In order to achieve the effects and the improvement of membrane performance on dehydration of ethyl acetate/water, it will be interesting to study these properties such as (SEM, AFM and FTIR).

1.3 Objectives

The main objectives of this work are to develop sago membrane for dehydration of ethyl acetate/water and to study the effect of some operating parameters, namely volumetric flow rate, feed temperature, permeate-side pressure, thickness and degree of swilling on flux and ethyl acetate selectivity during the pervaporation separation process using sago membrane. Specific objectives of this study for achieving the above purpose are to:

- i. Develop sago based membranes for the dehydration of ethyl acetate -water mixtures at different operating conditions.
- ii. Investigate the effect of crosslinking on the physiochemical properties of sago/PVA blend membrane before and after crosslinking.
- iii. Study the effect of cross-linking on the composite membranes consisting of sago/PVA- poly sulfone for pervaporation of ethyl acetate-water mixture.

- iv. Study the effect of sago blended ration on the separation of ethyl acetate-water mixtures.
- v. Study and optimize the effect of operating conditions on pervaporation performance using a statistical design (RSM) of experimental approach.

1.4 Scope of the Thesis

This thesis is including the studies of various hydrophilic sago/PVA membranes, their characterization techniques and use for pervaporation of ethyl acetate- water mixture. Characterizing of the membrane is necessary in order to determine the physical and chemical properties of the thin film. The sago-based membranes were characterized using Scanning Electron Microscopy and Fourier Transform Infrared Spectroscopy (FTIR). The driving force for transport across the membrane is the chemical potential gradient and the physical structure of the membrane determines the flux. The difference between the individual penetrant components determines the membrane selectivity. Cross-linking modification was used for improvement of the membrane performance. The research consists of two parts. The first part is including the development, characterization and separation of ethyl acetate water mixture using various membrane of sago/PVA. The second part will focus on the optimization of pervaporation process variables. The scope of each chapter is listed as follows:

Chapter 1: presents an overview of the thesis, including a brief introduction to the pervaporation membrane technology and pervaporation process and its history and overview to membrane materials. The objectives and scope of the thesis are also given in this chapter.

Chapter 2: provided the overview of sago starch and some aspects of pervaporation characteristics, different type of membrane materials, membrane modification

techniques, factors affecting pervaporation and pervaporation of ethyl acetate-water mixture.

Chapter 3: presented material and method of the thesis that used for preparing of the homogenous membranes, composite membrane and blended membranes.

Chapter 4: discusses the effects of various cross-linking on the physicochemical properties of sago/PVA membrane and on the pervaporation of ethyl acetate-water mixture. The liquid sorption and pervaporation were investigated for the ethyl acetate-water mixture using sago/PVA membrane.

Chapter 5: study the effect of cross-linked sago/PVA - polysulfone composite membrane for pervaporation of ethyl acetate-water mixture. The results were compared with homogenous sago/PVA membrane using the pervaporation separation index (PSI).

Chapter 6: of this study focuses on the development of sago/PVA membrane and the effect of sago blended ration on the separation performance. The effect of feed temperature, concentration and sago blended ratio on the separation factor and permeation flux was investigated.

Chapter 7 presents a study on the optimization of the operating conditions on the separation factor and the permeation flux by Central Composite Rotatable Design (CCRD) for pervaporation of ethyl acetate-water mixture; in order to find the optimum operating conditions of feed temperature feed concentration and permeate pressure.

The final chapter is the conclusions of the studies conducted in the thesis and recommendations for future work.

REFERENCES

- Abd-Aziz, S. (2002). Sago Starch and Its Utilisation. *Journal of Bioscience and Bioengineering*. 94(6), 526-529.
- Abdehagh, N., Tezel, F. H. and Thibault, J. (2014). Separation Techniques in Butanol Production: Challenges and Developments. *Biomass and Bioenergy*. 60,(0), 222-246.
- Abdorrezza, M. N. (2012). Physicochemical, Thermal, and Rheological Properties of Acid-Hydrolyzed Sago (Metroxylon Sagu) Starch. *LWT - Food Science and Technology*. 46,(1), 135-141.
- Abuhabib, A; Ghasemi, Mostafa; Mohammad, A.; Rahman, Rakmi; El-Shafie, A. (2013). Desalination of Brackish Water Using Nanofiltration: Performance Comparison of Different Membranes. *Arabian Journal for Science and Engineering*. 38(11), 2929-2939.
- Ahmad, N. A., Leo, C. P. and Ahmad, A. L. (2013). Superhydrophobic Alumina Membrane by Steam Impingement: Minimum Resistance in Microfiltration. *Separation and Purification Technology*. 107,(0), 187-194.
- Albo, J., Wang, J. and Tsuru, T. (2014). Application of Interfacially Polymerized Polyamide Composite Membranes to Isopropanol Dehydration: Effect of Membrane Pre-Treatment and Temperature. *Journal of Membrane Science*. 453,(0), 384-393.
- Alebooyeh, A. M., and Jokar, M. (2012). The Effects of Znnanorodson the Characteristics of Sago Starch Biodegradable Films. *Journal of Chemical Health Risks*. 2,(4), 13-16.
- Alghezawi, N. *et al.* (2005). Separation of Acetic Acid–Water Mixtures through Acrylonitrile Grafted Poly(Vinyl Alcohol) Membranes by Pervaporation. *Chemical Engineering and Processing: Process Intensification*. 44,(1), 51-58.

- Alves, V. D. *et al.* (2007). Effect of Glycerol and Amylose Enrichment on Cassava Starch Film Properties. *Journal of Food Engineering*. 78,(3), 941-946.
- Amador-Hernández, J. and Luque De Castro, M. D. (2000). Pervaporation: A Useful Tool in Food Analysis. *Food Chemistry*. 68,(4), 387-394.
- Amnuaypanich, S., Patthana, J. and Phinyocheep, P. (2009). Mixed Matrix Membranes Prepared from Natural Rubber/Poly(Vinyl Alcohol) Semi-Interpenetrating Polymer Network (Nr/Pva Semi-Ipn) Incorporating with Zeolite 4a for the Pervaporation Dehydration of Water–Ethanol Mixtures. *Chemical Engineering Science*. 64,(23), 4908-4918.
- An, Q. F. *et al.* (2003). Compatibility of Pvc/Eva Blends and the Pervaporation of Their Blend Membranes for Benzene/Cyclohexane Mixtures. *Journal of Membrane Science*. 222,(1–2), 113-122.
- Andrade-Mahecha, M. M., Tapia-Blácido, D. R. and Menegalli, F. C. (2012). *Development and Optimization of Biodegradable Films Based on Achira Flour*. *Carbohydrate Polymers*. 88,(2), 449-458.
- Aptel, P. *et al.* (1974). Liquid Transport through Membranes Prepared by Grafting of Polar Monomers onto Poly(Tetrafluoroethylene) Films. II. Some Factors Determining Pervaporation Rate and Selectivity. *Journal of Applied Polymer Science*. 18,(2), 351-364.
- Athayde, A. L. B., Daniels, R.W. R., Le, M. H., Ly, J. H. (1997). Pervaporation for Wastewater Treatment. *American Chemical Society*. v27, no.n1, 34-39.
- Bai, Y. *et al.* (2008). Cross-Linked Htpb-Based Polyurethaneurea Membranes for Recovery of Ethyl Acetate from Aqueous Solution by Pervaporation. *Journal of Membrane Science*. 325,(2), 932-939.
- Baker, R. W. (2004a). *Front Matter. Membrane Technology and Applications*. i-xiii. John Wiley & Sons, Ltd.
- Baker, R. W. (2004b). *Membrane Technology and Applications*. (SECOND EDITION ed.): McGraw-Hill.
- Baker, R. W. (2012). *Membrane Technology and Applications*. (3rd Edition ed.).
- Bao, J. *et al.* (2003). Physical Properties of Octenyl Succinic Anhydride Modified Rice, Wheat, and Potato Starches. *Journal of Agricultural and Food Chemistry*. 51,(8), 2283-2287.

- Bae, H. J. *et al.* (2008). Film and Pharmaceutical Hard Capsule Formation Properties of Mungbean, Waterchestnut, and Sweet Potato Starches. *Food Chemistry*. 106,(1), 96-105.
- Bengtsson, E., Trägårdh, G. and Hallström, B. (1993). Concentration Polarization During the Enrichment of Aroma Compounds from a Water Solution by Pervaporation. *Journal of Food Engineering*. 19,(4), 399-407.
- Bing Bing Li, L. W., De Sun (2011). Organophilic Modification and Application of Nano-Fumed Silica in Pervaporation of Ethanol / Water Mixture. *Applied Mechanics and Materials*. 117 - 119, 679-682.
- Bitter, J. G. A. (1984). Effect of Crystallinity and Swelling on the Permeability and Selectivity of Polymer Membranes. *Desalination*. 51,(1), 19-35.
- Böddeker, K. W., Bengtson, G. and Pingel, H. (1990). Pervaporation of Isomeric Butanols. *Journal of Membrane Science*. 54,(1-2), 1-12.
- Bourtoom, T. and Chinnan, M. S. (2008). Preparation and Properties of Rice Starch–Chitosan Blend Biodegradable Film. *LWT - Food Science and Technology*. 41,(9), 1633-1641.
- Chanachai, A. *et al.* (2000). Pervaporation with Chitosan/Hydroxyethylcellulose (Cs/Hec) Blended Membranes. *Journal of Membrane Science*. 166,(2), 271-280.
- Chapman, P. D. *et al.* (2008). Membranes for the Dehydration of Solvents by Pervaporation. *Journal of Membrane Science*. 318,(1-2), 5-37.
- Chen, F. R. and Chen, H. F. (1996). Pervaporation Separation of Ethylene Glycol-Water Mixtures Using Crosslinked Pva-Pes Composite Membranes. Part I. Effects of Membrane Preparation Conditions on Pervaporation Performances. *Journal of Membrane Science*. 109,(2), 247-256.
- Chen, J. H. *et al.* (2008a). Dehydration of Acetic Acid by Pervaporation Using Spek-C/Pva Blend Membranes. *Journal of Membrane Science*. 320,(1-2), 416-422.
- Chen, J. H. *et al.* (2008b). Pervaporation Separation of Meoh/Dmc Mixtures Using Sta/Cs Hybrid Membranes. *Journal of Membrane Science*. 315,(1-2), 74-81.
- Chen, S.-H. *et al.* (2001). Pervaporation Separation Water/Ethanol Mixture through Lithiated Polysulfone Membrane. *Journal of Membrane Science*. 193,(1), 59-67.
- Chiang, W.-Y. and Lin, Y.-H. (2002). Properties of Modified Poly(Vinyl Alcohol) Membranes Prepared by the Grafting of New Polyelectrolyte Copolymers for

- Water–Ethanol Mixture Separation. *Journal of Applied Polymer Science*. 86,(11), 2854-2859.
- Chopade, S. P. and Mahajani, S. M. (2000). *Pervaporation: Membrane Separations*. In Wilson, I. D. (ed.) *Encyclopedia of Separation Science*. 3636-3641. Oxford: Academic Press.
- Colla E, D. a. S. P., Menegalli Fc. (2006). Amaranthus Cruentus Flour Edible Films: Influence of Stearic Acid Addition, Plasticizer Concentration, and Emulsion Stirring Speed on Water Vapor Permeability and Mechanical Properties. *Journal of Agricultural and Food Chemistry*. 54(18), 6645-6653.
- Cui, R. and Oates, C. G. (1997). The Effect of Retrogradation on Enzyme Susceptibility of Sago Starch. *Carbohydrate Polymers*. 32,(1), 65-72.
- Davis, G. and Song, J. H. (2006). Biodegradable Packaging Based on Raw Materials from Crops and Their Impact on Waste Management. *Industrial Crops and Products*. 23(2), 147-161.
- Demšar, D. Ž., Dg Svetec (2011). Impact of Uv Radiation on the Physical Properties of Polypropylene Floating Row Covers. *African Journal of Biotechnology*. 10, 7998-8006.
- Dietz, P. *et al.* (1992). Surface Pore Structures of Micro- and Ultrafiltration Membranes Imaged with the Atomic Force Microscope. *Journal of Membrane Science*. 65,(1–2), 101-111.
- Donat B, B. (1963). *Saline Water Conversion by Flash Evaporation Utilizing Solar Energy. Saline Water Conversion?Ii*. 99-116. *American Chemical Society*.
- Dong, Z. *et al.* (2014). High Performance Ceramic Hollow Fiber Supported Pdms Composite Pervaporation Membrane for Bio-Butanol Recovery. *Journal of Membrane Science*. 450,(0), 38-47.
- Drioli, E., Zhang, S. and Basile, A. (1993). Recovery of Pyridine from Aqueous Solution by Membrane Pervaporation. *Journal of Membrane Science*. 80,(1), 309-318.
- Du, J. R., Chakma, A. and Feng, X. (2008). Dehydration of Ethylene Glycol by Pervaporation Using Poly(N,N-Dimethylaminoethyl Methacrylate)/Polysulfone Composite Membranes. *Separation and Purification Technology*. 64,(1), 63-70.

- Durmaz-Hilmioglu, N. *et al.* (2001). Acetic Acid Dehydration by Pervaporation. *Chemical Engineering and Processing: Process Intensification*. 40,(3), 263-267.
- Fels, M. and Huang, R. Y. M. (1971). Theoretical Interpretation of the Effect of Mixture Composition on Separation of Liquids in Polymers. *Journal of Macromolecular Science, Part B*. 5,(1), 89-109.
- Feng, X. (1994). *Studies on Pervaporation Membrane and Pervaporation Process*. University of Waterloo, Canada.
- Feng, X. and Huang, R. Y. M. (1992). Separation of Isopropanol from Water by Pervaporation Using Silicone-Based Membranes. *Journal of Membrane Science*. 74,(1-2), 171-181.
- Feng, X. and Huang, R. Y. M. (1996). Pervaporation with Chitosan Membranes. I. Separation of Water from Ethylene Glycol by a Chitosan/Polysulfone Composite Membrane. *Journal of Membrane Science*. 116,(1), 67-76.
- Feng, X. and Huang, R. Y. M. (1997). Liquid Separation by Membrane Pervaporation: A Review. *Industrial & Engineering Chemistry Research*. 36,(4), 1048-1066.
- Fowler, J. F. a. P. (2003). The Use of Starch and Its Derivatives as Biopolymer Sources of Packaging Materials. *Journal of Food Agriculture and Environment*. 1,(3-4), 82-84.
- Fu, Y.-J. *et al.* (2014). Hydrophobic Composite Membranes for Separating of Water–Alcohol Mixture by Pervaporation at High Temperature. *Chemical Engineering Science*. 111,(0), 203-210.
- Fujita, H., Kishimoto, A. and Matsumoto, K. (1960). Concentration and Temperature Dependence of Diffusion Coefficients for Systems Polymethyl Acrylate and N-Alkyl Acetates. *Transactions of the Faraday Society*. 56,(0), 424-437.
- Gao, W. *et al.* (2012). Effects of Clays with Various Hydrophilicities on Properties of Starch–Clay Nanocomposites by Film Blowing. *Carbohydrate Polymers*. 88,(1), 321-328.
- García, M., Sanz, M. T. and Beltrán, S. (2009a). Separation by Pervaporation of Ethanol from Aqueous Solutions and Effect of Other Components Present in Fermentation Broths. *Journal of Chemical Technology & Biotechnology*. 84,(12), 1873-1882.

- García, V. *et al.* (2009b). Dehydration of Water/Dichloromethane/N-Butanol Mixtures by Pervaporation; Optimisation and Modelling by Response Surface Methodology. *Journal of Membrane Science*. 338,(1–2), 111-118.
- Ghazali, M., Nawawi, M. and Huang, R. Y. M. (1997). Pervaporation Dehydration of Isopropanol with Chitosan Membranes. *Journal of Membrane Science*. 124,(1), 53-62.
- Gonzalez-Gutierrez, J. *et al.* (2010). Development of Highly-Transparent Protein/Starch-Based Bioplastics. *Bioresource Technology*. 101,(6), 2007-2013.
- Guan, H.-M. *et al.* (2006). Poly(Vinyl Alcohol) Multilayer Mixed Matrix Membranes for the Dehydration of Ethanol–Water Mixture. *Journal of Membrane Science*. 268,(2), 113-122.
- Guo, R. *et al.* (2007). Pervaporation Separation of Ethylene Glycol/Water Mixtures through Surface Crosslinked Pva Membranes: Coupling Effect and Separation Performance Analysis. *Journal of Membrane Science*. 289,(1–2), 191-198.
- Hasanoğlu, A. *et al.* (2005). Pervaporation Separation of Ethyl Acetate–Ethanol Binary Mixtures Using Polydimethylsiloxane Membranes. *Chemical Engineering and Processing: Process Intensification*. 44,(3), 375-381.
- Hasanoğlu, A. *et al.* (2007). Pervaporation Separation of Organics from Multicomponent Aqueous Mixtures. *Chemical Engineering and Processing: Process Intensification*. 46,(4), 300-306.
- Haska, N. and Ohta, Y. (1992). Mechanism of Hydrolysis of the Treated Sago Starch Granules by Raw Starch Digesting Amylase from *Penicillium Brunneum*. *Starch - Stärke*. 44,(1), 25-28.
- Hassan, H. (2008). *Chitosan Based Membrane for Pervaporation Separation of Isopropanol-Water Mixtures*. Department of Chemical Engineering, Universiti Teknologi Malaysia.
- Hassan Nejad, M. G., Johannes Bohn, Andreas Volkert, Bert Lehmann, André (2011). Nanocomposites of Starch Mixed Esters and Mmt: Improved Strength, Stiffness, and Toughness for Starch Propionate Acetate Laurate. *Carbohydrate Polymers*. 84(1), 90-95.

- Hassan Nejad, M., Ganster, J. and Volkert, B. (2010). Starch Esters with Improved Mechanical Properties through Melt Compounding with Nanoclays. *Journal of Applied Polymer Science*. 118,(1), 503-510.
- Heintz, A. and Stephan, W. (1994). A Generalized Solution—Diffusion Model of the Pervaporation Process through Composite Membranes Part I. Prediction of Mixture Solubilities in the Dense Active Layer Using the Uniquac Model. *Journal of Membrane Science*. 89,(1–2), 143-151.
- Huang, R. Y. M. and Lin, V. J. C. (1968). Separation of Liquid Mixtures by Using Polymer Membranes. I. Permeation of Binary Organic Liquid Mixtures through Polyethylene. *Journal of Applied Polymer Science*. 12,(12), 2615-2631.
- Huang, R. Y. M., Pal, R. and Moon, G. Y. (1999a). Characteristics of Sodium Alginate Membranes for the Pervaporation Dehydration of Ethanol–Water and Isopropanol–Water Mixtures. *Journal of Membrane Science*. 160,(1), 101-113.
- Huang, R. Y. M., Pal, R. and Moon, G. Y. (1999b). Crosslinked Chitosan Composite Membrane for the Pervaporation Dehydration of Alcohol Mixtures and Enhancement of Structural Stability of Chitosan/Polysulfone Composite Membranes. *Journal of Membrane Science*. 160,(1), 17-30.
- Huang, R. Y. M., Rhim, J.W (1991). Separation Characteristics of Pv Membranes Separation Process. In: Huang, R.Y.M. (Ed.). Separation Pervaporation Membrane Separation Prozesse. *Amsterdam: Elsevier*. 111-180.
- Huang, R. Y. M. and Yeom, C. K. (1991). Pervaporation Separation of Aqueous Mixtures Using Crosslinked Polyvinyl Alcohol Membranes. III. Permeation of Acetic Acid-Water Mixtures. *Journal of Membrane Science*. 58(1), 33-47.
- Hyder, M. N. (2008). *Preparation, Characterization and Performance of Poly(Vinyl Alcohol) Based Membrane for Pervaporation Dehydration of Alcohol*. Doctor of Philosophy. Waterloo.
- Hyder, M. N. and Chen, P. (2009). Pervaporation Dehydration of Ethylene Glycol with Chitosan–Poly(Vinyl Alcohol) Blend Membranes: Effect of Cs–Pva Blending Ratios. *Journal of Membrane Science*. 340,(1–2), 171-180.
- Hyder, M. N., Huang, R. Y. M. and Chen, P. (2006). Correlation of Physicochemical Characteristics with Pervaporation Performance of Poly(Vinyl Alcohol) Membranes. *Journal of Membrane Science*. 283,(1–2), 281-290.

- Hyder, M. N., Huang, R. Y. M. and Chen, P. (2009). Pervaporation Dehydration of Alcohol–Water Mixtures: Optimization for Permeate Flux and Selectivity by Central Composite Rotatable Design. *Journal of Membrane Science*. 326,(2), 343-353.
- Idris, A., Kormin, F. and Noordin, M. Y. (2006). Application of Response Surface Methodology in Describing the Performance of Thin Film Composite Membrane. *Separation and Purification Technology*. 49,(3), 271-280.
- Inui, K. *et al.* (1999). Pervaporation Characteristics of Methyl Methacrylate–Methacrylic Acid Copolymer Membranes Ionically Crosslinked with Metal Ions for a Benzene/Cyclohexane Mixture. *Journal of Applied Polymer Science*. 71,(2), 233-241.
- Jagannath, J. H., Nadanasabapathi, S. and Bawa, A. S. (2006). Effect of Starch on Thermal, Mechanical, and Barrier Properties of Low Density Polyethylene Film. *Journal of Applied Polymer Science*. 99,(6), 3355-3364.
- Jiang, L. Y. *et al.* (2009). Polyimides Membranes for Pervaporation and Biofuels Separation. *Progress in Polymer Science*. 34,(11), 1135-1160.
- Jiratananon, R. *et al.* (2002). Pervaporation Dehydration of Ethanol–Water Mixtures with Chitosan/Hydroxyethylcellulose (Cs/Hec) Composite Membranes: I. Effect of Operating Conditions. *Journal of Membrane Science*. 195,(2), 143-151.
- Johnson, T. and Thomas, S. (1999). Pervaporation of Acetone-Chlorinated Hydrocarbon Mixtures through Polymer Blend Membranes of Natural Rubber and Epoxidized Natural Rubber. *Journal of Applied Polymer Science*. 71,(14), 2365-2379.
- K.V.Ramana Murthy, S. N., D.Tahera Parveen, Z.Ashok, M.Archana,E.G.Mohan, K.Meghana (2010). Effect of Sago Starch on Controlled Release Matrix Tablets of Tramadol Hcl. *Journal of Chemical and Pharmaceutical Research* 2(4), 232-239.
- Kaewkannetra, P. *et al.* (2011). Separation of Ethanol from Ethanol–Water Mixture and Fermented Sweet Sorghum Juice Using Pervaporation Membrane Reactor. *Desalination*. 271,(1–3), 88-91.
- Kanti, P. *et al.* (2004). Dehydration of Ethanol through Blend Membranes of Chitosan and Sodium Alginate by Pervaporation. *Separation and Purification Technology*. 40,(3), 259-266.

- Karim, A. A. *et al.* (2008). Starch from the Sago (Metroxylon Sagu) Palm Tree- Properties, Prospects, and Challenges as a New Industrial Source for Food and Other Uses. *Comprehensive Reviews in Food Science and Food Safety*. 7,(3), 215-228.
- Kaur, B., Fazilah, A. and Karim, A. A. (2011). Alcoholic-Alkaline Treatment of Sago Starch and Its Effect on Physicochemical Properties. *Food and Bioproducts Processing*. 89,(4), 463-471.
- Kesting, R. E. (1985). *Synthetic Polymeric Membranes: A Structural Perspective*. Wiley-Interscience.
- Khayet, M., Cojocaru, C. and Zakrzewska-Trznadel, G. (2008). Response Surface Modelling and Optimization in Pervaporation. *Journal of Membrane Science*. 321,(2), 272-283.
- Kiing, S. C., Dzulkefly, K. and Yiu, P. H. (2013). Characterization of Biodegradable Polymer Blends of Acetylated and Hydroxypropylated Sago Starch and Natural Rubber. *Journal of Polymers and the Environment*. 21,(4), 995-1001.
- Kim, S.-G., Ahn, H.-R. and Lee, K.-H. (2009). Pervaporation Characteristics of Polyelectrolyte Complex Gel Membranes Based on Two Anionic Polysaccharides Having a Chelating Structure. *Current Applied Physics*. 9,(2, Supplement), e42-e46.
- Koch, K. and Górak, A. Pervaporation of Binary and Ternary Mixtures of Acetone, Isopropyl Alcohol and Water Using Polymeric Membranes: Experimental Characterisation and Modelling. *Chemical Engineering Science*. 115, 95-114.
- Konakom, K. *et al.* (2011). Use of a Batch Reactive Distillation with Dynamic Optimization Strategy to Achieve Industrial Grade Ethyl Acetate. *AIP Conference Proceedings*. 262-275.
- Krasemann, L., Toutianoush, A. and Tieke, B. (2001). Self-Assembled Polyelectrolyte Multilayer Membranes with Highly Improved Pervaporation Separation of Ethanol/Water Mixtures. *Journal of Membrane Science*. 181,(2), 221-228.
- Kuila, S. B. and Ray, S. K. (2013). Separation of Isopropyl Alcohol–Water Mixtures by Pervaporation Using Copolymer Membrane: Analysis of Sorption and Permeation. *Chemical Engineering Research and Design*. 91,(2), 377-388.

- Kuila, S. B. and Ray, S. K. (2014). Dehydration of Dioxane by Pervaporation Using Filled Blend Membranes of Polyvinyl Alcohol and Sodium Alginate. *Carbohydrate Polymers*. 101,(0), 1154-1165.
- Kujawski, W. (1996). Membrane Selectivity in Pervaporation. *Separation Science and Technology*. 31,(11), 1555-1571.
- Kujawski, W. (2000). Pervaporative Removal of Organics from Water Using Hydrophobic Membranes. Binary Mixtures. *Separation Science and Technology*. 35,(1), 89-108.
- Kunnakorn, D. *et al.* (2011). Performance of Sodium a Zeolite Membranes Synthesized Via Microwave and Autoclave Techniques for Water–Ethanol Separation: Recycle-Continuous Pervaporation Process. *Desalination*. 269,(1–3), 78-83.
- Kusumocahyo, S. P. *et al.* (2000). Water Permselectivity in the Pervaporation of Acetic Acid–Water Mixture Using Crosslinked Poly(Vinyl Alcohol) Membranes. *Separation and Purification Technology*. 18,(2), 141-150.
- Lai, L. *et al.* (2012). The Preparation of Zeolite Naa Membranes on the Inner Surface of Hollow Fiber Supports. *Journal of Membrane Science*. 409–410,(0), 318-328.
- Li, B.-B. *et al.* (2006). Chitosan-Poly (Vinyl Alcohol)/Poly (Acrylonitrile) (Cs–Pva/Pan) Composite Pervaporation Membranes for the Separation of Ethanol–Water Solutions. *Desalination*. 193,(1–3), 171-181.
- Li, G., Kikuchi, E. and Matsukata, M. (2003). A Study on the Pervaporation of Water–Acetic Acid Mixtures through Zsm-5 Zeolite Membranes. *Journal of Membrane Science*. 218,(1–2), 185-194.
- Li, G. *et al.* (2007a). Time-Dependence of Pervaporation Performance for the Separation of Ethanol/Water Mixtures through Poly(Vinyl Alcohol) Membrane. *Journal of Colloid and Interface Science*. 306,(2), 337-344.
- Liu, H. *et al.* (2009). Thermal Processing of Starch-Based Polymers. *Progress in Polymer Science*. 34,(12), 1348-1368.
- Li, Y. *et al.* (2007b). Hydrothermal Stability of Lta Zeolite Membranes in Pervaporation. *Journal of Membrane Science*. 297,(1–2), 10-15.
- Lin, D.-J. *et al.* (2004). Formation of Multilayer Poly(Acrylic Acid)/Poly(Vinylidene Fluoride) Composite Membranes for Pervaporation. *Journal of Applied Polymer Science*. 93,(5), 2266-2274.

- Liu, Y. *et al.* (2011). The Chemical Crosslinking of Polyelectrolyte Complex Colloidal Particles and the Pervaporation Performance of Their Membranes. *Journal of Membrane Science*. 385–386,(0), 132-140.
- Lu Bai, P. Q., Shuai Li, Yuan Gao, Li Ping Zhang (2011). Poly (Vinyl Alcohol)/Cellulose Nanocomposite Pervaporation Membranes for Ethanol Dehydration. *Materials Science Forum*. 675 - 677, 383-386.
- Lu, C. M. X., S. J. Xu (2009a). Starch-Based Completely Biodegradable Polymer Materials. *eXPRESS Polymer Letters* Vol.3, No.6 366–375.
- Lu, C. M. X., S. J. Xu (2009b). Starch-Based Completely Biodegradable Polymer Materials. *EXPRESS Polymer Letters*. 6, 366-375.
- Mali, S. *et al.* (2005). Mechanical and Thermal Properties of Yam Starch Films. *Food Hydrocolloids*. 19,(1), 157-164.
- Man, Y. B. C. *et al.* (2001). Study of Sago Starch (Metroxylon Sagu) Gelatinization by Differential Scanning Calorimetry. *Journal of Food Processing and Preservation*. 25,(2), 101-121.
- Marseno, F. J. P. J. T. H. a. D. W. and (2012). Properties of Biodegradable Films from Hydroxypropyl Sago Starches *Asian Journal of Food and Agro-Industry*. 5,(03), 183-192.
- Mashhadi, A. A. (2001). *Ethanol Recovery from an Aqueous Medium Using a Pervaporation Membrane*. Philosophiae Doctor. Laval University.
- Masuda, T. *et al.* (1990). Pervaporation of Organic Liquid-Water Mixtures through Substituted Polyacetylene Membranes. *Journal of Membrane Science*. 49,(1), 69-83.
- Matsuura, T. (1993). *Synthetic Membranes and Membrane Separation Processes*.
- Moheb Shahrestani, M., Moheb, A. and Ghiaci, M. (2013). High Performance Dehydration of Ethyl Acetate/Water Mixture by Pervaporation Using Naa Zeolite Membrane Synthesized by Vacuum Seeding Method. *Vacuum*. 92,(0), 70-76.
- Molina, J. M., Vatai, G. and Bekassy-Molnar, E. (2002). Comparison of Pervaporation of Different Alcohols from Water on Cmg-Om-010 and 1060-Sulzer Membranes. *Desalination*. 149,(1–3), 89-94.
- Mondragón, M., Arroyo, K. and Romero-García, J. (2008). Biocomposites of Thermoplastic Starch with Surfactant. *Carbohydrate Polymers*. 74,(2), 201-208.

- Monick, J. A. (1968). *Alcohols*, Reinhold Book Corporation.
- Moon, G. Y. (2000). *Synthesis and Preparation of Polysaccharide Based Membranes for the Pervaporatton Separation of Liquid Mixture Systems of Industrial Interest*. Doctor of Philosophy. University of Waterloo.
- Naghizadeh, A. *et al.* (2011). Application of Mbr Technology in Municipal Wastewater Treatment. *Arabian Journal for Science and Engineering*. 36,(1), 3-10.
- Nagy, E. (2012). *Pervaporation. Basic Equations of the Mass Transport through a Membrane Layer*. . Oxford: Elsevier.
- Namazi, H., Mosadegh, M. and Dadkhah, A. (2009). New Intercalated Layer Silicate Nanocomposites Based on Synthesized Starch-G-Pcl Prepared Via Solution Intercalation and in Situ Polymerization Methods: As a Comparative Study. *Carbohydrate Polymers*. 75,(4), 665-669.
- Nawawi. *Pervaporation of Isopropanol-Water System Using Chitosan Membrane*. Department of Chemical Engineering. Ph.D Thesis. University of Waterloo; 1997.
- Odusanya, O. S. *et al.* (2000). On Mechanical Properties of Sago Starch/Poly(E-Caprolactone) Composites. *Polymer Engineering & Science*. 40,(6), 1298-1305.
- Ohya, H. *et al.* (1992). The Separation of Water and Ethanol by Pervaporation with Pva-Pan Composite Membranes. *Journal of Membrane Science*. 68,(1-2), 141-148.
- Okada, T., Yoshikawa, M. and Matsuura, T. (1991). A Study on the Pervaporation of Ethanol/Water Mixtures on the Basis of Pore Flow Model. *Journal of Membrane Science*. 59,(2), 151-168.
- Pakkethati, K. *et al.* (2011). Development of Polybenzoxazine Membranes for Ethanol–Water Separation Via Pervaporation. *Desalination*. 267,(1), 73-81.
- Parvez, A. M. *et al.* (2012). Separation of Ethyl Acetate–Isooctane Mixtures by Pervaporation and Pervaporation-Based Hybrid Methods. *Chemical Engineering Journal*. 210,(0), 252-262.
- Peelman, N. *et al.* (2013). Application of Bioplastics for Food Packaging. *Trends in Food Science & Technology*. 32,(2), 128-141.

- Pelissari, F. M. *et al.* (2013). Comparative Study on the Properties of Flour and Starch Films of Plantain Bananas (*Musa Paradisiaca*). *Food Hydrocolloids*. 30,(2), 681-690.
- Penkova, A., Polotskaya, G. and Toikka, A. (2015). Pervaporation Composite Membranes for Ethyl Acetate Production. *Chemical Engineering and Processing: Process Intensification*. 87,(0), 81-87.
- Qiao, X., Chung, T.-S. and Pramoda, K. P. (2005a). Fabrication and Characterization of Btda-Tdi/Mdi (P84) Co-Polyimide Membranes for the Pervaporation Dehydration of Isopropanol. *Journal of Membrane Science*. 264(1–2), 176-189.
- Qiao, X., Jiang, W. and Sun, K. (2005b). Reinforced Thermoplastic Acetylated Starch with Layered Silicates. *Starch - Stärke*. 57(12), 581-586.
- R.D. Noble, S. a. S. (1995). *Membrane Separation Technology: Principles and Applications*. ELSEVIER.
- Rachipudi, Rachipudi, P. S. Kariduraganavar, Kittur, Sajjan. (2011). Synthesis and Characterization of Sulfonated-Poly(Vinyl Alcohol) Membranes for the Pervaporation Dehydration of Isopropanol. *Journal of Membrane Science*. 383,(1–2), 224-234.
- Ramana, K. V., Ganesan, K. and Singh, L. (2006). Pervaporation Performance of a Composite Bacterial Cellulose Membrane: Dehydration of Binary Aqueous–Organic Mixtures. *World Journal of Microbiology and Biotechnology*. 22,(6), 547-552.
- Reddy, N. and Yang, Y. (2010). Citric Acid Cross-Linking of Starch Films. *Food Chemistry*. 118,(3), 702-711.
- Rhim, J.-W., Lee, S.-W. and Kim, Y.-K. (2002). Pervaporation Separation of Water–Ethanol Mixtures Using Metal-Ion-Exchanged Poly(Vinyl Alcohol) (Pva)/Sulfosuccinic Acid (Ssa) Membranes. *Journal of Applied Polymer Science*. 85,(9), 1867-1873.
- Rishabha , P. S., Annamalai Pandurangan, & Sharma, M. B. A. P. K (2010). A Brief Review on Thermo-Rheological Properties of Starch Obtained from “Metroxylon Sagu”. *World Applied Sciences Journal*. 9, 553-560.
- Rosa, M. J. and De Pinho, M. N. (1997). Membrane Surface Characterisation by Contact Angle Measurements Using the Immersed Method. *Journal of Membrane Science*. 131,(1–2), 167-180.

- Rosentrater, K. and Otieno, A. (2006). Considerations for Manufacturing Bio-Based Plastic Products. *Journal of Polymers and the Environment*. 14,(4), 335-346.
- Salt, Salt, Yavuz Hasanoğlu, Ayça Salt, İnci Keleşer, Sevinç Özkan, Semra Dinçer, Salih. (2005). Pervaporation Separation of Ethylacetate–Water Mixtures through a Crosslinked Poly(Vinylalcohol) Membrane. *Vacuum*. 79,(3–4), 215-220.
- Sandeep , P. M. B., Rane N .M., Garkal D.J., Samdani S R (2011). Pervaporation Process for Ethanol-Water Mixture. *International Journal of Research in Chemistry and Environment*. Vol. 1, 147-152.
- Sander U, S. P. 1988. Practical Experience with Pervaporation Systems for Liquid and Vapor Separation. *Conf. on PV Proc. in the Chem. Ind. Nancy, France*: R. Bakish (Ed.), Bakish Materials Corporation, Engle wood.
- Schleiffelder, M. and Staudt-Bickel, C. (2001). Crosslinkable Copolyimides for the Membrane-Based Separation of P-/O-Xylene Mixtures. *Reactive and Functional Polymers*. 49,(3), 205-213.
- Shah, Kissick, Ghorpade,Hannah, Bhattacharyya,. (2000). Pervaporation of Alcohol–Water and Dimethylformamide–Water Mixtures Using Hydrophilic Zeolite Naa Membranes: Mechanisms and Experimental Results. *Journal of Membrane Science*. 179,(1–2), 185-205.
- Shao, Shao, Changlu Kim, Hak-Yong Gong, Jian Ding, Bin Lee, Douk-Rae Park, Soo-Jin. (2003). Fiber Mats of Poly(Vinyl Alcohol)/Silica Composite Via Electrospinning. *Materials Letters*. 57,(9–10), 1579-1584.
- Shao, P. and Huang, R. Y. M. (2007). Polymeric Membrane Pervaporation. *Journal of Membrane Science*. 287,(2), 162-179.
- Shieh, J.-J. and Huang, R. Y. M. (1997). Pervaporation with Chitosan Membranes Ii. Blend Membranes of Chitosan and Polyacrylic Acid and Comparison of Homogeneous and Composite Membrane Based on Polyelectrolyte Complexes of Chitosan and Polyacrylic Acid for the Separation of Ethanol-Water Mixtures. *Journal of Membrane Science*. 127,(2), 185-202.
- Shieh, J.-J. and Huang, R. Y. M. (1998). Chitosan/N-Methylol Nylon 6 Blend Membranes for the Pervaporation Separation of Ethanol–Water Mixtures. *Journal of Membrane Science*. 148,(2), 243-255.

- Singh, A. V. and Nath, L. K. (2013). Evaluation of Chemically Modified Hydrophobic Sago Starch as a Carrier for Controlled Drug Delivery. *Saudi Pharmaceutical Journal*. 21,(2), 193-200.
- Singhal, R. S. *et al.* (2008). Industrial Production, Processing, and Utilization of Sago Palm-Derived Products. *Carbohydrate Polymers*. 72,(1), 1-20.
- Siracusa,. (2008). Biodegradable Polymers for Food Packaging: A Review. *Trends in Food Science & Technology*. 19,(12), 634-643.
- Smitha, B. Suhanya, D. Sridhar, S. Ramakrishna, M.. (2004). Separation of Organic–Organic Mixtures by Pervaporation—a Review. *Journal of Membrane Science*. 241,(1), 1-21.
- Sourirajan, S., S. Bao, and T. Matsuura. 1987. An Approach to Membrane Separation by Pervaporation in Proc. Sec. Conf. *On pervaporation processes in the Chem. Ind., Bakish Materials Corp., . Englewood.*
- Sridhar, S., Smitha, B. and Reddy, A. A. (2006). Separation of 2-Butanol–Water Mixtures by Pervaporation through Pva–Nyl 66 Blend Membranes. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 280,(1–3), 95-102.
- Strathmann, H. (2000). *Introduction to Membrane Science and Technology*. Italy: wiley.
- Sukitpaneemit, P., Chung, T.-S. and Jiang, L. Y. (2010). Modified Pore-Flow Model for Pervaporation Mass Transport in PvdF Hollow Fiber Membranes for Ethanol–Water Separation. *Journal of Membrane Science*. 362,(1–2), 393-406.
- Sun, D., Li, B.-B. and Xu, Z.-L. (2013). Pervaporation of Ethanol/Water Mixture by Organophilic Nano-Silica Filled Pdms Composite Membranes. *Desalination*. 322,(0), 159-166.
- Sun, Y.-M. and Huang, T.-L. (1996). Pervaporation of Ethanol-Water Mixtures through Temperature-Sensitive Poly(Vinyl Alcohol-G-N-Isopropylacrylamide) Membranes. *Journal of Membrane Science*. 110,(2), 211-218.
- Sunitha, K., Satyanarayana, S. V. and Sridhar, S. (2012). Phosphorylated Chitosan Membranes for the Separation of Ethanol–Water Mixtures by Pervaporation. *Carbohydrate Polymers*. 87,(2), 1569-1574.

- Svang-Ariyaskul, A. *et al.* (2006). Blended Chitosan and Polyvinyl Alcohol Membranes for the Pervaporation Dehydration of Isopropanol. *Journal of Membrane Science*. 280,(1–2), 815-823.
- Takegami, S., Yamada, H. and Tsujii, S. (1992). Dehydration of Water/Ethanol Mixtures by Pervaporation Using Modified Poly(Vinyl Alcohol) Membrane. *Polym J*. 24,(11), 1239-1250.
- Tang, X. and Alavi, S. (2011). Recent Advances in Starch, Polyvinyl Alcohol Based Polymer Blends, Nanocomposites and Their Biodegradability. *Carbohydrate Polymers*. 85,(1), 7-16.
- Tapia-Blácido, D., Sobral, P. J. and Menegalli, F. C. (2005). Development and Characterization of Biofilms Based on Amaranth Flour (*Amaranthus Caudatus*). *Journal of Food Engineering*. 67,(1–2), 215-223.
- Tian, X. and Jiang, X. (2008). Poly(Vinylidene Fluoride-Co-Hexafluoropropene) (Pvdf-Hfp) Membranes for Ethyl Acetate Removal from Water. *Journal of Hazardous Materials*. 153,(1–2), 128-135.
- Trang, T. T. C. and Kobayashi, T. (2011). Vulcanized Paper for Separation of Alcohol Aqueous Solutions by Pervaporation. *Journal of Applied Polymer Science*. 121,(2), 639-647.
- Tyagi, R. K., Fouda, A. E. and Matsuura, T. (1995). A Pervaporation Model: Membrane Design. *Chemical Engineering Science*. 50,(19), 3105-3114.
- Uragami, Tadashi Matsuda, Toshiko Okuno, Hiroshi Miyata, Takashi. (1994). Structure of Chemically Modified Chitosan Membranes and Their Characteristics of Permeation and Separation of Aqueous Ethanol Solutions. *Journal of Membrane Science*. 88,(2–3), 243-251.
- Uragami, T., Ohshima, T. and Miyata, T. (2003). Removal of Benzene from an Aqueous Solution of Dilute Benzene by Various Cross-Linked Poly(Dimethylsiloxane) Membranes During Pervaporation. *Macromolecules*. 36,(25), 9430-9436.
- Uragami, T. and Takigawa, K. (1990). Permeation and Separation Characteristics of Ethanol-Water Mixtures through Chitosan Derivative Membranes by Pervaporation and Evapomeation. *Polymer*. 31,(4), 668-672.
- Uragami, T., Yamada, H. and Miyata, T. (2001). Removal of Dilute Volatile Organic Compounds in Water through Graft Copolymer Membranes Consisting of Poly(Alkylmethacrylate) and Poly(Dimethylsiloxane) by Pervaporation and

- Their Membrane Morphology. *Journal of Membrane Science*. 187,(1–2), 255-269.
- Villagra Di Carlo, B. and Habert, A. (2013). Plasma-Treated Polyethersulfone Coated with Crosslinked Poly(Vinyl Alcohol): Composite Membranes for Pervaporation Dehydration of Ethanol. *Journal of Materials Science*. 48,(4), 1457-1464.
- Villaluenga, J. P. G.Khayet, M.Godino, P.Seoane, B.Mengual, J. I. (2005). Analysis of the Membrane Thickness Effect on the Pervaporation Separation of Methanol/Methyl Tertiary Butyl Ether Mixtures. *Separation and Purification Technology*. 47,(1–2), 80-87.
- Wang, Luying Li, Jiding Lin, Yangzheng Chen, Cuixian. (2007). Separation of Dimethyl Carbonate/Methanol Mixtures by Pervaporation with Poly(Acrylic Acid)/Poly(Vinyl Alcohol) Blend Membranes. *Journal of Membrane Science*. 305,(1–2), 238-246.
- Wang, Xin-Ping Shen, Zhi-Quan Zhang, Fu-Yao Zhang, Yi-Feng. (1996). A Novel Composite Chitosan Membrane for the Separation of Alcohol-Water Mixtures. *Journal of Membrane Science*. 119,(2), 191-198.
- Wang, Y., Gruender, M. and Chung, T. S. (2010). Pervaporation Dehydration of Ethylene Glycol through Polybenzimidazole (Pbi)-Based Membranes. 1. Membrane Fabrication. *Journal of Membrane Science*. 363,(1–2), 149-159.
- Wee, S. L., Tye, C. T. and Bhatia, S. (2010). Process Optimization Studies for the Dehydration of Alcohol–Water System by Inorganic Membrane Based Pervaporation Separation Using Design of Experiments (Doe). *Separation and Purification Technology*. 71,(2), 192-199.
- Whistler, J. B. a. R. (2009). *Starch: Chemistry and Technology* London:Academic.
- Wijmans, J. G. and Baker, R. W. (1995). The Solution-Diffusion Model: A Review. *Journal of Membrane Science*. 107,(1–2), 1-21.
- Will, B. and Lichtenthaler, R. N. (1992). Comparison of the Separation of Mixtures by Vapor Permeation and by Pervaporation Using Pva Composite Membranes. I. Binary Alcohol-Water Systems. *Journal of Membrane Science*. 68,(1–2), 119-125.
- Wu, Hong Fang, Xin Zhang, Xiongfei Jiang, Zhongyi Li, Ben Ma, Xiaocong. (2008). Cellulose Acetate–Poly(N-Vinyl-2-Pyrrolidone) Blend Membrane for

- Pervaporation Separation of Methanol/Mtbe Mixtures. *Separation and Purification Technology*. 64,(2), 183-191.
- Wu, Shufeng Wang, Jinqu Liu, Guangli Yang, Yue Lu, Jinming. (2012a). Separation of Ethyl Acetate (Ea)/Water by Tubular Silylated Mcm-48 Membranes Grafted with Different Alkyl Chains. *Journal of Membrane Science*. 390–391, 175-181.
- Wu, Shufeng Wang, Jinqu Liu, Guangli Yang, Yue Lu, Jinming. (2012b). Separation of Ethyl Acetate (Ea)/Water by Tubular Silylated Mcm-48 Membranes Grafted with Different Alkyl Chains. *Journal of Membrane Science*. 390–391,(0), 175-181.
- Xia, Shanshan Dong, Xueliang Zhu, Yuexin Wei, Wang Xiangli, Fenjuan Jin, Wanqin. (2011). Dehydration of Ethyl Acetate–Water Mixtures Using Pva/Ceramic Composite Pervaporation Membrane. *Separation and Purification Technology*. 77,(1), 53-59.
- Xiangli, Fenjuan Chen, Yiwei Jin, Wanqin Xu, Nanping (2007). Polydimethylsiloxane (Pdms)/Ceramic Composite Membrane with High Flux for Pervaporation of Ethanol–Water Mixtures. *Industrial & Engineering Chemistry Research*. 46,(7), 2224-2230.
- Xiao, S., Huang, R. Y. M. and Feng, X. (2006). Preparation and Properties of Trimesoyl Chloride Crosslinked Poly(Vinyl Alcohol) Membranes for Pervaporation Dehydration of Isopropanol. *Journal of Membrane Science*. 286,(1–2), 245-254.
- Xie, (2013). Starch-Based Nano-Biocomposites. *Progress in Polymer Science*. 38,(10–11), 1590-1628.
- Yamasaki, A., Shinbo, T. and Mizoguchi, K. (1997). Pervaporation of Benzene/Cyclohexane and Benzene/N-Hexane Mixtures through Pva Membranes. *Journal of Applied Polymer Science*. 64,(6), 1061-1065.
- Yang, Guang Zhang, Lina Peng, Tao Zhong, Wei (2000). Effects of Ca²⁺ Bridge Cross-Linking on Structure and Pervaporation of Cellulose/Alginate Blend Membranes. *Journal of Membrane Science*. 175,(1), 53-60.
- Yang, S. (2007). Bioprocessing for Value-Added Products from Renewable Resources.

- Yeom, C.-K. and Lee, K.-H. (1996). Pervaporation Separation of Water-Acetic Acid Mixtures through Poly(Vinyl Alcohol) Membranes Crosslinked with Glutaraldehyde. *Journal of Membrane Science*. 109,(2), 257-265.
- Yeom, C. K., Jegal, J. G. and Lee, K. H. (1996). Characterization of Relaxation Phenomena and Permeation Behaviors in Sodium Alginate Membrane During Pervaporation Separation of Ethanol–Water Mixture. *Journal of Applied Polymer Science*. 62,(10), 1561-1576.
- Yeom, C. K. and Lee, K. H. (1998a). Characterization of Sodium Alginate and Poly(Vinyl Alcohol) Blend Membranes in Pervaporation Separation. *Journal of Applied Polymer Science*. 67,(5), 949-959.
- Yeom, C. K. and Lee, K. H. (1998b). Characterization of Sodium Alginate Membrane Crosslinked with Glutaraldehyde in Pervaporation Separation. *Journal of Applied Polymer Science*. 67,(2), 209-219.
- Yong Nam, S. and Moo Lee, Y. (1999). Pervaporation of Ethylene Glycol–Water Mixtures: I. Pervaporation Performance of Surface Crosslinked Chitosan Membranes. *Journal of Membrane Science*. 153,(2), 155-162.
- Yongquan, D. *et al.* (2012). Preparation, Characterization of P(Vdf-Hfp)/[Bmim]Bf₄ Ionic Liquids Hybrid Membranes and Their Pervaporation Performance for Ethyl Acetate Recovery from Water. *Desalination*. 295,(0), 53-60.
- Yu, J., Lee, C. H. and Hong, W. H. (2002). Performances of Crosslinked Asymmetric Poly(Vinyl Alcohol) Membranes for Isopropanol Dehydration by Pervaporation. *Chemical Engineering and Processing: Process Intensification*. 41,(8), 693-698.
- Yuan, Hai-Kuan Ren, Jie Ma, Xiao-Hua Xu, Zhen-Liang (2011). Dehydration of Ethyl Acetate Aqueous Solution by Pervaporation Using Pva/Pan Hollow Fiber Composite Membrane. *Desalination*. 280,(1–3), 252-258.
- Zhang, Qiu Gen Liu, Qing Lin Jiang, Zhong Ying Chen, Yu (2007). Anti-Trade-Off in Dehydration of Ethanol by Novel Pva/Apteos Hybrid Membranes. *Journal of Membrane Science*. 287,(2), 237-245.
- Zhang, Qiu Gen Liu, Qing Lin Zhu, Ai Mei Xiong, Ying Ren, Lang (2009a). Pervaporation Performance of Quaternized Poly(Vinyl Alcohol) and Its Crosslinked Membranes for the Dehydration of Ethanol. *Journal of Membrane Science*. 335,(1–2), 68-75.

- Zhang, W., Wahlgren, M. and Sivik, B. (1989). Membrane Characterization by the Contact Angle Technique: Ii. Characterization of Uf-Membranes and Comparison between the Captive Bubble and Sessile Drop as Methods to Obtain Water Contact Angles. *Desalination*. 72,(3), 263-273.
- Zhang, Wei Xu, Yunxia Yu, Zhejun Lu, Shui Wang, Xinping (2014). Separation of Acetic Acid/Water Mixtures by Pervaporation with Composite Membranes of Sodium Alginate Active Layer and Microporous Polypropylene Substrate. *Journal of Membrane Science*. 451,(0), 135-147.
- Zhang, Xiu Hua Liu, Qing Lin Xiong, Ying Zhu, Ai Mei Chen, Yu Zhang, Qiu Gen (2009b). Pervaporation Dehydration of Ethyl Acetate/Ethanol/Water Azeotrope Using Chitosan/Poly (Vinyl Pyrrolidone) Blend Membranes. *Journal of Membrane Science*. 327,(1-2), 274-280.
- Zhao, CuihongWu, Hong Li, XianshiPan, Fusheng Li, Yifan Zhao, Jing Jiang, Zhongyi Zhang, Peng Cao, Xingzhong Wang, Baoyi (2013). High Performance Composite Membranes with a Polycarbophil Calcium Transition Layer for Pervaporation Dehydration of Ethanol. *Journal of Membrane Science*. 429,(0), 409-417.
- Zhao, Qiang Qian, Jinwen An, Quanfu Zhu, Meihua Yin, Minjie Sun, Zhiwei (2009). Poly(Vinyl Alcohol)/Polyelectrolyte Complex Blend Membrane for Pervaporation Dehydration of Isopropanol. *Journal of Membrane Science*. 343,(1-2), 53-61.
- Zhen Huang, Y. H. G., Gui Mei Guo, Li Jun Teng (2011). Pervaporation Dehydration of Aqueous Ethanol Solution with Zeolite-Filled Poly (Vinyl Alcohol) Composite Membranes. *Advanced Materials Research*. 239 - 242, 1331-1334.
- Zhou, Ke Zhang, Qiu Gen Han, Guang Lu Zhu, Ai Mei Liu, Qing Lin (2013). Pervaporation of Water-Ethanol and Methanol-Mtbe Mixtures Using Poly (Vinyl Alcohol)/Cellulose Acetate Blended Membranes. *Journal of Membrane Science*. 448,(0), 93-101.
- Zhu, B. K., Tian, X. Z. and Xu, Y. Y. (2005). Recovering Ethyl Acetate from Aqueous Solution Using P(Vdf-Co-Hfp) Membrane Based Pervaporation. *Desalination*. 184,(1-3), 71-78.
- Zhu, Meihua Qian, Jinwen Zhao, Qiang An, Quanfu Song, Yihu Zheng, Qiang (2011). Polyelectrolyte Complex (Pec) Modified by Poly(Vinyl Alcohol) and

Their Blend Membranes for Pervaporation Dehydration. *Journal of Membrane Science*. 378,(1-2), 233-242.

Zhu, Yuexin Xia, Shanshan Liu, Gongping Jin, Wanqin (2010). Preparation of Ceramic-Supported Poly(Vinyl Alcohol)-Chitosan Composite Membranes and Their Applications in Pervaporation Dehydration of Organic/Water Mixtures. *Journal of Membrane Science*. 349,(1-2), 341-348.