

**STUDY ON DEFECT OF ALUMINIUM FILLED EPOXY  
MOLD INSERT IN INJECTION MOLDING**

**SAIFUL AZRIL BIN ABD RAHIM**

A thesis submitted in fulfillment of the requirement for the award of the degree of  
Master of Engineering  
(Advanced Manufacturing Technology)

**Faculty of Mechanical Engineering  
University Technology Malaysia**

JANUARY 2013

To my beloved mother, father, wife and children.

## **ACKNOWLEDGEMENT**

In preparing this thesis, I was in contact with many people, researchers, academicians, and practitioners. They have contributed towards my understanding and thoughts. In particular, I wish to express my sincere appreciation to my main thesis supervisor, Professor Dr. Safian Bin Sharif, for encouragement, guidance, critics and friendship. I am also very thankful to Mr. Mohd Tanwyn Bin Khusyairi and Miss Sharifah Zawanah for their guidance, advices and motivation. Without their continued support and interest, this thesis would not have been the same as presented here.

I am also indebted to German Malaysian Institute (GMI) and Majlis Amanah Rakyat (MARA) for funding my master study. Librarians at UTM and GMI also deserve special thanks for their assistance in supplying the relevant literatures. My fellow postgraduate students should also be recognised for their support.

My sincere appreciation also extends to all my colleagues in GMI and others who have provided assistance at various occasions. Their views and tips are useful indeed. Unfortunately, it is not possible to list all of them in this limited space.

Finally I would like to give my special thanks to the whole family especially my wife Nurhanani Binti Ghazali and my children for their supporting and understanding during the period I pursuing my master. I will not be able to finish this work without their loves, patience and sacrifices.

## ABSTRAK

Kajian ini dilakukan untuk mengkaji penggunaan bahan komposit yang digunakan bagi menghasilkan alat kemasukan di dalam proses penyuntikan acuan. Campuran *Epoxy* dan Aluminium digunakan sebagai bahan utama dalam pembuatan alat kemasukan tersebut melalui proses penuangan. Seperti alatan – alatan lain yang dihasilkan melalui proses penuangan, proses pemesinan diperlukan memandangkan proses penuangan hanya dapat menghasilkan alatan yang menghampiri bentuk sebenar tanpa mengambil kira ukuran yang tepat. Oleh yang sedemikian, mesin CNC digunakan dalam proses pemesinan untuk mendapatkan bentuk dan ukuran yang dikehendaki. Perisian analisa aliran plastik digunakan untuk mendapatkan bacaan mesin penyuntikan acuan yang optimum dalam proses penghasilan barangan plastik daripada bahan *Polypropylene* (PP). Telahpun dibuktikan bahawa akan berlaku perubahan fizikal pada alat kemasukan kerana sifat bahan komposit tersebut dikatakan cenderung untuk mengalami kegagalan selepas proses suntikan diulang beberapa kali. Simulasi perisian analisa unsur terhingga keatas perubahan anjakan alat kemasukan dijalankan dan didapati ia berpunca daripada peningkatan suhu yang dialami oleh keseluruhan sistem acuan. Selepas 300 suntikan berjaya dilaksanakan, alatan kemasukan dikeluarkan dari acuan untuk pemeriksaan. Hasil pemeriksaan mendapati berlaku perubahan anjakan dari segi ukuran pada alat kemasukan. Keputusan perisian analisa unsur terhingga dibandingkan bersama dengan keputusan hasil pemeriksaan fizikal dan ukuran daripada proses ujikaji penyuntikan plastik. Selepas perbandingan dijalankan, didapati alat kemasukan mengalami perubahan fizikal dan ukuran.

## **ABSTRACT**

The purpose of this project is to study the used of composite material as an insert in injection molding process. Epoxy with aluminium filled was used and casted to fabricate the cavity insert of the mold. As with most cast products, machining is necessary due to the fact that cast parts can only be made to near net shape. For that reason, CNC machine was used to machine the casted material into desired shape and dimensions. Plastic flow analysis software has been used to obtain optimum injection machine parameters for production of polypropylene (PP) part. It was evident that slight changes had happen to the insert as the composite material itself tends to fail after a number of injection shots. Finite element analysis (FEA) software was used to simulate the insert displacement or deformation due to the effect of molding temperature experienced by the insert. After 300 successful injections were obtained, the insert was inspected and measured physically. It was found that the insert experienced a slight change uniformly and dimensionally after comparing the data against results of the FEA software.

## TABLE OF CONTENTS

<b>CHAPTER</b>	<b>TITLE</b>	<b>PAGE</b>
	<b>STATUS OF THESIS</b>	
	<b>SUPERVISOR DECLARATION</b>	
	<b>TITLE PAGE</b>	i
	<b>DECLARATION OF ORIGINALITY</b>	ii
	<b>DEDICATION</b>	iii
	<b>ACKNOWLEDGEMENTS</b>	iv
	<b>ABSTRAK</b>	v
	<b>ABSTRACT</b>	vi
	<b>TABLE OF CONTENTS</b>	vii
	<b>LIST OF TABLES</b>	x
	<b>LIST OF FIGURES</b>	xii
	<b>LIST OF SYMBOLS</b>	xv

### **CHAPTER 1 INTRODUCTION**

1.1	Background	1
1.2	Problem statement	3
1.3	Project objective	4
1.4	Scope of study	5

### **CHAPTER 2 LITREATURE REVIEW**

2.1	Epoxy Composite	
-----	-----------------	--

2.1.1	Chemistry	6
2.1.2	Epoxy Crystallization	8
2.1.3	Mechanical Properties of FEA Modelling	9
2.2	Rapid Tooling (RT) Technology	11
2.3	Mold Insert: Metal vs Composite	15
2.4	Performance of Rapid Tooling (RT) Mold	22

### **CHAPTER 3 PROJECT METHODOLOGY**

3.1	Introduction	25
3.2	Plastic Flow Analysis	27
3.3	Finite Element Analysis	29
3.4	Fabrication and Preparation of the Inserts	32
3.5	Machining Process	34
3.6	Mold Assembly and Injection Process	36
3.7	Insert Inspection	39
3.8	Data analysis and Interpretation	41

### **CHAPTER 4 RESULTS AND DISCUSSION**

4.1	Result	
4.1.1	Plastic Flow Analysis	42
4.1.2	Finite Element Analysis	46
4.1.3	CMM Inspection	48
4.1.4	RE Scanner Inspection	52
4.2	Discussions	53

## **CHAPTER 5 CONCLUSION AND RECOMMENDATION**

5.1 Conclusion 54

5.2 Recommendation 55

**REFERENCES 56**

**APPENDICES 66**



## **LIST OF TABLE**

<b>TABLE</b>	<b>TITLE</b>
--------------	--------------

- |     |   |
|-----|---|
| 2.1 | Comparison between RT and conventional tooling                  |
| 2.2 | Ingredients of powder reinforced epoxy composites               |
| 2.3 | Important rapid tooling processes and their parent RP processes |

## LIST OF FIGURES

<b>FIGURE</b>	<b>TITLE</b>
2.1	Structure of unmodified epoxy pre-polymer resin
2.2	Structure of TETA a typical hardener
2.3	Hierarchal structure of tooling requirements and attributes
2.4	Classification of rapid tooling technologies
2.5	Temperature variations (degrees Celsius) over the cycle time for the inserts made by epoxy tooling
2.6	Graph of Injection pressure vs cycle time
2.7	Unbalanced cooling effect on volumetric shrinkage
2.8	Mold material influence on volumetric shrinkage
2.9	Unbalanced cooling effect on warpage
2.10	Mold material influence on cycle time
2.11	Measured heat conductivity of the epoxy mold inserts
3.1	Project process flow
3.2	3D model of the cup (produced part).
3.3	Process flow of plastic flow analysis by using MoldFlow software
3.4	Picture of insert with constraint region (blue) and temperature region (red) that need to be assign during analysis process set up.
3.5	Procedure for insert fabrication
3.6	Picture above shows the epoxy (left) and the hardener (right).
3.7	Picture shows how the mixture being poured into the temporary mold
3.8	3D model of Cavity Insert
3.9	Insert workpiece undergo turning operation at CNC Lathe machine
3.10	Insert workpiece undergo milling operation at CNC milling machine

- 3.11 Insert workpiece after completing turning operation
- 3.12 Insert workpiece after completed milling and machining process
- 3.13 Picture of mold assembly together with the composite inserts
- 3.14 Schematic drawing of the complete mold showing the cavity insert
- 3.15 Exploded view of an injection molding machine
- 3.16 Injection molding process
- 3.17 Picture shows 5 points on the cavity insert profile to be used for CMM
- 3.18 Model of portable RE scanner machine for inspection
- 3.19 Preparation set up for scanning operation
- 3.20 Scanning operation in action by using RE scanner

## LIST OF APPENDICES

<b>APPENDIX.</b>	<b>TITLE</b>	<b>PAGE</b>
A1	Insert Drawing	59
A2	Complete Mold Drawing	61
B1	Epoxy Composites Properties	63
C1	Result CMM	67
DI	RE Scanning Report	70

## LIST OF SYMBOLS & ABBREVIATIONS

%	percent
°C	Degree celsius
mm	Millimetre
MPa	Mega Pascal
N	Newton
wt	Weight
K	Degree Kelvin
Ni	Nickel
Cu	Copper
Fe	Iron
Mo	Molybdenum
Al	Aluminium
Ti	Titanium
Mn	Manganese
Si	Silicon
C	Carbon
N	Nitrogen
FCC	Face-centered cubic
ANSI	American National Standards Institute
CBN	Cubic boron nitride
CNC	Computer Numerical Control
CMM	Coordinate measuring machine
FEM	Finite Element Methodology
FEA	Finite Element Analysis
RT	Rapid Tooling
RE	Reverse Engineering

## **CHAPTER 1**

### **INTRODUCTION**

#### **1.1 Background**

The requirements for faster product development cycles, lower product cost and environmental sustainability are ever increasing in today's globally competitive market. Tooling is a very important phase in the product manufacturing cycle. To overcome the shortcomings of long lead time and high cost associated with conventional tooling processes, new tooling methods with shorter lead time and lower cost are strongly under demand. In the modern consumer market, the success in launching and marketing a new product is highly dependent upon the time to market [1]. Much work has been carried out with a variety of available Rapid Prototyping (RP) and Rapid Tooling (RT) techniques [2–6] for producing direct and indirect tooling used for mould production. In this paper, an indirect rapid soft tooling approach, namely, aluminium filled epoxy resin tooling for mould production which is based on RP fabricated master patterns, is evaluated.

The high cost of raw material stock used in current RP systems makes them economically unsuitable even for smallbatch production during the product evaluation and manufacturing stages [7]. Furthermore, many RP methods currently in use are unable to produce functional parts with good material properties, and are

generally cost prohibitive for making more than a handful of models. Even though the technology is improving and there is increasing use of RP for direct rapid manufacturing (RM), it is often not possible to fabricate many parts that require high accuracy and good material properties. Therefore, it is highly desirable to have complimentary tooling, made to produce more components in representative materials, but still utilizing the speed and flexibility of rapid prototyping.

In today manufacturing world, many products have insufficient quantity requirements to justify steel tooling. Also in the new product development cycle, there is often need of some intermediate tooling to produce a small quantity of prototypes or working samples for marketing, functional test, or production process design and evaluation purposes. In these cases, making cost-effective tooling quickly for small batch production can become very important. In this aspect, RT is good enough to replace a more conventional method, saving time and money in the process. The demand for faster and less expensive tooling solutions has resulted in an impressive number of RT methods being developed worldwide. RP and RT technologies have been identified and proved to have a great impact on product development cycle lead time and cost [8]. Based on previous study, plastic tools can be up to 50% cheaper than conventional tooling and usually take 70% less time to manufacture. Since they are made of plastic, they are light in weight and easy to handle and need no special storage. Building plastic materials are usually epoxies or polyurethane which both set at room temperature. Oven treatment is necessary only when heat resistant tools are to be made. Plastic tools are easy to patch and not brittle. They bond to practically any material when inner support structures for additional tool stiffness is required. They are durable and won't rust and won't warp. They provide quick, easy and inexpensive modification for repair of valuable tools. For example, tooling for injection molding applications has been a promising area for deploying one of the RP method which is the Stereolithography (SL) technique. SL molds allow complex geometry to be built with ease and with considerable reduction in cost and tool development time. SL molds can be built in hours instead of days or months as for conventional steel molds [9].

## 1.2 Problem Statement

During the last few years, significant research and developments are achieved by different research groups which have worked on rapid tooling issues. Weissman has demonstrated that a rapid prototype model can be used as a master to get a shell of metal and with a supporting material such as epoxy resin, it can be used for injection moulding, metal forming, and electrical discharge machining (EDM) electrode [12]. The injection of fibre reinforced thermoplastic polymers is in a process of great expansion. Moulds manufactured with metallic filled polymers exhibit limited durability, due to the extensive wear to which they are submitted during the filling injection stage of abrasive thermoplastic polymers, making their use in this application not very attractive. They are used for low to high volume runs, however these are also heat sinks, which greatly retard production cycles, and cannot be controlled to run at a consistent temperature.

Epoxy tools often will begin to crack and break apart when repeatedly brought to high temperatures and cooled to room temperature. High temperatures affect the mechanical properties of the composite, due to resin softening and reduction of the particle and fibre/matrix adhesion [11]. During ejection, stresses are applied at the surface of the mold due to the plastic part shrinkage on the core coupled with inherent interlocking between molds and the part. The molds usually chip at the surface leading to an immediate fracture, or cracks can initiate and failure may occur after limited further cycling. Other type of failure has been observed when the mold has had time to reach a steady state. after more than twenty cycles. This failure type usually involves some chipping. This process has been compared to a fatigue type of failure and can occur during either injection or ejection, depending on the length to which the crack has grown [9]. Depending on the geometry and the process conditions, the molds end up failing by one of these modes.

The low thermal conductivity of the epoxy resins, about 5% of the thermal conductivity of the metals, have a substantial influence in the heat transfer process.



One of the current possibilities to overcome the lower thermal properties of the materials is the incorporation of cooling channels within the mold. Hybrid injection molds with non-metallic components in the molding zone are being considered as the single possibility to realize short runs or single parts. Hot spots, occurring in low cooling areas, can be minimized leading to the desirable homogeneous temperature field throughout the part.

Despite the cost and time advantages, RT molds generally have poor thermal and mechanical properties, hence are liable to fail during the molding process. Previous work on RT molds has shown that their life is highly dependent on the stress applied to the mold during the injection molding cycle. During injection, the polymer flow creates a bending stress on small features, and can either permanently deform the mold or break it. There are several more problems that limit the effectiveness of rapid tooling. These problems include but are not limited to the following characteristic such as the surface roughness inherent to the layered process, the surface roughness and part inaccuracy owing to the approximation of the CAD model, the part inaccuracy owing to shrinkage, the poor injection mold properties owing to the low thermal conductivity of the material, and the short mold life owing to limited material strength and partially cured parts [9].

### **1.3 Project Objectives**

The main objective of this research is to study the effect of the molding temperature on the RT mold insert by mean of Finite Element Analysis (FEA) and the actual experimental work. The effect on the insert was analysed in terms of the displacement defects on the insert itself. In order to achieve this goal, the following specific objectives were set for this research :

- i. To determine the optimum parameters for injection molding machine for Polypropylene (PP) material by using plastic flow analysis method.
- ii. To design and fabricate aluminium-epoxy cavity insert for production of PP material.
- iii. To study the displacement of aluminium-epoxy composite insert due to molding temperature by using finite element method (FEM).
- iv. To validate and verify the simulation results with experimental work.

#### **1.4 Scope of the study**

The scope of study for this project covers the followings :

- i. Aluminium-epoxy composite material was used to fabricate the cavity insert.
- ii. Plastic flow analysis simulation, MoldFlow software was used to predict molding temperature of the Polypropylene (PP) part.
- iii. Injection Molding machine with capacity of 100 tones was used to conduct the experiments.
- iv. CNC Lathe and CNC Milling was employed for insert fabrication.
- v. Coordinate Measuring Machine (CMM) was used for inspection.
- vi. Portable Reverse Engineering (RE) scanner was used to scan the insert.
- vii. Finite element software, HyperMesh ver. 10 was used for linear static analysis to predict the insert deflection of the insert.

## REFERENCES

- [1]. Easterlow, “*Rapid Prototyping and Tooling: What Next For Rover Group*”, Rapid News, Winter 1993.
- [2]. B. Badrinarayan and J. W. Barlow, “*Manufacture of injection moulds using SLS*”, proceedings of Solid Freeform Fabrication Symposium, Austin, Texas, pp. 371–378, 1994.
- [3]. J. W. Barlow, J. J. Beaman and B. Balasubramaniam, “*A rapid mould-making system: material properties and design considerations*”, Rapid Prototyping Journal, 2(3), pp. 4–15, 1996.
- [4]. C. K. Chua, K. H. Hong and S. L. Ho, “*Rapid tooling technology. Part I: A comparative study*”, International Journal of Advanced Manufacturing Technology, 15(8), p. 604–608, 1999.
- [5]. C. K. Chua, K. H. Hong and S. L. Ho, “*Rapid tooling technology; Part 2: A case study using arc spray metal tooling*”, International Journal of Advanced Manufacturing Technology, 15(8), p. 609–614, 1999.
- [6]. E. Sachs, E. Wylonis and S. Allen, “*Production of injection molding tooling with conformal cooling channels using the three dimensional printing process*”, Polymer Engineering and Science, 40(5), pp. 1232–1247, 2000.
- [7]. C. M. Cheah, C. K. Chua, H. S. Ong, “*Rapid Moulding Using Epoxy Tooling Resin*”, Int J Adv Manuf Technol (2002) 20:368–374.

- [8]. D. Greenwood and M. Gloden, “*Using rapid prototyping to reduce costs and time to market*”, Proceedings of Rapid Prototyping and Manufacturing Conference, Dearborn, Michigan, SME, Section 15, 1993.
- [9]. Vincent Rodet and Jonathan S. Colton, “*Properties of Rapid Prototype Injection Mold Tooling Materials*”, Center for Polymer Processing and The George Woodruff School of Mechanical Engineering Georgia Institute of Technology Atlanta. GA 30332-0405.
- [10]. Jonathan Colton and Bryan Blair, “*Experimental study of post-build cure of stereolithography polymers for injection molds*”, Rapid Prototyping Journal Volume 5 • Number 2 • 1999 • pp. 72–81.
- [11]. Pedro V. Vasconcelos, F. Jorge Lino, Ant´onio M. Baptista, Rui J.L. Neto, “*Tribological behaviour of epoxy based composites for rapid tooling*”, 0043-1648/2005 Elsevier B.V.
- [12]. Weiss L E, Gursoz E L, Prinz F B, et al. “*A rapid tool manufacturing system based on stereolithography and thermal spraying*”. Manufacturing Review, 1990, 3: 40-48.
- [13]. Jo´zsef Ga´bor Kova´cs, “*Construction of Pre-Deformed Shapes for Rapid Tooling in Injection Molding*”, Macromol. Symp. 2006, 239, 259–265.
- [14]. Bayer Material Science, “*Processing by Injection Molding for Desmopan and Texin*”, page 14.
- [15]. Gonalves MW, Salmoria GV, Ahrens CH, Pouzada AS (2007) “*Study of tribological properties of moulds obtained by stereolithography*”. Virtual and Physical Prototyping 2:29–36.

- [16]. Antonio J. Pontes & Miguel P. Queirós, Pedro G. Martinho, Paulo J. Bártolo & António S. Pouzada, "Experimental assessment of hybrid mould performanc", Int J Adv Manuf Technol (2010) 50:441–448.
- [17]. May, Clayton A. (1987-12-23). *Epoxy Resins: Chemistry and Technology* (Second ed.). New York: Marcel Dekker Inc. p. 794.
- [18]. Luft, J.H. (1961). "Improvements in epoxy resin embedding methods". The Journal of biophysical and biochemical cytology (Rockefeller Univ Press) 9 (2): pp. 409.
- [19]. Morena, John J (1988). *Advanced Composite Mold Making*. New York: Van Nostrand Reinhold Co. Inc. pp. 124–125.
- [20]. Nagahanumaiah, K. Subburaj, B. Ravi, "Computer aided rapid tooling process selection and manufacturability evaluation for injection mold development", Computers in Industry 59 (2008) 262–276.
- [21]. S. Maa, I. Gibson, G. Balaji, Q.J. Hua, "Development of epoxy matrix composites for rapid tooling applications", Journal of Materials Processing Technology 192–193 (2007) 75–82
- [22]. J.C. Ferreira, A. Mateus, "Studies of rapid soft tooling with conformal cooling channels for plastic injection moulding", Journal of Materials Processing Technology 142 (2003) 508–516
- [23]. Soon Chun Kuek, "An investigation of cavity pressure as a process and quality indicator in the micro- injection molding process", UMI Microform, UMI Number: 1447707.