

**SYNTHESIS OF MESOPOROUS MATERIALS AS ADSORBENT FOR
ADSORPTION AND DESORPTION OF PARAQUAT**

NUR FARALIANA BINTI JAPRI

UNIVERSITI TEKNOLOGI MALAYSIA

SYNTHESIS OF MESOPOROUS MATERIALS AS ADSORBENT FOR
ADSORPTION AND DESORPTION OF PARAQUAT

NUR FARALIANA BINTI JAPRI

A dissertation submitted in partial fulfilment of the
requirements for the award of the degree of
Master of Science

Faculty of Science
Universiti Teknologi Malaysia

JUNE 2017

*Very special dedication to my beloved parents, Japri bin
Khamis and Mayzurah binti Basri, my husband, Ahmad
Uzair bin Said, respected supervisor, Assoc. Prof. Dr.
Zainab binti Ramli, all lecturers, families and friends.
Thank you for the prayers, supports and encouragements.*

ACKNOWLEDGEMENT

In the name of Allah, the most Gracious, the Most Merciful

Firstly, Alhamdulillah, All praises be to Allah, The supreme Lord of the universe. Peace and blessing to our Prophet, Prophet Muhammad P.B.U.H, all the prophets, their families and all the Muslims.

I wish to thank to my project supervisor, Assoc. Prof. Dr. Zainab binti Ramli, for her help, guidance, encouragement and patience throughout this dissertation project from the beginning until the ending part. Her understanding, experience, knowledge and supervision are very much appreciated.

My heartfelt thanks and appreciation also goes to all the laboratory members of Physical Chemistry Research Laboratory I for their help and sharing knowledge. Their ideas and opinions have contributed a lot throughout my project.

Finally, I am grateful to my beloved parents, husband, families and friends for their understanding, continual support and encouragement. Without them, I may not able to complete this dissertation project. Thank you so much.

ABSTRACT

Paraquat is a pesticide that is used to control weeds but it is very poisonous to humans and environment. Therefore, removal of paraquat from the environment is very important and in poisoning cases that involve paraquat, the sample need to be preconcentrated prior to analysis because the pesticide concentration may very low to be measured and in small sample size. In this research, several types of mesoporous materials were synthesised to adsorb and desorb paraquat namely mesoporous aluminosilicate using various saccharides templates as mesoporous directing agent which are glucose (MAS-GLU), lactose (MAS-LAC), sucrose (MAS-SUC) and without saccharide template (MAS-WOT) and being compared to mesoporous silica material, MCM-41. The formations of synthesised materials were confirmed from FTIR, XRD, SAXS, XRF and surface area analysis. The characterisation results revealed that MAS-SUC formed mesoporous aluminosilicate with ZSM-5 zeolite framework, MAS-GLU, MAS-LAC and MAS-WOT formed mesoporous aluminosilicate with amorphous structure and MCM-41 is mesoporous silica. MAS-SUC, MAS-WOT and MCM-41 were chosen as the representative of different type of mesoporous materials for adsorption and desorption experiment. From the adsorption result of paraquat, it showed that the maximum adsorption capacity in the order of MAS-WOT, MAS-SUC and MCM-41 with maximum adsorption capacity 37.59 mg/g, 36.76 mg/g and 4.45 mg/g respectively. The isotherm study shows all adsorbents fit Langmuir isotherm better than Freundlich isotherm. The desorption results revealed that desorption by sonication process is better than shaking process and even though MAS-WOT and MAS-SUC have good adsorption ability, but paraquat not able to desorb well from them. Only 33% of adsorbed paraquat can be desorbed from MAS-WOT and 31% from MAS-SUC. MCM-41 showed better desorption ability because almost 100% of the analyte able to be desorbed. Study showed that mesoporous aluminosilicate materials are better adsorbents as compared to MCM-41, but poor in desorption ability for paraquat.

ABSTRAK

Parakuat ialah racun perosak yang digunakan untuk mengawal rumpai tetapi ia sangat beracun kepada manusia dan alam sekitar. Oleh itu, penyingkiran parakuat dari alam sekitar adalah sangat penting dan dalam kes-kes keracunan yang melibatkan parakuat, sampel perlu diprakonsentrasi sebelum dianalisis kerana kepekatan racun perosak yang berkemungkinan sangat rendah untuk diukur dan saiz sampel yang kecil. Dalam kajian ini, beberapa jenis bahan mesoliat telah disintesis untuk menjerap dan menyahjerap parakuat iaitu mesoliat aluminosilikat menggunakan pelbagai templat sakarida sebagai ejen pengarah mesoliat iaitu glukosa (MAS-GLU), laktosa (MAS-LAC), sukrosa (MAS-SUC) dan tanpa templat sakarida (MAS-WOT) dan dibandingkan dengan bahan mesoliat silika, MCM-41. Pembentukan bahan disintesis telah disahkan dari FTIR, XRD, SAXS, XRF dan analisis kawasan permukaan. Keputusan pencirian mendedahkan bahawa MAS-SUC membentuk mesoliat aluminosilikat dengan kerangka zeolit ZSM-5, MAS-GLU, MAS-LAC dan MAS-WOT membentuk mesoliat aluminosilikat dengan struktur amorfus dan MCM-41 adalah mesoliat silika. MAS-SUC, MAS-WOT dan MCM-41 telah dipilih sebagai wakil bahan mesoliat yang berlainan jenis untuk eksperimen penjerapan dan penyahjerapan. Dari hasil penjerapan parakuat, ia menunjukkan bahawa kapasiti penjerapan maksimum dalam urutan MAS-WOT, MAS-SUC dan MCM-41 dengan kapasiti penjerapan maksimum 37.59 mg/g, 36.76 mg/g dan 4.45 mg/g masing-masing. Kajian isoterma menunjukkan semua penjerap mematuhi isoterma Langmuir lebih baik daripada isoterma Freundlich. Keputusan penyahjerapan mendedahkan bahawa penyahjerapan oleh proses sonikasi adalah lebih baik daripada proses goncangan dan walaupun MAS-WOT dan MAS-SUC mempunyai keupayaan penjerapan yang baik, tetapi parakuat tidak dapat dinyahjerap dengan baik dari mereka. Hanya 33% daripada parakuat yang terjerap boleh dinyahjerap dari MAS-WOT dan 31% dari MAS-SUC. MCM-41 menunjukkan kebolehan penyahjerapan yang lebih baik kerana hampir 100% daripada analit dapat dinyahjerap. Kajian menunjukkan bahawa bahan-bahan mesoliat aluminosilikat adalah penjerap yang lebih baik berbanding dengan MCM-41, tetapi kurang keupayaan dalam penyahjerapan parakuat.

TABLE OF CONTENTS

| CHAPTER | TITLE | PAGE |
|----------|---|-------------|
| | DECLARATION | ii |
| | DEDICATION | iii |
| | ACKNOWLEDGEMENT | iv |
| | ABSTRACT | v |
| | ABSTRAK | vi |
| | TABLE OF CONTENTS | vii |
| | LIST OF TABLES | x |
| | LIST OF FIGURES | xi |
| | LIST OF ABBREVIATIONS | xiii |
| | LIST OF SYMBOLS | xv |
| 1 | INTRODUCTION | 1 |
| | 1.1 Background of study | 1 |
| | 1.2 Statement of Problem | 3 |
| | 1.3 Objective of Study | 4 |
| | 1.4 Scope of Study | 4 |
| | 1.5 Significance of Study | 5 |
| 2 | LITERATURE REVIEW | 6 |
| | 2.1 Paraquat | 6 |
| | 2.1.1 Suicide and Poisoning Cases of Paraquat | 7 |
| | 2.1.2 Environmental Effect of Paraquat | 9 |
| | 2.2 Mesoporous Material | 9 |
| | 2.2.1 Mesoporous Silica MCM-41 | 10 |
| | 2.3 Aluminosilicate | 10 |
| | 2.3.1 Synthesis of Mesoporous Aluminosilicate | 11 |

| | | |
|----------|--|-----------|
| | 2.3.2 Mesoporous Aluminosilicate as Adsorbent | 13 |
| | 2.4 Saccharide | 14 |
| | 2.5 Adsorption and Desorption of Paraquat | 15 |
| 3 | MATERIALS AND METHODS | 19 |
| | 3.1 Chemical reagents | 19 |
| | 3.2 Synthesis of Mesoporous Aluminosilicate | 20 |
| | 3.3 Synthesis of Mesoporous Silica MCM-41 | 21 |
| | 3.4 Characterisation | 22 |
| | 3.4.1 Fourier Transform Infrared Spectroscopy | 22 |
| | 3.4.2 X-ray Diffraction | 23 |
| | 3.4.3 Small Angle X-ray Scattering | 23 |
| | 3.4.4 X-ray Fluorescence | 23 |
| | 3.4.5 Surface Area Analysis | 24 |
| | 3.5 Adsorption of Paraquat | 24 |
| | 3.5.1 Optimisation of Adsorption Time | 24 |
| | 3.5.2 Effect of Initial Concentration on Adsorption | 24 |
| | 3.5.3 Isotherm Study | 25 |
| | 3.5.4 Determination of Adsorption Capacity | 25 |
| | 3.5.5 Determination of Removal Efficiency | 26 |
| | 3.6 Desorption of Paraquat | 26 |
| | 3.6.1 Effect of Different of Desorption Method | 26 |
| | 3.6.2 Determination of Concentration of Desorbed Paraquat | 27 |
| | 3.6.3 Determination of Desorption Removal Efficiency | 27 |
| | 3.7 Analysis of Supernatant | 27 |
| | 3.8 Research Flow Chart | 28 |
| 4 | RESULT AND DISCUSSION | 29 |
| | 4.1 Synthesis of Mesoporous Aluminosilicate | 29 |
| | 4.2 Characterisation | 29 |
| | 4.2.1 Fourier Transform Infrared Spectroscopy | 29 |
| | 4.2.2 X-ray Diffraction | 32 |

| | |
|---|-----------|
| 4.2.3 Small Angle X-ray Scattering | 33 |
| 4.2.4 X-ray Fluorescence | 34 |
| 4.2.5 Surface Area Analysis | 35 |
| 4.3 Adsorption of Paraquat | 41 |
| 4.3.1 Optimisation of Adsorption Time | 41 |
| 4.3.2 Effect of Initial Concentration | 44 |
| 4.3.3 Isotherm Study | 45 |
| 4.3.3.1 Langmuir Isotherm | 45 |
| 4.3.3.2 Freundlich Isotherm | 48 |
| 4.3.3.3 Analysis on Adsorption Isotherm | 51 |
| 4.4 Desorption of Paraquat | 51 |
| 4.4.1 Effect of Different Desorption Method | 52 |
| 5 CONCLUSION AND RECOMMENDATION | 54 |
| 5.1 Conclusion | 54 |
| 5.2 Recommendation | 55 |
| REFERENCES | 57 |

LIST OF TABLES

| TABLE NO. | TITLE | PAGE |
|------------------|---|-------------|
| 2.1 | Properties of paraquat | 7 |
| 2.2 | Adsorption capacities of several synthetic and natural adsorbents | 18 |
| 3.1 | List of chemicals | 20 |
| 3.2 | Designation of synthesised samples | 21 |
| 4.1 | Summary of FTIR frequencies for MAS-GLU, MAS-SUC, MAS-LAC, MAS-WOT and MCM-41 | 31 |
| 4.2 | XRF elemental analysis of MAS-SUC and MAS-WOT | 35 |
| 4.3 | Surface area analysis result for MAS-GLU, MAS-SUC, MAS-LAC, MAS-WOT and MCM-41 | 37 |
| 4.4 | Values of the Langmuir parameters for adsorption of paraquat by MAS-WOT, MCM-41 and MAS-SUC | 48 |
| 4.5 | Values of the Freundlich parameters for adsorption of paraquat by MAS-WOT, MCM-41 and MAS-SUC | 50 |
| 4.6 | Parameter of different desorption methods | 53 |

LIST OF FIGURES

| FIGURE NO. | TITLE | PAGE |
|------------|--|------|
| 2.1 | Molecular structure of paraquat | 6 |
| 2.2 | Structure of aluminosilicate material | 11 |
| 2.3 | Molecular structure of a) glucose, b) sucrose and c) lactose | 15 |
| 3.1 | Research flow chart | 28 |
| 4.1 | IR spectra of a) MAS-GLU, b) MAS-SUC, c) MAS-LAC, d) MAS-WOT and e) MCM-41 | 31 |
| 4.2 | XRD patterns of MAS-WOT, MAS-GLU, MAS-SUC and standard of TPA ZSM-5 from International Zeolite Association | 33 |
| 4.3 | Small angle X-ray scattering pattern of MCM-41 and MAS-GLU | 34 |
| 4.4 | Isotherm for a) MAS-GLU, b) MAS-SUC, c) MAS-LAC, d) MAS-WOT and e) MCM-41 | 38 |
| 4.5 | t-plot of a) MAS-GLU, b) MAS-SUC, c) MAS-LAC, d) MAS-WOT and e) MCM-41 | 39 |
| 4.6 | Maximum pore width distribution of a) MAS-GLU, b) MAS-SUC, c) MAS-LAC, d) MAS-WOT and e) MCM-41 | 40 |
| 4.7 | Plot of adsorption capacity versus time for MAS-WOT, MCM-41 and MAS-SUC | 43 |
| 4.8 | Adsorption capacity of MAS-WOT, MCM-41 and MAS-SUC at 60 minute adsorption time | 43 |
| 4.9 | Removal efficiency of MAS-WOT, MCM-41 and MAS-SUC at 60 minute adsorption time | 44 |

| | | |
|------|---|----|
| 4.10 | Plot of adsorption capacity versus time for MAS-WOT, MCM-41 and MAS-SUC | 45 |
| 4.11 | Plot of C_e/q_e versus C_e for paraquat adsorbed by MAS-WOT | 47 |
| 4.12 | Plot of C_e/q_e versus C_e for paraquat adsorbed by MCM-41 | 47 |
| 4.13 | Plot of C_e/q_e versus C_e for paraquat adsorbed by MAS-SUC | 48 |
| 4.14 | Plot of $\log q_e$ versus $\log C_e$ for paraquat adsorbed by MAS-WOT | 49 |
| 4.15 | Plot of $\log q_e$ versus $\log C_e$ for paraquat adsorbed by MCM-41 | 50 |
| 4.16 | Plot of $\log q_e$ versus $\log C_e$ for paraquat adsorbed by MAS-SUC | 50 |
| 4.17 | Desorption removal efficiency of MAS-WOT, MCM-41 and MAS-SUC | 52 |
| 4.18 | Desorption removal efficiency of MAS-WOT and MAS-SUC by different desorption method | 53 |

LIST OF ABBREVIATIONS

| | | |
|------------------|---|---|
| λ_{\max} | - | Maximum Absorption Wavelength |
| BSA | - | Bovine Serum Albumin |
| CE | - | Capillary Electrophoresis |
| CTABr | - | Cetyltrimethylammonium Bromide |
| FTIR | - | Fourier Transform Infrared Spectroscopy |
| IUPAC | - | International Union of Pure and Applied Chemistry |
| IZA | - | International Zeolite Association |
| MAA | - | Methacrylic Acid |
| MAS-GLU | - | Mesoporous aluminosilicate that synthesised with glucose template |
| MAS-LAC | - | Mesoporous aluminosilicate that synthesised with lactose template |
| MAS-SUC | - | Mesoporous aluminosilicate that synthesised with sucrose template |
| MAS-WOT | - | Mesoporous aluminosilicate that synthesised without saccharide template |
| MCM-41 | - | Mobil Crystalline Matter 41 |
| PAN | - | Pesticide Action Network |
| PUF | - | Polyurethane Foam |
| R^2 | - | Regression coefficient |
| SAXS | - | Small Angle X-ray Scattering |
| SDS | - | Sodium Dodecylsulfate |
| TEOS | - | Tetraethyl Orthosilicate |
| TPAOH | - | Tetrapropylammonium Hydroxide |
| USEPA | - | United States Environmental Protection Agency |

| | | |
|--------|---|---------------------------------------|
| UV | - | Ultraviolet |
| UV-vis | - | Ultraviolet-visible Spectrophotometer |
| XRD | - | X-ray diffraction |
| XRF | - | X-ray Fluorescence |
| WHO | - | World Health Organization |
| ZSM-5 | - | Zeolite Socony Mobile-5 |

LIST OF SYMBOLS

| | | |
|--------------------|---|---------------------------|
| Å | - | Armstrong |
| °C | - | Degree Celsius |
| % | - | Percent |
| µm | - | Micrometer |
| cm ⁻¹ | - | Per Centimeter |
| cm ³ /g | - | Cubic Centimeter per Gram |
| g | - | Gram |
| g/cm ³ | - | Gram per Cubic Centimeter |
| g/mol | - | Gram per Mol |
| K | - | Kelvin |
| L | - | Liter |
| M | - | Molar |
| m ² /g | - | Square Meter per Gram |
| mg | - | Milligram |
| mg/g | - | Milligram per Gram |
| mg/kg | - | Milligram per Kilogram |
| mg/L | - | Milligram per Liter |
| mg/mL | - | Milligram per Milliliter |
| mL | - | Milliliter |
| mm | - | Millimeter |
| ng/L | - | Nanogram per Liter |
| nm | - | Nanometer |
| rpm | - | Rate per Minute |

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Paraquat is a controversial pesticide under herbicide class that commonly used to control weeds. Even though the pesticide is very effective in controlling weeds however it gives adverse effect to human and environment. Paraquat is very toxic to human with lethal ingestion dosage 35 mg/kg (Extension Toxicology Network, 1993). Due to its toxicity, many poisoning cases due to paraquat were reported especially among agricultural workers (Fernandez *et al.*, 2002). Not only that, some people has misused its usage as a suicide agent because ingestion of less than one tea spoon can cause fatal (Madeley, 2002). Other than that, paraquat is reported as very persistent in soil environment with field half-life more than 1000 days and it also very toxic to some aquatic life (Madeley, 2002). Since paraquat is very dangerous to human and environment, its removal from the environment has becomes an interest for many researchers (Ait Sidhoum *et al.*, 2013; Majid *et al.*, 2016; Nanseu-Njiki *et al.*, 2010; Oliveira *et al.*, 2014; Tsai and Lai, 2006). One of method for removal of paraquat is by using suitable adsorbent such as silica (Brigante and Schulz, 2011), clay (Rytwo *et al.*, 2002; Ait Sidhoum *et al.*, 2013; Seki and Yurdakoç, 2005), polymer (Vinhai *et al.*, 2015) and resin (Leite *et al.*, 2013) so that the study on the ability of the adsorbent to adsorb paraquat and retained it from leached out has been performed. Besides that, study on adsorption and desorption of paraquat on adsorbent also can be applied for preconcentration method of forensic sample for suicide and poisoning cases that has trace amount of paraquat and small sample size.

Adsorbent like porous materials such as carbon, zeolites and mesoporous material has shown encouraging results for removal of paraquat. Porous materials can be divided into three categories namely microporous, mesoporous and macroporous. International Union of Pure and Applied Chemistry (IUPAC) has notated that microporous materials are materials that have pore diameters less than 2 nm while macroporous materials are for materials that have pore diameters more than 50 nm. Materials that fall under mesoporous category are those that have pore diameter that lies between 2 to 50 nm. Mesoporous material being a favour of researchers to synthesise because it has larger pore size without compromising the active sites that will promote more effective reactions. For adsorption purpose, mesoporous adsorbent will able to adsorb higher amount of analyte and larger size of compound.

Aluminosilicate is a type of material that build from element of aluminium, silicon and oxygen. The material has negative charge on the surface that come from isomorphous substitution of Al^{3+} ion for Si^{4+} ion in the silicate structure and due to dissociation of silanol groups in structural and adsorbed silicate (Perrott, 1977). This material can occur naturally or be synthesised. Zeolite is a hydrated microporous aluminosilicate material that has 3-dimensional framework with enclosing cavities and uniform channels, that occupied with water molecules and cations balancing the negatively charge of the aluminosilicate framework (Smith, 1963). This material is highly demand in industry because of its application as catalyst, adsorbent and molecular sieve (Ni *et al.*, 2011; Rutkowska *et al.*, 2015; Rasamimanana *et al.*, 2016; Jovanovic *et al.*, 2016; Razavian and Fatemi, 2015). Due to its microporous nature of zeolites, has limits its applications to smaller molecules. To enhance zeolites property for bigger molecules, many studies on converting the microporous material aluminosilicate material like zeolite to mesoporous material by using mesoporous directing agent have been done (Kadja *et al.*, 2016; Liu *et al.*, 2012; Sun *et al.*, 2015).

In this research, aluminosilicate materials having mesoporous properties was synthesised using saccharide template as mesoporous directing agent and used for adsorption and desorption of paraquat. Mesoporous aluminosilicate was chosen because it has negative charge while paraquat is positively charge, so it will be easy

for mesoporous aluminosilicate to bind with paraquat. Mesoporous silica MCM-41 was chosen as comparison to the result of adsorption and desorption of paraquat using mesoporous aluminosilicate material.

1.2 Statement of Problem

Paraquat is known to be dangerous to human and our environment. Suitable material can be used as adsorbent for preconcentration of trace amount and small sample size of paraquat and for removal of it in environment. Previous researches on adsorption of paraquat have used various type of adsorbent like clays, silica, polymer, resin, and soil. Clay is material that occur naturally and composed primarily of fine-grained minerals, which is generally plastic at appropriate water contents and will harden with dried or fired (Guggenheim and Martin, 1995). Some clay minerals consist of aluminium and silicon element and known as aluminosilicate material such as illite and bentonite mineral. Aluminosilicate material has negative charge on surface because of isomorphous substitution of Al^{3+} on Si^{4+} on the silicate structure arrangement. Paraquat is positively charge so theoretically, it can be easily bind with negatively charge aluminosilicate material and lead to effective adsorption process. Previous researches that had been done on adsorption of paraquat on aluminosilicate material only use naturally occurring aluminosilicate which is clay type materials such as bentonite, and illite, and modification of these type of materials (Seki and Yurdakoç, 2005; Ait Sidhoum *et al.*, 2013). The reported adsorption capacity range of these adsorbents is from 20 to 100 mg/g. However, this naturally occurring aluminosilicates and its modification form have a drawback since most of them were not fully characterised in order to understand the relation of the adsorption capacity with the physicochemical properties of the adsorbents. As such study need to be done using synthesised aluminosilicate material to study the relationship of the physicochemical property with adsorption capacity of paraquat.

Aluminosilicate such as zeolite is a hydrated microporous aluminosilicate material that can exist naturally or can be synthesised in the laboratory. As adsorbent for bigger molecule such as paraquat, the porous system of zeolite need to be

modified from micropores to mesopores and it can be done using mesoporous directing agent such as ammonium type surfactant (Chen *et al.*, 2010; Choopun and Jitkarnka, 2016; Ahmadpour and Taghizadeh, 2015; Teh *et al.*, 2015), carbon material (Koo *et al.*, 2010; Pavlačková *et al.*, 2006) and saccharide (Jin *et al.*, 2016; Ma *et al.*, 2013; Wang *et al.*, 2009; Zhang *et al.*, 2016) to improve its properties by having larger pore size so it can absorb higher amount of paraquat. Compare to another mesoporous directing agents, saccharide is less expensive and environmental friendly. By using synthesised aluminosilicate material such as zeolite with mesoporous characteristic, the adsorption capacity of paraquat on the adsorbents can be studied and compare to previous researches that had been done that use naturally occurring aluminosilicate material and its modified form.

1.3 Objective of Study

The objectives of this study are:

1. To synthesise different type of mesoporous aluminosilicate materials using various saccharide template.
2. To characterise the as-synthesised mesoporous materials to confirm the formation of synthesised materials.
3. To study the adsorption and desorption ability of paraquat on synthesised mesoporous materials.

1.4 Scope of Study

In this study, the mesoporous aluminosilicates were synthesised using saccharides templates as mesoporous directing agent namely glucose, sucrose and lactose. The mesoporous aluminosilicate without saccharide template also had been synthesised to compare the result between with and without presence of saccharide

template. The source of silica that was used is from tetraethyl orthosilicate (TEOS) and the alumina source comes from aluminium sulphate octadecahydrate, $\text{Al}_2(\text{SO}_4)_3 \cdot 18\text{H}_2\text{O}$. For MCM-41, the silica source that was used is Ludox solution and cetyltrimethylammonium bromide (CTABr) act as cationic surfactant.

The adsorption and desorption experiment was done in batch sorption method. The parameter that have been studied for adsorption part were adsorption time and initial concentration of paraquat. The isotherm of adsorption study was done based on the result of the initial concentration of paraquat parameter and analysed using Langmuir and Freundlich isotherm. Effect of different desorption method was studied for desorption part.

1.5 Significance of Study

The purpose of this study is to study the adsorption and desorption of paraquat on mesoporous materials. One of the significance of this research is the mesoporous material that has larger size of pores so it can absorb larger size of compound and higher amount of analyte. Other than that, aluminosilicate is negatively charged so it is good to be used as an adsorbent for adsorption of paraquat because paraquat is positively charged, so it will easily bind to aluminosilicate material. In this research, saccharide templates were used in synthesising mesoporous aluminosilicate as mesoporous directing agent and the advantages of using saccharides as template are there are cheap and environmental friendly template.

The other significance of this research is by studying the adsorption and desorption ability of synthesised mesoporous materials on paraquat, the materials can be applied as adsorbent for removal of paraquat in environment and for preconcentration of trace amount of paraquat in small sample size *i.e.* in forensic sample prior to analysis using less expensive instrument like ultraviolet-visible spectrophotometer that will reduce the cost of analysis.

REFERENCES

- Ahmadpour, J. and Taghizadeh, M. (2015). Catalytic Conversion of Methanol to Propylene over High-Silica Mesoporous ZSM-5 Zeolites Prepared by Different Combinations of Mesogenous Templates. *Journal of Natural Gas Science and Engineering*, 23, 184–194.
- Ait Sidhoum, D., Socías-Viciana, M. M., Ureña-Amate, M. D., Derdour, A., González-Pradas, E. and Debbagh-Boutarbouch, N. (2013). Removal of Paraquat from Water by an Algerian Bentonite. *Applied Clay Science*, 83–84, 441–448.
- Akhlaghian, F., Ghadermazi, M. and Chenarani, B. (2014). Removal of Phenolic Compounds by Adsorption on Nano Structured Aluminosilicates. *Journal of Environmental Chemical Engineering*, 2, 543–549.
- Al-Jammal, N., Al-Hamamre, Z. and Alnaief, M. (2016). Manufacturing of Zeolite Based Catalyst from Zeolite Tuft for Biodiesel Production from Waste Sunflower Oil. *Renewable Energy*, 93, 449–459.
- Brigante, M. and Avena, M. (2014). Synthesis, Characterization and Application of a Hexagonal Mesoporous Silica for Pesticide Removal from Aqueous Solution. *Microporous and Mesoporous Materials*, 191, 1–9.
- Brigante, M. and Schulz, P. C. (2011). Adsorption of Paraquat on Mesoporous Silica Modified with Titania: Effects of pH, Ionic Strength and Temperature. *Journal of Colloid and Interface Science*, 363, 355–361.
- Chen, G., Jiang, L., Wang, L. and Zhang, J. (2010). Synthesis of Mesoporous ZSM-5 by One-pot Method in the Presence of Polyethylene Glycol. *Microporous and Mesoporous Materials*, 134, 189–194.
- Choi, J. S., Kim, D. J., Chang, S. H. and Ahn, W. S. (2003). Catalytic Applications of MCM-41 with Different Pore Sizes in Selected Liquid Phase Reactions. *Applied Catalysis A: General*, 254, 225–237.

- Choopun, W. and Jitkarnka, S. (2016). Catalytic Activity and Stability of HZSM-5 Zeolite and Hierarchical Uniform Mesoporous MSU-SZSM-5 Material during Bio-ethanol Dehydration. *Journal of Cleaner Production*, 135, 368–378.
- Chuntib, P. and Jakmune, J. (2015). Simple Flow Injection Colorimetric System for Determination of Paraquat in Natural Water. *Talanta*, 144, 432–438.
- Da, J., Xiao, T., Su, J., Xu, X., Green, M. L. H. and Wolf, T. (2002). Preparation of MCM-41 in Industrial Scale and Its Application in Heavy Oil Processing, 18, 169–174.
- Enterría, M., Suárez-García, F., Martínez-Alonso, A. and Tascón, J. M. D. (2014). Preparation of Hierarchical Micro-Mesoporous Aluminosilicate Composites by Simple Y Zeolite/MCM-48 Silica Assembly. *Journal of Alloys and Compounds*, 583, 60–69.
- Extension Toxicology Network. (1993). Pesticide Information Profile: Paraquat.
- Fernandez, I., Thomas, E., Anthony, J. and Rengam, S. V. (2002). *Poisoned and Silenced*.
- Fogler, H. S. (2006). Collision Theory. In *Professional Reference Shelf*.
- Guggenheim, S. and Martin, R. T. (1995). Definition of Clay and Clay Mineral: Joint Report of the AIPEA Nomenclature and CMS Nomenclature Committees. *Clays and Clay Minerals*, 43, 255–256.
- Guthrie, C. P. and Reardon, E. J. (2016). Hydrogen Absorption in Palladized MCM-41. *Facets*, 1, 248–262.
- Hsu, S. T., Chen, L. C., Lee, C. C., Pan, T. C., You, B. X. and Yan, Q. F. (2009). Preparation of Methacrylic Acid-Modified Rice Husk Improved by an Experimental Design and Application for Paraquat Adsorption. *Journal of Hazardous Materials*, 171, 465–470.
- Hsu, S. T. and Pan, T. C. (2007). Adsorption of Paraquat Using Methacrylic Acid-Modified Rice Husk. *Bioresource Technology*, 98, 3617–3621.
- Isenring, R. (2006). *Paraquat: Unacceptable health risks for users. Berne Declaration, Pesticide Action Network UK and Pesticide Action Network Asia and the Pacific*.
- Jeyaratnam, J., Lun, K. C. and Phoon, W. (1987). Survey of Acute Pesticide Poisoning Among Agricultural Workers in Four Asian Countries, 65, 521–527.
- Jha, B. and Singh, D. N. (2016). Basics of Zeolites. *Fly Ash Zeolite*, 78.
- Jin, J., Zhang, X., Li, Y., Li, H., Wu, W., Cui, Y. and Shi, J. (2012). A Simple Route

- to Synthesize Mesoporous ZSM-5 Templated by Ammonium-modified Chitosan. *Chemistry - A European Journal*, 18, 16549–16555.
- Jin, L., Xie, T., Liu, S., Li, Y. and Hu, H. (2016). Controllable Synthesis of Chainlike Hierarchical ZSM-5 Templated by Sucrose and Its Catalytic Performance. *Catalysis Communications*, 75, 32–36.
- Jovanovic, M., Arcon, I., Kovac, J., Tusar, N. N., Obradovic, B. and Rajic, N. (2016). Removal of Manganese in Batch and Fluidized Bed Systems Using Beads of Zeolite A as Adsorbent. *Microporous and Mesoporous Materials*, 226, 378–385.
- Kadja, G. T. M., Mukti, R. R., Liu, Z., Rilyanti, M., Ismunandar, Marsih, I. N. and Okubo, T. (2016). Mesoprogen-free Synthesis of Hierarchically Porous ZSM-5 Below 100°C. *Microporous and Mesoporous Materials*, 226, 344–352.
- Khalid, A., Dewayanto, N., Du, D., Hasbi, M. and Rahim, A. (2016). Novel Modified ZSM-5 as an Efficient Adsorbent for Methylene Blue Removal. *Journal of Environmental Chemical Engineering*, 4, 2607–2616.
- Khatamian, M. and Irani, M. (2009). Preparation and Characterization of Nanosized ZSM-5 Zeolite Using Kaolin and Investigation of Kaolin Content, Crystallization Time and Temperature Changes on the Size and Crystallinity of Products. *Journal of the Iranian Chemical Society*, 6, 187–194.
- Koo, J. B., Jiang, N., Saravanamurugan, S., Bejblova, M., Musilova, Z., Čejka, J. and Park, S. E. (2010). Direct Synthesis of Carbon-Templating Mesoporous ZSM-5 Using Microwave Heating. *Journal of Catalysis*, 276, 327–334.
- Kreethawate, L., Larpkiattaworn, S., Phonnoi, J. and Tong-On, S. (2016). Zeolite Layer Synthesized on Porous Alumina Substrate for Water/Methanol Separation. *Surface and Coatings Technology*, 2–5.
- Lee, C. K., Liu, S. S., Juang, L. C., Wang, C. C., Lin, K. S. and Lyu, M. Du. (2007). Application of MCM-41 for Dyes Removal from Wastewater. *Journal of Hazardous Materials*, 147, 997–1005.
- Leite, M. P., dos Reis, L. G. T., Robaina, N. F., Pacheco, W. F. and Cassella, R. J. (2013). Adsorption of Paraquat from Aqueous Medium by Amberlite XAD-2 and XAD-4 Resins Using Dodecylsulfate as Counter Ion. *Chemical Engineering Journal*, 215–216, 691–698
- Liu, B., Li, C., Ren, Y., Tan, Y., Xi, H. and Qian, Y. (2012). Direct Synthesis of Mesoporous ZSM-5 Zeolite by a Dual-Functional Surfactant Approach.

- Chemical Engineering Journal*, 210, 96–102.
- Liu, M., Hou, L. A., Xi, B., Zhao, Y. and Xia, X. (2013). Synthesis, Characterization, and Mercury Adsorption Properties of Hybrid Mesoporous Aluminosilicate Sieve Prepared with Fly Ash. *Applied Surface Science*, 273, 706–716.
- Luo, Y., Hou, Z., Li, R. and Zheng, X. (2008). Synthesis of Ultrastable Ordered Mesoporous Aluminosilicates Molecular Sieves with “Hard Template.” *Microporous and Mesoporous Materials*, 110, 583–589.
- Ma, Y., Hu, J., Jia, L., Li, Z., Kan, Q. and Wu, S. (2013). Synthesis, Characterization and Catalytic Activity of a Novel Mesoporous ZSM-5 Zeolite. *Materials Research Bulletin*, 48, 1881–1884.
- Madeley, J. (2002). *Paraquat – Syngenta’s controversial herbicide. Berne Declaration, Swedish Society for Nature Conservation, Pesticide Action Network UK, Pesticide Action Network Asia Pacific and Foro Emaús.*
- Majid, Z. A., Zakaria, N. F., Ramli, Z., Ali, R., Jaafar, J. and Aris, A. (2016). Adsorbent from Waste and Natural Deposits for Paraquat Removal in Water. *Malaysian Journal of Analytical Sciences*, 20, 469–476.
- Mehdi, S., Halimah, M., Nashriyah, M. and Ismail, B. S. (2009). Adsorption and Desorption of Paraquat in Two Malaysian Agricultural Soils. *American-Eurasian Journal of Sustainable Agriculture*, 3, 555–560.
- Nanseu-Njiki, C. P., Dedzo, G. K. and Ngameni, E. (2010). Study of the Removal of Paraquat from Aqueous Solution by Biosorption onto Ayous (*Triplochiton Schleroxylon*) Sawdust. *Journal of Hazardous Materials*, 179, 63–71.
- Ni, Y., Sun, A., Wu, X., Hai, G., Hu, J., Li, T. and Li, G. (2011). The Preparation of Nano-Sized H[Zn, Al]ZSM-5 Zeolite and Its Application in the Aromatization of Methanol. *Microporous and Mesoporous Materials*, 143, 435–442.
- Noicharoen, D., Parkpian, P., Shipin, O. V, Polprasert, C., Delaune, R. D. and Kongchum, M. (2012). Effect of Salinity on Adsorption and Desorption of Paraquat in Pak Phanang River Sediment, Thailand. *Journal of Environmental Science and Health. Part A, Toxic/hazardous Substances & Environmental Engineering*, 47, 1897–908.
- Núñez, O., Kim, J. B., Moyano, E., Galceran, M. T. and Terabe, S. (2002). Analysis of the Herbicides Paraquat, Diquat and Difenzoquat in Drinking Water by Micellar Electrokinetic Chromatography Using Sweeping and Cation Selective Exhaustive Injection. *Journal of Chromatography A*, 961, 65–75.

- Nur Izzati Hazira Hashim. (2010). *Pesticide Poisoning Pattern on Admissions at Hospital Melaka*. Bachelor Thesis, Universiti Teknologi MARA.
- Oliveira, C., Gruskevica, K., Juhna, T., Tihomirova, K., Alves, A. and Madeira, L. M. (2014). Removal of paraquat pesticide with Fenton reaction in a pilot scale water system. *Drinking Water Engineering and Science*, 7, 11–21.
- Parangi, T. F., Patel, R. M. and Chudasama, U. V. (2014). Synthesis and Characterization of Mesoporous Si-MCM-41 Materials and Their Application as Solid Acid Catalysts in Some Esterification Reactions. *Bulletin of Materials Science*, 37, 609–615.
- Pateiro-Moure, M., Arias-Estévez, M. and Simal-Gándara, J. (2010). Competitive and Non-Competitive Adsorption/Desorption of Paraquat, Diquat and Difenzoquat in Vineyard-Devoted Soils. *Journal of Hazardous Materials*, 178, 194–201.
- Pavlačková, Z., Košová, G., silková, N., Zukal, A. and Čejka, J. (2006). Formation of Mesopores in ZSM-5 by Carbon Templating. *Studies in Surface Science and Catalysis*, 162, 905–912.
- Perrott, K. W. (1977). Surface Charge Characteristics of Amorphous Aluminosilicates. *Clays and Clay Minerals*, 25, 417–421.
- Pesticide Action Network Germany. (2011). PAN International List of Highly Hazardous Pesticides, 16.
- Pesticide Action Network Germany. (2003). *Paraquat and Suicide. Pestizid Aktions-Netzwerk e.V. (PAN Germany)*.
- Pinkas, J. (2005). Chemistry of Silicates and Aluminosilicates. *Ceramics-Silikaty*, 49, 287–298.
- Qoniah, I., Prasetyoko, D., Bahruji, H., Triwahyono, S., Jalil, A. A., Suprpto, Hartati and Purbaningtias. T. E. (2015). Direct Synthesis of Mesoporous Aluminosilicates from Indonesian Kaolin Clay without Calcination. *Applied Clay Science*, 118, 290–294.
- Rajasuriar, R., Awang, R., Hashim, S. B. H. and Rahmat, H. R. B. H. (2007). Profile of Poisoning Admissions in Malaysia. *Human & Experimental Toxicology*, 26, 73–81.
- Rasamimanana, S., Mignard, S. and Batonneau-Gener, I. (2016). Hierarchical Zeolites as Adsorbents for Mesosulfuron-Methyl Removal in Aqueous Phase. *Microporous and Mesoporous Materials*, 226, 153–161.

- Razavian, M. and Fatemi, S. (2015). Synthesis and Application of ZSM-5/SAPO-34 and SAPO-34/ZSM-5 Composite Systems for Propylene Yield Enhancement in Propane Dehydrogenation Process. *Microporous and Mesoporous Materials*, 201, 176–189.
- Rhodes, C. J. (2010). Properties and Applications of Zeolites. *Science Progress*, 93, 223–284.
- Rutkowska, M., Macina, D., Mirocha-Kubien, N., Piwowarska, Z. and Chmielarz, L. (2015). Hierarchically Structured ZSM-5 Obtained by Desilication as New Catalyst for DME Synthesis from Methanol. *Applied Catalysis B: Environmental*, 174–175, 336–343.
- Rytwo, G., Tropp, D. and Serban, C. (2002). Adsorption of Diquat, Paraquat and Methyl Green on Sepiolite: Experimental Results and Model Calculations. *Applied Clay Science*, 20, 273–282.
- Sazaroni, M. R., Awang, R., Zyoud, S. H., Haslina, H., Adilah, M. A. and Asdariah, M. (2011). Review on Paraquat Poisoning in Malaysia after Lifting of Ban. *J. Med. Toxicol.*, 10, 1.
- Seki, Y. and Yurdakoç, K. (2005). Paraquat Adsorption onto Clays and Organoclays from Aqueous Solution. *Journal of Colloid and Interface Science*, 287, 1–5.
- Sepehrian, H., Ahmadi, S. J., Waqif-Husain, S., Faghihian, H. and Alighanbari, H. (2010). Adsorption Studies of Heavy Metal Ions on Mesoporous Aluminosilicate, Novel Cation Exchanger. *Journal of Hazardous Materials*, 176, 252–256.
- Smith, J. V. (1963). Structural Classification of Zeolites. *Mineralogical Society of America, Special Paper 1. International Mineralogical Association, Papers, Third General Meeting*.
- Smith, J. V. (1984). Definition of a Zeolite. *Zeolites*, 4, 309–310.
- Sun, C., Zhang, F., Wang, A., Li, S. and Cheng, F. (2015). Direct Synthesis of Mesoporous Aluminosilicate Using Natural Clay from Low-Grade Potash Ores of a Salt Lake in Qinghai, China, and Its Use in Octadecylamine Adsorption. *Applied Clay Science*, 108, 123–127.
- Tcheumi, H. L., Tonle, I. K., Walcarius, A. and Ngameni, E. (2012). Electrocatalytic and Sensors Properties of Natural Smectite Type Clay towards the Detection of Paraquat Using a Film-Modified Electrode. *American Journal of Analytical Chemistry*, 3, 746–754.

- Teh, L. P., Triwahyono, S., Jalil, A. A., Mukti, R. R., Aziz, M. A. A. and Shishido, T. (2015). Mesoporous ZSM5 having both Intrinsic Acidic and Basic Sites for Cracking and Methanation. *Chemical Engineering Journal*, 270, 196–204.
- Treacy, M. M. J. and Higgins, J. B. (2001). Collection of Simulated XRD Powder Patterns for Zeolites. *Elsevier*, 13.
- Tsai, W. T., Hsien, K. J., Chang, Y. M. and Lo, C. C. (2005). Removal of Herbicide Paraquat from an Aqueous Solution by Adsorption onto Spent and Treated Diatomaceous Earth. *Bioresource Technology*, 96, 657–663.
- Tsai, W. T. and Lai, C. W. (2006). Adsorption of Herbicide Paraquat by Clay Mineral Regenerated from Spent Bleaching Earth. *Journal of Hazardous Materials*, 134, 144–148.
- United States Environmental Protection Agency. (1997). R . E . D . Facts.
- Vadia, N. and Sadhana, R. (2011). Mesoporous Material, MCM-41: a New Drug Carrier. *Asian Journal of Pharmaceutical and Clinical Research*, 4, 44–53.
- Vanea, E. and Simon, V. (2011). XPS Study of Protein Adsorption onto Nanocrystalline Aluminosilicate Microparticles. *Applied Surface Science*, 257, 2346–2352.
- Vinhal, J. O., Lage, M. R., Carneiro, J. W. M., Lima, C. F. and Cassella, R. J. (2015). Modeling, Kinetic, and Equilibrium Characterization of Paraquat Adsorption onto Polyurethane Foam Using the Ion-Pairing Technique. *Journal of Environmental Management*, 156, 200–208.
- Wade, L. G. (2010). *Organic Chemistry*. (7th ed.). Pearson Education, Inc.
- Wai, K. C. (2015). *Luminol Immobilized Mesoporous Silica MCM-41 as Chemosensor for Ferrum(III) Ion*. Bachelor Thesis, Universiti Teknologi Malaysia.
- Wang, L., Wang, Y., Wang, A., Li, X., Zhou, F. and Hu, Y. (2013). Highly Acidic Mesoporous Aluminosilicates Assembled from Zeolitic Subunits Generated by Controllable Desilication of ZSM-5 in Na₂SiO₃ Solution. *Microporous and Mesoporous Materials*, 180, 242–249.
- Wang, L., Yin, C., Shan, Z., Liu, S., Du, Y. and Xiao, F. S. (2009). Bread-Template Synthesis of Hierarchical Mesoporous ZSM-5 Zeolite with Hydrothermally Stable Mesoporosity. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 340, 126–130.
- Watts, M. (2011). *Paraquat. Pesticide Action Network Asia and the Pacific*.

- White, R. J., Fischer, A., Goebel, C. and Thomas, A. (2011). A Sustainable Template for Mesoporous Zeolite Synthesis. *Green Chem.*, 13, 2428.
- Winek, C. L. and Wahba, W. W. (2001). Winek' s Drug & Chemical Blood-Level Data 2001.
- World Health Organization. (2006). Pesticides are a Leading Suicide Method.
- World Health Organization. (2010). The WHO Recommended Classification of Pesticides by Hazard and Guidelines to Classification 2009. *World Health Organization*, 1–60.
- Wu, X. W., Ma, H. W., Li, J. H., Zhang, J. and Li, Z. H. (2007). The Synthesis of Mesoporous Aluminosilicate Using Microcline for Adsorption of Mercury(II). *Journal of Colloid and Interface Science*, 315, 555–561.
- Wu, X. W., Ma, H. W. and Zhang, Y. R. (2010). Adsorption of Chromium(VI) from Aqueous Solution by a Mesoporous Aluminosilicate Synthesized from Microcline. *Applied Clay Science*, 48, 538–541.
- Xu, L., Liu, Z., Li, Z., Liu, J., Ma, Y., Guan, J. and Kan, Q. (2011). Non-Crystalline Mesoporous Aluminosilicates Catalysts: Synthesis, Characterization and Catalytic Applications. *Journal of Non-Crystalline Solids*, 357, 1335–1341.
- Yang, B., Liu, Y. and Li, M. (2016). Separation of CO₂–N₂ Using Zeolite NaKA with High Selectivity. *Chinese Chemical Letters*, 27, 933–937.
- Yoo, W. C., Zhang, X., Tsapatsis, M. and Stein, A. (2012). Synthesis of Mesoporous ZSM-5 Zeolites Through Desilication and Re-Assembly Processes. *Microporous and Mesoporous Materials*, 149, 147–157.
- Yutthalekha, T., Wattanakit, C., Warakulwit, C., Wannapakdee, W., Rodponthukwaji, K., Witoon, T. and Limtrakul, J. (2016). Hierarchical FAU-Type Zeolite Nanosheets as Green and Sustainable Catalysts for Benzylolation of Toluene. *Journal of Cleaner Production*, 1–8.
- Zainab Ramli. (1995). *Rhenium-Impregnated Zeolites: Synthesis, Characterization and Modification as Catalysts in the Metathesis of Alkenes*. PhD Thesis, Universiti Teknologi Malaysia.
- Zhang, M., Liu, X. and Yan, Z. (2016). Soluble Starch as In-Situ Template to Synthesize ZSM-5 Zeolite with Intracrystal Mesopores. *Materials Letters*, 164, 543–546.
- Zhou, C., Sun, T., Gao, Q., Alshameri, A., Zhu, P., Wang, H., Qiu, X., Ma, Y. and Yan, C. (2014). Synthesis and Characterization of Ordered Mesoporous

Aluminosilicate Molecular Sieve from Natural Halloysite. *Journal of the Taiwan Institute of Chemical Engineers*, 45, 1073–1079.