SYNTHESIS AND CHARACTERIZATION OF SURFACE MODIFIED BANANA TRUNK AS ADSORBENT FOR BENZENE REMOVAL FROM AQUEOUS SOLUTION

HELEN KONG

UNIVERSITI TEKNOLOGI MALAYSIA

SYNTHESIS AND CHARACTERIZATION OF SURFACE MODIFIED BANANA TRUNK AS ADSORBENT FOR BENZENE REMOVAL FROM AQUEOUS SOLUTION

HELEN KONG

A thesis submitted in fulfilment of the requirements for the award of the degree of Doctor of Philosophy (Chemical Engineering)

Faculty of Chemical and Energy Engineering Universiti Teknologi Malaysia

MAY 2017

To my beloved family

ACKNOWLEDGEMENT

I would like to express my utmost appreciation to my supervisor Assoc. Prof. Dr. Hanapi Mat for his constructive advice, support and time in the completion of this thesis. The guidance I received from him motivated me to push forward and guided me to the correct directions. Special thanks to my beloved family and best friends for their unconditional support and encouragement which help during my time of needs.

I am truly grateful to my lab-mates and seniors in Advanced Materials and Process Engineering (AMPEN) Research Laboratory for their support. I appreciate all the experience and fun we had in the laboratory. I would like to acknowledge the financial support from the UTM scholarships (Zamalah UTM). I would also like to thank the UTM's staffs and technician who has provided me all the necessary facilities throughout my research.

ABSTRACT

Petroleum monoaromatics especially benzene contamination in water and wastewater is the major concern in the industry today. Various removal techniques have been studied. The adsorptive removal process is considered as one of the most cost-efficient and feasible methods because it does not require a large amount of energy and additional chemical. In adsorption technology, several problems such as adsorbent cost, adsorption selectivity and adsorbent reusability are the main concerns. Therefore, the potential conversion and modification of agrowaste adsorbent into an effective adsorbent alternative to removing benzene constituent from the wastewater were studied. The banana trunk (BT) was selected as an agrowaste model in the present study. The raw BT (Raw-BT) was first mercerized and this mercerized BT (M-BT) was then reacted with different surfactants, namely cetyltrimethylammonium bromide, (M-CTAB-BT), 4-(1,1,3,3-tetramethylbutyl)phenyl-polyethylene glycol. CTAB Triton X-100 (M-TX100-BT) and sodium dodecyl sulfate, SDS (M-SDS-BT). Surface etherification by using 3-chloro-2-hydroxypropyl was also conducted trimethylammonium chloride, CTA with the mass ratio of 1 and this etherified BT (M-1CTA-BT) was then coated with SDS (M-1CTA-SDS-BT). All the adsorbents were characterized by using a Fourier transform infrared spectrometer, a field emission scanning electron microscope, an x-ray photoelectron spectroscopy analyzer and nitrogen adsorption/desorption analysis. The experimental batch adsorption studies showed that the adsorption capacity increased in the following order: Raw-BT < M-BT < M-CTAB-BT < M-TX100-BT < M-1CTA-SDS-BT. The Langmuir maximum benzene adsorption capacity, q_{Lmax} achieved by the M-1CTA-SDS-BT was 468.187×10^{-3} mmol/g. The fundamental adsorption equilibrium and kinetic studies revealed that the benzene adsorption data were fitted well into the Langmuir isotherm and pseudo-second order kinetic models which suggested that the adsorption process was governed by a physical phenomenon. The film diffusion was considered as the rate-limiting step for the overall benzene adsorption process. The adsorbents were chemically stable within the pH range. It was revealed the benzene adsorption was an endothermic and non-spontaneous process. The regeneration study using 50 % ethanol-water as the desorbing agent, demonstrated that the modified adsorbents could withstand five adsorption/desorption cycles without a drastic reduction of adsorption uptake (8.5 - 13.0%). The BT could potentially be employed as an adsorbent precursor for benzene adsorptive removal from aqueous solution.

ABSTRAK

Pencemaran monoaromatik petroleum terutamanya benzena dalam air dan air sisa adalah kebimbangan utama dalam industri hari ini. Pelbagai teknik penyingkiran telah dikaji. Proses penjerapan merupakan salah satu kaedah yang paling cekap dari segi kos kerana ia tidak memerlukan banyak tenaga dan bahan kimia tambahan. Dalam teknologi penjerapan, beberapa masalah seperti kos bahan penjerap, pemilihan penjerapan dan kebolehan gunapakai bahan penjerap adalah persoalan utama. Oleh itu, potensi penukaran dan pengubahsuaian sisa-sisa pertanian sebagai bahan penjerap pilihan yang berkesan untuk menyingkir juzuk benzena dari air sisa telah dikaji. Batang pisang (BT) telah dipilih sebagai satu model sisa pertanian dalam kajian ini. Batang pisang mentah (Raw-BT) telah dimerserais dahulu dan BT merserais ini (M-BT) telah bertindak balas dengan bahan permukaan yang berbeza seperti setiltrimetilammonium bromida, CTAB (M-CTAB-BT), 4-(1,1,3,3tetrametilbutil)fenil-polietilena glikol, Triton X-100 (M-TX100-BT) dan natrium dodesil sulfat, SDS (M-SDS-BT). Pengeteran permukaan juga telah dijalankan dengan menggunakan 3-kloro-2-hidroksilpropil trimetilammonium klorida, CTA dengan nisbah jisim 1 dan BT yang melalui proses pengeteran ini (M-1CTA-BT) telah kemudiannya disalut dengan SDS (M-1CTA-SDS-BT) kemudian. Semua bahan penjerap dicirikan dengan menggunakan spektrometer inframerah transformasi Fourier, mikroskop elektron pengimbas pancaran medan, penganalisis spektroskopi fotoelektron sinar-x dan analisis penjerapan/penyahjerapan nitrogen. Eksperimen penjerapan secara kelompok menunjukkan bahawa kapasiti penjerapan meningkat mengikut urutan berikut: Raw-BT < M-BT < M-CTAB-BT < M-TX100-BT < M-1CTA-SDS-BT. Kapasiti penjerapan benzena maksimum untuk model Langmuir yang dicapai oleh M-1CTA-SDS-BT adalah 468.187 \times 10⁻³ mmol/g. Kajian penjerapan telah menggambarkan bahawa seluruh data penjerapan benzena mengikuti model garis sesuhu Langmuir dan model kinetik pseudo kedua yang mencadangkan bahawa proses penjerapan ini mematuhi fenomena fizikal. Peresapan filem dianggap sebagai langkah pembatas kadar bagi keseluruhan proses penjerapan benzena. Bahan penjerap adalah stabil secara kimia dalam julat pH. Kajian ini menunjukkan bahawa proses penjerapan benzena ini adalah proses endoterma yang tidak berlaku secara spontan. Kajian penjana semula bahan penjerap dijalankan dengan menggunakan 50 % larutan etanolair sebagai agen penyahjerapan. Keputusan kajian ini menunjukkan bahawa bahan penjerap yang diubahsuai dapat bertahan lima kitaran penjerapan/penyahjerapan tanpa pengurangan kapasiti penjerapan yang melampau (hanya 8.5 - 13.0 %). BT adalah sangat berpotensi untuk digunakan sebagai pelopor bahan penjerap untuk menjerap unsur benzena daripada larutan berair.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	V
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xiii
	LIST OF FIGURES	XV
	LIST OF SYMBOLS	xix
	LIST OF ABBREVIATIONS	xxi
	LIST OF APPENDICES	xxiii
1	INTRODUCTION	1
	1.1 Research Background	1
	1.2 Problem Statement	3
	1.3 Research Objectives	6
	1.4 Research Scopes	6
	1.5 Thesis Outline	7
	1.6 Summary	7
2	LITERATURE REVIEW	9
	2.1 Benzene in the Environment	9
	2.1.1 Introduction	9
	2.1.2 Chemical and physical properties of benzene	9

	2.1.3	Sources of benzene contamination	11
	2.1.4	Health effects caused by benzene	12
	2.1.5	Benzene analysis	13
2.2	Benze	ene Removal Technologies	14
	2.2.1	Introduction	14
	2.2.2	Bioremediation	14
	2.2.3	Wet air oxidation	15
	2.2.4	Membrane filtration	15
	2.2.5	Adsorption	16
2.3	Benze	ene Removal by Adsorption	16
	2.3.1	Introduction	16
	2.3.2	Benzene adsorbents	17
		2.3.2.1 Carbonaceous materials	17
		2.3.2.2 Silica materials	20
		2.3.2.3 Clay materials	23
		2.3.2.4 Zeolite and zeolite-like materials	24
		2.3.2.5 Polymeric materials	27
	2.3.3	Banana trunk as adsorbent precursor	33
		2.3.3.1 Introduction	33
		2.3.3.2 Origin and properties	33
		2.3.3.3 Adsorbent modification	35
2.4	Adsor	rption Fundamentals	41
	2.4.1	Adsorption parameters	41
	2.4.2	Adsorption isotherms	43
	2.4.3	Thermodynamic parameters	49
	2.4.4	Adsorption kinetics	51
	2.4.5	Adsorption mechanism	57
	2.4.6	Adsorbent regeneration	58
2.5	Sumn	nary	59
MA	TERI	ALS AND METHODS	60
3.1	Introd	luction	60
3.2	Mater	rials	62

3

viii

3.3	Adsor	rbent Syr	nthesis Procedures	63
	3.3.1	Introduc	ction	63
	3.3.2	Physica	l modification of agrowaste	63
	3.3.3	Surface	mercerization of BT adsorbent	64
	3.3.4	Chemic surfacta	al modification of BT adsorbents by nts	64
	3.3.5	Etherifi	cation of BT adsorbents	65
3.4	Adsor	rbent Cha	aracterization	65
	3.4.1	Microst	ructure determination	65
	3.4.2	Surface	chemistry	65
	3.4.3	Surface determin	area and pore diameter nation	66
3.5	Benze	ene Adso	rption Procedure	67
	3.5.1	Preparat	tion of benzene solution	67
	3.5.2	Adsorpt	ion experiment	67
	3.5.3	Desorpt	ion experiment	68
3.6	Analy	tical Pro	cedures	69
	3.6.1	pH dete	rmination	69
	3.6.2	Benzene	e concentration determination	69
	3.6.3	Surfacta	ant concentration determination	69
3.7	Error	analysis		70
3.8	Sumn	nary		71
RES	SULT	S AND I	DISCUSSIONS	73
4.1	Introc	luction		73
4.2	Catio	nic Sur	factant-Coated-Mercerized Banana	
	Trunk	c Adsorb	ents	74
	4.2.1	Adsorbe	ent characterization	74
		4.2.1.1	Surface morphology	74
		4.2.1.2	Functional groups	75
		4.2.1.3	Chemical state of adsorbent surfaces	76
		4.2.1.4	Surface area and pore property	78
		4.2.1.5	Benzene adsorption capacity	79

4.2.2	CTAB a	adsorption characteristics	80
	4.2.2.1	Effect of CTAB initial concentrations	80
	4.2.2.2	CTAB adsorption isotherm model analysis	81
	4.2.2.3	Effect of contact time	83
	4.2.2.4	CTAB adsorption kinetic model analysis	84
4.2.3	Batch b	enzene adsorption studies	86
	4.2.3.1	Effects of CTAB loading capacity	86
	4.2.3.2	Effect of benzene initial concentration	87
	4.2.3.3	Benzene adsorption isotherm model analysis	89
	4.2.3.4	Effect of contact time	91
	4.2.3.5	Benzene adsorption kinetic model analysis	92
4.2.4	Adsorpt	tion mechanism	96
4.2.5	Adsorbe	ent regeneration	98
Non-l	lonic Su	rfactant-Coated-Mercerized Banana	
Trunk	Adsorb	ents	99
4.3.1	Adsorbe	ent characterization	99
	4.3.1.1	Surface morphology	99
	4.3.1.2	Functional groups	101
	4.3.1.3	Benzene adsorption capacity	103
	4.3.1.4	Surface area and pore property	104
	4.3.1.5	Chemical state of the adsorbent surface	104
4.3.2	Batch b	enzene adsorption studies	107
	4.3.2.1	Effect of pH	107
	4.3.2.2	Effect of benzene initial concentration and adsorbent dosage	108
	4.3.2.3	Isotherm model analysis	109
	4.3.2.4	Effect of temperature and contact time	112

4.3

х

		4.3.2.5	Thermodynamic parameter analysis	113
		4.3.2.6	Kinetic model analysis	114
	4.3.3	Adsorpt	tion mechanism	119
	4.3.4	Adsorpt	ion regeneration	120
4.4	Anior	nic Su	rfactant-Coated-Etherified Banana	
	Trunk	c Adsorb	ents	121
	4.4.1	Adsorbe	ent characterization	121
		4.4.1.1	Surface morphology	121
		4.4.1.2	Functional groups	122
		4.4.1.3	Chemical state of adsorbent surfaces	125
		4.4.1.4	Surface area and pore property	127
	4.4.2	Batch b	enzene adsorption studies	127
		4.4.2.1	Effect of surface etherification	127
		4.4.2.2	Effect of pH	129
		4.4.2.3	Effect of benzene initial concentration and adsorbent dosage	130
		4.4.2.4	Isotherm model analysis	131
		4.4.2.5	Effect of temperature and contact time	134
		4.4.2.6	Thermodynamic parameters analysis	135
		4.4.2.7	Kinetic model analysis	136
	4.4.3	Adsorpt	ion mechanism	141
	4.4.4	Adsorbe	ent regeneration	141
4.5	Comp Based	oarative l Adsorbo	Adsorption Studies of Agrowaste ents	143
4.6	Sumn	nary		144
CO	NCLU	ISION A	ND RECOMMENDATIONS	146
5.1	Sumn	nary of R	esearch Findings	146
5.2	Recor	nmendat	ion for Future Research	149
5.3	Concl	luding Re	emark	150

5

REFERENCES	152
Appendices A - E	176 - 197

LIST OF TABLES

TABLE NO.

TITLE

PAGE

2.1	A summary of benzene properties.	10
2.2	Benzene content in produced water (Neff et al., 2011b).	12
2.3	Maximum allowable BTEX contents in drinking water.	13
2.4	A summary of benzene adsorption capacity of carbonaceous materials.	19
2.5	A summary of benzene adsorption capacity, q (mmol/g) of silica materials.	22
2.6	A summary of benzene adsorption capacity, q (mmol/g) of clay materials.	24
2.7	A summary of benzene adsorption capacity, q (mmol/g) of zeolites and zeolite materials.	26
2.8	A summary of benzene adsorption capacity, q (mmol/g) of polymeric materials.	28
2.9	A summary of conventional adsorbents for VOCs adsorptive removal.	30
2.10	Holocellulose and lignin content of banana pseudo stem, coconut coir, rice straw, rice husk, corncob.	34
2.11	A summary of common adsorbent modification technologies.	36
2.12	Adsorption parameters.	41
2.13	Adsorption isotherm models (Park et al., 2010).	44
2.14	Best fitted adsorption isotherm models.	47
2.15	Thermodynamic parameters of benzene adsorption onto adsorbents.	50
2.16	Reaction based adsorption kinetic models.	55
2.17	Best fitted reaction based adsorption kinetic models and parameters.	56

3.1	Summary of the synthesized banana trunk (BT) adsorbents.	63
4.1	The FTIR wavenumber (cm ⁻¹) of various functional groups.	75
4.2	Specific surface area, pore diameter and pore volume of the adsorbents.	79
4.3	Isotherm model parameters for CTAB loading capacity analysis.	82
4.4	Kinetic model parameters for CTAB loading rate analysis.	85
4.5	Isotherm model parameters obtained from benzene adsorption isotherm analysis.	90
4.6	Kinetic model parameters obtained from benzene adsorption kinetic analysis.	93
4.7	FTIR wavenumber (cm ⁻¹) of various functional groups.	101
4.8	Specific surface area, pore diameter and pore volume of the adsorbents.	104
4.9	Isotherm model parameters obtained from benzene adsorption isotherm data analysis.	110
4.10	Thermodynamic parameters for benzene adsorptive by M-TX100-BT.	114
4.11	Kinetic parameters obtained from benzene adsorption kinetic data analysis.	117
4.12	FTIR wavenumber (cm ⁻¹) of various functional groups.	123
4.13	Specific surface area, pore diameter and pore volume of the adsorbents.	127
4.14	Isotherm model parameters obtained from benzene adsorption isotherm data analysis.	133
4.15	Thermodynamic parameters for adsorption by M-1CTA-SDS-BT.	135
4.16	Kinetic parameters obtained from benzene adsorption kinetic data analysis.	138
4.17	Benzene adsorption capacity comparison among agrowaste adsorbents.	143

LIST OF FIGURES

FIGURE NO.

TITLE

3.1	Flowchart of research activities.	61
3.2	Chemical formula and molecular structure of (a) CTAB, (b) Triton-X 100, (c) SDS, (d) CTA, and (e) Pluronic 123.	
		62
4.1	FESEM image of (a) Raw-BT, (b) M-BT and (c) M-CTAB-BT.	74
4.2	FTIR spectrum of (a) Raw-BT, (b) M-BT and (c) M-CTAB-BT.	76
4.3	An XPS wide scan of (a) Raw-BT, (b) M-BT and (c) M-CTAB-BT.	77
4.4	A high resolution XPS spectrum of the adsorbent: (a) O_{1s} ; (b) N_{1s} and (c) C_{1s} .	78
4.5	Benzene adsorption capacity of the synthesized adsorbents (Experimental conditions: initial benzene concentration (C ₀), 1.0 mmol/L; contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 0.5 mg/mL).	80
4.6	Effect of initial CTAB concentrations on CTAB loading capacity (Experimental conditions: contact time (t), 2 h; pH, 7; temperature (T), 303 K; and dosage (S/L), 2 mg/mL).	81
4.7	Isotherm model analysis of CTAB adsorption equilibrium data.	83
4.8	CTAB adsorption rate of the Raw-BT and M-BT at several CTAB concentration (Experimental conditions: initial CTAB concentration (C_0), 0.1, 1.0 and 5.0 mmol/L; pH, 7; temperature (T), 303 K; and dosage (S/L), 2 mg/mL).	84
4.9	Kinetics of CTAB adsorption onto Raw-BT and M-BT adsorbents (Experimental conditions: initial CTAB	

	concentration (C ₀), 1.0 mmol/L; pH, 7; temperature (T), 303 K; and dosage (S/L), 2 mg/mL).	86
4.10	Effects of CTAB loading capacity on benzene adsorption capacity (Experimental conditions: initial benzene concentration (C ₀), 1.0 mmol/L; contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 0.5 mg/mL).	87
4.11	Effect of initial benzene concentrations on benzene adsorption capacity (Experimental conditions: contact time (t), 24 h; pH, 7; temperature (T), 303K; and dosage (S/L), 0.5 mg/mL. (b) Isotherm model analysis of benzene adsorption equilibrium data).	88
4.12	Isotherm model analysis of benzene adsorption equilibrium data.	91
4.13	Benzene adsorption rate of Raw-BT, CTAB-BT and M-CTAB-BT and kinetic modeling analysis (Experimental conditions: initial benzene concentration (C ₀), 1.0 mmol/L; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 0.5 mg/mL).	92
4.14	Intraparticle/Weber-Morris plots of benzene adsorption kinetic data.	95
4.15	Adsorption performance of M-CTAB-BT as a function of adsorption cycles (Experimental conditions: initial benzene concentration (C ₀), 1.0 mmol/L; contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 0.5 mg/mL).	98
4.16	FESEM image of (a) Raw-BT, (b) M-BT, (c) M-CTAB-BT, (d) M-SDS-BT, (e) M-P123-BT, and (f) M-TX100-BT.	100
4.17	FTIR spectrum of (a) M-CTAB-BT, (b) M-SDS-BT, (c) M-P123-BT, and (d) M-TX100-BT.	102
4.18	Benzene adsorption performance of raw and modified BT adsorbents (Experimental conditions: initial benzene concentration (C ₀), 2.5 mmol/L; contact time (t), 24 h; temperature (T), 303 K; and adsorbent dosage (S/L), 1.0 mg/mL).	103
4.19	An XPS wide scan of the M-TX100-BT.	105
4.20	A high resolution XPS spectrum of Raw-BT and M-TX100-BT: (a) O_{1s} ; (b) N_{1s} , and (c) C_{1s} .	106
4.21	Effect of pH on benzene adsorption capacity of M-TX100-BT (Experimental conditions: initial benzene concentration (C_0), 2.5 mmol/L; contact time (t), 24 h;	

	temperature (T), 303 K; and adsorbent dosage (S/L), 1.0 mg/mL).	107
4.22	Effect of initial benzene concentrations on benzene adsorption capacity of M-1TX100-BT and M-TX100-BT (Experimental conditions: contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 0.5 mg/mL and 1.0 mg/mL).	108
4.23	Isotherm model analysis of the equilibrium data: (a) Langmuir and (b) Temkin isotherm models.	111
4.24	Benzene adsorption rate of M-TX100-BT at various reaction temperatures (Experimental conditions: initial benzene concentration (C ₀), 2.5 mmol/L; pH, 7; and adsorbent dosage (S/L), 1.0 mg/mL).	113
4.25	Intraparticle/Weber-Morris plot for benzene adsorption by M-TX100-BT at different reaction temperatures.	116
4.26	Kinetic modeling of benzene adsorption onto M-TX100-BT.	118
4.27	Adsorption performance of M-TX100-BT as function of adsorption cycles (Experimental conditions: initial benzene concentration (C ₀), 2.5 mmol/L; contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage, 1.0 mg/mL).	121
4.28	FESEM image of (a) Raw-BT, (b) M-BT, (c) M-1CTA-BT and (d) M-1CTA-SDS-BT.	122
4.29	FTIR spectrum of (a) Raw-BT, (b) M-BT, (c) M-1CTA-SDS-BT and (d) M-1CTA-SDS-BT.	124
4.30	An XPS wide scan of (a) Raw-BT, (b) M-BT, (c) M-1CTA-BT and (d) M-1CTA-SDS-BT.	125
4.31	A high resolution XPS spectrum of M-1CTA-BT and M-1CTA-SDS-BT: (a) O_{1s} ; (b) N_{1s} and (c) C_{1s} .	126
4.32	Benzene adsorption capacity, q_e of adsorbents (Experimental conditions: initial benzene concentration (C ₀), 2.5 mmol/L; contact time (t), 24 h; temperature (T), 303 K; and adsorbent dosage (S/L), 1.0 mg/mL).	128
4.33	Benzene adsorption capacity of various adsorbents with different mass ratio of adsorbent to CTA (Experimental conditions: initial benzene concentration (C ₀), 2.5 mmol/L; contact time (t), 24 h; temperature (T), 303 K; and adsorbent dosage (S/L), 1.0 mg/mL).	129
4.34	Effect of pH on benzene adsorption capacity of M-1CTA- SDS-BT (Experimental conditions: initial benzene concentration (C_0), 2.5 mmol/L; contact time (t), 24 h;	>

		• •	٠
X	\mathbf{V}^{1}	11	1

	temperature (T), 303 K; and adsorbent dosage (S/L), 1.0 mg/mL).	130
4.35	Effect of initial benzene concentrations on benzene adsorption capacity of M-1CTA-SDS-BT (Experimental conditions: contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 0.5 mg/mL and 1.0 mg/mL).	131
4.36	Isotherm model analysis of equilibrium adsorption data.	132
4.37	Benzene adsorption rate of M-1CTA-SDS-BT at various reaction temperatures (Experimental conditions: initial benzene concentration (C ₀), 2.5 mmol/L; pH, 7; and adsorbent dosage (S/L), 1.0 mg/mL).	134
4.38	Intraparticle/Weber-Morris plot for benzene adsorption by M-1CTA-SDS-BT at different reaction temperatures.	139
4.39	Kinetic modeling of benzene adsorption onto M-1CTA-SDS-BT.	140
4.40	Adsorption performance of M-1CTA-SDS-BT as the function of adsorption cycles (Experimental conditions: initial benzene concentration (C_0), 2.5 mmol/L; contact time (t), 24 h; pH, 7; temperature (T), 303 K; and adsorbent dosage (S/L), 1.0 mg/mL).	142

LIST OF SYMBOLS

η_b	-	Water viscosity (0.89 cp)
$ ho_s$	-	Solid density (g/mL)
Ø	-	Associate parameter of water (2.60)
ΔG	-	Gibbs free energy change
ΔH	-	Enthalpy change
ΔS	-	Entropy change
а	-	Temkin constant (L/g)
b _T	-	Heat of adsorption (kJ/mol)
C_0	-	Initial adsorbate concentration (mmol/L)
Ce	-	Equilibrium adsorbate concentration (mmol/L)
D_{AB}	-	Molecule diffusivity
\mathbf{D}_{eff}	-	Effective diffusion coefficient (m ² /min)
$\mathbf{D}_{\mathrm{film}}$	-	Film diffusion coefficient (m ² /min)
$\mathbf{D}_{\mathbf{p}}$	-	Pore diffusion (m ² /min)
Ds	-	Surface diffusion (m ² /min)
8	-	Polanyi potential
Κ	-	Thermodynamic constant at equilibrium
\mathbf{k}_1	-	PFO equilibrium rate constant (min ⁻¹)
k_2	-	PSO equilibrium rate constant (min ⁻¹)
\mathbf{K}_{F}	-	Freundlich constant (L ⁿ mmol ⁿ⁻¹ /g)
\mathbf{k}_{id}	-	Intraparticle diffusion constant
k _L	-	External mass transfer coefficient (m/min)
K _L	-	Langmuir constant (L/mmol)
M_B	-	Water molecular weight (18.0 g/mol)
n	-	Adsorption intensity
pH_{i}	-	Initial adsorbate pH

q	-	Adsorption capacity (mmol/g)
q_e	-	Equilibrium adsorption capacity (mmol/g)
q _{max}	-	Maximum adsorption capacity (mmol/g)
q_t	-	Adsorption capacity at time t (mmol/g)
$r \Gamma_e$	-	Retained CTAB loading capacity on the adsorbent (mmol/g)
R	-	Universal gas constant (8.314 J K ⁻¹ mol ⁻¹)
\mathbb{R}^2	-	Linear coefficient of determination
S/L	-	Adsorbent dosage (solid to liquid ratio, mg/mL)
\mathbf{S}_{eff}	-	Slope of the Boyd plot
Т	-	Temperature (°C)
t	-	Time (min)
V	-	Adsorbate volume (L)
VA	-	Liquid molar volume (m ³ /mol)
W	-	Adsorbent Weight (g)
α	-	Initial Adsorption Rate (mmol/g·min)
β	-	Desorption constant (g/mmol)
δ	-	Nernst film thickness
Δq_e	-	Normalized standard deviation for adsorption capacity (%)
$\Delta\Gamma_{e}$	-	Normalized standard deviation for CTAB loading capacity (%)
φ	-	Adsorbent to CTA ratio
χ^2	-	Pearson's chi-squared
Γ_{e}	-	CTAB loading capacity (mmol/g)

LIST OF ABBREVIATIONS

ACF	-	Activated carbon fiber
BET	-	Brunanuer-Emmet Teller
BT	-	Banana trunk
BTEX	-	Benzene, toluene, ethylbenzene and xylene
CAE	-	Constant analyzer energy
CNT	-	Carbon nanotubes
CPB	-	Cetyl pridinium bromide
CTA	-	(3-chloro-2-hydroxypropyl) trimethylammonium chloride
CTAB	-	Cetyltrimethylammonium bromide
D-R	-	Dubinin-Raduchkevich
FESEM	-	Field emission scanning electron microscope
FID	-	Flame ionization detector
FT-IR	-	Fourier transform infra-red
GC	-	Gas chromatography (GC)
HPLC	-	High performance liquid chromatography
KBr	-	Potassium bromide
NAD	-	Nitrogen adsorption/desorption
NPD	-	Naphthalene, phenanthrene and dibenzothiophene
OPEFB	-	Oil palm empty fruit bunch
PEG	-	Poly ethylene glycol
PFO	-	Pseudo-first order
Pluronic 123	-	Poly(ethylene glycol)- <i>block</i> -poly(propylene glycol)- <i>block</i>
		poly(ethylene glycol)
PSO	-	Pseudo-second order
O-SWCNT	-	Oxydized single-walled carbon nanotubes
P-SWCNT	-	Purified single-walled carbon nanotubes
SDS	-	Sodium dodecyl sulfate

SPME	-	Solid phase micro-extraction
TOC	-	Total organic carbon
Triton X-100	-	4-(1,1,3,3-tetramethylbutyl)phenyl-polyethylene glycol
UV	-	Ultra-violet
Vis	-	Visible
XPS	-	X-ray photoelectron spectroscopy

xxiii

LIST OF APPENDICES

APPENDIX

TITLE

PAGE

BStandard calibration curve178CBenzene adsorption capacity screening181DCTAB loading data182EBatch benzene adsorption data184	А	Ultra-violet visible scan	176
CBenzene adsorption capacity screening181DCTAB loading data182EBatch benzene adsorption data184	В	Standard calibration curve	178
DCTAB loading data182EBatch benzene adsorption data184	С	Benzene adsorption capacity screening	181
E Batch benzene adsorption data 184	D	CTAB loading data	182
	E	Batch benzene adsorption data	184

CHAPTER 1

INTRODUCTION

1.1 Research Background

In recent decades, many industries such as fossil fuels production, oil and gas refinery, plastic and synthetic rubber manufacturing have been growing extensively every year in order to fulfill the global application and demand (Vidal *et al.*, 2012). As a consequence, water pollution caused by the petroleum production, transportation, processing and application activities has been the major concern all over the world (Tiburtius *et al.*, 2005; Falkova *et al.*, 2016; Li *et al.*, 2016). Petroleum monoaromatic compounds such as benzene, toluene, ethylbenzene and xylene (BTEX) are commonly detected in almost any gasoline and petrol spill in water bodies (Aivalioti *et al.*, 2010). According to a report by the Ohio Department of Health, 18 % of gasoline is made up by BTEX components, by which 11 % of them is benzene component (Ohio Department of Health, 2014). Benzene can enter water bodies by the cracked pipelines, underground fuel tank leakages as well as improper effluent discharge (Sharmasarkar *et al.*, 2000; Seifi *et al.*, 2011a).

Benzene is generally used as either a raw material or a solvent in various chemical and petrochemical related industries (Hindarso *et al.*, 2001; Torabian *et al.*, 2010; Asenjo *et al.*, 2011). It is also one of the volatile organic compounds (VOC) which is colorless and flammable (Bennett and Peters, 1988; Fawell *et al.*, 2003). Many studies have reported that it is highly toxic and carcinogenic to humans (Wibowo *et al.*, 2007; Aivalioti *et al.*, 2012a). It is revealed that a long-term exposure to its compounds at high concentration can cause cancers of the blood forming organs

such as aplastic anemia and leukemia (Weisel, 2010). The stringent regulations have been enforced on its concentration in water bodies due to its toxicity which is harmful to the aquatic environment and human health (Carvalho *et al.*, 2012). According to the World Health Organization (WHO) drinking water guidelines, the maximum permissible its concentration is 0.01 ppm (Gorchev and Ozolins, 2011).

Due to the acute toxicity of the hazardous benzene in water and wastewater, it is utmost crucial to remove it from the waters and wastewaters. Consequently, a wide variety of removal technologies involves chemical, physical and/or biological methods have been investigated. In particular, the most common technologies are chemical or thermal oxidation, bioremediation, volatilization, condensation, membrane separation, and adsorption are developed (Lin and Huang, 1999; Ranck *et al.*, 2005; Farhadian and Duchez, 2008; Fakhru'l-Razi *et al.*, 2009; Aivalioti *et al.*, 2012b; Ali *et al.*, 2012; Carvalho *et al.*, 2012). Among all the conventional removal methods, the adsorption process is suggested to be the most cost-efficient and feasible method because it does not require a large amount of energy and additional chemicals. Besides that, adsorptive removal offers advantages including simple design and operation as well as cheap operating costs (Zytner, 1994; Lin and Huang, 1999; Wibowo *et al.*, 2007; Liang and Chen, 2010; Moura *et al.*, 2011; Yakout and Daifullah, 2013; Ray and Shipley, 2015; Mohammed *et al.*, 2015).

In adsorption technology, activated carbon has been most commonly used as an adsorbent for removing a wide variety of pollutants, such as aromatic organic compounds, heavy metals and dyes, from aqueous solution (Wibowo *et al.*, 2007; Karnib *et al.*, 2014; Sulaymon and Abood, 2014). This is because activated carbon possesses high specific surface area and chemical stability (Hindarso *et al.*, 2001; Su *et al.*, 2010a; Asenjo *et al.*, 2011; Serrano *et al.*, 2011). However, activated carbon is very expensive and not locally available in most of the countries (Daifullah and Girgis, 2003; Seifi *et al.*, 2011c). Besides activated carbon, other materials such as carbon nanotubes (Lu *et al.*, 2008; Su *et al.*, 2010b; Yu *et al.*, 2012), macro-reticular resins (Lin and Huang, 1999), clays (Jaynes and Vance, 1999; Sharmasarkar *et al.*, 2000; Vianna *et al.*, 2005; Nourmoradi *et al.*, 2012), zeolites (Ghiaci *et al.*, 2004; Seifi *et al.*, 2011b), carbon-silica aerogel composites (Dou *et al.*, 2011), diatomite (Aivalioti *et al.*, 2011).

2010, 2012a), and membranes (Ohshima *et al.*, 2005; Mukherjee and De, 2016; Uragami *et al.*, 2016) have been employed as adsorbents for the adsorption of benzene and other VOCs.

1.2 Problem Statement

The simple design and operation as well as the capability of adsorbent regeneration, have made the adsorption process as one of the most cost-effective pollutant removal alternatives (Delval et al., 2006; Johari et al., 2013). The active carbon is one of the most effective and conventional adsorbent employed in this process as it can adsorb organic pollutants at a wider spectrum. However, the high affinity toward the adsorbed pollutant molecules causes the difficulty in activated carbon regeneration (Koyuncu et al., 2011). Nowadays, the synthetic adsorbents which are bio-converted from the agricultural wastes (i.e. agrowastes), especially plant fibers, seeds, husks, piths and leaves, have been developed in recently years. This is because agrowastes are cheap, locally available, renewable, natural and biodegradable (Shin and Rowell, 2005; Saman et al., 2014). The applications of raw/unmodified agrowastes such as rice bran, angico saw-dust and peat as agrowaste-based adsorbents for BTEX removal were reported (Adachi et al., 2001; Akhtar et al., 2005; Costa et al., 2012). However, the use of unmodified agrowaste adsorbent has been proven to have low adsorption affinity and selectivity (Ibrahim et al., 2010a; Johari et al., 2016). It is reported that raw agrowastes contain a large number hydroxyl (-OH) groups which has made the agrowastes to be readily functionalized with various chemical functional groups (Kumar et al., 2014). The adsorbent functionalization or modification is conducted to improve their adsorption affinity towards specific pollutants (Tiemann et al., 1999; Delval et al., 2005; Fu and Wang, 2011).

The thermal treatment or carbonization is one of the most common methods used in synthesizing adsorbents (Singh *et al.*, 2003; Demirbas, 2009; Zhou *et al.*, 2015). It was reported that agrowastes such as peach stone, olive stone, date pit, coconut shell, almond shell, and *Moringa oleifera* pods have been employed to produce agrowaste-

based activated carbon for BTEX removal from aqueous solution (Daifullah and Girgis, 2003; Akhtar *et al.*, 2007; Mohammed *et al.*, 2015). A strong binding between the benzene molecules and carbon surface has made it difficult for regeneration and thus increased the material and operating cost (Koyuncu *et al.*, 2011; Zhang *et al.*, 2012b). The alkaline treatment or mercerization process is revealed to create more carboxyl groups and thus produce more potential binding sites on the adsorbent surfaces (Hashim *et al.*, 2012). The mercerization process also resulted in the irregular adsorbent surface as well as increased the adsorbent pore size and surface area by degrading the surface lignin. This leads to better binding effects between the adsorbate and the adsorbent surfaces (Ibrahim *et al.*, 2010a; Koay *et al.*, 2014).

Other chemical modifications such as esterification, acetylation, sulfonation, graft polymerization, impregnation and etherification are also conducted to enhance the adsorption performance towards target adsorbates (Chakraborty et al., 2005; Shin and Rowell, 2005; Alila and Boufi, 2009; Carvalho et al., 2012; Foo and Hameed, 2012b; Song et al., 2013; Teli and Valia, 2013). It was reported that adsorption uptake of BTEX removal relies on the surface hydrophobicity of the adsorbent employed (Seifi et al., 2011b). The surface modification by surfactants (i.e. cationic, anionic and non-ionic) is one of the well-known methods to increase the adsorbents surface hydrophobicity. Agrowastes (e.g. barley and wheat straw, peanut husk, coconut coir pith as well as yeast) functionalized by various cationic surfactants with different molecular weights (e.g. cetylpyridinium bromide (CPB), cetylpyridinium chloride (CPC), cetyltrimethylammonium bromide (CTAB) and hexadecyltrimethylammonium (HDTMA)) prepared using simple impregnation technique are successfully employed in the adsorption of a wide variety of pollutants including oil, dyes and metal ions from waters and wastewaters (Bingol et al., 2004; Namasivayam and Sureshkumar, 2008; Ibrahim et al., 2009, 2010a; Oei et al., 2009; Zhang et al., 2014; Zhao et al., 2014).

The utilization of agrowastes modified with surfactant for removal of benzene or BTEX has so far not been reported. However, inorganic adsorbents such as clay and zeolite modified with cationic surfactants including, benzyldimethyltetradecylammonium (BDTDA), benzyltrimethylammonium (BTMA), CPB and HDTMA (Koh and Dixon, 2001; Ghiaci *et al.*, 2004; Vianna *et al.*, 2005) have also been employed in volatile organic compounds (VOC) adsorption successfully. It was revealed that the BDTDA modified clay can achieve up to 70 % benzene adsorption uptake of those shown by activated carbon (Koh and Dixon, 2001). Polyethylene glycol (PEG, a type of non-ionic surfactant) was used to modify montmorillonite which showed promising results for the BTEX adsorptive removal process (Nourmoradi *et al.*, 2012). It was suggested that adsorbents modified with non-ionic surfactants may achieve higher BTEX adsorption uptake than that achieved with the adsorbents modified with cationic surfactants. Adsorbents such as bentonite, sawdust, alumina and montmorillonite modified with anionic surfactants (e.g. sodium dodecyl sulfate (SDS) and sodium stearate) were reported for total organic carbon (TOC) and dyes adsorption from aqueous state (Adak *et al.*, 2005; Chen *et al.*, 2010; Ansari *et al.*, 2012; El-dars *et al.*, 2015).

The surfactant-modified agrowastes was investigated as low-cost adsorbents for benzene removal from aqueous solution. The banana trunk (BT) was selected as a model agrowastes in the present study since banana is one of the most cultivated fruits the tropical region (Hameed *et al.*, 2008). It is generally left in unmanaged/decomposing in the plantation estates or disposed at a landfill after fruit harvesting (Sathasivam and Mas Haris, 2010). It is reported that it contains up to 33 % (dry basis) of holocellulose (hemicellulose and cellulose). It also contains a lot of pectin and polyphenols in its extract (Medeiros et al., 2000; Bilba et al., 2007). The high content of holocellulose has made it a potential adsorbent precursor because it is easy to be functionalized to treat the desired pollutant species. It was reported that it was used as adsorbents in adsorptive removal of heavy metal ions such as cobalt (Co(II)), cadmium (Cd(II)), copper (Cu(II)), iron (Fe(II)) and Zinc (Zn (II)), oil and methylene blue (Shibi and Anirudhan, 2005; Hameed et al., 2008; Sathasivam and Mas Haris, 2010; Teli and Valia, 2013). Thus, in the present study, the BT adsorbents were synthesized by surface modification followed by surfactant functionalization to enhance benzene adsorption from aqueous solution.

1.3 Research Objectives

- (a) To synthesize low-cost agrowaste based adsorbents by surface mercerization; surfactants modification; and surface etherification.
- (b) To characterize synthesized agrowaste based adsorbents.
- (c) To investigate the adsorption performance of the synthesized adsorbents towards benzene removal from aqueous solution.

1.4 Research Scopes

The banana trunk (BT) was selected agrowaste based adsorbent precursor. The raw agrowaste adsorbent was firstly modified by surface mercerization. The mercerized adsorbent was coated with various surfactants (i.e. cationic, anionic and non-ionic), namely cetyltrimethylammonium bromide (CTAB), sodium dodecyl sulfate (SDS), Poly(ethylene glycol)-*block*-poly(propylene glycol)-*block*-poly(ethylene glycol) (Pluronic 123) and 4-(1,1,3,3-tetramethylbutyl)phenyl-polyethylene glycol (Triton X-100). The surface etherification of adsorbent was also conducted by introducing the quaternary ammonium groups, namely (3-chloro-2-hydroxypropyl) trimethylammonium chloride solution (CTA) to enhance its surface reactivity towards surfactant coating.

The raw/unmodified and modified adsorbents surface morphologies were characterized by a field emission scanning microscope (FESEM). The existing functional groups on the adsorbent surfaces were determined with the Fourier transform infrared (FTIR) spectrometer and X-ray photoelectron spectrometer (XPS). The Brunauer-Emmet Teller surface area and pore diameters of the adsorbents were also investigated by nitrogen adsorption/desorption analyzer.

The adsorption performance of the surface modified adsorbent towards benzene removal from the aqueous solution was evaluated. The effects of adsorption parameters namely initial pH, initial benzene concentration, adsorbent dosage, temperature and contact time toward benzene adsorption capacity were studied. The isotherm adsorption data were analyzed by using the existing isotherm models namely Langmuir, Freundlich, Temkin and Dubinin-Raduchkevich (D-R) isotherm models, while pseudo-first-order (PFO), pseudo-second-order (PSO), Elovich and Weber and Morris models were applied to investigate the benzene adsorption kinetics. The analysis of the adsorption results led to the proposed adsorption mechanism. The adsorbent regeneration was also investigated.

1.5 Thesis Outline

This research thesis contains seven chapters. Chapter 1 describes briefly of the research background, problem statement, objective and scopes of the study. Chapter 2 presents a critical review on the benzene as pollutants in water, pollutants removal technologies, potential adsorbent precursors, adsorbent modifications as well as technical aspects of adsorption systems. The materials and procedures for adsorbent synthesis and characterization as well as benzene adsorption experiments are discussed in Chapter 3. The research findings are discussed in Chapters 4. The research conclusions and recommendations for future works are presented in Chapter 5.

1.6 Summary

Benzene pollutant existing in the water and wastewater must be removed since it is extremely hazardous and carcinogenic. Flora and fauna as well as humans' health can be seriously affected by its contamination in water. Adsorption is one of the simplest technologies to remove benzene pollutant from aqueous solution using lowcost adsorbents synthesized from agricultural wastes such as the banana trunk. The banana trunk (BT) is cheap and environmentally friendly. In addition, it contains a large amount of holocellulose which can be easily functionalized. The benzene adsorption by the synthesized adsorbents was evaluated at various experimental conditions followed by the theoretical thermodynamic and kinetic analyses of the experimental adsorption data.

REFERENCES

- Abbas, A., Abussaud, B. A., Ihsanullah, Al-Baghli, N. A. H., Khraisheh, M., Atieh, M. A., Abbas, A., Abussaud, B. A., Ihsanullah, Al-Baghli, N. A. H., Khraisheh, M. and Atieh, M. A. (2016). Benzene Removal by Iron Oxide Nanoparticles Decorated Carbon nNanotubes. *Journal of Nanomaterials*. 5654129, 1–10.
- Abd El-Latif, M. M., Ibrahim, A. M. and El-Kady, M. F. (2010). Adsorption Equilibrium, Kinetics and Thermodynamics of Methylene Blue from Aqueous Solutions Using Biopolymer Oak Sawdust Composite. *Journal of American Science*. 6(6), 267–283.
- Abraham, E., Deepa, B., Pothan, L. A., Jacob, M., Thomas, S., Cvelbar, U. and Anandjiwala, R. (2011). Extraction of Nanocellulose Fibrils from Lignocellulosic Fibres: A Novel Approach. *Carbohydrate Polymers*. 86(4), 1468–1475.
- Abussaud, B. A., Ulkem, N., Berk, D. and Kubes, G. J. (2008). Wet Air Oxidation of Benzene. *Industrial & Engineering Chemistry Research*. 47, 4325–4331.
- Adachi, A., Ikeda, C., Takagi, S., Fukao, N., Yoshie, E. and Okano, T. (2001). Efficiency of Rice Bran for Removal of Organochlorine Compounds and Benzene from Industrial Wastewater. *Journal of Agricultural and Food Chemistry*. 49(3), 1309–1314.
- Adak, A., Bandyopadhyay, M. and Pal, A. (2005). Adsorption of Anionic Surfactant on Alumina and Reuse of the Surfactant-Modified Alumina for the Removal of Crystal Violet from Aquatic Environment. *Journal of environmental science and health.* 40(1), 167–182.
- Ahmaruzzaman, M. and Gupta, V. K. (2011). Rice Husk and Its Ash as Low-Cost Adsorbents in Water and Wastewater Treatment. *Industrial & Engineering Chemistry Research*. 50, 13589–13613.
- Aivalioti, M., Papoulias, P., Kousaiti, A. and Gidarakos, E. (2012a). Adsorption of BTEX, MTBE and TAME on Natural and Modified Diatomite. *Journal of Hazardous Materials*. 207–208, 117–127.

- Aivalioti, M., Pothoulaki, D., Papoulias, P. and Gidarakos, E. (2012b). Removal of BTEX, MTBE and TAME from Aqueous Solutions by Adsorption onto Raw and Thermally Treated Lignite. *Journal of Hazardous Materials*. 207–208, 136–146.
- Aivalioti, M., Vamvasakis, I. and Gidarakos, E. (2010). BTEX and MTBE Adsorption onto Raw and Thermally Modified Diatomite. *Journal of Hazardous Materials*. 178, 136–143.
- Akhtar, M., Bhanger, M. I., Iqbal, S. and Hasany, S. M. (2005). Efficiency of Rice Bran for the Removal of Selected Organics from Water: Kinetic and Thermodynamic Investigations. *Journal of Agricultural and Food Chemistry*. 53(22), 8655–8662.
- Akhtar, M., Moosa Hasany, S., Bhanger, M. I. and Iqbal, S. (2007). Sorption Potential of Moringa Oleifera Pods for the Removal of Organic Pollutants from Aqueous Solutions. *Journal of Hazardous Materials*. 141(3), 546–556.
- Akpa, J. G. and Nmegbu, C. G. J. (2014). Adsorption of Benzene on Activated Carbon from Agricultural Waste Materials. *Research Journal of Chemical Sciences*. 4(9), 34–40.
- Aksu, Z. (2005). Application of Biosorption for the Removal of Organic Pollutants: A Review. *Process Biochemistry*. 40(3–4), 997–1026.
- Alamo-Nole, L. a., Perales-Perez, O. and Roman-Velazquez, F. R. (2011). Sorption Study of Toluene and Xylene in Aqueous Solutions by Recycled Tires Crumb Rubber. *Journal of Hazardous Materials*. 185, 107–111.
- Ali, I., Asim, M. and Khan, T. A. (2012). Low Cost Adsorbents for the Removal of Organic Pollutants from Wastewater. *Journal of Environmental Management*. 113, 170–183.
- Ali, S. A. and Singh, R. P. (2009). Synthesis and Characterization of A Modified Chitosan. *Macromolecular Symposia*. 277(1), 1–7.
- Alila, S., Aloulou, F., Thielemans, W. and Boufi, S. (2011). Sorption Potential of Modified Nanocrystals for the Removal of Aromatic Organic Pollutant from Aqueous Solution. *Industrial Crops and Products*. 33(2), 350–357.
- Alila, S. and Boufi, S. (2009). Removal of Organic Pollutants from Water by Modified Cellulose Fibres. *Industrial Crops and Products*. 30(1), 93–104.
- Alkaram, U. F., Mukhlis, A. A. and Al-Dujaili, A. H. (2009). The Removal of Phenol from Aqueous Solutions by Adsorption Using Surfactant-Modified Bentonite and Kaolinite. *Journal of Hazardous Materials*. 169(1–3), 324–332.

- Aloulou, F., Boufi, S. and Labidi, J. (2006). Modified Cellulose Fibres for Adsorption of Organic Compound in Aqueous Solution. *Separation and Purification Technology*. 52(2), 332–342.
- Amari, T., Themelis, N. J. and Wernick, I. K. (1999). Resource Recovery from Used Rubber Tires. *Resources Policy*. 25, 179–188.
- Ansari, R., Seyghali, B., Mohammad-khah, A. and Zanjanchi, M. A. (2012). Application of Nano Surfactant Modified Biosorbent as An Efficient Adsorbent for Dye Removal. *Separation Science and Technology*. 47(12), 1802–1812.
- Antal, M. J., Mochidzuki, K. and Paredes, L. S. (2003). Flash Carbonization of Biomass. *Industrial & Engineering Chemistry Research*. 42, 3690–3699.
- Asenjo, N. G., Álvarez, P., Granda, M., Blanco, C., Santamaría, R. and Menéndez, R. (2011). High Performance Activated Carbon for Benzene/Toluene Adsorption from Industrial Wastewater. *Journal of Hazardous Materials*. 192, 1525–1532.
- Augustine, A. A., Orike, B. D. and Edidiong, A. D. (2007). Adsorption Kinetics and Modelling of Copper (II) Ion Sorption Using Mercaptoacetic Acid Modified Cassava (Manihot Sculenta Cranz) Waste. *Electronic Journal of Environmental, Agricultural and Food Chemistry*. 6(4), 2221–2234.
- Bachtiar, D., Sapuan, S. M. and Hamdan, M. M. (2008). The Effect of Alkaline Treatment on Tensile Properties of Sugar Palm Fibre Reinforced Epoxy Composites. *Materials & Design*. 29(7), 1285–1290.
- Barde, P. and Barde, M. (2012). What To Use To Express the Variability of Data: Standard Deviation or Standard Error of Mean? *Perspectives in Clinical Research*. 3(3), 113–116.
- Barrer, R. M. (1989). Shape-Selective Sorbents Based on Clay Minerals: A Review. Clays and Clay Minerals. 37(5), 385–395.
- Bennett, G. F. and Peters, R. W. (1988). The Removal of Oil from Wastewater by Air
 Flotation : A Review. In *CRC Critical Reviews in Environmental Control*. 189–253, Boca Raton, Florida: CRC Press Inc.
- Berge, N. D., Ro, K. S., Mao, J., Flora, J. R. V, Chappell, M. A. and Bae, S. (2011). Hydrothermal Carbonization of Municipal Waste Streams. *Environmental Science and Technologycience & Technology*. 45, 5696–5703.
- Bhatnagar, A. and Sillanpää, M. (2010). Utilization of Agro-Industrial and Municipal Waste Materials as Potential Adsorbents for Water Treatment — A Review. *Chemical Engineering Journal*. 157, 277–296.

- Bilba, K., Arsene, M. and Ouensanga, A. (2007). Study of Banana and Coconut Fibers Botanical Composition, Thermal Degradation and Textural Observations. *Bioresource Technology*, 98, 58–68.
- Bingol, A., Ucun, H., Bayhan, Y. K., Karagunduz, A., Cakici, A. and Keskinler, B. (2004). Removal of Chromate Anions from Aqueous Stream by A Cationic Surfactant-Modified Yeast. *Bioresource Technology*. 94, 245–249.
- Boufi, S. and Belgacem, M. N. (2006). Modified Cellulose Fibres for Adsorption of Dissolved Organic Solutes. *Cellulose*. 13(1), 81–94.
- Bowman, R. S. (2003). Applications of Surfactant-Modified Zeolites to Environmental Remediation. *Microporous and Mesoporous Materials*. 61(1–3), 43–56.
- Boyd, S. A., Sun, S., Lee, J. F. and Mortland, M. M. (1988). Pentachlorophenol Sorption by Organo-Clays. *Clays and Clay Minerals*. 36(2), 125–130.
- Brunauer, S., Emmett, P. H. and Teller, E. (1938). Adsorption of gases in multimolecular layers. *Journal of the American Chemical Society*. 60, 309–319.
- Cai, Z. S., Song, Z. Q., Shang, S. Bin and Yang, C. S. (2007). Study on the Flocculating Properties of Quaternized Carboxymethyl Chitosan. *Polymer Bulletin*. 59(5), 655–665.
- Campos-Candel, A., Llobat-Estellés, M. and Mauri-Aucejo, A. (2009). Comparative Evaluation of Liquid Chromatography Versus Gas Chromatography Using A Beta-Cyclodextrin Stationary Phase for the Determination of BTEX in Occupational Environments. *Talanta*. 78(4–5), 1286–1292.
- Cao, L., Jiang, H., Yang, J., Fan, L., Li, F. and Huang, Q. (2013). Simultaneous Determination of Benzene and Toluene in Pesticide Emulsifiable Concentrate by Headspace GC-MS. *Journal of Analytical Methods in Chemistry*. 121783, 1–6.
- Carvalho, M. N., da Motta, M., Benachour, M., Sales, D. C. S., Abreu, C. A. M., Motta, M., Benachour, M., Sales, D. C. S. and Abreu, C. A. M. (2012). Evaluation of BTEX and Phenol Removal from Aqueous Solution by Multi-Solute Adsorption onto Smectite Organoclay. *Journal of Hazardous Materials*. 239–240, 95–101.
- Carvalho, W. S., Martins, D. F., Gomes, F. R., Leite, I. R., Gustavo da Silva, L., Ruggiero, R. and Richter, E. M. (2011). Phosphate Adsorption on Chemically Modified Sugarcane Bagasse Fibres. *Biomass and Bioenergy*. 35(9), 3913–3919.
- Cestari, A. R., Vieira, E. F. S., Vieira, G. S. and Almeida, L. E. (2007). Aggregation and Adsorption of Reactive Dyes in the Presence of An Anionic Surfactant on Mesoporous Aminopropyl Silica. *Journal of Colloid and Interface Science*.

309(2), 402–411.

- Chakraborty, S., Sahoo, B., Teraoka, I., Miller, L. M. and Gross, R. A. (2005). Enzyme-Catalyzed Regioselective Modification of Starch Nanoparticles. *Macromolecules*. 38, 61–68.
- Chang, C.-F. C.-F., Chang, C.-Y. C.-Y., Höll, W., Ulmer, M., Chen, Y.-H. Y.-H. and Gross, H.-J. H.-J. (2004). Adsorption Kinetics of Polyethylene Glycol from Aqueous Solution onto Activated Carbon. *Water research*. 38(10), 2559–2570.
- Charkhi, A., Kazemian, H. and Kazemeini, M. (2010). Optimized Experimental Design for Natural Clinoptilolite Zeolite Ball Milling to Produce Nano Powders. *Powder Technology*. 203(2), 389–396.
- Chen, B., Yuan, M. and Liu, H. (2011). Removal of Polycyclic Aromatic Hydrocarbons from Aqueous Solution Using Plant Residue Materials as A Biosorbent. *Journal of Hazardous Materials*. 188(1–3), 436–442.
- Chen, D. M., Chen, J., Wang, X. M., Luan, X. L., Ji, H. P. and Xu, F. (2010). Adsorption of Methylene Blue from Aqueous Solution by Anionic Surfactant Modified Montmorillonite. *Advanced Materials Research*. 178, 29–34.
- Chen, L., Wang, H., Wei, H., Guo, Z., Khan, M. A., Young, D. P. and Zhu, J. (2015). Carbon Monolith with Embedded Mesopores and Nanoparticles as A Novel Adsorbent for Water Treatment. *RSC Advances*. 5(53), 42540–42547.
- Chen, W., Duan, L., Wang, L. and Zhu, D. (2008). Adsorption of Hydroxyl- and Amino-Substituted Aromatics to Carbon Nanotubes. *Environmental Science and Technology*. 42(18), 6862–6868.
- Cheu, S. C., Kong, H., Song, S. T., Johari, K., Saman, N., Che Yunus, M. A. and Mat, H. (2016a). Separation of Dissolved Oil from Aqueous Solution by Sorption onto Acetylated Lignocellulosic Biomass—Equilibrium, Kinetics and Mechanism Studies. *Journal of Environmental Chemical Engineering*. 4(1), 864–881.
- Cheu, S. C., Kong, H., Song, S. T., Saman, N., Johari, K. and Mat, H. (2016b). High Removal Performance of Dissolved Oil from Aqueous Solution by Sorption Using Fatty Acid Esterified Pineapple Leaves as Novel Sorbents. *RSC Advances*. 6(17), 13710–13722.
- Chin, C. J. M., Shih, L. C., Tsai, H. J. and Liu, T. K. (2007). Adsorption of o-Xylene and p-Xylene from Water by SWCNTs. *Carbon*. 45, 1254–1260.
- Chin, C. J. M., Shih, M. W. and Tsai, H. J. (2010). Adsorption of Nonpolar Benzene Derivatives on Single-Walled Carbon Nanotubes. *Applied Surface Science*. 256,

6035-6039.

- Chiriac, R., Carré, J., Perrodin, Y., Vaillant, H., Gasso, S. and Miele, P. (2009). Study of the Dispersion of VOCs Emitted by A Municipal Solid Waste Landfill. *Atmospheric Environment*. 43(11), 1926–1931.
- Cho, D., Kim, J. M., Song, I. S. and Hong, I. (2011). Effect of Alkali Pre-Treatment of Jute on the Formation of Jute-Based Carbon Fibers. *Materials Letters*. 65(10), 1492–1494.
- Chowdhury, S., Mishra, R., Saha, P. and Kushwaha, P. (2011). Adsorption Thermodynamics, Kinetics and Isosteric Heat of Adsorption of Malachite Green onto Chemically Modified Rice Husk. *Desalination*. 265(1–3), 159–168.
- Chu, B. S., Baharin, B. S., Che Man, Y. B. and Quek, S. Y. (2004). Separation of Vitamin E from Palm Fatty Acid Distillate Using Silica: I Equilibrium of Batch Adsorption. *Journal of Food Engineering*. 62(1), 97–103.
- Čížová, A., Neščáková, Z., Malovíková, A. and Bystrický, S. (2016). Preparation and Characterization of Cationic and Amphoteric Mannans from Candida Albicans. *Carbohydrate Polymers*. 149, 1–7.
- Coca-prados, J., Gutiérrez, G. and Benito, J. M. (2013). Treatment of Oily Wastewater
 by Membrane Hybrid Processes. In Coca-prados, J. and Gutiérrez-Cervelló, G.
 (Eds.). Economic Sustainability and Environmental Protection in Mediterranean
 Countries through Clean Manufacturing Methods. 35–61, Springer Science.
- Cookson, J. T. (1978). Adsorption Mechanisms: The Chemistry of Organic Adsorption on Activated Carbon. In Cheremisinoff, P. N. and Ellerbusch, F. (Eds.). *Carbon Adsorption Handbook*. 241–279, Ann Arbor, Michigan: Ann Arbor Science.
- Cordeiro, N., Belgacem, M. N., Torres, I. C. and Moura, J. C. V. P. (2004). Chemical Composition and Pulping of Banana Pseudo-stems. *Industrial Crops and Products*. 19, 147–154.
- Costa, A. S., Romão, L. P. C., Araújo, B. R., Lucas, S. C. O., Maciel, S. T. A., Wisniewski, A. and Alexandre, M. R. (2012). Environmental Strategies to Remove Volatile Aromatic Fractions (BTEX) from Petroleum Industry Wastewater Using Biomass. *Bioresource Technology*. 105, 31–39.
- Crini, G. and Badot, P. M. (2008). Application of Chitosan, A Natural Aminopolysaccharide, for Dye Removal from Aqueous Solutions by Adsorption Processes Using Batch Studies: A Review of Recent Literature. *Progress in Polymer Science (Oxford)*. 33(4), 399–447.

- Cui, L., Puerto, M., Lo, J. L., Biswal, S. L. and Hirasaki, G. J. (2014). Improved Methylene Blue Two-Phase Titration Method for Determining Cationic Surfactant Concentration in High-Salinity Brine. *Analytical Chemistry*. 86, 11055–11061.
- Daifullah, A. A. M. and Girgis, B. S. (2003). Impact of Surface Characteristics of Activated Carbon on Adsorption of BTEX. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 214, 181–193.
- Daud, Z., Zainuri, M., Hatta, M., Sari, A., Kassim, M., Awang, H. and Aripin, A. M. (2014). Exploring of Agro Waste (Pineapple Leaf, Corn Stalk, and Napier Grass) by Chemical Composition and Morphological Study. *BioResources*. 9(1), 872–880.
- Delle Site, A. (2001). Factors Affecting Sorption of Organic Compounds in Natural Sorbent/Water Systems and Sorption Coefficients for Selected Pollutants. A Review. *Journal of Physical and Chemical Reference Data*. 30(1), 187–439.
- Delval, F., Crini, G., Bertini, S., Filiatre, C. and Torri, G. (2005). Preparation, Characterization and Sorption Properties of Crosslinked Starch-Based Exchangers. *Carbohydrate Polymers*. 60, 67–75.
- Delval, F., Crini, G. and Vebrel, J. (2006). Removal of Organic Pollutants from Aqueous Solutions by Adsorbents Prepared from An Agroalimentary By-Product. *Bioresource technology*. 97(16), 2173–2181.
- Demirbas, A. (2009). Agricultural Based Activated Carbons for the Removal of Dyes from Aqueous Solutions : A Review. *Journal of Hazardous Materials*. 167, 1–9.
- Deng, S. (2006). Sorbent Technology. In Lee, S. (Ed.). Encylopedia oF Chemical Processing. 2825–2845, New York: Taylor & Francis Group.
- Dhaouadi, H. and M'Henni, F. (2008). Textile Mill Effluent Decolorization Using Crude Dehydrated Sewage Sludge. *Chemical Engineering Journal*. 138(1), 111– 119.
- Djilani, C., Zaghdoudi, R., Modarressi, A., Rogalski, M. and Lallam, A. (2012). Elimination of Organic Micropollutants by Adsorption on Activated Carbon Prepared from Agricultural Waste. *Chemical Engineering Journal*. 189–190, 203–212.
- Dong, C., Zhang, F., Pang, Z. and Yang, G. (2016). Efficient and Selective Adsorption of Multi-Metal Ions Using Sulfonated Cellulose as Adsorbent. *Carbohydrate Polymers*. 151, 230–236.

- Dotto, G. L. and Pinto, L. A. A. (2011). Adsorption of Food Dyes Acid Blue 9 and Food Yellow 3 Onto Chitosan: Stirring Rate Effect in Kinetics and Mechanism. *Journal of Hazardous Materials*. 187(1–3), 164–170.
- Dou, B., Li, J., Wang, Y., Wang, H., Ma, C. and Hao, Z. (2011). Adsorption and Desorption Performance of Benzene Over Hierarchically Structured Carbon-Silica Aerogel Composites. *Journal of Hazardous Materials*. 196, 194–200.
- Doyle, D. and Brown, A. (2000). Produced Water Treatment and Hydrocarbon Removal with Organoclay. In SPE Annual Technical Conference and Exhibition. 2000, Dallas, Texas, 1-11.
- Ekins, P., Vanner, R. and Firebrace, J. (2005). Management of Produced Water on Offshore Oil Installations: A Comparative Assessment Using Flow Analysis. In *Policy Studies Institute (PSI) Working Paper*. 2005, London.
- El-dars, F. M. S. E., Hussien, M. Y. M. and Kandil, A. H. T. (2015). TOC Reduction in Drinking Water Using Anionic Surfactant Modified Bentonite. *International Journal of Scientific & Engineering Research*. 6(3), 584–594.
- Etzkorn, T., Klotz, B., Sørensen, S., Patroescu, I. V., Barnes, I., Becker, K. H. and Platt, U. (1999). Gas-Phase Absorption Cross Sections of 24 Monocyclic Aromatic Hydrocarbons in the UV and IR Spectral Ranges. *Atmospheric Environment*. 33(4), 525–540.
- Fakhru'l-Razi, A., Pendashteh, A., Abdullah, L. C., Biak, D. R. A., Madaeni, S. S. and Abidin, Z. Z. (2009). Review of Technologies for Oil and Gas Produced Water Treatment. *Journal of Hazardous Materials*. 170, 530–551.
- Falkova, M., Vakh, C., Shishov, A., Zubakina, E., Moskvin, A., Moskvin, L. and Bulatov, A. (2016). Automated IR Determination of Petroleum Products in Water based on Sequential Injection Analysis. *Talanta*. 148, 661–665.
- Farhadian, M. and Duchez, D. (2008). BTX Removal from Polluted Water Through Bioleaching Processes. *Applied Biochemistry and Biotechnology*. 151, 295–306.
- Fawell, J. K., Lund, U., Mintz, B., Galal-Gorchev, H., Helmer, R., Bonnefoy, X. and Espinoza, O. (2003). *Benzene in Drinking Water*. Sheffer, M. (Ed.). Geneva, Switzerland: World Health Organization.
- Febrianto, J., Kosasih, A. N., Sunarso, J., Ju, Y. H., Indraswati, N. and Ismadji, S. (2009). Equilibrium and Kinetic Studies in Adsorption of Heavy Metals Using Biosorbent: A Summary of Recent Studies. *Journal of Hazardous Materials*. 162, 616–645.

- Foo, K. Y. and Hameed, B. H. (2012a). A Cost Effective Method for Regeneration of Durian Shell and Jackfruit Peel Activated Carbons by Microwave Irradiation. *Chemical Engineering Journal*. 193, 404–409.
- Foo, K. Y. and Hameed, B. H. (2012b). Microporous and Mesoporous Materials Porous Structure and Adsorptive Properties of Pineapple Peel Based Activated Carbons Prepared via Microwave Assisted KOH and K₂CO₃ Activation. *Microporous and Mesoporous Materials*. 148, 191–195.
- Franke, T. M., Ho, T. and Christie, C. A. (2011). The Chi-Square Test: Often Used and More Often Misinterpreted. *American Journal of Evaluation*. 33(3), 448– 458.
- Fu, F. and Wang, Q. (2011). Removal of Heavy Metal Ions from Wastewaters: A Review. Journal of Environmental Management. 92(3), 407–418.
- Furusawa, T. and Smith, J. M. (1973). Fluid-Particle and Intraparticle Mass Transport Rates in Slurries. *Industrial & Engineering Chemistry Fundamentals*. 12(2), 197–203.
- Garcia-Reyes, R. B. and Rangel-Mendez, J. R. (2010). Adsorption Kinetics of Chromium(III) Ions on Agro-Waste Materials. *Bioresource Technology*. 101(21), 8099–8108.
- Ghadiri, S. K., Nabizadeh, R., Mahvi, A. H., Nasseri, S., Mesdaghinia, A. R. and Talebi, S. . (2012). Potential of Granulated Modified Nanozeolites Y for MTBE Removal from Aqueous Solutions : Kinetic and Isotherm Studies. *Polish Journal* of Chemical Technology. 14(2), 1–8.
- Ghiaci, M., Abbaspur, A., Kia, R. and Seyedeyn-Azad, F. (2004). Equilibrium Isotherm Studies for the Sorption of Benzene, Toluene, and Phenol onto Organo-Zeolites and As-Synthesized MCM-41. *Separation and Purification Technology*. 40, 217–229.
- Gil, A., Assis, F. C. C., Albeniz, S. and Korili, S. a. (2011). Removal of Dyes from Wastewaters by Adsorption on Pillared Clays. *Chemical Engineering Journal*. 168(3), 1032–1040.
- Gorchev, H. G. and Ozolins, G. (2011). Chemical fact sheets-Benzene. In *Guidelines* for Drinking-water Quality. 322, Geneva, Switzerland: World Health Organization.
- Guibal, E. (2004). Interactions of Metal Ions with Chitosan-Based Sorbents: A Review. *Separation and Purification Technology*. 38(1), 43–74.

- Guo, L., Sun, C. M., Li, G. Y., Liu, C. P. and Ji, C. N. (2009). Thermodynamics and Kinetics of Zn(II) Adsorption on Crosslinked Starch Phosphates. *Journal of Hazardous Materials*. 161, 510–515.
- Guo, L., Zhang, S. F., Ju, B. Z. and Yang, J. Z. (2006). Study on Adsorption of Cu(II) by Water-Insoluble Starch Phosphate Carbamate. *Carbohydrate Polymers*. 63, 487–492.
- Hameed, B. H., Mahmoud, D. K. and Ahmad, A. L. (2008). Sorption Equilibrium and Kinetics of Basic Dye from Aqueous Solution Using Banana Stalk Waste. *Journal of Hazardous Materials*. 158(2–3), 499–506.
- Han, R., Zhang, L., Song, C., Zhang, M., Zhu, H. and Zhang, L. (2010). Characterization of Modified Wheat Straw, Kinetic and Equilibrium Study about Copper Ion and Methylene Blue Adsorption in Batch Mode. *Carbohydrate Polymers*. 79(4), 1140–1149.
- Hashim, M. Y., Roslan, M. N., Amin, A. M., Ahmad Zaidi, A. M. and Ariffin, S. (2012). Mercerization Treatment Parameter Effect on Natural Fiber Reinforced Polymer Matrix Composite: A Brief Review. World Academy of Science, Engineering and Technology. 68, 1638–1644.
- Hindarso, H., Ismadji, S., Wicaksana, F. and Indraswati, N. (2001). Adsorption of Benzene and Toluene from Aqueous Solution onto Granular Activated Carbon. *Journal of Chemical and Engineering Data*. 46(4), 788–791.
- Hiwarkar, A. D., Srivastava, V. C. and Deo mall, I. (2015). Comparative Studies on Adsorptive Removal of Indole by Granular Activated Carbon and Bagasse Fly Ash. *Environmental Progress & Sustainable Energy*. 34(2), 492–503.
- Ho, Y.-S. (2006). Isotherms for the Sorption of Lead onto Peat: Comparison of Linear and Non-Linear Methods. *Polish Journal of Environmental Studies*. 15(1), 81–86.
- Ho, Y. S. and McKay, G. (1999). Pseudo-Second Order Model for Sorption Processes. Process Biochemistry. 34, 451–465.
- Ho, Y. S., Ng, J. C. Y. and McKay, G. (2000). Kinetics of Pollutant Sorption by Biosorbents: Review. Separation & Purification Reviews. 29(2), 189–232.
- Horner, J. E., Castle, J. W. and Rodgers, J. H. (2011). A Risk Assessment Approach to Identifying Constituents in Oilfield Produced Water for Treatment Prior to Beneficial Use. *Ecotoxicology and Environmental Safety*. 74(4), 989–999.

Hornig, G., Northcott, K., Snape, I. and Stevens, G. (2008). Assessment of Sorbent

Materials for Treatment of Hydrocarbon Contaminated Ground Water in Cold Regions. *Cold Regions Science and Technology*. 53, 83–91.

- Hu, B. and Luo, H. (2010). Adsorption of Hexavalent Chromium onto Montmorillonite Modified with Hydroxyaluminum and Cetyltrimethylammonium Bromide. *Applied Surface Science*. 257(3), 769–775.
- Hu, X., Qiao, S., Zhao, X. S., Lu, G. Q. and Section, E. (2001). Adsorption Study of Benzene in Ink-Bottle-Like MCM-41. *Industrial & Engineering Chemistry Research*. 40, 862–867.
- Hubbe, M. A., Park, J. and Park, S. (2014). Cellulosic Substrates for Removal of Pollutants from Aqueous Systems: A Review. Part 4. Dissolved Petrochemical Compounds. *BioResources*. 9(4), 7782–7925.
- Ibrahim, S., Ang, H. M. and Wang, S. (2009). Removal of Emulsified Food and Mineral Oils from Wastewater Using Surfactant Modified Barley Straw. *Bioresource technology*. 100, 5744–5749.
- Ibrahim, S., Fatimah, I., Ang, H.-M. and Wang, S. (2010a). Adsorption of Anionic Dyes in Aqueous Solution Using Chemically Modified Barley Straw. Water Science and Technology. 62(5), 1177–1182.
- Ibrahim, S., Wang, S. and Ang, H. M. (2010b). Removal of Emulsified Oil from Oily Wastewater Using Agricultural Waste Barley Straw. *Biochemical Engineering Journal*. 49(1), 78–83.
- Ingale, S., Joshi, S. J. and Gupte, A. (2014). Production of Bioethanol Using Agricultural Waste: Banana Pseudo Stem. *Brazilian Journal of Microbiology*. 45(3), 885–892.
- Ismadji, S. and Bhatia, S. K. (2000). Adsorption of Flavour Esters on Granular Activated Carbon. *The Canadian Journal of Chemical Engineering*. 78(5), 892– 901.
- Itodo, A. U. and Itodo, H. U. (2010). Sorption Energies Estimation Using Dubinin-Radushkevich and Temkin Adsorption Isotherms. *Life Science Journal*. 7(4), 68– 76.
- Jain, M., Garg, V. K. and Kadirvelu, K. (2009). Chromium(VI) Removal from Aqueous System Using Helianthus Annuus (Sunflower) Stem Waste. *Journal of Hazardous Materials*. 162(1), 365–372.
- Jaynes, W. F. and Vance, G. F. (1999). Sorption of Benzene, Toluene, Ethylbenzene, and Xylene (BTEX) Compounds by Hectorite Clays Exchange with Aromatic

Organic Cations. Clays and Clay Minerals. 47(3), 358–365.

- Jibril, B., Houache, O., Al-Maamari, R. and Al-Rashidi, B. (2008). Journal of Analytical and Applied Pyrolysis Effects of H₃PO₄ and KOH in carbonization of lignocellulosic material. *Journal of Analytical and Applied Pyrolysis*. 83, 151– 156.
- Jo, M. S., Rene, E. R., Kim, S. H. and Park, H. S. (2008). An Analysis of Synergistic and Antagonistic Behavior during BTEX Removal in Batch System Using Response Surface Methodology. *Journal of Hazardous Materials*. 152, 1276– 1284.
- Johari, K., Saman, N., Song, S. T., Chin, C. S., Kong, H. and Mat, H. (2016). Adsorption Enhancement of Elemental Mercury by Various Surface Modified Coconut Husk as Eco-Friendly Low-Cost Adsorbents. *International Biodeterioration & Biodegradation*. 109, 45–52.
- Johari, K., Saman, N., Song, S. T., Mat, H. and Stuckey, D. C. (2013). Utilization of Coconut Milk Processing Waste as A Low-cost Mercury Sorbent. *Industrial & Engineering Chemistry Research*. 52(44), 15648–15657.
- Karaoğlu, M. H., Doğan, M. and Alkan, M. (2010). Kinetic Analysis of Reactive Blue 221 Adsorption on Kaolinite. *Desalination*. 256, 154–165.
- Karapanagioti, H. K., Sabatini, D. a. and Bowman, R. S. (2005). Partitioning of Hydrophobic Organic Chemicals (HOC) into Anionic and Cationic Surfactant-Modified Sorbents. *Water Research*. 39, 699–709.
- Karnib, M., Kabbani, A., Holail, H. and Olama, Z. (2014). Heavy Metals Removal Using Activated Carbon, Silica and Silica Activated Carbon Composite. *Energy Procedia*. 50, 113–120.
- Karnitz, O., Gurgel, L. V. A. and Gil, L. F. (2010). Removal of Ca(II) and Mg(II) from Aqueous Single Metal Solutions by Mercerized Cellulose and Mercerized Sugarcane Bagasse Grafted with EDTA Dianhydride (EDTAD). *Carbohydrate Polymers*. 79(1), 184–191.
- Kasuriya, S., Namuangruk, S., Treesukol, P., Tirtowidjojo, M. and Limtrakul, J. (2003).
 Adsorption of Ethylene, Benzene, and Ethylbenzene over Faujasite Zeolites Investigated by the ONIOM Method. *Journal of Catalysis*. 219, 320–328.
- Khalil, H. P. S. A., Alwani, M. S. and Mohd Omar, A. K. (2006). Chemical Composition, Anatomy, Lignin Distribution, and Cell Wall Structure of Malaysia Plant Waste Fibers. *BioResources*. 1(2), 220–232.

- Khatib, Z., Verbeek, P. and others (2003). Water to Value-Produced Water Management for Sustainable Field Development of Mature and Green Fields. *Journal of Petroleum Technology*. 55(1), 26–28.
- Kheirmand, M., Barkhordari, A., Mosaddegh, M. and Farajzadegan, Z. (2014). Determination of Benzene, Toluene, Ethyl Benzene and Xylene in Administration Room's air of Hospitals Using Solid Phase Micro Extraction/Gas Chromatography/Flame Ionization Detector. *International Journal of Environmental Health Engineering*. 3(2), 64–70.
- Koay, Y. S., Ahamad, I. S., Nourouzi, M. M., Abdullah, L. C. and Choong, T. S. Y. (2014). Development of Novel Low-Cost Quaternized Adsorbent from Palm Oil Agriculture Waste for Reactive Dye Removal. *BioResources*. 9(1), 66–85.
- Koh, S. M. and Dixon, J. B. (2001). Preparation and Application of Organo-Minerals as Sorbents of Phenol, Benzene and Toluene. *Applied Clay Science*. 18, 111–122.
- Koner, S., Pal, A. and Adak, A. (2011). Utilization of Silica Gel Waste for Adsorption of Cationic Surfactant and Adsolubilization of Organics from Textile Wastewater: A Case Study. *Desalination*. 276(1–3), 142–147.
- Kong, H., Cheu, S.-C., Othman, N. S., Song, S.-T., Saman, N., Johari, K. and Mat, H. (2016). Surfactant Modification of Banana Trunk as Low-Cost Adsorbents and Their High Benzene Adsorptive Removal Performance from Aqueous Solution. *RSC Adv.* 6(29), 24738–24751.
- Koyuncu, H., Yıldız, N., Salgın, U., Köroğlu, F. and Calımlı, A. (2011). Adsorption of o-, m- and p-Nitrophenols onto Organically Modified Bentonites. *Journal of Hazardous Materials*. 185(2–3), 1332–1339.
- Kuan, Y. H. and Liong, M. T. (2008). Chemical and Physicochemical Characterization of Agrowaste Fibrous Materials and Residues. *Journal of Agricultural and Food Chemistry*. 56, 9252–9257.
- Kuleyin, A. (2007). Removal of Phenol and 4-Chlorophenol by Surfactant-Modified Natural Zeolite. *Journal of Hazardous Materials*. 144, 307–315.
- Kumar, A., Negi, Y. S., Choudhary, V. and Bhardwaj, N. K. (2014). Characterization of Cellulose Nanocrystals Produced by Acid-Hydrolysis from Sugarcane Bagasse as Agro-waste. *Journal of Materials Physics and Chemistry*. 2(1), 1–8.
- Langmuir, I. (1918). The Adsorption of Gases on Plane Surfaces of Glass, Mica and Platinum. *Journal of the American Chemical Society*. 40(1914), 1361–1403.

Lee, S. Y., Kim, S. J., Chung, S. Y. and Jeong, C. H. (2004). Sorption of Hydrophobic

Organic Compounds onto Organoclays. Chemosphere. 55(5), 781-785.

- Leyva-Ramos, R. and Geankoplis, C. J. (1985). Model Simulation and Analysis of Surface Diffusion of Liquids in Porous Solids. *Chemical Engineering Science*. 40(5), 799–807.
- Leyva-Ramos, R., Rangel-Mendez, J., Bernal-Jacome, L. and Berber Mendoza, M. (2005). Intraparticle Diffusion of Cadmium and Zinc Ions during Adsorption from Aqueous Solution on Activated Carbon. *Journal of Chemical Technology* & *Biotechnology*. 80(8), 924–933.
- Li, G., Fu, Y., Shao, Z., Zhang, F. and Qin, M. (2015). Preparing Cationic Cellulose Derivative in NaOH/Urea Aqueous Solution and Its Performance as Filler Modifier. *BioResources*. 10(4), 7782–7794.
- Li, K., Fu, S., Zhan, H., Zhan, Y. and Lucia, L. A. (2010). Analysis of The Chemical Composition and Morphological Structure of Banana Pseudo-stem. *BioResources*. 5(2), 576–585.
- Li, P., Cai, Q., Lin, W., Chen, B. and Zhang, B. (2016). Offshore Oil Spill Response Practices and Emerging Challenges. *Marine Pollution Bulletin*. 110(1), 6–27.
- Liang, C. and Chen, Y.-J. (2010). Evaluation of Activated Carbon for Remediating Benzene Contamination: Adsorption and Oxidative Regeneration. *Journal of Hazardous Materials*. 182(1–3), 544–551.
- Liao, Q., Sun, J. and Gao, L. (2008). The Adsorption of Resorcinol from Water Using Multi-Walled Carbon Nanotubes. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 312, 160–165.
- de Lima, A. C. A., Nascimento, R. F., de Sousa, F. F., Filho, J. M. and Oliveira, A. C. (2012). Modified Coconut Shell Fibers : A Green and Economical Sorbent for the Removal of Anions from Aqueous Solutions. *Chemical Engineering Journal*. 185–186, 274–284.
- Lin, S. H. and Huang, C. Y. (1999). Adsorption of BTEX from Aqueous Solution by Macroreticular Resins. *Journal of Hazardous Materials*. 70, 21–37.
- Liu, W., Liu, Y. F., Tao, Y. Q., Yu, Y. J., Jiang, H. M. and Lian, H. Z. (2014). Comparative Study of Adsorption of Pb(II) on Native Garlic Peel and Mercerized Garlic Peel. *Environmental Science and Pollution Research*. 21(3), 2054–2063.
- Lu, C., Su, F. and Hu, S. (2008). Surface Modification of Carbon Nanotubes for Enhancing BTEX Adsorption from Aqueous Solutions. *Applied Surface Science*. 254, 7035–7041.

- Luck, F. (1999). Wet Air Oxidation: Past, Present and Future. *Catalysis Today*. 53(1), 81–91.
- Mahvi, A. H., Vosoughi, M., Mohammadi, M. J., Asadi, A., Hashemzadeh, B., Zahedi,
 A. and Pourfadakar, S. (2016). Sodium Dodecyl Sulfate Modified-Zeolite as A
 Promising Adsorbent for the Removal of Natural Organic Matter From Aqueous
 Environments. *Health Scope*. 5(1), 1–8.
- Mangun, C. L., Yue, Z., Economy, J., Maloney, S., Kemme, P. and Cropek, D. (2001). Adsorption of Organic Contaminants from Water Using Tailored ACFs. *Chemistry of Materials*. 13, 2356–2360.
- Marshall, W. E. and Wartelle, L. H. (2004). An Anion Exchange Resin from Soybean Hulls. *Journal of Chemical Technology and Biotechnology*. 79(11), 1286–1292.
- Mason, C. A., Ward, G., Keren, O. and Dosoretz, C. G. (2000). Biodegradation of BTEX by Bacteria on Powdered Activated Carbon. *Bioprocess Engineering*. 23, 331–336.
- McHugh, M. L. (2012). The Chi-square Test of Independence. *Biochemia Medica*. 23(2), 143–149.
- McKay, G. and Al-Duri, B. (2007). Study of the Mechanism of Pore Diffusion in Batch Adsorption Systems. *Journal of Chemical Technology & Biotechnology*. 48(3), 269–285.
- Medeiros, R. G., Soffner, M. L., Thomé, J. A., Cacais, A. O., Estelles, R. S., Salles, B. C., Ferreira, H. M., Lucena Neto, S. A., Silva, F. G. and Filho, E. X. (2000). The Production of Hemicellulases by Aerobic Fungi on Medium Containing Residues of Banana Plant as Substrate. *Biotechnology Progress*. 16(3), 522–524.
- Milewska-Duda, J., Duda, J., Nodzeński, A. and Lakatos, J. (2000). Absorption and Adsorption of Methane and Carbon Dioxide in Hard Coal and Active Carbon. *Langmuir.* 16, 5458–5466.
- Ming, D. W. and Dixon, J. B. (1987). Quantitative Determination of Clinoptilolite in Soils by A Cation-Exchange Capacity Method. *Clays and Clay Minerals*. 35(6), 463–468.
- Mohamed, M. and Ouki, S. K. (2011). Kinetic and Removal Mechanisms of Ethylbenzene from Contaminated Solutions by Chitin and Chitosan. *Water, Air,* and Soil Pollution. 220, 131–140.
- Mohammed, J., Nasri, N. S., Ahmad Zaini, M. A., Hamza, U. D. and Ani, F. N. (2015). Adsorption of Benzene and Toluene onto KOH Activated Coconut Shell Based

Carbon Treated with NH3. *International Biodeterioration & Biodegradation*. 102, 245–255.

- Mohapatra, D., Mishra, S. and Sutar, N. (2010). Banana and Its By-product Utilisation: An Overview. *Journal of Scientific and Industrial Research*. 69(5), 323–329.
- Mortland, M. M. (1970). Clay-Organic Complexes and Interactions. Advance in Agronomy. 22, 75–117.
- Moura, C. P., Vidal, C. B., Barros, A. L., Costa, L. S., Vasconcellos, L. C. G., Dias, F. S. and Nascimento, R. F. (2011). Adsorption of BTX (Benzene, Toluene, o-Xylene, and p-Xylene) from Aqueous Solutions by Modified Periodic Mesoporous Organosilica. *Journal of Colloid and Interface Science*. 363, 626–634.
- Mukherjee, R. and De, S. (2016). Novel Carbon-Nanoparticle Polysulfone Hollow Fiber Mixed Matrix Ultrafiltration Membrane: Adsorptive Removal of Benzene, Phenol and Toluene from Aqueous Solution. *Separation and Purification Technology*. 157, 229–240.
- Munusamy, T., Ya-Ting, J. and Jiunn-Fwu, L. (2015). Enhanced Adsorption of Inorganic and Organic Pollutants by Amine Modified Sodium Montmorillonite Nanosheets. *RSC Adv.* 5(26), 20583–20594.
- Nabil, G. M., El-Mallah, N. M. and Mahmoud, M. E. (2014). Enhanced Decolorization of Reactive Black 5 Dye by Active Carbon Sorbent-Immobilized-Cationic Surfactant (AC-CS). *Journal of Industrial and Engineering Chemistry*. 20(3), 994–1002.
- Nada, A. M. A., El-Gendy, A. A. and Mohamed, S. H. (2010). Banana Leaves as Adsorbents for Removal of Metal Ions from Waste Water. *Carbohydrate Polymers*. 82, 1028–1030.
- Namasivayam, C. and Sureshkumar, M. V. (2008). Removal of Chromium(VI) from Water and Wastewater Using Surfactant Modified Coconut Coir Pith as A Biosorbent. *Bioresource Technology*. 99(7), 2218–2225.
- Nayyar, S. P., Sabatini, D. A. and Harwell, J. H. (1994). Surfactant Adsolubilization and Modified Admicellar Sorption of Nonpolar, Polar, and Ionizable Organic Contaminants. *Environmental Science and Technology*. 28(11), 1874–1881.
- Neff, J., Lee, K. and DeBlois, E. M. (2011a). Environmental Risks and Advances in Mitigation Technologies. In Lee, K. and Neff, J. (Eds.). *Produced Water*. New York, NY: Springer Science.

- Neff, J., Lee, K. and DeBlois, E. M. (2011b). Overview of Cmposition, Fates, and Effects. In Lee, K. and Neff, J. (Eds.). *Produced Water*. 3–54, New York, NY: Springer Science.
- Neff, J. M. (2002). Chapter 1 Produced Water BT Bioaccumulation in Marine Organisms. In *Bioaccumulation in Marine Organisms*. 1–35, Oxford: Elsevier.
- Nethaji, S. and Sivasamy, A. (2011). Adsorptive Removal of An Acid Dye by Lignocellulosic Waste Biomass Activated Carbon: Equilibrium and Kinetic Studies. *Chemosphere*. 82, 1367–1372.
- Nollet, H., Roels, M., Lutgen, P., Van Der Meeren, P. and Verstraete, W. (2003). Removal of PCBs from Wastewater Using Fly Ash. *Chemosphere*. 53(6), 655–665.
- Nourmoradi, H., Nikaeen, M., Khiadani, H. H. and Hajian, M. K. (2012). Removal of Benzene, Toluene, Ethylbenzene and Xylene (BTEX) from Aqueous Solutions by Montmorillonite Modified with Nonionic Surfactant: Equilibrium, Kinetic and Thermodynamic Study. *Chemical Engineering Journal*. 191, 341–348.
- Ocampo-Pérez, R., Abdel daiem, M. M., Rivera-Utrilla, J., Méndez-Díaz, J. D. and Sánchez-Polo, M. (2012). Modeling Adsorption Rate of Organic Micropollutants Present in Landfill Leachates onto Granular Activated Carbon. *Journal of Colloid* and Interface Science. 385(1), 174–182.
- Ocampo-Perez, R., Leyva-Ramos, R., Alonso-Davila, P., Rivera-Utrilla, J. and Sanchez-Polo, M. (2010). Modeling Adsorption Rate of Pyridine onto Granular Activated Carbon. *Chemical Engineering Journal*. 165(1), 133–141.
- Oei, B. C., Ibrahim, S., Wang, S. and Ang, H. M. (2009). Surfactant Modified Barley Straw for Removal of Acid and Reactive Dyes from Aqueous Solution. *Bioresource Technology*. 100(18), 4292–4295.
- Ofomaja, A. E. (2011). Kinetics and Pseudo-Isotherm Studies of 4-Nitrophenol Adsorption onto Mansonia Wood Sawdust. *Industrial Crops and Products*. 33, 418–428.
- Ogah, A. O., Afiukwa, J. N. and Englund, K. (2014). Characterization and Comparison of Thermal Stability of Agro Waste Fibers in Bio-composites Application. *J. Chem. Eng. Chem. Res.* 1(2), 84–93.
- Ohio Department of Health (2014). *Benzene, Toluene, Ethylbenzene, and Xylenes Where do you find BTEX?* [Pamphlet]. Columbus: Bureau of Environmental Health.

- Ohshima, T., Miyata, T. and Uragami, T. (2005). Selective Removal of Dilute Benzene from Water by Various Cross-Linked Poly(dimethylsiloxane) Membranes Containing Tert-butylcalix[4]arene. *Macromolecular Chemistry and Physics*. 206(24), 2521–2529.
- Onyango, M. S., Kojima, Y., Aoyi, O., Bernardo, E. C. and Matsuda, H. (2004). Adsorption Equilibrium Modeling and Solution Chemistry Dependence of Fluoride Removal from Water by Trivalent-Cation-Exchanged Zeolite F-9. *Journal of Colloid and Interface Science*. 279(2), 341–350.
- Orlando, U. S., Baes, A. ., Nishijima, W. and Okada, M. (2002). A New Procedure to Produce Lignocellulosic Anion Exchangers from Agricultural Waste Materials. *Bioresource Technology*. 83(3), 195–198.
- Paria, S. and Khilar, K. C. (2004). A Review on Experimental Studies of Surfactant Adsorption at the Hydrophilic Solid – Water Interface. Advances in Colloid and Interface Science. 110(3), 75–95.
- Paria, S., Manohar, C. and Khilar, K. C. (2004). Effect of Cationic Surfactant on the Adsorption Characteristics of Anionic Surfactant on Cellulose Surface. *Colloids* and Surfaces A: Physicochemical and Engineering Aspects. 232(2–3), 139–142.
- Park, D., Yun, Y. and Park, J. M. (2010). The Past, Present, and Future Trends of Biosorption. *Biotechnology and Bioprocess engineering*. 15, 86–102.
- Patel, S. (2012). Potential of Fruit and Vegetable Wastes as Novel Biosorbents: Summarizing the Recent Studies. *Reviews in Environmental Science and Biotechnology*. 11, 365–380.
- Pavlova, A. and Ivanova, R. (2003). GC Methods for Quantitative Determination of Benzene in Gasoline. *Acta Chromatograhica*. 13(13), 215–225.
- Quek, A., Zhao, X. and Balasubramanian, R. (2010). Mechanistic Insights into Copper Removal by Pyrolytic Tire Char through Equilibrium Studies. *Industrial & Engineering Chemistry Research*. 49, 4528–4534.
- Ranck, J. M., Bowman, R. S., Weeber, J. L., Katz, L. E. and Sullivan, E. J. (2005). BTEX Removal From Produced Water Using Surfactant Modified Zeolite. *Journal of Environmental Engineering*. 131(1), 434–442.
- Ray, P. Z. and Shipley, H. J. (2015). Inorganic Nano-Adsorbents for the Removal of Heavy Metals and Arsenic: A Review. *RSC Advances*. 5(38), 29885–29907.
- Redding, A. Z., Burns, S. E., Upson, R. T. and Anderson, E. F. (2002). Organoclay Sorption of Benzene as A Function of Total Organic Carbon Content. *Journal of*

Colloid and Interface Science. 250(1), 261–264.

- Reisinger, H. (1997). The Impact of Research Designs on R2 in Linear Regression Models: An Exploratory Meta-Analysis. *Journal of Empirical Generalisations in Marketing Science*. 2, 1–12.
- Rene, E. R., Jo, M. S., Kim, S. H. and Park, H. S. (2007). Statistical Analysis of Main and Interaction Effects during the Removal of BTEX Mixtures in Batch Conditions, Using Wastewater Treatment Plant Sludge Microbes. *International Journal of Environmental Science & Technology*. 4(2), 177–182.
- Saman, N., Johari, K., Song, S.-T., Kong, H., Cheu, S.-C. and Mat, H. (2016). High Removal Efficiency of Hg(II) and MeHg(II) from Aqueous Solution by Coconut Pith—Equilibrium, Kinetic and Mechanism analyses. *Journal of Environmental Chemical Engineering*. 4(2), 2487–2499.
- Saman, N., Johari, K., Song, S. T. and Mat, H. (2014). Removal of Hg(II) and CH3 Hg(I) Using Rasped Pith Sago Residue Biosorbent. *CLEAN - Soil, Air, Water*. 42(11), 1541–1548.
- Sanchez, A. B., Budziak, D., Martendal, E. and Carasek, E. (2012). Determination of Benzene in Beverages by Solid-Phase Microextraction and Gas Chromatography. *Scientia Chromatographica*. 4(3), 209–216.
- Sathasivam, K. and Mas Haris, M. R. H. (2010). Banana Trunk Fibers as An Efficient Biosorbent for the Removal of Cd(II), Cu(II), Fe(II) and Zn(II) from Aqueous Solutions. *Journal of Chilean Chemical Society*. 55(2), 278–282.
- Schulze-Makuch, D., Pillai, S. D., Guan, H., Bowman, R., Couroux, E., Hielscher, F., Totten, J., Espinosa, I. Y. and Kretzschmar, T. (2002). Surfactant-Modified Zeolite Can Protect Drinking Water Wells from Viruses and Bacteria. *Eos, Transactions American Geophysical Union*. 83(18), 193–201.
- Seifi, L., Torabian, A. and Kazemian, H. (2011a). Adsorption of Petroleum Monoaromatics from Aqueous Solutions Using Granulated Surface Modified Natural Nanozeolites : Systematic Study of Equilibrium Isotherms. *Water, Air, & Soil Pollution.* 217, 611–625.
- Seifi, L., Torabian, A., Kazemian, H., Bidhendi, G. N., Azimi, A. A., Farhadi, F. and Nazmara, S. (2011b). Kinetic Study of BTEX Removal Using Granulated Surfactant-Modified Natural Zeolites Nanoparticles. *Water, Air, and Soil Pollution.* 219, 443–457.

Seifi, L., Torabian, A., Kazemian, H., Bidhendi, G. N., Azimi, A. A., Nazmara, S. and

Alimohammadi, M. (2011c). Adsorption of BTEX on Surfactant Modified Granulated Natural Zeolite Nanoparticles : Parameters Optimizing by Applying Taguchi Experimental Design Method. *CLEAN - Soil, Air, Water*. 39(10), 939– 948.

- Serna-Guerrero, R. and Sayari, A. (2007). Applications of Pore-Expanded Mesoporous Silica. 7. Adsorption of Volatile Organic Compounds. *Environmental Science* and Technology. 41(13), 4761–4766.
- Serrano, L., Urruzola, I., Nemeth, D., Bela, K. and Labidi, J. (2011). Modified Cellulose Microfibrils as Benzene Adsorbent. *Desalination*. 270, 143–150.
- Shareef, K. M. (2009). Sorbents for Contaminants Uptake from Aqueous Solutions. Part 1: Heavy Metals. World Journal of Agricultural Sciences. 5, 819–831.
- Sharmasarkar, S., Jaynes, W. F. and Vance, G. F. (2000). BTEX Sorption by Montmorillonite Organo-Clays: TMPA , ADAM, HDTMA. *Water, Air, & Soil Pollution*. 119, 257–273.
- Shayesteh, H., Rahbar-Kelishami, A. and Norouzbeigi, R. (2016). Evaluation of Natural and Cationic Surfactant Modified Pumice for Congo Red Removal in Batch Mode: Kinetic, Equilibrium, and Thermodynamic Studies. *Journal of Molecular Liquids*. 221, 1–11.
- Sheng, G. D., Shao, D. D., Ren, X. M., Wang, X. Q., Li, J. X., Chen, Y. X. and Wang, X. K. (2010). Kinetics and Thermodynamics of Adsorption of Ionizable Aromatic Compounds from Aqueous Solutions by As-Prepared and Oxidized Multiwalled Carbon Nanotubes. *Journal of Hazardous Materials*. 178, 505–516.
- Shibi, I. G. and Anirudhan, T. S. (2005). Adsorption of Co(II) by A Carboxylate-Functionalized Polyacrylamide Grafted Lignocellulosics. *Chemosphere*. 58(8), 1117–1126.
- Shim, H., Ma, W., Lin, A. and Chan, K. (2009). Bio-Removal of Mixture of Benzene,
 Toluene, Ethylbenzene, and Xylenes/Total Petrol
 Hydrocarbons/Trichloroethylene from Contaminated Water. *Journal of Environmental Sciences (China).* 21, 758–763.
- Shin, E. W. and Rowell, R. M. (2005). Cadmium Ion Sorption onto Lignocellulosic Biosorbent Modified by Sulfonation: The Origin of Sorption Capacity Improvement. *Chemosphere*. 60, 1054–1061.
- Simkovic, I. (1999). Preparation of Anion Exchangers from Beech Sawdust and Wheat Straw. *Industrial Crops and Products*. 10(3), 167–173.

- Singh, K. P., Mohan, D., Sinha, S., Tondon, G. S. and Gosh, D. (2003). Color Removal from Wastewater Using Low-Cost Activated Carbon Derived from Agricultural Waste Material. *Industrial & Engineering Chemistry Research*. 42(9), 1965– 1976.
- Slejko, F. L. (1985). Adsorption technology: A step-by-step approach to process evaluation and application. New York: Marcel Dekker Inc.
- Song, S.-T., Hau, Y.-F., Saman, N., Johari, K., Cheu, S.-C., Kong, H. and Mat, H. (2016). Process Analysis of Mercury Adsorption onto Chemically Modified Rice Straw in A Fixed-Bed Adsorber. *Journal of Environmental Chemical Engineering*. 4(2), 1685–1697.
- Song, S. T., Saman, N., Johari, K. and Mat, H. (2013). Removal of Hg (II) from Aqueous Solution by Adsorption Using Raw and Chemically Modified Rice Straw as Novel Adsorbents. *Industrial & Engineering Chemistry Research*. 52, 13092–13101.
- Sparks, D. L. (2002). Environmental Soil Chemistry. (2nd ed.). Cambridge, Massachusetts: Academic Press.
- Štandeker, S., Novak, Z. and Knez, Ž. (2009). Removal of BTEX Vapours from Waste Gas Streams Using Silica Aerogels of Different Hydrophobicity. *Journal of Hazardous Materials*. 165, 1114–1118.
- Strub, M. and Cieszewski, C. J. (2012). The Comparative R-Square and Its Application to Self-Referencing Models. *Mathematical and Computational Forestry and Natural-Resource Sciences (MCFNS)*. 4(2), 73–76.
- Su, F., Lu, C. and Hu, S. (2010a). Adsorption of Benzene, Toluene, Ethylbenzene and p-Xylene by NaOCl-Oxidized Carbon Nanotubes. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 353(1), 83–91.
- Su, F., Lu, C., Johnston, K. R. and Hu, S. (2010b). Kinetics, Thermodynamics, and Regeneration of BTEX Adsorption in Aqueous Solutions via NaOCl-Oxidized Carbon Nanotubes. In *Environanotechnology*. 71–97, Elsevier.
- Sulaymon, A. H. and Abood, W. M. (2014). Removal of Reactive Yellow Dye by Adsorption onto Activated Carbon Using Simulated Wastewater. *Desalination* and Water Treatment. 52(16–18), 3421–3431.
- Teli, M. D. and Valia, S. P. (2013). Acetylation of Banana Fibre to Improve Oil Absorbency. *Carbohydrate Polymers*. 92(1), 328–333.
- Tham, Y. J., Latif, P. A., Abdullah, A. M., Shamala-Devi, A. and Taufiq-Yap, Y. H.

(2011). Performances of Toluene Removal by Activated Carbon Derived from Durian Shell. *Bioresource Technology*. 102(2), 724–728.

- Tiburtius, E. R. L., Peralta-Zamora, P. and Emmel, A. (2005). Treatment of Gasoline-Contaminated Waters by Advanced Oxidation Processes. *Journal of Hazardous Materials*. 126(1–3), 86–90.
- Tiemann, K. J., Gardea-Torresdey, J. L., Gamez, G., Dokken, K., Sias, S., Renner, M.
 W. and Furenlid, L. R. (1999). Use of X-ray Absorption Spectroscopy and Esterification to Investigate Cr (III) and Ni (II) Ligands in Alfalfa Biomass. *Environmental Science & Technology*. 33(1), 150–154.
- Torabian, A., Kazemian, H., Seifi, L., Bidhendi, G. N., Azimi, A. A. and Ghadiri, S. K. (2010). Removal of Petroleum Aromatic Hydrocarbons by Surfactant-Modified Natural Zeolite: The Effect of Surfactant. *Clean - Soil, Air, Water*. 38(1), 77–83.
- Treybal, R. E. (1980). *Mass-Transfer Operations*. (3rd ed.). New York: McGraw Hill Education.
- Tsubochi, M., Yamasaki, N. and Matsuoka, K. (1979). Determination of Anionic Surfactants by Two-Phase Titration with Tetrabromophenolphthalein Ethyl Ester as Indicator. *Journal of the American Oil Chemists' Society*. 56(11), 921–923.
- Uragami, T., Fukuyama, E. and Miyata, T. (2016). Selective Removal of Dilute Benzene from Water by Poly(methyl methacrylate)-Graft-Poly(dimethylsiloxane) Membranes Containing Hydrophobic Ionic Liquid by Pervaporation. *Journal of Membrane Science*. 510, 131–140.
- Vianna, M. M. G. R., Valenzuela-Díaz, F. R., Kozievitch, V. F. J., Dweck, J. and Büchler, P. M. (2005). Synthesis and Characterization of Modified Clays as Sorbents of Toluene and Xylene. *Materials Science Forum*. 498–499, 691–696.
- Vidal, C. B., Raulino, G. S. C., Barros, A. L., Lima, A. C. A., Ribeiro, J. P., Pires, M. J. R. and Nascimento, R. F. (2012). BTEX Removal from Aqueous Solutions by HDTMA-Modified Y Zeolite. *Journal of Environmental Management*. 112, 178–185.
- Vijayaraghavan, K. and Yun, Y. (2008). Bacterial Biosorbents and Biosorption. *Biotechnology Advances*. 26, 266–291.
- Walton, K. S. and Snurr, R. Q. (2007). Applicability of the BET Method for Determining Surface Areas of Microporous Metal-Organic Frameworks. *Journal* of the American Chemical Society. 129(27), 8552–8556.

- Wan Ngah, W. S. and Hanafiah, M. A. K. M. (2008). Removal of Heavy Metal Ions from Wastewater by Chemically Modified Plant Wastes as Adsorbents: A Review. *Bioresource Technology*. 99(10), 3935–3948.
- Wang, X. and Xing, B. (2007). Sorption of Organic Contaminants by Biopolymer-Derived Chars. *Environmental Science & Technology*. 41(24), 8342–8348.
- Weisel, C. P. (2010). Benzene Exposure: An Overview of Monitoring Methods and Their Findings. *Chemico-Biological Interactions*. 184(1–2), 58–66.
- Weschayanwiwat, P., Kunanupap, O. and Scamehorn, J. F. (2008). Benzene Removal from Waste Water Using Aqueous Surfactant Two-Phase Extraction with Cationic and Anionic Surfactant Mixtures. *Chemosphere*. 72(7), 1043–1048.
- Wibowo, N., Setyadhi, L., Wibowo, D., Setiawan, J. and Ismadji, S. (2007). Adsorption of Benzene and Toluene from Aqueous Solutions onto Activated Carbon and Its Acid and Heat Treated Forms: Influence of Surface Chemistry on Adsorption. *Journal of Hazardous Materials*. 146, 237–242.
- Windsor, R., Neivandt, D. J. and Davies, P. B. (2002). Temperature and pH Effects on The Coadsorption of Sodium Dodecyl Sulfate and Poly(ethylenimine). *Langmuir*. 18, 2199–2204.
- Wiśniewski, M., Furmaniak, S., Kowalczyk, P., Werengowska, K. M. and Rychlicki, G. (2012). Thermodynamics of Benzene Adsorption on Oxidized Carbon Nanotubes – Experimental and Simulation Studies. *Chemical Physics Letters*. 538, 93–98.
- Wu, Z. and Lee, K. (2004). Adsorption Mechanisms of Mesoporous Adsorbents in Solutions. *Chemical Research in Chinese Universities*. 20(2), 185–187.
- Xie, F., Lu, Q., Toledo, R. A. de and Shim, H. (2016). Combined Removal of An MTBE and BTEX Mixture Using Indigenous Microbe Immobilized on Waste Silica Gel. International Journal of Environmental Science and Development. 7(4), 244–247.
- Xie, J., Meng, W., Wu, D., Zhang, Z. and Kong, H. (2012). Removal of Organic Pollutants by Surfactant Modified Zeolite: Comparison between Ionizable Phenolic Compounds and Non-Ionizable Organic Compounds. *Journal of Hazardous Materials*. 231–232, 57–63.
- Yakout, S. M. and Daifullah, A. A. M. (2013). Adsorption/Desorption of BTEX on Activated Carbon Prepared from Rice Husk. *Desalination and Water Treatment*. 52(22–24), 4485–4491.

- You, L., Lu, F., Song, L., Yin, Y. and Zhang, Q. (2015). Enhanced Decolorization of Aqueous Dye Solutions by A High Quality Copolymer Flocculant. *RSC Adv*. 5(79), 64711–64723.
- Yu, F., Wu, Y., Li, X. and Ma, J. (2012). Kinetic and Thermodynamic Studies of Toluene, Ethylbenzene, and m-Xylene Adsorption from Aqueous Solutions onto KOH-Activated Multiwalled Carbon Nanotubes. *Journal of Agricultural and Food Chemistry*. 60(50), 12245–12253.
- Zhang, P., Whistler, R. L., Bemiller, J. N. and Hamaker, B. R. (2005). Banana Starch : Production, Physicochemical Properties, and Digestibility — A Review. *Carbohydrate Polymers*. 59, 443–458.
- Zhang, R., Zhang, J., Zhang, X., Dou, C. and Han, R. (2014). Adsorption of Congo Red from Aqueous Solutions Using Cationic Surfactant Modified Wheat Straw in Batch Mode: Kinetic and Equilibrium Study. *Journal of the Taiwan Institute* of Chemical Engineers. 45, 2578–2583.
- Zhang, W., Li, H., Kan, X., Dong, L., Yan, H., Jiang, Z., Yang, H., Li, A. and Cheng,
 R. (2012a). Adsorption of Anionic Dyes from Aqueous Solutions Using Chemically Modified Straw. *Bioresource Technology*. 117, 40–47.
- Zhang, W., Qu, Z., Li, X., Wang, Y., Ma, D. and Wu, J. (2012b). Comparison of Dynamic Adsorption/Desorption Characteristics of Toluene on Different Porous Materials. *Journal of Environmental Sciences*. 24(3), 520–528.
- Zhang, W., Yan, H., Li, H., Jiang, Z., Dong, L., Kan, X., Yang, H., Li, A. and Cheng,
 R. (2011). Removal of Dyes from Aqueous Solutions by Straw Based Adsorbents:
 Batch and Column Studies. *Chemical Engineering Journal*. 168(3), 1120–1127.
- Zhao, B., Xiao, W., Shang, Y., Zhu, H. and Han, R. (2014). Adsorption Behavior of Light Green Anionic Dye Using CationicWheat Straw in Batch and Column Mode. *Environmental Science and Pollution Research*. 20(8), 5558–5568.
- Zhou, Y., Zhang, L. and Cheng, Z. (2015). Removal of Organic Pollutants from Aqueous Solution Using Agricultural Wastes: A Review. *Journal of Molecular Liquids*. 212, 739–762.
- Zuluaga, R., Putaux, J.-L., Restrepo, A., Mondragon, I. and Gañán, P. (2007). Cellulose Microfibrils from Banana Farming Residues: Isolation and Characterization. *Cellulose*. 14(6), 585–592.
- Zytner, R. G. (1994). Sorption of Benzene, Toluene, Ethylbenzene and Xylenes to Various Media. *Journal of Hazardous Materials*. 38, 113–126.