

SYNTHESIS AND CHARACTERIZATION OF GRAPHENE NANOSHEETS
SUPPORTED PLATINUM NANOCOMPOSITE AS CATALYST FOR
METHANOL OXIDATION

MOHAMAD FAHRUL RADZI BIN HANIFAH

A thesis submitted in fulfillment of the
requirements for the award of the degree of
Master of Science (Chemistry)

Faculty of Science
Universiti Teknologi Malaysia

OCTOBER 2015

DEDICATIONS

To my beloved father and mother,

Allahyarham Hanifah Bin Abdul Karim

&

Puan Hamrah Binti Haron

To my siblings

To my uncles and aunties

To my friends

And

To those who are always gave me the support towards the success of this research.

ACKNOWLEDGEMENTS

In the name of Allah swt, the most gracious, the most merciful.

We glorify Allah swt and ask blessings and salutations of peace for the noble prophet Muhammad (peace be upon him) and his companions and those who follow him in up-holding the cause of the right religion.

First and foremost, I would like to express my gratitude to both of my supervisors, Dr. Juhana Jaafar and Prof. Dr. Madzlan Aziz for their enthusiasm, moral support, encouragement, great advices and concern against to my research work. Within the duration of my research, they have given a good supervision and always created a positive research environment which made the research enjoyable.

Special thanks to the members of Advanced Membrane Technology Research Centre (AMTEC) and faculty of science for their assistance, especially Mr. Ihsan Wan Azelee, Mr. Mohd Zharif Mohd Thirmizir, Mr. Mohammad Abdul Razis Saidin, Miss. Nurfarahidayu, Miss. Nuraidayu, Madam Siti Munira Jamil and others. I would also like to thanks Madam Hamitul Asma Ghazali, Madam Suhaila Borhamdin, Mr. Ng Be Cheer, Mr. Mohd Hanis, Madam Amy Zuria, Miss. Siti Zhahara and Tan Yi Hong for their valuable assistance in all technical work.

Thanks to the Ministry of Education Malaysia for financial support under My Brain 15 (My Master) and Universiti Teknologi Malaysia to carry out this study. Last but not least, I would like extend my sincere acknowledge and thanks to my parents, lecturers from Faculty of Science and AMTEC who supported me throughout the duration of this study.

ABSTRACT

Platinum (Pt) is a noble metal catalyst that is most frequently used as the anode catalyst in direct methanol fuel cell (DMFC) because of its superior catalytic activity performance as compared to other metal catalysts. Besides the merit, Pt catalyst is expensive and also contributes to the problem of Pt poisoning by carbon monoxide (CO) during the methanol oxidation which can reduce the performance of DMFC. The use of carbonaceous material which is graphene nanosheets (GNS) as catalyst support for Pt catalyst can reduce the cost and enhance the catalytic property. Since the GNS have large surface area, the Pt nanoparticles can be dispersed uniformly onto the surface of GNS. Therefore, the main objective of this research is to synthesis and characterize the GNS supported Pt catalyst nanocomposite for methanol oxidation in DMFC. The nanocomposite from GNS and Pt catalyst precursor was fabricated by chemical reduction method using sodium borohydride as reducing agent. The physiochemical properties of the prepared graphene oxide nanosheets, GNS and the catalytic activity performance of GNS/Pt nanocomposite catalyst were successfully studied. Extensive characterization of the produced GNS as catalyst support in terms of morphology, structure, thermal stability and electrical conductivity property were conducted. The results showed that the prepared GNS possess high electrical conductivity of 7.65 S cm^{-1} thus indicated a highly potential catalyst support. HRTEM and FESEM analysis showed well-dispersed Pt nanoparticles on the surface of GNS with small average particle size around 3.33 nm obtained. The findings were consistent with the XRD data ($\sim 4.47 \text{ nm}$) obtained. The catalytic activities of GNS/Pt nanocomposites were measured by cyclic voltammogram. The electrochemical surface area (ECSA) of GNS/Pt nanocomposite catalyst was 0.36 cm^2 larger than Vulcan XC-72/Pt (0.25 cm^2) and graphite/Pt (0.14 cm^2) catalysts. It has been found that GNS/Pt nanocomposite catalyst has better catalytic activity and high stability than Vulcan XC-72/Pt and graphite/Pt catalysts for methanol oxidation reaction. As a conclusion, the GNS/Pt nanocomposite catalyst fabricated in this study possesses appropriate characteristics to be used as anode catalyst in DMFC system.

ABSTRAK

Platinum (Pt) adalah mangkin logam yang paling kerap digunakan sebagai pemangkin anod dalam sel bahan api metanol terus (DMFC) kerana keunggulan prestasi aktiviti pemangkin berbanding mangkin logam yang lain. Selain daripada merit tersebut, mangkin Pt adalah mahal dan ia juga menyumbang kepada masalah keracunan Pt dengan karbon monoksida (CO) semasa pengoksidaan metanol yang boleh mengurangkan prestasi DMFC. Penggunaan bahan berasaskan karbon iaitu kepingan nano grafena (GNS) sebagai penyokong untuk mangkin Pt boleh mengurangkan kos dan meningkatkan aktiviti pemangkin. Oleh kerana GNS mempunyai luas permukaan yang besar, maka zarah nano Pt boleh tersebar secara sekata pada keseluruhan permukaan GNS. Oleh itu, objektif utama penyelidikan ini adalah untuk mensintesis dan mencirikan komposit nano mangkin Pt yang disokong oleh GNS bagi pengoksidaan metanol dalam DMFC. Komposit nano daripada GNS dan bahan pemula mangkin Pt difabrikasikan melalui kaedah penurunan kimia menggunakan natrium borohidrida sebagai agen penurun. Sifat fisiokimia kepingan nano grafena oksida, GNS dan prestasi aktiviti pemangkin daripada komposit nano GNS/Pt telah berjaya dikaji. Pencirian secara menyeluruh ke atas GNS yang dihasilkan sebagai penyokong mangkin daripada segi morfologi, struktur, kestabilan terma dan sifat kekonduksian elektrik telah dijalankan. Hasil kajian menunjukkan bahawa GNS yang disediakan memiliki kekonduksian elektrik yang tinggi iaitu 7.65 S cm^{-1} dan ini menunjukkan potensi yang tinggi sebagai penyokong mangkin. Analisis HRTEM dan FESEM menunjukkan penyebaran zarah nano Pt secara sekata pada permukaan GNS dengan purata saiz zarah yang kecil sekitar 3.33 nm telah diperolehi. Penemuan ini selaras dengan data XRD ($\sim 4.47 \text{ nm}$) yang diperolehi. Aktiviti pemangkin komposit nano GNS/Pt telah diukur melalui voltamogram berkitar. Luas permukaan elektrokimia (ECSA) mangkin komposit nano GNS/ Pt adalah 0.36 cm^2 lebih besar daripada mangkin Vulkan XC-72/ Pt (0.25 cm^2) dan grafit/ Pt (0.14 cm^2). Mangkin komposit nano GNS/ Pt didapati mempunyai aktiviti pemangkin yang lebih baik dan kestabilan yang lebih tinggi berbanding dengan mangkin Vulkan XC-72/Pt dan mangkin grafit/Pt untuk tindak balas pengoksidaan metanol. Kesimpulannya, mangkin komposit nano GNS/Pt yang telah difabrikasi dalam kajian ini mempunyai ciri-ciri yang sesuai untuk digunakan sebagai mangkin anod dalam sistem DMFC.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENTS	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xii
	LIST OF FIGURES	xiv
	LIST OF ABBREVIATIONS	xviii
	LIST OF SYMBOLS	xxi
	LIST OF APPENDICES	xxii
1	INTRODUCTION	1
	1.1 Research Background	1
	1.2 Problem Statement	3
	1.3 Significance of Study	5
	1.4 Objective of Study	5
	1.5 Scopes of the Study	6

2	LITERATURE REVIEW	7
2.1	Introduction	7
2.2	Fuel Cell	8
2.3	Direct Methanol Fuel Cell (DMFC)	9
2.4	Operating Principles of DMFC	11
2.4.1	Drawbacks of DMFC	13
2.4.1.1	The weaknesses of the polymer electrolyte membrane	13
2.4.1.2	Limited activity of the anode Catalyst	14
2.4.2	Reaction Mechanism of Methanol Oxidation	14
2.5	The Development of Hybrid Alloy of Pt Catalyst for DMFC	16
2.6	Carbonaceous Materials as the Catalyst Support for DMFC	20
2.6.1	Carbon Black (CB)	20
2.6.2	Carbon Nanotube (CNT)	21
2.6.3	Carbon Nanofiber (CNF)	23
2.6.4	Graphene	24
2.6.4.1	Graphene Oxide as the Precursor	25
2.6.4.2	Determination of the effect of GO reduction	29
2.6.4.2.1	Visual Observation	29
2.6.4.2.2	X-ray photoelectron Spectroscopy (XPS) analysis	30
2.6.4.2.3	Raman Spectra Analysis	32
2.6.4.2.4	Electrical Conductivity	33
2.6.4.3	Chemical reduction of GO	34
2.7	The Current Development of Carbonaceous	

	Materials supported Pt Nanocomposite Catalyst for DMFC	38
3	RESEARCH METHODOLOGY	44
3.1	Introduction	44
3.2	Chemicals	46
3.3	Preparation of Materials	46
3.3.1	Synthesis of Graphene Oxide Nanosheets	46
3.3.2	Preparation of Graphene Nanosheets (GNS)	47
3.3.3	Fabrication of GNS/Pt Nanocomposite Catalyst	48
3.4	Characterization of Synthesized Materials	49
3.4.1	FTIR Analysis	50
3.4.2	UV-vis Analysis	50
3.4.3	X-ray Diffraction Analysis	50
3.4.4	¹³ C NMR Analysis	51
3.4.5	X-ray Photoelectron Spectroscopy Analysis	51
3.4.6	Raman Spectra Analysis	51
3.4.7	Morphological Analysis	51
3.4.8	Thermal Stability Analysis	52
3.4.9	Electrical Conductivity Analysis	52
3.5	Electrocatalytic Performance Study	53
3.5.1	Preparation of GNS/Pt nanocomposite catalyst working electrode	53
4	SYNTHESIS AND PHYSICOCHEMICAL PROPERTIES OF GRAPHENE NANOSHEETS	54
4.1	Process Oxidation of Graphite Powder	54
4.2	Possible Deoxygenation Reaction of GO	55
4.3	Plausible Reduction Mechanism of GO	56

4.4	Physicochemical properties of GNS as electrocatalyst support	61
4.4.1	Structural analysis	61
4.4.2	Morphology analysis	71
4.4.3	Thermal stability analysis	73
4.4.4	Electrical conductivity analysis (room temperature)	74
4.5	Conclusion	75

5	FABRICATION OF GRAPHENE NANOSHEETS SUPPORTED PLATINUM NANOCOMPOSITE CATALYST FOR METHANOL OXIDATION	76
5.1	Fabrication of GNS/Pt Nanocomposite Catalyst	76
5.2	Plausible Mechanism for the Formation of GNS/Pt Nanocomposites Catalyst	77
5.3	Characterization of GNS/Pt Nanocomposite Catalyst	79
5.3.1	Structural Analysis	79
5.3.1.1	X-ray Diffraction Analysis	79
5.3.1.2	Raman Spectrometry	80
5.3.1.3	X-Ray Photoelectron Spectroscopy	82
5.3.2	Morphological Analysis	84
5.3.2.1	HRTEM analysis	84
5.3.2.2	FESEM analysis	87
5.4	Electrochemical Characterizations of GNS/Pt Nanocomposite Catalyst	90
5.5	Electrochemical Oxidation of Methanol on GNS/Pt Nanocomposite Catalyst	92
5.6	Conclusion	94

6	CONCLUSIONS AND RECOMMENDATIONS	95
6.1	Overall Conclusions	95
6.2	Recommendations	97
	LIST OF PUBLICATIONS	99
	REFERENCES	101
	Appendices A-B	119-121

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Advantages of DMFC	10
2.2	The properties of DMFC	11
2.3	Hybrid alloy of Pt catalyst for DMFC	19
2.4	Summary for synthesis of GO via Hummers' method and its modification	27
2.5	Some of reducing agents used for chemical reduction of GO	36
2.6	Carbonaceous materials supported Pt nanocomposite catalysts for DMFC	41
3.1	Experimental parameters involved in producing GNS	48
4.1	Fitting XRD data summary of d-value for graphite, GO and GNS-3	61
4.2	Summary of FTIR results for GO, GNS-1, GNS-2 and GNS-3	64
4.3	Results summary of GO and GNS-3 from XPS	69
4.4	Summary of the value of electrical conductivity for GO, GNS-1, GNS-2 and GNS-3	74
5.1	Fitting of XRD data summary for GNS/ Pt nanocomposite catalyst	79
5.2	Results summary of GNS/Pt catalyst from XPS	84

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	Schematic diagram of Fuel cell	9
2.2	Schematic diagram of operating process of direct methanol fuel cell	12
2.3	Plausible of methanol oxidation via Pt catalyst	15
2.4	Schematic representation of different path of the MOR mechanism	15
2.5	CV curves of polycrystalline Pt electrode, nanoporous Pt (A) and Pt–Ru (B):(a) in 0.5M H ₂ SO ₄ at 20 mVs ⁻¹ and (b) in 0.1 MCH ₃ OH + 0.5 M H ₂ SO ₄ at 20 mVs ⁻¹	17
2.6	Cyclic voltammograms curve of Pt nanorod, Pt/Ru nanorods with 3-layers, Pt/Ru nanorods with 7-layers, and Pt/Ru nanorods with 13-layers in Ar-purged 0.5 M H ₂ SO ₄ at 50 mV s ⁻¹ .	18
2.7	(A) The structure of (a) armchair, (b) zigzag and (c) chiral SWCNTs. (B) the structure of MWCNT made up of three shells of differing chirality	22
2.8	The ilustration of three types of CNFs	23
2.9	An illustration of graphene oxide structure based on Lerf-Klinowski model	26
2.10	The typical visual images of (A) GO film and rGO film (B) GO suspension (left) and RGO suspension (right)	30
2.11	(a) C 1s spectra of GO (b) C 1s spectra of graphene	31

2.12	Raman spectra of GO and graphene sheet	33
2.13	CV curves for GNR/Pt, MWCNT/Pt and commercial Vulcan XC-72R/Pt (40 wt% Pt) catalyst measured in (A) 0.5 M H ₂ SO ₄ and (B) 0.5 M H ₂ SO ₄ + 1M CH ₃ OH aqueous solutions with a scan rate of 50 mV s ⁻¹	40
3.1	Flowchart of research activities	45
3.2	(a) Digital images of oxidation process of graphite in an ice bath and (b) the GO slurry	47
3.3	Digital image for preparation process of GNS/Pt nanocomposite catalyst	49
4.1	The synthesis pathway for the formation of GNS from GO via chemical reduction process	56
4.2 (a)	Possible mechanism of reduction of carbonyl groups in GO	57
4.2 (b)	Possible mechanism for reduction of hydroxyl groups in GO	58
4.2 (c)	Plausible mechanism for reduction of carboxyl groups in GO	59
4.2 (d)	Plausible mechanism for reduction of epoxide groups in GO	60
4.3	XRD spectra of GO, GNS-1, GNS-2, GNS-3 and pristine graphite	62
4.4	FTIR spectra for GO, GNS-1, GNS-2 and GNS-3	63
4.5	UV-vis absorption spectra for GO, GNS-1, GNS-2 and GNS-3	65
4.6	Solid-state ¹³ C NMR spectra of (a) GO and (b) GNS-3	66
4.7	XPS survey scans of GO and GNS-3	67
4.8	(a) C 1s spectra for GO (b) C 1s spectra for GNS-3.	68
4.9	Raman spectra of GO and GNS-3	70
4.10	TEM images of (a) GO, (b) GNS-2, (c) GNS-3, HRTEM image layers for (d) GNS-2 and (e, f) GNS-3	71
4.11	HRTEM image layers for (a) GNS-2 and (b, c) GNS-3	72

4.12	TGA curves of (a) GO and (b) GNS-3	73
5.1	The illustration of synthesis pathway of GNS/Pt nanocomposite catalyst	77
5.2	Plausible mechanism of formation of GNS/Pt nanocomposite catalyst	78
5.3	XRD pattern of GNS/Pt nanocomposite catalyst	80
5.4	First-order (a) and second-order (b) Raman spectra of GNS and GNS/Pt nanocomposite catalyst.	81
5.5	XPS spectra of GNS/ Pt nanocomposite catalyst: (a) survey scans spectrum; (b) Pt 4f; (c) C 1s; and (d) O 1s	83
5.6	HRTEM images of (a) GNS (b) GNS edges (c), (d) and (e) HRTEM image of GNS/ Pt nanocomposite catalyst with different magnification, (f) Histogram of Pt nanoparticles distribution of GNS/ Pt nanocomposite catalyst, (g) HRTEM images of GNS/ Pt nanocomposite catalyst with lattice fringes measurement.	86
5.7	FESEM images of (a) GO, (b) GNS, (c) and (d) GNS/Pt nanocomposites catalyst, (e) EDX spectrum for GNS/Pt nanocomposite catalyst	89
5.8	FESEM images of (a) and (b) Vulcan XC-72/Pt catalyst with different magnification, (c) and (d) graphite/Pt catalyst with different magnification.	
5.9	Cyclic voltammograms of (a) GNS/Pt nanocomposite catalyst (b) Vulcan XC-72/Pt catalyst (c) graphite/Pt catalyst in 0.5 M H ₂ SO ₄ at a scan rate of 50 mV s ⁻¹	90
5.10	CV of (a) GNS/Pt nanocomposite catalyst (b) Vulcan XC-72/Pt catalyst (c) graphite/Pt catalyst in 0.5 M H ₂ SO ₄ containing 1.0 M of CH ₃ OH at a scan rate of 50 mV s ⁻¹ .	93

LIST OF ABBREVIATIONS

^{13}C NMR	- ^{13}C Carbon Nuclear Magnetic Resonance
2D	- 2-Dimensional
3D	- 3-Dimensional
AFC	- Alkaline fuel cell
C/O	- Carbon to Oxygen ratio
CB	- Carbon Black
CNF	- Carbon Nanofiber
CNT	- Carbon nanotube
CO	- Carbon monoxide
CV	- Cyclic Voltammogram
CVD	- Chemical Vapor Deposition
DC-PECVD	- Direct Current Plasma-Enhanced Chemical Vapor Deposition
DMFC	- Direct methanol fuel cell
DWCNT	- Di-Wall Carbon Nanotube
ECSA	- Electrochemical Active Surface Area
EDX	- Energy Dispersive X-ray
FC	- Fuel Cell
FESEM	- Field emission scanning electron microscopy
FTIR	- Fourier transform infrared
GNF	- Graphitic Nanocarbon
GNS	- Graphene nanosheets
GO	- Graphene oxide Nanosheets
HRTEM	- High resolution - transmission electron microscopy

MCFC	- Molten carbonate fuel cell
MOR	- Methanol Oxidation Reaction
MWCNT	- Multi-Wall Carbon Nanotube
NASA	- National Aeronautics and Space Administration
OAD	- Oblique Angle Deposition
PAFC	- Phosphoric acid fuel cell
PC	- Personal Computer
PECVD	- Plasma-Enhanced Chemical Vapor Deposition
PEMFC	- Proton exchange membrane fuel cell
PFI	- Perfluorinated Ionic
POM	- Polyoxometalates
Pt	- Platinum
Pt-Ru	- Platinum-Ruthenium
rGO	- reduced Graphene Oxide
RT	- Room Temperature
SOFC	- Solid oxide fuel cell
SWCNT	- Single Wall Carbon Nanotube
TCF	- Transparent Conductive Films
TEM	- Transmission electron microscopy
TGA	- Thermogravimetric Analysis
UV-Vis Spectrophotometry	- Ultra Violet -Visible Spectrophotometry
VGCNF	- Vapor Grown Carbon Nanofiber
XPS	- X-Ray Photoelectron Spectroscopy
XRD	- X-Ray Diffractometer

LIST OF SYMBOLS

d	-	Average particle size
π	-	Mathematical constant (~ 3.142)
θ	-	Angle
λ	-	Wavelength
$\beta_{1/2}$	-	Width of the peak at half height in radians
ρ	-	Resistivity
σ	-	Conductivity

LIST OF APPENDICES

A	Mathematical Expressions for Determination the Crystallite Size of Platinum Nanoparticles from the XRD pattern	119
B	Mathematical Expressions for Determination the Electrochemical Active Surface Area (ECSA)	120

CHAPTER 1

INTRODUCTION

1.1 Research Background

Fuel cells have received much attention as the most promising alternative energy sources. Based on 'reverse electrolysis' concept of converting a fuel directly into electrical energy, fuel cells have several advantages such as high efficiency, low environmental impact and flexible application. Therefore, the great efforts to develop and design fuel cells as new power sources have been devoted due to the increasing concern of environmental issues and the depletion of fossil fuels for the last few decades (Sundmacher, 2010). The basic principal of a fuel cell is to directly convert the chemical energy into electricity and heat. Among the type of fuel cells, direct methanol fuel cell (DMFC) is one of the most promising fuel cell for the environmentally friendly energy conversion system. DMFC is a promising alternative to rechargeable batteries due to the high energy density of 6.1 kWh kg^{-1} of the methanol fuel used in the DMFC (McGrath *et al.*, 2004) and high efficiency of the fuel cell system itself (Li and Faghri, 2012). In general, DMFC consists of a proton exchange membrane or polymer electrolyte membrane in between catalyst layer and diffusion layer at either side of anode and cathode which porous electro-catalytic electrodes are attached.

DMFC have been extensively studied and persistent attention in recent years due to some advantages such as ease of handling liquid fuels (McGrath *et al.*, 2004), low pollutant emission, high energy conversion efficiency and low operating temperature (Basri *et al.*, 2010). These advantages are important for portable electronic devices such as laptop, computers, smart phones and MP3 players since it has been developed at rapid pace and demanding ever-increasing energy and power density in rechargeable batteries (Li and Faghri, 2012). However, the commercialization of DMFCs is still inhibited by some critical barriers such as the high cost of Platinum (Pt) electrocatalyst (Cheng *et al.*, 2013), the poisoning of the electrocatalyst by CO-like species at the anode and the slow electrooxidation kinetics of methanol at relatively low temperatures (Huang *et al.*, 2012). According to Huang *et al.*, (2012), the development of a novel class of electrocatalyst with higher poison tolerance and greater methanol oxidation activity is the best ideal to overcome the problems as stated above. Many attempts have been carried out in order to enhance the electrocatalytic activity and CO tolerance of catalysts such as preparing alloying metal catalyst (Tian *et al.*, 2007) and preparing Pt and its alloy with different morphology (Chen *et al.*, 2004; Liang *et al.*, 2004).

Nowadays, the adoption of novel carbon materials as the catalyst support arises great interest to achieve high catalytic activity toward methanol oxidation reaction such as multi-wall carbon nanotube (Jha *et al.*, 2008), carbon nanofiber (Guo *et al.*, 2006) and graphene (Dong *et al.*, 2010). According to Han *et al.*, (2003), the performance and stability of DMFCs are strongly dependent on the characteristics of carbon support as well as catalytic active species. A significant enhancement in DMFCs performance have been brought by using carbon materials with a desirable characteristics such as good crystallinity and high surface area. Therefore, the fabrication of catalyst supports together with a low platinum loading is an attractive goal in DMFC technology.

1.2 Problem Statement

Platinum (Pt) is a noble metal catalyst that most frequently used as the anode electro-catalyst in DMFC application because of its superiority catalytic activity performance. However, the high cost of Pt issue is the major obstacle in the commercial application of DMFC (Liu *et al.*, 2012). In addition, the efficiency of Pt-based electro-catalyst in DMFC is limited with the consequence of highly Pt poisoning by carbon monoxide (CO). CO is an intermediate product produced during the oxidation process of methanol or impurities (Bambagioni *et al.*, 2009). This intermediate causes the slow of electro-oxidation kinetic due to its adsorption to the active site of Pt catalyst. Thus causes a significant loss in DMFC performance.

Based on these drawbacks, many researchers have made some efforts to produce alternative catalyst via modification of Pt to another metal with the decrease of Pt content. The most Pt-based alloy used as anode catalyst in DMFC is Pt-Ru. Pt-Ru is the predominant binary electro-catalyst since it has the capability to exhibit significant activity for methanol electro-oxidation as well as the removal of the poisoning CO or CHO species. However, previous studies have shown that the use of Pt-Ru catalyst still requires high loading which is lead to high cost and the durability issue is one of the serious problems due to the dissolution of Ru under fuel cell conditions (Kanninen *et al.*, 2012).

Therefore, in order to reduce the cost and improve the activity of electro catalyst, there is a need to develop the platinum-based catalyst with conductive support usually carbon black which can greatly influence to enhance the dispersion, activation and stability of metal catalyst, electrochemical behavior as well as increasing the electro-conductivity (Liu *et al.*, 2012). Carbon black is a carbon-based materials that are the most widely used in anode electrocatalyst support. Typically, carbon blacks are always found in commercial electrocatalyst for DMFC. This is because carbon black has the high electrical conductivity (Hall *et al.*, 2004).

Unfortunately, there are some disadvantages of using carbon black in which related to pore size distribution and surface chemistry affects (Liu *et al.*, 2012).

Nowadays, many of the new and novel carbon-based nanomaterials have been developed to replace carbon black as electrocatalyst supports such as carbon nanotubes (Song *et al.*, 2010), carbon nanofibers (Sebastian *et al.*, 2012) and graphene (Ji *et al.*, 2012). In recent years, graphene as electrocatalyst support has given a rise attention in fuel cell application and shown a great promising material due to its unique characteristics such as high surface area, high stability and large surface to volume ratio (Geim and Novoselov, 2007), strong mechanical property (Lee *et al.*, 2008), electrical conductivity (Service, 2009) and thermal conductivity (Balandin *et al.*, 2008). Graphite powder can be used as the raw material to produce graphene through the formation of graphene oxide by oxidation with acid using modified Hummer's method and subsequently chemical reduction process. According to Liu *et al.*, (2012), the stability and dispersion of electrocatalyst is greatly influenced by the physicochemical properties of the electrocatalyst support, the highly distributed of small size catalyst nanoparticles and narrow distribution due to the large surface-to-volume ratios. Therefore, the development of highly disperse electrocatalyst onto the support is still a great challenge.

In the present work, the fabrication of the graphene nanosheets supported Pt nanocomposite catalyst (GNS/Pt) via the impregnation and chemical reduction method by using sodium borohydride as reducing agent for methanol oxidation reaction at the anode electrode in DMFC was investigated. This Pt electrocatalyst incorporation with graphene nanosheets as the electrocatalyst support has the capability to enhance the electrocatalytic activity for methanol oxidation reaction at the anode in DMFC (Qian *et al.*, 2011).

1.3 Significance of Study

The significance of this study lies in the fact that the fabrication of this Pt nanocomposite catalyst can increase the rate of methanol oxidation reaction at the anode electrode in DMFC. Furthermore, the method used to fabricate the nanocomposite catalysts are very simple, clean, easy to handle and no time consuming. Therefore, the fabrication of this GNS/Pt nanocomposites catalyst can contribute to the significance benefits in term of processing method and the performance of DMFC.

1.4 Objective of study

Based on the aforementioned research background and problem statement identified, the main objective of this study is to develop the Pt-based catalyst by incorporating with graphene nanosheets as catalyst support with improved catalytic properties. Thus, the specific objectives include the following:

- i. To synthesis and characterize the graphene oxide nanosheets and graphene nanosheets.
- ii. To fabricate and characterize the GNS/Pt nanocomposite catalyst.
- iii. To evaluate the catalytic performance of GNS/Pt nanocomposite catalyst for methanol oxidation reaction at the anode.

1.5 Scopes of the study

In order to achieve the aforementioned objectives, the following scopes are drawn:

- i. Preparing graphene oxide nanosheets (GO) via modified Hummers' method.
- ii. Preparing graphene nanosheets via chemical reduction process using sodium oxalate ($\text{Na}_2\text{C}_2\text{O}_4$) as the reducing agent at 95°C with varying the reduction time for 30 minutes, 1 hour and 2 hours.
- iii. Characterizing of GO and GNS by using XRD, TEM, HRTEM, UV-Vis Spectrophotometry, FTIR, XPS, Raman Spectroscopy, solid ^{13}C NMR and TGA.
- iv. The electrical conductivity characterization of GO and GNS using Four Point Probe measurement method.
- v. Preparing GNS/Pt nanocomposite catalyst via impregnation and chemical reduction method simultaneously using sodium borohydride as reducing agent at 85°C with the reduction time for 3 hours.
- vi. The GNS/Pt nanocomposite catalyst characterization using XRD, HRTEM, FESEM, EDX, Raman spectrometer and XPS.
- vii. Testing the electrocatalytic properties of GNS/Pt nanocomposite catalyst via cyclic voltammogram.
- viii. Preparing Vulcan XC-72/Pt catalyst and graphite/Pt catalyst as control sample for comparison in term of catalytic performance with GNS/Pt nanocomposite catalyst.

REFERENCES

- Ai, K., Liu, Y., Lu, L., Cheng, X., Huo, L. (2011). A novel strategy for making soluble reduced graphene oxide sheets cheaply by adopting an endogenous reducing agent, *J. Mater. Chem.*, 21: 3365-3370.
- Al-Saleh, M. H. and Sundararaj, U. (2009). A review of vapor grown carbon nanofiber/polymers conductive composite. *Carbon* 47: 2-22.
- Amamath, C. A., Hong, C. E., Kim, N. H., Ku, B. C., Kuila, T., Lee, J. H. (2011). Efficient synthesis of graphene sheets using pyrrole as a reducing agent. *Carbon* 49: 3497-3502.
- Andujar, J.M. and Segura, F. (2009). Fuel cells: History and updating. A walk along two centuries. *Renewable and Sustainable Energy Reviews* 13: 2309-2322.
- Arico, A.S., Srinivasan, S. and Antonucci, V. (2001). DMFCs: from fundamental aspects to technology development. *Fuel Cells*. 1(1):133-161.
- Baglio, V., Stassi, A., di Blasi, A., D'Urso, C., Antonucci, V. and Aricò, A. S. (2007). "Investigation of bimetallic Pt-M/C as DMFC cathode catalysts," *Electrochimica Acta*, 53 (3): 1360–1364.
- Bai, H., Li, C. and Shi, G. Q. (2011). Functional composite materials based on chemically converted graphene. *Advanced Materials* 23 (9): 1089-1115.
- Balandin, A. A., Ghosh, S., Bao, W., Calizo, I., Teweldebrhan, D., Miao, F., Lau, C. N. (2008). Superior Thermal Conductivity of Single-Layer Graphene. *Nano Letter*. 8 (3): 902–907.
- Bambagioni, V., Bianchini, C., Marchionni, A., Filippi, J., Vizza, F., Teddy, J., Serp, P., Zhiani, M. (2009). Pd and Pt–Ru anode electrocatalysts supported on multi-walled carbon nanotubes and their use in passive and active direct alcohol fuel

- cells with an anion-exchange membrane (alcohol =methanol, ethanol, glycerol). *Journal of Power Sources* 190: 241–251.
- Barreiro, A., Kramberger, C., Rummeli, M. H., Neis, A. G., Grimm, D., Hampel, S. (2007). Control of the single-wall carbon nanotube mean diameter in sulphur promoted aerosol-assisted chemical vapour deposition. *Carbon* 45: 55-61.
- Basko, D. M. and Piscanec, S. (2009). Electron-electron interaction and doping dependence of two-phonon Raman intensity in graphene, *Phys. Rev. B* 80: 165413.
- Basri, S. and Kamarudin, S. K. (2011). Process system engineering in direct methanol fuel cell. *International Journal of Hydrogen Energy* 36 (10): 6219–6236.
- Basri, S., Kamarudin, S. K., Daud, W. R. W. and Yaakub, Z. (2010). Nanocatalyst for direct methanol fuel cell (DMFC), *International Journal of Hydrogen Energy* 35: 7957-7970.
- Bozbag, S. E. and Erkey, C. (2012). Supercritical fluids in fuel cell research and development. *Journal of Supercritical Fluids*. 60: 1-31.
- Chang, H. W., Chang, H. W., Tsai, Y. C., Cheng, C. W., Lin, C. Y., Wu, P. H. (2012). Reduction of graphene oxide in aqueous solution by femtosecond laser and its effect on electroanalysis *Electrochem. Commun.* 23: 37-40.
- Changgu, L., Xiaoding, W., Jeffrey, W. K., James, H. (2008). Measurement of the Elastic Properties and Intrinsic Strength of Monolayer Graphene. *Science*. 321 (5887): 385-388.
- Chen, H., Duan, J., Zhang, X., Zhang, Y., Guo, C., Nie, Li, Liu, X. (2014). One step synthesis of Pt/ CeO₂-graphene catalyst by icrowave-asissted ethylene glycol process for direct methanol fuel cell. *Materials Letters* 126: 9-12.
- Chen, D., Li, L. and Guo, L. (2011). An environment-friendly preparation of reduced graphene oxide nanosheets via amino acid. *Nanotechnology* 22: 325601.
- Chen, W. X., Lee, J. Y., Liu. Z. (2004). Preparation of Pt and PtRu nanoparticles supported on carbon nanotubes by microwave-assisted heating polyol process. *Materials Letters* 58 (25): 3166–3169.
- Cheng, Y., Jiang, S. P. (2013). Highly effective and CO-tolerant PtRu electrocatalysts supported on poly (ethyleneimine) functionalized carbon nanotubes for direct methanol fuel cells. *Electrochimica Acta* 99: 124-132.

- Choi, H. J., Jung, S. M., Seo, J. M., Chang, D. W., Dai, L. M., Baek, J. B. (2012). Graphene for energy conversion and storage in fuel cells and supercapacitors. *Nano Energy* 1 (4): 534-551.
- Choi, J. H., Park, K. W., Park, I. S., Nam, W. H. and Sung, Y. E. (2004). Methanol electro-oxidation and direct methanol fuel cell using Pt/Rh and Pt/Ru/Rh alloy catalysts, *Electrochimica Acta* 50: 787–790.
- Compton, O. C., Jain, B., Dikin, D. A., Abouimrane, A., Amine, K, Nguyen, S. T. (2011). Chemically active reduced graphene oxide with tunable C/O ratios. *ACS Nano* 5: 4380.
- Crawley, G. (2007). Opening doors to fuel cell commercialization-Direct methanol fuel cell. *Fuel Cell Today*.
- Deivaraj, T.C., Chen, W. and Lee, J. Y. (2003). Preparation of Pt-Ni Nanoparticles for the Electrocatalytic Oxidation of Methanol. *J. Mater. Chem.* **13**: 2555-2560.
- Deng, Y. J., Tian, N., Zhou, Z. Y., Huang, R., Liu, Z. L., Xiao, J., and Sun. S. G. (2012). Alloy tetrahedral Pd–Pt catalysts: enhancing significantly the catalytic activity by synergy effect of high-index facets and electronic structure *Chem. Sci.* 3: 1157.
- Dicks, A. L. (2006). The role of carbon in fuel cells. *J. Power Sources* 156: 128-141.
- Dong, L., Gari, R. R. S., Li, Z., Craig, M. M., Hou, S. (2010). Graphene-supported Platinum and Platinum–Ruthenium nanoparticles with high electrocatalytic activity for methanol and ethanol oxidation. *Carbon* 48: 781 –787.
- Dreyer, D. R., Park, S., Bielawski, C. W., Ruoff, R. S. (2010). The chemistry of graphene oxide. *Chem Soc Rev* 39 (1): 228–40.
- Dubosc, M., Casimirus, S., Besland, M. P., Cardinaud, C., Granier, A., Duvail, J. L. (2007). Impact of the Cu-based substrates and catalyst deposition techniques on carbon nanotube growth at low temperature by PECVD. *Microelectronic Engineering* 84: 2501-5.
- Durrer, L., Helbling, T., Zenger, C., Jungen, A., Stampfer, C. and Hierold, C. (2008). SWNT growth by CVD on Ferritin-based iron catalyst nanoparticles towards CNT sensors. *Sensors and Actuators B: Chemical* 132: 485-90.
- Duy, D. Q., Kim, H. S., Yoon, D. M., Lee, K. J., Ha, J. W., Hwang, Y. G. (2009). Growth of carbon nanotubes on stainless steel substrates by DC-PECVD. *Applied Surface Science* 256: 1065-8.

- Ebbesen, T. W., Ajayan, P. M. (1992). Large-scale synthesis of carbon nanotubes, *Nature* 358: 220 – 222.
- Eda, G., Fanchini, G. and Chhowalla, M. (2008). Large-area ultrathin films of reduced graphene oxide as a transparent and flexible electronic material, *Nat. Nanotechnol.* 3: 270.
- Fan, X., Peng, W., Li, Y., Li, X., Wang, S., Zhang, G. and Zhang, F. (2008). Deoxygenation of Exfoliated Graphite Oxide under Alkaline Conditions: A Green Route to Graphene Preparation. *Adv. Mater.* 20: 4490–4493.
- Fan, Z., Wang, K., Wei, T., Yan, J., Song, L., Shao, B. (2010). An environmentally friendly and efficient route for the reduction of graphene oxide by aluminum powder. *Carbon* 48: 1670 –1692.
- Fernandez-Merino, M. J., Guardia, L., Paredes, J. I., Villar-Rodil, S., Solis-Fernandez, P., Martinez-Alonso, A. (2010). Vitamin C is an ideal substitute for hydrazine in the reduction of graphene oxide suspensions. *J Phys Chem C* 114 (14): 6426–32.
- Ferrari, A. C., Meyer, J. C., Scardaci, V., Casiraghi, C., Lazzeri, M., Mauri, F., Piscanec, S., Jiang, D., Novoselov, K. S., Roth, S., Geim, A. K. (2006). Raman spectrum of graphene and graphene layers, *Phys. Rev. Lett.* 97: 187401.
- Fuel Cell Bulletin. (2005). Quest Air signs deals to market, supply hydrogen purification. Elsevier Ltd. doi: 10.1016/S1464-2859(05)70700-8.
- Fujiwara, N., Yasuda, K., Ioroi, T., Siroma, Z., Miyazaki, Y. (2002). Preparation of platinum_ruthenium onto solid polymer electrolyte membrane and the application to a DMFC anode. *Electrochimica Acta* 47: 4079-4084.
- Gao, L., Ding, L., Fan, L. (2013). Pt nanoflower/ graphene-layered composites by ZnO nanoparticle expansion of graphite and their enhanced electrocatalytic activity for methanol oxidation. *Electrochimica Acta* 106: 159-164.
- Gao, J., Liu, F., Liu, Y., Ma, N., Wang, Z. and Zhang, X. (2010). Environment-Friendly Method to Produce Graphene That Employs Vitamin C and Amino Acid. *Chem. Mater.* 22: 2213-2218.
- Gao, W., Alemany, L. B., Ci, L. and Ajayan, P. M. (2009). New insights into the structure and reduction of graphite oxide. *Nat Chem* 1(5):403–8.
- Gao, X. and Tang, X. (2014). Effective reduction of graphene oxide thin films by a fluorinating agent: Diethylaminosulfur trifluoride, *Carbon* 76: 133–140.

- Geim, A. K. and Novoselov, K. S. (2007). The rise of graphene. *Nature Materials* 6: 83-191.
- Ghadim, E. E., Rashidi, N., Kimiagar, S., Akhavan, O., Manouchehri, F. and Ghaderi, E. (2014). Pulsed laser irradiation for environment friendly reduction of graphene oxide suspensions. *Appl. Surf. Sci.* 301: 183-188.
- Guo, J., Sun, G., Wang, Q., Wang, G., Zhou, Z., Tang, S., Jiang, L., Zhou, B., Xin, Q. (2006). Carbon nanofibers supported Pt–Ru electrocatalysts for direct methanol fuel cells *Carbon* 44 (1): 152–157.
- Gurunathan, S., Han, J. W., Eppakayala, V. and Kim, J. H. (2013). Green synthesis of graphene and its cytotoxic effects in human breast cancer cells. *International Journal of Nanomedicine* 8: 1015–1027.
- Gurunathan, S., Han, J. W., Eppakayala, V., Kim, J. H. (2013). Microbial reduction of graphene oxide by *Escherichia coli*: A green chemistry approach. *Colloids and Surfaces B: Biointerfaces* 102: 772– 777.
- Hall, S. C., Subramanian, V., Teeter, G., Rambabu, B. (2004). Influence of metal–support interaction in Pt/C on CO and methanol oxidation reactions. *Solid State Ionics* 175: 809–813.
- Hanifah, M. F. R., Jaafar, J., Aziz, M., Ismail, A. F., Othman, M. H. D., Rahman, M. A., Norddin, M. N. A. M., Yusof, N. and Salleh, W. N. W. (2015). Efficient reduction of graphene oxide nanosheets using $\text{Na}_2\text{C}_2\text{O}_4$ as a reducing agent, *Functional Materials Letters* 8 (2): 15500261-15500265.
- Harrison, W. L. (2002). *Synthesis and characterization of sulfonated poly (arylene ether sulfone) copolymers via direct copolymerization: candidates for proton exchange membrane fuel cells*. Virginia Polytechnic Institute and State University. PhD thesis.
- Hassan, H. B. (2009). Electrodeposited Pt and Pt-Sn nanoparticles on Ti as anodes for direct methanol fuel cells. *Journal of Fuel Chemistry and Technology* 37 (3): 346–354.
- Huang, J., Yang, H., Huang, Q., Tang, Y., Lu, T., Akins, D. L. (2004). Methanol Oxidation on Carbon-Supported Pt-Os Bimetallic Nanoparticle Electrocatalysts. *J. Electrochem. Soc.* 151 (11): A1810-A1815.
- Huang, M., Dong, G., Wu, C., Guan, L. (2014). Preparation of highly dispersed Pt nanoparticles supported on single-walled carbon nanotubes by a microwave-

- assisted polyol method and their remarkably catalytic activity. *International Journal of Hydrogen Energy* 39: 4266-4273.
- Huang, Y., Cai, J. and Guo, Y. (2012). "Roles of Pb and MnO_x in PtPb/MnO_x-CNTs catalyst for methanol electro-oxidation," *International Journal of Hydrogen Energy*, 37(2): 1263– 1271.
- Jha, N. and Ramaprabhu, S. (2008). Enhancement of thermal conductivity in copper nanoparticles decorated multiwalled carbon nanotubes based nanofluids. *J Phys Chem C* 112: 9315-9.
- Ji, K., Chang, G., Oyama, M., Shang, X., Liu, X., He, Y. (2012). Efficient and clean synthesis of graphene supported platinum nanoclusters and its application in direct methanol fuel cell. *Electrochimica Acta* 85: 84– 89.
- Ji, Y., Liu, Q., Cheng, M., Lai, L., Li, Z., Peng, Y. and Yang, Y. (2013). Facile synthesis of reduced graphene oxide nanosheets by a sodium diphenylamine sulfonate reduction process and its electrochemical property. *J. Mater. Sci. Eng. C* 33: 3811-3816.
- Jin, Y., Huang, S., Zhang, M., Jia, M. and Hu, D. (2013). A green and efficient method to produce graphene for electrochemical capacitors from graphene oxide using sodium carbonate as a reducing agent. *Applied Surface Science* 268: 541– 546.
- Joo, J. B., Kim, N. D., Yun, H. J., Kim, P. and Yi, J. (2011). Preparation of highly crystalline graphitic nanocarbon for the electro-oxidation of methanol. *Nano Res.* 4 (1): 92-102.
- Kang, D. and Shin, H. S. (2012). Control of size and physical properties of graphene oxide by changing the oxidation temperature. *Carbon Lett.* 13: 39.
- Kang, Y. and Christopher B. (2010). Murray Synthesis and Electrocatalytic Properties of Cubic Mn–Pt Nanocrystals (Nanocubes) *J. Am. Chem. Soc.* 132 (22):7568–7569.
- Kanninen, P., Borgheib, M., Ruizb, V., Kauppinenb, E.I., Kallioa, T. (2012). The effect of Nafion content in a graphitized carbon nanofiber-based anode for the direct methanol fuel cell. *International Journal of Hydrogen Energy.* 37 (24): 19082-19091.
- Khaligh, A., Rahimi, A. M., Young-Joo, L., Jian, C. J., Emadi, A., Andrews, S. D., Robinson, C. and Finnerty C, F. (2007). Digital control of an isolated active

- hybrid fuel cell/Li-ion battery power supply. *IEEE Transactions on Vehicular Technology* 56 (6): 3709–21.
- Kim, N. H., Kuila, T., Lee, J. H. (2013). Simultaneous reduction, functionalization and stitching of graphene oxide with ethylenediamine for composites application *J. Mater. Chem. A*, 1: 1349-1358.
- Kim, T. and Kwon, S. (2008). MEMS fuel cell system for portable power source: integration of methanol reformer, PROX, and fuel cell. *IEEE 21st International Conference on Micro Electro Mechanical Systems (MEMS)* 1:980–3.
- Kim, Y. I., Soundararajan, D., Park, C. W., Kim, S. H., Park, J. H. and Ko, J. M. (2009). Electrocatalytic Properties of Carbon Nanofiber Web-Supported Nanocrystalline Pt Catalyst as Applied to Direct Methanol Fuel Cell. *Int. J. Electrochem. Sci.*, 4: 1548 – 1559.
- Kou, R., Shao, Y. Y., Wang, D. H., Engelhard, M. H., Kwak, J. H., Wang, J., Viswanathan, V. V., Wang, C. M., Lin, Y. H., Wang, Y., Aksay, I. A., Liu, J. (2009). Enhanced activity and stability of Pt catalysts on functionalized graphene sheets for electrocatalytic oxygen reduction. *Electrochemistry Communications* 11: 954-957.
- Kudin, K. N., Ozbas, B., Schniepp, H. C., Prud'homme R. K., Aksay, I. A., Car, R. (2007). Raman spectra of graphite oxide and functionalized graphene sheets. *Nano Lett* 8 (1): 36–41.
- Lee, C., Wei, X., Kysar, J. W., Hone, J. (2008). Measurement of the Elastic Properties and Intrinsic Strength of Monolayer Graphene. *Science* 321: 385.
- Lee, S. A., Park, K. W., Choi, J. H., Kwon, B. K., Sung, Y. E. (2002). Nanoparticle synthesis and electrocatalytic activity of Pt alloys for direct methanol fuel cells. *Journal of the Electrochemical Society* 149: A1299-A1304.
- Lee, S., Lee, K. and Zhong, Z. (2010). Wafer Scale Homogeneous Bilayer Graphene Films by Chemical Vapor Deposition. *Nano Lett.* 10: 4702-4707.
- Li, D., Muller, M.B., Gilje, S., Kaner, R. B., Wallace, G.G. (2008). Processable aqueous dispersions of graphene nanosheets. *Nature Nanotechnology* 3(2): 101-105.
- Li, S., Yu, X., Zhang, G., Ma, Y., Yao, J. and Oliveira, P. (2011). Green synthesis of a Pt nanoparticle/polyoxometalate/carbon nanotube tri-component hybrid and its activity in the electrocatalysis of methanol oxidation. *Carbon*. 49 (6): 1906–1911.

- Li, W., Liang, C., Zhou, W., Qiu, J., Zhou, Z., Sun, G. and Xin, Q. (2003). Preparation and Characterization of Multiwalled Carbon Nanotube-Supported Platinum for Cathode Catalysts of Direct Methanol Fuel Cells. *J. Phys. Chem. B* 107: 6292-6299.
- Li, X. and Faghri, M. (2012). Optimization of the Cathode Structure of Lithium-Air Batteries Based on a Two-Dimensional, Transient, Non-Isothermal Model. *Journal Electrochemistry Society*. 159 (10): A1747-A1754.
- Li, Y., Tang, L., Li, J. (2009). Preparation and electrochemical performance for methanol oxidation of Pt/graphene nanocomposites. *Electrochemistry Communications* 11: 846–849.
- Li, Z., Li, M., Han, M., Zeng, J., Li, Y., Guo, Y. and Liao, S. (2014). Preparation and characterization of carbon-supported PtOs electrocatalysts via polyol reduction method for methanol oxidation reaction. *Journal of Power Sources* 268: 824-830.
- Liang, Q., Zhang, L., Cai, M., Li, Y., Jiang, K., Zhang, X., Shen, P. K. (2013). Preparation and characterization of Pt/ functionalized graphene and its electrocatalysis for methanol oxidation. *Electrochimica Acta* 111: 275-283.
- Liang, H. P., Zhang, H.M., Hu, J. S., Guo, Y. G. (2004). Pt hollow nanospheres: facile synthesis and enhanced electrocatalysts. *Angew Chem Int Ed*. 116(12):1566–1569.
- Liu, P., Huang, Y. and Wang, L. (2013). Synthesis of reduced graphene oxide using indole as a reducing agent and preparation of reduced graphene oxide-Ag nanocomposites. *Synthetic Metals* 167: 25– 30.
- Liu, Y., Gokcen, D., Bertocci, U., Moffat, T. P. (2012). Self-Terminating Growth of Platinum Films by Electrochemical Deposition. *Science*. 338 (6112): 1327-1330.
- Liu, Y., Huang, Y., Xie, Y., Yang, Z., Huang, H., Zhou, Q. (2012). Preparation of highly dispersed CuPt nanoparticles on ionic-liquid-assisted graphene sheets for direct methanol fuel cell. *Chemical Engineering Journal* 197: 80–87.
- Lopez, V., Sundaram, R. S., Gomez-Navarro, C., Olea, D., Burghard, M., Gomez-Herrero, J. (2009). Chemical vapor deposition repair of graphene oxide: a route to highly-conductive graphene monolayers. *Adv Mater* 21 (46): 4683–6.

- Luo, B., Yan, X., Xu, S., Xue, Q. (2012). Polyelectrolyte functionalization of graphene nanosheets as support for platinum nanoparticles and their applications to methanol oxidation. *Electrochimica Acta* 59: 429-434.
- Ma, C., Liu, W., Shi, M., Lang, X., Chu, Y., Chen, Z., Zhao, D., Lin, W., Hardacre, C. (2013). Low loading platinum nanoparticles on reduced graphene oxide-supported tungsten carbide crystallites as a highly active electrocatalyst for methanol oxidation. *Electrochimica Acta* 114: 133-141.
- Makris, T. D., Giorgi, L., Giorgi, R., Lisi, N. and Salernitano, E. (2005). CNT growth on alumina supported nickel catalyst by thermal CVD. *Diamond & Related Materials* 14:815-9.
- Marcano, D. C., Kosynkin, D. V., Berlin, J. M., Sinitskii, A., Sun, Z., Slesarev, A., Alemany, L. B., Lu, W., Tour, J. M. (2010). Improved synthesis of graphene oxide. *ACS Nano* 4: 4806.
- Martínez-Huerta, M. V., Tsiouvaras, N., Peñna, M. A., Fierro, J. L. G., Rodríguez, J. L. and Pastor, E. (2010). "Electrochemical activation of nanostructured carbon-supported PtRuMo electrocatalyst for methanol oxidation," *Electrochimica Acta*, 55 (26): 7634–7642.
- McAllister, M. J., Li, J. L., Adamson, D. H., Schniepp, H. C., Abdala, A. A., Liu, J., Herrera-Alonso, M., Milius, D. L., Car, R., Prud'homme, R. K. and Aksay, I. A. (2007). Single Sheet Functionalized Graphene by Oxidation and Thermal Expansion of Graphite. *Chem. Mater.* 19, 4396-4404.
- McGrath, K. M., Prakash, G. K. S., and Olah, G. A. (2004). Direct methanol fuel cells. *J. Ind. Eng. Chem.* 10, 1063–80.
- McKee, G. S. B., Decka, C. P. and Vecchio, K. S. (2009). Dimensional control of multi-walled carbon nanotubes in floating-catalyst CVD synthesis. *Carbon* 47:2085-94.
- Mitra, M., Chatterjee, K., Kargupta, K., Ganguly, S., Banerjee, D. (2013). Reduction of graphene oxide through a green and metal-free approach using formic acid. *Diamond & Related Materials* 37: 74–79.
- Mkhoyan, K. A., Contryman, A. W., Silcox, J., Stewart, D. A., Eda, G., Mattevi, C. (2009). Atomic and electronic structure of graphene-oxide. *Nano Lett* 9 (3): 1058–63.

- Morante-Catacora, T. Y., Ishikawa, Y., Cabrera, C. R. (2008). Sequential electrodeposition of Mo at Pt and PtRu methanol oxidation catalyst particles on HOPG surfaces. *Journal of Electroanalytical Chemistry* 621 (1):103–112.
- Nethravathi, C., Anumol, E. A., Rajamathi, M., Ravishankar, N. (2011). Highly dispersed ultrafine Pt and PtRu nanoparticles on graphene: formation mechanism and electrocatalytic activity. *Nanoscale* 3: 569–571.
- Neto, A. O., Dias, R. R., Tusi, M. M., Linardi, M., Spinacé, E. V. (2007). Electro-oxidation of methanol and ethanol using PtRu/C, PtSn/C and PtSnRu/C electrocatalysts prepared by an alcohol-reduction process. *Journal of Power Sources* 166: 87-91.
- Novoselov, K. S., Geim, A. K., Morozov S. V., Jiang, D., Zhang, Y., S.Dubonos, S. V., Grigorieva I. V. and Firsov A. A. (2004). Electric Field Effect in Atomically Thin Carbon Films. *Science*: 306 (5696):666-669.
- Othman, M.H.D. (2006). *Development and characterization of sulfonated poly (ether ether ketone)/ boron orthophosphate composite membrane for direct methanol fuel cell application*. Universiti Teknologi Malaysia. MSc Thesis.
- Pandey, D., Reifengerger, R., Piner, R. (2008). Scanning probe microscopy study of exfoliated oxidized graphene sheets. *Surf Sci* 602 (9): 1607–13.
- Paredes, J. I., Villar-Rodil, S., Alonso, A. M., Tascon, J. M. D. (2008). Graphene oxide dispersions in organic solvents. *Langmuir* 24: 10560.
- Paredes, J. I., Villar-Rodil, S., Fernandez, S., Martinez-Alonso, A., Tascon, J. M. D. (2009). Atomic force and scanning tunneling microscopy imaging of graphene nanosheets derived from graphite oxide, *Langmuir* 25: 5957.
- Park, S., An, J. H., Piner, R. D., Jung, I., Yang, D. X., Velamakanni, A., Nguyen, S. T., Ruoff, R. S. (2008). Aqueous suspension and characterization of chemically modified graphene sheets, *Chem. Mater.* 20: 6592.
- Park, Y. C., Peck, D. H., Kim, S. K., Lim, S., Jung, D. H. and Lee, D. Y. (2011). Operation of a direct methanol fuel cell stack by self-heating at low temperatures. *International Journal of Hydrogen Energy* 36:5655-5665.
- Pei, S. and Cheng, H. M. (2012). The reduction of graphene oxide. *Carbon* 50: 3210-3228.
- Pei, S., Zhao, J., Du, J., Ren, W. and Cheng, H-M. (2010). Direct reduction of graphene oxide films into highly conductive and flexible graphene films by hydrohalic acids, *Carbon* 48(15):4466–74.

- Peng, X., Koczur, K. and Chen, A. (2007). Synthesis and characterization of ruthenium-decorated nanoporous platinum materials, *Nanotechnology* 18: 305605.
- Pham, T. A., Kim, J. K., Kim, J. S. and Jeong, Y. T. (2011). One-step reduction of graphene oxide with l-glutathione, *Colloids and Surfaces A: Physicochem. Eng. Aspects* 384: 543-548.
- Pham, V. H., Pham, H. D., Dang, T. T., Hur, S. H., Kim, E. J., Kong, B. S., Kima, S. and Chung, J. S. (2012). Chemical reduction of an aqueous suspension of graphene oxide by nascent hydrogen. *J. Mater. Chem.*, 22: 10530.
- Qian, Y., Wang, C. and Z. G. Le, Z. G. (2011). Decorating graphene sheets with Pt nanoparticles using sodium citrate as reductant, *Appl. Surf. Sci.* 257: 10758-10762.
- Qiao, Y. and Li, C. M. (2011). Nanostructured catalysts in fuel cells. *Journal of Material Chemistry*. 21 (12): 4027-4036.
- Sahoo, S., Bhattacharya, P., Hatui, G., Ghosh, D. and C. K. (2013). Sonochemical Synthesis and characterization of amine-modified graphene/conducting polymer nanocomposites. *J. Appl. Polym. Sci.*, DOI: 10.1002/APP.38285.
- Sandoval-González, Borja-Arco, E., Escalante, J., Jiménez- Sandoval, O., and Gamboa, S.A. (2012). Methanol oxidation reaction on PtSnO₂ obtained by microwave-assisted chemical reduction. *International Journal of Hydrogen Energy*, 37 (2): 1752– 1759.
- Satheesh, K. and Jayavel, R. (2013). Synthesis and electrochemical properties of reduced graphene oxide via chemical reduction using thiourea as a reducing agent, *Mater. Lett.* 113: 5-8.
- Schniepp, H. C., Li, J. L., McAllister, M. J., Sai, H., Herrera-Alonso, M., Adamson, D. H. (2006). Functionalized single graphene sheets derived from splitting graphite oxide, *J Phys Chem B* 110 (17): 8535–9.
- Sebastián, D., Lázaro, M. J., Suelves, I., Moliner, R., Baglio, V., Stassi, A., Aricò, A. S. (2012). The influence of carbon nanofiber support properties on the oxygen reduction behavior in proton conducting electrolyte-based direct methanol fuel cells, *International Journal of Hydrogen Energy* 37 (7): 6253–6260.
- Service, R. F. (2009). Carbon Sheets an Atom Thick Give Rise to Graphene Dreams, *Science*. 324: 875.

- Shao, G., Lu, Y., Wu, F., Yang, C., Zeng, F., Wu, Q. (2012). Graphene oxide: the mechanism of oxidation and exfoliation, *J. Mater. Sci.* 47: 4400.
- Sharma, S. and Pollet, B. G. (2012). Support materials for PEMFC and DMFC electrocatalysts: A review, *Journal of Power Sources* 208: 96-119.
- Sharma, S., Ganguly, A., Papakonstantinou, P., Miao, X., Li, M., Hutchison, J. L., Delichatsios, M. and Ukleja, S. (2010). Rapid Microwave Synthesis of CO Tolerant Reduced Graphene Oxide-Supported Platinum Electrocatalysts for Oxidation of Methanol, *J. Phys. Chem. C* 114 (45): 19459–19466.
- Song, P., Zhang, X., Sun, M., Cui, X. and Lin, Y. (2012). Synthesis of graphene nanosheets via oxalic acid-induced chemical reduction of exfoliated graphite oxide. *RSC Advances* 2: 1168–1173.
- Song, S., Qin, Y., He, Y., Huang, Q., Fan, C., Chen, H. Y. (2010). Functional nanoprobes for ultrasensitive detection of biomolecules *Chem. Soc. Rev.* 39: 4234-4243.
- Spiegel, R. J., Preston, J. L. (2003). Technical assessment of fuel cell operation on anaerobic digester gas at the Yonkers, NY, wastewater treatment plant. *Waste Management* 23 (8): 709–17.
- Stankovich, S., Dikin, D. A., Dommett, G.H., Kohlhaas, K.M., Zimney, E.J., Stach, E.A., Piner, R. D., Nguyen, S.T., Ruoff, R.S. (2006). Graphene-based composite materials. *Nature* 442 (7100): 282-286.
- Stankovich, S., Dikin, D. A., Piner, R. D., Kohlhaas, K. A., Kleinhammes, A., Jia, Y. (2007). Synthesis of graphene-based nanosheets via chemical reduction of exfoliated graphite oxide. *Carbon* 45(7):1558–1565.
- Stankovich, S., Piner, R. D., Chen, X. Q., Wu, N. Q., Nguyen, S. T., Ruoff, R. S. (2006). Stable aqueous dispersions of graphitic nanoplatelets via the reduction of exfoliated graphite oxide in the presence of poly (sodium 4-styrenesulfonate). *J. Mater. Chem.* 16: 155.
- Steigerwalt, E. S., Deluga, G. A., Lukehart, C. M. (2002). Pt-Ru/Carbon fiber nanocomposites: synthesis, characterization and performance as anode catalysts of direct methanol fuel cell. A search for exceptional performance. *Journal Physical Chemistry B.* 106 (4): 760-766.
- Su, Q., Pang, S., Alijani, V., Li, C., Feng, X. and Mullen, K. (2009). Composites of graphene with large aromatic molecules. *Adv Mater* 21 (31): 3191–5.

- Subrahmanyam, K. S., Panchakarla, L. S., Govindaraj, A., Rao, C. N. R. (2009). Simple Method of Preparing Graphene Flakes by an Arc-Discharge Method. *J. Phys. Chem. C* 113: 4257.
- Sundmacher, K. (2010). Fuel Cell Engineering: Towards the Design of Efficient Electrochemical Power Plants (Oral). *Industrial and Engineering Chemistry Research*. 49: 10159-10182.
- Szabo', T., Berkesi, O., Forgo', P., Josepovits, K., Sanakis, Y., Petridis, D. (2006). Evolution of surface functional groups in a series of progressively oxidized graphite oxides. *Chem Mater* 18(11): 2740–9.
- Takamura, T., Endo, K., Fu, L., Wu, Y., Lee, K. J., Matsumoto, T. (2007). Identification of Nano-Sized Holes by TEM in the Graphene Layer of Graphite and the High Rate Discharge Capability of Li-ion Battery Anodes. *Electrochimica Acta* 53: 1055-1061.
- Thess, A., Lee, R., Nikolaev, P., Dai, H., Petit, P., Robert, J., Xu, C., Lee, Y. H., Kim, S. G., Rinzler, A. G., Colbert, D. T., Scuseria, G. E., Tomanek, D., Fischer, J. E., Smalley, R. E. (1996). Crystalline Ropes of Metallic Carbon Nanotubes *Science* 273(5274):483-7.
- Tian, N., Zhou, Z. –Y., Sun, S. –G., Ding, Y., Zhong, L. W. (2007). Synthesis of tetrahedral platinum nanocrystals with high-index facets and high electro-oxidation activity. *Science* 316 (5825): 732–735.
- Tibbetts, G. G., Lake, M. L., Strong, K. L. and Rice, B. P. (2007). A review of the fabrication and properties of vapor-grown carbon nanofiber/polymer composites. *Composites Science and Technology* 67:1709-18.
- Tiwari, J. N., Tiwari, R. N., Singh, G., Kim, K. S. (2013). Recent progress in the development of anode and cathode catalysts for direct methanol fuel cells. *Nano Energy* 2: 553–578.
- Toh, S. Y., Loh, K. S., Kamarudin, S. K. and Daud, W. R. W. (2014). Graphene production via electrochemical reduction of graphene oxide: Synthesis and characterization. *Chemical Engineering Journal* 251: 422–434.
- Tong, Y., Hee, S. K., Babu, P. K., Waszczuk, P., Wieckowski, A. and Oldfield, E. (2002). “An NMR investigation of CO tolerance in a Pt/Ru fuel cell catalyst,” *Journal of the American Chemical Society* 124 (3): 468–473.
- Vinayan, B. P., Jafri, R. I., Nagar, R., Rajalakshmi, N., Sethupathi, K. and Ramaprabhu, S. (2012). “Catalytic activity of platinumcobalt alloy

- nanoparticles decorated functionalized multiwalled carbon nanotubes for oxygen reduction reaction in PEMFC,” *International Journal of Hydrogen Energy*, 37 (1): 412–421.
- Viswanathan, B., Scibioh, M. A. (2007). *Fuel Cells: Principles and application, universities press*, Hyderabad, India.
- Wade, Jr., L. G. (2010). *Organic Chemistry*, 7th edn. (Pearson education, USA).
- Wang, C., Li, H., Zhao, J., Zhu, Y., Yuan, W. Z. and Zhang, Y. (2013). Graphene nanoribbons as a novel support material for high performance fuel cell electrocatalysts. *International Journal of Hydrogen Energy* 38: 13230-13237.
- Wang, G., Yang, J., Park, J., Gou, X., Wang, B., Liu, H. and Yao, J. (2008). Facile Synthesis and Characterization of Graphene Nanosheets. *J. Phys. Chem. C* 112, 8192-8195.
- Wang, X., Zhi, L. J. and Mullen, K. (2008). Transparent, conductive graphene electrodes for dye-sensitized solar cells. *Nano Lett.* 8: 323-327.
- Whitener Jr., K. E. and Sheehan, P. E. (2014). Graphene synthesis. *Diamond & Related Materials* 46: 25–34.
- Williamson, S.S., Emadi, A., Shahidehpour, M. (2004). Distributed fuel cell generation in restructured power systems. *IEEE Power Engineering Society General Meeting* 2 (10): 2079–84.
- Winter, M. and Brodd, R. J. (2004). “What Are Batteries, Fuel Cells, and Supercapacitors?” *Chemical Reviews*. 104 (10): 4245-4269.
- Winters, D. (2005). *Fuel cells past, present and future*. Technology Assessment Division. Louisiana Department of Natural Resources.
- Wong, H. –S. P and Deji Akinwande, D. (2011). *Carbon Nanotube and Graphene Device Physics*, 1st edn. (Cambridge university press, UK).
- Woo, S., Lee, J., Park, S. K., Kim, H., Chung, T. D. and Piao, Y. (2015). Electrochemical codeposition of Pt/graphene catalyst for improved methanol oxidation. *Current Applied Physics* 15: 219-225.
- Wu, G., Huang, H., Chen, X., Cai, Z., Jiang, Y. and Chen, X. (2013). Facile synthesis of clean Pt nanoparticles supported on reduced graphene oxide composites: Their growth mechanism and tuning of their methanol electrocatalytic oxidation property. *Electrochimica Acta* 111: 779– 783.

- Wu, T., Gao, J., Xu, X., Wang, W., Gao, C. and Qiu, H. (2013). A new rapid chemical route to prepare reduced graphene oxide using copper metal nanoparticles. *Nanotechnology* 24: 215604.
- Xiao, M., Zhu, J., Ge, J., Liu, C., Xing, W. (2015). The enhanced electrocatalytic activity and stability of supported Pt nanoparticles for methanol electro-oxidation through the optimized oxidation degree of carbon nanotubes. *Journal of Power Sources* 281: 34-43.
- Xiong, B., Zhou, Y. K., Zhao, Y. Y., Wang, J., Chen, X., O'Hayre, R., Shao, Z. P. (2013). The use of nitrogen-doped graphene supporting Pt nanoparticles as a catalyst for methanol electrocatalytic oxidation. *Carbon* 52: 181–192.
- Xu, C., Hou, J., Pang, X., Li, X., Zhu, M. and Tang, B. (2012). “Nanoporous PtCo and PtNi alloy ribbons for methanol electrooxidation,” *International Journal of Hydrogen Energy*, 37: 10489–10498.
- Xu, X., Zhou, Y., Lu, J., Tian, X., Zhu, H., Liu, J. (2014). Single-step synthesis of PtRu/N-doped graphene for methanol electrocatalytic oxidation. *Electrochimica Acta* 120: 439–451.
- Xu, Y., Sheng, K., Li, C., Shi, G. (2011). Highly conductive chemically converted graphene prepared from mildly oxidized graphene oxide. *J. Mater. Chem.* 21: 7376.
- Yang, D., Velamakanni, A., Bozoklu, G., Park, S., Stoller, M., Piner, R. D., Stankovich, S., Jung, I., Field, D. A., Ventrice Jr., C. A. and Ruoff, R. S. (2009). Chemical analysis of graphene oxide films after heat and chemical treatments by X-ray photoelectron and micro-Raman spectroscopy. *Carbon* 47: 145.
- Yang, J. H., Qiu, L. H., Liu, B. Q., Peng, Y. J., Yan, F., Shang, S. M. (2011). Synthesis of Polymeric Ionic Liquid Microsphere/Pt Nanoparticle Hybrids for Electrocatalytic Oxidation of Methanol and Catalytic Oxidation of Benzyl Alcohol. *Journal of Polymer Science Part A: Polymer Chemistry* 49: 4531-4538.
- Ye, F., Liu, H., Feng, Y., Li, J., Wang, X., Yang, J. (2014). A solvent approach to the size-controllable synthesis of ultrafine Pt catalysts for methanol oxidation in direct methanol fuel cells. *Electrochimica Acta* 117: 480–485.

- Yoo, E., Okata, T., Akita, T., Kohayama, M., Nakamura, J. and Honma, I. (2009). Enhanced electrocatalytic activity of Pt subnanoclusters on graphene nanosheet surface. *Nano Lett.* 9: 2255.
- Yoo, S. J., Jeon, T. Y., Kim, K. S., Lim, T. H., Sung, Y. E. (2010). Multilayered Pt/Ru nanorods with controllable bimetallic sites as methanol oxidation catalysts. *Phys. Chem. Chem. Phys.* 12: 15240-15246.
- Yuan, Q., Zhou, Z., Zhuang, J. and Wang, X. (2010). Pd–Pt random alloy nanocubes with tunable compositions and their enhanced electrocatalytic activities. *Chem. Commun.*, 46: 1491–1493.
- Zaid, R. M., Chong, F. C., Teo, E. Y. L., Ng, E. P., Chong, K. F. (2015). Reduction of graphene oxide nanosheets by natural beta carotene and its potential use as supercapacitor electrode. *Arabian Journal of Chemistry*, 8 (4): 560-569.
- Zeng, J. and Lee, J. Y. (2005). Effects of preparation conditions on performance of carbon-supported nanosize Pt-Co catalysts for methanol electro-oxidation under acidic conditions. *Journal of Power Sources* 140: 268-273.
- Zhang, J. (2008). PEM fuel cell electrocatalysts and catalyst layers: fundamentals and applications. London: Springer-Verlag London Limited.
- Zhang, J. L., Zhang, J., Yang, H., Shen, G., Cheng, P., Zhang, J. and Guo, S. (2010). Reduction of graphene oxide *via* L-ascorbic acid. *Chem. Commun.* 46: 1112-1114.
- Zhang, S., Shao, Y., Liao, H., Engelhard, M. H., Yin, G. and Lin, Y. (2011). Polyelectrolyte-Induced Reduction of Exfoliated Graphite Oxide: A Facile Route to Synthesis of Soluble Graphene Nanosheets, *ACS Nano*, 5 (3): 1785–1791.
- Zhang, X., Kumar, P. S., Aravindan, V., Liu, H. H., Sundaramurth, J., Mhaisalkar, S. G., Duong, H. M., Ramakrishna, S and Madhavi, S. (2012). Electrospun TiO₂-Graphene Composite Nanofibers as a Highly Durable Insertion Anode for Lithium Ion Batteries. *J. Phys. Chem. C* 116: 14780-14788.
- Zhang, X., Li, K., Li, H. and Lu, J. (2013). Dipotassium hydrogen phosphate as reducing agent for the efficient reduction of graphene oxide nanosheets. *Journal of Colloid and Interface Science* 409: 1–7.
- Zhang, X., Li, K., Li, H., Lu, J., Fu, Q. and Chu, Y. (2014). Graphene nanosheets synthesis via chemical reduction of graphene oxide using sodium acetate trihydrate solution. *Synthetic Metals* 193: 132-138.

- Zhang, Y. Z., Gu, Y. E., Lin, S. X., Wei, J. P., Wang, Z. H., Wang, C. M., Du, Y. L., Ye, W. C. (2011). One-step synthesis of PtPdAu ternary alloy nanoparticles on graphene with superior methanol electrooxidation activity. *Electrochimica Acta* 56 (24): 8746.
- Zhao, T. S., Yang, W. W., Chen, R., Wu, Q. X. (2010). Towards operating direct methanol fuel cells with highly concentrated fuel. *Journal of Power Sources*. 195: 3451–3462.
- Zhou, M., Wang, Y., Zhai, Y., Zhai, J., Ren, W., Wang, F., Dong, S. (2009). Controlled synthesis of large-area and patterned electrochemically reduced graphene oxide films. *Chem. Eur. J.* 15: 6116.
- Zhou, T., Chen, F., Liu, K., Deng, H., Zhang, Q., Feng, J. and Fu, Q. (2011). A simple and efficient method to prepare graphene by reduction of graphite oxide with sodium hydrosulfite. *Nanotechnology* 22: 045704.
- Zhou, X., Zhang, J., Wu, H., Yang, H., Zhang, J. and Guo, S. (2011). Reducing Graphene Oxide via Hydroxylamine: A Simple and Efficient Route to Graphene, *J. Phys. Chem. C* 115 (24): 11957–11961.
- Zhu, Y., Murali, S., Cai, W., Li, X., Suk, J. W., Potts, J.R. (2010). Graphene and Graphene oxide: synthesis, properties, and applications. *Adv Mater* 22 (35): 3906–24.