

EFFECT OF CERIUM AND BARIUM ADDITIONS AND SUPERHEATING MELT
TREATMENT ON THE MORPHOLOGY AND HARDNESS OF Al-Mg₂Si-Cu
COMPOSITE

NUR AZMAH BINTI NORDIN

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy (Mechanical Engineering)

Faculty of Mechanical Engineering
Universiti Teknologi Malaysia

FEBRUARY 2017

I dedicated this thesis to my beloved parents and family for their endless love and motivational support.

ACKNOWLEDGEMENT

Alhamdulillah.

I would like to express my special thanks to my supervisors, Dr. Tuty Asma Abu Bakar and Prof. Dr. Esah Hamzah for the constant guidance, thoughtful opinions and constructive comments during the course of my research work. Not to forget, I also wish to convey my deep gratitude to Prof. Dr. Ali Ourdjini and my supportive research partner, Dr. Saeed Farahany for the great skill, priceless input and consistent encouragement during my journey as a PhD candidate.

I would also like to acknowledge Universiti Teknologi Malaysia (UTM) and the Ministry of Education of Malaysia for the opportunity and facilities provided to complete my research work. I would also like to extend my gratitude to UTM for the financial support via Zamalah Scholarship during years of my research. Special thanks are also dedicated to all technicians in the Mechanical-Material's lab and fellow friends for the help in supporting my project and tasks. Last but not least, I would like to thank my internal/external panels, Associate Professor Dr. Astuty Amrin and Associate Professor Dr. Zuhailawati Hussain for their useful advices and encouragement to improve my current research work.

ABSTRACT

Aluminium-based alloy, reinforced with particulate Mg_2Si phase has been widely accepted to replace Al-Si alloy due to its improved properties in producing engineering products especially for automotive and aerospace applications. However, in as-cast Al-based reinforced with Mg_2Si composite, the particles formed are coarse with large skeleton shapes and eutectic Al- Mg_2Si phase which are also present in flake-like form. These phases are known to have detrimental effect on the mechanical properties of the composite. The present research is therefore aimed to investigate the effect of elements addition and superheating melt treatment in order to modify the undesired structures and phases in Al- Mg_2Si -Cu metal matrix composite. The elements addition were Ce (0.3-1.0 wt.%) and Ba (0.1-1.0 wt.%). Meanwhile, superheating above the melting temperature of Al- Mg_2Si -Cu composite was carried out at three different temperatures (850°C, 900°C and 950°C) and three different holding times (15, 30 and 45 minutes) to further modify the microstructures. The samples were produced by melting commercial Al-Mg-Si ingot and pouring into a ceramic mould and the transformation temperatures were determined by computer aided cooling curve thermal analysis (CACCTA). The phase and microstructural changes were characterized using optical microscopy, field emission scanning electron microscopy (FESEM), scanning electron microscopy (SEM) and X-ray diffraction (XRD). Hardness test (ASTM E92) was performed in order to investigate the effect of morphology modification on the hardness of the composite. Both approaches, namely, elements addition and melt superheating with varying parameters were found to refine not only Mg_2Si_P reinforcement particles but also eutectic Al- Mg_2Si phase. Various morphologies of the phases were observed, particularly, coarse skeleton of Mg_2Si_P has been transformed to finer polygonal structure. Likewise, flake-like morphology of Mg_2Si_E has transformed to rod and fibrous-like form while the needle-like intermetallic β has transformed to α phase. The optimum concentrations to achieve the adequate refinement effect were found to be 0.8wt% Ce and 0.2wt% Ba. While, the optimum parameter for the melt superheating was 950°C and underwent 15 minutes holding melt duration. The modified composite with addition of optimum concentration of Ce and Ba were observed to increase in hardness property from 61.32Hv to 74.3Hv and 67.95Hv for Ce and Ba, respectively. Whereas, for the composite modified by melt superheating, the hardness improved from 61.32Hv to 70.22Hv.

ABSTRAK

Aloi aluminium yang diperkuatkan dengan pengisian seramik partikel Mg_2Si telah diterima secara meluas bagi menggantikan aloi Al-Si kerana sifatnya yang memuaskan dalam penghasilan produk-produk kejuruteraan, terutamanya dalam aplikasi automotif dan aeroangkasa. Namun, dalam hasil tuangan komposit Al dengan pengisian seramik partikel Mg_2Si , partikel-partikel tersebut telah wujud dalam bentuk yang kasar dengan saiz tetulang yang besar dan fasa eutektik Al- Mg_2Si yang wujud adalah dalam bentuk kepingan-kepingan. Fasa-fasa ini telah dikenalpasti memberi kesan yang memudaratkan ke atas sifat-sifat mekanikal komposit tersebut. Maka, kajian ini adalah bertujuan untuk menyelidik kesan penambahan unsur-unsur dan rawatan lebur pemanasan lampau untuk memperbaiki struktur dan fasa-fasa dalam komposit matrik logam Al- Mg_2Si -Cu (*MMC*). Penambahan unsur-unsur tersebut adalah dengan menggunakan Ce (0.3-1.0% berat) dan Ba (0.1-1.0% berat). Sementara itu, kaedah pemanasan lampau melebihi suhu leburan komposit Al- Mg_2Si -Cu (750°C) telah dijalankan pada tiga suhu (850°C, 900°C dan 950°C) dan dibiarkan dalam tempoh masa yang berbeza (15, 30 dan 45 minit), bagi penambakan selanjutnya mikrostruktur-mikrostruktur tersebut. Sampel tuangan diproses dengan meleburkan jongkong Al- Mg_2Si -Cu komersil dan dituang dalam acuan seramik dan suhu-suhu perubahan telah ditentukan dengan menggunakan perisian komputer analisa haba lengkok penyejukan (*CACCTA*). Perubahan fasa dan mikrostruktur-mikrostruktur telah dicirikan dengan menggunakan mikroskop optik, mikroskop elektron pengimbasan medan (*FESEM*), mikroskop imbasan electron (*SEM*) dan pembelauan sinar x (*XRD*). Ujian kekerasan (*ASTM E92*) telah dijalankan bagi menguji kesan pembaikan mikrostruktur ke atas sifat kekerasan komposit tersebut. Kedua-dua pendekatan iaitu penambahan unsur-unsur dan pemanasan lampau dengan pelbagai parameter telah dilihat dapat menghaluskan bukan sahaja partikel-partikel penguat Mg_2Si_P malah fasa eutektik Al- Mg_2Si . Pelbagai morfologi fasa-fasa telah diperhatikan terutamanya partikel kasar Mg_2Si telah berubah kepada struktur halus poligon. Begitu juga dengan morfologi kepingan-kepingan fasa eutektik Mg_2Si yang berubah kepada bentuk rod dan serabut halus, sementara itu, bentuk jejaram bagi sebatian antara logam fasa β juga telah berubah kepada fasa α . Komposisi optimum untuk mencapai kesan pembaikan yang mencukupi adalah 0.8% berat Ce dan 0.2% berat Ba. Bagi kaedah pemanasan lampau pula, parameter yang terbaik adalah pada suhu 950° dan dibiarkan selama 15 minit. Komposit yang berubah suai dengan penambahan unsur Ce dan Ba telah menunjukkan peningkatan dalam sifat kekerasan komposit, daripada 61.32Hv kepada 74.3Hv untuk Ce dan 67.95Hv untuk Ba. Sementara itu, nilai kekerasan komposit yang berubah suai dengan pemanasan lampau pula telah meningkat daripada 61.32Hv kepada 70.22 Hv.

TABLE ON CONTENT

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xii
	LIST OF FIGURES	xiii
	LIST OF SYMBOLS	xxv
	LIST OF ABBREVIATIONS	xxvii
	LIST OF APPENDICES	xxviii
1	INTRODUCTION	1
	Research Background	1
	Problem Statement	5
	Objectives of Research	6
	Scopes of Research	8
	Significance of Research	9
2	LITERATURE REVIEW	10
	2.1 Introduction	10
	2.2 Al-Mg-Si System	12
	2.3 In-Situ and Ex-Situ Metal Matrix Composite	16

2.3.1	Al-Mg ₂ Si In-Situ Composite	18
2.4	Solidification Process	22
2.4.1	Nucleation	25
2.4.1.1	Homogeneous Nucleation	26
2.4.1.2	Heterogeneous Nucleation	26
2.4.1.3	Difference between Homogeneous and Heterogeneous Nucleation	27
2.4.2	Growth of Solid Nucleus	29
2.4.3	Nucleation and Growth of Primary Mg ₂ Si Phase	29
2.4.3.1	Octahedron Shape of Mg ₂ Si Crystal	32
2.4.3.2	Hopper Shape of Mg ₂ Si Crystal	33
2.4.3.3	Truncated Octahedron Shape of Mg ₂ Si Crystal	35
2.4.3.4	Cubic Shape of Mg ₂ Si Crystal	38
2.4.3.5	Dendrite Shape of Mg ₂ Si Crystal	39
2.5	Modification and Refinement of Primary Mg ₂ Si Phase	42
2.5.1	Modification by Elements Addition	42
2.5.2	Modification by Superheating Melt Treatment	50
2.6	Mechanism of Modification and Refinement Effect	52
2.6.1	Elements Addition Melt Treatment	53
2.6.1.1	Heterogeneous Nucleation Site	53
2.6.1.2	Restricted Growth Theory	55
2.6.1.3	Oxide Bifilm	57
2.6.2	Superheating Melt Treatment	59
2.6.2.1	Heredity Phenomenon of Melt Alloy	60
2.6.2.2	Phase Formation of τ -AlMn	61
2.7	Thermal Analysis	62
2.7.1	Cooling Curve	63
2.7.2	Correlation between Modification/ Refinement Effect with Thermal Analysis	65

2.8	Effect of Morphology on Mechanical Properties of the Composite	67
3	RESEARCH METHODOLOGY	72
3.1	Introduction	72
3.2	Materials	74
3.3	Ceramic Mould Preparation	74
3.4	Thermal Analysis Set Up	77
3.5	Melt Treatment Process	79
3.5.1	Interrupted Quench Test	80
3.5.2	Elements Addition Melt Treatment	82
3.5.3	Superheating Melt Treatment	84
3.6	Sample Preparation	86
3.6.1	Cutting	86
3.6.2	Grinding and Polishing	87
3.7	Microstructural Analysis	88
3.8	Quantitative Analysis of Primary Mg ₂ Si Particles Reinforced Al-Mg ₂ Si-Cu in-situ Composite	88
3.9	Hardness Test	90
4	RESULTS AND DISCUSSION	91
4.1	Introduction	91
4.2	Al-20Mg ₂ Si-2Cu Metal Matrix Composite	92
4.2.1	Sequence of Phase Formation	97
4.2.1.1	Primary Phase of Mg ₂ Si	98
4.2.1.2	Secondary Phase of Eutectic Al-Mg ₂ Si	100
4.2.1.3	Third Phase of Intermetallic Al ₅ FeSi	102
4.2.1.4	Fourth Phase of Al ₅ Cu ₂ Mg ₈ Si ₆ + Al ₂ Cu	103
4.2.2	Solidification Path of Al-Mg ₂ Si-Cu In-situ Composite	106
4.2.3	Solid Fraction of Phases in Al-Mg ₂ Si-Cu In-situ Composite	110
4.2.4	Construction of Al-20Mg ₂ Si-2Cu-0.6Fe Phase	112

Diagram	
4.3 Effect of Elements Addition	116
4.3.1 Effect of Cerium (Ce) on the Composite	117
4.3.1.1 Effect of Ce Addition on Microstructures of the Composite	117
4.3.1.2 Quantitative Analysis of Microstructures with Ce Addition	124
4.3.1.3 Distribution of Mg_2Si_p Particles with Ce Addition	127
4.3.1.4 Effect of Ce Addition on Cooling Curves	131
4.3.1.5 Effect of Ce Addition on Solid Fraction	136
4.3.1.6 Effect of Ce Addition on Hardness Test	138
4.3.1.7 Mechanism of Modification/Refinement Effect with Ce Addition	139
4.3.2 Effect of Barium (Ba) on the Composite	151
4.3.2.1 Effect of Ba Addition on Microstructures of the Composite	151
4.3.2.2 Quantitative Analysis of Microstructures with Ba Addition	161
4.3.2.3 Distribution of Mg_2Si_p Particles with Ba Addition	163
4.3.2.4 Effect of Ba Addition on Cooling Curves	165
4.3.2.5 Effect of Ba Addition on Solid Fraction	173
4.3.2.6 Effect of Ba Addition on Hardness Test	174
4.3.2.7 Mechanism of Modification/Refinement Effect with Ba Addition	176
4.4 Effect of Superheating Melt Treatment	188
4.4.1 Effect of Superheating Melt Treatment on Microstructures of the Composite	188
4.4.2 Quantitative Analysis of Microstructures with Superheating Melt Treatment	199

4.4.3	Distribution of Mg ₂ Si _p Particles with Superheating Melt Treatment	202
4.4.4	Effect of Superheating Melt Treatment on Cooling Curves	205
4.4.5	Effect of Superheating Melt Treatment on Hardness Test	210
4.4.6	Mechanism of Modification/Refinement Effect with Superheating melt Treatment	212
4.5	Summary	
4.5.1	Al-20%Mg ₂ Si-2%Cu In-situ Composite	213
4.5.2	Effect of Ce and Ba Additions on Modification of Mg ₂ Si _p Particles in Al-Mg ₂ Si-Cu Composite – Comparison between the Two Elements Addition	215
4.5.3	Effect of Ce Addition and Superheating Melt Treatment on Modification of Mg ₂ Si _p Particles in Al-Mg ₂ Si-Cu Composite – Comparison between the Two Approaches	220
5	CONCLUSIONS AND RECOMMENDATION FOR FUTURE WORK	224
5.1	Conclusions	224
5.2	Recommendations for Future Work	226
	REFERENCES	227
	Appendices A-K	240

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Properties and characteristics of Al-Si-Cu, Al-Si and Al-Mg cast alloys	13
2.2	General properties and applications of cerium (Ce) and barium (Ba)	49
3.1	Chemical composition of as received commercial Al-20%Mg ₂ Si-2%Cu in-situ composite	74
3.2	Amount of cerium (Ce) additions (g)	83
3.3	Amount of barium (Ba) additions (g)	83
3.4	Temperatures, T _S and holding times used in superheating melt treatment	85
4.1	Characteristic parameters for observed phases in Al-20%Mg ₂ Si-2%Cu composite (the N, Min, G and Rec represent the nucleation, minimum, growth and recalescence of crystals)	108
4.2	Reactions calculated based on non-equilibrium solidification of 77.55Al + 12.71Mg + 7.07Si + 2.03Fe + 0.64Fe alloy	115

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	Types of Al alloy with respective alloying elements and corresponding general properties	11
2.2	Classification of aluminium alloy	12
2.3	(a) Ternary phase diagram of Al-Mg-Si alloy with dotted line represents pseudo-binary Al-20%Mg ₂ Si phase and (b) Pseudo-binary phase diagram of Al-Mg ₂ Si with 20% of Mg ₂ Si reinforcement phase	15
2.4	Schematic diagram of preparation (a) ex-situ and (b) in-situ composite	18
2.5	Example of Al MMC products (a) piston, (b) piston connecting rod and (c) engine with cylinder barrel, made of Al MMC	20
2.6	Morphology of Al-Mg ₂ Si in normal cast alloy consist of (a) primary Mg ₂ Si and (b) eutectic Al-Mg ₂ Si phase	21
2.7	Total free energy change of solid-liquid solidification system	24
2.8	Cooling curve of a material associated with undercooling trend	25
2.9	Schematic diagram of homogeneous nucleation process	26
2.10	Schematic diagram of heterogeneous nucleation process	27

2.11	Schematic diagram of difference between homogeneous and heterogeneous nucleation in terms of free energy and temper	28
2.12	Schematic diagram of phase transformation process of a material	29
2.13	Face center cubic (FCC) of primary Mg_2Si particle	31
2.14	(a) FESEM micrograph of primary Mg_2Si grow in perfect octahedron and (b) schematic growth of respective octahedron shape of Mg_2	31
2.15	SEM micrograph of octahedron shape of Mg_2Si crystal	32
2.16	Schematic diagram of Mg_2Si transformation from nuclei to octahedron shape of particles; (a) Formation of primary Mg_2Si nuclei, (b) Formation of branches along $\langle 100 \rangle$ directions, (c) Formation of octahedral pattern of Mg_2Si , (d) Further growth of Mg_2Si crystal in $\langle 111 \rangle$ directions and (e) Formation of octahedron shape of Mg_2Si crystal	33
2.17	(a) Directions and crystallographic planes involved in transformation of Mg_2Si hopper-like crystal and (b) SEM micrograph of Mg_2Si in hopper-like crystal	34
2.18	Schematic diagram of formation hopper-like Mg_2Si crystal; (a) Formation of Mg_2Si seed crystal, (b) Growth of seed crystal forming the octahedral outline of Mg_2Si and (c) Hopper-like crystal formed due to interruption growth step in $\langle 111 \rangle$ directions	35
2.19	SEM micrograph of truncated octahedron shape (tetracaidecahedron) of Mg_2Si	36
2.20	SEM micrograph of truncated octahedral shape of Mg_2Si	37
2.21	Schematic diagram of truncated octahedral shape of Mg_2Si ; (a) Formation of Mg_2Si nuclei, (b) Nuclei grow in $\langle 100 \rangle$ directions, then in $\langle 110 \rangle$ and $\langle 111 \rangle$	37

	directions forming octahedral outline of Mg_2Si , (c-d) Further grow of Mg_2Si crystal until the adjacent branches are joining and (e) Suppression of some facet planes in $\langle 100 \rangle$ directions causing truncated shape of Mg_2Si	
2.22	SEM micrograph of cubic shape Mg_2Si crystal	38
2.23	Schematic diagram of Mg_2Si crystal that transformed from truncated octahedral into cubic shape; (a) Formation of Mg_2Si seed crystal, (b) Bulges emerge along $\langle 100 \rangle$ directions then in $\langle 110 \rangle$ and $\langle 111 \rangle$ directions forming octahedral pattern of Mg_2Si , (c-d) Further growth of Mg_2Si crystal until the adjacent branches are joining, (e) Suppression of some faces in $\langle 100 \rangle$ directions (truncated octahedral), (f) Growing of other faces while $\{100\}$ planes are held and (g) Perfect cubic shape of Mg_2Si crystal	39
2.24	SEM micrograph Mg_2Si crystal in dendrite shape	40
2.25	Schematic diagram of Mg_2Si dendrite shape; (a) Formation of primary dendrite arm in $\langle 100 \rangle$ directions, (b) Formation of secondary dendritic arm perpendicular to primary arm and (c) Transformation of Mg_2Si into dendrite shape	41
2.26	Alteration of primary Mg_2Si particles from (a) dendritic and coarse shape into (b) polygonal form with Al-3%P master alloy	43
2.27	Optical micrograph showing refinement of (a) coarse primary Mg_2Si and (b) polygonal shape with addition of Sr	45
2.28	Examples of new intermetallic compound (IMC) in white colour as a result of elements addition to a composite and they act as heterogeneous nucleation site for Mg_2Si primary phase	55
2.29	Schematic diagram of restricted growth mechanism	57

2.30	Schematic diagram of oxide bi-film phenomenon that occurred in the Al melt alloy/composite	59
2.31	Schematic flow steps of τ -AlMn formation as a result of superheating melt treatment	62
2.32	Cooling curve with respective first and second derivative curves correspond to Al-Si-Cu alloy during solidification process	64
2.33	Specific points of temperatures extracted from the derivative curves for Al-Si-Cu alloy	64
2.34	(a) Depression in cooling curve as a result of 0.012%wt Sr added to 319Al (Al-Si) alloy, (b) Unmodified and (c) Corresponding refined morphology after addition of 0.012% Sr to the alloy	66
2.35	Schematic plot showing relationship between nucleation rate, \dot{N} , growth rate, \dot{G} and the overall transformation rate versus temperature	67
2.36	Schematic diagram of crack initiated at sharp ends of Mg_2Si particles	68
2.37	Ultimate tensile strength (UTS) and elongation (%) improved as a function of Mn added to Al- Mg_2Si composite	70
2.38	UTS and %El of Al-15% Mg_2Si composite as a result of B addition	70
3.1	Flow chart of the experimental process	73
3.2	Dimension of polystyrene cut foam	75
3.3	The sequence process of ceramic mould preparation	75
3.4	(a) Schematic diagram of thermal analysis set up (CACCTA) and (b) the corresponding exact of CACCTA set up	78
3.5	Melting procedure of Al-20% Mg_2Si -2%Cu in-situ composite; (a) re-melted ingot of Al- Mg_2Si -Cu in-situ composite (top view), (b) preheated the ceramic mould (front view), (c) pouring of molten composite	80

	and recording the temperature-time changed and (d) as-cast samples	
3.6	(a) Schematic diagram of interrupted quench set up with the used of funnel copper mould and (b) The actual interrupted quench test	81
3.7	Schematic flow process of superheating melt treatment	85
3.8	Sample area chosen for morphology analysis of primary Mg ₂ Si reinforced particles as well as other phases	87
3.9	(a) SEM micrograph of Mg ₂ Si particles and examples quantitative calculation of respective particles based on (b) perimeter size, (c) aspect ratio and (d) particles density per unit area	89
4.1	(a) Cooling curve of Al-20%Mg ₂ Si-2%Cu in-situ composite comprised with first and second derivatives curves and (b-e) magnified of cooling curves of four phases transformation (1, 2, 3, 4)	93
4.2	Cooling curve recorded at the centre (<i>TC</i>) and wall (<i>TW</i>) thermocouples and difference temperatures curve between them ($\Delta T = TW - TC$)	95
4.3	(a) BSE micrograph of as received commercial Al-Mg ₂ Si-Cu in-situ composite together with corresponding (b) EDX and (c) mapping analysis	96
4.4	Quench stage applied on cooling curve of fully solidified Al-Mg ₂ Si-Cu in-situ composite at three different steps to reveal the sequence of phase transformation	98
4.5	(a) Optical micrograph of Al-Mg ₂ Si-Cu quenched after first phase formation with corresponding (b) BSE micrograph and EDX analysis of observed particles	100

4.6	(a) Optical micrograph, (b) BSE micrograph and corresponding elemental mapping analysis of Al-Mg ₂ Si-Cu composite quenched at Q2	101
4.7	(a) Optical micrograph of Al-20%Mg ₂ Si-2%Cu composite quenched at Q3, (b) BSE image and (c) corresponding EDX spectra of iron intermetallic	103
4.8	(a) Optical and (b) SEM micrographs of fully solidified Al-20Mg ₂ Si-2Cu composite, (c) BSE image and corresponding EDX spectra of (d) grey and (e) bright intermetallic compounds	105
4.9	XRD pattern of the as-cast Al-20Mg ₂ Si-2Cu composite (a) without and (b) with Al matrix removed	107
4.10	Schematic of physical model of phase transformations during solidification of Al-20Mg ₂ Si-2Cu in-situ composite	110
4.11	(a) Cooling curve, second derivative curve and associated fraction solid curve and (b) Calculated solid fraction, <i>f_s</i> (%) of unmodified in situ composite corresponding to primary Mg ₂ Si, Al-Mg ₂ Si eutectic, intermetallic Al ₅ FeSi (β -intermetallic) and Al ₅ Cu ₂ Mg ₈ Si ₆ (Q) + Al ₂ Cu (θ)	112
4.12	(a) Phase diagram for Al-20Mg ₂ Si-2Cu system with the variation of Al content and (b) The liquid fraction of alloy in equilibrium and non-equilibrium solidification	113
4.13	FESEM micrograph of Al-20Mg ₂ Si-2Cu composite cooled in ceramic mould, contains of (i) Mg ₂ Si _P , (ii) Mg ₂ Si _E , (iii) β -intermetallic and (iv) Q+ θ phase	116
4.14	Cooling curves of Al-20Mg ₂ Si-2Cu in-situ composite added with different Ce levels: 0.3, 0.5, 0.8 and 1.0 wt%	118

4.15	Optical micrographs showing changes of morphologies for Mg_2Si_P (a1–e1), Mg_2Si_E (a2–e2), Al_5FeSi (a3–e3), $Al_5Cu_2Mg_8Si_6 + Al_2Cu$ (a4–e4) in Al- Mg_2Si -Cu in-situ composite	120
4.16	BSE micrograph of Mg_2Si_E phase showing transformation of (a) flake-like morphology (unmodified) into (b) rod-like form (with 0.5 wt% Ce)	122
4.17	Shrinkage porosity formations as a result of β -intermetallic has impeded the flow of melt during solidification of composite at the last stage of solidification process	123
4.18	Particles characteristics of Mg_2Si_P in Al- Mg_2Si composite composed of different Ce concentrations; 0.3, 0.5, 0.8 and 1.0wt.%	125
4.19	Average Mg_2Si_E cells size as a function of various Ce concentrations	125
4.20	Particles characteristics of β -intermetallic phase corresponds to various Ce concentrations added into the composite; 0.3, 0.5, 0.8 and 1.0wt.%	126
4.21	Optical macrograph of Al- Mg_2Si -Cu in-situ composite indicating allocation of phases entire the composite area	128
4.22	Particles distribution of primary Mg_2Si particles in the composite treated with different level of Ce: (i) 0wt%, (ii) 0.3wt%,(iii) 0.5wt%, (iv) 0.8wt% and (v) 1.0wt%	130
4.23	Change of nucleation temperature, T_N and solidus line of all phases corresponding to effect of various Ce additions	133
4.24	Duration of Mg_2Si_P particles to nucleate and grow, $t_G^{Mg_2Si_P} - t_N^{Mg_2Si_P}$ as a function of Ce concentrations	133
4.25	Time difference of $t_G^{Mg_2Si_E} - t_N^{Mg_2Si_E}$ (s) indicating	135

	nucleation and growth duration of Mg_2Si_E cells	
4.26	Time difference of $t_G^\beta - t_N^\beta$ (s) indicating nucleation and growth duration of β -intermetallic cells	136
4.27	Solid fraction of Al- Mg_2Si -Cu composite as a result of Ce addition	137
4.28	Hardness values with variation of Ce accordance to optical micrograph of the microstructure at each of concentration	139
4.29	(a) BSE image of Al- Mg_2Si -Cu in-situ composite treated with 0.8wt% Ce and (b) elemental mapping indicating Ce element white region	140
4.30	(a) BSE micrograph of non-uniform Ce white particle (Spectrum 1), (b) EDX analysis on corresponding non uniform white Ce particle, (c) BSE micrograph of needle-like Ce white particle (Spectrum 2) and (d) enclosed EDX analysis on respective needle-like white particle	142
4.31	XRD results of Al-20 Mg_2Si -2Cu in-situ composite with (a) Combination of unmodified and all Ce-treated results and (b) Magnified XRD result of Al-20 Mg_2Si -2Cu + 0.8wt% Ce in situ composite	144
4.32	(a) BSE micrograph indicating white Ce compounds near Mg_2Si_P particles and (b) EDX point analysis on respective white Ce compounds	145
4.33	(a) SEM micrographs of Mg_2Si_P in tetracaidecahedron (3D shape) and together with small white particles surround the particles and (b) EDX analysis on small white point particles surrounds Mg_2Si_P particle	146
4.34	Formation of white Ce compounds distributed on eutectic area as a result of different Ce concentrations of (a) 0.3wt%, (b) 0.5wt%, (c) 0.8wt% and (d) 1.0wt%	149

4.35	Cooling curves of Al-Mg ₂ Si-Cu in-situ composite as a result of Ba addition in different levels: 0.1, 0.2, 0.4, 0.6, 0.8, 1.0wt% Ba	152
4.36	Optical micrographs presenting changes of morphologies for Mg ₂ Si _P (a1–g1), Mg ₂ Si _E (a2– g2), β-intermetallic (a3–g3) and Q+θ phase (a4–g4) in Al-Mg ₂ Si-Cu in-situ composite	154
4.37	Optical micrograph of showing α-intermetallic phase nucleated at the needle-like β-intermetallic	159
4.38	Twin-platelets Fe-rich phase formation that growing from β-intermetallic	160
4.39	(a) SEM micrograph of script-type α-intermetallic together with (b) corresponding EDX analysis (Spectrum 1)	161
4.40	Characteristics particles of Mg ₂ Si _P respective to change in normalized average area, average grain size, aspect ratio and particles formed per unit area correspond to various Ba concentrations	162
4.41	Particles distribution of Mg ₂ Si _P particles in the composite treated with different concentration of Ba: (a) 0wt%, (b) 0.1wt%, (c) 0.2wt%, (d) 0.4wt%, (e) 0.6wt%, (f) 0.8wt% and (g) 1.0wt%	164
4.42	Change of arrests corresponding to formation of Mg ₂ Si _P phase	166
4.43	Change of T_N of all phases including solidus line as a result of different concentration of Ba addition	167
4.44	Duration for Mg ₂ Si _P particles formation and growth	168
4.45	(a) Decrease of eutectic growth temperature, $T_G^{Mg_2SiE}$ and (b) corresponding increases of depression eutectic temperature, $\Delta T_G^{Mg_2SiE}$ and (c) Period Mg ₂ Si _E phase formation	170
4.46	Cooling curve of 0.4wt% Ba added to Al-Mg ₂ Si-Cu in-situ composite associated with corresponding first	172

	derivative curve and indication of Fe-rich phase formation	
4.47	Solid fractions of all four phases, Mg_2Si_P , Mg_2Si_E , β -intermetallic and $Q+\theta$ with respect to various amount of Ba addition	174
4.48	Hardness values as a result of Ba addition in various concentrations	176
4.49	(a) FESEM micrograph of 0.2wt% Ba treated sample accompany with (b) elemental mapping analysis on corresponding phases	177
4.50	(a) FESEM micrograph of Al- Mg_2Si -Cu in-situ composite treated with 0.4wt% Ba and associated with corresponding (b) elemental mapping	178
4.51	(a) FESEM micrograph of white point inside the Mg_2Si_P phase and (b) Corresponding EDX analysis on this white point shape	179
4.52	(a) FESEM micrograph of white Ba particles observed near the Mg_2Si_P particles; (b) and (c) are corresponding EDX on two white spots	180
4.53	(a) FESEM micrograph of needle-like Ba intermetallic and (b) corresponding EDX analysis	181
4.54	Combination of XRD results of all Ba concentrations containing diffraction angles of certain phases including new peak observation as in oval ($\sim 83^\circ C$)	182
4.55	SEM micrograph of 3D shape Mg_2Si_P particle treated with 0.2wt% Ba	183
4.56	FESEM micrograph of white Ba compounds forming around the Mg_2Si_E phase and its change in shape and size as a result of different Ba concentration; (a) 0.1wt%, (b) 0.2wt%, (c) 0.4wt%, (d) 0.6wt% and (e) 0.8wt% and (f) 1.0wt% with correspond low magnified area, respectively	185
4.57	Needle-like Al_5Si_2Ba intermetallic has disrupted	187

	structure of flakes-like Mg_2Si_E	
4.58	Refinement of Mg_2Si_P particles as a result of various superheat temperatures (850-950°C) and holding times (15-45 min)	190
4.59	Effect of Mg_2Si_E phase as a result of various superheat temperatures (850-950°C) and different holding times (15-45 min)	192
4.60	Effect of β -intermetallic phase as a result of different superheat temperatures (850-950°C) and holding times (15-45 min)	195
4.61	Effect of Q+ θ phase as a result of different superheat temperatures (850-950°C) and holding melt times (15-45 min)	198
4.62	Quantitative analysis of Mg_2Si_P particles respective to various superheat temperatures (850-950) and different holding times (15-45 minutes)	199
4.63	Optical micrograph of Mg_2Si_P particles distribution over the composite area respective to (a) unmodified; the composite treated with superheating melt treatment at fixed superheat temperature of 950°C for (b) 15 min, (c) 30 min, (d) 45 min; and the composite treated at a constant 15 min melt holding time for (e) 850°C, (f) 900°C, (g) 950°C	203
4.64	Cooling curves of Al- Mg_2Si -Cu in-situ composite under superheat melt treatment with various temperature and holding times	206
4.65	Change in T_N of all phases corresponding to various superheat temperatures with respect to holding times	206
4.66	Change of $T_G^{Mg_2Si_E}$ as a result of various superheat temperature and respective holding melt time on Al- Mg_2Si -Cu in-situ composite	208
4.67	Hardness values as a result of superheating melt treatments with (a) vary the superheat temperatures	211

	(850-950°) at a fixed 15 minutes holding time and (b) vary the holding melt duration (15-45 minutes) at a constant superheat temperature of 950°C	
4.68	Cooling curve of Al-Mg ₂ Si-2Cu in-situ composite, equipped with projected cooling curves and corresponding phase formation at respective each peak (Adopted from Fig. 4.1)	214
4.69	SEM micrograph of Mg ₂ Si _P particles illustrating the shape of particles in (a) polygonal form (0.8wt% Ce), (b) Square and rectangular/triangle form (0.2wt% Ba), (c) 3D shape of respective polygonal in truncated structure (0.8wt% Ce) and (d) 3D shape of square in cubic form (0.2wt% Ba)	216
4.70	Characteristics particle of Mg ₂ Si _P correspond to 0.8wt% Ce and 0.2wt% Ba	217
4.71	Change of T_N respective to Mg ₂ Si _P phase as a result of optimum concentration of Ce and Ba	218
4.72	Duration of Mg ₂ Si _P formation correspond to Ce and Ba elements addition	219
4.73	Effect of optimum concentration of Ba and Ce on hardness, compared to the base composite	220
4.74	Comparison of Mg ₂ Si _P shape between two approaches (a) Addition of 0.8wt% Ce and (b) 950°C superheat temperature with 15 minutes holding time	221
4.75	Characteristics particle of Mg ₂ Si _P correspond to 0.8wt% Ce and 950°C_15 min superheating melt treatment	222
4.76	Comparison in hardness value as a result of 0.8wt% Ce addition element and 950°C_15 minutes holding time in superheating melt treatment, respective to base composite	223

LIST OF SYMBOLS

Mg_2Si	-	Magnesium silicide
Al_3Ti	-	Titanium trialuminide
AlP	-	Alkaline phosphate
Y_2O_3	-	Yttrium oxide
SiC	-	Silicon carbide
Al_2O_3	-	Alumina
K_2TiF_6	-	Potassium fluotitanate
$Mg_3(PO_4)$	-	Magnesium phosphate
Mg_3P	-	Magnesium phosphide
Mg_3Sb_2	-	Magnesium antimonide
KBF_4	-	Potassium tetrafluoroborate
HCl	-	Hydrochloric acid
r^*	-	Critical radius
ΔG_v	-	Free energy per unit volume
ΔG_s	-	Surface free energy per unit area
G_v	-	Volume free energy
G_s	-	Surface free energy
ΔG^*	-	Activation energy
ΔG	-	Gibbs free energy
γ_{SI}	-	Solid surface free energy
γ_{SL}	-	Soli-liquid free energy
γ_{IL}	-	Liquid surface free energy
Θ	-	Wetting angle
T_m	-	Melting temperature
T_P	-	Pouring temperature

T_S	-	Superheat temperature
T_N	-	Nucleation temperature
T_{\min}	-	Minimum temperature
T_G	-	Growth temperature
T_c	-	Temperature at centre
T_w	-	Temperature at wall
CR	-	Cooling rate

LIST OF ABBREVIATIONS

MMC	-	Metal Matrix Composite
CACCTA	-	Computer Aided Cooling Curve Analysis
DTA	-	Differential Thermal Analysis
DSC	-	Differential Scanning Calorimetry
TGA	-	Thermogravimetric Analysis
FESEM	-	Field Emission Scanning Electron Microscopy
EDX	-	Energy Dispersive X-ray Analysis
XRD	-	X-ray Diffraction
BSE	-	Backscattered Secondary Electron
FCC	-	Face Centered Cubic

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Temper designation system of Al alloy based on Identification of Aluminum Alloy Designation System (IADS)	236
B	Difference between volume, ΔG_V and surface free energy, ΔG_s	
C	Theoretical calculation of 20% Mg_2Si in the Al-based composite	237
D	Zahn flow cup	238
E	Formula of average value regarding the characteristics particles of Mg_2Si_P respective to grain size, normalized area, aspect ratio and number of particles per unit area (mm^2)	238
F	Changed of $T_G^{Mg_2SiP}$ as a result of Ce addition element	238
G	Diffraction angle data of Al-Si-Ce compounds indicating the element presents at angle of $28.7^\circ C$ and $27.7^\circ C$	239
H	Collection of atomic number (%) respective to white needle-like and white non-uniform Ce compounds	239
I	Collection of atomic numbers (%) correspond to white particles and needle-like Ba compounds	240
J	Matching analysis on 83° identifies presence of Al	240
K	List of Publications	245

CHAPTER 1

INTRODUCTION

1.1 Research Background

As a class of advanced engineering materials, aluminium metal matrix composites (MMCs) have been paid greater attention extensively owing to their excellent properties which make them useful for high performance applications. Their properties such as low density, excellent castability, excellent mechanical properties and low production cost render these materials more attractive to meet further application demands especially for light-weight components [1-3], particularly in the manufacture of automotive parts where the pressure to use light-weight material has been increasing due to environmental issues.

The common aluminium metal matrix composites (Al-MMC) are mostly based on the Aluminium-Silicon (Al-Si) casting alloys reinforced with hard ceramic particles, such as silicon carbide (SiC) and alumina (Al_2O_3) [4, 5]. However, these metal matrix composites suffer from thermodynamic instability of interfaces between the ceramic reinforcement and matrix, in addition to poor wettability of the reinforcements [6]. Moreover, small particle size of the reinforcement and the density differences between reinforcement and matrix make the fabrication of these composites more difficult due to settling and agglomeration issues [7].

Al-based composite, reinforced with particulate Mg_2Si phase have recently been shown to possess advantages [5, 8]. However, mechanical properties in normal cast Al- Mg_2Si in-situ composite is unsatisfactory due to the nature form of dendrite and coarse morphology of primary Mg_2Si phase which lead to stress concentration at sharp edges and corners of Mg_2Si structure [9, 10]. This would cause more brittle phase of structure [11] and low ductility of the in situ composite [2]. Thus, mechanical properties of the composite are rather limited especially at high temperature [10, 12]. Therefore, melt treatment by refinement and modification of the coarse primary Mg_2Si structure as well as corresponding matrix phase of Al- Mg_2Si in-situ composite is crucial in order to improve the morphology of Mg_2Si reinforcement and achieve better mechanical properties.

Various methods have been employed and developed to enhance the composite properties by refining the structure of the primary Mg_2Si as well as that of the matrix. Among the techniques [13, 14], melt treatment method with modifier or refiner elements is chosen due to result effectiveness in addition to low cost because of the use of Al, Mg and Si as starting materials [6, 7]. Furthermore, the technique results in an even distribution of reinforcing phase, good particle wetting and less steps of processing for industrial utilization. Besides, reinforcement particles are thermodynamically stable in the matrix, leading to less degradation in high temperature services [5, 11, 12].

It has been reported that potassium fluotitanate, K_2TiF_6 [15], potassium fluotitanate + potassium tetrafluoroborate ($K_2TiF_6+KBF_4$) [16], strontium (Sr) [17-19], sodium (Na) [19] and phosphorus (P) [9, 18, 20] are important additives to be introduced to the melt alloy in order to refine or modify the morphology of the primary Mg_2Si and enhance the properties. However, some of the findings from this research have reported drawbacks as described by and Zhao *et al.* [19] and Wang *et al.* [16] in their research respectively. In particular, Na has limited solid solubility in Al melt and has a very high vapour pressure. Thus, Na is readily volatilized during the modification process, resulting in negative effects [19]. Another case, addition of K_2TiF_6 and KBF_4 individually in Mg-Si composite have refined and modified the shape of primary Mg_2Si respectively. However, combination of $K_2TiF_6+KBF_4$ in the

composite has reduced the role of KBF_4 as modifier and as a result, primary Mg_2Si become coarser again [16].

Previous research also showed that the refinement effect have been achieved by addition of extra silicon (Si) [9, 21] since the morphology of coarse primary Mg_2Si particles resulted in finer polyhedral shape with a reduced size. The addition also caused modification in the eutectic Mg_2Si phase by altering the flake-like structure to a finer fiber shape. Similar results of refined primary and eutectic Mg_2Si structures have also been obtained with the addition of lithium (Li) to Al- Mg_2Si melt composite [11, 22], addition of antimony (Sb) [23, 24], Sr [25, 26] and bismuth (Bi) [10, 27].

The role of rare earth elements as modifiers or refiners have also been investigated but most research have focused on Al-Si alloys [28-30]. It was reported that addition of rare earth elements (RE) such as lanthanum (La), cerium (Ce), neodymium (Nd), yttrium (Y) and mischmetal could be capable to modify the eutectic structure but not the primary Si phase [31]. However, in a recent research by Qin Lin *et al.* [28] it has been shown that addition of Ce has a significant refining effect on the primary Si crystals besides modifying the eutectic Si structure as well. Knuutinen *et al.* [29] in their research on barium (Ba), calcium (Ca), Y and ytterbium (Yb) also concluded that both Ca and Ba can act as modifiers while Y and Yb act as refiners to modify and refine the morphology of Al-Si alloy respectively.

Similar refinement result was obtained with the use of Ce into Al-Si-Cu composite on the primary Mg_2Si structure as reported by Zhang *et al.* [32]. In other research, Zheng *et al.* [33] have proved that addition of Y_2O_3 compound has caused modification of the morphology of primary Mg_2Si in Mg-Si base composite while other findings have claimed that Y itself just affect the size and not the morphology of Mg_2Si particles. However, Emamy *et al.* [34] claimed that Y individually could modify both the morphology of Mg_2Si phase as well as its size and produce a refined structure. In addition, Wang *et al.* [35] who investigated the effect of La in Mg-Si composite have revealed that La could refine the morphology of Mg_2Si from coarse to refined polygonal structure.

Instead of melt treatment by the elements addition approach, the morphology of cast alloys can also be affected by superheating melt treatment. It is a process that involves preheating the cast alloy at higher temperature, basically above the melting temperature and holding it for a certain period of time and then immediately cooled to pouring temperature before casting or solidifying [36-38]. The process of preheating at elevated temperature would cause a change in heredity of the alloy by remelting the particles and clusters completely and homogeneously in the melt, then resolidify as finer particles. This would result in finer grain nucleation [37, 39].

It was reported that melt superheating temperature on $Mg_2Si/Al-Si-Cu$ composite resulted in a change of coarse dendritic primary Mg_2Si particles to equiaxed shape and a decrease in their size while the eutectic Mg_2Si phase has been improved from Chinese script type to irregular type [39]. Similar result was observed by Zhamin *et al.* [33] who claimed that superheating melt treatment on $Mg-3.5Si-1Al$ composite caused reduction in heredity phenomenon of the composite such that both primary and eutectic Mg_2Si phase have been refined.

Besides that, Chen *et al.* [38] in their study on Al-Si melt alloy have claimed that eutectic Si phase could be modified and refined by reducing heredity phenomenon in the melt and changing its growth phase to get better final structure. Meanwhile, Haque *et al.* [40] have clarified that superheating technique with addition of Sr results in better modification effect compared to modified alloy with Sr without superheating. Indeed, the morphology of eutectic Si phase has been refined. Although most of the research concerning superheating melt treatment focused on the eutectic Si phase in Al-Si alloy, it is believed that superheating could also result in similar modification effect on the primary Mg_2Si phase in Al- Mg_2Si in-situ composite.

In summary, modification and refinement of coarse morphology of any material by addition of inoculation agents and superheating melt treatment are important and may be considered as useful routes to enhance the mechanical properties of the material. Inoculation agents, similar to neutralizer or modifier elements would be induced to the Al melt alloy/composite in order to treat the undesirable structure and produced modified and refined morphology. Although,

most of research studies on refinement and modification treatment are related to the Al-Si alloy, there is great similarities between the solidification behaviour of Al-Si and Al-Mg₂Si systems [31]. Therefore, it is believed that element additions of Ce and Ba as well as superheating melt treatment at certain temperature ranges and holding time can be effective routes to alter the morphology of primary Mg₂Si structure in the Al-Mg₂Si in-situ composite. Control of their microstructure is more practical and cost effective method because of low production cost commercially and is the same as that practiced in casting of metallic alloys.

1.2 Problem Statement

High performance of Al-Mg-Si composites containing Mg₂Si reinforced phase are attractive candidates to manufacture industrial products especially for automotive and aerospace components. However, the presence of Mg₂Si reinforced particles in the form of dendrite and coarse shape have adverse effect on the mechanical properties of the composites due to ease of crack formation at sharp edges and corners of the Mg₂Si particles. Therefore, modification and refinement of the coarse morphology is required in order to improve the structure and thus enhance the mechanical properties such as reduce the brittleness of the Al-Mg₂Si in-situ composite.

Elements addition and superheating melt treatment have been proposed to alter the coarse morphologies of the phases in the melt alloys. The first approach is by element addition. Examples of elements addition are cerium (Ce) and barium (Ba). However, scarcity of Ce and Ba elements has limited their use as modifier or refiner elements and restricted their use in general industrial applications. Research findings, albeit very little have proved that addition of such elements causes modification and refinement effects of phases in many melt alloys. Moreover, the interaction between these rare earth elements and the exact mechanism of

modification is still unclear. In fact, focus of Ce and Ba elements are rather limited that inspired to further emphasis its role as modifier and refiner agents.

Superheating melt treatment as a second approach has been suggested to achieve refinement in the in-situ composite melt. Preheating the melt composite at elevated temperature, normally above the melting temperature of Al-20%Mg₂Si-2%Cu in-situ composite, causes complete dissolution of particles and yet lead to nucleation of finer particles. However, the exact reasons and role of modifying effect is not clearly understood, in addition to very little research work done regarding the superheating treatment on primary phase and in Al-Mg-Si composite.

Therefore, this current research is carried out in order to investigate the effect of elements addition namely Ce and Ba as well as superheating melt treatment on the primary Mg₂Si phase. Both methods will be carried out with computer aided cooling curve thermal analysis (CACCTA) technique in order to monitor the solidification behavior of the composite and to determine the characteristic temperatures for each phase. Understanding the characteristic temperatures can be beneficial in controlling the solidification process of the cast alloy, yet producing improved microstructure of composite with the corresponding desired mechanical properties. As both methods are expected to improve the morphology and properties of the in situ composite, they will be compared and the best method will be proposed at the end of this research study.

1.3 Objectives of the Research

The primary aim of this research is to investigate the effect of elements addition (Ce and Ba) and superheating melt treatment on the morphology of primary Mg₂Si phase and mechanical property namely hardness of commercial Al-20%Mg₂Si-2%Cu in-situ composite.

The specific objectives of the research are:

1. To evaluate the characteristic temperatures of the in-situ composite during solidification process by elements addition and superheating melt treatment using computer aided cooling curve thermal analysis (CACCTA) technique.
2. To determine the effects of elements addition (Ce and Ba) on the morphology of in-situ Mg_2Si reinforced particles in Al- Mg_2Si -Cu composites and the hardness of respective in-situ composites using gravitational casting process.
3. To determine the effect of superheating temperature (850-950°C) and holding time (15-45 minutes) on primary Mg_2Si structure phase and the hardness of the corresponding Al- Mg_2Si -Cu in-situ composite.
4. To determine the optimum concentration of Ce and Ba addition and the optimum parameter of superheating melt treatment that resulted in adequate modification and refinement effect on the morphology of Al- Mg_2Si -Cu in-situ composite.
5. To propose the mechanisms related to phase transformation of Al-20% Mg_2Si -2%Cu in situ composite, in addition to modification effect of primary Mg_2Si as a result of Ce and Ba additions as well as superheating melt treatment.

1.4 Scopes of the Research

The scopes of the research are as follows:

1. Preparation of ceramic moulds for the casting process.
2. Preparation of samples by casting as-cast commercial Al-Mg₂Si-Cu composite with and without elements addition (Ce and Ba) and superheating melt treatment.
3. Analysis of the as-cast molten Al-Mg-Si-Cu in-situ composite with and without elements addition using computer aided cooling curve thermal analysis (CACCTA) in order to determine the characteristic temperatures of the primary Mg₂Si phase.
4. Analysis of Al-Mg₂Si-Cu composite melt during superheating melt treatment using CACCTA to characterize the characteristic temperatures of the primary Mg₂Si.
5. Microstructural and phase analysis of as-cast prepared samples using optical microscopes, field emission scanning electron microscopy (FESEM) with energy dispersive x-ray analysis (EDX) and x-ray diffraction (XRD).
6. Perform hardness test on as-cast samples that have treated with elements addition and superheating melt treatment.

REFERENCES

- [1] A. Bahrami, A.R., M. Emamy, H.R. Jafari and G.S. Mousavi. Microstructure and Tensile Properties of Al-15wt%Mg₂Si Composite After Hot Extrusion and Heat Treatment. *Key Engineering Materials*. 2011. 471-472: 1171-1176.
- [2] Chong Li, Y., Hui Li and Xiangfa Liu. Microstructural Formation in Hypereutectic Al–Mg₂Si with Extra Si. *Journal of Alloys and Coumpounds*. 2009. 477: 212-216.
- [3] H. Liao, Y.S. and G. Sun. Restraining Effect of Strontium on the Crystallization of Mg₂Si Phase during Solidification in Al-Si-Mg Casting Alloys and Mechanisms. *Materials Science and Engineering A*. 2003. 358: 164-170.
- [4] H. Ahlatci, E. Candan and H. Cimenoglu. Mechanical Properties of Al-60%SiC Particulate Composites Alloyed with Mg. *Metallurgical and Materials Transactions A*, 2004. 35: 2127-2141.
- [5] M. Suery, L. Lajoie in P. Rohatgi. Solidification of Metal Matrix Composites. *The Minerals Metals and Materials Society*. 1990: 171-179.
- [6] E. Candan, H.V. Atkinson and H. Jones. Effect of Alloying Addition on Treshold Pressure for Infiltration and Porosity of Aluminium-Based Melt Infiltrated Silicon Carbide Power Compact. *Key Engineering Materials*. 1997. 127-131: 463-470.
- [7] I.A. Ibrahim, F.A. Mohamed and E.J. Lavernia. Particulate Reinforced Metal Matrix Composites - A Review. *Journal of Materials Science*. 1991. 26: 1137-1156.
- [8] M. Gupta and S.F. Hassan. Development of A Novel Magnesium-Copper Based Composite with Improved Mechanical Properties. *Materials Research Bulletin*. 2002. 37: 377-389.

- [9] Chong Li, X. Liu and Y. Wu. Refinement and Modification Performance of Al–P Master Alloy on Primary Mg₂Si in Al–Mg–Si Alloys. *Journal of Alloys and Compounds*. 2008. 465: 145-150.
- [10] E.J. Guo, B.X. Ma and L.P. Wang. Modification of Mg₂Si Morphology in Mg–Si Alloys with Bi. *Journal of Materials Processing and Technology*. 2008. 206: 161-166.
- [11] R. Hadian, M. Emamy, N. Varahram and N. Nemati. The Effect of Li on The Tensile Properties of Cast Al–Mg₂Si Metal Matrix Composite. *Materials Science and Engineering A*. 2008. 490: 250-257.
- [12] M.R. Ghorbani, M. Emami, R. Khorshidi, J. Rasizadehghani and A.R. Emami. Effect of Mn Addition on the Microstructure and Tensile Properties of Al–15%Mg₂Si Composite. *Materials Science and Engineering A*. 2012. 550: 191-198.
- [13] M. Mabuchi and K. Higashi. Strengthening Mechanism of Mg–Si Alloys. *Acta Materialia*. 1996. 4: 4611-4618.
- [14] Y. Tsunekawa, H.S. and Y. Genma, Application of Ultrasonic Vibration to In-Situ MMC Process by Electromagnetic Melt Stirring. *Materials Desisgn*. 2001. 22: 467-472.
- [15] Y.G. Zhao, Q.D. Qin, Y.Q. Zhao, Y.H. Liang and Q.C. Jiang. In Situ Mg₂Si/Al–Si Composite Modified by K₂TiF₆. *Materials Letters*. 2004. 58: 2192-2194.
- [16] H.Y. Wang, Q.C. Jiang, B.X. Ma, Y. Wang, J.G. Wang and J.B. Li. Modification of Mg₂Si in Mg–Si alloys with K₂TiF₆, KBF₄ and KBF₄ + K₂TiF₆. *Journal of Alloys and Compounds*. 2005. 387: 105-108.
- [17] Q.D. Qin, Y.G. Zhao, C. Liu, P.J. Cong and W. Zhou. Strontium Modification and Formation of Cubic Primary Mg₂Si Crystals in Mg₂Si–Al Composite. *Journal of Alloys and Compounds*. 2008. 454: 142-146.
- [18] Y.H. Cho, H.C.L., K.H. Oh and A.K. Dahle. Effect of Strontium and Phosphorus on Eutectic Al–Si Nucleation and Formation of β–Al₅FeSi in Hypoeutectic Al–Si Foundry Alloys. *Metallurgical and Materials Transactions A*. 2008. 39A: 2435-2488.
- [19] Y.G. Zhao, Q.D. Qin, Y.H. Liang, W. Zhou and Q.C. Jiang, In-situ Mg₂Si/AlSi–Cu Composites Modified by Strontium. *Journal of Materials Science*. 2005. 40: 1831-1833.

- [20] Q.D. Qin, Y.G. Zhao, W. Zhou and P.J. Cong. Effect of Phosphorus on Microstructure and Growth Manner of Primary Mg_2Si Crystal in Mg_2Si/Al Composite. *Materials Science and Engineering A*. 2007. 477: 186-191.
- [21] N. Nasiri, M. Emamy and A. Malekan. Microstructural Evolution and Tensile Properties of the In-situ Al–15% Mg_2Si Composite with Extra Si Contents. *Materials Design*. 2012. 37: 215-222.
- [22] R. Hadian, M. Emamy and J. Campbel. Modification of Cast Al- Mg_2Si Metal Matrix Composite by Li. *Metallurgical and Materials Transactions B*. 2009. 4: 822-832.
- [23] Ren Bo, L.Z., Zhao Ruifeng, Zhang T., Liu Z., Wang M. and Weng Y.. Effect of Sb on Microstructure and Mechanical Properties of $Mg_2Si/Al-Si$ Composites. *Transaction of Nonferrous Metals Society of China*. 2010. 20: 1367-1377.
- [24] Yan Hong, H. Yong and W. Xiaoqian. Influence of Sb Modification on Microstructures and Mechanical Properties of $Mg_2Si-AM60$ Composite. *Transaction of Nonferrous Metals Society of China*. 2010. 20: 411-145.
- [25] Yang M., Pan F., Cheng R. and Shen J. Comparison About Effects of Sb, Sn and Sr on As-Cast Microstructure and Mechanical Properties of AZ61–0.7Si Magnesium Alloy. *Materials Science and Engineering A*. 2008. 489: 423-418.
- [26] Yang M., Pan F., Shen J. and Bai L. Comparison of Sb and Sr on Modification and Refinement of Mg_2Si Phase in AZ61-0.7Si Magnesium Alloy. *Transaction of Nonferrous Metals Society of China*. 2009. 19: 287-292.
- [27] NA. Nordin, S. Farahany, A. Ourdjini, TA. Bakar and E. Hamzah. Refinement of Mg_2Si Reinforcement in a Commercial Al-20% Mg_2Si In-situ Composite with Bismuth, Antimony and Strontium. *Materials Characterization*. 2013. 86: 97-107.
- [28] Q. Li, T.X., Y. Lan, W. Zhao, L. Fan and P. Li. Effect of Rare Earth Cerium Addition on the Microstructure and Tensile Properties of Hypereutectic Al–20%Si Alloy. *Journal of Alloys and Compounds*. 2013. 562: 25-32.
- [29] A. Knuutinen, K. Nogita, S.D. McDonald and A.K. Dahle. Modification of Al–Si Alloys with Ba, Ca, Y and Yb. *Journal of Light Metals*. 2001. 1: 229-240.

- [30] Q. Li, T. Xia, Y. Lan, P. Li and L. Fan. Effects of Rare Earth Er Addition on Microstructure and Mechanical Properties of Hypereutectic Al-20%Si Alloy. *Materials Science and Engineering A*. 2013. 588: 97-102.
- [31] J. Zhang, Z.F., Y.Q. Wang and B.L. Zhou. Microstructural Development of Al-15wt.%Mg₂Si In Situ Composite with Mischmetal Addition. *Materials Science and Engineering A*. 2000. 281: 102-144.
- [32] Y.G. Zhao, Q.D. Qin, W. Zhou and Y.H. Liang. Microstructure of the Ce-Modified In-Situ Mg₂Si/Al-Si-Cu Composite. *Journal of Alloys and Compounds*. 2005. 389: 1-4.
- [33] Zheng Na, Wang H., Zhao F., Gu Z., Li D. and Jiang Q. Modification of Primary Mg₂Si in Mg-5Si Alloys with Y₂O₃. *Transaction of Nonferrous Metals Society of China*. 2007. 17: 440-443.
- [34] M. Emany, H.R.J. Nodooshan and A. Malekan. The Microstructure, Hardness and Tensile Properties of Al-15%Mg₂Si In-situ Composite with Yttrium Addition. *Materials Design*. 2011. 32: 4559-4566.
- [35] Wang L., Guo. E., and Ma B. Modification Effect of Lanthanum in Primary Phase Mg₂Si in Mg-Si Alloys. *Journal of Rare Earth*. 2008. 26: 105-109.
- [36] Song C., Han Q. and Zhai Q. Review on Grain Refinement Methods for As-Cast Microstructure of Magnesium Alloy. *China Foundry*. 2009. 6: 93-103.
- [37] Zha Min, W.H., Liu Bo, Zhao Bing, Liang Minli, Li Dong and Jiang Qichuan. Influence of Melt Superheating on Microstructure of Mg-3.5Si-1Al Alloy. *Transaction of Nonferrous Metals Society of China*. 2008. 18: 107-112.
- [38] Wanqi Ji, Z.C.W Reif and K. Muller. Superheat Treatment of Al-7Si-0.55Mg Melt and Its Influence on the Solidification Structures and the Mechanical Properties. *Metallurgical and Materials Transactions A*. 2009. 34: 799-806.
- [39] Q.D. Qin, Y.G. Zhao, Y.H. Liang and Q. Zhou. Effect of Melt Superheating Treatment on Microstructure of Mg₂Si/Al-Si-Cu Composite. *Journal of Alloys and Compounds*. 2005. 399: 106-109.
- [40] M.M. Haque and A.F. Ismail. Effect of Superheating Temperatures on Microstructure and Properties of Strontium Modified Aluminum-Silicon Eutectic Alloy. *13th International Scientific Conference in Achievement in Mechanical and Materials Engineering*. Gliwice-Wisla, Poland: Worldwide

- Congress on Materials Manufacturing Engineering and Technology. 2005. 267-270.
- [41] John Weritz. *The Aluminium Association Alloy and Temper System*. United State. 2016.
- [42] Ron Cobden, Alcan and Banbury. *Aluminium: Physical properties, Characteristics and Alloys*. EAA - European Aluminium Association. 1994.
- [43] J.R. Davis. *Aluminium and Aluminium Alloy*. *Light Metals and Alloy*. 2001: 351-416.
- [44] D. Kopeliovich. *Classification of Aluminium Alloy: Cast Aluminium Alloy*. 2012.
- [45] D. Kopeliovich. *Classification of Aluminium Alloys: Temper Designation of Aluminium Alloys*. 2012.
- [46] S. Storen. *Understanding Aluminium as a Material: TALAT Lecture 2101.01*. 1994. *EAA - European Aluminium Association*.
- [47] H. Wang. *In-Situ Si/Al Composite Produced by Semisolid Metal Processing*. *Materials and Manufacturing Processes*. 2007. 22: 696-699.
- [48] Haizhi Ye. *An Overview of the Development of Al-Si Alloy Based Material for Engine Applications*. *Journal of Materials Engineering and Performance*. 2003. 12(3): 288-297.
- [49] *Aluminium Alloy: Aluminum Alloy Selection and Applications*. The Aluminium Association, Inc. 1998: 1-24.
- [50] K.C. Hari Kumar, N.C., Hans-Leo Lukas, Oksana Bodak and Lazar Rokhlin. *Aluminium – Magnesium – Silicon*. *Light Metal System*. 2005: 165-177. Springer: Verlag.
- [51] J. Zhang, Z.F., Y.Q. Wang and B.L. Zhou. *Equilibrium Pseudobinary Al-Mg₂Si Phase Diagram*. *Materials Science and Technology*. 2001. 17: 212-216.
- [52] V. Raghavan. *Al-Mg-Si (Aluminum-Magnesium-Silicon)*. *Journal of Phase Equilibria and Diffusion*. 2007. 28: 188-190.
- [53] Ram N.R., A.K.P. Rao, G.L. Dutta and M. Chakraborty. *Forming Behaviour of Al-TiC In-situ Composites*. *Materials Science Forum*. 2013. 765: 418-422.
- [54] E. Georgatis, A. Lekatou, A.E. Karantzalis, H. Petropoulos, S. Katsamakis and A. Poulia. *Development of a Cast Al-Mg₂Si-Si In Situ Composite*:

- Microstructure, Heat Treatment and Mechanical Properties. *Journal of Materials Engineering and Performance*. 2013. 22: 729-741.
- [55] A.R.Kennedy and S.M. Wyatt. Characterizing Particle-Matrix Interfacial Bonding in Particulate Al-TiC MMCs Produced by Different Methods: Composites Part A. *Applied Science and Manufacturing*. 2001. 32: 555-559.
- [56] A. Bahrami, A. Razaghian, M. Emamy and R. Khorshidi. The Effect of Zr on the Microstructure and Tensile Properties of Hot-Extruded Al-Mg₂Si Composite. *Materials Design*. 2012. 36: 323-330.
- [57] M. Emamy, M. Khodadadi, A. Honarbakhsh Raouf and N. Nasiri. The Influence of Ni Addition and Hot Extrusion on the Microstructure and Tensile Properties of Al-15%Mg₂Si Composite. *Materials Design*. 2013. 46: 381-390.
- [58] R.M. Aikin Jr. The Mechanical Properties of In-Situ Composites. *Journal of the Mineral, Metals and Materials Society (JOM)*. 1997. 49(8): 35-39.
- [59] K. Sundaram. Ex-situ and In-situ Metal Matrix Composite.
- [60] M. Emamy, A.R. Emami and K. Tavighi. The effect of Cu Addition and Solution Heat Treatment on the Microstructure Hardness and Tensile Properties of Al-15%Mg₂Si-0.15%Li Composite. *Materials Science and Engineering A*. 2013. 576: 36-44.
- [61] A. Akrami, M. Emamy and H. Mousavian. The Effect of Bi Addition on the Microstructure and Tensile Properties of Cast Al-15%Mg₂Si Composite. *Mat.-wiss. u. Werkstofftech*. 2013. 44: 431-435.
- [62] C. Li, Y.Y. Wu, H. Li and X.F. Liu. Morphological Evolution and Growth Mechanism of Primary Mg₂Si Phase in Al-Mg₂Si Alloys. *Acta Materialia*. 2011. 59: 1058-1067.
- [63] F. Misahi and M. Meratian. High Temperature Tensile Properties of Modified Mg/Mg₂Si In Situ Composite. *Materials Design*. 2011. 33: 557-562.
- [64] C. Li, Y. Wu, Hui Li, Y. Wu and X. Liu. Effect of Ni on Eutectic Structural Evolution in Hypereutectic Al-Mg₂Si Cast Alloys. *Materials Science and Engineering A*. 2010. 528: 573-577.
- [65] B. Stojanovic and L. Ivanovic. Application of Aluminium Hybrid Composites in Automotive Industry. *Technical Gazette*. 2015. 22(1): 247-251.
- [66] Wu Xiaofeng, Z. Guang'an, Wu Fufa and Wang Zhe. Influence of Neodymium Addition on Microstructure, Tensile Properties and Fracture

- Behavior of Cast Al-Mg₂Si Metal Matrix Composite. *Journal of Rare Earth*. 2013. 31(3): 307-312.
- [67] Yuhua Zhao, X.W., Xinghao Du and Chao Wang. Effects of Sb and Heat Treatment on the Microstructure of Al-15.5wt%Mg₂Si Alloy. *International Journal of Minerals, Metallurgy and Materials*. 2013. Springer.
- [68] T. Grostad. Nucleation of Primary Mg₂Si in Al-Mg-Si Alloys, in Department of Materials Science and Engineering. 2014. Norwegian University of Science and Technology: Norway. 1-12.
- [69] Kazuhiko Iwai and Jun Du. Modification of Primary Mg₂Si Crystals in Hypereutectic Mg-Si Alloy by Application Alternating Current. *Materials Transactions*. 2009. 50: 562-569.
- [70] L. Liao, X. Zhang, H. Wang, X. Li and N. Ma. Influence of Sb on Damping Capacity and Mechanical Properties of Mg₂Si-Mg-9Al Composite Materials. *Journal of Alloys and Compounds*. 2007. 430: 292-296.
- [71] C. Vives. Effect of Electromagnetic Vibrations During the solidification of Aluminium: Part 1. Solidification in the Presence of Crossed Alternating Electric Fields and Stationary Magnetic Field. *Metallurgical and Materials Transactions B*. 1994. 27: 445-454.
- [72] Kurz W. and D.J. Fisher. Fundamentals of solidification. 4th Edition. Switzerland: Trans Tech Publications. 1998.
- [73] W.D. Callister. Phase Transformation: Development of Microstructure and Alteration of Mechanical Behaviour. Materials Science and Engineering: An Introduction. 7th Edition. New York: John Wiley & Sons, Inc. 13. 2006.
- [74] D. Kaschiev. Nucleation: Basic Theory with Applications. Burlington: Butterworth-Heinemann, Oxford. 2000.
- [75] Donald R.A., Pradeep P.F. and Wendelin J.W. The Science and Engineering of Materials: Principle of Solidification. Sixth Edition. United State: Cengage Learning Inc. 8. 2010.
- [76] James J. De Yoreo and Peter G. Vekilov. Principles of Crystal Nucleation and Growth. 2003: 57-93.
- [77] J.W. Mullin. *Crystallization*. Fourth Edition. Oxford: Butterworth-Heinemann. 2001.
- [78] X.Y. Liu. Heterogeneous Nucleation or Homogeneous Nucleation. *Journal of Chemical and Physics*. 2000. 112: 9949-9955.

- [79] K. Chen, Z.Q. Li, J.S. Liu, J.N. Yang, Y.D. Sun and S.G. Bian. The Effect of Ba Addition on Microstructure of In Situ Synthesized $Mg_2Si/Mg-Zn-Si$ Composites. *Journal of Alloys and Compounds*. 2009. 487: 293-297.
- [80] L. Chen, H.Y. Wang, Y.J. L.M. Zha and Q.C. Jiang. Morphology and Size Control of Octahedral and Cubic Primary Mg_2Si in an $Mg-Si$ System by Regulating Sr Contents. *Cryst. Eng. Comm.* 2014. 16: 448-454.
- [81] Tanghong Yi, S.C., Shawn Li, Hao Yang, Sabah Bux, Zhixi Bian, Nebil A. Katcho, Ali Shakouri, Natalio Mingo, Jean-Pierre Fleurial, Nigel D. Browning and Susan M. Kauzlarich. Synthesis and Characterization of Mg_2Si/Si Nanocomposites Prepared from MgH_2 and Silicon, and Their Thermoelectric Properties. *Journal of Materials and Chemistry*. 2012. 22: 24805-24813.
- [82] I. Sunagawa. Growth and Morphology of Crystals. Japan: Mathematical Sciences. 1999.
- [83] L. Chen, H.Y. Wang, D. Luo, H.Y. Zhang, Bo Liu and Q.C. Jiang. Synthesis of Octahedron and Truncated Octahedron Primary Mg_2Si by Controlling the Sb Contents. *Cryst. Eng. Comm.* 2013. 15: 1787-1793.
- [84] M.R. Ghorbani, M. Emamy and N. Nemati. Microstructural and Mechanical Characterization of $Al-15\%Mg_2Si$ Composite Containing Chromium. *Materials Design*. 2011. 32: 4262-4269.
- [85] J.L. Hu, C.P. Tang, X.M. Zhang and Y.L. Deng. Modification of Mg_2Si in $Mg-Si$ Alloys with Neodymium. *Transaction of Nonferrous Metals Society of China*. 2013. 23: 3161-3166.
- [86] Q.C. Jiang, H.Y. Wang, Y. Wang, B.X. Ma and J.G. Wang. Modification of Mg_2Si in $Mg-Si$ Alloys with Yttrium. *Materials Science and Engineering A*. 2005. 392: 130-135.
- [87] J. Hou, C. Li and X. Liu. Nucleating Role of an Effective In Situ Mg_3P_2 on Mg_2Si in $Mg-Al-Si$ Alloys. *Journal of Alloys and Compounds*. 2011. 509: 735-739.
- [88] N. Nasiri, M. Emamy, A. Malekan and M.H. Norouzi. Microstructure and Tensile Properties of Cast $Al-15\%Mg_2Si$ Composite: Effects of Phosphorous Addition and Heat Treatment. *Materials Science and Engineering A*. 2012. 556: 446-453.

- [89] Yang Mingbo, and Shen Jia. Modification and Refinement Mechanism of Mg_2Si Phase in Sr Containing AZ61-0.7Si Magnesium Alloy. *Research and Development*. 2009. 6: 37-42.
- [90] M. Tebib, A.M. Samuel, F. Ajersch and X.G. Chen. Effect of P and Sr Additions on the Microstructure of Hypereutectic Al-15Si-14Mg-4Cu Alloy. *Materials Characterization*. 2014. 89: 112-123.
- [91] J.H. Jun. Microstructure and Damping Capacity of $Mg_2Si/MgAlSi(Bi)$ Composites. *Materials Transaction*. 2012. 53: 2064-2066.
- [92] A. Razaghian, A. Bahrami and M. Emamy. The Influence of Li on the Tensile Properties of Extruded in situ Al-15%Mg₂Si Composite. *Materials Science and Engineering A*. 2012. 532: 346-353.
- [93] M. Emamy, N. Nemati and A. Heidarzadeh. The Influence of Cu rich Intermetallic Phases on the Microstructure, Hardness and Tensile Properties of Al-15% Mg₂Si Composite. *Materials Science and Engineering A*. 2010. 527: 2998-3004.
- [94] N. Maleki, M. Meratian, M. Panjepour and A. Foroozmehr. The Effect of Zinc on the Morphology and Wear Resistance of Mg₂Si-Reinforced Magnesium Matrix Composites. 2011. 18th International Conference on Composite Materials (ICCM 18). Jeju Island.
- [95] X.F. Wu, G.G. Zhang and F.F. Wu. Microstructure and Dry Sliding Wear Behavior of cast Al-Mg₂Si In-situ Metal Matrix Composite Modified by Nd. *Rare Metals*. 2013. 32(3): 284-289.
- [96] *Barium Periodic Table*. Royal Society of Chemistry. 2016.
- [97] *Cerium. Periodic Table*. Royal Society of Chemistry 2016.
- [98] Doug Stewart, Cacbril D., Moore J. W and Kotz J. C. *Barium Element Facts*. Chemicool Periodic Table. 2017.
- [99] Z. Liu and M. Xie. Hypereutectic Al-Si-Mg In-Situ Composite Prepared by Melt Superheating. Switzerland: Trans. Tech. Publication. 2011: 113-116.
- [100] Changshuai Wang, J.Z., Lin Liu and Hengzhi Fu. Effect of Melt Superheating Treatment on Directional Solidification Interface Morphology of Multi-component Alloy. *Journal of Materials Science and Technology*. 2011. 27(7): 668-672.
- [101] E.F. Emley. Principles of Magnesium Technology. Oxford: Pergamon Oress Ltd. 1966.

- [102] O. Fakhraei, M. Emamy and H.Farhangi. The Effect of Al–5Ti–1B Grain Refiner on the Structure and Tensile Properties of Al–20%Mg Alloy. *Materials Science and Engineering A*. 2013. 465: 148-153.
- [103] W.D. Callister. *Materials Science and Engineering: An Introduction*. 7th Edition. Vol. 3. Salt Lake City, Utah: John Wiley & Sons, Inc. 2007.
- [104] J. Campbell. *Castings: Entrainment*. 2nd Edition. Boston, Butterworth Heinemann: Oxford. 2003.
- [105] F.C. Robles Hernandez and J.H. Sokolowski. Thermal Analysis and Microscopical Characterization of Al–Si Hypereutectic Alloys. *Journal of Alloys and Compounds*. 2006. 419: 180-190.
- [106] J.E. Gruzleski and B.M. Closset. The Treatment of Liquid Aluminum-Silicon Alloys. 1990. American United State of America: Foundrymen's Society, Inc
- [107] J. Campbell. Entrainment Defects. *Materials Science and Technology*. 2006. 22: 127-145.
- [108] Zheng Liu, M. Xie. Hypereutectic Al-Si-Mg In-situ Composite Prepared by Melt Treatment. *Advance Materials Research*. 2011. 194-196: 113-116.
- [109] S.G. Shabestari and M. Malekan. Computer-Aided Cooling Curve Thermal Analysis Used to Predict the Quality of Aluminum Alloys. *Journal of Thermal Analysis and Calorimetry*. 2011. 103: 453-458.
- [100] D. Emadi, L.V. Withing, S. Nafisi and R. Ghomashchi. Applications of Thermal Analysis in Quality Control of Solidification Processes. *Journal of Thermal Analysis and Calorimetry*. 2005. 81: 235-242.
- [111] S. Farahany, A. Ourdjini and M.H. Idris. The Usage of Computer-Aided Cooling Curve Thermal Analysis to Optimise Eutectic Refiner and Modifier in Al–Si Alloys. *Journal of Thermal Analysis and Calorimetry*. 2011. 109(1): 105-111.
- [112] S. Farahany, A. Ourdjini, M.H. Idris and S.G. Shabestari. Evaluation of the Effect of Bi, Sb, Sr and Cooling Condition on Eutectic Phases in an Al-Si ADC12 Alloy by In-situ Thermal Analysis. *Thermochimica Acta*. 2013. 559: 56-86.
- [113] Shabestari S.G. and M. Malekan. Assessment of the Effect of Grain Refinement of the Solidification Characteristics of 319 Aluminium Alloy Using Thermal Analysis. *Journal of Alloy and Compounds*. 2007. 492: 134-142.

- [114] Saeed Farahany. Assessment of the Effect Additives and Their Interaction on Silicon Structure of Complex Al-Si-Cu-Mg Alloy by Thermal Analysis, in *Materials Engineering*. 2012. Universiti Teknologi Malaysia (UTM), Johor: 181.
- [115] S.G. Shabestari, M. Malekan. Assessment of the Effect of Grain Refinement of the Solidification Characteristics of 319 Aluminium Alloy Using Thermal Analysis. *Journal of Thermal Analysis and Calorimetry*. 2007. 492: 134-142.
- [116] M. Azarbarmas, M. Emamy, M. Karamouz, M. Alipour and J. Rassizadehghani. The Effects of Boron Additions on the Microstructure, Hardness and Tensile Properties of In situ Al-15%Mg₂Si Composite. *Materials Design*. 2011. 33: 5049-5054.
- [117] N. Nafsin and HMMA. Rashed. Effects of Copper and Magnesium on Microstructure and Hardness of Al-Cu-Mg Alloys. *International Journal of Engineering and Advanced Technology (IJEAT)*. 2013. 2(5): 533-536.
- [118] M. Azabarmas, M. Emamy, J. Rasizadeh, M. Alipour and M. Karamouz. The Effect of Be on Mechanical Properties of Al-Mg₂Si In-situ Composite. *The Minerals, Metals and Materials Society*. 2011. 3: 1-9.
- [119] S. Farahany, H.R. Bakhsheshi-Rad, M.H. Idris, M.R.A. Kadir, A.F. Lotfabadi and A. Ourdjini. In-situ Thermal Analysis and Macroscopical Characterization of Mg-xCa and Mg-0.5Ca-xZn Alloy System. *Thermochimica Acta*. 2012. 527: 180-189.
- [120] A.E. Karantzalis, A. Lekatou, E. Georgatis, V. Poulas and H. Mavros. Microstructural Observations in a Cast Al-Si-Cu/TiC Composite. *Journal of Materials Engineering and Performance*. 2009. 19(4): 585-590.
- [121] S. Ji, W. Yang, F. Gao, D. Watson and Z. Fa. Effect of Iron on the Microstructure and Mechanical Property of Al-Mg-Si-Mn and Al-Mg-Si Die Cast Alloys. *Materials Science and Engineering A*. 2013. 564: 130-139.
- [122] J.A. Taylor. The Effect of Iron in Al-Si Casting Alloys. *Cooperative Research Centre for Cast Metals Manufacturing (CAST)*. 2003.
- [123] S.G. Shabestari. The Effect of Iron and Manganese on the Formation of Intermetallic Compounds in Aluminium-Silicon Alloys. *Materials Science and Engineering A*. 2004. 383: 289-298.

- [124] L. Anantha Narayanan, F.H. Samuel and J.E. Gruzleski. Crystallization Behavior of Iron-Containing Intermetallic Compounds in 319 Aluminum Alloy. *Metallurgical and Materials Transactions A*. 1994. 25: 1761-1773.
- [125] A.M. Samuel, F.H.S., C. Villeneuve, H.W. Doty and S. Valtierra. Effect of Trace Elements on B-Al₁₅FeSi Characteristics, Porosity and Tensile Properties of Al-Si-Cu (319) Cast Alloy. *International Journal of Casting Metal*. 2001. 14: 97-120.
- [126] J.A. Taylor, G.B.S. and D.H. StJohn. The Role of Iron in The Formation of Porosity in Al-Si-Cu Based Casting Alloys: Part II. A Phase Diagram Approach. *Metallurgical and Materials Transactions A*. 1999. 30: 4273-4280.
- [127] S.D. McDonald, A.K. Dahle, J.A. Taylor and D.H. StJohn. Eutectic Grains in Unmodified and Strontium-Modified Hypoeutectic Aluminum-Silicon Alloys. *Metallurgical and Materials Transactions A*. 2004. 35: 1829-1837.
- [128] S.D. McDonald, K.N. and A.K. Dahle. Eutectic Nucleation in Al-Si Alloys. *Acta Materialia*. 2004. 52: 4273-4280.
- [129] S. Nafisi and R. Ghomashchi. Combined Grain Refining and Modification of Conventional and Rheo-Cast A356 Al-Si Alloy. *Materials Characterization*. 2006. 57: 371-385.
- [130] Stuart D. McDonald, K. Nogita and A.K. Dahle. Eutectic Grain Size and Strontium Concentration in Hypoeutectic Aluminium–Silicon Alloys. *Journal of Alloys and Compounds*. 2006. 422: 184-191.
- [131] M.H. Mulazimoglu and A. Zaluska, J.E. Gruzleski and F. Paray. Electron Microscope Study in 6201 Aluminum Alloy of Al-Fe-Si Intermetallics. *Metallurgical and Materials Transactions A*. 1996. 27: 929-936.
- [132] N.S. Tiedje, J.A.T. and M.A. Easton. A New Multi-zone Model for Porosity Distribution in Al–Si Alloy Castings. *Acta Materialia*. 2013. 61: 3037-3049.
- [133] J. Zhang, Z.F., Y. Wang and B. Zhou. Microstructure and Mechanical Properties of In situ Al-Mg₂Si Composite. *Materials Science and Technology*. 2000. 16: 913-918.
- [134] Sathayapagal H. and K.N. Prabhu. Modification of Eutectic Silicon in Al–Si Alloys. *Journal of Materials Science*. 2008. 49: 3009-3027.
- [135] M. Rosefort, C.M., H. Buck and H. Koch. Determination of α - and β -AlFeSi-Phases in Wrought Aluminium Alloys. 1-7.

- [136] M.V. Kral, P.N.H. Nakashima and D.R.G. Mitchell. Electron Microscope Studies of Al-Fe-Si Intermetallics in an Al-11 Pct Si Alloy. *Metallurgical and Materials Transactions A*. 2006. 37: 1987-1997.
- [137] M. Husseinifar and D. Malakho. The Sequence of Intermetallics Formation during the Solidification of an Al-Mg-Si Alloy Containing La. *Metallurgical and Materials Transactions A*. 2010. 42: 825-833.
- [138] Z.H. Gu, H.Y. Wang, N. Zheng, M. Zha, L.L. Jiang, W. Wang and Q.C. Jiang. Effect of Melt Superheating Treatment on the Cast Microstructure of Mg-1.5Si-1Zn Alloy. *Journal of Materials Science*. 2008. 43: 980-984.
- [139] Chen H.S., Zu F.Q., Chen J., Zou Li, Ding G.H. and Huang Z.Y. The Effect of Melt Overheating on the Melt Structure Transition and Solidified Structures of Sn-Bi40 Alloy. *Science in China Series E: Technological Sciences*. 2008. 51. 1402-1408.