

**CARBON CRYOGEL PRODUCTION FROM LIGNIN, IONIC LIQUID AND
LIQUEFIED OIL PALM FROND AS CATALYST FOR ESTERIFICATION
OF LEVULINIC ACID**

MUZAKKIR BIN MOHAMMAD ZAINOL

UNIVERSITI TEKNOLOGI MALAYSIA

CARBON CRYOGEL PRODUCTION FROM LIGNIN, IONIC LIQUID AND
LIQUEFIED OIL PALM FROND AS CATALYST FOR ESTERIFICATION OF
LEVULINIC ACID

MUZAKKIR BIN MOHAMMAD ZAINOL

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy (Chemical Engineering)

Faculty of Chemical and Energy Engineering
Universiti Teknologi Malaysia

JUNE 2017

*To my beloved family, friends and
all those who have contributed in this thesis.
This thesis is very special for me and all of you.
Alhamdulillah.*

ACKNOWLEDGEMENT

Firstly, I would like to take this opportunity to express my gratitude to Allah S.W.T for His blessing and guidance. Alhamdulillah this long journey has come to an end, where I have gained a lot of experience in conducting the research and experiments, and also other tasks that I have performed and accomplished throughout my stay here, directly or indirectly.

My sincere and gratefulness goes to my supervisor, Prof. Ir. Dr. Nor Aishah Saidina Amin and co-supervisor, Dr. Mohd Asmadi Mohammed Yussuf for their priceless guidance and suggestion in supervising my research. Besides, they have taught me a lot in writing skill for preparation of journal paper. This knowledge will be very useful for me especially in the future works; academic and research. Besides, I would like to extend my warmest thanks to Chemical Reaction Engineering Group (CREG) members for their support and valuable inputs regarding the research. Special thanks to Dr. Nur Aainaa, Dr. Mahadhir, Mr. Latfi, Mrs. Zainab, Mrs. Ambiga, Mrs. Sabrina, Mrs. Nur Umisyuhada, Mrs. Roslindawati and for those who have helped me in the experimental work, analysis, characterization and thesis writing, directly or indirectly.

Furthermore, I also wish to express my gratitude and utmost appreciation to my beloved mother, Mrs. Na'amah Zakaria for being with me through this journey and all my siblings especially to my sisters; Mahfuzah, Mazrina and Mahaniza for their moral and financial support. To my late father, this thesis is special for you. Special thanks to all my friends especially to Mohd Feerdhous for their moral support. Last but not least, I would like to gratefully acknowledge the financial support by Ministry of Education (MOE) through MyPhD scholarship.

ABSTRACT

Carbon cryogel synthesized from lignin, ionic liquid (IL) and mixtures of liquefied oil palm frond-ionic liquid (LOPF-IL), was used as an acid catalyst for esterification of levulinic acid in ethanol. Commercial lignin was reacted with furfural via sol-gel poly-condensation reaction at 90 °C for 30 min and the gel was freeze-dried and finally carbonized or calcined to produce carbon cryogel. Parametric study for the gel preparation was conducted to evaluate the carbon cryogel surface area and acidity. Similar parametric study was also performed on gel synthesis from IL and furfural. The selected gel condition of IL and furfural was applied for gel preparation from LOPF-IL and furfural. Nitrogen physisorption and temperature programmed desorption of ammonia measurements revealed the selected carbon cryogels obtained a large total surface area ($>200 \text{ m}^2/\text{g}$) and high acidity ($>10 \text{ mmol/g}$). The selected carbon cryogels from lignin-furfural (CCLF), IL-furfural (CCIL) and liquefied OPF-IL-furfural (CCOPF) were further characterized using thermogravimetric analyzer, Fourier transform infrared spectroscopy, x-ray diffraction and field emission scanning electron microscopy with energy dispersive x-ray spectrometry. The phase structure of the synthesized spherical carbon cryogel was amorphous, has micro structures (microspheres) and thermally stable. The synthesized CCLF, CCIL and CCOPF were tested as catalyst in the esterification of levulinic acid. Carbon cryogels showed high potential as an acid catalyst for levulinic acid esterification with above 70.0 mol.% yield of ethyl levulinate. The kinetic studies using CCLF and CCIL revealed the esterification of levulinic acid followed pseudo-first order kinetics and have low activation energy. Meanwhile, the thermodynamic parameters conferred the reaction was endergonic and more ordered.

ABSTRAK

Kriogel karbon dihasilkan daripada lignin, cecair ionik (IL), dan campuran cecair pelepah kelapa sawit-cecair ionik (LOPF-IL), telah digunakan sebagai pemangkin asid bagi pengesteran asid levulinik dalam etanol. Lignin komersial bertindak balas dengan furfural melalui tindak balas poli-kondensasi sol-gel pada 90 °C selama 30 min dan gel ini dibekukeringkan dan akhirnya dikarbonkan atau dikalsinkan untuk menghasilkan kriogel karbon. Kajian parameter terhadap penyediaan gel telah dilakukan bagi menilai luas permukaan dan keasidan karbon kriogel. Kajian parameter yang sama juga dilakukan terhadap sintesis gel daripada IL dan furfural. Keadaan gel IL dan furfural yang terpilih telah digunakan bagi penyediaan gel daripada LOPF-IL dan furfural. Pengukuran fisijerapan nitrogen dan penyahjerapan berprogram suhu ammonia mendedahkan kriogel karbon yang dipilih memperoleh jumlah luas permukaan yang tinggi ($>200 \text{ m}^2/\text{g}$) dan keasidan ($>10 \text{ mmol/g}$). Kriogel karbon yang dipilih daripada lignin-furfural (CCLF), IL-furfural (CCIL) dan cecair OPF-IL-furfural (CCOPF) selanjutnya dicirikan dengan menggunakan analisis termogravimetri, pembelauan sinar-x, spektroskopi inframerah transformasi Fourier, dan mikroskopi elektron pengimbas pancaran medan dengan spektrometri sinar-x sebaran tenaga. Struktur fasa kriogel karbon yang disintesis ialah amorfus, mempunyai struktur mikro (mikrosfera), dan stabil secara terma. CCLF, CCIL dan CCOPF yang disintesis telah diuji sebagai pemangkin dalam tindak balas pengesteran asid levulinik. Kriogel-kriogel karbon menunjukkan potensi tinggi sebagai pemangkin asid bagi pengesteran asid levulinik dengan hasil etil levulinat melebihi 70.0 mol.%. Kajian kinetik menggunakan CCLF dan CCIL mendedahkan pengesteran asid levulinik mengikut kinetik tertib pseudo-pertama dan mempunyai tenaga pengaktifan yang rendah. Sementara itu, parameter termodinamik menjelaskan bahawa tindak balas adalah endergonik dan lebih teratur.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xiv
	LIST OF FIGURES	xvi
	LIST OF ABBREVIATIONS	xxiii
	LIST OF SYMBOLS	xxvi
	LIST OF APPENDICES	xxviii
1	INTRODUCTION	1
	1.1 Research Background	1
	1.2 Problem Statement	6
	1.3 Research Hypotheses	9
	1.4 Research Objectives	11
	1.5 Scope of Research	11
	1.6 Research Significance	14
	1.7 Research Outline	14

2	LITERATURE REVIEW	16
2.1	Biomass as Renewable Sources	16
2.1.1	Lignocellulosic Biomass Material and Its Composition	17
2.1.1.1	Cellulose	18
2.1.1.2	Hemicellulose	20
2.1.1.3	Lignin	21
2.1.2	Oil Palm Frond (OPF)	22
2.2	Liquefaction Process in Biomass Conversion	23
2.2.1	Factor Affecting Liquefaction Process	25
2.2.1.1	Reaction Temperature	26
2.2.1.2	Reaction Time	27
2.2.1.3	Type of Catalysts	28
2.2.1.4	Solvent	28
2.3	Lignocellulosic Biomass Derivation for Catalyst Preparation	29
2.4	Ionic Liquid as Green Solvent	37
2.5	Production of Resin	43
2.5.1	Phenolic Resin	43
2.5.1.1	Phenolic-Formaldehyde Resin	45
2.5.1.2	Phenolic-Furfural Resin	47
2.5.1.3	Resin from Biomass Derived- Product	49
2.5.2	Type of Phenolic Resin	52
2.5.2.1	Novolak Type Resin	52
2.5.2.2	Resol Resin	53
2.6	Carbon Gel	55
2.6.1	Dried Organic Gel	56
2.6.2	Carbon Cryogel	59
2.7	Ethyl levulinate Production via Catalytic Esterification Process	61
2.7.1	Applications of Alkyl Levulinate	61

2.7.2	Process Synthesis of Ethyl Levulinate	62
2.7.2.1	Ethyl levulinate from Levulinic acid	63
2.7.2.2	Ethyl levulinate from Furfuryl Alcohol	66
2.7.2.3	Ethyl levulinate from Biomass Derivation	68
2.7.3	Catalyst and Their Catalytic Activity	69
2.7.4	Factor Affecting Ethyl Levulinate Synthesis	70
2.7.4.1	Catalyst Loading	70
2.7.4.2	Ratio of Ethanol to Levulinic Acid	76
2.7.4.3	Reaction Temperature	77
2.7.4.4	Reaction Time	78
2.7.5	Kinetic and Thermodynamic Studies	79
2.8	Summary	83
3	METHODOLOGY	85
3.1	Material and Chemical	85
3.2	Overall Methodology	86
3.3	Carbon Cryogel Production from Lignin and Furfural	89
3.4	Carbon Cryogel Production from Ionic liquid and Furfural	92
3.5	Carbon Cryogel Production from Liquefied Oil Palm Frond Mixture	94
3.5.1	Parameters Study on Liquefaction of Oil Palm Frond (OPF)	94
3.5.2	Gel Synthesis and Carbon Cryogel Preparation from LOPF-IL	97
3.6	Characterization and Analysis of Samples	98
3.6.1	Nitrogen Adsorption and Desorption	98
3.6.2	NH ₃ -Temperature Programmed Desorption	99

3.6.3	Fourier Transform Infrared Spectroscopy (FTIR)	99
3.6.4	Thermogravimetric Analyzer (TGA)	99
3.6.5	X-Ray Diffraction (XRD)	100
3.6.6	Field Emission Scanning Electron Microscopy with Energy Dispersive X-ray Spectrometry (FESEM-EDX)	100
3.6.7	High performance Liquid Chromatography (HPLC)	100
3.7	Esterification Reaction of Levulinic Acid	101
3.7.1	Catalytic Testing for Screening Process	102
3.7.2	Parameter study of Ethyl Levulinate Synthesis	102
3.7.3	Catalyst Reusability for Esterification Reaction	104
3.7.4	Kinetic and Thermodynamic Studies for Ethyl Levulinate Synthesis	105

4	CARBON CRYOGEL MICROSPHERES FROM LIGNIN-FURFURAL MIXTURE	109
4.1	Introduction	109
4.2	Parameter study on Carbon Cryogel Synthesis: Effect on Carbon Cryogel Surface Area and Acidity	110
4.2.1	Effect of Lignin to Furfural Ratio	110
4.2.2	Effect of Lignin to Water Ratio	112
4.2.3	Effect of Acid Concentration	114
4.2.4	Effect of Carbonization Temperature and Time	116
4.2.5	Effect of Calcination Temperature and Time	119
4.3	Characterization on Selected Carbon Cryogel	123
4.3.1	Fourier Transform Infrared Spectroscopy (FTIR)	123
4.3.2	Thermogravimetric Analysis (TGA)	126

4.3.3	X-ray Diffraction (XRD)	128
4.3.4	Field Emission Scanning Electron Microscopy with Energy Dispersive X-ray Spectrometry (FESEM-EDX)	130
4.4	Perspective on Calcined Cryogel Production as Potential Catalyst	131
4.5	Reaction Using Carbon Cryogel from Lignin- furfural	132
4.5.1	Catalytic Testing on Esterification Reaction	132
4.5.2	Parameter Study on Esterification Reaction	136
4.5.3	Kinetic and Thermodynamic Studies on Esterification Reaction	142
4.6	Summary	153
5	CARBON CRYOGEL MICROSPHERES FROM IONIC LIQUID-FURFURAL MIXTURE	155
5.1	Introduction	155
5.2	Parameter study on Carbon Cryogel Synthesis: Effect on Carbon Cryogel Surface Area and Acidity	156
5.2.1	Effect of Furfural to Ionic Liquid Ratio	157
5.2.2	Effect of Water to Ionic Liquid Ratio	158
5.2.3	Effect of Acid Loading	160
5.2.4	Effect of Calcination Temperature and Time	161
5.3	Characterization on Selected Carbon Cryogel	165
5.3.1	Fourier Transform Infrared Spectroscopy (FTIR)	165
5.3.2	Thermogravimetric Analysis (TGA)	167
5.3.3	X-ray diffraction (XRD)	169
5.3.4	Field Emission Scanning Electron Microscopy with Energy Dispersive X-ray Spectrometry (FESEM-EDX)	170
5.4	Perspective on CCIL Production as Potential Catalyst	172

5.5	Reaction Using Carbon Cryogel from Ionic Liquid-furfural	173
5.5.1	Catalytic Testing on Esterification Reaction	174
5.5.2	Parameters Studies on Esterification Reaction	177
5.5.3	Kinetic and Thermodynamic Studies on Esterification Reaction	182
5.6	Summary	192
6	CARBON CRYOGEL PRODUCTION FROM OIL PALM FROND LIQUIFACTION- IONIC LIQUID MIXTURES IN FURFURAL	194
6.1	Introduction	194
6.2	Liquefaction of Oil Palm Frond	194
6.2.1	Parameter Study on Liquefaction Process	195
6.2.2	Characterization and Analysis of Samples Product	199
6.3	Synthesis and Characterization of Carbon Cryogel	205
6.3.1	Fourier Transform Infrared Spectroscopy (FTIR)	205
6.3.2	Thermogravimetric Analysis (TGA)	206
6.3.3	Nitrogen Adsorption and Desorption	208
6.3.4	Temperature Programmed Desorption (TPD)	209
6.3.5	X-ray diffraction (XRD)	210
6.3.6	Field Emission Scanning Electron Microscopy with Energy Dispersive X-ray Spectrometry (FESEM-EDX)	212
6.4	Reaction Using Carbon Cryogel from OPF Liquefaction-Ionic Liquid-Furfural Mixture	213
6.4.1	Parameters Studies on Esterification Reaction	213
6.4.2	Reusability of CCOPF on Esterification Reaction	215

6.4.3	Comparative Studies of Catalyst Performance on the Reaction	216
6.5	Summary	218
7	CONCLUSIONS AND RECOMMENDATIONS	221
7.1	Conclusions	221
7.2	Recommendations	224
	REFERENCES	226
	Appendices A-D	247-253

LIST OF TABLES

TABLE NO	TITLE	PAGE
1.1	Examples of the biomass energy sources.	3
2.1	Lignocelluloses Biomass-based catalysts preparation.	31
2.2	The Ionic Liquids with Their Structures and Short Names.	38
2.3	Pretreatment of lignocellulosic biomass in ILs.	42
2.4	Phenolic monomers and aldehyde-type components.	44
2.5	Monomers for furan resin.	45
2.6	Types of novolak resins.	53
2.7	Alkyl levulinate synthesis via levulinic acid esterification using different types of alcohol and catalysts.	72
2.8	Activation energy (E_a) of the esterification of levulinic acid by using a different type of catalysts and solvents.	81
3.1	List of chemicals used in the study	85
3.2	Conditions of esterification reaction testing for CCLF and CCIL	102
3.3	Conditions for parameters studies of levulinic acid esterification.	103
4.1	Related functional group of lignin, CLF and selected CCLF.	124
4.2	Comparison study on the levulinic acid esterification via heterogeneous acid catalyst.	141
4.3	Kinetic parameters of levulinic acid esterification using CCLF.	148

4.4	Activation energy and thermodynamic parameters of levulinic acid esterification using CCLF.	151
5.1	Related functional group of [BMIM][HSO ₄], CIL and CCIL.	166
5.2	Comparison levulinic acid conversion and ethyl levulinate yield via heterogeneous acid catalyst	181
5.3	Kinetic parameters of levulinic acid esterification using CCIL.	187
5.4	Activation energy and thermodynamic parameters of levulinic acid esterification using CCIL.	191
6.1	Estimated composition of oil palm frond (wt.%, dry basis composition based on TGA)	195
6.2	Liquefaction of OPF.	196
6.3	OPF Liquefaction under Selected Conditions.	199
6.4	Related functional group of OPF, OPF residue and LOPF-IL mixture.	201
6.5	Related functional group of COPF and CCOPF.	206
6.6	Comparison heterogeneous catalyst performance for ethyl levulinate production.	217

LIST OF FIGURES

FIGURE NO	TITLE	PAGE
1.1	Biomass Initiatives as Renewable Energy (Sumathi <i>et al.</i> , 2008).	2
2.1	Components in Plant Biomass. Updated from Mohan <i>et al.</i> (2006).	17
2.2	Macromolecular Network (Olivier-Bourbigou <i>et al.</i> , 2010).	18
2.3	The structure of Cellulose Chain (Mohan <i>et al.</i> , 2006; Olivier-Bourbigou <i>et al.</i> , 2010).	19
2.4	Inter and Intra H-bonds in Cellulose (Olivier-Bourbigou <i>et al.</i> , 2010).	19
2.5	The Structure of Hemicellulose.	20
2.6	Building Blocks of Lignin (Chakar and Ragauskas, 2004).	21
2.7	Oil Palm Frond (OPF).	23
2.8	Schematic Diagram for Liquefaction Reaction (Yokoyama and Matsumura, 2008).	24
2.9	Carbon support/modified catalyst derived from lignocelluloses biomass.	30
2.10	Common Cations and Anions in Ionic Liquid Structures. Adapted from Fauzi and Amin (2012).	39
2.11	The Classification of Cation and Anion as Acidic and Basic Ionic Liquids (Olivier-Bourbigou <i>et al.</i> , 2010).	40

2.12	The Schematic Diagram for Imidazolium-Based Ionic Liquid with a Different Type of Interactions (Olivier-Bourbigou <i>et al.</i> , 2010).	40
2.13	Reaction mechanism for the addition of formaldehyde on phenol in basic medium (Fink, 2005a).	46
2.14	Acid catalyzed self-condensation of furfuryl alcohol (Fink, 2005b).	48
2.15	Proposed mechanism of lignin-furfural condensation products (Dongre <i>et al.</i> , 2015).	51
2.16	Structure of novolak resin (Fink, 2005a).	53
2.17	Structure of resol resin (Fink, 2005a).	54
2.18	SEM images of RF dried gels. (a) RF aerogel, (b) RF cryogel, (c) RF xerogels (Czakkal <i>et al.</i> , 2005).	57
2.19	SEM images of (a) carbon xerogel, (b) carbon cryogel, (c) carbon aerogels from melamin, resorcinol and formaldehyde (Veselá <i>et al.</i> , 2015).	57
2.20	Mechanism of Ice Growth during Freezing (Large Enough Solvent) (a) Wet Gel (b) Ice Crystals Appearance (c) Ice Crystal Growth and Texture Reorganization (d) Dried Polymer After Ice Removal by Sublimation (Job <i>et al.</i> , 2005).	58
2.21	SEM Images of Carbon Cryogel for (a) Microspheres (b) Surface and (c) Cross Section (Yamamoto <i>et al.</i> , 2002).	60
2.22	Feedstocks used in synthesis alkyl levulinates and their potential applications (Démolis <i>et al.</i> , 2014).	62
2.23	Alternative routes in derived alky levulinate (Melero <i>et al.</i> , 2013).	64
2.24	Levulinic acid conversion to other chemicals and fuels (Rackemann and Doherty, 2011).	65
2.25	Proposed mechanism for levulinic acid esterification with ethanol (Pasquale <i>et al.</i> , 2012).	65
2.26	Proposed mechanism for levulinic acid esterification with ethanol in the presence of ArSO ₃ H-HMCS (Song <i>et al.</i> , 2015).	66

2.27	Possible mechanism of ethanolysis of furfuryl alcohol in the presence of ArSO ₃ H-HMCS for ethyl levulinate production (Song <i>et al.</i> , 2015).	67
2.28	Two possible catalytic route for levulinate ester production (Neves <i>et al.</i> , 2013).	68
3.1	General steps of research works of this study.	87
3.2	Overall methodology of processes involve in this study.	88
3.3	Heating setup for gels synthesis.	90
3.4	Schematic diagram of CCLF production.	90
3.5	Process summary and methodology of CCLF production (Phase 1a).	91
3.6	1-Butyl-3-methylimidazolium hydrogen sulfate [BMIM][HSO ₄].	92
3.7	Process summary and methodology of CCIL production (Phase 1b).	93
3.8	Process summary and methodology for the liquefaction and CCOPF productions (Phase 1c).	95
3.9	Schematic diagram for liquefaction process (Supandi, 2009).	96
3.10	Flow process of OPF liquefaction reaction.	97
3.11	Schematic diagram for esterification process using reactor setup.	101
4.1	Effect of lignin to furfural (L/F) ratio (at L/W = 0.7, 6M, carbonize = 500 °C, 4 h) on CCLF surface area and acidity synthesized at 90 °C, 0.5 h.	112
4.2	Effect of lignin to water (L/W) ratio (at L/F = 1.0, 6M, carbonize = 500 °C, 4 h) on CCLF surface area and acidity synthesized at 90 °C, 0.5 h.	113
4.3	Effect of acid concentration (at L/F = 1.0, L/W = 1.0, carbonize = 500 °C, 4 h) on CCLF surface area and acidity synthesized at 90 °C, 0.5 h.	115
4.4	The effect of carbonization temperature at 5 h (L/F = 1.0, L/W = 1.0, 8M) on surface area and acidity of carbonized CLF.	116

4.5	NH ₃ -TPD thermograph of carbonized CLF at different carbonization temperature (at 5 h).	118
4.6	The effect of carbonization time at 500 °C (L/F = 1.0, L/W = 1.0, 8M) on surface area and acidity of carbonized CLF.	118
4.7	The effect of calcination temperature at 4 h (L/F = 1.0, L/W = 1.0, 8M) on surface area and acidity of calcined CLF.	119
4.8	NH ₃ -TPD thermograph of calcined CLF at different calcination temperature (at 4 h).	120
4.9	The effect of calcination time at 500 °C (L/F = 1.0, L/W = 1.0, 8M) on surface area and acidity of calcined CLF.	121
4.10	(a) N ₂ sorption isotherm and (b) pore distribution of selected calcined CLF (500 °C, 1 h).	122
4.11	FTIR spectra of lignin, CLF and selected carbonized CLF (500 °C, 4 h) and calcined CLF (500 °C, 1 h).	124
4.12	(a) TGA and (b) DTG curve of lignin, CLF and selected carbonized CLF (500 °C, 4 h) and calcined CLF (500 °C, 1 h).	127
4.13	XRD diffractograms of (a) lignin, (b) CLF, (c) carbonized CLF and (d) calcined CLF.	129
4.14	FESEM images of (a) lignin, (b) CLF and selected (c) carbonized CLF (500 °C, 4 h) and (d) calcined CLF (500 °C, 1 h).	131
4.15	The yield of ethyl levulinate using carbonized and calcined CLF at 78°C, 10 h, 15 wt.% catalyst loading, and 19:1 molar ratio of ethanol to levulinic acid. The effects of carbonization and calcination (a) temperature and (b) time.	134
4.16	Proposed reaction mechanism of levulinic acid with ethanol in the presence of carbon cryogel.	136
4.17	The yield of ethyl levulinate and levulinic acid conversion of esterification reaction catalyzed by calcined CLF at different (a) catalyst loading (78°C, 6 h,	

	20:1), (b) molar ratio of ethanol to levulinic acid (78°C, 6 h, 25 wt.%), (c) reaction temperature (6 h, 25 wt.%, 15:1), and (d) reaction time (150°C, 25 wt.%, 15:1).	138
4.18	Reusability of CCLF on levulinic acid conversion.	140
4.19	Effect of (a) CCLF particle sizes and (b) agitation speed on levulinic acid conversion (78 °C, 25 wt.%, 15:1).	143
4.20	Effect of temperature and time on the levulinic acid conversion (at 25 wt.%, 15:1).	145
4.21	Concentration profile of levulinic acid consumption and ethyl levulinate production at 78 °C and 150 °C (25 wt.%, 15:1).	146
4.22	Plot of pseudo- (a) zeroth, (b) first, and (c) second order kinetic models for levulinic acid conversion. ● 78°C, ▲ 100°C, ■ 120°C, × 150°C.	147
4.23	Parity plot of pseudo- (a) zeroth, (b) first, and (c) second order kinetic model.	149
4.24	Arrhenius plot of $\ln k$ versus $1/T$ of pseudo-first order reaction.	151
4.25	Plot of $\ln k/T$ versus $1/T$ for the levulinic acid esterification in the presence of CCLF.	152
5.1	Effect of furfural to IL (F/IL) ratio (at W/IL = 0.125, 0.5 mL acid loading, 400 °C, 2 h) on CCIL surface area and acidity.	158
5.2	Effect of water to IL (W/IL) ratio (at F/IL = 1.25, 0.5 mL acid loading, 400 °C, 2 h) on CCIL surface area and acidity.	159
5.3	Effect of acid loading (at F/IL = 1.25, W/IL = 0.125, 400 °C, 2 h) on CCIL surface area and acidity.	160
5.4	Effect of calcination (a) temperature and (b) time (at F/IL = 1.25, W/IL = 0.125, 0.5 mL acid loading) on CCIL surface area and acidity.	162
5.5	NH ₃ -TPD thermograph of CCIL at different calcination temperature.	163

5.6	(a) Nitrogen sorption isotherm and (b) pore distribution of selected CCIL.	164
5.7	FTIR Spectra of (a) [BMIM][HSO ₄], (b) CIL and (c) CCIL.	166
5.8	(a) TGA and (b) DTG of [BMIM][HSO ₄], CIL and CCIL.	168
5.9	XRD patterns of (a) CIL and (b) CCIL.	170
5.10	FESEM images of (a) CIL at 250x, (b) CCIL at 1000x and (c) CCIL at 5000x.	171
5.11	Proposed reaction mechanism of levulinic acid with ethanol on the Brønsted acid sites of CCIL.	173
5.12	Reaction testing on ethyl levulinate production (at ethanol to LA molar ratio = 19, catalyst loading = 15 wt.%, ~78 °C, 6 h) by using CCIL at different (a) F/IL ratio, (b) W/IL ratio, (c) acid loading, and calcination (d) temperature and (e) time.	176
5.13	The yield of ethyl levulinate and levulinic acid conversion of esterification reaction catalyzed by CCIL at different (a) catalyst loading (78°C, 4 h, 20:1), (b) molar ratio of ethanol to levulinic acid (78°C, 4 h, 30 wt.%), (c) reaction temperature (4 h, 30 wt.%, 15:1), and (d) reaction time (170°C, 30 wt.%, 15:1).	179
5.14	Reusability of CCIL on levulinic acid conversion.	180
5.15	Effect of (a) CCIL particle sizes and (b) agitation speed on levulinic acid conversion (78 °C, 30 wt.%, 15:1).	183
5.16	Concentration profile of levulinic acid consumption and ethyl levulinate production at 170 °C (30 wt.%, 15:1) in the presence of CCIL.	184
5.17	Plot of pseudo- (a) zeroth, (b) first, and (c) second order kinetic model for levulinic acid conversion by CCIL. ●78°C, ▲100°C, ■120°C, ×150°C, +170°C.	186
5.18	Parity plot of pseudo- (a) zeroth, (b) first, and (c) second order kinetic models.	188

5.19	Arrhenius plot of $\ln k$ versus $1/T$ of pseudo-first order reaction.	190
5.20	Plot of $\ln k/T$ versus $1/T$ for the levulinic esterification in the presence of CCIL.	192
6.1	Effects of (a) the IL to OPF ratio (150°C, 1 h), (b) the reaction temperature (4 IL/OPF, 1 h), and (c) the reaction time (4 IL/OPF, 140°C) on liquefaction product yield and IL recovery.	197
6.2	FTIR spectra of (a) OPF, (b) OPF residue, (c) cellulose, (d) LOPF-IL mixture, and (e) [BMIM][HSO ₄].	201
6.3	TGA/DTG results for (a) OPF, the OPF residue and cellulose and (b) [BMIM][HSO ₄] and the LOPF-IL mixture.	203
6.4	FESEM images of (a) OPF and (b) the OPF residue.	204
6.5	FTIR spectra of COPF and CCOPF.	205
6.6	TGA/DTG curves of COPF and CCOPF.	207
6.7	(a) Nitrogen sorption isotherm and (b) pore distribution of CCOPF.	209
6.8	NH ₃ -TPD thermograph of CCOPF.	210
6.9	XRD patterns of COPF and CCOPF.	211
6.10	FESEM images of (a) COPF at 500x, (b) CCOPF at 500x and (c) CCOPF at 5000x.	212
6.11	Effects of (a) the ethanol to levulinic acid molar ratio, (b) catalyst loading and (c) the reaction time on esterification reaction yield and conversion.	214
6.12	Reusability of CCOPF for levulinic acid esterification.	216

LIST OF ABBREVIATIONS

[AMIM][Cl]	–	1-allyl-3-methylimidazolium chloride
[BMIM][CH ₃ COO]	–	1-butyl-3-methylimidazolium acetate
[BMIM][Cl]	–	1-butyl-3-methylimidazolium chloride
[BMIM][HSO ₄]	–	1-butyl-3-methylimidazolium hydrogensulfate
[BMIM][MeSO ₄]	–	1-butyl-3-methylimidazolium methylsulfonate
[BMIM][N(CN)]	–	1-butyl-3-methylimidazolium methylsulfonate
[BMIM][OTf]	–	1-butyl-3-methylimidazolium trifluoromethanesulfonate
[EMIM] [CH ₃ COO]	–	1-ethyl-3-methylimidazolium acetate
[EMIM][Cl]	–	1-ethyl-3-methylimidazolium chloride
Ba(OH) ₂	–	Barium hydroxide
BET	–	Brunauer-Emmett-Teller
BHMF	–	bis(hydroxymethyl)furan
BJH	–	Barrett-Joyner-Halenda
CCIL	–	Carbon cryogel ionic liquid-furfural
CCLF	–	Carbon cryogel lignin-furfural
CCOPF	–	Carbon cryogel from liquefied OPF-IL
CO ₂	–	Carbon dioxide
DMF	–	Dimethyleformamide
DMSO	–	Dimethyl sulfoxide
EDX	–	Energy dispersive X-ray
EFB	–	Empty fruit bunch

EL	–	Ethyl levulinate
FA	–	Furfuryl alcohol
FESEM	–	Field emission scanning electron microscopy
FTIR	–	Fourier Transform Infrared
GC-FID	–	Gas chromatography flame ionization detector
GPN	–	General-purpose novolak
GVL	–	γ -valerolactone
H ₂ O	–	Water
H ₂ SO ₄	–	Sulfuric acid
HCl	–	Hydrochloric acid
HMF	–	5-hydroxymethylfurfural
HON	–	High <i>ortho</i> novolak
HPA-AC	–	Heteropoly acid activated carbon
HPLC	–	High performance liquid chromatography
HPN	–	High <i>para</i> novolak
IL	–	Ionic liquid
K ₂ CO ₃	–	Potassium carbonate
KOH	–	Potassium hydroxide
KOH-AC	–	Potassium hydroxide activated carbon
LA	–	Levulinic acid
LOPF	–	Liquefied OPF
LOPF-IL	–	Liquefied OPF-ionic liquid
MARDI	–	Malaysian Agricultural Research and Development Institute
MPOB	–	Malaysian Palm Oil Board
NaOH	–	Sodium hydroxide
NH ₃	–	Ammonia
OPF	–	Oil palm frond
OPT	–	Oil Palm Trunk
PEFB	–	Phenolated empty fruit bunch
PF	–	Phenol-formaldehyde

Rb ₂ CO ₃	–	Rubidium carbonate
RF	–	resorcinol-formaldehyde
RHA	–	Rice husk ash
RI	–	Refractive index
SCB	–	Sugar cane bagasse
SEM	–	Scanning electron microscopy
TGA	–	Thermogravimetric analysis
TPA	–	Tungstophosphoric acid
TPD	–	Temperature programmed desorption
UV	–	Ultraviolet
XRD	–	X-ray diffraction

LIST OF SYMBOLS

°	–	Degree
%	–	Percentage
ΔG^\ddagger	–	Gibbs energy of activation
ΔH^\ddagger	–	Enthalpy of activation
ΔS^\ddagger	–	Entropy of activation
°C	–	Degree Celsius
μL	–	Microliter
μm	–	Micrometer
‡	–	State of activated complex
A	–	Pre-exponential factor
C_A	–	Concentrations of levulinic acid
C_{AO}	–	Initial concentrations of levulinic acid
C_B	–	Concentrations of ethanol
C_C	–	Concentrations of ethyl levulinate
C_D	–	Concentrations of water
C_E	–	Final concentration of ethyl levulinate
C_L	–	Final concentration of levulinic acid
cm^3	–	Cubic centimeter
E_a	–	Activation energy
g	–	Gram
h	–	Hour
h	–	Planck's constant
I_f	–	Weight of ionic liquid after recovery
I_i	–	Initial weight of ionic liquid
J	–	Joules

k	–	Reaction rate constant
K	–	Kelvin
K^{\ddagger}	–	Thermodynamic equilibrium constant
k_B	–	Boltzmann's constant
kJ	–	Kilojoules
kV	–	Kilovolt
L_f	–	Final weight of liquid product
M	–	Molar
m^2	–	Square meter
mA	–	Miliampere
M_E	–	Molecular weight of ethyl levulinate
mg	–	Milligram
min	–	Minutes
mL	–	Milliliter
M_L	–	Molecular weight of levulinic acid
Mmol	–	Milimolar
MPa	–	Megapascal
P	–	Total weight of ionic liquid and OPF
R	–	Gas constant
R^2	–	Regression coefficient
s	–	Seconds
t	–	Time
T	–	Temperature
v/v	–	Volume per volume
V_p	–	Final volume of product
W_i	–	Weight of levulinic acid
wt.	–	Weight
wt/wt	–	Weight per weight
X_A	–	Conversion of levulinic acid

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	List of Publications	247
B	Data of Production of Carbon Cryogel	248
C	Calibration Curve	250
D	Mathematical Derivation For Kinetic Study	252

CHAPTER 1

INTRODUCTION

1.1 Research Background

Nowadays, biomass energy becomes an attraction especially among the researches because it has high potentials as energy sources couple with the abundant availability. Biomass waste can be converted into renewable energy (bio-fuel and bio-power) or value added products (bio-product) (Sumathi *et al.*, 2008), as shown in Figure 1.1. There are many sources of biomass such as waste from plants and animals that can be used to produce energy for wide range of applications. Plants, animal and human are sources of biomass energy. This energy can be used in generating electricity, heating homes, fueling vehicles and provide process heat for industrial facilities (Demirbaş, 2001).

Biomass resources can be divided into three categories. The first is wastes (agricultural, crop residues, urban organic and urban wood wastes), the second is forest products (wood, logging residues, trees, and waste from forest cleaning) and the last category is the energy crops (consists of short rotation woody crops, grasses, starch crop, sugar crop, and oilseed crop) (Demirbaş, 2001). Besides, Yusoff (2006) have mentioned that the sources of biomass energy come from plant and animal

materials such as wood from the natural forest, waste from agricultural and forest industries, and domestic wastes. Furthermore, Effendi *et al.* (2008) has done a review on the biomass feedstock and they classified it into five categories which are woods (softwood, hardwood), forest residue (bark waste, peat moss, treetops, limbs), agriculture residues (bagasse, cashew nut shell, corn bran), industrial residues (paper and wood waste), and industrial lignins (organosolv lignin, liginosulphonate).

Thus, from the classification above, the biomass sources can be simplified into four major inputs as shown in Table 1.1. Lignocellulosic biomass that was come from the agricultural, forest and industrial sources was usually used in derived chemicals, fuels and materials. While for domestic biomass it can be used in fermentation in producing light hydrocarbon like methane. The by-product of fermentation such as bio-solid can be converted into a new material such as fertilizer.




Figure 1.1 Biomass Initiatives as Renewable Energy (Sumathi *et al.*, 2008).

In Malaysia, large amount of palm oil residues are produced including oil palm fronds (OPF), empty fruit bunches (EFB) and also palm oil mill effluent (POME). Therefore, many researches in Malaysia are interesting in developed new products and chemical derivative from palm oil biomass since it is largely produced each year. Biomass from palm oil plantation are usually recycled or reused for other applications. Fronds, empty fruit bunches and palm oil mill effluent have already

been used in nutrient recycling (MPOB, 2012). A total of 10 tonnes pruned fronds are produced per hectare per year (MPOB, 2012). Thus, in this study, biomass OPF is utilized to produce carbon-based catalyst.

Table 1.1 : Examples of the biomass energy sources.

Sources	Example
Domestic	Human and food waste from urban and rural area
Livestock and agricultural	Plant crops residue, grasses, animal waste
Forest	Wood, logging residue, trees, bark and forest cleaning waste
Industrial	Industrial waste and lignin, paper and wood waste

Various types of homogeneous and heterogeneous catalysts including acid and base (organic and inorganic), metal oxide, and non-metal oxide (Alsalmeh *et al.*, 2008; Casas *et al.*, 2013; Gombotz *et al.*, 2012; Pasquale *et al.*, 2012; Yan *et al.*, 2013; Zhang *et al.*, 2012) are being synthesized. Recently, there is a prevalence of biomass-derived catalysts for application in green chemical processes (Chin *et al.*, 2012; Hidayat *et al.*, 2015; Man *et al.*, 2013; Olivier-Bourbigou *et al.*, 2010; Steinrück and Wasserscheid, 2015). In fact, carbon has been widely explored in the development of catalyst (Mar and Somsook, 2012; Shu *et al.*, 2009) instead of using as merely adsorbents only (Al-Omair and El-Sharkawy, 2007; Kadirvelu *et al.*, 2002; Malik, 2004). Carbon is suitable as catalyst support due to its high surface area and thermal stability (Baroutian *et al.*, 2010; Han *et al.*, 2010; Hara, 2010; Labrecque and Lavoie, 2011). These two properties are important to be applied as catalyst support in various types of reactions especially at high temperature.

Wide application of the carbon gel has attracted our attention in synthesis the carbon gel as the catalyst or catalyst supports. Carbon gel is one of the carbon types similar to activated carbon, carbon composite, and carbon film. However, the carbon gel is synthesized using chemicals and prepared by drying and carbonization process.

Different drying methods such as supercritical drying, freeze drying and evaporative drying would produce aerogels, cryogels, and xerogels, respectively. Carbon cryogel has good properties, characteristics and much potential due to its unique structure. There are some applications that used carbon cryogel which are column packing material in high performance liquid chromatography (HPLC) (Yamamoto *et al.*, 2002), anode material (Chao *et al.*, 2008) and support catalyst (Mukai *et al.*, 2005). This is due to the low cost in drying process compared to the supercritical drying. Besides, the freeze drying is capable in preserved the gel structure during the drying process by prevent the pore shrinkage.

The alternative method in order to substitute phenol was made by using lignin (Çetin and Özmen, 2002; Tejado *et al.*, 2007; Vázquez *et al.*, 1995) to produce organic gel with formaldehyde. Instead of using formaldehyde, aldehyde derivative such as furfural are possible to be applied for gel production in the presence of acid medium (Fink, 2005a). Both lignin and furfural are biomass-based side products of biofuel processes. The use of lignin and furfural in the synthesis of the carbon gel as catalyst is an alternative method for improving the sustainability in bio-fuel industry. Lignin-furfural mixture can be classified as furan resin that is synthesized via polycondensation reaction in the presence of acid catalyst. The synthesized furan resin resulting in linear oligomers through the furan rings linkage by methylene and methylene-ether bridges (Fink, 2005b). Lignin itself has linked with monomers in their structures and the linkage with furfural produced more complex polymeric structures. In addition, the direct liquefied product of biomass which contains lignin that can be used as feedstock for gels synthesis.

As an approach for gel derivative from the biomass, the liquefaction process is conducted to dissolve high phenolic compound from biomass precursor. Previously, it was found that the liquefaction can be applied at a moderate temperature by using phenol as a solvent with an acid catalyst in order to produce phenolated lignin which is used in resin synthesis with formaldehyde (Ahmadzadeh *et al.*, 2009; Alma and Basturk, 2006; Lin *et al.*, 2004). Since phenol is a highly toxic chemical, other solvents have been applied in liquefaction, such as ionic liquids

(ILs). ILs show excellent solubility in terms of dissolving biomass. 1-butyl-3-methylimidazole hydrogen sulfate ([BMIM][HSO₄]) is one of the ILs that has been used for the extraction of lignin (Brandt *et al.*, 2011; da Costa Lopes *et al.*, 2013).

The different feedstocks are used in gel synthesis to produce a different type of gel structure. There is very limited study on resin or gel synthesis from ILs. Guo *et al.* (2015) has used the liquefied wood powder in ionic liquid mixture for resin synthesis by blending with phenol and formaldehyde. Thus, the finding was showed the IL has potential in resin synthesis. This progress becomes an alternative way to synthesized resin from mixture of IL biomass-derived compound. The resin is potentially applied for the carbon gel. The production of the carbon gel by using different feedstock and reaction condition used might influence the properties and structure of the carbon gel produce.

In the catalytic process, the synthesis of bio-fuel becomes attention to many researches in the world. Producing bio-fuel based chemical products from derivation of renewable sources such as biomass is an alternative technique to replace petroleum resources due to the depletion of fossil fuel. Levulinic acid is one of the organic acids that show high potential to be derived from lignocellulosic biomass. Levulinic acid is suitable for fuel additive derivation such as ethyl levulinate via esterification with ethanol. The synthesized ethyl levulinate might be used as an oxygenate additive in fuels (Pasquale *et al.*, 2012) and diesel miscible biofuel (up to 5 wt.%) (Nandiwale *et al.*, 2013). It is functioning as fuel additive in order to improve the engine performance, fuel handling and stability, and fuel quality which is help to reduce the production of carbon monoxide. Besides, the ethyl levulinate also can be used as flavoring agent and precursor for production of γ -valerolactone (GVL) (Maldonado *et al.*, 2012b).

The catalytic process requires good performance of catalyst which has good chemical properties and stability. The application of the carbon cryogel as heterogeneous catalyst in the esterification reaction becomes an alternative method in

substituted the usage of homogeneous acid catalyst. The derivative of carbon cryogel from biomass is an approach in tailoring good properties of the carbon-based catalyst. As comparison with carbon-based catalyst from direct carbonization of biomass and their modification, the carbon cryogel derived from biomass shows more advantages in their properties and stability. This is due to the chemical linkage in the carbon cryogel structure during the gel synthesis. The drying and thermal heating process in carbon cryogel preparation is helpful in improved the surface properties.

1.2 Problem Statement

Every year, lignocellulosic biomass generates high production of waste. Nowadays, the biomass is applied for fuel and chemical production due to high potential of producing bio-fuel, bio-gas and chemicals. However, in biomass and biofuel industry, the reaction process still produces byproduct which becomes an unused chemical for industries due to less functioning application. Therefore, in order to reduce waste and byproduct from industries, the use of these abundant are required in order to generate beneficial material as well as retain sustainability. Organic catalyst, especially derivative from lignocellulosic biomass, is currently being developed for application in reaction engineering. The organic catalyst is referred to carbon-based catalyst which is potentially derived from biomass such as activated carbon and carbon gel.

In carbon gel synthesis, phenol has been commonly used with formaldehyde to produce gels (Mukai *et al.*, 2005; Poljanšek and Krajnc, 2005; Scherdel and Reichenauer, 2009). However, the use of chemical compound such as phenol and formaldehyde are hazardous and give bad impact to human health. Instead of using phenol and formaldehyde, gels could be synthesized by using phenol and formaldehyde derivatives. The synthesis of organic gels via phenol and aldehyde

derivatives compounds might give different properties and reactivity to the organic gel compound. Lignin as the byproduct from the biomass conversion is potentially derives the organic gel for preparation of carbon gel. Previously, lignin (Çetin and Özmen, 2002; Tejado *et al.*, 2007; Vázquez *et al.*, 1995), tannin (Grishechko *et al.*, 2013b; Szczurek *et al.*, 2011), and resorcinol (Babić *et al.*, 2004; Czakkel *et al.*, 2005; Tamon *et al.*, 1997) have been used to produce organic gels as another alternative to substitute and reduce phenol usage. On the other hand, formaldehyde derivatives such as paraformaldehyde, acetaldehyde, propionaldehyde, butyraldehyde, glyoxal, trioxane, furfural, and furfurool have been tested to produce phenolic resins (Fink, 2005a). For instance, substitution of phenol and formaldehyde derivatives with tannin and furfural (Kraiwattanawong *et al.*, 2007) and phenolic polymer and furfural (Pekala *et al.*, 1995) have produced organic gels.

In Malaysia, Oil palm frond (OPF) is one of the largest productions of palm oil wastes in palm oil plantation after empty fruit bunch. Many efforts have been done in order to reduce the capacity of OPF. For example, preparation of activated carbon from OPF for bentazon adsorption from aqueous solutions (Salman and Hameed, 2010), glucose recovery using OPF via pretreatment by hot compressed water (Goh *et al.*, 2010) and pulp production from OPF (Wanrosli *et al.*, 2007). This effort might help to reduce the remaining waste materials by converting the waste into beneficial products. The biomass conversion through the liquefaction process for carbon cryogel production is one of the alternatives to produce useful material. The liquefied product with high content of lignin are consists of phenol derivative which could be used to substitute phenol into gel synthesis.

Over the last decade, the derivative product from biomass through the liquefaction was explored in the synthesis of resin. However, the synthesis process involves phenol as a solvent for the liquefaction process. Liquefaction process is usually occurred at high temperature in order to produce bio-oil (Akhtar *et al.*, 2010; Tymchyshyn and Xu, 2010). The bio-oil which is rich with phenolic compound is also used in resin synthesis. It was reported that there has an alternative in processing the biomass through liquefaction in phenol at moderate temperatures in

the presence of an acid catalyst to produce phenolated lignin (Ahmadzadeh *et al.*, 2009; Alma and Basturk, 2006; Lin *et al.*, 2004). The phenolated lignin also has been used in gel synthesis with formaldehyde.

Another alternative is used in this study by applied ionic liquid as a solvent for the liquefaction. The ionic liquid shows high potential in liquefy the biomass due to the excellent solubility for dissolving biomass. Although the ionic liquid is good in dissolving the biomass, nevertheless, the potential of using ionic liquid in gel synthesis is still unclear. Though, there is a study that has using the functional ionic liquid with liquefied wood powder mixture for resin production (Guo *et al.*, 2015), however, phenol and formaldehyde still involve in liquefied mixture for resin synthesis. Therefore, the detail study of gel synthesis from ionic liquid should be conducted as an alternative to replace phenol in resin synthesis. It is predicted that, a successful work of gel synthesis from the ionic liquid might open a different pathway in gel derivative by using ionic liquid with biomass mixture. Therefore, the gel can be used in preparation carbon gel. The chemical properties of ionic liquid as a solvent and also pseudo homogeneous catalyst can influence the properties of carbon cryogel production. The gel synthesis and carbon production from the ionic salt is a good alternative in liquid sample conversion into solid structure which it can be used in another application. The synthesis of the carbon cryogel from the ionic liquid and their mixture with the biomass-derivative product is studied toward the application as acid catalyst.

High production of biodiesel requires an additive in order to improve their quality and performance. The esterification reaction of levulinic acid is carried out in the presence of acid catalyst to produce ethyl levulinate which can be used as additive. However, the use of homogeneous acid catalyst shows some drawbacks although high yield of product is achieved. Therefore, the application of heterogeneous catalyst is required to improve the synthesis of ethyl levulinate. Fernandes *et al.* (2012) has mentioned that the heterogeneous catalyst is required for easy catalyst separation and can be reused several times, instead of using mineral acid that is corrosive to the equipment and need further neutralization process.

Therefore, appropriate heterogeneous catalyst is required during the reaction in order to overcome the problem in ethyl levulinate synthesis. High stability, surface area and acidity of the carbon cryogel catalyst are useful to solve this problem.

Many catalysts have been developed and carbon-based catalyst shows the potential to be applied as the heterogeneous organic catalyst. High acidity and surface area presented by carbon cryogel shows the advantage to be used as a solid acid catalyst for the esterification reaction in synthesizing a fuel additive. Besides, the carbon cryogel is possibly derived from a low cost biomass feedstock give benefit towards the production. Therefore, the carbon cryogel was used as an alternative catalyst instead of using non-organic catalyst in the esterification reaction.

1.3 Research Hypotheses

The carbon cryogel is potentially derives by using phenolic compound such as the lignin. The reactivity of the lignin could be increased by conduct the reaction with furfural in the presence of concentrated acid medium. The lignin and furfural is possibly linked through the electrophilic substitution of lignin phenylpropanoid with the carbonyl group of furfural as explained by Dongre *et al.* (2015). This linkage mechanism is related to the idea of gel production from [BMIM][HSO₄] ionic liquid. The electrophilic substitution of the imidazole structure of the ionic liquid with the carbonyl group of the furfural is possibly occurs to obtain the linkage between both chemical. The study of gel synthesis from ionic liquid is conducted as an initial step for the preparation of the biomass-derived carbon cryogel. This is because the ionic liquid will be applied with liquefied oil palm frond as a mixture for production of the carbon cryogel.

Carbon cryogel production is depends on the gel synthesis and preparation method. In previous study, the application of solvent exchange with *t*-butanol was used to prevent the pore shrinkage of the gel structure. However, the usage of *t*-butanol can be avoiding as the production of monolith carbon is not required. The synthesis and drying process should be controlled to produce carbon cryogel of different shapes and sizes for various applications. There are some factors might influence the surface area of carbon cryogel which are feedstock ratio, amount of water and acid loading. Besides, the heating condition in preparation of carbon cryogel also can affect their surface area.

All the gel production is from lignin, ionic liquid and the liquefied OPF-ionic liquid (LOPF-IL). There are connected via cross-linking network. In their structure, the chemicals were linkage through neither dimethyl-ether nor methylene bridges. The dried gel (cryogel) will be formed after freeze drying process and obtained the carbon after the heating process at high temperature. The carbon cryogel will produce large surface area and high acidity with good thermal stability. Thus, the carbon cryogel produce can be utilized as acid catalyst in the esterification reaction of levulinic acid in ethanol.

As for the esterification reaction, all the carbon cryogel consists of Brønsted acid site which is potentially applied as acid catalysts. High surface area and acidity can enhance the levulinic acid esterification in ethanol to produce high yield of ethyl levulinate. The kinetic and thermodynamic study is performed on the levulinic acid conversion to reduce the activation energy in the presence of carbon cryogel and study their reaction behavior.

1.4 Research Objectives

Based on the carbon cryogel production, the synthesis process involves the production of three different types of carbon cryogel catalyst for the study on ethyl levulinate production. The objectives of the research are:

- i. To synthesize and characterize of the carbon cryogel production from commercial lignin, 1-butyl-3-methylimidazole hydrogen sulfate ionic liquid [BMIM][HSO₄], and liquefied oil palm frond-ionic liquid mixture (LOPF-IL).
- ii. To study the effect of parameters on esterification reaction of levulinic acid.
- iii. To perform kinetic and thermodynamic studies of reaction in the presence of carbon cryogel as catalyst.

1.5 Scope of Research

In order to achieve the research objectives, the scopes of research were drawn as follow:

- i. Carbon cryogel was synthesized from commercial lignin and furfural via sol-gel poly-condensation reaction at 90 °C for 30 min followed by drying and thermal treatment. For gel synthesis, the process conditions were

initially investigated at various lignin to furfural ratio (0.77 to 1.43), lignin to water ratio (0.5 to 1.5), and acid concentration (2M to 8M). As the preparation for carbon cryogel, the temperature and time for carbonization (300 to 700 °C; 1 to 5 h), and calcination (300 to 550 °C; 1 to 5 h) processes were studied to determine the optimum condition. The effect of parameters study was observed toward the total surface area and acidity. The carbon cryogel that was produced from lignin and furfural was labelled as CCLF.

- ii. Carbon cryogel also was synthesized from [BMIM][HSO₄] ionic liquid (IL) through the thermal reaction at 100 °C, 1 h followed by drying and thermal treatment. The parameters studies of furfural to ionic liquid ratio (0.75 to 1.50), water to ionic liquid ratio (0.063 to 0.25), acid amount (0.5 to 2.0 mL) and calcination temperature (350 to 500 °C) and time (1 to 2.5 h) were observed on the surface area and acidity of carbon cryogel. The carbon cryogel that was produced from ionic liquid and furfural was labelled as CCIL. The reaction between ionic liquid with furfural was studied on carbon cryogel production as an initial step to produce the carbon cryogel from liquefied oil palm frond (OPF) in ionic liquid mixture.
- iii. As for the liquefaction, the parameters of temperature (110 to 180 °C), time (0.5 to 2.0 h) and IL to OPF ratio (2 to 4) were investigated towards the liquefied OPF yield. After the liquefaction, the mixture of liquefied OPF and ionic liquid were produced and directly utilized in gel synthesis. Therefore, investigation on carbon cryogel from ionic liquid as stated before is important to avoid the problem on carbon cryogel synthesis from liquefied OPF-IL mixture. The same reaction condition of CCIL synthesis was applied to produce carbon cryogel from liquefied OPF-IL mixture. The carbon cryogel produce from liquefied OPF-IL (LOPF-IL) mixture with furfural is known as CCOPF.

- iv. The CCLF, CCIL and CCOPF were characterized using N_2 adsorption and desorption (BET), temperature programmed desorption of ammonia (NH_3 -TPD), thermogravimetric analyzer (TGA), Fourier transform infrared spectroscopy (FTIR), X-ray diffraction (XRD) and field emission scanning electron microscope with energy dispersive X-ray Spectrometry (FESEM-EDX). Through the characterization studies, the physical and chemical properties of carbon cryogel can be explained. Besides, the surface structure of the carbon cryogel also was observed.

- v. The carbon cryogel was applied as acid catalyst in derived ethyl levulinate from the levulinic acid. The catalytic testing and parameters studies are conducted in the presence of synthesized carbon cryogel. Four reaction parameters were studied which are carbon cryogel loading (CCLF and CCIL – 5 to 35 wt.%, CCOPF – 15 to 35 wt.%), ethanol to levulinic acid molar ratio (5 to 30), reaction temperature (CCLF – 78 to 170 °C, CCIL – 78 to 200 °C) and reaction time (CCLF – 1 to 8 h, CCIL and CCOPF – 1 to 6 h). The condition was selected based on the response of ethyl levulinate yield and levulinic acid conversion. All the parameters were studied by CCLF and CCIL in batch reactor system. However, the CCOPF only performed in the reaction with reflux experiment setup at fixed reaction temperature as preliminary study.

- vi. The kinetic and thermodynamic studies were conducted on the reaction in the presence of CCLF and CCIL. The kinetic study was performed using the pseudo homogenous approach in order to determine the reaction rate constant and activation energy. The pseudo-zero, pseudo-first and pseudo-second order kinetic models were performed and compared. The models were validated using the linear plot of the kinetic models and the parity plot of the predicted data and actual data. As for the thermodynamic study, the parameters such as the enthalpy of activation, entropy of the activation and the Gibbs energy of activation were determined.

1.6 Research Significance

This research is utilized carbon cryogel (CCLF, CCIL and CCOPF) as benign catalyst for the ethyl levulinate production from the levulinic acid and ethanol. The production of carbon cryogel as new carbon-based catalyst is applied for the replacement of the homogeneous acid catalyst such as H_2SO_4 in the esterification reaction. High acidity and surface area of carbon cryogel catalyst was produced to enhance the reaction toward the high production of ethyl levulinate. Due to high thermal stability of the carbon cryogel makes their application more useful as catalyst. The optimum parameters on the gel synthesis and carbon preparation can be used in produce the carbon cryogel more efficiently and particularly useful for baseline study by using other feedstocks and for upscaling process. The selected condition of ethyl levulinate synthesis in the presence of carbon cryogel can give information in conducting the reaction with better utilization of resources especially for large scale processes. In addition, the kinetic and thermodynamic parameters obtained from this study can be used to describe the levulinic acid conversion under the influence of different reaction temperatures. Based on the overall results, the carbon cryogel is highly potentially as super acid carbon-based catalyst in derived the ethyl levulinate.

1.7 Research Outline

This thesis is divided into 7 chapters and begins with an introduction as presented in Chapter 1. The introduction is consists the research background, the related problems in the research area, the hypotheses, research objectives and scope, and the significance of this research. As in the Chapter 2, the literatures is describe the previous research works related to the biomass conversion, ionic liquid production, resin and carbon gel studies, and levulinic acid esterification. Next, Chapter 3 elaborates the details on experimental procedures such as the carbon gel

REFERENCES

- Abdullah, A. Z., Salamatinia, B. and Kamaruddin, A. H. (2009). Application of response surface methodology for the optimization of NaOH treatment on oil palm frond towards improvement in the sorption of heavy metals. *Desalination*, 244(1), 227-238.
- Abdullah, S. S. S., Shirai, Y., Ali, A. A. M., Mustapha, M. and Hassan, M. A. (2016). Case study: Preliminary assessment of integrated palm biomass biorefinery for bioethanol production utilizing non-food sugars from oil palm frond petiole. *Energy Conversion and Management*, 108, 233-242.
- Ahmadzadeh, A., Zakaria, S. and Rashid, R. (2009). Liquefaction of oil palm empty fruit bunch (EFB) into phenol and characterization of phenolated EFB resin. *Industrial Crops and Products*, 30(1), 54-58.
- Akhtar, J., Kuang, S. K. and Amin, N. S. (2010). Liquefaction of empty palm fruit bunch (EPFB) in alkaline hot compressed water. *Renewable Energy*, 35(6), 1220-1227.
- Al-Omair, M. and El-Sharkawy, E. (2007). Removal of heavy metals via adsorption on activated carbon synthesized from solid wastes. *Environmental technology*, 28(4), 443-451.
- Ali, A. and Sarani, Z. (2009). Preparation of novolak resin by liquefaction of oil palm empty fruit bunches (EFB) and characterization of EFB residue. *Polymer-plastics technology and engineering (Softcover ed)*, 48(1-3), 10-16.
- Alma, M. H. and Basturk, M. A. (2006). Liquefaction of grapevine cane (*Vitis Vinisera* L.) waste and its application to phenol–formaldehyde type adhesive. *Industrial Crops and Products*, 24(2), 171-176.

- Alsalmeh, A., Kozhevnikova, E. F. and Kozhevnikov, I. V. (2008). Heteropoly acids as catalysts for liquid-phase esterification and transesterification. *Applied Catalysis A: General*, 349(1–2), 170-176.
- Amen-Chen, C., Pakdel, H. and Roy, C. (2001). Production of monomeric phenols by thermochemical conversion of biomass: A review. *Bioresource Technology*, 79(3), 277-299.
- Babić, B., Kaluđerović, B., Vračar, L. and Krstajić, N. (2004). Characterization of carbon cryogel synthesized by sol–gel polycondensation and freeze-drying. *Carbon*, 42(12–13), 2617-2624.
- Badday, A. S., Abdullah, A. Z. and Lee, K.-T. (2014). Transesterification of crude Jatropha oil by activated carbon-supported heteropolyacid catalyst in an ultrasound-assisted reactor system. *Renewable Energy*, 62, 10-17.
- Badgajar, K. C. and Bhanage, B. M. (2015). Thermo-chemical energy assessment for production of energy-rich fuel additive compounds by using levulinic acid and immobilized lipase. *Fuel Processing Technology*, 138, 139-146.
- Balcerowiak, W., Hetper, J., Kaładkowski, B. and Gryta, M. (1998). A new approach to the determination of the heat of phenolic resol synthesis. *Thermochimica Acta*, 320(1–2), 209-214.
- Baroutian, S., Aroua, M. K., Raman, A. A. A. and Sulaiman, N. M. N. (2010). Potassium hydroxide catalyst supported on palm shell activated carbon for transesterification of palm oil. *Fuel Processing Technology*, 91(11), 1378-1385.
- Baroutian, S., Aroua, M. K., Raman, A. A. A. and Sulaiman, N. M. N. (2011). A packed bed membrane reactor for production of biodiesel using activated carbon supported catalyst. *Bioresource Technology*, 102(2), 1095-1102.
- Bedard, J., Chiang, H. and Bhan, A. (2012). Kinetics and mechanism of acetic acid esterification with ethanol on zeolites. *Journal of Catalysis*, 290, 210-219.
- Bermúdez, J. M., Arenillas, A. and Menéndez, J. A. (2011). Syngas from CO₂ reforming of coke oven gas: Synergetic effect of activated carbon/Ni– γ -Al₂O₃ catalyst. *International Journal of Hydrogen Energy*, 36(21), 13361-13368.
- Boey, P.-L., Ganesan, S., Lim, S.-X., Lim, S.-L., Maniam, G. P. and Khairuddean, M. (2011). Utilization of BA (boiler ash) as catalyst for transesterification of palm olein. *Energy*, 36(10), 5791-5796.

- Borsato, D., Galvan, D., Pereira, J. L., Orives, J. R., Angilelli, K. G. and Coppo, R. L. (2014). Kinetic and thermodynamic parameters of biodiesel oxidation with synthetic antioxidants: simplex centroid mixture design. *Journal of the Brazilian Chemical Society*, 25(11), 1984-1992.
- Brandt, A., Hallett, J. P., Leak, D. J., Murphy, R. J. and Welton, T. (2010). The effect of the ionic liquid anion in the pretreatment of pine wood chips. *Green Chemistry*, 12(4), 672-679.
- Brandt, A., Ray, M. J., To, T. Q., Leak, D. J., Murphy, R. J. and Welton, T. (2011). Ionic liquid pretreatment of lignocellulosic biomass with ionic liquid–water mixtures. *Green Chemistry*, 13(9), 2489-2499.
- Brown, L. and Watson, D. (1959). Curing phenol-furfural resins. *Industrial & Engineering Chemistry*, 51(5), 683-684.
- Brown, L. H. (1952). Resin Forming Reactions of Furfural and Phenol. *Industrial & Engineering Chemistry*, 44(11), 2673-2675.
- Bu, Q., Lei, H., Wang, L., Wei, Y., Zhu, L., Liu, Y., Liang, J. and Tang, J. (2013). Renewable phenols production by catalytic microwave pyrolysis of Douglas fir sawdust pellets with activated carbon catalysts. *Bioresource Technology*, 142, 546-552.
- Buasri, A., Chaiyut, N. and Nakweang, C. (2011). Preparing activated carbon from palm shell for biodiesel fuel production. *Chiang Mai J. Sci.*, 38 (4), 572-578.
- Casas, A., Ramos, M. J., Rodríguez, J. F. and Pérez, Á. (2013). Tin compounds as Lewis acid catalysts for esterification and transesterification of acid vegetable oils. *Fuel Processing Technology*, 106, 321-325.
- Çetin, N. S. and Özmen, N. (2002). Use of organosolv lignin in phenol–formaldehyde resins for particleboard production: i. organosolv lignin modified resins. *International Journal of Adhesion and Adhesives*, 22(6), 477-480.
- Chakar, F. S. and Ragauskas, A. J. (2004). Review of current and future softwood kraft lignin process chemistry. *Industrial Crops and Products*, 20(2), 131-141.
- Chao, Y.-J., Yuan, X. and Ma, Z.-F. (2008). Preparation and characterization of carbon cryogel (CC) and CC–SiO composite as anode material for lithium-ion battery. *Electrochimica Acta*, 53(9), 3468-3473.

- Chen, F. and Li, J. (2010). Synthesis and structural characteristics of organic aerogels with different content of lignin. *Advanced Materials Research*, 113, 1837-1840.
- Chen, G. and Fang, B. (2011). Preparation of solid acid catalyst from glucose–starch mixture for biodiesel production. *Bioresource Technology*, 102(3), 2635-2640.
- Chen, K.-T., Wang, J.-X., Dai, Y.-M., Wang, P.-H., Liou, C.-Y., Nien, C.-W., Wu, J.-S. and Chen, C.-C. (2013). Rice husk ash as a catalyst precursor for biodiesel production. *Journal of the Taiwan Institute of Chemical Engineers*, 44(4), 622-629.
- Chin, L. H., Abdullah, A. Z. and Hameed, B. H. (2012). Sugar cane bagasse as solid catalyst for synthesis of methyl esters from palm fatty acid distillate. *Chemical Engineering Journal*, 183(0), 104-107.
- Cirujano, F. G., Corma, A. and Llabrés i Xamena, F. X. (2015). Conversion of levulinic acid into chemicals: Synthesis of biomass derived levulinate esters over Zr-containing MOFs. *Chemical Engineering Science*, 124, 52-60.
- Czakkel, O., Marthi, K., Geissler, E. and László, K. (2005). Influence of drying on the morphology of resorcinol–formaldehyde-based carbon gels. *Microporous and Mesoporous Materials*, 86(1–3), 124-133.
- da Costa Lopes, A. M., João, K. G., Morais, A. R. C., Bogel-Lukasik, E. and Bogel-Lukasik, R. (2013). Ionic liquids as a tool for lignocellulosic biomass fractionation. *Sustainable Chemical Processes*, 1(1), 3.
- Dawodu, F. A., Ayodele, O., Xin, J., Zhang, S. and Yan, D. (2014). Effective conversion of non-edible oil with high free fatty acid into biodiesel by sulphonated carbon catalyst. *Applied Energy*, 114, 819-826.
- Dehkhoda, A. M. and Ellis, N. (2013). Biochar-based catalyst for simultaneous reactions of esterification and transesterification. *Catalysis Today*, 207, 86-92.
- Demirbaş, A. (2001). Biomass resource facilities and biomass conversion processing for fuels and chemicals. *Energy Conversion and Management*, 42(11), 1357-1378.
- Démolis, A., Essayem, N. and Rataboul, F. (2014). Synthesis and applications of alkyl levulinates. *ACS Sustainable Chemistry & Engineering*, 2(6), 1338-1352.

- Dharaskar, S. A., Wasewar, K. L., Varma, M. N., Shende, D. Z. and Yoo, C. (2016). Synthesis, characterization and application of 1-butyl-3-methylimidazolium tetrafluoroborate for extractive desulfurization of liquid fuel. *Arabian Journal of Chemistry*, 9(4), 578-587.
- Dharne, S. and Bokade, V. V. (2011). Esterification of levulinic acid to n-butyl levulinate over heteropolyacid supported on acid-treated clay. *Journal of Natural Gas Chemistry*, 20(1), 18-24.
- Díaz, J. A., de la Osa, A. R., Sánchez, P., Romero, A. and Valverde, J. L. (2014). Influence of CO₂ co-feeding on Fischer–Tropsch fuels production over carbon nanofibers supported cobalt catalyst. *Catalysis Communications*, 44, 57-61.
- Dilaeleyana, A. B. S., Norzita, N., Nor Aishah, S. A. and Haw, K. E. (2012). Synthesis and characterization of renewable carbon cryogel beads from empty fruit bunch. *International Journal*, 3(2).
- Doherty, T. V., Mora-Pale, M., Foley, S. E., Linhardt, R. J. and Dordick, J. S. (2010). Ionic liquid solvent properties as predictors of lignocellulose pretreatment efficacy. *Green Chemistry*, 12(11), 1967-1975.
- Dongre, P., Driscoll, M., Amidon, T. and Bujanovic, B. (2015). Lignin-furfural based adhesives. *Energies*, 8(8), 7897-7914.
- Effendi, A., Gerhauser, H. and Bridgwater, A. V. (2008). Production of renewable phenolic resins by thermochemical conversion of biomass: A review. *Renewable and Sustainable Energy Reviews*, 12(8), 2092-2116.
- Evans, M. G. and Polanyi, M. (1935). Some applications of the transition state method to the calculation of reaction velocities, especially in solution. *Transactions of the Faraday Society*, 31, 875-894.
- Ezebor, F., Khairuddean, M., Abdullah, A. Z. and Boey, P. L. (2014). Esterification of oily-FFA and transesterification of high FFA waste oils using novel palm trunk and bagasse-derived catalysts. *Energy Conversion and Management*, 88, 1143-1150.
- Fauzi, A. H. M. and Amin, N. A. S. (2012). An overview of ionic liquids as solvents in biodiesel synthesis. *Renewable and Sustainable Energy Reviews*, 16, 5770-5786.
- Fernandes, D. R., Rocha, A. S., Mai, E. F., Mota, C. J. A. and Teixeira da Silva, V. (2012). Levulinic acid esterification with ethanol to ethyl levulinate

- production over solid acid catalysts. *Applied Catalysis A: General*, 425–426, 199-204.
- Fidalgo, B., Muradov, N. and Menéndez, J. A. (2012). Effect of H₂S on carbon-catalyzed methane decomposition and CO₂ reforming reactions. *International Journal of Hydrogen Energy*, 37(19), 14187-14194.
- Fink, J. K. (2005a). 4 - Phenol/formaldehyde resins. *Reactive Polymers Fundamentals and Applications* (pp. 241-281). Norwich, NY: William Andrew Publishing.
- Fink, J. K. (2005b). 7 - Furan resins. *Reactive Polymers Fundamentals and Applications* (pp. 307-320). Norwich, NY: William Andrew Publishing.
- Fu, X., Li, D., Chen, J., Zhang, Y., Huang, W., Zhu, Y., Yang, J. and Zhang, C. (2013). A microalgae residue based carbon solid acid catalyst for biodiesel production. *Bioresource Technology*, 146, 767-770.
- Gírio, F. M., Fonseca, C., Carvalheiro, F., Duarte, L. C., Marques, S. and Bogel-Lukasik, R. (2010). Hemicelluloses for fuel ethanol: A review. *Bioresource Technology*, 101(13), 4775-4800.
- Girisuta, B., Janssen, L. P. B. M. and Heeres, H. J. (2006). Green Chemicals: A kinetic study on the conversion of glucose to levulinic acid. *Chemical Engineering Research and Design*, 84(5), 339-349.
- Goh, C. S., Lee, K. T. and Bhatia, S. (2010). Hot compressed water pretreatment of oil palm fronds to enhance glucose recovery for production of second generation bio-ethanol. *Bioresource Technology*, 101(19), 7362-7367.
- Gombotz, K., Parette, R., Austic, G., Kannan, D. and Matson, J. V. (2012). MnO and TiO solid catalysts with low-grade feedstocks for biodiesel production. *Fuel*, 92(1), 9-15.
- Grishechko, L. I., Amaral-Labat, G., Szczurek, A., Fierro, V., Kuznetsov, B. N. and Celzard, A. (2013a). Lignin–phenol–formaldehyde aerogels and cryogels. *Microporous and Mesoporous Materials*, 168, 19-29.
- Grishechko, L. I., Amaral-Labat, G., Szczurek, A., Fierro, V., Kuznetsov, B. N., Pizzi, A. and Celzard, A. (2013b). New tannin–lignin aerogels. *Industrial Crops and Products*, 41, 347-355.
- Guo, F., Xiu, Z.-L. and Liang, Z.-X. (2012). Synthesis of biodiesel from acidified soybean soapstock using a lignin-derived carbonaceous catalyst. *Applied Energy*, 98, 47-52.

- Guo, L.-y., Zhang, B., Wang, Z.-m., Ma, X.-y. and Huang, P.-c. (2015). Preparation of phenolic resin composites with functional ionic liquids and their liquefaction product of wood powder. *Acta Polymerica Sinica*, (5), 556-563.
- Han, W., Kennedy, E. M., Liu, H., Li, Y., Adesina, A. A., Mackie, J. C. and Dlugogorski, B. Z. (2010). Catalytic pyrolysis of CHF_3 over activated carbon and activated carbon supported potassium catalyst. *Journal of Fluorine Chemistry*, 131(6), 698-703.
- Hara, M. (2010). Biodiesel production by amorphous carbon bearing SO_3H , COOH and phenolic OH groups, a solid Brønsted acid catalyst. *Topics in Catalysis*, 53(11-12), 805-810.
- Hendriks, A. T. W. M. and Zeeman, G. (2009). Pretreatments to enhance the digestibility of lignocellulosic biomass. *Bioresource Technology*, 100(1), 10-18.
- Hidayat, A., Rochmadi, Wijaya, K., Nurdiawati, A., Kurniawan, W., Hinode, H., Yoshikawa, K. and Budiman, A. (2015). Esterification of palm fatty acid distillate with high amount of free fatty acids using coconut shell char based catalyst. *Energy Procedia*, 75, 969-974.
- Hoo, P. and Abdullah, A. Z. (2015). Kinetics modeling and mechanism study for selective esterification of glycerol with lauric acid using 12-tungstophosphoric acid post-impregnated SBA-15. *Industrial & Engineering Chemistry Research*, 54(32), 7852-7858.
- Hu, X., Song, Y., Wu, L., Gholizadeh, M. and Li, C.-Z. (2013). One-pot synthesis of levulinic acid/ester from C5 carbohydrates in a methanol medium. *ACS Sustainable Chemistry & Engineering*, 1(12), 1593-1599.
- Ibrahim, M. N. M., Zakaria, N., Sipaut, C. S., Sulaiman, O. and Hashim, R. (2011). Chemical and thermal properties of lignins from oil palm biomass as a substitute for phenol in a phenol formaldehyde resin production. *Carbohydrate polymers*, 86(1), 112-119.
- Irmak, S., Kurtuluş, M., Hasanoglu, A. and Erbatur, O. (2013). Gasification efficiencies of cellulose, hemicellulose and lignin fractions of biomass in aqueous media by using Pt on activated carbon catalyst. *Biomass and Bioenergy*, 49, 102-108.

- Jingfa, D., Guirong, Z., Shuzhong, D., Haishui, P. and Huaiming, W. (1988). Acidic properties of ZSM-5 zeolite and conversion of ethanol to diethyl ether. *Applied catalysis*, 41, 13-22.
- Job, N., Théry, A., Pirard, R., Marien, J., Kocon, L., Rouzaud, J.-N., Béguin, F. and Pirard, J.-P. (2005). Carbon aerogels, cryogels and xerogels: influence of the drying method on the textural properties of porous carbon materials. *Carbon*, 43(12), 2481-2494.
- Kadirvelu, K., Senthilkumar, P., Thamaraiselvi, K. and Subburam, V. (2002). Activated carbon prepared from biomass as adsorbent: elimination of ni(ii) from aqueous solution. *Bioresource Technology*, 81(1), 87-90.
- Karre, A. V., Kababji, A., Kugler, E. L. and Dadyburjor, D. B. (2012). Effect of addition of zeolite to iron-based activated-carbon-supported catalyst for Fischer–Tropsch synthesis in separate beds and mixed beds. *Catalysis Today*, 198(1), 280-288.
- Kastnera, J., R., Millera, J., Gellera, D. P., Locklinb, J., Keithc, L. H. and Johnsonc, T. (2012). Catalytic esterification of fatty acids using solid acid catalysts generated from biochar and activated carbon. *Catalysis Today*, 190, 122-132.
- Keskin, S., Kayrak-Talay, D., Akman, U. and Hortaçsu, Ö. (2007). A review of ionic liquids towards supercritical fluid applications. *The Journal of Supercritical Fluids*, 43(1), 150-180.
- Khder, A. S., El-Sharkawy, E. A., El-Hakam, S. A. and Ahmed, A. I. (2008). Surface characterization and catalytic activity of sulfated tin oxide catalyst. *Catalysis Communications*, 9(5), 769-777.
- Kong, X., Wu, S., Li, X. and Liu, J. (2016). Efficient conversion of levulinic acid to ethyl levulinate over a silicotungstic-acid-modified commercially silica-gel sphere catalyst. *Energy & Fuels*, 30(8), 6500-6504.
- Konwar, L. J., Das, R., Thakur, A. J., Salminen, E., Mäki-Arvela, P., Kumar, N., Mikkola, J.-P. and Deka, D. (2014). Biodiesel production from acid oils using sulfonated carbon catalyst derived from oil-cake waste. *Journal of Molecular Catalysis A: Chemical*, 388, 167-176.
- Kraiwattanawong, K., Mukai, S. R., Tamon, H. and Lothongkum, A. W. (2007). Preparation of carbon cryogels from wattle tannin and furfural. *Microporous and Mesoporous Materials*, 98(1–3), 258-266.

- Kuwahara, Y., Fujitani, T. and Yamashita, H. (2014a). Esterification of levulinic acid with ethanol over sulfated mesoporous zirconosilicates: Influences of the preparation conditions on the structural properties and catalytic performances. *Catalysis Today*, 237, 18-28.
- Kuwahara, Y., Kaburagi, W., Nemoto, K. and Fujitani, T. (2014b). Esterification of levulinic acid with ethanol over sulfated Si-doped ZrO₂ solid acid catalyst: Study of the structure–activity relationships. *Applied Catalysis A: General*, 476, 186-196.
- Labrecque, R. and Lavoie, J.-M. (2011). Dry reforming of methane with CO₂ on an electron-activated iron catalytic bed. *Bioresource Technology*, 102(24), 11244-11248.
- Li, M., Chen, D. and Zhu, X. (2013a). Preparation of solid acid catalyst from rice husk char and its catalytic performance in esterification. *Chinese Journal of Catalysis*, 34, 1674-1682.
- Li, M., Zheng, Y., Chen, Y. and Zhu, X. (2014). Biodiesel production from waste cooking oil using a heterogeneous catalyst from pyrolyzed rice husk. *Bioresource Technology*, 154, 345-348.
- Li, X.-f., Zuo, Y., Zhang, Y., Fu, Y. and Guo, Q.-x. (2013b). In situ preparation of K₂CO₃ supported Kraft lignin activated carbon as solid base catalyst for biodiesel production. *Fuel*, 113, 435-442.
- Lin, L., Yao, Y., Yoshioka, M. and Shiraishi, N. (2004). Liquefaction mechanism of cellulose in the presence of phenol under acid catalysis. *Carbohydrate Polymers*, 57(2), 123-129.
- Liu, T., Li, Z., Li, W., Shi, C. and Wang, Y. (2013). Preparation and characterization of biomass carbon-based solid acid catalyst for the esterification of oleic acid with methanol. *Bioresource Technology*, 133, 618-621.
- Long, D.-H., Zhang, J., Yang, J.-H., Hu, Z.-J., Li, T.-Q., Cheng, G., Zhang, R. and Ling, L.-C. (2008). Preparation and microstructure control of carbon aerogels produced using m-cresol mediated sol-gel polymerization of phenol and furfural. *New Carbon Materials*, 23(2), 165-170.
- Lou, W.-Y., Zong, M.-H. and Duan, Z.-Q. (2008). Efficient production of biodiesel from high free fatty acid-containing waste oils using various carbohydrate-derived solid acid catalysts. *Bioresource Technology*, 99(18), 8752-8758.

- Luo, J., Genco, J., Cole, B. J. W. and Fort, R. C. (2011). Lignin recovered from the near-neutral hemicellulose extraction process as a precursor for carbon fiber. *BioResources*, 6(4).
- Maheria, K., Kozinski, J. and Dalai, A. (2013). Esterification of levulinic acid to n-butyl levulinate over various acidic zeolites. *Catalysis Letters*, 143(11), 1220-1225.
- Maldas, D. and Shiraishi, N. (1997). Liquefaction of biomass in the presence of phenol and H₂O using alkalies and salts as the catalyst. *Biomass and Bioenergy*, 12(4), 273-279.
- Maldonado, G. M. G., Assary, R. S., Dumesic, J. and Curtiss, L. A. (2012a). Experimental and theoretical studies of the acid-catalyzed conversion of furfuryl alcohol to levulinic acid in aqueous solution. *Energy & Environmental Science*, 5(5), 6981-6989.
- Maldonado, G. M. G., Assary, R. S., Dumesic, J. A. and Curtiss, L. A. (2012b). Acid-catalyzed conversion of furfuryl alcohol to ethyl levulinate in liquid ethanol. *Energy & Environmental Science*, 5(10), 8990-8997.
- Malik, P. (2004). Dye removal from wastewater using activated carbon developed from sawdust: adsorption equilibrium and kinetics. *Journal of Hazardous Materials*, 113(1), 81-88.
- Man, Z., Elsheikh, Y. A., Bustam, M. A., Yusup, S., Mutalib, M. I. A. and Muhammad, N. (2013). A Brønsted ammonium ionic liquid-KOH two-stage catalyst for biodiesel synthesis from crude palm oil. *Industrial Crops and Products*, 41, 144-149.
- Mar, W. W. and Somsook, E. (2012). Sulfonic-functionalized carbon catalyst for esterification of high free fatty acid. *Procedia Engineering*, 32, 212-218.
- MARDI. (2015). Animal Feed form Oil Palm Frond Retrieved 9-7-2015, 2015
- Martínez, A., Úsuga, L. F., Gil, C., Castro, C. D. and Quintana, G. C. (2016). Thermal study of gels obtained from resol type phenolic resins modified with lignin. Proceedings of the 2016 *Macromolecular Symposia*, 7-16.
- Melero, J., Morales, G., Iglesias, J., Paniagua, M., Hernandez, B. and Penedo, S. (2013). Efficient conversion of levulinic acid into alkyl levulinates catalyzed by sulfonic mesostructured silicas. *Applied Catalysis A: General*, 466, 116-122.

- Mellmer, M. A., Gallo, J. M. R., Martin Alonso, D. and Dumesic, J. A. (2015). Selective production of levulinic acid from furfuryl alcohol in THF solvent systems over H-ZSM-5. *ACS Catalysis*, 5(6), 3354-3359.
- Mohan, D., U. Pittman, J. C. and H. Steele, P. (2006). Pyrolysis of wood/biomass for bio-oil: A critical review. *Energy & Fuels* 20(3), 848-889.
- Mohd Yasin, N. H., Fukuzaki, M., Maeda, T., Miyazaki, T., Hakiman Che Maail, C. M., Ariffin, H. and Wood, T. K. (2013). Biohydrogen production from oil palm frond juice and sewage sludge by a metabolically engineered *Escherichia coli* strain. *International Journal of Hydrogen Energy*, 38(25), 10277-10283.
- Moreno, A., Arenillas, A., Calvo, E., Bermúdez, J. and Menéndez, J. (2013). Carbonisation of resorcinol–formaldehyde organic xerogels: effect of temperature, particle size and heating rate on the porosity of carbon xerogels. *Journal of Analytical and Applied Pyrolysis*, 100, 111-116.
- Moubarik, A., Pizzi, A., Allal, A., Charrier, F. and Charrier, B. (2009). cornstarch and tannin in phenol–formaldehyde resins for plywood production. *Industrial Crops and Products*, 30(2), 188-193.
- MPOB. (2015). Economics and industry development division, MPOB Retrieved 19th January, 2017, from www.mpob.gov.my.
- MPOB, M. P. O. B. (2012). Oil palm and the environment Retrieved 29th January, 2013, from www.mpob.gov.my.
- Mukai, S. R., Tamitsuji, C., Nishihara, H. and Tamon, H. (2005). Preparation of mesoporous carbon gels from an inexpensive combination of phenol and formaldehyde. *Carbon*, 43(12), 2628-2630.
- Nakajima, K. and Hara, M. (2012). Amorphous carbon with SO₃H groups as a solid Brønsted acid catalyst. *ACS Catalysis*, 2(7), 1296-1304.
- Nandiwale, K. Y. and Bokade, V. V. (2015a). Environmentally benign catalytic process for esterification of renewable levulinic acid to various alkyl levulinates biodiesel. *Environmental Progress & Sustainable Energy*, 34(3), 795-801.
- Nandiwale, K. Y. and Bokade, V. V. (2015b). Esterification of renewable levulinic acid to n-butyl levulinate over modified H-ZSM-5. *Chemical Engineering & Technology*, 38(2), 246-252.

- Nandiwale, K. Y., Niphadkar, P. S., Deshpande, S. S. and Bokade, V. V. (2014a). Esterification of renewable levulinic acid to ethyl levulinate biodiesel catalyzed by highly active and reusable desilicated H-ZSM-5. *Journal of Chemical Technology and Biotechnology*, 89(10), 1507-1515.
- Nandiwale, K. Y., Sonar, S. K., Niphadkar, P. S., Joshi, P. N., Deshpande, S. S., Patil, V. S. and Bokade, V. V. (2013). Catalytic upgrading of renewable levulinic acid to ethyl levulinate biodiesel using dodecatungstophosphoric acid supported on desilicated H-ZSM-5 as catalyst. *Applied Catalysis A: General*, 460, 90-98.
- Nandiwale, K. Y., Yadava, S. K. and Bokade, V. V. (2014b). Production of octyl levulinate biolubricant over modified H-ZSM-5: Optimization by response surface methodology. *Journal of Energy Chemistry*, 23(4), 535-541.
- Nautiyal, P., Subramanian, K. and Dastidar, M. (2014). Kinetic and thermodynamic studies on biodiesel production from *Spirulina platensis* algae biomass using single stage extraction–transesterification process. *Fuel*, 135, 228-234.
- Neves, P., Lima, S., Pillinger, M., Rocha, S. M., Rocha, J. and Valente, A. A. (2013). Conversion of furfuryl alcohol to ethyl levulinate using porous aluminosilicate acid catalysts. *Catalysis Today*, 218–219, 76-84.
- Okamura, M., Takagaki, A., Toda, M., Kondo, J. N., Domen, K., Tatsumi, T., Hara, M. and Hayashi, S. (2006). Acid-catalyzed reactions on flexible polycyclic aromatic carbon in amorphous carbon. *Chemistry of Materials*, 18(13), 3039-3045.
- Oliveira, B. L. and Teixeira da Silva, V. (2014). Sulfonated carbon nanotubes as catalysts for the conversion of levulinic acid into ethyl levulinate. *Catalysis Today*, 234, 257-263.
- Oliveira, F. B., Gardrat, C., Enjalbal, C., Frollini, E. and Castellan, A. (2008). Phenol–furfural resins to elaborate composites reinforced with sisal fibers—molecular analysis of resin and properties of composites. *Journal of applied polymer science*, 109(4), 2291-2303.
- Olivier-Bourbigou, H., Magna, L. and Morvan, D. (2010). Ionic liquids and catalysis: Recent progress from knowledge to applications. *Applied Catalysis A: General*, 373(1–2), 1-56.
- Ong, L., Kurniawan, A., Suwandi, A., Lin, C., Zhao, X. and Ismadji, S. (2013). Transesterification of leather tanning waste to biodiesel at supercritical

- condition: Kinetics and thermodynamics studies. *The Journal of Supercritical Fluids*, 75, 11-20.
- Panneerselvam, P., Morad, N. and Tan, K. A. (2011). Magnetic nanoparticle (Fe_3O_4) impregnated onto tea waste for the removal of nickel(II) from aqueous solution. *Journal of Hazardous Materials*, 186(1), 160-168.
- Papadopoulou, E. and Chrissafis, K. (2011). Thermal study of phenol–formaldehyde resin modified with cashew nut shell liquid. *Thermochimica Acta*, 512(1–2), 105-109.
- Pasquale, G., Vázquez, P., Romanelli, G. and Baronetti, G. (2012). Catalytic upgrading of levulinic acid to ethyl levulinate using reusable silica-included Wells-Dawson heteropolyacid as catalyst. *Catalysis Communications*, 18, 115-120.
- Patel, A. and Brahmkhatri, V. (2013). Kinetic study of oleic acid esterification over 12-tungstophosphoric acid catalyst anchored to different mesoporous silica supports. *Fuel Processing Technology*, 113, 141-149.
- Patel, A., Brahmkhatri, V. and Singh, N. (2013). Biodiesel production by esterification of free fatty acid over sulfated zirconia. *Renewable Energy*, 51, 227-233.
- Patil, C. R., Niphadkar, P. S., Bokade, V. V. and Joshi, P. N. (2014). Esterification of levulinic acid to ethyl levulinate over bimodal micro–mesoporous H/BEA zeolite derivatives. *Catalysis Communications*, 43, 188-191.
- Patil, P. D. and Deng, S. (2009). Optimization of biodiesel production from edible and non-edible vegetable oils. *Fuel*, 88(7), 1302-1306.
- Pekala, R. W. (1989). Organic Aerogels from the Polycondensation of Resorcinol with Formaldehyde *Journal of material science*, 24, 3221-3227.
- Pekala, R. W., Alviso, C. T., Lu, X., Gross, J. and Fricke, J. (1995). New organic aerogels based upon a phenolic-furfural reaction. *Journal of Non-Crystalline Solids*, 188(1–2), 34-40.
- Peng, L., Lin, L., Zhang, J., Zhuang, J., Zhang, B. and Gong, Y. (2010). Catalytic conversion of cellulose to levulinic acid by metal chlorides. *Molecules*, 15(8), 5258-5272.
- Phung, T. K. and Busca, G. (2015). Diethyl ether cracking and ethanol dehydration: Acid catalysis and reaction paths. *Chemical Engineering Journal*, 272, 92-101.

- Pileidis, F. D., Tabassum, M., Coutts, S. and Titirici, M.-M. (2014). Esterification of levulinic acid into ethyl levulinate catalysed by sulfonated hydrothermal carbons. *Chinese Journal of Catalysis*, 35(6), 929-936.
- Pogliani, L. (2008). Pseudo-zero-order reactions. *Reaction Kinetics and Catalysis Letters*, 93(2), 187-191.
- Poljanšek, I. and Krajnc, M. (2005). Characterization of Phenol-formaldehyde prepolymer resins by in line FT-IR spectroscopy. *Acta Chimica Slovenica*, 52, 238-244.
- Prabhavathi Devi, B. L. A., Vijai Kumar Reddy, T., Vijaya Lakshmi, K. and Prasad, R. B. N. (2014). A green recyclable SO₃H-carbon catalyst derived from glycerol for the production of biodiesel from FFA-containing karanja (*Pongamia glabra*) oil in a single step. *Bioresource Technology*, 153, 370-373.
- Qiao, W., Li, S., Guo, G., Han, S., Ren, S. and Ma, Y. (2015). Synthesis and characterization of phenol-formaldehyde resin using enzymatic hydrolysis lignin. *Journal of Industrial and Engineering Chemistry*, 21, 1417-1422.
- Rackemann, D. W. and Doherty, W. O. (2011). The conversion of lignocellulosics to levulinic acid. *Biofuels, Bioproducts and Biorefining*, 5(2), 198-214.
- Ramli, N. A. S. and Amin, N. A. S. (2014). Catalytic hydrolysis of cellulose and oil palm biomass in ionic liquid to reducing sugar for levulinic acid production. *Fuel Processing Technology*, 128, 490-498.
- Ramli, N. A. S. and Amin, N. A. S. (2016a). Kinetic study of glucose conversion to levulinic acid over Fe/HY zeolite catalyst. *Chemical Engineering Journal*, 283, 150-159.
- Ramli, N. A. S. and Amin, N. A. S. (2016b). Optimization of biomass conversion to levulinic acid in acidic ionic liquid and upgrading of levulinic acid to ethyl levulinate. *BioEnergy Research*, 1-14.
- Rosatella, A. A., Simeonov, S. P., Frade, R. F. and Afonso, C. A. (2011). 5-Hydroxymethylfurfural (HMF) as a building block platform: Biological properties, synthesis and synthetic applications. *Green Chemistry*, 13(4), 754-793.
- Salamatinia, B., Kamaruddin, A. H. and Abdullah, A. Z. (2008). Modeling of the continuous copper and zinc removal by sorption onto sodium hydroxide-

- modified oil palm frond in a fixed-bed column. *Chemical Engineering Journal*, 145(2), 259-266.
- Salman, J. M. and Hameed, B. H. (2010). Effect of preparation conditions of oil palm fronds activated carbon on adsorption of bentazon from aqueous solutions. *Journal of Hazardous Materials*, 175(1-3), 133-137.
- Scherdel, C. and Reichenauer, G. (2009). Carbon xerogels synthesized via phenol-formaldehyde gels. *Microporous and Mesoporous Materials*, 126(1-2), 133-142.
- Sharma, M., Khan, A. A., Puri, S. K. and Tuli, D. K. (2012). Wood ash as a potential heterogeneous catalyst for biodiesel synthesis. *Biomass and Bioenergy*, 41, 94-106.
- Shibata, M., Varman, M., Tono, Y., Miyafuji, H. and Saka, S. (2008). Characterization in chemical composition of the oil palm (*Elaeis guineensis*). *Journal of the Japan Institute of Energy*, 87, 383-388.
- Shu, Q., Zhang, Q., Xu, G., Nawaz, Z., Wang, D. and Wang, J. (2009). Synthesis of biodiesel from cottonseed oil and methanol using a carbon-based solid acid catalyst. *Fuel Processing Technology*, 90(7-8), 1002-1008.
- Sidik, D. A. B., Ngadi, N. and Amin, N. A. S. (2013). Optimization of Lignin Production from Empty Fruit Bunch via Liquefaction with Ionic Liquid. *Bioresource Technology*, 135, 690-696.
- Singare, P. U., Lokhande, R. S. and Madyal, R. S. (2011). Thermal degradation studies of some strongly acidic ca-tion exchange resins. *Open Journal of Physical Chemistry*, 1(2), 45.
- Sismanoglu, T., Ercag, A., Pura, S. and Ercag, E. (2004). Kinetics and isotherms of dazomet adsorption on natural adsorbents. *Journal of the Brazilian Chemical Society*, 15(5), 669-675.
- Song, D., An, S., Lu, B., Guo, Y. and Leng, J. (2015). Arylsulfonic acid functionalized hollow mesoporous carbon spheres for efficient conversion of levulinic acid or furfuryl alcohol to ethyl levulinate. *Applied Catalysis B: Environmental*, 179, 445-457.
- Song, D., An, S., Sun, Y. and Guo, Y. (2016). Efficient conversion of levulinic acid or furfuryl alcohol into alkyl levulinates catalyzed by heteropoly acid and ZrO₂ bifunctionalized organosilica nanotubes. *Journal of Catalysis*, 333, 184-199.

- Steinrück, H.-P. and Wasserscheid, P. (2015). Ionic liquids in catalysis. *Catalysis Letters*, 145(1), 380-397.
- Striūgas, N., Zakarauskas, K., Stravinskas, G. and Grigaitienė, V. (2012). Comparison of steam reforming and partial oxidation of biomass pyrolysis tars over activated carbon derived from waste tire. *Catalysis Today*, 196(1), 67-74.
- Su, F., Ma, L., Song, D., Zhang, X. and Guo, Y. (2013). Design of a highly ordered mesoporous $H_3PW_{12}O_{40}/ZrO_2$ -Si(Ph)Si hybrid catalyst for methyl levulinate synthesis. *Green Chemistry*, 15(4), 885-890.
- Sudhir, N. V. K. A., Berlyn, R. M., Eric, M. S. and Joan, F. B. (2004). High-pressure phase behavior of carbon dioxide with imidazolium-based ionic liquids. *J. Phys. Chem. B*, 108, 20355-20365.
- Sumathi, S., Chai, S. P. and Mohamed, A. R. (2008). Utilization of oil palm as a source of renewable energy in Malaysia. *Renewable and Sustainable Energy Reviews*, 12(9), 2404-2421.
- Sun, N., Rahman, M., Qin, Y., Maxim, M. L., Rodríguez, H. and Rogers, R. D. (2009). Complete dissolution and partial delignification of wood in the ionic liquid 1-ethyl-3-methylimidazolium acetate. *Green Chemistry*, 11(5), 646-655.
- Supandi, M. (2009). *Synthesis and characterization of resin from empty palm fruit bunches*. Bachelor of Engineering (Chemical), Universiti Teknologi Malaysia, Johor Bahru.
- Swatloski, R. P., Spear, S. K., Holbrey, J. D. and Rogers, R. D. (2002). Dissolution of cellulose with ionic liquids. *Journal of the American Chemical Society*, 124(18), 4974-4975.
- Szczurek, A., Amaral-Labat, G., Fierro, V., Pizzi, A. and Celzard, A. (2011). The use of tannin to prepare carbon gels. Part II. Carbon cryogels. *Carbon*, 49(8), 2785-2794.
- Takahara, I., Saito, M., Inaba, M. and Murata, K. (2005). Dehydration of ethanol into ethylene over solid acid catalysts. *Catalysis Letters*, 105(3), 249-252.
- Tamon, H., Ishizaka, H., Mikami, M. and Okazaki, M. (1997). Porous structure of organic and carbon aerogels synthesized by sol-gel polycondensation of resorcinol with formaldehyde. *Carbon*, 35(6), 791-796.

- Tamon, H., Ishizaka, H., Yamamoto, T. and Suzuki, T. (1999). Preparation of mesoporous carbon by freeze drying. *Carbon*, 37(12), 2049-2055.
- Tejado, A., Peña, C., Labidi, J., Echeverria, J. M. and Mondragon, I. (2007). Physico-chemical characterization of lignins from different sources for use in phenol–formaldehyde resin synthesis. *Bioresource Technology*, 98(8), 1655-1663.
- Torr, K. M., Love, K. T., Çetinkol, Ö. P., Donaldson, L. A., George, A., Holmes, B. M. and Simmons, B. A. (2012). The impact of ionic liquid pretreatment on the chemistry and enzymatic digestibility of *Pinus radiata* compression wood. *Green Chemistry*, 14(3), 778-787.
- Trangkaprassith, K. and Chavalparit, O. (2010). Heating value enhancement of fuel pellets from frond of oil palm. *Proceedings of International Conference on Biology, Environment and Chemistry (ICBEC 2010)*.
- Tsubouchi, N., Xu, C. and Ohtsuka, Y. (2003). Carbon crystallization during high-temperature pyrolysis of coals and the enhancement by calcium. *Energy & Fuels*, 17(5), 1119-1125.
- Turunen, M., Alvila, L., Pakkanen, T. T. and Rainio, J. (2003). Modification of phenol–formaldehyde resol resins by lignin, starch, and urea. *Journal of applied polymer science*, 88(2), 582-588.
- Tymchyshyn, M. and Xu, C. (2010). Liquefaction of Bio-mass in Hot-compressed water for the production of phenolic compounds. *Bioresource Technology*, 101(7), 2483-2490.
- Vadery, V., Narayanan, B. N., Ramakrishnan, R. M., Cherikkallinmel, S. K., Sugunan, S., Narayanan, D. P. and Sasidharan, S. (2014). Room temperature production of jatropha biodiesel over coconut husk ash. *Energy*, 70, 588-594.
- Varisli, D., Dogu, T. and Dogu, G. (2007). Ethylene and diethyl-ether production by dehydration reaction of ethanol over different heteropolyacid catalysts. *Chemical Engineering Science*, 62(18), 5349-5352.
- Varkolu, M., Moodley, V., Potwana, F. S. W., Jonnalagadda, S. B. and van Zyl, W. E. (2016). Esterification of levulinic acid with ethanol over bio-glycerol derived carbon–sulfonic-acid. *Reaction Kinetics, Mechanisms and Catalysis*, 1-12.

- Vázquez, G., Antorrena, G., González, J. and Mayor, J. (1995). Lignin-phenol-formaldehyde adhesives for exterior grade plywoods. *Bioresource Technology*, 51(2–3), 187-192.
- Veselá, P., Riikonen, J., Nissinen, T., Lehto, V.-P. and Slovák, V. (2015). Optimisation of thermoporometry measurements to evaluate mesoporous organic and carbon xero-, cryo- and aerogels. *Thermochimica Acta*, 621, 81-89.
- Wan Omar, W. N. N. and Amin, N. A. S. (2016). Multi response optimization of oil palm frond pretreatment by ozonolysis. *Industrial Crops and Products*, 85, 389-402.
- Wang, M., Leitch, M. and Xu, C. (2009a). Synthesis of phenol-formaldehyde resol resins using organosolv pine lignins. *European Polymer Journal*, 45(12), 3380-3388.
- Wang, M., Xu, C. and Leitch, M. (2009b). Liquefaction of cornstalk in hot-compressed phenol-water medium to phenolic feedstock for the synthesis of phenol-formaldehyde resin. *Bioresource Technology*, 100(7), 2305-2307.
- Wang, X., Li, H., Cao, Y. and Tang, Q. (2011). Cellulose extraction from wood chip in an ionic liquid 1-allyl-3-methylimidazolium chloride (AmimCl). *Bioresource Technology*, 102(17), 7959-7965.
- Wanrosli, W. D., Zainuddin, Z., Law, K. N. and Asro, R. (2007). Pulp from oil palm fronds by chemical processes. *Industrial Crops and Products*, 25(1), 89-94.
- Wu, D. and Fu, R. (2006). Synthesis of organic and carbon aerogels from phenol-furfural by two-step polymerization. *Microporous and Mesoporous Materials*, 96(1), 115-120.
- Wu, D., Fu, R., Sun, Z. and Yu, Z. (2005a). Low-density organic and carbon aerogels from the sol-gel polymerization of phenol with formaldehyde. *Journal of Non-Crystalline Solids*, 351(10), 915-921.
- Wu, D., Fu, R. and Yu, Z. (2005b). Organic and carbon aerogels from the NaOH-catalyzed polycondensation of resorcinol-furfural and supercritical drying in ethanol. *Journal of applied polymer science*, 96(4), 1429-1435.
- Wu, D., Fu, R., Zhang, S., Dresselhaus, M. S. and Dresselhaus, G. (2004). The preparation of carbon aerogels based upon the gelation of resorcinol-furfural in isopropanol with organic base catalyst. *Journal of Non-Crystalline Solids*, 336(1), 26-31.

- Wu, H., Mora-Pale, M., Miao, J., Doherty, T. V., Linhardt, R. J. and Dordick, J. S. (2011). Facile pretreatment of lignocellulosic biomass at high loadings in room temperature ionic liquids. *Biotechnology and bioengineering*, 108(12), 2865-2875.
- Xu, E., Sun, J., Zhu, X., Wang, X. and Gao, Z. (2016). Liquefaction of coconut fibers in alkaline hot-compressed water. *Energy Sources, Part A: Recovery, Utilization, and Environmental Effects*, 38(12), 1750-1755.
- Yadav, G. D. and Yadav, A. R. (2014). Synthesis of ethyl levulinate as fuel additives using heterogeneous solid superacidic catalysts: Efficacy and kinetic modeling. *Chemical Engineering Journal*, 243, 556-563.
- Yakari, M. I. (2008). *Oil palm frond (OPF) as an alternative source of pulp & paper production material*. Bachelor of Chemical Engineering, Universiti Malaysia Pahang, Pahang.
- Yamamoto, T., Sugimoto, T., Suzuki, T., Mukai, S. R. and Tamon, H. (2002). Preparation and characterization of carbon cryogel microspheres. *Carbon*, 40(8), 1345-1351.
- Yan, K., Wu, G., Wen, J. and Chen, A. (2013). One-step synthesis of mesoporous $H_4SiW_{12}O_{40}-SiO_2$ catalysts for the production of methyl and ethyl levulinate biodiesel. *Catalysis Communications*, 34, 58-63.
- Yan, L., Cui, Y., Gou, G., Wang, Q., Jiang, M., Zhang, S., Hui, D., Gou, J. and Zhou, Z. (2016). Liquefaction of lignin in hot-compressed water to phenolic feedstock for the synthesis of phenol-formaldehyde resins. *Composites Part B: Engineering*.
- Yang, H., Yan, R., Chen, H., Lee, D. H. and Zheng, C. (2007). Characteristics of hemicellulose, cellulose and lignin pyrolysis. *Fuel*, 86(12-13), 1781-1788.
- Yokoyama, S. and Matsumura, Y. (2008). *The asian biomass handbook: A guide for biomass production and utilization*. S. Yokoyama & Y. Matsumura (Eds.)
- Yusoff, S. (2006). Renewable Energy from palm oil – Innovation on effective utilization of waste. *Journal of Cleaner Production*, 14(1), 87-93.
- Zahari, M. W., Hassan, O. A., Wong, H. and Liang, J. (2003). Utilization of oil palm frond-based diets for beef and dairy production in Malaysia. *Asian Australasian Journal of Animal Sciences*, 16(4), 625-634.

- Zainol, M. M., Amin, N. A. S. and Asmadi, M. (2015). Synthesis and characterization of carbon cryogel microspheres from lignin-furfural mixtures for biodiesel production. *Bioresource Technology*, 190, 44-50.
- Zainol, M. M., Asmadi, M. and Amin, N. A. S. (2014). Impregnation of magnetic particles on oil palm shell activated carbon for removal of heavy metal ions from aqueous solution. *Jurnal Teknologi*, 72(1), 7-11.
- Zaman, M., Khodadi, A. and Mortazavi, Y. (2009). Fischer–Tropsch synthesis over cobalt dispersed on carbon nanotubes-based supports and activated carbon. *Fuel Processing Technology*, 90(10), 1214-1219.
- Zapata-Benabithé, Z., Carrasco-Marín, F., de Vicente, J. and Moreno-Castilla, C. (2013). Carbon xerogel microspheres and monoliths from resorcinol–formaldehyde mixtures with varying dilution ratios: preparation, surface characteristics, and electrochemical double-layer capacitances. *Langmuir*, 29(20), 6166-6173.
- Zhang, W., Ma, Y., Wang, C., Li, S., Zhang, M. and Chu, F. (2013a). Preparation and properties of lignin–phenol–formaldehyde resins based on different biorefinery residues of agricultural biomass. *Industrial Crops and Products*, 43, 326-333.
- Zhang, W., Ma, Y., Xu, Y., Wang, C. and Chu, F. (2013b). Lignocellulosic ethanol residue-based lignin–phenol–formaldehyde resin adhesive. *International Journal of Adhesion and Adhesives*, 40, 11-18.
- Zhang, X., Ma, Q., Cheng, B., Wang, J., Li, J. and Nie, F. (2012). Research on KOH/La-Ba-Al₂O₃ catalysts for biodiesel production via transesterification from microalgae oil. *Journal of Natural Gas Chemistry*, 21(6), 774-779.
- Zhao, G., Hu, L., Sun, Y., Zeng, X. and Lin, L. (2014). Conversion of biomass-derived furfuryl alcohol into ethyl levulinate catalyzed by solid acid in ethanol. *Bioresources*, 9(2), 2634-2644.
- Zhao, S., Xu, G., Chang, J., Chang, C., Bai, J., Fang, S. and Liu, Z. (2015). Direct Production of ethyl levulinate from carbohydrates catalyzed by H-ZSM-5 supported phosphotungstic acid. *Bioresources*, 10(2), 2223-2234.
- Zhao, Y., Yan, N. and Feng, M. (2010). Characterization of phenol–formaldehyde resins derived from liquefied lodgepole pine barks. *International Journal of Adhesion and Adhesives*, 30(8), 689-695.

- Zhou, Y.-X., Chen, Y.-Z., Hu, Y., Huang, G., Yu, S.-H. and Jiang, H.-L. (2014). MIL-101-SO₃H: A highly efficient brønsted acid catalyst for heterogeneous alcoholysis of epoxides under ambient conditions. *Chemistry – A European Journal*, 20(46), 14976-14980.
- Zhu, Y., Hu, H., Li, W.-C. and Zhang, X. (2006). Cresol–formaldehyde based carbon aerogel as electrode material for electrochemical capacitor. *Journal of Power Sources*, 162(1), 738-742.
- Zong, M.-H., Duan, Z.-Q., Lou, W.-Y., Smith, T. J. and Wu, H. (2007). Preparation of a sugar catalyst and its use for highly efficient production of biodiesel. *Green Chemistry*, 9(5), 434-437.