

PERFORMANCE OF POLYMER MODIFIED CONCRETE INCORPORATING
POLYVINYL ACETATE WASTE

AINUL HAEZAH BINTI NORUZMAN

A thesis submitted in fulfilment of the
requirement for the award of the degree of
Doctor of Philosophy (Civil Engineering)

School of Civil Engineering
Faculty of Engineering
Universiti Teknologi Malaysia

AUGUST 2019

Special dedication to my parents

Haji Noruzman bin Haji Mohamed Sam and Hajah Wan Paziah Binti Wan Abdul

Manan

To my greatest supporters

Hambali Bahri, Ain Suhara, Ainie Hayati, Azizul Hafidz and Wan Mohd Aidid

Daniel Hasbollah

And also to all who supported me by Doa and work. Thanks for everything. May

Allah bless you. Amin

ACKNOWLEDGEMENT

I wish to express my sincere appreciation to my supervisor Prof. Dr. Mohammad Ismail and Dr. Nur Hafizah Abd Khalid for their encouragement, guidance, critics and full academic support. I am also very thankful to my beloved friend Dr. Taliat Yusuf for his tireless advices and motivations. Without their continued support and interest, this thesis would not have been the same as presented here.

I am greatly indebted to Universiti Teknologi Malaysia (UTM) for give me this golden opportunity to pursue Ph.D., most especially; Department of Structures and Material, School Civil Engineering, Faculty of Engineering for their assistance and helps during completing the study.

I gratefully acknowledge the support for this research from Ministry of Education (MOE). Finally, I am grateful to all my family members and friends.

ABSTRACT

Generation of waste latex paint (WLP) from the manufacturing process of binder paint products is increasing globally due to the increasing need for aesthetical features in association with rapid industrialisation and urbanisation. The volume of waste generated in the form of solids and effluents from these productions annually cause not only financial burden, but accountable for future environmental consequences. The use of polymers such as natural rubber, acrylic, and styrene-butadiene latex has been acknowledged of their characteristics to influence the properties of concrete. In spite of the various researches conducted on the study of polymer in concrete, very little information is known about the incorporation of WLP consisting of polyvinyl acetate waste (PVAW) generated from the binder paint industries. This research aimed to investigate the effect of utilisation of PVAW as an admixture to improve the properties of concrete. The fundamental analysis of WLP was determined including ICP-MS, GPC, DSC, and FTIR. The properties of fresh state concrete include setting time, workability, and heat of hydration. The tests were carried out on mechanical properties of hardened concrete such as compressive, tensile, and flexural strength. The durability test was conducted to investigate the chemical resistance in acids and sulphate solutions, elevated temperature, water absorption, drying shrinkage and leaching test. The microstructural tests in terms of XRD, FESEM, and MIP were also studied. The properties of WLP in terms of the chemical and physical were studied and compared with original latexes. The finding showed that incorporating PVAW impacted positively on the workability of concrete and reduce temperature rise in mass concrete. The setting time of the modified cement paste was delayed compared to the control specimen. However, the delayed setting time was within the limit as suggested by the relevant standard. While in hardened state properties, it shows that optimal compressive strength was achieved from the incorporation of 2-3% PVAW in concrete. Both tensile and flexural strength were larger than the strength of control concrete from the addition of 5% and 1% PVAW, respectively. Better performance in flexural strength was observed in the reinforced modified concrete beam. Modified concrete showed a decrease in water absorption with increase of the PVAW addition. The research examined various aspects of the durability of concrete against physical and chemical attacks. However, it demonstrated slightly less performance to destructive chemicals and elevated temperature. Meanwhile, the incorporation of polymer up to 10% PVAW had no significant effect of heavy metal ion mobilisation in leaching test. It can be concluded that the incorporation of PVAW in concrete may give better performance in strength and durability of the concrete as well as able to minimise the PVAW waste disposal from the production of binder paint for a sustainable environment.

ABSTRAK

Penjanaan sisa cat lateks (WLP) daripada proses pembuatan produk cat pengikat semakin meningkat secara global disebabkan oleh peningkatan keperluan ciri-ciri estetika seiring dengan peningkatan urbanisasi dan industrialisasi yang pesat. Janaan sisa pepejal dan efluen yang dihasilkan secara tahunan ini, telah menyebabkan masalah bukan sahaja dari segi kewangan tetapi juga kepada alam sekitar. Penggunaan polimer seperti getah asli, akrilik, dan stirena-butadiena lateks telah diakui cirinya dapat mempengaruhi sifat-sifat konkrit. Walaupun pelbagai kajian telah dijalankan ke atas polimer konkrit, namun tidak banyak yang diketahui tentang penambahan WLP yang mengandungi sisa polivinil asetat (PVAW) daripada hasil buangan industri cat pengikat. Oleh itu, objektif kajian ini adalah untuk mengkaji kesan penggunaan PVAW sebagai bahan tambah bagi menambah baik sifat-sifat konkrit. Analisis asas WLP telah dilakukan termasuk menggunakan ICP-MS, GPC, DSC, dan FTIR. Sifat konkrit segar yang dikaji adalah masa pemejalan, keboleherjaan, dan haba penghidratan. Ujian terhadap sifat mekanikal pula adalah kekuatan mampatan, tegangan, dan lenturan. Ujian ketahananlasakan turut dijalankan untuk mengkaji rintangan kimia dalam larutan asid dan sulfat, peningkatan suhu, penyerapan air, pengecutan kering dan ujian pengurusan. Ujian struktur-mikro menggunakan XRD, FESEM, dan MIP juga dikaji. Selain itu, ciri-ciri WLP dari segi kimia dan fizikal juga diuji dan dibandingkan dengan lateks asal. Hasil kajian menunjukkan dengan penambahan PVAW boleh memberi kesan positif terhadap keboleherjaan konkrit dan merendahkan peningkatan suhu dalam jisim konkrit. Didapati bahawa masa pemejalan adalah lebih lama bagi simen yang diubahsuai berbanding dengan spesimen kawalan. Namun begitu, masa pemejalan bagi simen yang diubahsuai masih dalam lingkungan piawai. Bagi konkrit yang berada dalam keadaan keras, didapati kekuatan mampatan optimum tercapai dengan pencampuran 2–3% PVAW. Kekuatan tegangan dan lenturan konkrit adalah lebih tinggi berikutan dengan penambahan sebanyak 5% dan 1% PVAW berbanding kekuatan konkrit yang asal. Didapati rasuk konkrit bertetulang yang telah diubahsuai menunjukkan prestasi yang baik dalam ujian lenturan. Konkrit yang diubahsuai menunjukkan penurunan dalam penyerapan air dengan peningkatan penambahan PVAW. Daripada segi aspek ketahanan konkrit terhadap serangan fizikal dan kimia, didapati konkrit yang mengandungi PVAW menunjukkan prestasi yang agak lemah dalam menangani serangan kimia perosak dan ujian peningkatan suhu tinggi. Sementara itu, penambahan sehingga 10% PVAW tidak mempunyai kesan ketara dalam mobilisasi ion logam berat dalam ujian pengurusan. Kesimpulannya, penambahan PVAW dalam konkrit mampu menghasilkan konkrit yang lebih kuat dan tahanlasak disamping dapat meminimumkan pelupusan sisa PVAW hasil daripada pengilangan cat pengikat untuk persekitaran yang mampan.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xiii
	LIST OF FIGURES	xv
	LIST OF ABBREVIATIONS	xix
	LIST OF APPENDICES	xx
1	INTRODUCTION	1
	1.1 Introduction	1
	1.2 Background of the Study	3
	1.3 Problem Statement	7
	1.4 Aim and Objective of the Study	8
	1.5 Research Hypothesis	8
	1.6 Scope and Limitations of the Study	9
	1.7 Significance of the Research	9
	1.8 Research Approach	10
	1.9 Organization of the Thesis	11
2	LITERATURE REVIEW	14
	2.1 Introduction	14
	2.2 Basic Properties of Polymer	15

2.3	Polymers in Concrete	18
2.4	Historical of Polymers in Mortar and Concrete	18
2.5	Concrete-Polymer Composites	19
2.6	Benefits of Polymers in Concrete	20
2.7	Polymer Latexes	21
2.8	Polymerisation on Structure Formation	24
2.9	Aqueous Polymer Dispersions	26
2.9.1	Monomer	27
2.9.2	Water	27
2.9.3	Surfactant	28
2.9.4	Initiator	28
2.9.5	Protective Colloid	29
2.9.6	Chain Transfer	29
2.9.7	Compounding Ingredients	29
2.10	Water Borne Coating Systems	30
2.11	Chemical Structure and the Synthesis of Vinyl Acetate	30
2.12	Hydrolysis of Vinyl Acetate	32
2.13	Properties of Polymer Modified Concrete and Mortar	33
2.13.1	Physical Properties of the Fresh Mix	33
2.13.2	Curing Process	35
2.13.3	Mechanical Properties	36
2.13.4	Durability Properties	38
2.13.5	Fire Endurance	42
2.13.6	Practical Application	43
2.14	Recent Innovation of Polymer Modified Cement	45
2.15	Overview of Paint or Surface Coating Production	46
2.15.1	Paint Formulation	47
2.15.2	Classification of Paint	47
2.15.3	Paint Manufacturing and Processing	48
2.15.4	Wastes from Paint Manufacturing Industries	49

	2.15.5	Waste Minimization Options	50
	2.16	Overview of Constituents of Latex-based Paints	52
	2.17	Waste Latex Paint (WLP) as Polymer Addition	52
	2.18	Summary of Literature	53
3		RESEARCH METHODOLOGY	56
	3.1	Introduction	56
	3.2	Experimental Programme	56
	3.3	Materials: Polymer Dispersion Discharge	57
	3.3.1	Preparation of Polymer Waste	58
	3.3.2	Composition of Waste Latex Paint	60
	3.3.3	Chemical Analyses	60
	3.3.4	Physical Properties	62
	3.3.5	Polymer Structure	64
	3.4	Material Acquisition	70
	3.4.1	Cement	70
	3.4.2	Fine Aggregate	71
	3.4.3	Coarse Aggregate	72
	3.4.4	Water	72
	3.5	Analysis of Cement and Waste Latex Paint	72
	3.5.1	Setting Time	72
	3.6	Design and Proportioning of Concrete Mixture	73
	3.7	Specimen Preparations	75
	3.7.1	Batching and Mixing	75
	3.7.2	Casting	76
	3.7.3	Compaction	76
	3.7.4	Curing of Concrete	76
	3.8	Test Specimens	78
	3.9	Testing: Fresh Properties	79
	3.9.1	Measurement for Workability	79
	3.10	Testing: Properties of Normal and Waste Latex Paint Concrete	79
	3.10.1	Compressive strength	79
	3.10.2	Indirect Tensile Strength	80

3.10.3	Flexural Strength	82
3.10.4	Reinforced Normal Concrete and Modified Concrete	83
3.10.5	Water Absorption	84
3.10.6	Heat Hydration	86
3.10.7	Drying Shrinkage	88
3.10.8	Fire Resistance	89
3.10.9	Bulk Density	90
3.10.10	Porosity	91
3.10.11	Sorptivity Test	92
3.10.12	Resistant to Sulphate Attack	93
3.10.13	Resistance to Acid Attack	94
3.10.14	Leaching Test	94
3.11	Microstructural Studies - FESEM, TGA and MIP	95
3.11.1	Field Emission Scanning Electron Microscope (FESEM)	95
3.11.2	Thermogravimetric Analysis (TGA)	96
3.11.3	Mercury Intrusion Porosimetry (MIP)	97
4	CHARACTERISTICS PROPERTIES OF EMULSION POLYMER EFFLUENTS	99
4.1	Introduction	99
4.2	Characteristics of Emulsion Polymer Effluents	99
4.2.1	Chemical Properties	100
4.2.2	Physical Properties	102
4.3	Polymer Structure	107
4.4	Morphology	109
4.5	Glass Transition Temperature (T _g)	110
4.6	XRD Analysis	112
4.7	Molecular weight distributions	114
4.8	Summary	115

5	PERFORMANCE OF EMULSION POLYMER EFFLUENTS ON FRESH AND HARDENED PROPERTIES OF CONCRETE	116
5.1	Introduction	116
5.2	Setting Time	116
5.3	Resistance to Elevated Temperature	118
5.4	Workability	122
5.5	Compressive Strength	124
5.6	Favourable Curing Regime	127
5.7	Indirect Tensile Strength	128
5.8	Flexural Strength	129
5.9	Water Absorption	131
5.10	Drying Shrinkage	132
5.11	Fire Endurance	135
	5.11.1 Furnace Temperature Rating	135
	5.11.2 Effect of Elevated Temperature on Compressive Strength	136
	5.11.3 Effect of Elevated Temperature on Mass Loss	140
	5.11.4 Effect of Elevated Temperatures on Visual Appearances	143
5.12	Summary	144
6	DURABILITY AND PERFORMANCE OF FLEXURAL BEHAVIOUR OF MODIFIED CONCRETE	146
6.1	Introduction	146
6.2	Resistance to Chemical Ingress	146
	6.2.1 Resistance to Sulphuric Acid Penetration	147
	6.2.2 Resistance to sodium sulphate penetration	150
6.3	Leaching Test	154

6.4	Reinforced Concrete Beam Application for OPC and Emulsion Polymer Effluent (PVAWRCB)	155
6.4.1	Ultimate Load on Reinforced Concrete	156
6.4.2	Load – Deflection Behaviour	156
6.4.3	Load Reinforcement Strain of Concrete	158
6.4.4	Compressive and Tensile Strain Characteristics	159
6.4.5	Crack Pattern and Mode of Failure	160
6.4.6	Ductility of Concrete Beam	161
6.5	Summary	162
7	CONCLUSION	164
7.1	Introduction	164
7.2	Conclusions	164
7.2.1	Conclusions on Properties of Waste Latex Paint	164
7.2.2	Conclusions on Fresh State Properties of Modified Concrete	165
7.2.3	Conclusions on Hardened State Properties of Modified Concrete	166
7.2.4	Conclusions on Durability and Performance of Flexural Behaviour Modified Concrete	167
7.3	Concluding Remark	168
7.4	Recommendations for Further Investigations	168
	REFERENCES	170

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Paint manufacturing process waste (Randall, 1992)	50
2.2	Pollution prevention methods for paint manufacturing industry (Randall, 1992)	51
2.3	Summary of waste latex paint on properties of concrete	55
3.1	Composition of waste latex paint given by manufacturer	60
3.2	Parameter testing using APHA methods	62
3.3	Chemical composition, physical and mechanical properties of the cement were determined using BS EN 197-:2011	71
3.4	Mix design for grades 25	74
3.5	Mix design proportions for modified concrete	74
3.6	Water absorption rate	85
4.1	Physico-chemical characteristic of the emulsion polymer effluents (All values in mg/l except for turbidity and temperature value)	101
4.2	The comparison of pH value from the tested samples	103
4.3	Results of specific gravity	103
4.4	Results of viscosity	104
4.5	Results of total solids content	105
4.6	Results of particle size distribution for both samples	107
4.7	The comparison between the absorption of emulsion polymer effluents and control in cm^{-1}	109

4.8	Elemental analysis of emulsion polymer effluents using EDX	110
4.9	Molecular weight distributions in comparison	115
5.1	Characteristics of the heat of hydration of normal and latex effluents concrete	119
5.2	Optimum emulsion polymer effluent for compressive strength	126
5.3	Drying shrinkage of modified mortar at ambient temperature.	133
5.4	Residual compressive strength at 28 th days	137
5.5	Compressive strength loss percent after heating at elevated temperatures	138
5.6	Mass loss percent due to high temperatures	141
5.7	Effect of temperature rise on visual characteristic	144
6.1	Compressive strength of control concrete and modified concrete due to sulphuric acid attack	147
6.2	Compressive strength of control concrete and modified concrete due to sodium sulphate attack	151
6.3	The leaching result	155
6.4	Number of cracks and average crack width in PMRCB and control beam	161
6.5	Summary of the results of PMRCB and control beam	162

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	System and classification of concrete polymer-composites (Ohama, 1997)	20
2.2	Classification of polymer-based (or polymeric) admixtures (Ohama, 1997)	23
2.3	Step 1, Immediately after mixing, the aggregates, cement, polymer and water particles interact with each other. Small ettringite needles are formed (Gemert <i>et al.</i> , 2005)	25
2.4	Step 2, Polymer particles interacts with cement and the aggregates. Polymer particles flocculate to form a continuous close-packed layer on the surface of the cement gel (Gemert <i>et al.</i> , 2005)	25
2.5	Step 3, as cement hydration proceeds, polymer film formation starts on specific spots thus, polymer particles coalesce together into a continuous film (Gemert <i>et al.</i> , 2005)	25
2.6	Final step, as cement hydration continuous, the polymer coalesce into a continuous film and the cement particles are hydrated (Gemert <i>et al.</i> , 2005)	26
2.7	Block diagram of paint manufacture (Randall, 1992)	49
2.8	Research gap of the study	54
3.1	Schematic diagram for the overall programme	57
3.2	Polymer waste from production of polymer dispersion	59
3.3	Perkin Elmer Sciex Elan 6100	61
3.4	Brookfield Cole-Parmer	63

3.5	FTIR Nicolet	65
3.6	Table top SEM Hitachi TM 3000	67
3.7	Mastersizer Micro Ver. 2.18	68
3.8	Perkin Elmer differential scanning calorimeter (DSC-7)	69
3.9	Siemens Diffractometer D5000	70
3.10	Vicat apparatus	73
3.11	Curing in wet condition	78
3.12	Curing in dry condition at ambient temperature with 60% RH	78
3.13	Testing for compressive strength	80
3.14	Testing for indirect tensile test	81
3.15	Testing for flexural strength	82
3.16	Specimens of beam concreting	83
3.17	Schematic diagram of beam testing	84
3.18	Reinforced concrete beam test setup	84
3.19	The coring machine	86
3.20	Cored specimens for water absorption test	86
3.21	Arrangement of cubical plywood	87
3.22	Insulator plywood box	88
3.23	Measuring shrinkage using demec gauge	89
3.24	Electric furnace	90
3.25	Sample under elevated temperature	90
3.26	Vacuum saturation apparatus	92
3.27	Gemini FESEM setup	96
3.28	Auto fine coater instrument	96
3.29	Thermogravimetric analyser Mettler Toledo TGA/STDA 851	97
3.30	Autpore IV 9500V1.09 Micrometrics instrument high-pressure MIP	98
4.1	Sample of emulsion polymer effluents in dry condition	105
4.2	Comparison between the emulsion polymer sources in particle size distribution	106

4.3	Comparison polymer sources with respect to the chemical structure	108
4.4	Repeat unit of poly (vinyl acetate-co-butyl acrylate) (Vargha and Truter, 2005)	109
4.5	Morphology of emulsion polymer effluents using SEM	110
4.6	Different scanning calorimetry analysis of PVAW	112
4.7	XRD of emulsion polymer effluents	113
5.1	Effect of emulsion polymer effluents dosage in setting time	118
5.2	Development of temperature in normal and modified concrete	119
5.3	Rate of heat of hydration as function of time	120
5.4	Fesem micrograph of PVAWC-2.5%	121
5.5	Fesem micrograph of PVAWC-5%	122
5.6	Effect of emulsion polymer effluents dosage on workability	123
5.7	Effect of emulsion polymer effluents dosage on compressive strength	125
5.8	Effect of emulsion polymer effluents dosage on the 28 th day compressive strength	127
5.9	Effect of curing regime on compressive strength	128
5.10	Effect of emulsion polymer effluents dosage on indirect tensile strength at 28 th days	129
5.11	Effect of emulsion polymer effluents dosage on flexural strength at 28 th days	130
5.12	Effect of latex dosage on water absorption	132
5.13	Effect of increase in latex on drying shrinkage	133
5.14	Characterisation of pore size distribution among the samples	134
5.15	Experimental time-temperature curve compared with the standard curve of ISO 834 and ASTM E 119	136
5.16	Effect of increase on compressive strength	137
5.17	Effect of increase in temperature on residual	

	compressive strength	140
5.18	Effect of elevated temperature on mass loss	142
6.1	Effect of sulphuric acid on compressive strength	149
6.2	Visual appearance of the concrete specimen in sulphuric acid solution after 3 months. From left; 0 %, 1 %, 2.5 %, 5 % and 10 % of PVAW	150
6.3	Impact of sodium sulphate on compressive strength with age	151
6.4	Effect of sodium sulphate on compressive strength	152
6.5	A typical example of the visual appearance of concrete specimens immersed in sodium sulphate solution after three months	153
6.6	Load versus deflection curve of PVAWCRCB and control beam	157
6.7	Load – reinforcement strain PVAWRCB and control beam	158
6.8	Compressive and tensile strains of PVAWRCB and control beam	159
6.9	Failure mode of PVAWRCB-2.5%	160
6.10	Failure mode of the control beam	161

LIST OF ABBREVIATIONS

ASTM	- American Society for Testing and Materials
BS	- British Standard
ACI	- American Concrete Institute
CSH	- Calcium silicate hydrate
C ₃ S	- Tricalcium silicate
C ₂ S	- Dicalcium silicate
C ₄ AF	- Tetracalcium aluminoferrite
Ca(OH) ₂	- Calcium hydroxide
PMC	- Polymer modified concrete
PMM	- Polymer modified mortar
PVAW	- Polyvinyl acetate waste
LMC	- Latex modified concrete
LMM	- Latex modified mortar
TGA	- Thermogravimetry analysis
SEM	- Scanning electron microscopy
MIP	- Mercury intrusion porosimetry
EDX	- Energy dispersive x-ray
UPV	- Ultrasonic pulse velocity
XRD	- X-ray diffraction
XRF	- X-ray fluorescence
FTIR	- Fourier transform infrared spectroscopy
DSC	- Differential scanning calorimetry
WLP	- Waste latex paint
VAW	- Vinyl acetate effluent

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Current process flow treatment rmsb effluent discharge treatment	193
B	Standard mix proportion (BS 5328: Part 2: 1991)	194
C	Calculation of amount of waste latex paint use in concrete	195
D	Results of sieve analysis data for fine aggregate	196
E	Design of single reinforced rectangular section	197
F	Research publications	199

CHAPTER 1

INTRODUCTION

1.1 Introduction

There is an increase of global concern on the environment demand that waste should be appropriately managed in order to minimise or possibly eliminate the harmful effect towards the environment. Due to ever-increasing quantities of waste materials and industrial by-products generated, solid waste management becomes a primary concern in the world (Siddique and Singh, 2011).

The establishment of a growing diverse manufacturing sector in Malaysia has contributed immensely to the advancement of the Malaysian economy. This development is key to the observable relative rapid economic growth of the country (Rashid *et al.*, 2010). Malaysia's economy has transformed since the 1970s from agriculture based economy into emerging an industrial manufacturing entity (Mokhtar *et al.*, 2010). According to (Aja *et al.*, 2016), the manufacturing sector in 1966 contributed 11% the nation's gross domestic product (GDP), 24% in 1988, and 24.6% in 2010 and while in 2012, the manufacturing sector contributed 24.2% to the Malaysian GDP. The chemicals industry is the second largest contributor to total manufactured exports, amounting to about 6% of the total Malaysian exports annually. The manufacturing of chemicals, including the manufacturing of refined petroleum products, vegetable and animal oils and fats; basic chemical, fertilisers including nitrogen compounds; plastics and synthetic rubber in its primary form, contribute 13.5%, 12.4% and 6.8% to GDP respectively (Abdullah, 2008). The rapid industrial growth and urban development in the country have contributed to a

significant rise in the volume as well as a variety of toxic and hazardous waste being generated annually (Abdullah, 1995; Saeed *et al.*, 2009). In a recent review by (Fazeli *et al.*, 2016) on waste energy, it was noted that the growing economy of Malaysia contributes to the environmental burden levied by high energy consumption and high volume waste generation. Waste generated in Malaysia is categorised based on the level of potential hazard. According to Department of Environment, waste is defined as “ any substance prescribed to be scheduled waste or any matter whether in a solid, semi-solid or liquid form or in the form of a gas or vapour, which is emitted, discharged, or deposited in the environment in such volume, composition, or manner as to cause pollution (DOE, 2001). Scheduled waste is the categories of waste listed in the First Schedule of the Environmental Quality (Scheduled Wastes) Regulations 2005. Sources of scheduled waste generated in Malaysia mainly from cement manufacturing, water treatment plant/power station, coal-fired power plant, chemical manufacturing operations, oleochemical and many more heavy industries (Jamin and Mahmood, 2015).

Waste generation from many sectors contributes to a significant amount of solid waste annually. In Malaysia, solid wastes are generally categorized into three major categories and each category under the responsibility of a different government department. There is a municipal solid waste (MSW) under Ministry of Housing and Local department, schedule/hazardous waste under Department of Environment (DOE) and clinical waste under Ministry of Health (Manaf *et al.*, 2009). At present, landfilling is the only method used for the disposal of MSW, and most of the landfill sites are open dumping areas, which pose serious environmental and social threats (Yunus and Kadir, 2006). With regard to economic aspects, in general, landfilling is the simplest, least expensive, and most cost-effective method of waste disposal (Allen, 2002). Disposal of waste through landfilling is becoming more difficult because existing new landfill sites are filling up at a very fast rate. At the same time, constructing new landfill sites is becoming more difficult because of land scarcity and the increase of land prices and high demands, especially in urban areas due to the increase in population (Manaf *et al.*, 2009). To reduce or to minimise the negative impact caused by these wastes, various ways and methods or process has been implemented including 3R concepts which are Reduce, Reuse and Recycle respectively. For instance, the utilization of solid wastes such as from agro- waste

(organic), industrial waste (inorganic), mining waste, non-hazardous waste and hazardous waste to produce construction materials such as wall panels, roof sheets, brick, particle board, fine and coarse aggregate, tiles, and other innovative products (Safiuddin *et al.*, 2010).

The addition of waste or by-product to concrete opens a new pathway in research activities, where concrete as a construction material is integrated with environmental technology. Chemical manufacturing such as plastic and synthetic rubber and polymer dispersion sectors produce a significant amount of polymeric waste materials during the manufacturing process, and these are known to pose problem occupying considerable space on landfills. Several types of research have been conducted with a view to converting waste materials into useful by-product rather than disposing of them in landfills or incinerators. Examples of such materials which have been reported for instance, Topçu, and Uygunoglu (2016) studied on the behaviour of concrete with the incorporation of waste rubber. Sharma, and Bansa (2016) revealed recent studies regarding the utilization of waste plastic in concrete and other related studies using waste material in concrete. Based on the need to promote effective environmental management that supports the drive for sustainable development, there is a strong expectation for the adoption of proper methods of protecting the environment from the cross-section of the industries. The burden of waste management on industries is therefore critical for their successful operations. For this reason, it is economically and environmentally viable to utilise waste or by-product from industries to minimise the problem of waste disposal as well as for sustainability environment.

1.2 Background of the Study

Concrete is known to be the most widely used in the world with global annual production of up to 20 billion metric tonnes (Mehta and Meryman, 2009). Its low cost, ease of application and compressive strength are the main reasons for its universal acceptance (Muthukumar and Mohan, 2004). However, there are many shortcomings of Portland cement concrete or mortar in its fresh as well as hardened

states are cause for concern. The common observable inadequacies in its fresh state are bleeding, segregation, excessive air entrainment, high surface tension, rapid loss of workability and rough surface texture. Moreover, while prolonging water or moist curing assist the concrete in tremendous and consistent strength appreciation, this exercise is both labours as well as cost intensive.

The common inadequacies of the hardened normal concrete or mortar are reflected in low tensile strength, flexural strength, modulus of rupture, toughness and energy absorption capacity, and high porosity that consequently affect the durability negatively. Water-based polymer emulsion or latex of copolymer types, when added to concrete or mortar system, improves many of the inadequacies. Due to its mobility, latex can improve the cohesiveness of the concrete matrix, reduces the chances of bleeding. However, it entraps a high percentage of air, which is liable to affect the concrete compressive strength considerably (Ray *et al.*, 1994). Furthermore, according to Ohama (1995) which stated that concrete or mortar has some drawbacks due to delayed hardening, higher drying shrinkage and low chemical resistance. These problems have been solved for some applications to improve the quality of concrete by introducing polymer compounds such as latexes, redispersible polymer powder, water-soluble polymers, liquid resins and monomers as an active ingredient at modifying or improving the performance of concrete. In the search for alternatives ways to improve strength and durability properties as well as to minimise or reduce concrete cost using environmentally friendly concrete, while utilising waste material for sustainable construction. Appreciable reported of studies have utilised various forms of polymeric waste in concrete specimen sourced from different types of solid waste materials most especially in paint industries.

Concrete-polymer composites are made from whole or partial replacement of Portland cement hydrate binder in conventional concrete with organic polymers. The composite system works by strengthening the cement hydrate binder with the polymers. Utilizing the principles of their process techniques, the concrete polymer composites are commonly classified as Polymer-modified mortar (PMM or PCM) and Polymer-modified concrete (PMC or PCC), Polymer mortar (PM) and Polymer concrete (PC) and Polymer-impregnated mortar (PIM) and concrete (PIC) (Fowler,

1999; Ohama, 1997). The monomers also called homopolymer are the basic unit of polymers joining together to form long chain molecules. However, some polymers are formed from copolymers which are two or more monomers joined to form the copolymers. Polymers are also classified as an elastomer, thermosetting or thermoplastic, each characterised by the relative degree of crosslinking of the polymer chains. The physical characteristic of the polymers is influenced by the effectiveness and density of the crosslinking (Kardon, 1997). The polymer content or mass-based polymer – cement (p/c) ratio, exert significant influence on the behaviour of the polymer. The properties of polymer modified concrete depend on the polymer content or mass-based polymer-cement (p/c) ratio, rather than the water-cement ratio (w/c) when assessing ordinary Portland cement concrete. While using polymer-based or polymeric admixtures in cementitious composites such as concrete, the need to ensure that both cement hydration and polymer film formation proceeds are paramount so as to yield a monolithic matrix phase with a network structure in which the cement hydrate phase and polymer phase interpenetrate (Gemert *et al.*, 2005). The superior properties of polymer-based composites in comparison with traditional cementitious materials results from the formation of the monolithic matrix phase. The distinctly enhanced properties of fresh and hardened phases of polymer modified concrete as against the conventional mix designs are attributable to many factors such as polymer type, polymer/cement ratio, water/cement ratio, air content and curing conditions. It is noteworthy that target properties can be achieved through the control of these factors during manufacture process (Almesfer *et al.*, 2012).

Currently, waste latex paint is being disposed of in a landfill without any meaningful reuse. This practice which does not take into account the inherent value attached to its reusability is faced with an attendant considerable economic and environmental cost. The properties of waste latex paint in certain aspects are similar to polymeric admixtures used in concrete production. For instance, the recycling of waste latex paint in concrete such an efforted done by Nehdi and Sumner (2003), using a collection of waste paint as an admixture in concrete. The latexes used as binder paint is a type of polymer dispersion product that suitable to be used in concrete. Hence, the properties of this latex could be similar to the characteristics of pure latexes used in concrete. The solid mass in paints is mainly made up of polymers and tends to behave like polymeric admixtures which have been an active

ingredient in the modification of cementitious applications for well over seven decades ago. Polymeric admixtures perform the role of enhancing the bond between the concrete aggregate matrix and the cement. This is due to the polymer when incorporated with concrete mixes, the polymer particles are uniformly dispersed in the cement paste phase. With water withdrawal by cement hydration, the close-packed layer polymer particles coalesce into continuous films, and the films bind the cement hydrates together to form a monolithic network in which the polymer phase interpenetrates throughout the cement hydrate phase (Ohama, 1995). With these characteristics, polymer cement concrete made with polymer latex exhibit excellent bonding to steel reinforcement and to old concrete. This bonding benefitting the modified concrete which provide good ductility, increased the water proofness, resistance to penetration by water and salt, and resistance to freeze-thaw damage (Blaga and Beaudoin, 1985). The addition of polymers makes the concrete mix to become more workable, and improved the workability of concrete. However, the properties of polymer cement concrete are thus dependent on the type of polymer and/or its amount.

The use of concrete-polymer composites as construction material might drastically increase the cost of a project; therefore it should be used for particular conditions or occasions. For instance, the utilisation of polymer to overcome the crack problem associated to the poor performance of concrete. Epoxy resin is one of common polymer that generally used in crack repair systems . The application of carbon fiber reinforced polymers (CFRP) is used in repair and the rehabilitation of reinforced concrete which offers superior performance in resistance in corrosion and high stiffness to weight ratio (Kasapoglu, 2008). Polymers containing large amounts of filler and mainly used as protective coatings in concrete, reinforced concrete, and rarely on steel which capable of withstanding in severe corrosive environments. In spite of high cost, polymer concrete notably useful for maintenance and repairs, especially when it is required to avoid delay and inconvenience (Halliwell, 2015). Furthermore, the benefits of using concrete-polymer composite including their superior properties in performance of concrete , reduce labour cost and low energy requirements (Figovsky and Beilin, 2014).

1.3 Problem Statement

The universally accepted role of paint and coating materials in the present day has made the products a globally demanded item. Extensive application of paint and coating materials has had impact on the increasing production of these materials. Water-based paint production is steadily growing, owing to its wide acceptance as a coating material for most buildings. Also, the need to control solvents use for paint production through the imposition of environmental regulations especially as it concerns health is responsible for the growth of the water-based paint. Polyvinyl acetate is a primary ingredient in the production of the paints. These polymers compared to others, are used extensively to produce emulsion paints for interior application. These type of coatings are flexible and durable, adhere well, dry quickly and generally do not discolour (Randall, 1992). The increase in demand for the paint has naturally called for a progressive increase in the production to match the increase in demand for the paint. However, significant waste in the form of vinyl acetate effluent is generated during production of the paint thereby raising concern for its disposal especially when an increase in production as a result of demand directly influences the volume of waste generated thereby posing waste disposal problem. For instance, the expected growth rate of Malaysian paint consumption is put at about 3.5% per annum, and the absolute volume of consumption was forecasted to be about 166,000 metric tonnes in 2014 (Reg, 2010). However, the percentage increases whereby an overview report is revealed that the Malaysian paint and coating industry recorded total sales amounting RM 3.64 billion at 257,047 metric tonnes in 2016 (CRCG, 2017). The consumption paint has a strong tendency to increase paint waste generation and landfill occupation by these industries. This figure is predisposed to proliferate with advancement in economic activities. Any devised means to recycle this waste would appreciably result to solve the environmental pollution problem and at the same time provide some inherent economic advantage.

The growing interest to recycle waste material from paint production by using it to modify concrete mixes is discernible. While several works have been done in the co-operating the cement with the paint waste to improve the properties of concrete (Nehdi and Sumner, 2003; Mohammed *et al.*, 2008; Ismail *et al.*, 2011;

Ismail and Al-Hashmi, 2011; Almesfer *et al.*, 2012), there are little research findings on the application of polyvinyl acetate waste from paint production in preparation of concrete normal strength. Therefore, this study is aimed to investigate the effect of polyvinyl acetate waste on fresh and hardened states, and durability to improve the properties of concrete. The material is in the liquid form taken from rinse of equipment washing activities in a paint factory. The utilisation of this material may show some excellent properties especially in durability study, that could emanate from its use in the concrete production not only for resource preservation and disposal concerns but also to evaluate the potential of the material can be used in concrete production.

1.4 Aim and Objective of the Study

This study aims to investigate the possibilities of using polyvinyl acetate waste as an ingredient in polymer modified concrete with the following objectives:

1. To characterise properties of polyvinyl acetate waste.
2. To assess the effect of polyvinyl acetate waste on fresh and hardened properties of concrete.
3. To determine the effect of polyvinyl acetate waste on durability performance of polymer modified concrete.

1.5 Research Hypothesis

In this study, it is hypothesised that polyvinyl acetate waste can be incorporated as polymer admixture to enhance the strength and durability properties of concrete significantly.

1.6 Scope and Limitations of the Study

The experimental study focuses on the utilisation and characterisation of polyvinyl acetate waste in concrete. The addition by weight of cement with polyvinyl acetate waste ranged from 0% to 20%. The samples are cured and measured at 7, 28 and 56 days. The study emphasises on the characterisation of polyvinyl acetate waste, properties of concrete at fresh and hardened states, as well as durability of concrete with polyvinyl acetate waste polymer. Furthermore, the morphological studies on microscopic observations of matrix networks, principally between cement and latex particles are also carried out

1.7 Significance of the Research

There is possible potential, innovative and cost benefitting the polymer modified concrete by utilising polyvinyl acetate waste as polymer additive to conventional concrete that will undoubtedly encourage and promote sustainable development, saving preserved natural resources and dumping spaces for maintaining a clean environment:

- i. The utilisation of polyvinyl acetate waste in concrete will be an innovative product to enhance strength and durability properties of concrete.
- ii. The utilisation of polyvinyl acetate waste will benefit in cost respectively, instead of using other branded chemical resin purely that would give similar behaviour in concrete. One such examples is the evaluation of acoustic absorption behaviour in the concrete. Brancher *et al.* (2016) utilised the polymer ethylene vinyl acetate waste in measuring the effect of acoustic absorption in the floor have similar effect with the study done by Kim *et al.* (2016) which used acrylic polymer emulsion resin in measuring the acoustic performance of the floor system. The performed investigations show that there is possible to use polymeric residues in a new product showing promising acoustic and thermal performance if compared with unmodified concrete.

- iii. The utilisation of polyvinyl acetate waste helps to reduce landfill problem associated with this waste by recycling the effluents to produce a meaningful concrete product.
- iv. The advantage of having the polyvinyl acetate waste is improving the surface of the concrete in addition to enhancing the aesthetics of the reinforced concrete structure. For instance, when a blemish appears on the concrete structure surface, it shows that it could be one of these concrete defects: blisters, cracking, crazing, curling, delamination, discolouration, dusting, efflorescence, low spots, popouts, scaling or spalling. These deficiencies can be due to various reasons or causes such as structural deficiency resulting from errors in design, loading criteria, unexpected overloading, and construction defects. The concrete defect also caused by damage due to chemical attack, marine environment, exposed to fire, flood, earthquake, cyclone and other relating causes. However, to minimise these defects, polymer latexes are one of the types of admixture used to overcome some of those defects. These are proved by recent studies which utilised the waste latex paint in concrete which minimised the concrete surface defects from other physical and chemical attack by reduction of permeability and porosity in concrete due to polymer latex (Nehdi and Sumner, 2003; Mohammed *et al.*, 2008).
- v. Finally, when the technology of polymer modified concrete incorporating polyvinyl acetate waste is adequately established, it will enhance sustainability through reduced environmental impact and reduced cost of the waste disposal, thus producing sustainable concrete.

1.8 Research Approach

- i. Carry out a detailed literature review on the utilisation of polymer additive in concrete and other related works on construction.
- ii. Select the materials such as cement, polyvinyl acetate waste, aggregate and other materials taking their characteristics into consideration.

- iii. Establish test procedures of various standards (ASTM, BS, and RILEM) to be adopted to perform various tests on mortars and concrete specimen prepared from ordinary Portland cement and relating their performance to those prepared from production of concrete containing polyvinyl acetate waste.
- iv. Conduct a preliminary study and trial mixes to obtain information that is useful for the refined experimental design employed in the full-scale experiment.
- v. Develop a well-planned schedule of experimental tests to study the effect of polyvinyl acetate waste on cementitious composites in relation to specimen prepared from Portland cement alone.
- vi. Carry out complementary studies to obtain insights on the effect of polyvinyl acetate waste on strength, deformation and durability properties of concrete.
- vii. Conduct microstructural examination on specimen prepared from polymer modified concrete incorporating polyvinyl acetate waste and OPC concrete.
- viii. Analyse results of tests conducted and present discussions on the findings on the use of polyvinyl acetate waste in concrete.
- ix. Draw conclusions and present recommendations on the application of polyvinyl acetate waste as a new innovative polymer modified concrete for construction.
- x. Make suggestions of areas for further research of polymer of modified concrete incorporating polyvinyl acetate waste application in concrete.

1.9 Organization of the Thesis

Chapter One: In this chapter, a general appraisal and a brief description of the background problem is discussed. Furthermore, the chapter indicates the aims and

objectives, scope and limitation, research hypothesis, research question, the significance of research and the research approach.

Chapter Two: This chapter provides a logical characterisation of Portland cement and critical discourse of the past research works on the utilisation of polymer thermoplastic materials. A review of the state-of-the-art knowledge on the application of polymer materials in concrete is discussed. However, despite the scanty availability of literature on the incorporation of polyvinyl acetate waste in concrete, a few available additions to many related to the field of polymer in concrete are reviewed.

Chapter Three: The chapter presents materials used for the study and methodology adopted following the appropriate standards and modified published procedures necessary for conducting various tests.

Chapter Four: The results of physical as well as chemical properties of the polyvinyl acetate waste and its effect on fresh concrete properties are presented. Parameters of study in this chapter are workability as it relates to the slump of concrete, air content, setting time of cement and heat of hydration. Presentation of the results obtained and discussion made on the evaluation of mechanical properties is done. Tests falling in this category include compressive, flexural, and tensile strength.

Chapter Five: The chapter contains the evaluation and discussion of deformation behaviour of concrete as influenced by polyvinyl acetate waste on drying shrinkage and reinforced concrete beam. In this chapter, results of Microstructural studies involve field emission scanning electron micrograph (FESEM), energy dispersive X-ray (EDX), thermogravimetric analysis (TGA), and Mercury intrusion porosimetry (MIP) are presented and discussed.

Chapter Six: This chapter consists of the results and discussion arising from various durability tests conducted on OPC concrete and polymer modified concrete incorporating polyvinyl acetate waste. Aspects of durability performance considered

in this chapter are water absorption, sorptivity, acid and sulphate attack, fire endurance and leaching.

Chapter seven: This is the concluding chapter of the thesis. In this chapter, the findings and achievements of the study objectives and the contribution of the research to the existing knowledge are stated. Recommendations made for further studies in related areas with a view on improving concrete quality using polyvinyl acetate waste for use as an alternative admixture in concrete are stated.

REFERENCES

- Abdullah (2008). The chemical industry in Malaysia. In M. Mokhtar, C.T. Goh, N. R. Z. (Ed.). *Round Table Dialogues No. 16 Managing Chemicals for a Better Quality of Life: Improving Our Performance (MyNICHE-3)*, Institute for Environment and Development (LESTARI), Unive.
- Abdullah, A. R. (1995). Environmental pollution in Malaysia : trends and prospects. *Trends in Analytical Chemistry*. 14(5), 191–198.
- Abdullatif, A. M. (2014). Effect of some types of coatings on the performance of reed in cement media. *European Scientific Journal*. 10(30), 269–277.
- Abrams, D. A. (1925). In *Experimental Studies of Concrete*. Structural Materials Research Laboratory, Lewis Institute, Chicago.
- Abrams, D. A. (1924). *Tests of Impure Waters For Maxing Concrete*. In proceedings of the American Concrete Institute, ACI.
- ACI 201.2R-08 (2008). *Guide to Durable Concrete:201.2R-08*. American Concrete Institute, Farmington Hills, Mich.
- Adin, A. (1999). Particle characteristics: A key factor in effluent treatment and reuse. *Water Science and Technology*. 40(4–5), 67–74.
- Afridi, M. U. K., Ohama, Y., Iqbal, M. Z. and Demura, K. (1995). Water retention and adhesion of powdered and aqueous polymer-modified mortars. *Cement and Concrete Composites*. 17(2), 113–118.
- Aggarwal, L. K. K., Thapliyal, P. C. C. and Karade, S. R. R. (2007). Properties of polymer-modified mortars using epoxy and acrylic emulsions. *Construction and Building Materials*. 21(2), 379–383.
- Ahmad, S., Elahi, A., Barbhuiya, S. A. and Farid, Y. (2012). Use of polymer modified mortar in controlling cracks in reinforced concrete beams. *Construction and Building Materials*. 27(1), 91–96.
- Aitcin, J. P. (2003a). Portland cement hydration. *Cement Lime Concrete*. 70, 115–130.

- Aitcin, P. C. (2003b). The durability characteristics of high performance concrete: A review. *Cement and Concrete Composites*. 25, 409–420.
- Aja, O. C., Al-Kayiem, H. H., Zewge, M. G. and Joo, M. S. (2016). Overview of hazardous waste management status in Malaysia. In *Management of Hazardous Wastes*. 69–87, Intech.
- Akchurin, T. K., Tukhareli, A. V and Cherednichenko, T. F. (2016). Effective concrete modified by complex additive based on waste products of construction acrylic paints. *Procedia Engineering*. 150, 1468–1473.
- Albrektsson, J., Flansbjer, M., Lindqvist, J. E. and Jansson, R. (2011). *Assessment of concrete structures after fire* Assessment of concrete structures after fire. SP Technical Research Institute of Sweden.
- Allen, A. (2002). *Low cost natural solutions to landfill management for developing counties*. In *Proceedings 2002 Istanbul, ISWA Conference*. 2, 739.
- Almesfer, N., Haigh, C. and Ingham, J. (2012). Waste paint as an admixture in concrete. *Cement and Concrete Composites*. 34(5), 627–633.
- Almesfer, N. and Ingham, J. (2014). Effect of waste latex paint on concrete. *Cement and Concrete Composites*. 46, 19–25.
- American Concrete Institute (2003). *Polymer-modified concrete*. ACI 548.3R-03.
- American Concrete Institute (1992). *State of the art report on polymer modified concrete*. ACI 548.3R-91.
- American Society for Testing and Materials (2018a). *Standard specification for ready mixed concrete*. ASTM C94.
- American Society for Testing and Materials (2016a). *Standard test method for amount of water required for normal consistency of hydraulic cement paste*. ASTM C187-16.
- American Society for Testing and Materials (2014). *Standard test method for assignment of the glass transition temperatures by differential scanning calorimetry*. ASTM E1356-08:2014.
- American Society for Testing and Materials (2018b). *Standard test method for drying shrinkage of mortar containing hydraulic cement*. ASTM C 596.
- American Society for Testing and Materials (2013). *Standard test method for measurement of rate of absorption of water by hydraulic-cement concretes*. ASTM C 1585.
- American Society for Testing and Materials (2000). *Standard test methods for fire*

- tests of building construction and materials*. ASTM E119:2000.
- American Society for Testing and Materials (2016b). *Standard test methods for rubber latices-synthetic*. ASTM D1417-16.
- American Society for Testing and Materials (2011). *Standard test methods for time of setting of hydraulic cement by Vicat Needle*. ASTM C191.
- Andayani, S. W., Suratman, R., Imran, I. and Mardiyati (2018). Polymer modified concrete of blended cement and natural latex copolymer: static and dynamic analysis. *Open Journal of Civil Engineering*. 08, 205–220.
- Anderson, C. D. and Daniels, E. S. (2003). *Emulsion polymerisation and latex applications*. Rapra Review Reports.
- APHA (2005). *Standards methods for the examination of water and wastewater*. (21st Editi.). APHA, Washington, DC, USA.
- Arioz, O. (2007). Effects of elevated temperatures on properties of concrete. *Fire Safety Journal*. 42(8), 516–522.
- Arnold, C., Klein, G., Maaloum, M., Ernstsson, M., Larsson, A., Marie, P. and Holl, Y. (2011). Surfactant distribution in waterborne acrylic films. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 374(1–3), 58–68.
- Asavapisit, S., Fowler, G. and Cheeseman, C. R. (1997). Solution chemistry during cement hydration in the presence of metal hydroxide wastes. *Cement and Concrete Research*. 27(8), 1249–1260.
- Assaad, J. J. (2016). Disposing waste latex paints in cement-based materials - Effect on flow and rheological properties. *Journal of Building Engineering*. 6, 75–85.
- Assaad, J. J. (2015). Effect of waste latex paints on rheological properties of cement pastes: Compatibility with water reducers. *Journal of Materials in Civil Engineering*. 27(12), 1–11.
- Asseo, J., Gray, E., Danilak, E. and Ritter, N. (2012). Characterization of a Paint-PMMA Polymer Blend. In *Governor's School of Engineering Research Symposium*,. 2012.
- Avci, H., Ghorbanpoor, H., Topcu, I. B. and Nurbas, M. (2017). Investigation and recycling of paint sludge with cement and lime for producing lightweight construction mortar. *Journal of Environmental Chemical Engineering*. 5(1), 861–869.
- Awal, A. S. M. A. and Hussin, M. W. (2011). Effect of palm oil fuel ash in controlling heat of hydration of concrete. *Procedia Engineering*. 14, 2650–

2657.

- Awal, A. S. M. A. and Shehu, I. A. (2013). Evaluation of heat of hydration of concrete containing high volume palm oil fuel ash. *Fuel*. 105, 728–731.
- Awal, A. S. M. A., Shehu, I. A. and Ismail, M. (2015). Effect of cooling regime on the residual performance of high-volume palm oil fuel ash concrete exposed to high temperatures. *Construction and Building Materials*. 98, 875–883.
- Azad, H. S. (1976). *Industrial Wastewater Management Hand Book*. McGraw-Hill Book Company, USA.
- Barbhuiya, S. and Kumala, D. (2017). Behaviour of a sustainable concrete in acidic environment. *Sustainability*. 9(9).
- Barbuta, M., Rujanu, M. and Nicuta, A. (2016). Characterization of polymer concrete with different wastes additions. *Procedia Technology*. 22, 407–412.
- Barluenga, G. and Olivares, F. H. (2004). SBR latex modified mortar rheology and mechanical behaviour. *Cement and Concrete Research*. 34(3), 527–535.
- Benali, Y. and Ghomari, F. (2017). Latex influence on the mechanical behavior and durability of cementitious materials. *Journal of Adhesion Science and Technology*. 31(3), 219–241.
- Benali, Y. and Ghomari, F. (2018). Mechanical behavior and durability of latex modified mortars. *Journal of Building Materials and Structures*. 5, 110–126.
- Bergström, J. (2015). Experimental Characterization Techniques. *Mechanics of Solid Polymers*. 19–114.
- Betioli, A. M. M., Hoppe Filho, J., Cincotto, M. A. A., Gleize, P. J. P. J. P. and Pileggi, R. G. G. (2009). Chemical interaction between EVA and Portland cement hydration at early-age. *Construction and Building Materials*. 23(11), 3332–3336.
- Bhikshma, V., Rao, K. J. and Balaji, B. (2010). An experimental study on behavior of polymer cement concrete. *Asian Journal of Civil Engineering (Building and Housing)*. 11(5), 563–573.
- Blaga, A. and Beaudoin, J. J. (1985). *Polymer modified concrete*. Canada: NRC-IRC Publication.
- Bothra, S. R. and Ghugal, Y. M. (2015). Polymer modified concrete: Review. *International Journal of Research in Engineering and Technology*. 4(4), 2321–7308.
- Brancher, L. R., Nunes, M. F. de O., Grisa, A. M. C., Pagnussat, D. T. and Zeni, M.

- (2016). Acoustic behavior of subfloor lightweight mortars containing micronized poly (ethylene vinyl acetate) (EVA). *Materials*. 9(1), 1–9.
- British Standard (2011a). *Cement. Composition, specifications and conformity criteria for common cements*. BS EN 197 Part 1:2011.
- British Standard (1980). *Method for Test for Making Concrete*. BS 3148:1980.
- British Standard (1991). *Methods for specifying concrete mixes*. BS 5328 Part 2:1991.
- British Standard (2002). *Mixing water for concrete. Specification for sampling, testing and assessing the suitability of water, including water recovered from processes in the concrete industry, as mixing water for concrete*. BS EN 1002:2002.
- British Standard (1975a). *Testing aggregates. Methods for determination of particle size and shape*. BS 812 Part 1:1975.
- British Standard (1975b). *Testing aggregates. Methods for determination of physical properties*. BS 812 Part 2:1975.
- British Standard (2011b). *Testing concrete. Method for determination of water absorption*. BS 1881 Part 122:2011.
- British Standard (1983). *Testing concrete. Method for making cubes from fresh concrete*. BS 1881 Part 108:1983.
- British Standard (1986). *Testing concrete. Methods for mixing and sampling fresh concrete in the laboratory*. BS 1881 Part 125:1986.
- British Standard (2009a). *Testing fresh concrete. Slump-test*. BS EN 12350 Part 2:2009.
- British Standard (2009b). *Testing hardened concrete. Compressive strength of test specimens*. BS EN 12390 Part 3:2009.
- British Standard (2009c). *Testing hardened concrete. Flexural strength of test specimens*. BS EN 12390 Part 5:2009.
- British Standard (2009d). *Testing hardened concrete. Making and curing specimens for strength tests*. BS EN 12390 Part 2:2009.
- British Standard (2009e). *Testing hardened concrete. Tensile splitting strength of test specimens*. BS EN 12350 Part 6:2009.
- Bunsell, A. R. (2009). *Handbook of tensile properties of textile and technical fibres*. Woodhead Publishing Limited.
- Burande, B. C. (2017). Utilization of paint sludge from automotive industries into

- valuable products. *International Journal of Recent Trends in Engineering and Research*. 513–519.
- Bureau, L., Alliche, A., Pilvin, P. and Pascal, S. (2001). Mechanical characterization of a styrene-butadiene modified mortar. *Materials Science and Engineering A*. 308(1–2), 233–240.
- Castillo, C. and Durrani, A. J. (1990). Effect of Transient High Temperature on High Strength Concrete. *ACI Materials Journal*. 87(1), 47–53.
- Chan, Y. N., Peng, G. F. and Anson, M. (1999). Residual strength and pore structure of high-strength concrete and normal strength concrete after exposure to high temperatures. *Cement and Concrete Composites*. 21(1), 23–27.
- Chandra, S., Berntsson, L. and Anderberg, Y. (1980). Some effects of polymer addition on the fire resistance of concrete. *Cement and Concrete Research*. 10(3), 367–375.
- Chandra, S. and Flodin, P. (1987). Interaction of polymers and organic admixtures on portland cement hydration. *Cement and Concrete Research*. 17(c), 875–890.
- Chandra, S. and Ohama, Y. (1994). *Polymer in concrete*. CRC Press.
- Charles, S. W., Cullen, F. C., Owen, N. L. and Williams, G. A. (1987). Infrared spectrum and rotational isomerism of acrylic acid. *Journal of Molecular Structure*. 157(1–3), 17–29.
- Chern, C.-S. (2008). *Principles and applications of emulsion polymerization*. John Wiley & Sons, Inc.
- Chung, D. D. L. (2004). Review : Use of polymers for cement-based structural. *Journal of Materials Science*. 39, 2973–2978.
- Ciullo, P. A. (1996). *Industrial minerals and their uses: A handbook and formulary*. Elsevier Science.
- Cocke, D. L. and Mollah, M. Y. (1993). The chemistry and leaching mechanisms of hazardous substances in cementations solidification /stabilization systems. In R.D. Spence (Ed.). *Chemistry and Microstructure of Solidified Waste Forms*. 187–242, Lewis Publishers Boca Raton, Florida.
- Colak, A., Çolak, A. and Colak, A. (2005). Properties of plain and latex modified Portland cement pastes and concretes with and without superplasticizer. *Cement and Concrete Research*. 35(8), 1510–1521.
- Collins, F. and Sanjayan, J. G. (2000). Effect of pore size distribution on drying shrinkage of alkali-activated slag concrete. *Cement and Concrete Research*.

- 30(9), 1401–1406.
- Concrete Society (1988). *Permeability testing of site concrete-a review of methods and experience*. Technical Report No.31.
- CRCG (2017). *Malaysian Paint & Coating Industry : An Overview*. 2017. Cardas Research Consulting Sdn. Bhd. Petaling Jaya, Selangor.
- Cree, D., Green, M. and Noumowé, A. (2013). Residual strength of concrete containing recycled materials after exposure to fire: A review. *Construction and Building Materials*. 45, 208–223.
- Decter, M. H. (1997). Durability concrete repair-important of compatibility and low shrinkage. *Construction and Building Materials*. I(5–6), 267–273.
- Devi, S. K. and Gopalakrishnan, A. N. (2016). Feasibility of making construction material using hazardous paint sludge. *International Journal of Emerging Technology in Computer Science & Electronics*. 22(2), 2–4.
- Dey, B. K., Hashim, M. A., Hasan, S. and Gupta, B. Sen (2004). Microfiltration of water-based paint effluents. *Advances in Environmental Research*. 8(3–4), 455–466.
- Dhiyaneshwaran, S., Ramanathan, P., Baskar, I. and Venkatasubramani, R. (2013). Study on durability characteristics of self-compacting concrete with fly ash. *Jordan Journal of Civil Engineering*. 7(3), 342–353.
- Diab, A. M., Elyamany, H. E. and Ali, A. H. (2013). Experimental investigation of the effect of latex solid/water ratio on latex modified co-matrix mechanical properties. *Alexandria Engineering Journal*. 52(1), 83–98.
- Dieter, U. and Koichi, T. (2002). *Polymer dispersions and their industrial applications*. Wiley-VCH, Weinheim,2002.
- DOE (2001). *Environmental Quality Act 1974*. Publications Section, Strategic Communications Division, Department of Environment Malaysia.
- DOE (2009). *Malaysia Environment Quality Report*. Publications Section, Strategic Communications Division, Department of Environment Malaysia.
- Dunn, A. S. (1982). *Emulsion polymerization*. Academic Press, New York.
- Dunn, D. J. and Beswick, R. H. D. (2002). *Natural and Synthetic Latex Polymers*. Rapra Technology Limited.
- Dursun, D. and Sengul, F. (2006). Waste minimization study in a solvent-based paint manufacturing plant. *Resources, Conservation and Recycling*. 47(4), 316–331.
- Duthinh, D. and Starnes, M. (2004). *Strength and ductility of concrete beams*

- reinforced with carbon fiber-reinforced polymer plates and steel*. National Institute of Standards and Technology.
- Ebewele, R. O. (2000). *Polymer science and technology*. CRC Press, Boca Raton, New York.
- Eguchi, K. and Teranishi, K. (2005). Prediction equation of drying shrinkage of concrete based on composite model. *Cement and Concrete Research*. 35(3), 483–493.
- Eliseeva, V. I., Ivanchev, S. S., Kuchanov, S. I. and Lebedev, A. V. (1981). *Emulsion polymerization and its applications in industry*. New York: Plenum Publishing Corporation.
- Erbil., H. Y. (2000). *Vinyl acetate emulsion polymerization and copolymerization with acrylic monomers*. (First Edit.). Boca Raton: CRC Press.
- Eren, F., Gödek, E., Keskinateş, M., Tosun-Felekoğlu, K. and Felekoğlu, B. (2017). Effects of latex modification on fresh state consistency, short term strength and long term transport properties of cement mortars. *Construction and Building Materials*. 133, 226–233.
- Faizuddin, S. and Ohama, Y. (2000). Properties of polymer modified mortar with silica fume. *The Indian Concrete Journal*. 467–470.
- Fazeli, A., Bakhtvar, F., Jahanshaloo, L., Che Sidik, N. A. and Bayat, A. E. (2016). Malaysia's stand on municipal solid waste conversion to energy: A review. *Renewable and Sustainable Energy Reviews*. 58, 1007–1016.
- Felicetti, R. (2004). Digital camera colorimetry for the assessment of fire damaged concrete. In *Fib Task Group 4.3 Workshop Fire Design of Concrete Structures: What now? What next?*. Milan, DEc. 2-4, 2004. 2004.
- Figovsky, O. and Beilin, D. (2014). *Advanced polymer concretes and compounds*. CRC Press, Taylor & Francis Group, Boca Raton.
- Fowler, D. W. (1999). Polymers in concrete: A vision for the 21st century. *Cement and Concrete Composites*. 21(5–6), 449–452.
- Fu, X. and Chung, D. D. L. (1998). Improving the bond strength of concrete to reinforcement by adding methylcellulose to concrete. *ACI Materials Journal*. 95 (5) p.601–608.
- Gemert, D. Van (2013). Synergies between polymers and cement concrete providing opportunities for sustainable construction. *Advanced Materials Research*. 687, 12–20.

- Gemert, D. Van, Czarnecki, L., Maultzsch, M., Schorn, H., Beeldens, A., Łukowski, P. and Knapen, E. (2005). Cement concrete and concrete–polymer composites: Two merging worlds. *Cement and Concrete Composites*. 27(9–10), 926–933.
- Georgali, B. and Tsakiridis, P. E. (2005). Microstructure of fire-damaged concrete. A case study. *Cement and Concrete Composites*. 27(2), 255–259.
- Golestaneh, M., Najafpour, G., Amini, G. and Beygi, M. (2013). Evaluation of chemical resistance of polymer concrete in corrosive environments. *Iranica Journal of Energy & Environment*. 4(3).
- Gomes, C. E. M. and Ferreira, O. P. (2005). Analyses of microstructural properties of VA/VeoVA copolymer modified cement pastes. *Polimeros Ciencia e Tecnologia*. 15, 193–198.
- Gomes, C. E. M., Ferreira, O. P. and Fernandes, M. R. (2005). Influence of vinyl acetate-versatic vinylester copolymer on the microstructural characteristics of cement pastes. *Materials Research*. 8(1), 51–56.
- Gougar, M. L. D., Scheetz, B. E. and Roy, D. M. (1996). Ettringite and csh portland cement phases for waste ion immobilization: A review. *Waste Management*. 16(4), 295–303.
- Goyal, A. and Agarwal, P. (2017). Use of co-polymer of styrene butadiene Rubber-a seismically innovative approach towards energy dissipation. *Procedia Engineering*. 173, 1800–1807.
- Grantham, M., Basheer, P. A. M., Magee, B. and Soutsos, M. (2014). *Concrete solutions: Proceeding of Concrete Solutions 5th International Conference on Concrete Repair, Belfast, Northern Ireland, 1-3 September 2014*.
- Guirguis, O. W. and Moselhey, M. T. H. (2012). Thermal and structural studies of poly (vinyl alcohol) and hydroxypropyl cellulose blends. *Natural Science*. 4(1), 57–67.
- Güneyisi, E., Gesolu, M. and Özbay, E. (2010). Strength and drying shrinkage properties of self-compacting concretes incorporating multi-system blended mineral admixtures. *Construction and Building Materials*. 24(10), 1878–1887.
- Guyot, A., Chu, F., Schneider, M., Graillat, C. and McKenna, T. F. (2002). High solid content latexes. *Progress in Polymer Science*. 27, 1573–1615.
- Hager, I. (2013). Behaviour of cement concrete at high temperature. *Bulletin of the Polish Academy of Sciences*. 61(March 2013), 1–10.
- Halliwell, S. M. (2015). *Polymers in Building and Construction*. [Online]. Rapra

- Review Reports. from
<https://books.google.com/books?id=vk8OBwAAQBAJ&pgis=1%5Cnhttp://link.springer.com/10.1007/978-3-319-08236-3>.
- Hansen, W. (1987). Drying shrinkage mechanisms in portland cement paste. *Journal of the American Ceramic Society*. 70(5), 323–328.
- Hare, C. H. (1992). The degradation of coatings by ultraviolet light and electromagnetic radiation. *Journal of Protective Coatings & Linings*. (May).
- Hobbs, D. W. (2003). Concrete deterioration: causes, diagnosis, and minimising risk. *International Materials Reviews*. 46(3), 117–144.
- Hwang, E. and Hwang, T. (2007). Comparison of physical properties of PAE polymer-modified mortars from recycled waste artificial marble and waste concrete fine aggregates. *Journal of Industrial and Engineering Chemistry*. 13(4), 585–591.
- Ibrahim, I. M., Ghaly, N. F., El-Shafie, M. and Rahman, A. M. M. A. El (2014). Effect of some polymers and asphalt emulsion on the deterioration of cement mortar and concrete. *Life Science Journal*. 11(10), 886–892.
- Idiart, A. E., López, C. M. and Carol, I. (2011). Modeling of drying shrinkage of concrete specimens at the meso-level. *Materials and Structures*. 44, 415–435.
- Illson, J. M. and Domone, P. L. J. (2001). *Construction materials*. (Third.). Spon Press.
- Ishida, T., Maekawa, K. and Kishi, T. (2007). Enhanced modeling of moisture equilibrium and transport in cementitious materials under arbitrary temperature and relative humidity history. *Cement and Concrete Research*. 37(4), 565–578.
- Ismail, M., Muhammad, B., Yatim, J. M., Noruzman, A. H. and Soon, Y. W. (2011a). Behavior of concrete with polymer additive at fresh and hardened states. *Procedia Engineering*. 14, 2230–2237.
- Ismail, M., Muhammad, B., Yussuf, A. A., Majid, Z. and Ismail, M. E. (2011b). Mechanical capabilities and fire endurance of natural rubber latex modified concrete. *Canadian Journal of Civil Engineering*. 38(6), 661–668.
- Ismail, Z. Z. and Al-Hashmi, E. A. (2011). Assessing the recycling potential of industrial wastewater to replace fresh water in concrete mixes: application of polyvinyl acetate resin wastewater. *Journal of Cleaner Production*. 19(2–3), 197–203.
- ISO (2012). *Fire resistance tests. Element of building construction*. ISO 834 Part

- 12:2012.
- ISO 124 (2008). *Determination of total solids content present in natural rubber latex*. United Kingdom: International Standard Organization (ISO 124).
- IUPAC (1972). Manual of symbols and terminology, appendix 2, part 1, Colloid and Surface Chemistry. *Journal Pure Application Chemical*. 31, 578.
- Jamin, N. C. and Mahmood, N. Z. (2015). Scheduled Waste Management in Malaysia: An Overview. *Advanced Materials Research*. 1113, 841–846.
- Jamshidi, M., Pakravan, H. R. and Pourkhorshidi, A. R. (2014). Application of polymer admixtures to modify concrete properties: Effects of polymer type and content. *Asian Journal of Civil Engineering*. 15(5), 779–787.
- Japanese Industrial Standard (2000). *Test methods for polymer-modified mortar*. JIS A 1171:2000.
- Jewell, L. L., Fasemore, O. A., Glasser, D., Hildebrandt, D., Heron, L., Van Wyk, N. and Cooray, B. (2004). Toward zero waste production in the paint industry. *Water SA*. 30(5), 643–647.
- Jiménez, F. J., Téllez, L., Valenzuela, M. A., Wohn, S. and Balmori, H. (2010). Effect of waste polyethylene addition on the properties of white portland cement. *Journal of Ceramic Processing Research*. 11(2), 22–26.
- Jupiter, T., Rashidi, A. H. and Ismail, I. (2010). Effect of seawater on the properties of epoxy modified concrete. *UNIMAS E-Journal of Civil Engineering*. 1(2), 1–8.
- Kalwane, U. B., Ghugal, Y. M. and Dahake, A. G. (2014). Elastic constants of polymer modified fiber reinforced concrete. *The Asian Review of Civil Engineering*. 3(2), 27–40.
- Karamyan, D. R., Segeeva, C. N., Beileryan, N. M., Voskanyann, P. S., Eritsyann, V. K. and Gevorkyan, L. A. (2004). Acid hydrolysis of vinyl acetate in an aqueous medium in the presence of non-ionogenic surfactants and polyvinyl alcohol. *International Polymer Science and Technology*. 31(4), 47–50.
- Kardon, J. B. (1997). Polymer modified concrete: Review. *Journals of Materials in Civil Engineering*. 9(2), 85–92.
- Kasapoglu, E. (2008). Polymer-based building materials: Effects of quality on durability. In *11DBMC International Conference on Durability of Building Materials and Components*. Istanbul, Turkey. 11-14 May 2008. 2008.
- Kažys, R. and Rekuviene, R. (2012). Viscosity and density measurement methods for

- polymer melts. *Ultrasound*. 66(4), 20–25.
- Kesalkar, V. P., Arukia, N. S., Sanghani, H. V and Jichkar, R. . (2017). Effect of poly vinyl acetate and poly vinyl alcohol as cement admixture on strength of concrete. *International Journal for Research in Applied Science & Engineering Technology*. 887(8), 2321–9653.
- Khan, A. and Zafar, N. S. (2011). Performance of blended and modified cements exposed to aggressive environments. *Interntional Conference on Durability of Building Materials and Components*. (September), 1–8.
- Khan, B. and Ullah, M. (2004). Effect of a retarding admixture on the setting time of cement pastes in hot weather. *Journal of King Abdulaziz University-Engineering Sciences*. 15(1), 63–79.
- Khan, K. A., Ahmad, I. and Alam, M. (2018). Effect of ethylene vinyl acetate (EVA) on the setting time of cement at different temperatures as well as on the mechanical strength of concrete. *Arabian Journal for Science and Engineering*.
- Kim, H. J., Park, J. Y., Suh, H. W., Cho, B. Y., Park, W. J. and Bae, S. C. (2019). Mechanical degradation and thermal decomposition of ethylene-vinyl acetate (EVA) polymer-modified cement mortar (PCM) exposed to high-temperature. *Sustainability (Switzerland)*. 11(2).
- Kim, H. J. and Park, W. J. (2017). Combustion and mechanical properties of polymer-modified cement mortar at high temperature. *Advances in Materials Science and Engineering*.
- Kim, H., Park, S. and Lee, S. (2016). Acoustic performance of resilient materials using acrylic polymer emulsion Resin. *Materials*. 9(7).
- Kim, J., Robertson, R. E. and Naaman, A. E. (1999). Structure and properties of poly (vinyl alcohol) -modified mortar and concrete. *Cement and Concrete Research*. 29, 407–415.
- Kim, Y.-Y., Lee, K.-M., Bang, J.-W. and Kwon, S.-J. (2014). Effect of w/c ratio on durability and porosity in cement mortar with constant cement amount. *Advances in Materials Science and Engineering*. 2014, 1–11.
- Kucche, K. J., Jamkar, S. S. and Sadgir, P. A. (2015). Quality of water for making concrete : A review of literature. *International Journal of Scientific and Research Publications*. 5(1), 1–10.
- Kumar, D. P., Eswaramoorthi, P. and Kumkuma, I. P. (2014). A comparative study on the strength of structural elements by incorporating waste latex paint in

- concrete. *International Journal of Engineering Research and Applications*. (January), 2248–9622.
- Kumar, M. A. and Bari, J. A. (2015). Flexural behaviour of polymer modified basalt fiber reinforced concrete- A review. *International Journal on Applications in Civil engineering Engineering*. 1(3), 1–5.
- Kumaran, M. K., Lackey, J. C., Normandin, N., Tariku, F. and van Reenen, D. (2004). Heat, air, and moisture transport properties of several North American bricks and mortar mixes. *Journal of Testing and Evaluation*. 32(5), 383–389.
- Kumbhare, M. B. (2014). Effect of initiator-monomer Ratio in polymerization of vinyl acetate. *International Journal of Chemical Sciences and Applications*. 5(2), 80–83.
- Kwan, A. K. H., Ho, J. C. M. and Pam, H. J. (2002). Flexural strength and ductility of reinforced concrete beams. *Proceedings of the ICE - Structures and Buildings*. 152(4), 361–369.
- Lambourne, R. and Strivens, T. A. (1999). *Paint and surface coatings: theory and practice*. (Second Edi.). Woodhead Publishing Limited.
- Larbi, J. . and Bijen, J. M. J. M. (1990). Interaction of polymers with portland cement during hydration: A study of the chemistry of the pore solution of polymer-modified cement systems. *Cement and Concrete Research*. 20(1), 139–147.
- Lee, B. J. and Kim, Y. Y. (2018). Durability of latex modified concrete mixed with a shrinkage reducing agent for bridge deck pavement. *International Journal of Concrete Structures and Materials*. 12(1).
- Lee, J.-H., Kim, H.-H., Park, S.-K., Oh, R.-O., Kim, H.-D. and Park, C.-G. (2018). Mechanical properties and durability of latex-modified fiber-reinforced concrete: A tunnel liner application. *Advances in Materials Science and Engineering*. 1–14.
- Leite, M. B., Filho, J. G. L. F. do and Lima, P. R. L. (2013). Workability study of concretes made with recycled mortar aggregate. *Materials and Structures/Materiaux et Constructions*. 46(10), 1765–1778.
- Lenart, M. (2015). Assessment of mortar shrinkage in aspect of organic and inorganic modifiers use. *Procedia Engineering*. 108, 309–315.
- Leong, Y. W., Abu Bakar, M. B., Ishak, Z. A. M., Ariffin, A. and Pukanszky, B. (2004). Comparison of the mechanical properties and interfacial interactions

- between talc, kaolin, and calcium carbonate filled polypropylene composites. *Journal of Applied Polymer Science*. 91(5), 3315–3326.
- Leopold, P. and Freese, S. D. (2009). *A simple guide to the chemistry, selection and use of chemicals for water and wastewater treatment*.
- Li, L., Wang, R. and Lu, Q. (2018). Influence of polymer latex on the setting time, mechanical properties and durability of calcium sulfoaluminate cement mortar. *Construction and Building Materials*. 169, 911–922.
- Li, M., Qian, C. and Sun, W. (2004). Mechanical properties of high-strength concrete after fire. *Cement and Concrete Research*. 34(6), 1001–1005.
- Liu, F., Wu, J., Chen, K. and Xue, D. (2010). Morphology study by using scanning electron microscopy. *Microscopy: Science, Technology, Applications and Education*. 1781–1792.
- Liu, S. F., Guo, S. J., Wang, P. M., Sifeng, L. I. U., Sijun, G. U. O. and Peiming, W. (2013). Influence of temperature on the hydration heat of polymer modified mortars. *Advanced MAterial Research*. 687, 130–135.
- Lorton, G. A. (1988). Hazardous waste minimization: Part III waste minimization in the paint and allied products industry. *Japca*. 38(4), 422–427.
- Lovell, P. . and El- Aasser, mohamed S. (1997). *Emulsion polymerization and emulsion p olymers*. John Wiley & Sons LTD.
- Luyben, M. L. and Tyréus, B. D. (1998). An industrial design/control study for the vinyl acetate monomer process. *Computers & Chemical Engineering*. 22(7–8), 867–877.
- Ma, Q., Guo, R., Zhao, Z., Lin, Z. and He, K. (2015). Mechanical properties of concrete at high temperature-A review. *Construction and Building Materials*. 93, 371–383.
- Ma, X., Zhou, B., Sheng, Y., Wang, C., Pan, Y., Ma, S. W. and Gao, Y. (2007). Preparation of calcium carbonate/poly(methyl methacrylate) composite microspheres by soaples emulsion polymerization. *Journal of Applied Polymer Science*. 105, 2925–2929.
- Madhani. B and Palson. P (2016). Comparative study of corrosion resistance of polymer modified concrete and concrete with corrosion inhibiting agent. *International Journal of Engineering Research and Technology*. 5(5).
- Manaf, L. A., Armi, M., Samah, A., Ilyana, N. and Zukki, M. (2009). Municipal solid waste management in Malaysia: Practices and challenges. *Waste*

- Management*. 29(11), 2902–2906.
- Mane, A. C. and Ghugal, Y. M. (2015). Polymer modified steel fiber concrete : Review. *International Journal of Engineering Research & Technology (IJERT)*. 4(04), 288–292.
- Maria, S. (2010). Methods for porosity measurement in lime-based mortars. *Construction and Building Materials*. 24(12), 2572–2578.
- Marinković, S., Radonjanin, V., Malešev, M. and Ignjatović, I. (2010). Comparative environmental assessment of natural and recycled aggregate concrete. *Waste Management*. 30(11), 2255–2264.
- McKeen, L. (2018). *The effect of sterilization on plastics and elastomers*. (Fourth Edi.). William Andrew.
- Mckeen, L. W. (2017). *Permeability properties of plastics and elastomers*. (Fourth Edi.). William Andrew Publishing.
- Medeiros, M. H. F. and Helene, P. (2009). Surface treatment of reinforced concrete in marine environment: Influence on chloride diffusion coefficient and capillary water absorption. *Construction and Building Materials*. 23(3), 1476–1484.
- Mehta, P. K. and Meryman, H. (2009). Tools for reducing carbon emissions due to cement consumption. *Structure Magazine*. (January), 11–15. from https://www.structuremag.org/wp-content/uploads/2014/08/C-BB-SustainableConcrete_MehtaMeryman-Jan091.pdf.
- Michler, G. H. (2008). Amorphous Polymer. In *Electron Microscopy of Polymers*. [Online]. 277–293, Springer Berlin Heidelberg. from <http://www.springer.com/la/book/9783540363507>.
- Min, H. and Song, Z. (2018). Investigation on the sulfuric acid corrosion mechanism for concrete in soaking environment. *Advances in Materials Science and Egnieering*.
- Mindness, S. and Young, J. . (1981). *Concrete*. Parentice- Hall, New Jersey.
- Mohammed, A., Nehdi, M. and Adawi, A. (2008). Recycling waste latex paint in concrete with added value. *ACI Materials Journal*. 105(4), 367–374.
- Mokhtar, M., Ta, G. C. and Murad, M. W. (2010). An essential step for environmental protection: Towards a sound chemical management system in Malaysia. *Journal of Chemical Health and Safety*. 17(5), 13–20.
- Momtazi, A. S., Khoshkbijari, R. K. and Mogharab, S. S. (2015). Polymers in concrete : Applications and specifications. *Journal of Natural and Social*

- Sciences*. 3(3), 62–72.
- Monteny, J., Belie, N. De and Taerwe, L. (2003). Resistance of different types of concrete mixtures to sulfuric acid. *Materials and Structures*.
- Montgomery, D. M., Sollars, C. J. and Perry, R. (1988). Cement-based solidification for the safe disposal of heavy metal contaminated sewage sludge. *Waste Management & Research*. 6(3), 217–226.
- Moodi, F., Kashi, A., Ramezani pour, A. A. and Pourebrahimi, M. (2018). Investigation on mechanical and durability properties of polymer and latex-modified concretes. *Construction and Building Materials*. 191, 145–154.
- Muhammad, B. and Ismail, M. (2012). Performance of natural rubber latex modified concrete in acidic and sulfated environments. *Construction and Building Materials*. 31, 129–134.
- Müller, H. S., Haist, M. and Vogel, M. (2014). Assessment of the sustainability potential of concrete and concrete structures considering their environmental impact, performance and lifetime. *Construction and Building Materials*. 67, 321–337.
- Muthukumar, M. and Mohan, D. (2004). Studies on polymer concretes based on optimized aggregate mix proportion. *European Polymer Journal*. 40(9), 2167–2177.
- Muwashee, R. S. (2018). Mechanical properties of polyvinyl acetate (PVA) concrete improved with silica fume. *International Journal of Civil Engineering and Technology*. 9(10), 763–770.
- Nabavi, F., Nejadi, S. and Samali, B. (2013). Experimental investigation on mix design and mechanical properties of polymer (latex) modified concrete. *Advanced Materials Research*. 687, 112–117.
- Naik, T. R., Singh, S. S. and Ramme, B. W. (2001). Time of setting influenced by inclusion of fly ash and chemical admixtures. In *The 7th International Conference on Fly Ash, Silica Fume, Slag and Natural Pozzolans in Concrete (CANMET/ACI)*. 2001, 393–413.
- Negim, E. S., Kozhamzharova, L., Khatib, J., Bekbayeva, L. and Williams, C. (2014). Effects of surfactants on the properties of mortar containing styrene/methacrylate superplasticizer. *Scientific World Journal*. 2014.
- Nehdi, M. and Sumner, J. (2003). Recycling waste latex paint in concrete. *Cement and Concrete Research*. 33(6), 857–863.

- Neville, A. M. (1981). *Properties of Concrete*. (4th Editio.). Pitman, London.
- Noushini, A., Vessalas, K., Arabian, G. and Samali, B. (2014). Drying shrinkage behaviour of fibre reinforced concrete incorporating polyvinyl alcohol fibres and fly ash. *Advances in Civil Engineering*. 2014, 1–10.
- Nu'man, A. and Hadithi, A. (2009). Flexural behaviour of polymer modified reinforced concrete beams. *Journal of Engineering and Development*. 13(1), 89–110.
- Nuttall, K. L., Gordon, W. H. and Ash, K. O. (1995). Inductively coupled plasma mass spectrometry for trace element analysis in the clinical laboratory. *Annals of Clinical and Laboratory Science*. 25(3), 264–271.
- Ohama, Y. (1995). *Handbook of polymer modified concrete and mortars: Properties and process technology*. Noyes Publication, Park Ridge, New Jersey.
- Ohama, Y. (1998). Polymer-based Admixtures. *Cement and Concrete Composites*. 20, 189–212.
- Ohama, Y. (1997). Recent progress in concrete-polymer composites. *Advanced Cement Based Materials*. 5(2), 31–40.
- Ohama, Y. and Kan, S. (1982). Effects of specimen size on strength and drying shrinkage of modified concrete. *The International Journal of Cement Composites and Lightweight Concrete*. 1138(4), 229–233.
- Oyawa, W. O., Sugiura, K. and Watanabe, E. (2004). Flexural response of polymer concrete filled steel beams. *Construction and Building Materials*. 18(6), 367–376.
- Padsalgikar, A. D. (2017). *Introduction to Plastics*. [Online]. Elsevier Inc. from <http://dx.doi.org/10.1016/B978-0-323-47357-6.00021-0>.
- Palson, P. and Vidivelli, B. (2017). Mechanical properties of latex modified concrete with silica fume. *International Journal of Civil Engineering and Technology*. 8(9), 701–710.
- Parghi, A. and Alam, M. S. (2016). Effects of curing regimes on the mechanical properties and durability of polymer-modified mortars – an experimental investigation. *Journal of Sustainable Cement-Based Materials*. 5(5), 324–347.
- Pascal, S., Alliche, a and Pilvin, P. (2004). Mechanical behaviour of polymer modified mortars. *Materials Science and Engineering: A*. 380(1–2), 1–8.
- PCA (2018). *Durability*. [Online]. 2018. Portland Cement Association. from <https://www.cement.org/learn/concrete-technology/durability>.

- Piasta, J., Sawicz, Z. and Rudzinski, L. (1984). Changes in the structure of hardened cement paste due to high temperature. *Materiaux et Constructions*. 17(4), 291–296.
- Prasad, G. R. and Rao, K. V. (2018). Experimental studies on behavior of polymer modified steel fiber reinforced concrete. *International Journal of Mechanical Engineering and Technology*. 7(5), 4578–4593.
- Ramachandran, V. S. (1981). *Concrete Science: A Treatise on Current Research*. Heyden & Son Ltd., Great Britain.
- Ramakrishnan, V. (1992). *Latex modified concretes and mortars. A synthesis of highway practice. NCHRP Synthesis 179*. Transportation Research Board, National Research council, Washington D.C.
- Ramli, M. and Tabassi, A. A. (2012). Effects of polymer modification on the permeability of cement mortars under different curing conditions: A correlational study that includes pore distributions, water absorption and compressive strength. *Construction and Building Materials*. 28(1), 561–570.
- Ramli, M., Tabassi, A. A. and Hoe, K. W. (2013). Porosity, pore structure and water absorption of polymer-modified mortars: An experimental study under different curing conditions. *Composites Part B: Engineering*. 55, 221–233.
- Randall, P. M. (1992). Pollution prevention methods in the surface coating industry. *Journal of Hazardous Materials*. 29(2), 275–295.
- Rashid, Z. A., Alias, A. B., Aris, M. J., El-Harbawi, M., Rahman, N. A. and Som, A. M. (2010). Hazardous waste management : current status and future strategies in Malaysia. *International Journal of Environmental Engineering*. 2, 139–158.
- Ravindrarajah, R. S. (1985). Casting delay on workability and strength of concrete. *International Journal of Cement Composites and Lightweight Concrete*. 7(2), 109–113.
- Ray, I., Gupta, a. P. and Biswas, M. (1994). Effect of latex and superplasticiser on Portland cement mortar in the fresh state. *Cement and Concrete Composites*. 16(4), 309–316.
- Reg, A. (2010). Asia/Pasific paint consumption will exceed 20 million tonnes in 2014. *Focus on Pigments*. 10, 1–3.
- Renault, F., Sancey, B., Badot, P. and Crini, G. (2009). Chitosan for coagulation / flocculation processes – An eco-friendly approach. *European Polymer Journal*. 45(5), 1337–1348.

- Riaz, U. and Ashraf, S. M. (2015). Characterization of polymer blends with FTIR spectroscopy. In *Characterization of Polymer Blends: Miscibility, Morphology, and Interfaces*. 625–678, Wiley VCH.
- Ribeiro, M. S. S., Gonçalves, A. F. and Branco, F. A. B. (2008). Styrene-butadiene polymer action on compressive and tensile strengths of cement mortars. *Materials and Structures/Materiaux et Constructions*. 41(7), 1263–1273.
- Riley, A. (2012). Basics of polymer chemistry for packaging materials. In *Packaging Technology*. 262–286, Woodhead Publishing Limited.
- Rodriguez, M., López, C. M. and Carol, I. (2015). Modeling of heat and mass transfer induced by high temperature in concrete. In *XIII International Conference on Computational Plasticity. Fundamentals and Applications COMPLAS XIII*. 2015, 346–353.
- Rogosic, M., Mencer, H. . and Gomzi, Z. (1996). Polydispersity index and molecular weight distributions of polymers. *European Polymer Journal*. 32. No. II, 1337–1344.
- Rossignolo, J. A. and Agnesini, M. V. C. (2004). Durability of polymer-modified lightweight aggregate concrete. *Cement and Concrete Composites*. 26(4), 375–380.
- Saeed, M. O. O., Hassan, M. N. N., Mujeebu, M. A. A., Osman, M., Nasir, M. and Mujeebu, M. A. A. (2009). Assessment of municipal solid waste generation and recyclable materials potential in Kuala Lumpur, Malaysia. *Waste Management*. 29(7), 2209–13.
- Safiuddin, M. and Hearn, N. (2005). Comparison of ASTM saturation techniques for measuring the permeable porosity of concrete. *Cement and Concrete Research*. 35(5), 1008–1013.
- Safiuddin, M., Jumaat, M. Z., Salam, M. A., Islam, M. S. and Hashim, R. (2010). Utilization of solid wastes in construction materials. *International Journal of the Physical Sciences*. 5(13), 1952–1963.
- Said, A. M., Quiroz, O. I., Hatchett, D. W. and Elgawady, M. (2016). Latex-modified concrete overlays using waste paint. *Construction and Building Materials*. 123, 191–197.
- Saija, L. M. (1995). Waterproofing of portland cement mortars with a specially designed polyacrylic latex. *Cement and Concrete Research*. 25(3), 503–509.
- Sakata, K. (1983). A study on moisture diffusion in drying and drying shrinkage of

- concrete. *Cement and Concrete Research*. 13, 1211–1214.
- Salvesen, R. H. (1989). Treatment: Solvent waste streams. In *USEPA seminar publication solvent waste reduction alternatives*. 105–108.
- Santo, C. E., Vilar, V. J. P., Botelho, C. M. S., Bhatnagar, A., Kumar, E. and Boaventura, R. A. R. (2012). Optimization of coagulation – flocculation and flotation parameters for the treatment of a petroleum refinery effluent from a Portuguese plant. *Chemical Engineering Journal*. 183, 117–123.
- Sarac, A., Elgin, C. and Şen, P. Y. (2016). Synthesis and characterization of water and poly(vinyl acetate) based wood adhesives. In A. Méndez-Vilas, A. Solano, E. (Ed.). *Polymer Science: Research Advances, Practical Applications and Educational Aspects*. 537–543.
- Sarac, A. and Turhan, K. (2009). The mechanical properties of water- based emulsion polymers: Effect of reaction conditions. In *Innovation in Chemical Biology*. 405–409, Springer, Dordrecht.
- Schulze, J. (1999). Influence of water-cement ratio and cement content on the properties of polymer-modified mortars. *Cement and Concrete Research*. 29(6), 909–915.
- Sharma, R. and Bansa, P. P. (2016). Use of different forms of waste plastic in concrete - a review. *Journal of Cleaner Production*. 112, 473–482.
- Sher, F., Malik, A. and Liu, H. (2013). Industrial polymer effluent treatment by chemical coagulation and flocculation. *Biochemical Pharmacology*. 1(4), 684–689.
- Siddique, R. and Singh, G. (2011). Utilization of waste foundry sand (WFS) in concrete manufacturing. *Resources, Conservation and Recycling*. 55(11), 885–892.
- Siddiqui, M. N., Gondal, M. A. and Redhwi, H. H. (2008). Identification of different type of polymers in plastic waste. *Journal of Environmental Science and Health Part A*. 43, 1303–1310.
- Silva, D. A. A., Roman, H. R. R. and Gleize, P. J. P. J. P. (2002). Evidences of chemical interaction between EVA and hydrating Portland cement. *Cement and Concrete Research*. 32(9), 1383–1390.
- Sivakumar, M. V. N. (2011). Effect of Polymer modification on mechanical and structural properties of concrete – An experimental investigation. *International Journal of Civil Engineering Structural Engineering*. 1(4), 732–740.

- Son, S.-W. and Yeon, J. H. (2012). Mechanical properties of acrylic polymer concrete containing methacrylic acid as an additive. *Construction and Building Materials*. 37, 669–679.
- Sotiriadis, K., Tupý, M., Žižková, N., Petránek, V. and Materials, A. (2014). Acid attack on cement mortars modified with rubber aggregates and EVA polymer binder. *International Journal of Civil, Environmental, Structural, Construction and Acritectural Engineering*. 8(6), 616–620.
- Spence, R. D. and Shi, C. (2004). *Stabilization and Solidification of Hazardous, Radioactive and Mixed Wastes*. CRC Press, Boca Raton, FL, US.
- Spiesz, P. and Brouwers, H. J. H. (2012). Efficiency of the saturation of concrete with liquid under vacuum conditions. In *18th Internationale Baustoffagung 'ibautil'.12-15 September 2012, Weimar, Deutschland (pp. 2-0601)*. Bauhaus-University Weimar, Germany.
- Steward, P. A., Hearn, J. and Wilkinson, M. C. (2000). An overview of polymer latex film formation and properties. *Advances in colloid and interface science*. 86(3), 195–267.
- Stojanović, Z., Marković, S. and Uskoković, D. (2012). Measurement of particle size distribution using laser light diffraction. *Technics-New Materials*. 21 p.1–15.
- Stokes, D. J. (2008). *Principles and practice of variable pressure/environmental scanning electron microscopy*. John Wiley & Sons LTD.
- Su, Z., Bijen, J. M. J. M. and Larbi, J. A. (1991). The influence of polymer modification on the adhesion of cement pastes to aggregates. *Cement and Concrete Research*. 21, 727–736.
- Susilorini, R. M. I. R., Hardjasaputra, H., Sri, T., Galih, H., Reksa, W. S., Ginanjar, H. and Joko, S. (2014). The advantage of natural polymer modified mortar with seaweed: Green construction material innovation for sustainable concrete. *Procedia Engineering*. 95, 419–425.
- Susilorini, R. M. I. R., Santosa, B., Rejeki, V. G. S., Riangsari, M. F. D. and Hananta, Y. D. (2017). The increase of compressive strength of natural polymer modified concrete with *Moringa oleifera*. *AIP Conference Proceedings*. 1818(March), 10–15.
- Swamp, S. and Schoff, C. K. (1993). A survey of surfactants in coatings technology. *Progress in Organic Coatings*. 23, 1–22.
- Topçu, I. B. and Uygunoglu, T. (2016). Sustainability of using waste rubber in

- concrete. In *Sustainability of Construction Materials*. [Online]. 597–623, Elsevier Ltd. from <http://dx.doi.org/10.1016/B978-0-08-100370-1.00023-8>.
- Torgal, F. P. and Ding, Y. (2013). Concrete with polymeric wastes. In *Eco-Efficient Concrete*. 311–339.
- Tosic, N., Marinkovic, S. and Stojanovic, A. (2017). Sustainability of the concrete industry: Current trends and future outlook. *Tehnika*. 72(1), 38–44.
- Tukimat, N. N. A., Sarbini, N. N., Ibrahim, I. S., Ma, C. K. and Mutusamy, K. (2017). Fresh and hardened state of polymer modified concrete and mortars – A review. In *MATEC Web of Conferences*. 2017, 1025.
- Vargha, V. and Truter, P. (2005). Biodegradable polymers by reactive blending trans-esterification of thermoplastic starch with poly(vinyl acetate) and poly(vinyl acetate-co-butyl acrylate). *European Polymer Journal*. 41(4), 715–726.
- Wang, J., Zhang, S., Yu, H., Kong, X., Wang, X. and Gu, Z. (2005). Study of cement mortars modified by emulsifier-free latexes. *Cement and Concrete Composites*. 27(9–10), 920–925.
- Wang, R., Ma, D. and Wang, P. M. (2013). Waterproof performance of polymer-modified cement mortar. *Advanced Materials Research*. 687, 213–218.
- Wang, R. and Shi, X. (2014). Influence of styrene-acrylic ester dispersion on the early hydration of cement. *Advances in Materials Science and Engineering*. 2014, 1–12.
- Wang, R. and Wang, P. (2010). Function of styrene-acrylic ester copolymer latex in cement mortar. *Materials and Structures/Materiaux et Constructions*. 43(4), 443–451.
- WHO (2011). *Guidelines for drinking water Quality*. (4rd Editio.). World Health Organization, Geneva 2011.
- Winter, N. B. (2012). *Scanning electron microscopy of cement and concrete*. WHD Microanalysis Consultants Ltd.
- Won, J. P., Kang, H. B., Lee, S. J., Lee, S. W. and Kang, J. W. (2011). Thermal characteristics of high-strength polymer-cement composites with lightweight aggregates and polypropylene fiber. *Construction and Building Materials*. 25(10), 3810–3819.
- Wu, K. and Zhang, D. (2018). Cement-based composite material. In: Yi, Xiao-Su, Du, Shanyi, Zhang, Litong (Eds). In *Composite Materials Engineering*. 489–

- 529, Springer, Singapore.
- Yamak, H. B. (2013). Emulsion polymerization : Effects of polymerization variables on the properties of vinyl acetate based emulsion polymers. In Yilmaz, F. (Ed.). *Polymer Sciences*. 35–70, InTech.
- Yamak, H. B. and Yildirim, H. (2013). Improvement of film properties of vinyl acetate based emulsion polymers by using different types of maleic acid diesters. *Progress in Organic Coatings*. 76(12), 1874–1878.
- Yilmaz, A. E., Boncukcuođlu, R. and Kocakerim, M. M. (2007). A quantitative comparison between electrocoagulation and chemical coagulation for boron removal from boron-containing solution. *Journal Hazardous Materials*. 149, 475–481.
- Yunus, M. N. M. and Kadir, K. Z. A. (2006). The development of municipal solid waste treatment technology based on refuse derived fuel and bio-gasification integration. *Proceedings of the International Symposium on Renewable Energy: Environment Protection and Energy Solution Malaysia*. 762.
- Zhang, J., Hou, D. and Gao, Y. (2012). Integrative studies on autogenous and drying shrinkages of concrete at early-age. *Advances in Structural Engineering*. 15(7), 1041–1051.
- Zhang, S., Li, L. and Kumar, A. (2008). *Materials Characterization Techniques*. CRC Press, Boca Raton, FL, US.
- Zheng, L., Sundaram, H. S., Wei, Z., Li, C. and Yuan, Z. (2017). Applications of zwitterionic polymers. *Reactive and Functional Polymers*. 118, 51–61.
- Zhou, W. and Wang, Z. L. (2006). *Scanning microscopy for nanotechnology*. In: Zhou W., W. Z. L. (eds) S. M. for N. (Ed.). Springer, New York, NY.
- Zulkarnain, F. and Suleiman, M. Z. (2016). The innovative performance of polymer modified cement systems for use in infrastructure applications. *International Journal of Engineering Research and Development*. 12(10), 8–14.