

PREPARATION, MODIFICATION AND CHARACTERIZATION OF ADSORBENTS  
FROM PALM FATTY ACID DISTILLATES (PFAD) FOR DYE REMOVAL FROM  
AQUEOUS SOLUTIONS

HAMZAT BASHIR ADEREMI

A thesis submitted in fulfilment of the  
requirements for the award of the degree of  
Doctor of Philosophy

School of Chemical and Energy Engineering  
Faculty of Engineering  
Universiti Teknologi Malaysia

OCTOBER 2019

## DEDICATION

To my beloved wife, daughters, and sons,  
for understanding the many nights, I was away thanks!  
To God be the glory.

## ACKNOWLEDGEMENT

With reference and supplication to most high God. I am sincerely grateful to the Most High God through His only son, Jesus Christ for given me the opportunity and privilege to successfully complete this PhD study. He has been with me throughout in thin and thick. I am grateful sir. I have no enough words in my heart through my mouth to show how grateful I am to my supervisor, Dr Muhammad Abbas Ahmad Zaini for his untiring efforts, support and encouragement. He tutored me from basis to a PhD stuff I am today. He is wonderful. His name and deposits he put in me cannot easily be eroded away with passage of time.

My wonderful wife, Magaret Hamzat and our children Victor, Kelly, Virtue, Success and Miracle, I am grateful for your love support and understanding. I cannot forget to mention my friends in our “CLEAR LAB”. Friends like Roy, Hakimi Shafiq, Helmi, Norimie Raja, Henry, Lijah Rosdi, Francis from ATBU in Nigeria, Alex Jok. My friends from Petroleum department, Augustine Agi, Jefry, and Hafiz. I also want to appreciate my church, Redeem church of God Skudai branch Johor. My friends and pastors like pastors Goke, Kayode, Babalola, Mathew and many more. I cannot forget my friends and colleagues Dr M.D Jibrin, Dr Funsho Akande, Dr Kabir Abdallah, Engr. Jibrin Waziri, Engr Tobias, Engr Omale, Engr Muazu, Engr Musa Lawal, Engr Kabir Offa and others I cannot remember now for their contributions and support to the success of this study.

I acknowledge the support of Kaduna Polytechnic, Kaduna, Nigeria for the opportunity given to me to study at the prestigious University Technology Malaysia.

## ABSTRACT

Adsorption is an effective approach in the treatment of wastewater as it utilizes low cost adsorbent, no sludge, and is simple to operate. Palm fatty acid distillates is a suitable precursor of adsorbents due to its high carbon content, less commercial value and abundant availability. This work is aimed to evaluate the adsorption properties of adsorbents prepared from palm fatty acid distillates for methylene blue and congo red removal. Adsorbents with more yield were selected with the aid of response surface methodology (RSM) using Box Behnken design (BBD) approach. The resultant adsorbents were characterized for ultimate analysis, thermogravimetric analysis, surface area analysis, Fourier transform infrared spectroscopy analysis, surface morphology analysis, X-ray spectroscopic property, Boehm titration and point of zero charge of adsorbents. The surface area was between 212-222 m<sup>2</sup>/g, pore volume was 7.0 x10<sup>-7</sup>-2.8 x10<sup>-7</sup> m<sup>3</sup>/g, pore size 51-122 Å and the pore structure was majorly micropore, Boehm titration showed the presence of carboxylic, lactonic, phenolic and basic groups on the surface. The pH of adsorbent was 5 while the point of zero charge was 5.5. The adsorption of methylene blue and congo red were studied at varying concentrations (5 – 300 mg/L), contact time (10min – 72 h), temperature (30 -70 °C) and pH (2 -10). RSM software using BBD approach was utilized to determine the optimum adsorption capacity of methylene blue and congo red by adsorbents and to know interrelationships and interactions among the factors that enhance maximum adsorption. The optimum adsorption of methylene blue was 47.8 mg/g at maximum initial concentration of 100 mg/L, temperature of 70 °C, and contact time of 18 h and pH of 6 compared with experimental value of maximum methylene blue adsorption of 56 mg/g at concentration of 100 mg/g, temperature of 70 °C, time of 36 h and pH of 5 was found to be suitable for methylene blue adsorption. Congo red adsorption was 189 mg/g at concentration of 300 mg/L, temperature of 70 °C contact time of 15 h and pH of 6. The experimental value of congo red optimum is 237 mg/g at concentration of 300 mg/L, temperature of 70 °C, time of 30 h and pH of 5. The model is suitable for congo red. The adsorption of methylene blue and congo red dyes by adsorbents was well described by Langmuir and Temkin models. The adsorption of dyes fitted into both pseudo-first order and pseudo-second order kinetic models, suggesting physicochemical adsorption. Weber-Morris or intraparticle diffusion model reveals that the intraparticle diffusion is involved, but it is not the only rate-limiting step. Boyd model shows that film diffusion is the controlling mechanism for both methylene blue and congo red adsorption. The dyes adsorption is thermodynamically endothermic and spontaneous in nature.

## ABSTRAK

Penjerapan merupakan pendekatan yang berkesan bagi rawatan air sisa kerana ia menggunakan penjerap kos rendah, tidak menjana enapcemar, dan mudah untuk digunakan. Asid lemak sawit tersuling adalah bahan penjerap yang sesuai kerana mempunyai kandungan karbon yang tinggi, kurang nilai komersial dan banyak tersedia. Kajian ini bertujuan untuk menilai sifat penjerapan penjerap yang dirumus daripada rawatan asid lemak sawit tersuling untuk penyingkiran metilena biru dan kongo merah. Penjerap dengan hasil jerapan yang tinggi telah dipilih dengan bantuan kaedah sambutan permukaan (RSM) menggunakan pendekatan Box-Behnken (BBD). Penjerap terhasil dicirikan untuk analisis muktamad, analisis termogravimetrik, analisis kawasan permukaan, spektroskopi inframerah jelmaan Fourier, analisis kumpulan berfungsi, analisis morfologi permukaan, sifat spektroskopik sinar-X, titrasi Boehm dan titik sifar caj penjerap. Luas permukaan penjerap adalah antara 212-222 m<sup>2</sup>/g, isipadu liang adalah 7.0 x10<sup>-7</sup>-2.8 x10<sup>-7</sup> m<sup>3</sup>/g, saiz liang adalah 51 -122 Å dan struktur utama liang adalah liang-liang mikro, titrasi Boehm menunjukkan kewujudan kumpulan karbosilik, laktonik, fenolik dan kumpulan-kumpulan asas atas permukaan. pH penjerap adalah 5 manakala titik sifar caj adalah 5.5. Penjerapan metilena biru dan kongo merah dikaji pada pelbagai kepekatan (5 - 300 mg/L), masa sentuhan (10 min - 72 jam), suhu (30 - 70 °C) dan pH (2 - 10) yang berbeza-beza. Perisian RSM dengan pendekatan BBD telah digunakan untuk menentukan kapasiti penjerapan yang optimum untuk metilena biru dan kongo merah dan untuk mengetahui hubungan dan interaksi antara faktor-faktor yang meningkatkan penjerapan maksimum. Penjerapan optimum metilena biru adalah 47 mg/g pada kepekatan awal maksimum 100 mg/L, suhu 70 °C, 18 jam masa sentuhan dan nilai pH 6 berbanding dengan nilai kajian dimana penjerapan maksimum metilena biru adalah 56 mg/g pada kepekatan 100 mg/g, suhu 70 °C, 36 jam dan pH 5 adalah sesuai untuk penjerapan metilena biru. Penjerapan kongo merah adalah 189 mg/g pada kepekatan 300 mg/L, suhu 70 °C, masa sentuhan 15 jam, dan pH 6. Nilai kajian menunjukkan penjerapan optimum kongo merah adalah 237 mg/g pada kepekatan 300 mg/L, suhu 70 °C, masa sentuhan 30 jam dan pH 5. Model ini sesuai untuk penjerapan kongo merah. Penjerapan metilena biru dan kongo merah oleh penjerap juga telah dijelaskan dengan baik oleh model Langmuir dan Temkin. Penjerapan pencelup ini sesuai untuk kedua-dua model kinetik pseudo tertib pertama dan tertib kedua, mencadangkan penjerapan fizikokimia. Weber-Morris atau model resapan intrazarah mendedahkan bahawa penjerapan intrazarah juga terlibat, tetapi ia bukan hanya langkah yang menghad kadar. Model Boyd menunjukkan bahawa penyerapan lapisan merupakan mekanisme kawalan bagi penjerapan metilena biru dan kongo merah. Penjerapan pencelup adalah endotermik secara termodinamik dan bersifat spontan.

## TABLE OF CONTENT

	<b>TITLE</b>	<b>PAGE</b>
	<b>DECLARATION</b>	<b>ii</b>
	<b>DEDICATION</b>	<b>iii</b>
	<b>ACKNOWLEDGEMENT</b>	<b>iv</b>
	<b>ABSTRACT</b>	<b>v</b>
	<b>ABSTRAK</b>	<b>vi</b>
	<b>TABLE OF CONTENT</b>	<b>vii</b>
	<b>LIST OF TABLES</b>	<b>xiii</b>
	<b>LIST OF FIGURES</b>	<b>xvi</b>
	<b>LIST OF APPENDICES</b>	<b>xx</b>
<b>1</b>	<b>INTRODUCTION</b>	<b>1</b>
	1.1 Background of Study	1
	1.2 Problem Statement	4
	1.3 Aim and Objectives	5
	1.4 Scope of the Study	6
	1.5 Significance of the Study	7
	1.6 Organization of the Study	7
<b>2</b>	<b>LITERATURE REVIEW</b>	<b>9</b>
	2.1 Introduction	9
	2.2 Water Contaminants	9
	2.2.1 Biodegradable Pollutants	10
	2.2.2 Non-Biodegradable Pollutants	10

2.3	Dyes	11
2.3.1	Types and Applications of Dyes	13
2.3.2	Methylene blue Dye	16
2.3.3	Congo Red Dye	18
2.4	Methods of Dyes Removal from Wastewater	19
2.5	Adsorption	21
2.6	Factors Affecting Adsorption	22
2.7	Types of Adsorption	24
2.8	Mechanisms of Dye Adsorption	25
2.9	Adsorbents for Dye Removal	28
2.9.1	Activated Carbon	28
2.9.2	Adsorbent from Agricultural Wastes	29
2.9.3	Adsorbent from Modified Agricultural Waste	30
2.9.4	Natural and Clay Adsorbents	31
2.9.5	Industrial Waste/By-product as Source of Adsorbent	33
2.10	Adsorbent Modification	34
2.10.1	Acid Modification	35
2.10.2	Basic Modification	36
2.10.3	Heat Modification	37
2.10.4	Microwave Modification	37
2.10.5	Other Methods of Modification	37
2.11	Adsorbents from Palm Fatty Acids Distillates (PFAD)	39
2.12	Zinc Chloride as Adsorbent Modifier	39
2.13	Adsorbent Properties	42
2.13.1	CHNOS Elemental Composition Property	42

2.13.2	Surface Area Properties	43
2.13.3	Thermogravimetric property	43
2.13.4	Surface Functional Group property	44
2.13.5	Morphological Properties	44
2.13.6	Energy Dispersive X-Ray Spectroscopic (EDS) Property	45
2.13.7	Surface Group (Boehm Titration) Property	45
2.13.8	Point of Zero Charge (PZC) Property	46
2.14	Palm Fatty Acid Distillates (PFAD)	46
2.15	Uses of PFAD	48
2.16	Optimization Using Design Expert Software (Version 7.1.6, Stat-Ease, Inc., Minneapolis, USA)	49
2.17	Adsorption Isotherm Models	51
2.17.1	Langmuir Adsorption Isotherm Model	52
2.17.2	Freundlich Adsorption Isotherm Model	53
2.17.3	Temkin Model	53
2.18	Adsorption Kinetic Model	54
2.18.1	Pseudo-first Order Model	54
2.18.2	Pseudo- second Order Model	55
2.18.3	Intra- particle Diffusion Model	55
2.19	Adsorption Thermodynamic	56
<b>3</b>	<b>METHODOLOGY</b>	<b>57</b>
3.1	Introduction	57
3.2	Materials	59
3.3	Adsorbates	59
3.4	Adsorbents Preparation	60
3.4.1	Ultimate Analysis of PFAD	60
3.4.2	Carbonization	60

3.4.3	Adsorbent Modification with ZnCl <sub>2</sub>	61
3.4.4	Experimental Design and Optimization of Yield using Design Expert Software	64
3.5	Characterization of Materials	66
3.5.1	Ultimate Analysis	66
3.5.2	Surface Area Analysis	66
3.5.3	Functional Groups Determination	67
3.5.4	Surface Morphology Analysis	67
3.5.5	Fixed Carbon Content by TGA	67
3.5.6	pH Determination	68
3.5.7	Boehm Titration	68
3.5.8	Point of Zero Charge (PZC) Analysis	69
3.6	Methylene Blue and Congo Red Adsorption	69
3.6.1	Effect of Concentration	71
3.6.2	Effect of Solution pH	72
3.6.3	Effect of Contact Time	72
3.6.4	Effect of Temperature	73
3.7	Justification of Selection of Zinc Chloride as Adsorbent Modifier	73
<b>4</b>	<b>RESULTS AND DISCUSSION</b>	<b>75</b>
4.1	Overview	75
4.2	Adsorbents Preparation from PFAD	75
4.3	Characteristics of PFAD, Adsorbents Prepared from PFAD and Modified Adsorbents	77
4.3.1	Yield and Elemental Composition	77
4.3.2	Thermogravimetric Profiles	78
4.3.3	Surface Functional Groups	80

4.3.4	BET- Surface Area of Adsorbents Prepared from PFAD	83
4.4	Adsorbent Modification with Zinc Chloride	84
4.5	Further Characterization of Modified Adsorbent	85
4.5.1	Surface Morphology Analysis	85
4.5.2	Energy Dispersive X-Ray Spectroscopy (EDS)	88
4.5.3	Boehm Titration	90
4.5.4	Point of Zero Charge of Adsorbents ( $pH_{PZC}$ )	91
4.6	Justification for Selection of Adsorbents over Carbon Char for Adsorption Studies	92
4.7	Adsorption Studies	93
4.7.1	Methylene Blue Adsorption by $ZnCl_2$ -Modified PFAD Adsorbents	93
4.7.2	Congo Red Adsorption	103
4.8	Factors Affecting Adsorption	111
4.8.1	Effect of Contact Time	111
4.8.2	Effect of solution pH	115
4.8.3	Effect of Temperature	118
4.8.4	Effect of Initial Concentration	119
4.9	Optimization of Methylene Blue and Congo Red Adsorption by Adsorbents	121
4.9.1	Box–Behnken Experimental Design	122
4.9.2	Analysis of Variance (ANOVA) for Methylene Blue Adsorption	128
4.9.3	Adequacy of Model for Methylene Blue Adsorption	131
4.9.4	Optimization of Methylene Blue Adsorption using the Desirability Function	134
4.9.5	Analysis of Variance (ANOVA) for Congo Red Adsorption	135

4.9.6	Adequacy of Model for Congo Red Adsorption	139
4.9.7	Optimization of Congo Red Adsorption using the Desirability Function	142
4.10	Equilibrium Adsorption Description by Model	143
4.10.1	Equilibrium Adsorption Isotherm models	144
4.10.2	Kinetics Models	148
4.10.3	Adsorption Thermodynamics	152
<b>5</b>	<b>CONCLUSION AND RECOMMENDATION</b>	<b>157</b>
5.1	Conclusions	157
5.2	Recommendations	159
	<b>REFERENCES</b>	<b>169</b>
	<b>LIST OF PUBLICATION</b>	<b>181</b>

## LIST OF TABLES

<b>TABLE NO.</b>	<b>TITLE</b>	<b>PAGE</b>
Table 2.1	Types of dyes and their health effects	12
Table 2.2	Types and applications of dyes (Benkhayab et al, 2017)	13
Table 2.3	Classification of dyes by chemical structure ((Yagub et al.,, 2018a)	15
Table 2.4	Properties of methylene blue (Swan & Zaini, 2019; Wang et al., 2017)	17
Table 2.5	Properties of congo red (Farias et al., 2018a; Swan & Zaini, 2019)	19
Table 2.6	Comparisons, advantages and disadvantages of different methods of dyes removal from waste water (Farias et al., 2018b; Katheresan et al., 2018b; Nurul-Ruhayu et al., 2015)	20
Table 2.7	Effects of different parameters on the adsorption process (Katheresan et al., 2018a)	23
Table 2.8	Types of dye adsorption (Katheresan et al., 2018a)	25
Table 2.9	Adsorbents from agricultural waste materials for dye removal.	29
Table 2.10	Modified agricultural waste adsorbent for dye removal	31
Table 2.11	Natural and low cost adsorbents (Sadegh et al., 2017)	32
Table 2.12	Adsorbents from palm oil industry for dye removal (Faridah et al., 2018)	33
Table 2.13	Modifying effects of zinc chloride on precursors for adsorbent preparation (Ozdemir et al., 2014)	41
Table 2.14	Fatty acid composition of PFAD (Tay, 2009).	47
Table 2.15	Distribution of participating palm oil refineries in PFAD production from various states in Malaysia (Tay, 2009).	47
Table 2.16	Present use and the future use of PFAD	49

Table 2.17	Selected experimental domain for each of the independent variables	50
Table 3.1	Designation of PFAD-based adsorbents	62
Table 3.2	Experimental design matrix in terms of actual factors and yield	66
Table 4.1	Adsorbents and their nomenclature.	76
Table 4.2	Ultimate analysis, colour and yield % of PFAD, adsorbents from PFAD and selected adsorbents prepared from the mixture of PFAD and Zinc chloride.	78
Table 4.3	BET Surface area of Chars and modified adsorbents	84
Table 4.4	Results of Boehm titration for selected adsorbents	91
Table 4.5	BET Surface area, yield % and methylene blue adsorption of chars and adsorbents	93
Table 4.6	Optimum conditions for methylene blue and congo red removal	112
Table 4.7	Independent variables for congo red and their levels used for Box-Behnken design (BBD)	126
Table 4.8	Box benkhen design matrix for CR removal	127
Table 4.9	ANOVA of variable factors for linear model of methylene blue adsorption by adsorbent AD5Z3T2	134
Table 4.10	ANOVA of deviation for linear model of methylene blue adsorption by adsorbent AD5Z3T2	135
Table 4.11	ANOVA of variable factors for linear model of congo red adsorption by adsorbent AD5Z3T2	143
Table 4.12	ANOVA of deviation for linear model of congo red adsorption by adsorbent AD5Z3T2	144
Table 4.13	Isotherm constants for methylene blue adsorption by adsorbents	150
Table 4.14	Isotherm constants for congo red adsorption by adsorbents	151
Table 4.15	Comparison of maximum adsorption capacity (Q <sub>m</sub> ) of methylene blue and congo red on different adsorbents	153

Table 4.16	Kinetics constants of pseudo-first-order and pseudo-second-order models	155
Table 4.17	Kinetics constants for intra-particle diffusion and Boyd's model	157
Table 4.18	Thermodynamics parameters of adsorbents for methylene blue adsorption	161
Table 4.19	Thermodynamics parameters of adsorbents for congo red adsorption	163

## LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
Figure 2.1	Methylene Blue chemical structure	17
Figure 2.2	Congo red chemical structure	18
Figure 2.3	Diffusion of molecules from liquid phase to the surface of adsorbent	22
Figure 2.4	Step –wise stages of dye adsorption onto adsorbent surface	27
Figure 2.5	Mechanisms of adsorption between methylene blue dye and adsorbent (Gunes, 2016).	27
Figure 2.6	Carbon surfaces functionalities attributed to different oxygen functional groups: (a) aromatic C=C stretching, (b) and (c) carboxyl-carbonates, (d) carboxylic acid, (e) lactone (4-membered ring), (f) lactone (5-membered ring), (g) ether bridge, (h) cyclic ethers, (i) cyclic anhydride-membered ring), (j) cyclic anhydride (5-membered ring), (k) quinone, (l) phenol, (m) alcohol, and (n) ketone.	36
Figure 2.7	Flow chart for the design expert (response surface methodology)	51
Figure 3.1	Process flow diagram for the methodology	58
Figure 3.2	Raw PFAD as obtained from industry before carbonization	59
Figure 3.3	PFAD char after carbonization process	61
Figure 3.4	Set-up for heating and mixing of the mixture of PFAD and Zinc Chloride before carbonization	64
Figure 3.5	Calibration curve for methylene blue	70
Figure 3.6	Calibration curve for congo red.	71

Figure 4.1	TGA curves for (a) PFAD, (b) C1 and (c) C2 prepared from PFAD	80
Figure 4.2	TGA curves for (a) AD6Z3T2 (b) AD5Z3T0.5 (c) AD5Z3T2 and (d) AD6Z3T0.5	80
Figure 4.3	FTIR spectra of (a) PFAD and PFAD-based chars, (b) C1 and (c) C2.	83
Figure 4.4	FTIR spectra of (a) AD5Z3T2 (b) AD6Z3T2 (c) AD5Z3T0.5 and (d) AD6Z3T0.5	83
Figure 4.5	SEM images of (a) AD5Z3T0.5 (b) AD5Z3T2 (c) AD6Z3T0.5 (d) AD6Z3T2	88
Figure 4.6	EDS results of (a) AD5Z3T0.5 (b) AD6Z3T2	90
Figure 4.7	pH <sub>pzc</sub> of ZnCl <sub>2</sub> modified - PFAD based adsorbents	92
Figure 4.8	Methylene blue adsorption by adsorbents prepared at 500 °C and 0.5 hour carbonization.	96
Figure 4.9	Methylene blue adsorption by adsorbents prepared at 500 °C and one hour carbonization	97
Figure 4.10	Methylene blue adsorption by adsorbents prepared at 500° C and two hours of carbonization	98
Figure 4.11	Methylene blue adsorption at higher initial concentrations by selected adsorbents prepared at 500 °C.	99
Figure 4.12	Methylene blue adsorption by adsorbents prepared at 600 °C and half hour of carbonization.	101
Figure 4.13	Methylene blue adsorption by adsorbents prepared at 600 °C and one hour of carbonization.	103
Figure 4.14	Methylene blue adsorption by adsorbents prepared at 600° C and two hours carbonization.	104
Figure 4.15	Methylene blue adsorption at higher initial concentration by adsorbents prepared at 600 °C.	105
Figure 4.16	Congo red adsorption by adsorbents prepared at 500 °C and 0.5 hour carbonization.	106
Figure 4.17	Congo red adsorption by adsorbents prepared at 500 °C and one hour carbonization.	107

Figure 4.18	Congo red adsorption by adsorbents prepared at 500 °C and two hours carbonization.	108
Figure 4.19	Congo red adsorption by adsorbents prepared at 600 °C and 0.5 hour carbonization.	109
Figure 4.20	Congo red adsorption by adsorbents prepared at 600 °C and one hour carbonization.	110
Figure 4.21	Congo red adsorption by adsorbents prepared at 600 °C and two hours of carbonization.	111
Figure 4.22	Schematic illustration of methylene blue adsorption on positively charged adsorbent	112
Figure 4.23	Effect of time on methylene blue adsorption at initial concentration of 5 mg/L on adsorbents AD5Z3T0.5, AD5Z3T2, AD6Z3T0.5 and AD6Z3T2.	114
Figure 4.24	Effect of time on methylene blue adsorption at initial concentration of 10 mg/L on adsorbents AD5Z3T0.5, AD5Z3T2, AD6Z3T0.5 and AD6Z3T2	115
Figure 4.25	Effect of time on congo red adsorption at initial concentration of 10 mg/L on adsorbents AD5Z3T0.5, AD5Z3T2, AD6Z3T0.5 and AD6Z3T2.	116
Figure 4.26	Effect of time on congo red adsorption at initial concentration of 50 mg/L on adsorbents AD5Z3T0.5, AD5Z3T2, AD6Z3T0.5 and AD6Z3T2	116
Figure 4.27	Effect of initial pH on adsorption of methylene blue onto adsorbents	118
Figure 4.28	Effect of initial pH on adsorption of congo red onto adsorbents	120
Figure 4.29	Effect of temperature on the equilibrium removal of methylene blue by adsorbents	122
Figure 4.30	Effect of temperature on the equilibrium removal of congo red by adsorbents	123
Figure 4.31	Effect of initial concentration of methylene blue on its adsorption by adsorbents predicted by Langmuir model	124
Figure 4.32	Effect of initial concentration of congo red on its adsorption by adsorbents predicted by Langmuir model.	125

Figure 4.33	3D of methylene blue adsorption by adsorbent AD5Z3T2	136
Figure 4.34	Normal probability plot of residual for methylene blue adsorption by adsorbent AD5Z3T2.	137
Figure 4.35	Plot of residual against predicted response of methylene blue adsorption by adsorbent AD5Z3T2.	138
Figure 4.36	Comparison between the actual values and the predicted values of RSM model on methylene adsorption by adsorbent AD5Z3T2.	139
Figure 4.37	Prediction by model for optimum adsorption of methylene blue by adsorbent AD5Z3T2	140
Figure 4.38	3D of congo red adsorption by adsorbent AD5Z3T2	145
Figure 4.39	Normal probability plot of residual for congo red adsorption by adsorbent AD5Z3T2.	146
Figure 4.40	Plot of residual against predicted response of congo red adsorption by adsorbent AD5Z3T2.	147
Figure 4.41	Comparison between the actual values and the predicted values of RSM model on congo red adsorption by adsorbent AD5Z3T2.	148
Figure 4.42	Prediction by model for optimum adsorption of methylene blue by adsorbent AD5Z3T2	149

## LIST OF APPENDICES

<b>APPENDIX</b>	<b>TITLE</b>	<b>PAGE</b>
Appendix A	Table of $\text{pH}_{\text{pzc}}$ for selected adsorbent	179
Appendix B	Selected adsorbents for RSM, Box behnken design approach	181
Appendix C	Effect of temperature of adsorption on congo red adsorption at different initial concentration	183
Appendix D	Summary of $R^2$ of congo red adsorption by adsorbents	185

# CHAPTER 1

## INTRODUCTION

### 1.1 Background of Study

Industrial growth, urbanization expansion and general increase in world population have led to increase in waste generation from industry as a result of the increase in industrial production activities to meet the ever-increasing demands for industrial products for man's use and consumption. These have contributed greatly to surface water and underground water becoming contaminated, harmful and polluted in most countries of the world with Malaysia not being an exception (Afroz *et al*, 2014; Afroz & Rahman, 2017; Alsaffar *et al*, 2016; Nurul-Ruhayu *et al* 2015).

In Malaysia, industries that produce appreciable volumes of wastewater include refining and petrochemical industries, palm oil and palm oil refinery industries, poultry and meat processing industries, chemical and fertilizer companies, paper and fiber industries, textile, steel mills, mineral processing industries and a host of others. Malaysia has undergone a period of rapid growth in the manufacturing sector since the 1960s and is continuing to attract new industries to the country. This growth has been accompanied by a corresponding increase in the number of industries generating hazardous waste. The contribution of the manufacturing industry to the Gross Domestic Product increased from 11% in 1966 to 24% in 1988. In 1987 Malaysian industry produced nearly 400,000 m<sup>3</sup> of hazardous waste, more than half coming from the states of Selangor and Penang (Yang *et al.*, 2016; Aja, *et al* 2016; Ong *et al* 2018).

Water pollution has therefore become a serious problem to mankind and the ecosystem (Chen *et al*, 2016; Dai *et al.*, 2018). Different techniques of wastewater treatment have been suggested and applied in the past decades. Adsorption has been a

preferred method for obvious reasons of low cost, simplicity of equipment and process, versatility and easy way of operation (Anastopoulos *et al.*, 2017; Bhatnagar & Anastopoulos, 2017; Nasrullah *et al.*, 2019). Low cost adsorbent materials can be obtained from different sources namely agricultural waste source, natural source, industrial waste/by-products source and agro-industrial waste/by-products source.

Agricultural waste is obtained from production of residues in agricultural and forestry processing. Examples are husks, straw, grouts and crumbs. The large quantity of agricultural wastes has many advantages in wastewater treatment such as low cost, environmental friendliness, chemical stability, abundant source, short regeneration cycle and green energy. Additionally, their surface has large specific area and high porosity. has made adsorption easier. Also their cell structures contain some active chemicals like pectin, hemicellulose, cellulose and lignin which could react with some chemical ions in waste water for an easy removal (Abdelhafez & Li, 2016; Basu *et al.*, 2017; Guiza, 2017; Qu *et al.*, 2018; Saxena *et al.*, 2017).

Natural clay minerals are considered as adsorbents because they are abundant natural resources, low cost and great capacity for adsorption and ion exchange. Clay materials with layer structures are the preferred materials for adsorbent production. The adsorption capacity of clay minerals emanates from the negative charge of their surface structure and can adsorb positively charged ions in the sewage. Moreover, adsorption properties emanated from high surface area and good porosity. Over many years, the preparation and utilization of clay has attracted researchers' interest and the interactions between pollutants and clay particles have been studied. Clay minerals can effectively adsorb both organic and inorganic pollutants (Devi & Saroha, 2017; Uddin, 2017).

Industrial waste has been used to prepare adsorbents due to its low cost, rich sources and wide distribution. Sludge, red mud fly ash etc. are common samples of industrial waste. Chemical treatment or modification on these wastes can enhance their adsorption capacity, can equally be used to adsorb hazardous chemicals from waste water (Gwenzi *et al.*, 2017; Giraldo *et al.*, 2014; Simate *et al.*, 2016). Industrial waste can also be used to produce adsorbents for dyes removal from waste industrial water (Silva *et al.*, 2018).

Activated carbon has been used for waste water treatment for a long period of time, research is gradually changing towards developing low-cost agro-industrial wastes/by-products based adsorbents such as palm kernel shell, palm oil mill effluent, EFB, coconut waste, fly ash, slag sludge, palm fatty acid distillates (PFAD), etc.(Devi & Saroha, 2017; Hafshejani *et al.*, 2016; Faridah *et al.*, 2018; Hidayu & Muda, 2016; Runtti, 2016; Tay, 2009; Wirasnita *et al.*, 2014).

There are large amount of agricultural wastes and industrial by-products that create environmental challenges in various form (soil, air and water) (Deng *et al.*, 2015). Agro industrial wastes/by-products are produced from industries that use agricultural produce as raw material for the production activities. The waste/by-products from such companies are called agro industrial wastes. Ineffective treatment of such waste and availability may cause serious environmental challenges (Anastopoulos *et al.*, 2017). The treatment methods available are expensive, complex and can easily cause secondary pollution. Most of these by-products can be transformed into reuse materials. This will reduce pollution challenge to a large extent (Li *et al.*, 2017; Omo-Okoro *et al.*, 2018; Silva *et a.*, 2018a) . The focus of this study is the conversion of palm fatty acid distillates (PFAD), a semi-solid by-product obtained in the course of converting crude palm oil to refined vegetable oil by palm oil refinery companies, to adsorbents for the removal of dyes from wastewater.

Thus, the use of low-cost adsorbents derived from industrial by-products for waste removal from waters is desirable. The industrial by-products from palm oil refinery industries are abundantly available and cheap and are underutilized as a result of growth and expansion in palm oil processing and refining industries. This explains the choice of the by- product from palm oil refinery industry, i.e., palm fatty acid distillates (PFAD), for the production of low-cost adsorbents for the treatment of waste water as the main focus of this research work

## 1.2 Problem Statement

Increase in the operations and activities of industries in order to meet the demand of ever growing population and industrial consumptions of raw materials have led to the increase in waste or by-products generation of palm oil and palm oil refinery industries. Industrial wastes from this sector of production are on the increase and currently under-utilized and in recent years have become a serious environmental challenge due to introduction of more federal and state legislation regulating their disposal

In the same vein, industrial wastewater containing dyes are a serious health and environmental risk. Most dyes used in textile industries are stable to light and are not biologically degradable. In order to minimize the risk of pollution problems from such effluents, it is important to adequately treat them before discharging them to the environment. Research activities are ongoing for some years now to develop cheaper and more effective adsorbents. As agricultural waste and industrial by-products are cheaper and available, activities towards different alternative materials for adsorbents have increased (Bhatnagar *et al.*, 2015). Clay materials like, zeolites kaolinite bentonite, perlite (Ruiz *et al.*, 2014). Agricultural waste materials like pulp, corn cob, rice husk, coconut shell; industrial wastes/by-products like palm fatty acid distillates, palm kernel cake, waste carbon cyclodextrin, cotton are used (Acquah *et al.*, 2016; Hadi, *et al.*, 2015; Simate *et al.*, 2016). Biological processes are not considered to be the best method for the removal of waste from the industrial wastewater. Lately, adsorption processes have begun to gain considerable importance in the treatment of industrial wastewater. Adsorbents are very effective and widely used due to their excellent adsorption ability, cost and availability (Sze, *et al.*, 2015). Currently, by-products from industries have not been fully exploited for adsorbents preparation for pollution control, this explains why this study focusses on palm fatty acid distillates (PFAD), a by-product from palm oil refinery for pollutants removal.

Adsorption has been discovered to be the cheap and widely used method in wastewater treatment and superior to chemical and physical treatment methods in terms of ability to remove non-biodegradable contaminants from wastewaters (Bhatnagar *et al.*, 2015). The reasons being that the raw materials for production are abundant, cheap and

simple at the same time the adsorption capacity is very high. Some adsorbents have low yield and low adsorption capacity, this explains why adsorbents are exposed to physical, chemical or combination of both methods in order to increase the yield and adsorption capacities. Palm fatty acid distillate is treated chemically in order to increase the yield and adsorption capacities of adsorbents prepared from it.

In an attempt to utilize the benefit associated with adsorbents, the use of abundantly, locally available, low cost adsorbent derived from palm oil refinery by-products are proposed in this study. In addition, the low cost adsorbent proposed as single use material to avoid regeneration problems. After use, the loaded adsorbent could be disposed of by land filling or incineration. The precursor, being a new source of preparing adsorbent, the performance evaluation and the effect of parametric variables on the performance and the characteristic properties of the adsorbent will be a subject of study in this research work.

### **1.3 Aim and Objectives**

This research work is aimed at evaluating the adsorption capacity and performance of adsorbents produced from palm fatty acid distillates (PFAD) in the removal of dyes from aqueous solutions.

The specific objectives are;

- I. To prepare and characterized adsorbents from palm fatty acid distillates (PFAD) by carbonization and chemical modification with zinc chloride at temperature range of 500 °C-600 °C and compare the characteristic properties.
- II. To evaluate the variables leading to the optimum production of adsorbents by using response surface methodology (RSM) and design of experiment (DOE).
- III. To assess the efficiency of adsorbents for methylene blue and congo red removal at different initial concentrations, contact times, solution pH and temperatures by using design of experiment approach using Box Behnken Design method (BBD).

- IV. To evaluate the adsorption equilibria, kinetics and thermodynamics of dyes adsorption.

#### **1.4 Scope of the Study**

Adsorbents were prepared from PFAD by carbonizing the precursor to temperature range of 500-600 ° C for the period of 0.5-1h. After, another set of adsorbents were prepared from the precursor by mixing the precursor with zinc chloride as a modifier at different mixing ratio of PFAD and zinc chloride. These various mixture were then carbonized at the same temperature range of 500-600 °C and varying the time of carbonization between 0.5h and 2h. All the adsorbents prepared from the two processes were characterized and the results of characterization were compared.

Response surface methodology (RSM) feature of Design Expert software (version 7.1.6, Stat-Ease, Inc., Minneapolis, USA) was used to design the experimental runs in order to reduce the number of experiments. The software was used to determine the effect of variables leading to optimum adsorption performance of adsorbents prepared. The effect of temperature, the effect of time and the effect of mixing ratio of precursor and zinc chloride were studied.

The effect of adsorbent dosage contact time between the adsorbents and adsorbates, temperature and initial concentrations of methylene blue and congo red on efficiency of adsorbents in removing dyes from solution were also studied.

The adsorption equilibria, kinetics and thermodynamics of dyes adsorption were evaluated. Isotherm models of Langmuir, Freundlich, and Temkin were used to check the nature of the adsorption. Pseudo-first order, pseudo-second order, intraparticle diffusion and Boyd models were used to predict the kinetics and the rate order of reaction. The thermodynamic behaviour of the process were equally studied and the entropy, enthalpy and the Gibbs energy of the processes were evaluated.

## **1.5 Significance of the Study**

Malaysia, a big producer of palm oil and refined oil products in the world has a large number of palm oil refinery industries that convert the oil produced into domestic and industrial raw materials for other associated companies. A large quantity of palm oil and refined oil are also exported to other countries. This gives rise to production of PFAD and continuous increase in production of waste and by-products as the production increases yearly. The use of available, cheap and abundant wastes for production of adsorbents- for subsequent use in the treatment of waste water generated by the industries in Malaysia will go a long way in combating environmental pollution challenges and waste water management which helps in environmental sustainability and to overcome in combating the potential health challenge associated with waste water from industries. It will also serve as source of revenue generation and job creation in the country. It will equally help the ever growing palm oil industries in their waste management as well as enhancing and improving on their production process and technology. More so, carbon adsorption technology is a better and more effective way for water treatment application as it is known to be cheapest treatment method and especially in treating non-biodegradable metals in waste water. The prominent advantage of adsorbents is its characteristic properties in removing wide range of toxic elements to a non-detectable level and also its ability for specific organic and inorganic substance removal.

## **1.6 Organization of the Study**

This thesis comprises of five chapters. In each chapter, the relevant subjects were discussed as follows: The background of the study discussed in chapter one. The problems prompted this study was highlighted. The objective, scope, and significance of this research were also stated. Chapter two focuses on the reviews of relevant and related literature to the study area. The preparation processes of adsorbents and their modifications for dye removal from wastewater. The use of high temperature environment for adsorbents preparation, modification strategies and the use of relevant software for optimization of the production of adsorbents were explored. Chapter three consists of selection of equipment

and materials, the methodology employed and steps followed in accomplishing the objectives of the research work. The procedures involved the production of bio-char, characterization of the raw materials, biochar and the produced modified adsorbents, activation process with zinc chloride and adsorption studies. Adsorption isotherms and kinetics equations were introduced to describe the experimental data. The thermodynamics properties and the use of design expert software for the optimization of process parameters were highlighted. In the same vein, methylene blue and congo red dyes adsorption were elaborated. In this chapter various characterization techniques were also explained. Chapter four presents the results of using palm fatty acid distillates (PFAD) for the preparation, modification and characterization of adsorbents at different environmental conditions. It also focused on the physicochemical properties of the modified and unmodified adsorbents. Experimental results in relation to the adsorption of both basic and acidic dyes by the adsorbents, and their correlation with the empirical models and optimization were verified accordingly. In chapter five, the findings from this research work were presented and recommendations were made for future work

## REFERENCES

- Abd wafti, N. S. (2017). Activated carbon from oil palm biomass as potential adsorbent for palm oil mill effluent treatment. *Journal of Oil Palm Research*, 29(2), 278–290.
- Abdelhafez, A. A., & Li, J. (2016). Removal of Pb(II) from aqueous solution by using biochars derived from sugar cane bagasse and orange peel. *Journal of the Taiwan Institute of Chemical Engineers*, 61, 367–375.
- Acquah, C., Yon, L. S., Tuah, Z., Ngee, N. L., & Danquah, M. K. (2016). Synthesis and performance analysis of oil palm ash (OPA) based adsorbent as a palm oil bleaching material, *Journal of Oil Cleaner Production*, 139, 1098-1104.
- Adegoke, K. A., & Bello, O. S. (2015). Dye sequestration using agricultural wastes as adsorbents. *Water Resources and Industry*, 12, 8-24.
- Adeleke, O. A., Latiff, A. A. A., Saphira, M. R., Daud, Z., Ismail, N., Aziz, N. A. A., Hijab, M. (2019). Locally Derived Activated Carbon From Domestic, Agricultural and Industrial Wastes for the Treatment of Palm Oil Mill Effluent. *Nanotechnology in Water and Wastewater Treatment*, 35–62.
- Afroz, R., Masud, M. M., Akhtar, R., & Duasa, J. B. (2014). Water pollution: Challenges and future direction for water resource management policies in malaysia. *Environment and Urbanization Asia*, 5(1), 63–81.
- Afroz, R., & Rahman, A. (2017). Health impact of river water pollution in Malaysia. *International Journal of Advanced and Applied Sciences*, 4(5), 78–85.
- Agarwal, S., Sadegh, H., Monajjemi, M., Hamdy, A. S., Ali, G. A. M., Memar, A. O. H., Gupta, V. K. (2016). Efficient removal of toxic bromothymol blue and methylene blue from wastewater by polyvinyl alcohol. *Journal of Molecular Liquids*, 218, 191–197.
- Ahmad Zaini, M. A., Chiew Ngiik, T., Kamaruddin, M. J., Mohd. Setapar, S. H., & Che Yunus, M. A. (2014). Zinc Chloride-activated Waste Carbon Powder for Decolourization of Methylene Blue. *Jurnal Teknologi*, 67(2).
- Ahmaruzzaman, M. (2011). Industrial wastes as low-cost potential adsorbents for the treatment of wastewater laden with heavy metals. *Advances in Colloid and Interface Science*. 166(1-2), 36-59.

- Al-Baidhany, J. H., & Al-Salihy, S. T. (2016). Removal of methylene blue dye from aqueous solution by using commercial granular activated carbon with different types of adsorbents. *Mesop. Environ. J*, 2(22), 1–11.
- Al-Degs, Y. S., El-Barghouthi, M. I., El-Sheikh, A. H., & Walker, G. M. (2008). Effect of solution pH, ionic strength, and temperature on adsorption behavior of reactive dyes on activated carbon. *Dyes and Pigments*, 77(1), 16–23.
- Ali, I., Asim, M., & Khan, T. A. (2012). Low cost adsorbents for the removal of organic pollutants from wastewater. *Journal of Environmental Management*, 113, 170-183.
- Alsaffar, M. S., Jaafar, M., & Kabir, N. (2016). Evaluation of heavy metals in surface water of major rivers in Penang , Malaysia. *International Journal of Environmental Sciences*, 6(5), 657–669.
- Anastopoulos, I., Bhatnagar, A., Hameed, B. H., Ok, Y. S., & Omirou, M. (2017). A review on waste-derived adsorbents from sugar industry for pollutant removal in water and wastewater. *Journal of Molecular Liquids*, 240, 179–188.
- Ayawei, N., Ekubo, A. T., Wankasi, D., & Dikio, E. D. (2015). Adsorption of Congo Red by Ni/Al-CO<sub>3</sub>: Equilibrium, Thermodynamic and Kinetic Studies. *Oriental Journal of Chemistry*, 31(3), 1307–1318.
- Barakat, M. A. (2011). New trends in removing heavy metals from industrial wastewater. *Arabian Journal of Chemistry*, 4(4), 361–377.
- Basu, M., Guha, A. K., & Ray, L. (2017). Adsorption Behavior of Cadmium on Husk of Lentil. *Process Safety and Environmental Protection*, 106, 11–22.
- Basu, P., & Basu, P. (2018). Torrefaction. *Biomass Gasification, Pyrolysis and Torrefaction*, 93–154.
- Beltrame, K. K., Cazetta, A. L., de Souza, P. S. C., Spessato, L., Silva, T. L., & Almeida, V. C. (2018). Adsorption of caffeine on mesoporous activated carbon fibers prepared from pineapple plant leaves. *Ecotoxicology and Environmental Safety*, 147, 64–71.
- Bhatnagar, A., & Anastopoulos, I. (2017). Adsorptive removal of bisphenol A (BPA) from aqueous solution: A review. *Chemosphere*, 168, 885–902.
- Bhatnagar, A., Hogland, W., Marques, M., & Sillanpää, M. (2013). An overview of the modification methods of activated carbon for its water treatment applications. *Chemical Engineering Journal*, 219, 499-511.

- Bhatnagar, A., Sillanpää, M., & Witek-Krowiak, A. (2015). Agricultural waste peels as versatile biomass for water purification - A review. *Chemical Engineering Journal*, 270, 244-271.
- Bouabidi, Z. B., El-Naas, M. H., Cortes, D., & McKay, G. (2018). Steel-Making dust as a potential adsorbent for the removal of lead (II) from an aqueous solution. *Chemical Engineering Journal*, 334, 837–844.
- Boumediene, M., Benaïssa, H., George, B., Molina, S., & Merlin, A. (2018). Effects of pH and ionic strength on methylene blue removal from synthetic aqueous solutions by sorption onto orange peel and desorption study. *J. Mater. Environ. Sci*, 9(6), 1700–1711.
- Budi, E., Nasbey, H., Yuniarti, B. D. P., Nurmayatri, Y., Fahdiana, J., & Budi, A. S. (2014). Pore structure of the activated coconut shell charcoal carbon (pp. 130–133).
- Chen, Y., Wang, F., Duan, L., Yang, H., & Gao, J. (2016). Tetracycline adsorption onto rice husk ash, an agricultural waste: Its kinetic and thermodynamic studies. *Journal of Molecular Liquids*, 222, 487–494.
- Dai, Y., Sun, Q., Wang, W., Lu, L., Liu, M., Li, J., Zhang, Y. (2018). Utilizations of agricultural waste as adsorbent for the removal of contaminants: A review. *Chemosphere*, 211, 235–253.
- De Gisi, S., Lofrano, G., Grassi, M., & Notarnicola, M. (2016). Characteristics and adsorption capacities of low-cost sorbents for wastewater treatment: A review. *Sustainable Materials and Technologies*, 9, 10-40.
- Deng, S., Nie, Y., Du, Z., Huang, Q., Meng, P., B. W.-J. 2015, U. (2015). r adsorption of perfluorooctane sulfonate and perfluorooctanoate by bamboo-derived granular activated carbon. *J. Hazard Mater*, 282, 150-7.
- Devi, P., & Saroha, A. K. (2017). Utilization of sludge based adsorbents for the removal of various pollutants: A review. *Science of The Total Environment*, 578, 16–33.
- Divband Hafshejani, L., Hooshmand, A., Naseri, A. A., Mohammadi, A. S., Abbasi, F., & Bhatnagar, A. (2016). Removal of nitrate from aqueous solution by modified sugarcane bagasse biochar. *Ecological Engineering*, 95, 101–111. 5
- Durotoye, T. O., Adeyemi, A. A., Omole, D. O., & Onakunle, O. (2018). Impact assessment of wastewater discharge from a textile industry in Lagos, Nigeria. *Cogent Engineering*, 5(1), 1–11.
- Farias, R. S. de, Buarque, H. L. de B., Cruz, M. R. da, Cardoso, L. M. F., Gondim, T. de A., Paulo, V. R. de, ... Paulo, V. R. de. (2018a). Adsorption of congo red dye from

- aqueous solution onto amino-functionalized silica gel. *Engenharia Sanitaria e Ambiental*, 23(6), 1053–1060.
- Faridah, M. M., Wan Ibrahim, W. A., Nodeh, H. R., Sutirman, Z. A., Ting, N. N., & Sanagi, M. M. (2018). Recent advances in the preparation of oil palm waste-based adsorbents for removal of environmental pollutants. *Malaysian Journal of Analytical Sciences*. (22), 175-184.
- Fegousse, A., El Gaidoumi, A., Miyah, Y., El Mountassir, R., & Lahrichi, A. (2019). Pineapple Bark Performance in Dyes Adsorption: Optimization by the Central Composite Design. *Journal of Chemistry*, 2019, 1–11.
- Ganiyu, S. A., Ajumobi, O. O., Lateef, S. A., Sulaiman, K. O., Bakare, I. A., Qamaruddin, M., & Alhooshani, K. (2017). Boron-doped activated carbon as efficient and selective adsorbent for ultra-deep desulfurization of 4,6-dimethyldibenzothiophene. *Chemical Engineering Journal*, 321, 651–661.
- Goswami, M., & Phukan, P. (2017). Enhanced adsorption of cationic dyes using sulfonic acid modified activated carbon. *Journal of Environmental Chemical Engineering*, 5(4), 3508–3517.
- Grammelis, P., Margaritis, N., & Karampinis, E. (2016). Solid fuel types for energy generation: Coal and fossil carbon-derivative solid fuels. *Fuel Flexible Energy Generation*, 29–58.
- Gratisito, M. K. B., Panyathanmaporn, T., Chumnanklang, R.-A., Sirinuntawittaya, N., & Dutta, A. (2008). Production of activated carbon from coconut shell: Optimization using response surface methodology. *Bioresource Technology*, 99(11), 4887–4895.
- Guiza, S. (2017). Biosorption of heavy metal from aqueous solution using cellulosic waste orange peel. *Ecological Engineering*, 99, 134–140.
- Gunes, G. K. & E. (2016). Desalination and Water Treatment. *Desalination and Water Treatment*, 15(1944–3994), 7085–7097.
- Gupta, V. K., Carrott, P. J. M., Ribeiro Carrott, M. M. L., & Suhas. (2009). Low-Cost Adsorbents: Growing Approach to Wastewater Treatment—a Review. *Critical Reviews in Environmental Science and Technology*, 39(10), 783–842.
- Gwenzi, W., Chaukura, N., Noubactep, C., & Mukome, F. N. D. (2017). Biochar-based water treatment systems as a potential low-cost and sustainable technology for clean water provision. *Journal of Environmental Management*. 197, 732-749.

- Hadi, P., Xu, M., Ning, C., Sze, C., Lin, K., & McKay, G. (2015). A critical review on preparation, characterization and utilization of sludge-derived activated carbons for wastewater treatment. *Chemical Engineering Journal*, 260, 895–906.
- Hegazi, H. A. (2013). Removal of heavy metals from wastewater using agricultural and industrial wastes as adsorbents. *HBRC Journal*, 9, 276–282. 4
- Heibati, B., Rodriguez-couto, S., Al-ghouti, M. A., & Asif, M. (2015). Kinetics and thermodynamics of enhanced adsorption of the dye AR 18 using activated carbons prepared from walnut and poplar woods. *Journal of Molecular Liquids*, 208, 99–105.
- Heibati, B., Rodriguez-Couto, S., Al-Ghouti, M. A., Asif, M., Tyagi, I., Agarwal, S., & Gupta, V. K. (2015). Kinetics and thermodynamics of enhanced adsorption of the dye AR 18 using activated carbons prepared from walnut and poplar woods. *Journal of Molecular Liquids*, 208, 99–105.
- Henze, M., & Comeau, Y. (2008). Wastewater Characterization. *Biological Wastewater Treatment: Principles Modelling and Design.*, 33–52.
- Hidayu, A. R., & Muda, N. (2016). Preparation and Characterization of Impregnated Activated Carbon from Palm Kernel Shell and Coconut Shell for CO<sub>2</sub> Capture. *Procedia Engineering*, 148, 106–113.
- Hock, P. E., & Zaini, M. A. A. (2018a). Activated carbons by zinc chloride activation for dye removal – a commentary. *Acta Chimica Slovaca*, 11(2), 99–106.
- Huang, P.-H., Cheng, H.-H., & Lin, S.-H. (2015). Adsorption of Carbon Dioxide onto Activated Carbon Prepared from Coconut Shells. *Journal of Chemistry*, 2015, 1–10
- Hussein, F. H., Halbus, A. F., Lafta, A. J., & Athab, Z. H. (2015). Preparation and Characterization of Activated Carbon from Iraqi Khestawy Date Palm. *Journal of Chemistry*, 2015, 1–8.
- Jain, S. N., & Gogate, P. R. (2017). Acid Blue 113 removal from aqueous solution using novel biosorbent based on NaOH treated and surfactant modified fallen leaves of *Prunus Dulcis*. *Journal of Environmental Chemical Engineering*, 5(4), 3384–3394.
- Javanbakht, V., & Ghoreishi, S. M. (2017). Application of response surface methodology for optimization of lead removal from an aqueous solution by a novel superparamagnetic nanocomposite. *Adsorption Science & Technology*, 35(1–2), 241–260.

- Jawad, A. H., Alkarkhi, A. F. M., & Mubarak, N. S. A. (2015). Photocatalytic decolorization of methylene blue by an immobilized TiO<sub>2</sub> film under visible light irradiation: optimization using response surface methodology (RSM). *Desalination and Water Treatment*, 56(1), 161–172.
- Joshi, R. R. (2016). Optimization of Conditions for the Preparation of Activated Carbon from Lapsi (*Choerospondias axillaris*) Seed Stone Using ZnCl<sub>2</sub>. *Journal of the Institute of Engineering*, 11(1), 128–139.
- kafa khalaf et al. (2018). Preparation of Activated Carbon From Waste Cooked Tea for Using as Chemical Dyes-Filter. In *IC onTES 2018: International Conference on Technology, Engineering and Science* (pp. 15–20). Antalya Turkey: ISRES publishing. Retrieved from <https://www.researchgate.net/publication/329905742>
- Kamaru, A. A., Sani, N. S., & Malek, N. A. N. N. (2016). Raw and surfactant-modified pineapple leaf as adsorbent for removal of methylene blue and methyl orange from aqueous solution. *Desalination and Water Treatment*, 57(40), 18836–18850.
- Katheresan, V., Kansedo, J., & Lau, S. Y. (2018a). Efficiency of various recent wastewater dye removal methods: A review. *Journal of Environmental Chemical Engineering*, 6(4), 4676–4697.
- Kausar, A., Iqbal, M., Javed, A., Aftab, K., Nazli, Z.-H., Bhatti, H. N., & Nouren, S. (2018). Dyes adsorption using clay and modified clay: A review. *Journal of Molecular Liquids*, 256, 395–407.
- Kavand, M., Soleimani, M., Kaghazchi, T., & Asasian, N. (2016). Competitive Separation of Lead, Cadmium, and Nickel from Aqueous Solutions Using Activated Carbon: Response Surface Modeling, Equilibrium, and Thermodynamic Studies. *Chemical Engineering Communications*, 203(1), 123–135.
- Khaniabadi, Y. O., Heydari, R., Nourmoradi, H., Basiri, H., & Basiri, H. (2016). Low-cost sorbent for the removal of aniline and methyl orange from liquid-phase: Aloe Vera leaves wastes. *Journal of the Taiwan Institute of Chemical Engineers*, 68, 90–98.
- Kharub, M. (2017). Comparative analyses of competitive advantage using Porter diamond model. *Competitiveness Review*, 27(2), 132-160.
- Kolade Amosa, M., Saedi Jami, M., Fahmi Alkhatib, an R., Tajari, T., Noraini Jimat, D., & Uthman Owolabi, R. (2016). Turbidity and suspended solids removal from high-strength wastewater using high surface area adsorbent: Mechanistic pathway and statistical analysis. *Cogent Engineering*, 5.

- Kondo, H., Suzuki, T., & Oishi, S. (2014). Production and Characterization of Activated Carbon from *Sasa Kurilensis*. *Eba*, 2–3.
- Lafi, R., Montasser, I., & Hafiane, A. (2019a). Adsorption of congo red dye from aqueous solutions by prepared activated carbon with oxygen-containing functional groups and its regeneration. *Adsorption Science & Technology*, 37(1–2), 160–181.
- Lahti, R., Bergna, D., Romar, H., Tuuttila, T., Hu, T., & Lassi, U. (2017). Physico-chemical properties and use of waste biomass-derived activated carbons. *Chemical Engineering Transactions*, 57.
- Li, J., Ng, D. H. L., Song, P., Kong, C., Song, Y., & Yang, P. (2015). Preparation and characterization of high-surface-area activated carbon fibers from silkworm cocoon waste for congo red adsorption. *Biomass and Bioenergy*, 75, 189–200.
- Li Lee, C., San H`ng, P., Paridah, T., Ling Chin, K., San Khoo, P., Ahmad Raja, R., Maminski, M. (2016). Effect of Reaction Time and Temperature on the Properties of Carbon Black Made from Palm Kernel and Coconut Shell. *Asian Journal of Scientific Research*, 10(1), 24–33.
- Lin, S. H., & Juang, R. S. (2009). Adsorption of phenol and its derivatives from water using synthetic resins and low-cost natural adsorbents: A review. *Journal of Environmental Management*, 90(3), 1336–49.
- Lin Zhi Lee & Muhammad Abbas Ahmad Zaini. (2015). Metal chloride salts in the preparation of activated carbon and their hazardous outlooka. *Desalination and Water Treatment*, 1–8.
- Liu, Z., Huang, Y., & Zhao, G. (2016). Preparation and Characterization of Activated Carbon Fibers from Liquefied Wood by ZnCl<sub>2</sub> Activation. *BioResources*, 11(2).
- Maneerung, T., Liew, J., Dai, Y., Kawi, S., Chong, C., & Wang, C. H. (2016). Activated carbon derived from carbon residue from biomass gasification and its application for dye adsorption: Kinetics, isotherms and thermodynamic studies. *Bioresource Technology*, 200, 350–359.
- Manera, C., Tonello, A. P., Perondi, D., & Godinho, M. (2018). Adsorption of leather dyes on activated carbon from leather shaving wastes: kinetics, equilibrium and thermodynamics studies. *Environmental Technology*, 1–13.
- Misran, E., Bani, O., Situmeang, E. M., & Purba, A. S. (2018). Removal efficiency of methylene blue using activated carbon from waste banana stem: Study on pH influence. *IOP Conference Series: Earth and Environmental Science*, 122, 012085.

- Mo, J., Yang, Q., Zhang, N., Zhang, W., Zheng, Y., & Zhang, Z. (2018). A review on agro-industrial waste (AIW) derived adsorbents for water and wastewater treatment. *Journal of Environmental Management*, *227*, 395–405.
- Mourabet, M., El Rhilassi, A., El Boujaady, H., Bennani-Ziatni, M., & Taitai, A. (2017). Use of response surface methodology for optimization of fluoride adsorption in an aqueous solution by Brushite. *Arabian Journal of Chemistry*, *10*, S3292–S3302.
- Mutasim H. Elhussien<sup>1</sup>, Rashida M. Hussein<sup>2</sup>, Sumia A. Nimir<sup>1</sup>, M. H. E. (2017). Preparation and Characterization of Activated Carbon from Palm Tree Leaves Impregnated with Zinc Chloride for the Removal of Lead (II) from Aqueous Solutions. *American Journal of Physical Chemistry*, *6–4*, 59–69.
- Nasri, N. S., Mohammed, J., Ahmad Zaini, M. A., Hamza, U. D., Mohd. Zain, H., & Ani, F. N. (2014). Equilibrium and Kinetic Studies of Benzene and Toluene Adsorption onto Microwave Irradiated-Coconut Shell Activated Carbon. *Advanced Materials Research*, *1043*, 219–223.  
<https://doi.org/10.4028/www.scientific.net/AMR.1043.219>
- Nasrullah, A., Saad, B., Bhat, A. H., Khan, A. S., Danish, M., Isa, M. H., & Naeem, A. (2019). Mangosteen peel waste as a sustainable precursor for high surface area mesoporous activated carbon: Characterization and application for methylene blue removal. *Journal of Cleaner Production*, *211*, 1190–1200.
- Nurul-Ruhayu, M.-R., An, Y. J., & Khairun, Y. (2015). Detection of River Pollution Using Water Quality Index: A Case Study of Tropical Rivers in Penang Island, Malaysia. *OALib*, *02(03)*, 1–8. 9
- Omo-Okoro, P. N., Daso, A. P., & Okonkwo, J. O. (2018). A review of the application of agricultural wastes as precursor materials for the adsorption of per- and polyfluoroalkyl substances: A focus on current approaches and methodologies. *Environmental Technology & Innovation*, *9*, 100–114.
- Ong, S. K., Mo, K. H., Alengaram, U. J., Jumaat, M. Z., & Ling, T. C. (2018). Valorization of Wastes from Power Plant, Steel-Making and Palm Oil Industries as Partial Sand Substitute in Concrete. *Waste and Biomass Valorization*, *9(9)*, 1645–1654.
- Ozdemir, I., Şahin, M., Orhan, R., & Erdem, M. (2014). Preparation and characterization of activated carbon from grape stalk by zinc chloride activation. *Fuel Processing Technology*, *125*, 200–206.
- Qu, J., Meng, X., Jiang, X., You, H., Wang, P., & Ye, X. (2018). Enhanced removal of Cd(II) from water using sulfur-functionalized rice husk: Characterization,

- adsorptive performance and mechanism exploration. *Journal of Cleaner Production*, 183, 880–886.
- Sadegh, H., Mazloumbilandi, M., & Chahardouri, M. (2017). Low-Cost Materials with Adsorption Performance. In *Handbook of Ecomaterials* (pp. 1–33). Cham: Springer International Publishing.
- Salema, A. A., Ting, R. M. W., & Shang, Y. K. (2019). Pyrolysis of blend (oil palm biomass and sawdust) biomass using TG-MS. *Bioresource Technology*, 274, 439–446.
- Saxena, A., Bhardwaj, M., Allen, T., Kumar, S., & Sahney, R. (2017). Adsorption of heavy metals from wastewater using agricultural–industrial wastes as biosorbents. *Water Science*, 31(2), 189–197.
- Sharma, P., Ayub, S., & Tripathi, C. (2013). Agro and Horticultural Wastes as Low Cost Adsorbents for Removal of Heavy Metals from Wastewater. *Int Refereed J Eng Sci*, 2(8), 18–27.
- Silva, J. S. da, Rosa, M. P. da, Beck, P. H., Peres, E. C., Dotto, G. L., Kessler, F., & Grasel, F. S. (2018). Preparation of an alternative adsorbent from *Acacia Mearnsii* wastes through acetosolv method and its application for dye removal. *Journal of Cleaner Production*, 180, 386–394.
- Silva, T. L., Cazetta, A. L., Souza, P. S. C., Zhang, T., Asefa, T., & Almeida, V. C. (2018a). Mesoporous activated carbon fibers synthesized from denim fabric waste: Efficient adsorbents for removal of textile dye from aqueous solutions.
- Simate, G. S., Maledi, N., Ochieng, A., Ndlovu, S., Zhang, J., & Walubita, L. F. (2016). Coal-based adsorbents for water and wastewater treatment. *Journal of Environmental Chemical Engineering*, 4(2), 2291-2312.
- Singh, N. B., Nagpal, G., Agrawal, S., & Rachna. (2018). Water purification by using Adsorbents: A Review. *Environmental Technology & Innovation*, 11, 187–240.
- Sriram, P. J., Pravalika, K. V., Meghana, P. K., & Ravindhranath, K. (2019). Effective Adsorbents Based on Biomaterials for Removal of Methylene Blue Dye from Water. *Asian Journal of Chemistry*, 31(3), 617–621.
- Mopoung, S., Moonsri P., Palas W., & Khumpai, S. (2015) Characterization and Properties of Activated Carbon Prepared from Tamarind Seeds by KOH Activation for Fe(III) Adsorption from Aqueous Solution: *The Scientific World Journal*, 2015, 1-9.

- Sulyman, M., Namiesnik, J., & Gierak, A. (2017). Low-cost adsorbents derived from agricultural by-products/wastes for enhancing contaminant uptakes from wastewater: A review. *Polish Journal of Environmental Studies*, 26(2), 479–510.
- Sulyman, M., Sienkiewicz, M., Haponiuk, J., & Zalewski, S. (2018). New Approach for Adsorptive Removal of Oil in Wastewater using Textile Fibers as Alternative Adsorbent, 2(6), 32–37.
- Swan, N. B., & Zaini, M. A. A. (2019). Adsorption of Malachite Green and Congo Red Dyes from Water: Recent Progress and Future Outlook. *Ecological Chemistry and Engineering S*, 26(1), 119–132.
- Tang, L., Yu, J., Pang, Y., Zeng, G., Deng, Y., Wang, J., Feng, H. (2018). Sustainable efficient adsorbent: Alkali-acid modified magnetic biochar derived from sewage sludge for aqueous organic contaminant removal. *Chemical Engineering Journal*, 336, 160–169.
- Tang, Y., Li, Y., Zhao, Y., Zhou, Q., & Peng, Y. (2018). Enhanced removal of methyl violet using NaOH-modified *C. camphora* leaves powder and its renewable adsorption. *Desalination and Water Treatment*, 98(2017), 306–314.
- Tay. (2009). Characteristics and Properties of Fatty Acid Distillates from Palm Oil. *Oil Palm Bulletin*, 59(November), 5–11.
- Tran, H. N., Chao, H.-P., & You, S.-J. (2018). Activated carbons from golden shower upon different chemical activation methods: Synthesis and characterizations. *Adsorption Science & Technology*, 36(1–2), 95–113.
- Travlou, N. A., Seredych, M., Rodríguez-Castellón, E., & Bandosz, T. J. (2015). Activated carbon-based gas sensors: effects of surface features on the sensing mechanism. *Journal of Materials Chemistry A*, 3(7), 3821–3831.
- Uddin, M. K. (2017). A review on the adsorption of heavy metals by clay minerals, with special focus on the past decade. *Chemical Engineering Journal*, 308, 438–462.
- Wakkal, M., Khiari, B., & Zagrouba, F. (2019). Basic red 2 and methyl violet adsorption by date pits: adsorbent characterization, optimization by RSM and CCD, equilibrium and kinetic studies. *Environmental Science and Pollution Research*, (19), 18942–18960.
- Wang, J., Xu, J., & Wu, N. (2017). Kinetics and equilibrium studies of methylene blue adsorption on 2D nanolamellar Fe<sub>3</sub>O<sub>4</sub>. *Journal of Experimental Nanoscience*, 12(1), 297–307.

- Wawrzkiwicz, M., & Hubicki, Z. (2015). Anion Exchange Resins as Effective Sorbents for Removal of Acid, Reactive, and Direct Dyes from Textile Wastewaters. In *Ion Exchange - Studies and Applications*. InTech.
- Wirasnita, R., Hadibarata, T., Yusoff, A. R. M., & Yusop, Z. (2014). Removal of Bisphenol A from Aqueous Solution by Activated Carbon Derived from Oil Palm Empty Fruit Bunch. *Water, Air, & Soil Pollution*, 225(10), 2148.
- Yang, C., Girma, A., Lei, T., Liu, Y., Ma, C., & Ng, C. A. (2016). Study on simultaneous adsorption of Zn(II) and methylene blue on waste-derived activated carbon for efficient applications in wastewater treatment. *Environmental Science*, 2(2).
- Zainal, N. H., Aziz, A. A., Ibrahim, M. F., Idris, J., Hassan, M. A., Bahrin, E. K., ... Abd-Aziz, S. (2018). Carbonisation-activation of oil palm kernel shell to produce activated carbon and methylene blue adsorption kinetics. *Journal of Oil Palm Research*, 30(3), 495–502.
- Zaini, M. A. A., Okayama, R., & Machida, M. (2009). Table 4.10 : Results of Point of Zero Charge of selected Adsorbents. *Journal of Hazardous Materials*, 170(2–3), 1119–1124.
- Zhang, J., Gao, J., Chen, Y., Hao, X., & Jin, X. (2017). Characterization, preparation, and reaction mechanism of hemp stem based activated carbon. *Results in Physics*, 7, 1628–1633.
- Zhou, H., Wu, L., Gao, Y., & Ma, T. (2011). Dye-sensitized solar cells using 20 natural dyes as sensitizers. *Journal of Photochemistry and Photobiology A: Chemistry*, 219(2–3), 188–194.

## LIST OF PUBLICATION

### Indexed Journal

1. **Hamzat Bashir Aderemi**, Muhammad Abbas Ahmad Zaini and Noor Shawal Nasir (2018) Adsorbents from the by-products of palm oil refinery for methylene blue removal Malaysian Journal of Analytical Sciences vol 22 No 4 642 -647. <https://doi.org/10.17576mjas-2018-2204-10>. **(Indexed by ISI and Scopus)**
2. **Hamzat Bashir Aderemi**, Muhammad Abbas Ahmad Zaini and Noor Shawal Nasir (2018) Physicochemical properties of char derived from palm fatty acid distillate Malaysian Journal of Fundamental and Applied Sciences vol 14 No 13 (403 – 406) DOI: 10.11113/mjfas.v14n3.1084 **(Indexed by ISI and Scopus)**
3. **Hamzat Bashir Aderemi**, Muhammad Abbas Ahmad Zaini and Noor Shawal Nasir (2017) Adsorbents from the by-products of palm oil refinery for methylene blue removal. Presented at the 2nd International Conference on Separation Technology (ICoST 2017) Johor bahru, Malaysia. **(Indexed by ISI and Scopus)**