

STRUCTURAL PERFORMANCE OF REPAIRED CIRCULAR REINFORCED  
CONCRETE COLUMNS USING STEEL STRAPPING TENSIONING  
TECHNIQUE

NAZIRAH BINTI MOHD APANDI

A thesis submitted in fulfilment of the  
requirements for the award of the degree of  
Doctor of Philosophy in Civil Engineering

School of Civil Engineering  
Faculty of Engineering  
Universiti Teknologi Malaysia

DECEMBER 2019

## **DEDICATION**

This thesis is dedicated to my supervisors, my father, my mother, family, and all my beloved friends

## ACKNOWLEDGEMENT

Bismillahirrahmanirrahim, first of all, I am grateful to Almighty Allah S.W.T., who gives me all the strength and patience to complete my PhD study. I am grateful because there have been whom have guided and assisted me to succeed in this study. This study is made possible through the help and support from everyone, especially supervisors, lecturers, parents, family, friends, and in essence, all sentient beings. First and foremost, I would like to express my sincere gratitude to my great supervisors, Dr Ma Chau Khun, Prof Datuk. Dr. Ir. Wahid Omar and Dr Abdullah Zawawi Awang for the excellent guidance, most support and encouragement to me in order to complete this research.

I would also like to thank to late Assoc. Prof. Dr. Abdul Kadir Marsono and technicians (En Zulkifli, En Hazry, Mazlina, En Azmi, En Zaaba, En Raja, En Nawawi, En Zailani Aman, and En Afif) that always willing to help and give some guidance with valuable advices. Without them, my research study would have not been possible done. A special thank you to my friends Chin Chee Loong, Irravani, Muhammad Amirul Affiz, Chiew Shing Mei, Tan Jia Yang, Ong Chin Boon, Azhari, Nursyamira, Muhd Fauzi, and Sofrie Chin for helping me through my research study. Finally, I sincerely thank to my parents Mohd Apandi Bin M. Hasan, Habibah Binti Mohd and my family, who provided the advice and encourage me with their best wishes in order to complete my research. This research would not be possible without all of them.

## ABSTRACT

Studies on the behaviour of intact reinforced concrete (RC) columns are widely available, however, studies focusing on the behaviour of deteriorated RC columns is quite limited. Deteriorated columns need to be repaired to remain structurally sound. Among the available repairing approaches, confining methods have been extensively researched. Current studies on confining damaged column only focusing on passive-typed confinement, which led to high dependency of the dilation of concrete. This study extends the investigation on repairing RC columns to the active-typed confinement, where confining stress is applied to columns before the concrete dilation. Both experimental and numerical modeling were conducted to investigate the applicability of active confinement in repairing RC columns with varied pre-damaged levels. The applicability of steel strapping confinement in repairing RC columns with the varied pre-damaged levels were confirmed through experimental works, the experimental involved testing of 34 plain concrete cylinders and 21 RC columns under monotonic uniaxial compression. The concrete cylinder tests were performed develop a suitable stress-strain model, which incorporated pre-damaged levels for confined concrete. The empirical stress-strain model was then used in the development of numerical model for the repaired RC columns. The tests on RC column specimens consisted of 3 control columns and 18 repaired RC columns with different confining levels. The overall response of the specimens was investigated in terms of crack pattern, load carrying capacity, axial displacement, stiffness and ductility of repaired columns. The results from the experimental works were then verified by using the numerical modeling before further analysis. The test results have shown that the restorability of confinement was significantly affected by pre-damaged levels. It is also observed that the increase in confining volumetric ratio is able to restore both strength and ductility of repaired RC columns up to 171% and 172%, for the same pre-damaged level. Additionally, the outcome of the finite element modelling also aligned with the experimental results where the average absolute errors (AAE) for both strength and ductility remained are within 15%. Based on this study, a design consideration for repairing columns using confinement was also developed. The design consideration serves as a tool for design engineers in using steel strapping confinement in repairing damaged columns.

## ABSTRAK

Kajian memberi tumpuan kepada tingkah laku tiang konkrit bertetulang (KB) dalam keadaan utuh semakin meluas, tetapi fokus dalam tiang-tiang KB yang mengalami kerosakan mekanikal masih sukar didapati. Tiang tersebut mestilah diperbaiki untuk memastikan strukturnya dalam keadaan baik. Dalam kebanyakan pendekatan dalam memperbaiki struktur yang ada, balutan sisi telah menjanjikan penyelesaian. Kajian terkini mendapati balutan sisi tiang hanya fokus kepada balutan sisi yang tidak giat yang menjurus kepada pengembangan konkrit. Dalam kajian ini menyambung penyiasatan dalam pembaikan tiang KB bagi balutan sisi aktif di mana tegasan balutan diberikan kepada tiang sebelum konkrit berkembang. Ujikaji makmal dan kaedah berangka telah dijalankan untuk mengkaji kebolegunaan balutan sisi aktif dalam pembaikan tiang KB dengan pelbagai tahap pra-kerosakan. Kebolegunaan besi balutan sisi dalam pembaikan tiang KB dengan pelbagai tahap pra-kerosakan ditentukan dengan 34 silinder konkrit biasa dan 21 tiang KB diuji di bawah beban mampatan satu paksi. Ujian silinder konkrit dilakukan untuk membina model tegasan-keterikan yang sesuai bagi menggabungkan tahap pra-kerosakan untuk konkrit berbalut. Model ini kemudiannya digunakan dalam pembangunan model berangka untuk tiang KB yang rosak. Ujian pada spesimen KB terdiri daripada 3 tiang asal dan 18 tiang KB diperbaiki dengan tahap pengasingan yang berbeza telah dijalankan. Tindak balas keseluruhan spesimen disiasat dari segi corak retak, keupayaan menanggung beban, pemendekan paksi, kekukuhan dan kemuluran pembaikan tiang. Hasil ujian menunjukkan tahap pra-kerosakan mempunyai kesan yang signifikan terhadap keupayaan menanggung beban. Peningkatan skema balutan dapat meningkatkan kekuatan dan kemuluran KB yang dibaiki sehingga 171% dan 172% untuk tahap pra-kerosakan yang sama. Selain itu, model berangka telah dibangunkan untuk mengetahui lebih lanjut mengenai tingkah laku tiang yang diperbaiki ini menggunakan balutan sisi. Hasil dari model yang menunjukkan keputusan baik dengan ujikaji makmal di mana purata selisih mutlak untuk kekuatan dan kemuluran berbeza kurang dari 15%. Garis panduan reka bentuk untuk kerja-kerja pembaikan menggunakan balutan sisi telah dibangunkan. Garis panduan reka bentuk ini adalah alat yang menjanjikan bagi jurutera reka bentuk dalam menggunakan balutan sisi dalam kerja pembaikan kerosakan tiang.

## TABLE OF CONTENTS

	<b>TITLE</b>	<b>PAGE</b>
	<b>DECLARATION</b>	<b>iii</b>
	<b>DEDICATION</b>	<b>iv</b>
	<b>ACKNOWLEDGEMENT</b>	<b>v</b>
	<b>ABSTRACT</b>	<b>vi</b>
	<b>ABSTRAK</b>	<b>vi</b>
	<b>TABLE OF CONTENTS</b>	<b>ix</b>
	<b>LIST OF TABLES</b>	<b>xv</b>
	<b>LIST OF FIGURES</b>	<b>xvii</b>
	<b>LIST OF SYMBOLS</b>	<b>xxii</b>
	<b>LIST OF APPENDICES</b>	<b>xxiii</b>
<b>CHAPTER 1</b>	<b>INTRODUCTION</b>	<b>1</b>
	1.1 Background of Study	1
	1.2 Problem Statement	2
	1.3 Objectives	3
	1.4 Scope of Works	4
	1.5 Significance of Study	5
	1.6 Thesis Layout	6
<b>CHAPTER 2</b>	<b>LITERATURE REVIEW</b>	<b>9</b>
	2.1 General	9
	2.2 High Strength Concrete	9
	2.3 Confinement of Concrete Structures	10
	2.4 Concrete Confinement Techniques	13
	2.4.1 Fibre Reinforced Polymer	13
	2.4.2 Ferrocement Jackets	15
	2.4.3 Steel Jacketing	17

2.4.4	Concrete Jacketing	18
2.5	Effectiveness of Measurement Methods	32
2.6	Testing Variables and Methods	32
2.7	Concluding Remarks	35
<b>CHAPTER 3</b>	<b>CLASSIFICATIONS OF PRE-DAMAGED LEVEL</b>	<b>37</b>
3.1	General	37
3.2	Pre-Damaged Level	37
3.2.1	Effects of Pre-damaged Level on Plain Concrete	40
3.2.2	Effects of Pre-damaged Level on RC Structures	47
3.2.3	Effects of Pre-damaged Level on the Strength Enhancement	58
3.2.4	Effects of Pre- Damaged Level on Stiffness	59
3.2.4	Effects of Pre-damaged Level on Ductility	61
3.3	Confinement Model	62
3.4	Damage Assessment Based on Codes of Practice	69
3.5	Assessment of Pre-damaged Level	72
3.6	Concluding Remarks	75
<b>CHAPTER 4</b>	<b>METHODOLOGY</b>	<b>77</b>
4.1	General	77
4.2	Specimen Design	79
4.3	Detail of Test Specimens	80
4.4	Material Properties	85
4.4.1	Concrete	85
4.4.2	Reinforcement Preparation	86
4.4.3	Properties of Steel Straps	88
4.5	Casting of Columns	90
4.6	Instrumentation	91
4.7	Pre–Damaging Process	94
4.8	Repair Works	96

4.9	Numerical Modeling	99
4.10	Concluding Remarks	101
<b>CHAPTER 5</b>	<b>EXPERIMENTAL TEST ON CONFINED PLAIN CYLINDER</b>	<b>103</b>
5.1	General	103
5.2	Failure Modes	104
5.3	Stress-Strain Relationships	105
	5.3.1 Effects of Confining Volumetric Ratio	109
5.4	Analytical Analysis	112
	5.4.1 Estimation of Strength and Strain	112
5.5	Stress-Strain Relationship	119
5.6	Proposed Stress-Strain Model	121
5.7	Concluding Remarks	128
<b>CHAPTER 6</b>	<b>EXPERIMENTAL TEST ON CONFINED RC COLUMNS</b>	<b>131</b>
6.1	Test Results of RC Columns	131
6.2	General Behaviour and Failure Modes	131
	6.3.2 Effect of Layer and Spacing of Steel Straps of Repaired RC Columns	139
	6.3.3 Effect of Pre-damaged Level on Repaired RC Columns	143
	6.2.4 Effect of Confining Volumetric Ratio on Repaired RC Columns	146
	6.3.5 Effect of Steel Reinforcement Ratio on Repaired RC Columns	147
	6.3.6 Effects of Steel Straps	148
6.4	Performance Indices of Repaired RC Columns	149
	6.4.1 Strength Index	149
	6.4.2 Stiffness Index	150
	6.4.3 Ductility Index	151
	6.4.4 Correlation between Damaged Degree and Confining Volumetric Ratio	153
6.5	Effect of Various Parameters on Performance Indices	156



6.5.1	Effects of Various Parameters on Strength Capacity	156
6.5.2	Effects of Various Parameters on Stiffness	160
6.5.3	Effects of Various Parameters on Ductility	163
6.6	Concluding Remarks	166
<b>CHAPTER 7</b>	<b>FINITE ELEMENT ANALYSIS</b>	<b>169</b>
7.1	General	169
7.2	Finite Element Analysis	169
7.3	Column Modelling Technique	170
7.3.1	Solid Element	170
7.3.2	Truss Element	171
7.3.3	Rigid Element	172
7.4	Material Models	172
7.4.1	Concrete	172
7.4.2	Steel Reinforcement	174
7.5	Discretion of Analysis	176
7.5.1	Steps, Increments, and Iterations	176
7.5.2	Mesh Convergence Study	176
7.6	Validation of Model with Experimental Test	178
7.7	Parametric Studies	188
7.7.1	Effects of Pre-damaged Level	189
7.7.2	Effects of Layer of Steel Straps	191
7.7.3	Effects of Spacing of Steel Straps	193
7.7.4	Effects of Longitudinal Reinforcement	195
7.7.5	Stiffness of Repaired Columns	197
7.8	Concluding Remarks	198
<b>CHAPTER 8</b>	<b>DESIGN CONSIDERATION</b>	<b>201</b>
8.1	General	201
8.2	International Design Guidelines	201
8.3	Analysis of Design Guidelines with Experimental Test	205

8.4	Proposed Design Consideration for Repair RC Columns	207
8.4.1	Compressive Strength of Repaired RC Columns	207
8.4.2	Stiffness of Repaired RC Columns	208
8.4.3	Ductility of Repaired RC Columns	209
8.5	Prediction Accuracy of Proposed Model	210
8.5.1	Validation against Experimental Test	210
8.6	General Assumptions	213
8.7	Repairing Consideration	214
8.7.1	Assessment of Pre-damaged Level	217
8.7.2	Structural Performance of Repaired RC Columns	218
8.7.3	Repairs of Steel Straps Tensioning Techniques	219
8.8	Concluding Remarks	220
<b>CHAPTER 9</b>	<b>CONCLUSION AND RECOMMENDATIONS</b>	<b>221</b>
9.1	General	221
9.2	The Applicability of using SSTT in Confined Plain Cylinders	221
9.3	Effecting Parameters in Restorability of Damaged RC Circular Columns	222
9.4	Evaluate the Structural Performance using Numerical Modelling	223
9.5	Design Consideration for Damaged Structures using SSTT	223
9.6	Recommendation for Future Works	224
	<b>REFERENCES</b>	<b>225</b>
	<b>LIST OF PUBLICATIONS</b>	<b>253</b>

## LIST OF TABLES

<b>TABLE NO.</b>	<b>TITLE</b>	<b>PAGE</b>
Table 2.1	The typical compressive strength of HSC	10
Table 2.2	Summary findings of repairing and strengthening techniques	21
Table 2.3	Confinement repairing methods and measured variables	33
Table 2.4	Testing variables and methods	34
Table 3.1	Definition of pre-damaged level for plain cylinder	39
Table 3.2	Summary of research on the effects of pre-damaged level in plain concrete	43
Table 3.3	Summary of previous studies on the effects of pre-damaged level in RC structures	51
Table 3.4	Summary of the effects of pre-damaged level in restoring the load carrying capacity	59
Table 3.5	Summary on the effects of pre-damaged level on stiffness	60
Table 3.6	Summary on effects of pre-damaged level on ductility	62
Table 3.7	Summary of confinement models	66
Table 3.8	Confinement models from previous researchers	67
Table 3.9	Classification of damage (Reproduced from: FEMA 356 [126] )	70
Table 3.10	Summary of damage assessment	71
Table 4.1	Plain cylinder test specimens	82
Table 4.2	Circular RC short columns specimen configurations	84
Table 4.3	Mix proportions for 1m <sup>3</sup> of concrete	85
Table 4.4	Properties of rebars	88
Table 4.5	Details steel straps from average value of tensile test	89
Table 4.6	Instruments and equipment used	93
Table 4.7	Details of pneumatic tensioner	96
Table 5.1	Comparisons of theoretical values and experimental values	116
Table 5.2	Test results	120

Table 6.1	Observation of failure modes for the damaged and repaired columns	135
Table 6.2	Test results of damaged RC column with different repairing techniques	152
Table 7.1	Summary of errors for experimental test results and finite element analysis for prediction axial strength	186
Table 7.2	Summary of errors for experimental test results and finite element analysis for prediction of stiffness	186
Table 7.3	Summary of errors for experimental test results and finite element analysis for prediction of ductility	187
Table 7.4	Parameter variations	189
Table 8.1	Summary of International Design Guidelines	203
Table 8.2	Experimental versus design guidelines equation for repair and strengthen RC columns	206
Table 8.3	Statistical analysis for strength model	211
Table 8.4	Statistical analysis for stiffness model	212
Table 8.5	Statistical analysis for ductility model	213
Table 8.6	The classifications of pre-damaged level	218

## LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
Figure 2.1	Effectively confined concrete columns for: (a) circular and (b) rectangular cross- section area (Reproduced from: Mander <i>et al.</i> [48] )	12
Figure 2.2	Repair of reinforced concrete bridge using fiber reinforced polymer (Reproduced from: Saadatmanesh [63])	15
Figure 2.3	Ferrocement laminate jacketing (Reproduced from: Makki [70])	17
Figure 2.4	Steel jacketing (Reproduced from: Belal <i>et al.</i> [72])	18
Figure 2.5	Concrete jacketing (Reproduced from: Vandoros <i>et al.</i> [76])	20
Figure 2.6	The taxonomy of the research	31
Figure 3.1	Pre-damaged levels in stress-strain relationship (Adapted from: Wu <i>et al.</i> [57] )	38
Figure 3.2	The failure modes of plain cylinder: (a) preloaded to ultimate; (b) preloaded to $0.9 f'_{co}$ ; (c) preloaded to $0.85 f'_{co}$ ; (d) loaded to failure (Reproduced from: Ma <i>et al.</i> [111])	42
Figure 3.3	Schematic diagram for strengthened columns (Reproduced from Chellapandian <i>et al.</i> [122])	50
Figure 3.4	Classification of the pre-damaged level based on previous studies	74
Figure 4.1	Research design	78
Figure 4.2	Design of RC columns	79
Figure 4.3	Specimen designations for: (a) plain cylinder and (b) RC columns	81
Figure 4.4	The cube test: (a) compression machine and typical failure mode of (b) NSC and (c) HSC	86
Figure 4.5	Failure mode of tensile test for steel reinforcement bar size: (a) 10 mm, (b) 12 mm and (c) 16mm	87
Figure 4.6	Stress-strain curves for rebar size 10 mm, 12 mm and 16 mm	88
Figure 4.7	Stress-strain curves for steel straps	89

Figure 4.8	The details of: (a) tensile test and (b) failure mode of steel straps	90
Figure 4.9	The preparation of: (a) formwork and (b) casting of RC columns	91
Figure 4.10	Measuring device used such as pi-gauges and LVDT	92
Figure 4.11	Calibration of pi-gauges	93
Figure 4.12	Schematic diagram of test setup and instrumentation	95
Figure 4.13	The details of: (a) pneumatic tensioner, (b) steel straps confinement and (c) steel straps clip connections	97
Figure 4.14	The process of: (a) damaging specimen; (b) repairing using mortar; (c) column after repair and ready for testing; and (d) column testing after repair.	97
Figure 4.15	Repaired columns with cement mortar	98
Figure 4.16	Details of repaired specimens: (a) concrete cylinder and (b) RC columns	98
Figure 4.17	Flowchart of numerical modelling	100
Figure 5.1	Failure modes: (a) C50-15-1(0); (b) C50-15-2(0); (c) C50-10-1(-80% to -50); (d) C50-10-1(+50 to +80%); (e) C50-10-1 (+80% to -80%)	105
Figure 5.2	Stress-deformation curves of tested specimen	106
Figure 5.3	Effects on confining volumetric ratio on: (a) strength and (b) strain increment	110
Figure 5.4	Effects of pre-damaged level on: (a) strength and (b) normalized strain increment	111
Figure 5.5	Comparisons of analytical models with tested results: (a) $f_{cc}/f_{co}$ ; (b) $\varepsilon_{cc}/\varepsilon_{cu}$	114
Figure 5.6	Typical stress-strain relationships	119
Figure 5.7	Comparisons of proposed equations with experimental results: (a) Eq. (5.10); (b) Eq. (5.11)	123
Figure 5.8	Comparisons of proposed equations with tested results: (a) Eq. (5.12); (b) Eq. (5.13); (c) Eq. (5.14)	124
Figure 5.9	Proposed n value	125
Figure 5.10	Evaluation of proposed model: (a) $\rho_v = 0.13$ ; (b) $\rho_v = 0.20$ ; (c) $\rho_v = 0.26$ ; (d) $\rho_v = 0.38$ ; (e) $\rho_v = 0.41$	126

Figure 6.1	Typical failure modes of control columns for concrete grade: (a) 30 MPa; (b) 50 MPa; and (c) 90 MPa at medium pre-damaged level	133
Figure 6.2	Typical failure modes of columns of: (a) low; (b) medium; and (c) heavy pre-damaged level for concrete strength 30 MPa	134
Figure 6.3	Typical failure of steel straps	134
Figure 6.4	Typical failure modes of repaired columns for concrete grade: (a) 30 MPa; (b) 50 MPa; and (c) 90 MPa for medium pre-damaged level	135
Figure 6.5	Relationship between load carrying capacity and concrete strength of repaired columns	139
Figure 6.6	Effect of layer and spacing of steel straps of repaired columns for; (a) 10-1, (b) 20-2, and (c) 30-3	141
Figure 6.7	Effect of confinement configuration on: (a) strength and (b) deformation	142
Figure 6.8	Effect of pre-damaged level on ultimate capacity of RC columns of; (a) +50% to +80%, (b) +80% to -80% and (c) -80% to -50%	144
Figure 6.9	Effect of pre-damaged level on: (a) strength and (b) deformation	145
Figure 6.10	Effect of confining volumetric ratio	146
Figure 6.11	Load-strain behaviour of longitudinal reinforcements	147
Figure 6.12	Effects of steel straps on repaired RC columns	148
Figure 6.13	Correlation of damaged degree and confining volumetric ratio for: (a) strength, (b) ductility and (c) stiffness of repaired RC columns	154
Figure 6.14	Effect of concrete strength in strength enhancement of repaired RC columns	157
Figure 6.15	Effect of confining volumetric ratio in strength enhancement of repaired RC columns	158
Figure 6.16	Effect of pre-damaged level in strength enhancement of repaired RC columns	159
Figure 6.17	Effect of the steel reinforcement ratio in strength enhancement of repaired RC columns	160
Figure 6.18	Effect of the concrete strength in the stiffness enhancement of repairing RC columns	161

Figure 6.19	Effect of confining volumetric ratio in the stiffness enhancement of repairing RC columns	162
Figure 6.20	Effect of the confining volumetric ratio in the stiffness enhancement of repairing RC columns	162
Figure 6.21	Effect of the steel reinforcement ratio in the stiffness enhancement of repairing RC columns	163
Figure 6.22	Effect of the concrete strength in the ductility enhancement of repairing RC columns	164
Figure 6.23	Effect of the pre-damaged level in the ductility enhancement of repairing RC columns	165
Figure 6.24	Effect of the confining volumetric ratio in the ductility enhancement of repairing RC columns	165
Figure 6.25	Effect of the diameter of longitudinal reinforcement in the ductility enhancement of repairing RC columns	166
Figure 7.1	First-order brick element	171
Figure 7.2	Truss element embedded in solid elements	171
Figure 7.3	Four node, bilinear quadrilateral rigid surface element	172
Figure 7.4	Strain hardening and perfectly plastic behaviour	173
Figure 7.5	Idealizations of the steel stress-strain curves	174
Figure 7.6	Mesh of the columns elements	177
Figure 7.7	Mesh convergence study	177
Figure 7.8	Validation of load-displacement between experimental works and FE for 30 MPa for: (a) C30-10-1-10(+50% to +80%) (b) C30-20-2-10(+50% to +80%), (c) C30-30-3-10(+50% to +80%) with typical failure model	180
Figure 7.9	Validation of load-displacement between experimental works and FE for 30 MPa for: (a) C30-10-1-10(+80% to -80%), (b) C30-20-2-10(+80% to -80%), (c) C30-30-3-10(+80% to -80%) with typical failure model	181
Figure 7.10	Validation of load-displacement between experimental works and FE for 30 MPa for: (a) C30-10-1-10(-80% to -50%), (b) C30-20-2-10(-80% to -50%), (c) C30-30-3-10(-80% to -50%) with typical failure model	182
Figure 7.11	Validation of load-displacement between experimental works and FE for 30 MPa at the different steel reinforcement ratio: (a) 1.78%, (b)2.56%, (c) 4.55% with typical failure model	183



Figure 7.12	Validation of load-displacement between experimental works and FE for 50 MPa at the pre-damaged level of: (a) +50% to +80%, (b) +80% to -80% and (c) -80% to -50% with typical failure model	184
Figure 7.13	Validation of load-displacement between experimental works and FE for 90 MPa at the pre-damaged level of: (a) +50% to +80%, (b) +80% to -80% and (c) -80% to -50% with typical failure model	185
Figure 7.14	Ultimate strength versus spacing of steel straps for pre-damaged level of: (a) +50% to +80%; (b) +80% to -80%; and (c) -80% to -50%	190
Figure 7.15	Ultimate strength versus concrete strength for: (a) 10 mm; (b) 20 mm; and (c) 30 mm spacing of steel straps	192
Figure 7.16	Ultimate strength versus concrete compressive strength for: (a) 1; (b) 2; and (c) 3 layers of steel strap	194
Figure 7.17	Ultimate strength versus pre-damaged level for: (a) 1.78%; (b) 2.56%; and (c) 4.56% of steel reinforcement ratio	196
Figure 7.18	k value with pre-damaged level for different concrete compressive strength	198
Figure 8.1	Average mean ratio of the international design guidelines to the experimental results	207
Figure 8.2	Performance of strength model	210
Figure 8.3	Performance of stiffness model	211
Figure 8.4	Performance of ductility model	212
Figure 8.5	Overall repairing procedure	215
Figure 8.6	Details repairing procedure	216
Figure 8.7	Example observations of pre-damaged level for NSC columns: a) low; b) medium; and c) heavy damaged	217
Figure 8.8	Example observations of pre-damaged level for HSC columns: a) low; b) medium; and c) heavy damaged	218

## LIST OF SYMBOLS

$E_f$	-	Elastic modulus of confining material
$E_0$	-	Initial slope of stress-strain curve
$\widetilde{E}_0$	-	Initial slope of stress-strain curve of damaged concrete
$E_h$	-	Slope of strain hardening
$\widetilde{E}_h$	-	Slope of strain hardening of damaged concrete
$f_0$	-	Elastic limit
$\widetilde{f}_0$	-	Elastic limit of damaged concrete
$f_c$	-	Stress of concrete
$f_{cc}$	-	Damaged concrete compressive strength
$f_{cd}$	-	Unconfined damaged concrete compressive strength
$f_{co}$	-	Unconfined undamaged concrete compressive strength
$f_l$	-	Confinement pressure
$f_{ys}$	-	Yield strength of steel straps
$n$	-	Transition parameter
$t_f$	-	Thickness of confining material
$V_c$	-	Volume of confined concrete
$V_s$	-	Volume of steel straps
$\delta$	-	Damaged degree
$\lambda$	-	Pre-damaged level
$\varepsilon_{cc}$	-	Ultimate strain of confined concrete
$\rho_v$	-	Strain of concrete
$\varepsilon_u$	-	Ultimate rupture strain of confining material
$\varepsilon_c$	-	Volumetric confinement ratio
$P_o$	-	Axial load of original RC columns
$P_r$	-	Axial load of repaired RC columns
$E_s$	-	Stiffness of steel reinforcement bar
$f_{yk}$	-	Yield strength of steel reinforcement

## LIST OF APPENDICES

<b>APPENDIX</b>	<b>TITLE</b>	<b>PAGE</b>
Appendix A	Sample of experimental data for pre-damaged RC columns	239
Appendix B	Parametric Analysis from Finite Elements	243
Appendix C	Example of Design Calculations for Repaired RC Columns	251

# CHAPTER 1

## INTRODUCTION

### 1.1 Background of Study

Over the past years, repairing of damaged concrete structures has become a major part in the construction industry. They contributed nearly half of the total expenditures from total construction activities. Repair is vital, especially for vertical elements such as reinforced concrete (RC) columns since RC columns is the main element that convey axial load of the buildings to the foundations. In practice, RC columns can lose its strength and stiffness especially during its service lifetime due to physical damage. Apart from that, repairs are required for the cases such as: i) arising service loads; ii) altering usage of structure; iii) errors in design or during construction; iv) seismic action; v) corrosion due to humidity; vi) fire effects; and vii) exposure to environmental effects such as the variance of temperature [1].

There are two categories of confinement which are external and internal confinement. Xiong *et al.* [2] claimed that external confinement can be adopted to repair the damaged concrete columns effectively. It can enhance the energy absorption capacity, ductility and significantly restore the strength of damaged structures. The effectiveness of confinement is highly dependent on the cross-sectional area of structure, either the shape is in circular, rectangular or square section. Besides, confinement can be either, active or passive. Passive confinement provides lateral restriction on the dilations of concrete under loading due to the Poisson's ratio and cracking of the structure. Active confinement allows lateral pressure to be applied to the column at the initial stages of loading. Active confinement is relatively recent and is increasingly being researched [3-6]. The steel strap confinement is one of the active confinements that has been studied by previous researchers. The early research of steel straps active confinement was conducted by

Frangou *et al.* [7] and Moghaddam *et al.* [8]. Active confinement increases the concrete strength more efficiently as compared to passive confinement [8]. Subsequently, many researchers studied on steel straps confinement in different perspectives such as strength improvement, ductility enhancement, durability and bond behaviour between steel and confined concrete [9-12].

The purpose of confinement is either to repair, rehabilitate or strengthen a concrete structure. Repairing of a concrete structure is defined as the process to restore the load carrying capacity of a damaged structure to its initial performance. Rehabilitation refers to increasing in the load carrying capacity RC structure for altering the purpose of the existing buildings. While, strengthening refers to the method used to improve the capacity of the structure more than the actual design. There are few types of repairing techniques using confinement which have been reported in open literature such as ferrocement [13-16], Fibre reinforced polymer (FRP) [17-19] and steel jacketing [20-22]. The confinement models developed by previous researchers were dedicated for strengthening and repairing confined concrete works [23-25]. The confinement model developed for repairing works is still scarce and needed to be improvised. In view of this, this study investigates the use of steel strapping tensioning technique (SSTT) as an alternative in repairing the pre-damaged reinforced columns. A finite element model was verified with experimental result and extended for further investigations. Finally, the design equation for the repairing works using SSTT is proposed.

## **1.2 Problem Statement**

Columns are major components in a structure that transfer vertical axial loads to the foundations. This will cause major failures or total collapse of the structure. The restoration of load carrying capacity of damaged columns using external confining method can be considered as one of the most efficient and quickest method. Most of the repairing techniques considered the passive confinement such as FRP concrete and steel jacketing. The study on using active confinements as

repairing techniques is still yet to be attempted by other researchers, to the best knowledge of the author. The understanding of active confinement as repairing techniques is still yet to be discovered. In practice, very less information of the damage assessment can be found in the open literature regarding the design of repairing works respectively. The assessment of pre-damaged levels is particularly important as it will affect the repairing efficiency considerably. Hence, the understanding of damaged level, which has been mostly very limited, is needed to be considered in the design of a confinement in repair works. Most importantly, the majority codes of practice neglected the state of damaged of column prior to repair works and assumed the restoration of load carrying capacity of repaired columns is only up to original capacity of column before it was deteriorated. Therefore, the insight view of the influence of pre-damaged level in the effectiveness of active confinement is required to be examined. These issues are urgently needed to be solved before the confinement can be used confidently in the construction industry.

### **1.3 Objectives**

The aim of this research is to examine the structural performance of repaired RC columns using SSTT. A combination of experimental and modeling methods. The study focused on RC short columns by considering the effects of pre-damaged levels. The more specific objectives of this study are as follows:

- i. To investigate the applicability of using SSTT in repairing damaged concrete cylinder in the restoration of the load carrying capacity and ductility through physical testing;
- ii. To evaluate the affecting parameters in the restorability of repaired circular RC short columns;
- iii. To evaluate the structural performance of SSTT repairing techniques by using finite element modelling;
- iv. To develop a design procedure of the load-carrying capacity, ductility and stiffness of damaged structures using SSTT confinement.

## 1.4 Scope of Works

The study consists of three major parts. The first part is the development of stress-strain model for steel straps repair works, whilst the second part is the experimental work for RC columns. The third part consists of the development of numerical models. In the experimental works, the testing parameters are as follows:

- i. A total of 34 normal strength concrete (NSC) and high strength concrete (HSC) cylindrical specimens were prepared with an identical cross-section of 100 mm diameter and 200 mm in height. Three out of 34 specimens are referred as the control specimens without pre-damaged level and unconfined. The strength classes considered were C30/37, C50/60 and C80/95;
- ii. All specimens were pre-damaged before the confining works. The pre-damaged levels ranging from +50% to +80%, +80% to -80% and -80% to -50% from its ultimate load carrying capacity of concrete cylinders. The +50% to +80% pre-damaged level represents the damage conditions before it reached ultimate load capacity whilst, -80% to -50% pre-damaged levels indicate the percentage loss after peak load;
- iii. The layers of steel strapping used are 1, 2 and 3 layer with 10, 20 and 30 mm of clear spacing between steel straps respectively;
- iv. A series of 21 circular RC short columns with the identical size of 150 mm diameter and 600 mm height were fabricated and tested, which three of them were control columns without any repairing works;
- v. The steel reinforcement ratio considered is 1.78 %, 2.56 % and 4.55 %;
- vi. The strength classes considered were C30/37, C50/60 and C80/95. C50/60 was set as boundary between NSC and HSC columns;

- vii. The testing variables also include difference confining schemes, which are the layer of steel straps (1, 2 and 3 layer) and the clear spacing between the strapping (10, 20 and 30 mm);
- viii. A finite element (FE) model is developed by using Abaqus V.6.14. The concrete and steel reinforcement bars were simulated with 3D–eight node solid reduced integration element (C3D8R) and 2-node linear displacement (T3D2) elements. Plasticity theory was considered in the material properties of steel and concrete;
- ix. The boundary condition was considered as fixed at one-end. Embedded interaction was applied between concrete and steel bars. An axial compressions displacement was applied. Then, the model developed was validated with experimental results.

## **1.5 Significance of Study**

The main objective of this study is to determine the applicability of pre-tensioning confinements in repairing damaged columns. In order to identify the parameters that affect the effectiveness of confined columns, several damaged columns were prepared and then repaired with different confining schemes. Most importantly, the existing design guidelines for repair works considering the pre-damaged level has not yet been addressed. Therefore, numerical approach will be developed to simulate the effects of pre-damaged level, concrete compressive strength, longitudinal volumetric ratio and confinement effects towards repaired columns. The design equation is then developed for the repaired columns using steel straps. The overall view of this research is to capture the effectiveness of this confinement method so that it can be applied in practice.



## **1.6 Thesis Layout**

This thesis was divided into nine chapters. This chapter gives an insight into the background information on the importance of repairing the structure in RC columns. Based on the Chapter 1, the fundamental and parameter of this research were identified based on the existing literature review from previous researcher.

In Chapter 2, a brief discussion was presented to explain mechanism of active and passive confinement. Previous research on the use of various confining materials to repair or strengthen existing structures was reviewed. At the end of this chapter, the focus of this research was presented by identifying the main variables that affect the repair works. The literature review was extended to Chapter 3 to review comprehensively the effects of pre-damaged level in concrete cylinder and RC columns.

The damage assessment from other researchers' perspectives and design considerations were presented in Chapter 3. It addressed each type of damage, according to behaviour of cracks formation for plain cylinder and RC columns. The overview of the damage conditions was summarized for visual assessment purposes. From this chapter, the different pre-damaged levels were classified.

The experimental methodology was presented in Chapter 4. The chapter was divided into two parts, which is experimental and numerical studies. It contains the information about mix proportion of NSC and HSC. It also shows the details specimen with the full experimental setup procedure. The repairing techniques were also elaborated. The formation for the numerical model considered in this study was presented at the end of this chapter.

Chapter 5 outlines the development of stress-strain models. The results of stress-strain relationship were analyzed. After that, the stress-strain model for steel straps confinement was proposed. Other than that, the strength and stiffness models were proposed for design considerations of repair columns.

In Chapter 6, it shows the results of an experimental program where the effects of the test parameter were analyzed and discussed. The failure modes and load-deformation behaviour were detailed out based on different parameter configurations. Subsequently, the experimental data were compared to predict the effects of the variables in strength, stiffness and ductility of repairing RC columns.

The Chapter 7 presents the prediction based on numerical analysis. Finite element analysis model was developed with elasto-plastic approach. The prediction of load-deformation behaviour of finite element were compared with experimental studies. The accuracy of the model was reported. Conclusions were drawn based to the parametric study conducted.

Chapter 8 reviews existing design consideration for repair works. The design consideration of repair work using SSTT was proposed in consideration the axial capacity of repaired columns. The example of calculations was shown in this chapter with step by step process of repair works.

Chapter 9 summarizes the outcome of the experimental test for development of stress-strain model from cylindrical specimens and results of RC columns. It also concludes the findings from finite element analysis and proposed design considerations for repaired RC columns. Consequently, the future recommendations from this research study were stated at the end of this thesis.

## REFERENCES

- [1] Achillopoulou D. V., Karabinis A. I. Assessment of concrete columns repaired with fiber reinforced mortar through damage indexes and numerical model. *Construction and Building Materials*. 2015.81:248-56.
- [2] Xiong G. J., Wu X. Y., Li F. F., Yan Z. Load carrying capacity and ductility of circular concrete columns confined by ferrocement including steel bars. *Construction and Building Materials*. 2011.25(5):2263-8.
- [3] Gholampour A., Ozbakkaloglu T. Fiber-reinforced concrete containing ultra high-strength micro steel fibers under active confinement. *Construction and Building Materials*. 2018.187:299-306.
- [4] Li P., Wu Y.-F. Stress–strain behavior of actively and passively confined concrete under cyclic axial load. *Composite Structures*. 2016.149:369-84.
- [5] Nematzadeh M., Fazli S., Naghipour M., Jalali J. Experimental study on modulus of elasticity of steel tube-confined concrete stub columns with active and passive confinement. *Engineering Structures*. 2017.130:142-53.
- [6] Zhou C., A S., Qiu Y., Pan Q. Experimental Investigation of Axial Compressive Behavior of Large-Scale Circular Concrete Columns Confined by Prestressed CFRP Strips. *Journal of Structural Engineering*. 2019.145(8).
- [7] Frangou M., Pilakoutas K., Dritsos S. Structural repair/strengthening of RC columns. *Construction and Building Materials*. 1995.9(5):259-66.
- [8] Moghaddam H., Samadi M., Pilakoutas K., Mohebbi S. Axial compressive behavior of concrete actively confined by metal strips; part A: experimental study. *Materials and Structures*. 2010.43(10):1369-81.
- [9] Awang A. Z., Omar W., Hoong-Pin L., Ma C. K. Behaviour of externally-confined high strength concrete column under uniaxial compression load. *Apscc-Iccer 2012*2012. p. 1-9.
- [10] Ma C.-K., Awang A. Z., Omar W., Maybelle L. Experimental tests on SSTT-confined HSC columns. *Magazine of Concrete Research*. 2014.66(21):1084-94.
- [11] Sulaiman M. F., Ma C.-K., Apandi N. M., Chin S., Awang A. Z., Mansur S. A., et al. A Review on Bond and Anchorage of Confined High-strength Concrete. *Structures*. 2017.11.

- [12] Chin C.-L., Ma C.-K., Awang A. Z., Omar W., Kueh A. B. H. Stress-strain evaluation of steel-strapped high-strength concrete with modified self-regulating end clips. *Structural Concrete*. 2018.19(4):1036-48.
- [13] Kondraivendhan B., Pradhan B. Effect of ferrocement confinement on behavior of concrete. *Construction and Building Materials*. 2009.23(3):1218-22.
- [14] Kaish A. B. M. A., Alam M. R., Jamil M., Wahed M. A. Ferrocement Jacketing for Restrengthening of Square Reinforced Concrete Column under Concentric Compressive Load. *Procedia Engineering*. 2013.54:720-8.
- [15] Bansal P. P., Civil B. E., Structures C. Effect of Wire Mesh Orientation on Strength of Beams Retrofitted Using Ferrocement Jackets. *International Journal*. 2014.5(2).
- [16] Jayasree S., Ganesan N., Abraham R. Effect of ferrocement jacketing on the flexural behaviour of beams with corroded reinforcements. *Construction and Building Materials*. 2016.121:92-9.
- [17] Tastani S. P., Pantazopoulou S. J. Experimental evaluation of FRP jackets in upgrading RC corroded columns with substandard detailing. *Engineering Structures*. 2004.26(6):817-29.
- [18] Ganesh Prabhu G., Sundarraja M. C. Behaviour of concrete filled steel tubular (CFST) short columns externally reinforced using CFRP strips composite. *Construction and Building Materials*. 2013.47:1362-71.
- [19] Zahran E. H. Effect of GFRP Wraps on HSC Columns Strengthened with GFRP with Different Steel Ratio. *International Journal of Engineering and Applied Sciences (IJEAS)*. 2016.3(2):8-12.
- [20] Ghobarah A., Biddah A., Mahgoub M. Rehabilitation of Reinforced Concrete Columns Using Corrugated Steel Jacketing. *Journal of Earthquake Engineering*. 1997.1(4):651-73.
- [21] Wu Y., Griffith M. C., Oehlers D. J. Improving the strength and ductility of rectangular reinforced concrete columns through composite partial interaction: Tests. *Journal of Structural Engineering*. 2003.129(9):1183-90.
- [22] Nam T.-H., Park J., Yoon S.-J., Choi E. Behavior of Reinforced Concrete Columns Confined by New Steel-Jacketing Method. *Magazine of Concrete Research*. 2009.61(10):787-96.
- [23] Mesbah1a H.-A., Benzaid R. Damage-based stress-strain model of RC cylinders wrapped with CFRP composites. 2017.

- [24] Djafar-Henni I., Kassoul A. Stress–strain model of confined concrete with Aramid FRP wraps. *Construction and Building Materials*. 2018.186:1016-30.
- [25] Wang W., Sheikh M. N., Al-Baali A. Q., Hadi M. N. Compressive behaviour of partially FRP confined concrete: Experimental observations and assessment of the stress-strain models. *Construction and Building Materials*. 2018.192:785-97.
- [26] Ferrotto M. F., Cavaleri L., Papia M. Compressive response of substandard steel-jacketed RC columns strengthened under sustained service loads: From the local to the global behavior. *Construction and Building Materials*. 2018.179:500-11.
- [27] Karzad A. S., Leblouba M., Toubat S. A., Maalej M. Repair and strengthening of shear-deficient reinforced concrete beams using Carbon Fiber Reinforced Polymer. *Composite Structures*. 2019.223:110963.
- [28] Jiang S.-F., Zeng X., Shen S., Xu X. Experimental studies on the seismic behavior of earthquake-damaged circular bridge columns repaired by using combination of near-surface-mounted BFRP bars with external BFRP sheets jacketing. *Engineering Structures*. 2016.106:317-31.
- [29] Azmee N. M., Shafiq N. Ultra-high performance concrete: From fundamental to applications. *Case Studies in Construction Materials*. 2018.9:e00197.
- [30] Rashid M. A., Mansur M. A. Considerations in producing high strength concrete. *Journal of Civil Engineering (IEB)*. 2009.37(1):53-63.
- [31] Russell H. G., Anderson A. R., Banning J. O., Cook J. E., Frantz G. C., Hester W. T., et al. State-of-the-Art Report on High-Strength Concrete by ACI Committee 363. 1997.
- [32] CEP/FIB. High strength concrete -state of the art. SR 90/1. 1990.
- [33] ACI 318 A. C. I. State-of-the-art report on high-strength concrete. 1992.
- [34] BS EN. 206-1 (2000) Concrete–Part 1: Specification, performance, production and conformity. *British Standards Institution*. 2000:1-20.
- [35] BC 2. Design Guide of High Strength Concrete to Singapore Standard CP65: Building and Construction Authority, Singapore.; 2008.
- [36] Saatcioglu M., Razvi R. S. Strength and ductility of confined concrete. *Journal of Structural Engineering*. 1992.118(6):1590-607.
- [37] Saadatmanesh H., Ehsani M. R., Li M. W. Strength and Ductility of Concrete Columns Externally Reinforced with Fiber-Composite Straps. *ACI Structural Journal*. 1994.91(4):434-47.

- [38] Najdanović D., Milosavljević B. Strength and ductility of concrete confined circular columns. *Journal of the Croatian Association of Civil Engineers*. 2014.66(5):417-23.
- [39] Chen Q., Shin M., Andrawes B. Experimental study of non-circular concrete elements actively confined with shape memory alloy wires. *Construction and Building Materials*. 2014.61:303-11.
- [40] Oskouie A. V., Valizadeh S., Aminnejad M. Behavior comparison of passive and active frp confined rectangular and wall-like columns. *Forth International Conference on FRP Composites in Civil Engineering (CICE2008)* Zurich, Switzerland 2008.
- [41] Rousakis T. C., Tourtouras I. S. RC columns of square section – Passive and active confinement with composite ropes. *Composites Part B: Engineering*. 2014.58:573-81.
- [42] Al-Salloum Y. A. Compressive Strength Models of FRP-Confined Concrete. *Asia-Pacific Conference on FRP in Structures*2007.
- [43] Colajanni P., Fossetti M., Macaluso G. Effects of confinement level, cross-section shape and corner radius on the cyclic behavior of CFRCM confined concrete columns. *Construction and Building Materials*. 2014.55:379-89.
- [44] Ribeiro F., Sena-Cruz J., Branco F. G., Júlio E. Hybrid FRP jacketing for enhanced confinement of circular concrete columns in compression. *Construction and Building Materials*. 2018.184:681-704.
- [45] Hadi M. N. S., Li J. External reinforcement of high strength concrete columns. *Composite Structures*. 2004.65(3-4):279-87.
- [46] Osman M., Soliman A. E.-k. S. Behavior of Confined Columns under Different Techniques. *International Journal of Structural and Construction Engineering*. 2015.9(1):70-8.
- [47] Park T. W., Na U. J., Chung L., Feng M. Q. Compressive behavior of concrete cylinders confined by narrow strips of CFRP with spacing. *Composites Part B: Engineering*. 2008.39(7-8):1093-103.
- [48] Mander J. B., Priestley M. J., Park R. Theoretical stress-strain model for confined concrete. *Journal of Structural Engineering*. 1988.114(8):1804-26.

- [49] Huang L., Zhang C., Yan L., Kasal B. Flexural behavior of U-shape FRP profile-RC composite beams with inner GFRP tube confinement at concrete compression zone. *Composite Structures*. 2018.184:674-87.
- [50] Karimizadeh H., Eftekhari M. R., Mostofinejad D. Effects of Midlayer Used in FRP Confinement of RC Columns. *Journal of Composites for Construction*. 2019.23(2).
- [51] Safitri E., Imran I., Nuroji. Concrete Strength Enhancement Due to External Steel Ring Confinement. *Procedia Engineering*. 2017.171:934-9.
- [52] Shin H.-O., Yoon Y.-S., Cook W. D., Mitchell D. Enhancing the confinement of ultra-high-strength concrete columns using headed crossties. *Engineering Structures*. 2016.127:86-100.
- [53] Si Youcef Y., Amziane S., Chemrouk M. CFRP confinement effectiveness on the behavior of reinforced concrete columns with respect to buckling instability. *Construction and Building Materials*. 2015.81:81-92.
- [54] Xie J., Fu Q., Yan J.-B. Compressive behaviour of stub concrete column strengthened with ultra-high performance concrete jacket. *Construction and Building Materials*. 2019.204:643-58.
- [55] Fakharifard M., Chen G., Sneed L., Dalvand A. Seismic performance of post-mainshock FRP/steel repaired RC bridge columns subjected to aftershocks. *Composites Part B: Engineering*. 2015.72:183-98.
- [56] Kazemi M. T., Morshed R. Seismic shear strengthening of R/C columns with ferrocement jacket. *Cement and Concrete Composites*. 2005.27(7-8):834-42.
- [57] Xiao Y., Wu H. Compressive Behavior of Concrete Confined by Carbon Fiber Composite Jackets. *Journal of Materials in Civil Engineering*. 2000.12(2):139-46.
- [58] Wu Y.-F., Yun Y., Wei Y., Zhou Y. Effect of Predamage on the Stress-Strain Relationship of Confined Concrete under Monotonic Loading. *Journal of Structural Engineering*. 2014.140(12).
- [59] Liu X., Nanni A., Silva P. F. Rehabilitation of Compression Steel Members Using FRP Pipes Filled with Non-expansive and Expansive Light-weight Concrete. *Advances in Structural Engineering*. 2005.8(2):129-42.
- [60] Valdmanis V., De Lorenzis L., Rousakis T., Tepfers R. Behaviour and capacity of CFRP-confined concrete cylinders subjected to monotonic and cyclic

axial compressive load. *Structural Concrete London Thomas Telford Limited*. 2007.8(4):187.

[61] Panjehpour M., Farzadnia N., Demirboga R., Ali A. A. A. Behavior of High-Strength Concrete Cylinders Repaired with Cfrp Sheets. *Journal of Civil Engineering and Management*. 2015.22(1):56-64.

[62] Yan Z., Pantelides C. P., Asce M., Lawrence D. R. Posttensioned FRP Composite Shells for Concrete Confinement. *Journal of Composites for Construction*. 2007.11(1):81-90.

[63] Saadatmanesh H. Bridge retrofit using fiber reinforced polymer 2014 [Available from: <https://cseengineermag.com/article/bridge-retrofit-using-fiber-reinforced-polymer/>].

[64] Batson G. B., Castro J. O., Guerra A. J., Iorns M. E., Johnston C. D., Naaman A. E., et al. GUIDE FOR THE DESIGN, CONSTRUCTION, AND REPAIR OF FERROCEMENT. *ACI Structural Journal*. 1988.85(3):325-51.

[65] Paramasivam P., Ong K. C. G., Lim C. T. E. Ferrocement laminates for strengthening RC T-beams. *Cement and Concrete Composites*. 1994.16(2):143-52.

[66] Nassif H. H., Najm H. Experimental and analytical investigation of ferrocement–concrete composite beams. *Cement and Concrete Composites*. 2004.26(7):787-96.

[67] Takiguchi K., Fujita S. Experimental investigation on repair of damaged RC columns with circular ferrocement jacket. *25th Conference on our world in concrete and structures2000*.

[68] Pancharathi R. K., Oshima T., Mikami S., Yamazaki T., Cheruku S. Studies on RC and ferrocement jacketed columns subjected to simulated seismic loading. *Asian Journal of Civil Engineering*. 2008.8:215-25.

[69] Peled A. Confinement of Damaged and Nondamaged Structural Concrete with FRP and TRC Sleeves. *Journal of Composites for Construction - J COMPOS CONSTR*. 2007.11.

[70] Makki R. F. Response of reinforced concrete beams retrofitted by ferrocement. *Int J Sci Technol Res*. 2014.3:27-34.

[71] Sarno L. D., Elnashai A. S., Nethercot D. A. Seismic retrofitting of framed structures with stainless steel. *Journal of Constructional Steel Research*. 2006.62(1):93-104.



- [72] Belal M. F., Mohamed H. M., Morad S. A. Behavior of reinforced concrete columns strengthened by steel jacket. *HBRC Journal*. 2015.11(2):201-12.
- [73] Bett B. J., Klingner R. E., Jirsa J. O. Lateral load response of strengthened and repaired reinforced concrete columns. *Structural Journal*. 1988.85(5):499-508.
- [74] Ersoy U., Tankut A. T., Suleiman R. Behavior of jacketed columns. *Structural Journal*. 1993.90(3):288-93.
- [75] Rodriguez M., Park R. Seismic load tests on reinforced concrete columns strengthened by jacketing. *Structural Journal*. 1994.91(2):150-9.
- [76] Vadoros K. G., Dritsos S. E. Concrete jacket construction detail effectiveness when strengthening RC columns. *Construction and Building Materials*. 2008.22(3):264-76.
- [77] Mirmiran A., Shahawy, Mohsen. Behaviour of Concrete Columns Confined by Fiber Composites. *Journal of Structural Engineering*. 1997.123:583-90.
- [78] Harajli M. H. Cyclic response of concrete members with bond-damaged zones repaired using concrete confinement. *Construction and Building Materials*. 2007.21(5):937-51.
- [79] Eid R., Roy N., Paultre P. Normal- and High-Strength Concrete Circular Elements Wrapped with FRP Composites. *Journal of Composites for Construction*. 2009.13(2):113-24.
- [80] Olivova K., Bilcik J. Strengthening of Concrete Columns with CFRP. *Slovak Journal of Civil Engineering*. 2009.1:1-9.
- [81] El-Hacha R., Mashrik M. A. Effect of SFRP confinement on circular and square concrete columns. *Engineering Structures*. 2012.36:379-93.
- [82] He R., Sneed L. H., Belarbi A. Rapid Repair of Severely Damaged RC Columns with Different Damage Conditions: An Experimental Study. *International Journal of Concrete Structures and Materials*. 2013.7(1):35-50.
- [83] Nguyen-Minh L., Rovňák M. Size effect in uncracked and pre-cracked reinforced concrete beams shear-strengthened with composite jackets. *Composites Part B: Engineering*. 2015.78:361-76.
- [84] Guo Y., Xie J., Xie Z., Zhong J. Experimental study on compressive behavior of damaged normal- and high-strength concrete confined with CFRP laminates. *Construction and Building Materials*. 2016.107:411-25.

- [85] Abdullah, Takiguchi K. An investigation into the behavior and strength of reinforced concrete columns strengthened with ferrocement jackets. *Cement and Concrete Composites*. 2003.25(2):233-42.
- [86] Mourad S. M., Shannag M. J. Repair and strengthening of reinforced concrete square columns using ferrocement jackets. *Cement and Concrete Composites*. 2012.34(2):288-94.
- [87] Li B., Lam E. S.-s., Wu B., Wang Y.-y. Experimental investigation on reinforced concrete interior beam–column joints rehabilitated by ferrocement jackets. *Engineering Structures*. 2013.56:897-909.
- [88] Xiao Y., ASCE M., Wu H. Retrofitted of Reinforced Concrete Columns Using Partially Stiffened Steel Jackets. *Journal of Structural Engineering*. 2003.129(6):725-32.
- [89] Assas M. M. Efficiency of Corrugated Steel Jackets for Strengthening or Repairing Square Section Concrete Columns. *Life Science Journal*. 2014.11(8s).
- [90] Abdel-Hay A. S., Fawzy Y. A. G. Behavior of partially defected R.C columns strengthened using steel jackets. *HBRC Journal*. 2015.11(2):194-200.
- [91] Jodawat A., Parekh A., Marathe B., Pawar K., Sahu Y., Jain I. Retrofitting of Reinforced Concrete Column by Steel Jacketing. *International Journal of Engineering Research and Application*. 2016.6(7):1-5.
- [92] He A., Cai J., Chen Q.-J., Liu X., Xu J. Behaviour of steel-jacket retrofitted RC columns with preload effects. *Thin-Walled Structures*. 2016.109:25-39.
- [93] Nasersaeed H. Evaluation Behaviour and Seismic Retrofitting of RC Structures by Concrete Jackets. *Asian Journal of Applied Sciences*. 2011.4(3):221-8.
- [94] Chalioris C. E., Thermou G. E., Pantazopoulou S. J. Behaviour of rehabilitated RC beams with self-compacting concrete jacketing – Analytical model and test results. *Construction and Building Materials*. 2014.55:257-73.
- [95] Dubey R., Kumar P. Experimental study of the effectiveness of retrofitting RC cylindrical columns using self-compacting concrete jackets. *Construction and Building Materials*. 2016.124:104-17.
- [96] Eduardo J. N., Branco F. A., Silva V. D. Reinforced concrete jacketing-interface influence on monotonic loading response. *ACI Structural Journal*. 2005.102(2):252.

- [97] Yuce S. Z., Yuksel E., Bingol Y., Taskin K., Karadogan H. F. Local thin jacketing for the retrofitting of reinforced concrete columns. *Structural Engineering and Mechanics*. 2007.27(5):589-607.
- [98] Can A. A., Olguhan K. Ş., Fuat G. A., Yesevi O. F., Murat G., Ebru K., et al. Modal parameter identification of RC frame under undamaged, damaged, repaired and strengthened conditions. *Measurement*. 2018.124:260-76.
- [99] Gherdaoui M., Guenfoud M., Madi R. Punching behavior of strengthened and repaired RC slabs with CFRP. *Construction and Building Materials*. 2018.170:272-8.
- [100] Murthy A. R., Karihaloo B., Rani P. V., Priya D. S. Fatigue behaviour of damaged RC beams strengthened with ultra high performance fibre reinforced concrete. *International Journal of Fatigue*. 2018.116:659-68.
- [101] Ortega A. I., Pellicer T. M., Adam J. M., Calderón P. A. An experimental study on RC columns repaired on all four sides with cementitious mortars. *Construction and Building Materials*. 2018.161:53-62.
- [102] Lehman D. E., Gookin S. E., Nacamuli A. M., Moehle J. P. Repair of earthquake-damaged bridge columns. *Structural Journal*. 2001.98(2):233-42.
- [103] Hsu T. T., Slate F. O., Sturman G. M., Winter G., editors. Microcracking of plain concrete and the shape of the stress-strain curve. *Journal Proceedings*; 1963.
- [104] Shah S. P., Chandra S., editors. Fracture of concrete subjected to cyclic and sustained loading. *Journal Proceedings*; 1970.
- [105] Krishnaswamy K., editor Strength and microcracking of plain concrete under triaxial compression. *Journal Proceedings*; 1968.
- [106] Derucher K. Application of the scanning electron microscope to fracture studies of concrete. *Building and Environment*. 1978.13(2):135-41.
- [107] Ashkan S. Application of damage mechanics to describe the behavior of concrete under fatigue and freeze-thaw processes: North Dakota State University; 2015.
- [108] Liu H.-K., Liao W.-C., Tseng L., Lee W.-H., Sawada Y. Compression strength of pre-damaged concrete cylinders reinforced by non-adhesive filament wound composites. *Composites Part A: Applied Science and Manufacturing*. 2004.35(2):281-92.
- [109] Zhou Y., Liu X., Sui L., Xing F., Zhou H. Stress–strain model for fibre reinforced polymer confined load-induced damaged concrete. *Materials Research Innovations*. 2015.19(sup6):S6-125-S6-31.

- [110] Rabehi B., Ghernouti Y., Li A., Boumchedda K. Comparative behavior under compression of concrete columns repaired by fiber reinforced polymer (FRP) jacketing and ultra high-performance fiber reinforced concrete (UHPFRC). *Journal of Adhesion Science and Technology*. 2014.28(22-23):2327-46.
- [111] Ma G., Li H., Yan L., Huang L. Testing and analysis of basalt FRP-confined damaged concrete cylinders under axial compression loading. *Construction and Building Materials*. 2018.169:762-74.
- [112] Benjeddou O., Ouezdou M. B., Bedday A. Damaged RC beams repaired by bonding of CFRP laminates. *Construction and Building Materials*. 2007.21(6):1301-10.
- [113] Kreit A., Castel A., Francois R., Al-Mahmoud F., editors. Behavior of damaged RC beams repaired with NSM CFRP Rods. *Concrete Solutions 2011, 4th International Conference on Concrete Repair*; 2011.
- [114] El-Ashkar N., Morsy A., Helmi K. FRP repair technique for RC beams pre-damaged in shear. *Proceedings of 14th International Structural faults and repair*. 2012.
- [115] Fayyadh M. M., Razak H. A. Assessment of effectiveness of CFRP repaired RC beams under different damage levels based on flexural stiffness. *Construction and Building Materials*. 2012.37:125-34.
- [116] Wang Y. T., Du X. L., Jiang F. X., Zhang W., editors. The Flexural Performance of Pre-Damaged Reinforced Concrete Beam Strengthened with CFRP in Seawater Environment. *Applied Mechanics and Materials*; 2012: Trans Tech Publ.
- [117] Hussein M., Afefy H. M. E.-D., Khalil A.-H. A.-K. Innovative repair technique for RC beams predamaged in shear. *Journal of Composites for Construction*. 2013.17(6):04013005.
- [118] Kabir M. I., Subhani M., Shrestha R., Samali B. Experimental and theoretical analysis of severely damaged concrete beams strengthened with CFRP. *Construction and Building Materials*. 2018.178:161-74.
- [119] Laskar, Musaddiq S., Talukdar, Sudip. A study on the performance of damaged RC members repaired using ultra-fine slag based geopolymer mortar. *Construction and Building Materials*. 2019.217:216-25.
- [120] Jain S., Chellapandian M., Prakash S. S. Emergency repair of severely damaged reinforced concrete column elements under axial compression: An experimental study. *Construction and Building Materials*. 2017.155:751-61.

- [121] Gao P., Wang J., Li Z., Hong L., Wang Z. Effects of predamage on the compression performance of CFRP-confined rectangular steel reinforced concrete columns. *Engineering Structures*. 2018.162:109-20.
- [122] Chellapandian, Prakash M., Suriya S. Rapid repair of severely damaged reinforced concrete columns under combined axial compression and flexure: An experimental study. *Construction and Building Materials*. 2018.173:368-80.
- [123] Tayeh B. A., Naja M. A., Shihada S., Arafa M. Repairing and Strengthening of Damaged RC Columns Using Thin Concrete Jacketing. *Advances in Civil Engineering*. 2019.2019.
- [124] Takeuti A. R., de Hanai J. B., Mirmiran A. Preloaded RC columns strengthened with high-strength concrete jackets under uniaxial compression. *Materials and Structures*. 2008.41(7):1251-62.
- [125] Jiang T., Teng J. G. Analysis-oriented stress–strain models for FRP–confined concrete. *Engineering Structures*. 2007.29(11):2968-86.
- [126] Ozbakkaloglu T., Lim J. C., Vincent T. FRP-confined concrete in circular sections: Review and assessment of stress–strain models. *Engineering Structures*. 2013.49:1068-88.
- [127] 356 F. FEMA 356 Prestandard and Commentary for the Seismic Rehabilitation of Buildings. 2000.
- [128] EN 1998-1-1. Eurocode No. 8: Design of Structures for Earthquake Resistance, Part 1: General Rules, European Committee for Standardization, prEN-1998-1. 2004.
- [129] Grunthal G., Musson R., Schwarz J., Stucchi M. European Macroseismic Scale 1998. 1998.
- [130] Japan Building Disaster Prevention Association. Standards for evaluation of seismic capacity and guidelines for seismic rehabilitation of existing reinforced concrete buildings. 1990.
- [131] BS8110. Structural Use of Concrete, Part 1: Code of Practice for Design and Construction. *British Standards Institution, UK*. 1997.
- [132] EN 1992-1-1. Eurocode 2: Part 1.1: General rules and rules for buildings. 1992.
- [133] EN 1993-1-1. Eurocode 3: Design of Steel Structures - Part 1-1: General - General Rules and Rules for Buildings. . 1992.

- [134] Rocca S., Galati N., Nanni A., editors. Large-size reinforced concrete columns strengthened with carbon FRP: Experimental evaluation. *Third International Conference on FRP Composites in Civil Engineering (CICE 2006)*; 2006.
- [135] Designation A. E8/E8M-09, Standard test methods for tension testing of metallic materials. *American association state highway and transportation officials standard AASHTO*. (T68):1-3.
- [136] Awang A. Z. Behaviour of high strength concrete with pre-tensioning steel straps confinement 2013.
- [137] Ma C.-K., Awang A. Z., Omar W., Pilakoutas K., Tahir M. M., Garcia R. Elastic design of slender high-strength RC circular columns confined with external tensioned steel straps. *Advances in Structural Engineering*. 2015.18(9):1487-99.
- [138] Ilki A., Kumbasar N. Behavior of damaged and undamaged concrete strengthened by carbon fiber composite sheets. *Structural Engineering and Mechanics*. 2002.13(1):75-90.
- [139] Wu Y.-F., Yun Y., Wei Y., Zhou Y. Effect of predamage on the stress-strain relationship of confined concrete under monotonic loading. *Journal of Structural Engineering*. 2014.140(12):04014093.
- [140] Gu D.-S., Wu G., Wu Z.-S., Wu Y.-F. Confinement effectiveness of FRP in retrofitting circular concrete columns under simulated seismic load. *Journal of Composites for Construction*. 2010.14(5):531-40.
- [141] Iacobucci R. D., Sheikh S. A., Bayrak O. Retrofit of square concrete columns with carbon fiber-reinforced polymer for seismic resistance. *Structural Journal*. 2003.100(6):785-94.
- [142] Stoppenhagen D. R., Jirs J. O., Wyllie L. A. Seismic repair and strengthening of a severely damaged concrete frame. *Structural Journal*. 1995.92(2):177-87.
- [143] Garcia R., Hajirasouliha I., Guadagnini M., Helal Y., Jemaa Y., Pilakoutas K., et al. Full-scale shaking table tests on a substandard RC building repaired and strengthened with Post-Tensioned Metal Straps. *Journal of Earthquake Engineering*. 2014.18(2):187-213.
- [144] Helal Y., Garcia R., Pilakoutas K., Guadagnini M., Hajirasouliha I. Strengthening of short splices in RC beams using post-tensioned metal straps. *Materials and Structures*. 2016.49(1-2):133-47.

- [145] Ma C. K., Awang A. Z., Omar W. New theoretical model for SSTT-confined HSC columns. *Magazine of Concrete Research*. 2014.66(13):674-84.
- [146] Ma C. K., Awang A. Z., Omar W. Load-deformation Behaviour of Eccentrically Loaded SSTT-confined High Strength Concrete Columns. *Jurnal Teknologi*. 2015.74(4).
- [147] Kwan A. K. H., Dong C. X., Ho J. C. M. Axial and lateral stress-strain model for FRP confined concrete. *Engineering Structures*. 2015.99:285-95.
- [148] Luccioni B., Rougier V. A plastic damage approach for confined concrete. *Computers and structures*. 2005.83(27):2238-56.
- [149] Sumarac D., Sekulovic M., Krajcinovic D. Fracture of reinforced concrete beams subjected to three point bending. *International Journal of Damage Mechanics*. 2003.12(1):31-44.
- [150] ACI 562M-13. Code requirements for evaluation, repair and rehabilitation of concrete buildings and commentary. MI: American Concrete Institute.; 2013.
- [151] 440 A. C., editor ACI 440.2 R-02: Guide for the Design and Construction of Externally Bonded FRP Systems for Strengthening Concrete Structures 2003: American Concrete Institute.
- [152] Association C. S. CSA-S806-02, Design and Construction of Building Components with Fibre-Reinforced Polymers. *Toronto, ON, Canada*. 2002.
- [153] *fib* 14. Externally bonded FRP reinforcement for RC structures. Fédération Internationale du béton (Fib); 2001.
- [154] TR 55 T. C. S. Design Guidance for Strengthening Concrete Structures Using Fibre Composites Materials. 2004.
- [155] Richart F. E., Brandtzaeg A., Brown R. L. A study of the failure of concrete under combined compressive stresses. University of Illinois at Urbana Champaign, College of Engineering; 1928.