

POLYAMIDE THIN FILM NANOCOMPOSITE MEMBRANE INCORPORATED
WITH CARBON NANOTUBES/GRAPHENE OXIDE FOR CARBON DIOXIDE
REMOVAL

WONG KAR CHUN

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy

School of Chemical and Energy Engineering
Faculty of Engineering
Universiti Teknologi Malaysia

SEPTEMBER 2019

DEDICATION

This thesis is dedicated to my beloved mother, who taught me to be firm in my principle but flexible with my perspective by amassing knowledge from diverse sources. I would also like to dedicate my work to my father, who taught me that perseverance and hard work are integral parts of success as even the largest task can be accomplished if it is done one step at a time.

ACKNOWLEDGEMENT

I have met many knowledgeable and helpful people who have contributed towards my understanding and perception throughout my study. In particular, I wish to express my utmost appreciation to my main supervisor, Assoc. Prof. Ts. Dr. Goh Pei Sean. Her encouragement and guidance have been my greatest motivation to press on with research work while her criticism kept me on the right track. She has been very supportive and caring throughout my years of working under her supervision. I am also thankful to my co-supervisor Prof. Datuk Dr. Ahmad Fauzi Ismail for his guidance. A special thanks to my internship mentor, Dr Takaaki Taniguchi for his hospitality and valuable input during my stay in Japan. I am grateful to Mr. Ng BeCheer for his contribution and support on development and maintenance of filtration system. Without their continuous support, I will not be able to pursue my interest in nanomaterial and the completion of this thesis would have been impossible.

I felt grateful to Universiti Teknologi Malaysia (UTM) and National Institute for Materials Science (NIMS) for the funding and resources received.

My fellow friends and colleagues deserve recognition for their assistance on various occasions throughout my study. Time spent with them is truly enjoyable. Last but not least, I am grateful to all my family members.

ABSTRACT

Carbon capture and storage (CCS) is a feasible option to reduce the atmospheric carbon dioxide (CO₂) concentration that has is rising in an alarming rate. However, the implementation of CCS is hampered by the high operating cost that is associated with CO₂ removal from the emission sources. Membrane is one of the sustainable technologies that holds much potential to drive down this cost. Thin film nanocomposite (TFN) is a particularly attractive membrane as its nanomaterial-embedded ultrathin selective layer could permit good separation efficiency at high rate of mass transport. Even though carbon nanotube (CNT) is a prized nanomaterial that could greatly elevate the membrane strength and separation performance, its high aggregation tendency limits its usefulness for the development of CNT-based TFN. In this study, the dispersibility of CNT was improved through amino functionalization and addition of graphene oxide (GO). Amino groups on the surface of functionalized CNT (ACNT) sterically hindered the nanotubes from bundling while the amphiphilic GO acted as dispersant that prevented clustering of the nanomaterials. This allowed successful incorporation of the nanofillers into the membrane ultrathin selective layer during interfacial polymerization (IP). The impacts of nanofillers loading, combination and ratio on IP were systematically explored. The nanomaterials' properties such as hydrophilicity and adsorptivity was found to affect the reactivity of IP which in turn altered the characteristics of selective layer. Gas separation results show that incorporation of ACNT improved the membrane selectivity due to its narrow openings that favor transport of the small CO₂. On the other hand, incorporation of GO led to the formation of relatively thin selective layer which improved the membrane gas permeability. Co-incorporation of ACNT with GO boosted the permeability and CO₂/nitrogen selectivity of TFN by 30% and 60%, respectively, compared to the control membrane. The resulted TFN was also more reproducible and stable under elevated temperature and exposure to air. The outcome of this study suggested that synergetic incorporation of ACNT and GO provides an additional degree of freedom to control the formation of selective layer as compared to single-filler incorporation. TFN containing these two geometrically different carbon-based nanomaterials showed fascinating properties and deserves further in-depth development.

ABSTRAK

Pemerangkapan dan penyimpanan karbon (CCS) merupakan kaedah yang mampu dilaksanakan untuk mengurangkan kepekatan karbon dioksida (CO_2) dalam atmosfera yang kian meningkat pada kadar yang membimbangkan. Walau bagaimanapun, pelaksanaan CCS terhalang oleh tingginya kos pengendalian yang dikaitkan dengan proses penyingkiran CO_2 daripada punca pelepasan. Membran merupakan salah satu teknologi lestari yang berpotensi tinggi untuk mengurangkan kos ini. Komposit nano filem tipis (TFN) adalah membran yang sangat menarik kerana lapisan selektifnya amat nipis dan mengandungi bahan nano yang mampu memberikan kecekapan pemisahan yang baik pada kadar pengangkutan jisim yang tinggi. Walaupun tiub nano karbon (CNT) adalah bahan nano berharga yang boleh meningkatkan kekuatan serta prestasi pemisahan membran, kecenderungan penggumpalan yang tinggi menghadkan kegunaannya untuk pembangunan TFN berasaskan CNT. Dalam kajian ini, penyerakan CNT telah ditambah baik melalui pemfungsian amino dan penambahan grafina oksida (GO). Kumpulan-kumpulan amino di permukaan CNT yang telah difungsikan (ACNT) akan menghalang secara sterik tiub-tiub nano tersebut daripada terikat manakala GO yang bersifat amfifilik bertindak sebagai penyerak yang menghalang pengelompokan bahan-bahan nano. Ini menjayakan penggabungan pengisi-pengisi nano ke dalam lapisan selektif membran yang amat nipis semasa pempolimeran antara muka (IP). Kesan-kesan daripada muatan, kombinasi dan nisbah pengisi-pengisi nano kepada IP telah diterokai secara sistematik. Sifat-sifat bahan-bahan nano seperti kehidrofilikan dan keterserapan didapati boleh menjejaskan kereaktifan IP yang kemudian mengubah ciri-ciri lapisan selektif. Keputusan pemisahan gas menunjukkan bahawa penggabungan ACNT telah meningkatkan kememilihan membran kerana bukaannya yang sempit memudahkan pengangkutan CO_2 yang kecil. Sebaliknya, penggabungan GO membawa kepada pembentukan lapisan selektif yang lebih tipis yang mana telah meningkatkan kebolehtelapan membran terhadap gas. Penggabungan ACNT bersama GO telah menggalakkan kebolehtelapan dan kememilihan CO_2 /nitrogen TFN, masing-masing sebanyak 30% dan 60%, berbanding membran kawalan. TFN yang dihasilkan juga lebih mampu dihasilkan semula dan stabil apabila terdedah kepada udara serta suhu yang tinggi. Hasil kajian ini mencadangkan bahawa penggabungan ACNT dan GO secara sinergi memberikan darjah kebebasan yang lebih tinggi untuk mengawal pembentukan lapisan selektif berbanding penggabungan pengisi secara tunggal. TFN yang mengandungi kedua-dua bahan nano berasaskan karbon yang berbeza geometri ini menunjukkan ciri-ciri menarik dan patut dibangunkan secara lebih mendalam.

TABLE OF CONTENTS

	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	x
	LIST OF FIGURES	xi
	LIST OF ABBREVIATIONS	xiv
	LIST OF SYMBOLS	xvii
	LIST OF APPENDICES	xix
CHAPTER 1	INTRODUCTION	1
1.1	Background of Research	1
1.2	Problem Statements	4
1.3	Research Objectives	5
1.4	Research Scope	6
CHAPTER 2	LITERATURE REVIEW	9
2.1	CO ₂ Separation Technologies	9
2.2	Membranes Technology for CO ₂ Separation	12
2.2.1	Polymeric Membranes	12
2.2.2	Inorganic Membranes	15
2.2.3	Nanocomposite Membranes	16
2.3	Interfacial Polymerization	21
2.3.1	Parameters of Interfacial Polymerization	25
2.4	Gas Transport Across Polymeric Membrane	31

2.4.1	Polyethylene Oxide for CO ₂ Solubility Selective Membrane	33
2.4.2	Facilitated Transport Behavior of Amine	34
2.5	Function of Nanomaterials in Gas Separation Membrane	36
2.6	Carbon Nanotubes	42
2.7	Functionalization of CNT	44
2.8	Graphene Oxide	46
2.9	Limitation	48
2.10	Research Gap	48
CHAPTER 3	RESEARCH METHODOLOGY	51
3.1	Introduction	51
3.2	Materials	52
3.3	Nanofiller Synthesis	52
3.4	Fabrication of Membranes	53
3.5	Characterizations of Nanofillers and Membranes	55
3.5.1	Transmission Electron Microscopy	55
3.5.2	Raman Spectroscopy	56
3.5.3	X-ray Diffraction Spectroscopy	56
3.5.4	Optical Microscopy and Zeta Potential Analysis	56
3.5.5	Water Contact Angle Estimation	57
3.5.6	Ultraviolet-Visible Spectrophotometry	58
3.5.7	Fourier-Transform Infrared Spectroscopy	59
3.5.8	Atomic Force Microscopy	59
3.5.9	Field Emission Scanning Electron Microscopy	60
3.5.10	Gas Permeation Measurement	60
CHAPTER 4	RESULTS AND DISCUSSION	63
4.1	Characterization of Nanomaterials	63
4.2	Effect of GO Loading	70
4.2.1	Characteristics of TFNs Incorporated with Different GO Loading	70

4.2.2	Gas Separation Performance of TFNs Incorporated with Different GO Loading	74
4.3	Effect of Nanotube-Nanosheet Combination	77
4.3.1	Characteristics of TFNs Incorporated with Different Nanotube-Nanosheet Combination	77
4.3.2	Gas Separation Performance of TFNs Incorporated with Different Nanotube-Nanosheet Combinations	82
4.3.3	Impact of Support Properties on Membrane Performance	86
4.4	Effect of ACNT-GO combination ratio	88
4.4.1	Characteristics of TFNs Incorporated Different ACNT:GO Ratio	88
4.5	Thermal and Air Exposure Stability of TFN ³ -3:3	94
CHAPTER 5	CONCLUSIONS	99
5.1	Research Outcomes and Contributions to Knowledge	99
5.2	Recommendations	100
	REFERENCES	103
	LIST OF PUBLICATIONS	137

LIST OF TABLES

TABLE NO.	TITLE	PAGE
Table 2.1	Comparison between different CO ₂ separation technologies	11
Table 2.2	Composite membranes for CO ₂ separation applications	24
Table 2.3	Summary of membrane transport mechanisms	32
Table 3.1	List of membranes fabricated in this study	55
Table 3.2	Classification of membrane separation process based on MWCO	59
Table 4.1	Properties of synthesized nanofillers	70
Table 4.2	Membrane information summarized from FESEM and AFM analysis	73
Table 4.3	Gas separation performance of resulted membranes at 2 bar feed pressure and room temperature	74
Table 4.4	Properties of fabricated PSF support, TFC ² and TFNs ²	82
Table 4.5	Gas separation performance of TFC ² and TFNs ²	85
Table 4.6	Properties of TFN ³ with different ACNT:GO ratio	89
Table 4.7	Gas separation performance of TFN with different ACNT:GO ratio	92
Table 4.8	Gas separation performance of TFN ³ -3:3 at different temperature	96
Table 4.9	Gas separation performance of TFN ³ -3:3 with air exposure	96
Table 4.10	Comparison of CO ₂ separation performance between TFN ³ -3:3 and similar MMMs from literatures	98

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
Figure 2.1	Graphical illustration of CO ₂ /methane (CH ₄) selectivity versus CO ₂ permeance of different membrane systems including inorganic membranes and room temperature ionic liquid (RTIL) for comparison	14
Figure 2.2	The quantity of studies conducted on nanocomposite membranes from 2008 to 2018. The inset illustrated the proportion of works done on different type of nanocomposite membranes	17
Figure 2.3	Schematic diagram of nanocomposite membranes	18
Figure 2.4	Mixed matrix dope preparation by (A) dispersing filler in solvent prior polymer addition, (B) dispersion filler in solvent after polymer dissolved and (C) mixing filler dispersion into pre-dissolved polymer solution	19
Figure 2.5	TFN preparation via IP with filler dispersed into (A) aqueous phase or (B) organic phase	21
Figure 2.6	The quantity of studies conducted on TFN membranes from 2008 to 2018. The inset shows the breakdown of IP fabricated TFNs based on their applications	22
Figure 2.7	Model of thin film growth during IP showing (A) diamine saturated support, (B) formation of PA tuff, (C) lateral growth of PA resulting in belt-like structure and (D) thickening and densification of PA film due to diffusion of diamine within the growing film	27
Figure 2.8	Schematic of film growth: (A) formation of nascent film with uniformly distributed pinholes; (B, C and D) formation of second, third and fourth generation of bubble-like films. The surface morphology of film after (E) 20 min and (F) 25 min of reaction as well as (G) internal morphology are shown	28
Figure 2.9	The impact of support membrane pore size, wettability and lag time on the IP	30
Figure 2.10	Schematic of transport mechanism in fixed carrier facilitated transport membrane	35
Figure 2.11	Schematic diagram of (A) perfect interaction between of polymer and filler, (B) encapsulation of filler by rigidified polymer layer, (C) delamination of polymer from filler surface leading to void formation and (D) clogging of filler pore by penetrated polymer	39

Figure 2.12	Illustration of formation of (A) rigidified region and (B) interstitial void as solvent leaves a vitrified polymer mass	40
Figure 2.13	3D illustration of (A) SWCNT and (B) MWCNT	43
Figure 2.14	Schematic of generation-based covalent CNT modification with (A) showing the side view and (B) the top view	44
Figure 2.15	Structure of GO	46
Figure 3.1	Overall research flow	51
Figure 4.1	AFM images with height profiles of (A) graphite, (B) GO and (C) AGO. TEM images of (D) graphite, (E) GO, (F) AGO, (G) pristine CNT, (H) OCNT and (I) ACNT. Cyan arrows point to impurities (amorphous carbon deposition on CNT and small crystal fragment on graphite) while yellow arrows depict <i>l</i> -Phe deposition	65
Figure 4.2	(A) XRD, (B) FTIR and (C) Raman spectra of nanofillers	66
Figure 4.3	Suspension of nanofillers (from left: OCNT; GO, ACNT, AGO, OCNT-GO, OCNT-AGO, ACNT-GO, ACNT-AGO) in Solution B (A) right after sonication and (B) after 12 hr standing	68
Figure 4.4	Optical microscopy images of (A & B) OCNT, (C & D) GO, (E & F) ACNT, (G & H) AGO, (I & J) OCNT-GO, (K & L) OCNT-AGO, (M & N) ACNT-GO and (O & P) ACNT-AGO dispersion in Solution B. The nanotube to nanosheet ratio of all dual-filler systems is 1:1. Blue circles depict GO sheets whereas red circles depict aggregated AGO	69
Figure 4.5	FTIR spectra of commercial PSF and resulted composite membranes	71
Figure 4.6	Surface (top) and cross section (bottom) morphologies of (A) TFC ¹ , (B) TFN ¹ -0.1, (C) TFN ¹ -0.25, (D) TFN ¹ -0.5 and (E) TFN ¹ -1.0 obtained using FESEM at ×5k and ×10k magnification respectively	73
Figure 4.7	(A) Comparison of TFNs ¹ gas permeance using TFC ¹ as baseline. (B) Gas separation performance of the resulted membranes at different GO loading	76
Figure 4.8	Possible gas transport mechanisms displayed by GO incorporated TFN; (A) diffusion of small gas is less restricted by the PA network, (B and C) introduction of voids and tortuous paths within the PA layer and (D) high CO ₂ affinity induced by the presence of functional groups	76

Figure 4.9	(A) FTIR spectra of fabricated membranes and (B) UV-Vis spectrum of Solution B after adsorption of diamine monomers by different fillers for 12 hr	77
Figure 4.10	(A) Top and (B) cross sectional views of crater feature on synthesized PA layer. Surface morphologies of (C) TFC ² , (D) TFN ² -OCNT, (E) TFN ² -GO, (F) TFN ² -ACNT, (G) TFN ² -AGO, (H) TFN ² -OCNT-GO, (I) TFN ² -OCNT-AGO, (J) TFN ² -ACNT-GO and (K) TFN ² -ACNT-AGO	80
Figure 4.11	Cross sections of (A & B) hand-casted PSF support, (C) TFC ² , (D) TFN ² -OCNT, (E) TFN ² -GO, (F) TFN ² -ACNT, (G) TFN ² -AGO, (H) TFN ² -OCNT-GO, (I) TFN ² -OCNT-AGO, (J) TFN-ACNT ² -GO and (K) TFN-ACNT ² -AGO. Area bounded by orange lines refers to dense layer resulted from penetration of PA into PSF	81
Figure 4.12	Gas separation performance of TFNs ² in term of P_{CO_2} , \bar{P}_{CO_2} , $\alpha_{N_2}^{CO_2}$ and $\alpha_{CH_4}^{CO_2}$ at different feed pressures. Black and blue lines depict the baselines for comparing the performance of TFNs ² with TFC ² .	84
Figure 4.13	Proteins filtration results of hand-casted PSF membrane	87
Figure 4.14	Cross section of (A & C) commercial PSF membrane and (B & D) hand-casted membrane. Insets in Figure A and B are the areas analyzed using ImageJ software to estimate the percentage of volume within the polymer networks that is occupied by voids	87
Figure 4.15	Surface morphologies of (A) TFC ² , (B) TFC ³ , (C) TFN ³ -3:1, (D) TFN ³ -3:2, (E) TFN ³ -3:3, (F) TFN ³ -2:3 and (G) TFN ³ -1:3	89
Figure 4.16	Cross sections of (A) TFC ³ , (B) TFN ³ -3:1, (C) TFN ³ -3:2, (D) TFN ³ -3:3, (E) TFN ³ -2:3 and (F) TFN ³ -1:3. Area bounded by orange lines refers to dense layer resulted from penetration of PA into PSF	90
Figure 4.17	Gas separation performance of TFNs ³	91
Figure 4.18	The schematic diagram of TFN membrane illustrating the homogeneous distribution of GO/CNT within the PA layer	93
Figure 4.19	Effects of (A) temperature and (B) exposure to air on performance of TFN ³ -3:3	95
Figure 4.20	Comparison of membranes in this work with references on Robeson's curve	97

LIST OF ABBREVIATIONS

2D	-	two dimensional
3D	-	three dimensional
ACNT	-	amino-functionalized carbon nanotube
AFM	-	atomic force microscopy
AGO	-	amino-functionalized graphene oxide
ATR	-	attenuated total reflection
CA	-	cellulose acetate
CCS	-	carbon capture and storage
CE	-	closed environment
CMS	-	carbon molecular sieve
CNT	-	carbon nanotube
CVD	-	chemical vapor deposition
DGBAmE	-	diethylene glycol bis(3-aminopropyl) ether
DNMDAm	-	3,3'-diamino-N-methyldipropylamine
EO	-	ethylene oxide
E-spun	-	electrospun
FESEM	-	field emission scanning electron microscopy
FO	-	forward osmosis
FTIR	-	Fourier transform infrared spectroscopy
GO	-	graphene oxide
GPU	-	gas permeation unit
HCl	-	hydrochloric acid
ID	-	internal diameter
IL	-	ionic liquid
ImGO	-	imidazole modified GO
IP	-	interfacial polymerization
IPC	-	isophthaloyl chloride
<i>l</i> -Phe	-	<i>l</i> -phenylalanine
MEDA	-	N-methyldiethanolamine
MMM	-	mixed matrix membrane

MOF	-	metal organic framework
MPD	-	m-phenylenediamine
MWCNT	-	multi-walled carbon nanotube
MWCO	-	molecular weight cut-off
nCNT	-	m-phenylenediamine modified carbon nanotube
NF	-	nanofiltration
nHNT	-	modified halloysite nanotube
NMP	-	N-methyl-2-pyrrolidone
OCNT	-	oxidized multiwalled carbon nanotube
OD	-	outer diameter
OE	-	opened environment
PA	-	polyamide
PC	-	polycarbonate
PDMS	-	polydimethylsiloxane
PEA	-	polyetheramine
PEG	-	polyethylene glycol
PEI	-	polyetherimine
PEO	-	polyethylene oxide
PES	-	polyethersulfone
PI	-	polyimide
PILM	-	poly(ionic liquid) membrane
PIP	-	piperazine
POS	-	polysiloxane
PRG	-	porous reduce graphene oxide
PSF	-	polysulfone
PVA	-	polyvinylalcohol
PVAm	-	polyvinyl amine
PVDF	-	polyvinylidene fluoride
PVP	-	polyvinyl pyrrolidone
<i>r.t.</i>	-	room temperature
RH	-	relative humidity
RO	-	reverse osmosis
RTIL	-	room temperature ionic liquid

SDS	-	sodium dodecyl sulfate
SILM	-	supported ionic liquid membrane
STP	-	standard pressure and temperature
SWCNT	-	single-walled carbon nanotube
Syn. Con.	-	synthesis condition
TEM	-	transition electron microscopy
TETA	-	triethylenetetramine
TFC	-	thin film composite
TFN	-	thin film nanocomposite
TMC	-	trimesoyl chloride
TNT	-	titanium nanotube
UF	-	ultrafiltration
UV-Vis	-	ultraviolet-visible spectrophotometry
WCA	-	water contact angle
XRD	-	X-ray diffraction spectroscopy

LIST OF SYMBOLS

$\ddot{R}_{x:y}$	-	ratio between filler 'x' and filler 'y'
\bar{P}	-	permeability
θ_{XRD}	-	diffraction angle of sample
θ_{XRD}	-	X-ray diffraction angle
\ddot{F}	-	type of filler combination
\ddot{L}	-	filler loading
ΔP	-	percentage change in permeance
ΔSP	-	difference in separation performance in term of permeance, permeability or selectivity
$\Delta\alpha$	-	percentage change in selectivity
A	-	effective membrane area
A_f	-	absorbance of UV by feed solution
A_p	-	absorbance o UV by permeate solution
A_q	-	aqueous phase
C	-	packing constant in Washburn's equation
D	-	diffusivity
d_k	-	kinetic diameter
d_p	-	pore diameter
d-spacing	-	interlayer distance
I_d	-	intensity of D-band in Raman spectrum
I_g	-	intensity of G-band in Raman spectrum
Kn	-	Knudsen number
L	-	length
l	-	thickness of membrane selective layer
l_F	-	thickness of PA film above support
l_P	-	penetration depth of PA into support
l_{Pavg}	-	average PA penetration at different synthesis condition
l_T	-	total thickness of selective layer of fabricated composite membrane ($l_F + l_{\text{Pavg}}$)
m	-	mass

M	-	molar
n	-	number of pores
N_p	-	molar flow rate through single pore
N_t	-	total molar flow rate
Og	-	organic phase
P	-	permeance
Q	-	volumetric flowrate of gas
R	-	universal gas constant
R_a	-	average plane roughness
r_m	-	average pore radii
R_{p-v}	-	peak-to-valley roughness
S	-	solubility
SP	-	separation performance in term of permeance, permeability or selectivity
T	-	temperature
t	-	time
T_g	-	glass transition temperature
Vap _{hex}	-	n-hexane vapor saturated environment
α	-	selectivity
γ	-	surface tension
Δp	-	pressure differential
ζ	-	zeta potential
η	-	viscosity
θ_h	-	hexane contact angle
θ_w	-	water contact angle
λ_{Kn}	-	gas mean free path length
λ_{Raman}	-	irradiation wavelength in Raman spectroscopy
λ_{XRD}	-	irradiation wavelength in X-ray diffraction spectrometer
ρ	-	density

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
Appendix A	Nanofillers Synthesis Procedures	129
Appendix B	Experimental Setup for MWCNT Oxidation	130
Appendix C	Experimental Setup for Graphite Oxidation	131
Appendix D	Fabrication Steps of PSF Support	132
Appendix E	Fabrication Steps of TFC or TFN	133
Appendix F	Experimental Setups for Interfacial Polymerization	134
Appendix G	Gas Permeation System	135

CHAPTER 1

INTRODUCTION

1.1 Background of Research

In recent years, awareness on the global warming has increased tremendously as people around the world began to feel the effects of dramatically raising earth temperature. Change in the world climate pattern and damage to the natural ecosystem are some of the devastations of global warming that affect our daily life (Powell and Qiao, 2006). The surge in anthropogenic activities including fossil fuel and coal combustion, natural gas exploration, biogas anaerobic digestion, and deforestation over the past century has resulted in the release of large amount of carbon dioxide (CO₂) into the atmosphere. This unregulated atmospheric CO₂ acts as an invisible blanket that retard the dissipation of heat from the earth, leading to accumulation of heat and consequently global warming. The global population is expected to expand close to 10 billion inhabitants by year 2050 (Lalia *et al.*, 2013), the increase in the world resources and energy demand is inevitable and will only bring about greater greenhouse gases emission (Adewole *et al.*, 2013). Hence, removal and mitigation of CO₂ emission are highly desired and thus becoming hot research topics (Lindau, Jönsson and Wimmerstedt, 1995). In addition to adverse environmental impacts, CO₂ also represents serious problem to the natural gas processing industry as it can lower the heating value of product stream and corrode the pipelines of transportation system due to its acidic nature (Zhang *et al.*, 2013).

CO₂ capture and storage (CCS) is well accepted by scientists and policy makers as a viable approach to mitigate this alarming issue (Dixon *et al.*, 2013; Pires *et al.*, 2011). However, separating this potent greenhouse component accounts for nearly 80% of the total cost involved in CO₂ sequestration (Choi, Kim and Lee, 2013; Favre, 2011). Therefore, development of economic means for capturing the CO₂ from the source of emission is crucial for successful implementation of CCS (Czyperek *et al.*,

2010). Membrane technology prevails as a viable option due to its design simplicity and modularity that ease scaling up process. Membrane separation is relatively energy efficient compared to conventional approaches such as absorption and cryogenic separation (Sanders *et al.*, 2013). Hybrid phase composite membrane known as mixed matrix membrane (MMM) is currently the most intensively studied membrane due to its capability to surpass the inherent performance limitations, i.e. Robeson's trade-off of polymeric material (Adewole *et al.*, 2013; Bastani, Esmaeili and Asadollahi, 2013). MMM consists of a dispersed phase of inorganic fillers within a polymeric host matrix. The fillers in used can be categorized as porous and non-porous materials. Porous materials include zeolite, carbon molecular sieve (CMS), activate carbon, metal organic framework (MOF) and carbon nanotube (CNT). Examples of non-porous materials are silica, titanium oxide (TiO₂) and fullerene particles.

In a typical MMM, fillers can occupy up to 30% of the membrane total weight (Bastani *et al.*, 2013; Castro-Muñoz and Fíla, 2019; Kim and Nair, 2013; Shahid *et al.*, 2015). Since the dense skin of membrane is the primary layer responsible for separation function, embedment of nanofillers should be focused within the skin layer in order to fully harness the nanofillers potential and achieve a well-balance productivity-to-cost ratio. Despite the colossal amount of studies (Guo *et al.*, 2015; Kiadehi *et al.*, 2015b; Quan *et al.*, 2017; De Sitter *et al.*, 2014; Zhang *et al.*, 2019) and reviews (Cui, Kundalwal and Kumar, 2016; Swain *et al.*, 2017; Yao and Wang, 2014; Zhang *et al.*, 2013) that showed promise of membrane performance enhancement though the incorporation of nanofillers, controlling the distribution of nanofillers within the MMM has been proven to be extremely difficult (Aroon *et al.*, 2010a). In fact, most of the nanofillers incorporated through single-step phase inversion technique tend to distribute within the porous support layer of MMM (Chung *et al.*, 2007; Khulbe, Feng and Matsuura, 2008; Tan *et al.*, 2019). This implied that a large portion of these precious nanomaterials would be wasted as they do not contribute actively in the separation process

In regard to this concern, the two-step approach involved in the fabrication of thin film nanocomposite (TFN) membrane is the key to overcome the constraints with fillers distribution (Seman, Khayet and Hilal, 2010). The selective skin layer of TFN is deposited on a pre-formed porous support layer. This two-step approach provides the flexibility to discretely manipulate the composite layers to attain the preferred properties (Albo, Wang and Tsuru, 2014; Misdan *et al.*, 2013). Through this approach, the distribution of nanofillers can be precisely controlled, i.e. deposited solely within the skin layer of the membrane or throughout the substrate. Among the coating techniques developed for the fabrication of the TFN skin, interfacial polymerization (IP) is very interesting because this technique is highly scalable and is already widely adopted in the industry (Liu *et al.*, 2011; Yu *et al.*, 2010; Yu *et al.*, 2011). Additionally, the availability of a vast variety of monomers enables the thin film chemistry to be freely tuned (Espeso *et al.*, 2006; Song *et al.*, 2005).

Contemporary, much of the development on IP fabricated TFN centered around the field of water treatment. The deployment of IP to produce gas separation membrane still lags behind (Li *et al.*, 2013). In fact, polyamide (PA) layer synthesized through IP possesses many attractive characteristics for gas separation such as high mechanical strength, thermal stability and chemical resistivity (Albo *et al.*, 2014; Petersen and Peinemann, 1997). More importantly, PA thin film is found capable of promoting CO₂ transport across the membrane (Andrew Lee, Stevens and Kentish, 2013). Hence, there are enormous opportunities for in-depth research and development of IP fabricated TFN for gas separation application which can be explored in this work.

1.2 Problem Statements

Low energy consumption of TFN is conferred by the membrane low feed pressure requirement to afford separation while retaining a high output. This is made possible by the extremely thin skin of TFN. Apart from reducing the thickness of selective layer to ease mass transport for high gas permeability, alteration to the polymer network such as increasing the mobility of polymer chain, pore size and porosity could be made. However, doing so diminishes the sieving ability of the selective layer. This permeability-selectivity trade-off is the fundamental limitation to the separation performance of a polymeric material. The contemporary strategy to negate this trade-off is by incorporating filler materials with superior separation capability into the polymer network. CNT is one of such materials. Once embedded into the skin layer, CNT functions as rapid transport channel that drives the diffusion of gas molecules across the membrane and resulted in high productivity. Besides, the nanotube precise and narrow aperture ensures good selectivity of the nanocomposite materials. Additionally, the incorporation of inorganic nanofillers has been known to elevate the physical and thermal stability of the polymeric matrix which can improve resistant to aging and plasticization (Kanehashi *et al.*, 2018). In this study, multi-walled carbon nanotube (MWCNT) was employed as the primary filler to enhance the performance of TFN.

Despite the advantages offered through the incorporation of MWCNT, past studies have witnessed poor compatibility between this nanofiller and the polymer matrix (Shen *et al.*, 2013). Moreover, MWCNT is prone to agglomeration due to its high aspect ratio (Annala, Lahelin and Seppälä, 2012; Goh *et al.*, 2010). This is a major hiccup to the development of nanocomposite membrane as the overall transport properties of the membrane are critically dependent on the nanoscale interface morphology of the membrane (Goh *et al.*, 2011; Kim *et al.*, 2016; Swain *et al.*, 2017). Ideally, good inorganic-polymer interaction and homogeneous nanofillers dispersion are favorable for fabrication of defect-free nanocomposite membrane especially when the nanofillers are incorporated into the ultrathin skin of TFN. Amino functionalization and co-dispersion of MWCNT with graphene oxide (GO) were adopted in this study to circumvent this challenge. Introduction of amino functional groups on the nanotube

surface reduces the inter-tube Van de Waals interaction and sterically hinders entanglement of MWCNT. Insertion of highly dispersive GO nanosheets can aid with the debundling and dispersion of the nanotubes in aqueous solution. Moreover, the presence of CO₂-affinitive functional groups such as amino can enhance the membrane overall CO₂ permeance whereas GO sheets can alter the tortuosity of the composite matrix which lead to better sieving property. It is of great interest in this research to investigate the impacts of incorporation of MWCNT, GO and their amino-functionalized counterparts (individually or as nanotube-nanosheet combination) on the TFN formation and CO₂ separation performance.

1.3 Research Objectives

Based on the aforementioned issues, this study sets out with the following objectives:

1. To study the effects of amino functionalization and GO co-dispersion on the dispersibility of MWCNT in aqueous solution containing diamine monomers.
2. To develop TFN membrane with different nanofillers loading, combination and ratio in the PA skin layer.
3. To investigate the CO₂ separation performance of PA-based TFN incorporated with nanotube-nanosheet in term of permeance and selectivity.
4. To study the stability of CO₂ separation performance of TFN at elevated temperature and exposure to air.

1.4 Research Scope

The scopes of study have been identified and are listed below:

For Objective 1:

- (a) Oxidizing MWCNT (OCNT) using a mix of sulfuric acid (H_2SO_4)/nitric acid (HNO_3) under reflux condition.
- (b) Synthesizing GO from graphite via modified Hummer's method.
- (c) Functionalizing OCNT and GO with amino groups under basic condition to obtain amino-functionalized CNT (ACNT) and amino-functionalized GO (AGO) respectively.
- (d) Characterizing the chemical properties of pristine and modified nanofillers via Fourier transform infrared spectroscopy (FTIR).
- (e) Studying the morphology of nanofillers via transition electron microscopy (TEM) and atomic force microscopy (AFM).
- (f) Characterizing the crystallinity and degree of distortion in the nanofillers graphitic structure via X-ray diffraction spectroscopy (XRD) and Raman spectroscopy respectively.
- (g) Determining the hydrophilicity of nanofillers using Washburn's equation.
- (h) Evaluating the dispersibility of nanoparticles in aqueous solution containing diamine monomers using optical microscope and zeta potential (ζ) analyzer.
- (i) Determining the diamine adsorptivity of nanofillers via ultraviolet-visible spectrophotometry (UV-Vis)

For Objective 2:

- (a) Preparing polysulfone (PSF) dope solution containing polyvinyl pyrrolidone (PVP) and N-methyl-2-pyrrolidone (NMP) as additive and solvent respectively.
- (b) Fabricating PSF support membrane via solvent-nonsolvent phase inversion technique.
- (c) Characterizing chemical properties, morphologies and surface roughness of PSF support via FTIR, field emission scanning electron microscopy (FESEM) and AFM, respectively.
- (d) Determining the molecular weight cut-off (MWCO) of PSF support based on rejection of various proteins.
- (e) Forming PA skin layer which is embedded with nanofiller atop PSF support via IP technique to obtain TFN.
- (f) Manipulating nanofiller loading (0.00 mg/mL – 1.00 mg/mL), nanotube-nanosheet combination (OCNT-GO, OCNT-AGO, ACNT-GO, ACNT-AGO) and weight (*wt*) ratio of nanotube-nanosheet (3:1, 3:2, 3:3, 2:3 and 1:3).
- (g) Characterizing chemical properties, morphologies and surface roughness of TFNs via FTIR, FESEM and AFM, respectively.

For Objective 3:

- (a) Evaluating the effects of nanofiller incorporation parameters (loading, type of nanofiller, combination and ratio) on PA formation and TFN CO₂ separation performance using custom-built testing rig.

For Objective 4:

- (a) Evaluating the performance stability of TFN at different operating temperature (30 – 70 °C) and exposure to air for a period of 20 days.

REFERENCES

- Abdolmaleki, A., Mallakpour, S. and Borandeh, S. (2013) Amino acid-functionalized multi-walled carbon nanotubes for improving compatibility with chiral poly(amide-ester-imide) containing *l*-phenylalanine and *l*-tyrosine linkages, *Appl. Surf. Sci.*, 287, 117–123.
- Ackerman, D. M., Skoulidas, A. I., Sholl, D. S. and Johnson, J. K. (2003) Diffusivities of Ar and Ne in carbon nanotubes, *Mol. Simul.*, 29(10–11), 677–684.
- Adewole, J. K., Ahmad, A. L., Ismail, S. and Leo, C. P. (2013) Current challenges in membrane separation of CO₂ from natural gas: A review, *Int. J. Greenh. Gas Control*, 17, 46–65.
- Ahmad, A. L., Jawad, Z. A., Low, S. C. and Zein, S. H. S. (2014) A cellulose acetate/multi-walled carbon nanotube mixed matrix membrane for CO₂/N₂ separation, *J. Memb. Sci.*, 451, 55–66.
- Ahmad, A. L. and Ooi, B. S. (2005) Properties-performance of thin film composites membrane: Study on trimesoyl chloride content and polymerization time, *J. Memb. Sci.*, 255, 67–77.
- Ahn, J., Chung, W. J., Pinnau, I. and Guiver, M. D. (2008) Polysulfone/silica nanoparticle mixed-matrix membranes for gas separation, *J. Memb. Sci.*, 314, 123–133.
- Albo, J., Wang, J. and Tsuru, T. (2014) Gas transport properties of interfacially polymerized polyamide composite membranes under different pre-treatments and temperatures, *J. Memb. Sci.*, 449, 109–118.
- Alghunaim, A., Kirdponpattara, S. and Newby, B. Z. (2016) Techniques for determining contact angle and wettability of powders, *Powder Technol.*, 287, 201–215.
- Alhwaige, A. A., Alhassan, S. M., Katsiotis, M. S., Ishida, H. and Qutubuddin, S. (2015) Interactions, morphology and thermal stability of graphene-oxide reinforced polymer aerogels derived from star-like telechelic aldehyde-terminal benzoxazine resin, *RSC Adv.*, 5(112), 92719–92731.

- Andrew Lee, S., Stevens, G. W. and Kentish, S. E. (2013) Facilitated transport behavior of humidified gases through thin-film composite polyamide membranes for carbon dioxide capture, *J. Memb. Sci.*, 429, 349–354.
- Angelucci, R., Boscolo, I., Ciorba, A., Cuffiani, M., Malferrari, L., Montanari, A., Odorici, F., Orlanducci, S., Rizzoli, R., Rossi, M., Sessa, V., Terranova, M. L. and Veronese, G. P. (2010) Honeycomb arrays of carbon nanotubes in alumina templates for field emission based devices and electron sources, *Phys. E Low-dimensional Syst. Nanostructures*, 42(5), 1469–1476.
- Annala, M., Lahelin, M. and Seppälä, J. (2012) The effect of MWCNTs on molar mass in in situ polymerization of styrene and methyl methacrylate, *Eur. Polym. J.*, 48(9), 1516–1524.
- Ansaloni, L., Zhao, Y., Jung, B. T., Ramasubramanian, K., Baschetti, M. G. and Ho, W. S. W. (2015) Facilitated transport membranes containing amino-functionalized multi-walled carbon nanotubes for high-pressure CO₂ separations, *J. Memb. Sci.*, 490, 18–28.
- Araújo, O. de Q. F. and de Medeiros, J. L. (2017) Carbon capture and storage technologies: present scenario and drivers of innovation, *Curr. Opin. Chem. Eng.*, 17, 22–34.
- Aroon, M. A., Ismail, A. F., Matsuura, T. and Montazer-Rahmati, M. M. (2010a) Performance studies of mixed matrix membranes for gas separation: A review, *Sep. Purif. Technol.*, 75(3), 229–242.
- Aroon, M. A., Ismail, A. F., Montazer-Rahmati, M. M. and Matsuura, T. (2010b) Effect of chitosan as a functionalization agent on the performance and separation properties of polyimide/multi-walled carbon nanotubes mixed matrix flat sheet membranes, *J. Memb. Sci.*, 364, 309–317.
- Askari, M. and Chung, T. S. (2013) Natural gas purification and olefin/paraffin separation using thermal cross-linkable co-polyimide/ZIF-8 mixed matrix membranes, *J. Memb. Sci.*, 444, 173–183.
- Athanasekou, C., Pedrosa, M., Tsoufis, T., Pastrana-Martínez, L. M., Romanos, G., Favvas, E., Katsaros, F., Mitropoulos, A., Psycharis, V. and Silva, A. M. T. (2017) Comparison of self-standing and supported graphene oxide membranes prepared by simple filtration: Gas and vapor separation, pore structure and stability, *J. Memb. Sci.*, 522, 303–315.

- Avilés, F., Cauich-Rodríguez, J. V., Moo-Tah, L., May-Pat, A. and Vargas-Coronado, R. (2009) Evaluation of mild acid oxidation treatments for MWCNT functionalization, *Carbon*, 47(13), 2970–2975.
- Balasubramanian, R. and Chowdhury, S. (2015) Recent advances and progress in the development of graphene-based adsorbents for CO₂ capture, *J. Mater. Chem. A*, 3(44), 21968–21989.
- Banerjee, R., Furukawa, H., Britt, D., Knobler, C., O’Keeffe, M. and Yaghi, O. M. (2009) Control of pore size and functionality in isorecticular zeolitic imidazolate frameworks and their carbon dioxide selective capture properties, *J. Am. Chem. Soc.*, 131(11), 3875–3877.
- Banihashemi, F., Pakizeh, M. and Ahmadpour, A. (2011) CO₂ separation using PDMS/ZSM-5 zeolite composite membrane, *Sep. Purif. Technol.*, 79(3), 293–302.
- Bansal, M., Lal, C., Srivastava, R., Kamalasanan, M. N. and Tanwar, L. S. (2010) Comparison of structure and yield of multiwall carbon nanotubes produced by the CVD technique and a water assisted method, *Phys. B Condens. Matter*, 405(7), 1745–1749.
- Baroña, G. N. B., Lim, J., Choi, M. and Jung, B. (2013) Interfacial polymerization of polyamide-aluminosilicate SWNT nanocomposite membranes for reverse osmosis, *Desalination*, 325, 138–147.
- Bastani, D., Esmaceli, N. and Asadollahi, M. (2013) Polymeric mixed matrix membranes containing zeolites as a filler for gas separation applications: A review, *J. Ind. Eng. Chem.*, 19(2), 375–393.
- Basu, S., Cano-Odena, A. and Vankelecom, I. F. J. (2010) Asymmetric Matrimid[®]/[Cu₃(BTC)₂] mixed-matrix membranes for gas separations, *J. Memb. Sci.*, 362, 478–487.
- Berezkin, A. V. and Khokhlov, A. R. (2006) Mathematical modeling of interfacial polycondensation, *J. Polym. Sci. Part B Polym. Phys.*, 44(18), 2698–2724.
- Briggs, N. M., Weston, J. S., Li, B., Venkataramani, D., Aichele, C. P., Harwell, J. H. and Crossley, S. P. (2015) Multiwalled carbon nanotubes at the interface of pickering emulsions, *Langmuir*, 31(48), 13077–13084.
- Briggs, N., Raman, A. K. Y., Barrett, L., Brown, C., Li, B., Leavitt, D., Aichele, C. P. and Crossley, S. (2018) Stable pickering emulsions using multi-walled carbon nanotubes of varying wettability, *Colloids Surfaces A*, 537, 227–235.

- Bruggen, B. V. D., Vandecasteele, C., Gestel, T. V., Doyen, W. and Leysen, R. (2003) A review of pressure-driven membrane processes in wastewater treatment and drinking water production, *Environ. Prog.*, 22(1), 46–56.
- Brunetti, A., Scura, F., Barbieri, G. and Drioli, E. (2010) Membrane technologies for CO₂ separation, *J. Memb. Sci.*, 359, 115–125.
- Bui, N. N., Lind, M. L., Hoek, E. M. V and McCutcheon, J. R. (2011) Electrospun nanofiber supported thin film composite membranes for engineered osmosis, *J. Memb. Sci.*, 385–386, 10–19.
- Calvo, J. I., Peinador, R. I., Prádanos, P., Bottino, A., Comite, A., Firpo, R. and Hernández, A. (2015) Porosimetric characterization of polysulfone ultrafiltration membranes by image analysis and liquid-liquid displacement technique, *Desalination*, 357, 84–92.
- Cao, W., Lu, L., Zhou, M., Tow, G. M., Huang, L., Yang, T. and Lu, X. (2017) Hydrophilicity effect on CO₂/CH₄ separation using carbon nanotube membranes: insights from molecular simulation, *Mol. Simul.*, 43(7), 502–509.
- Car, A., Stropnik, C., Yave, W. and Peinemann, K. V. (2008a) PEG modified poly(amide-b-ethylene oxide) membranes for CO₂ separation, *J. Memb. Sci.*, 307, 88–95.
- Car, A., Stropnik, C., Yave, W. and Peinemann, K. V. (2008b) Pebax[®]/polyethylene glycol blend thin film composite membranes for CO₂ separation: Performance with mixed gases, *Sep. Purif. Technol.*, 62, 110–117.
- Castarlenas, S., Téllez, C. and Coronas, J. (2017) Gas separation with mixed matrix membranes obtained from MOF UiO-66-graphite oxide hybrids, *J. Memb. Sci.*, 526, 205–211.
- Castro-Muñoz, R. and Fíla, V. (2019) Effect of the ZIF-8 distribution in mixed-matrix membranes based on matrimid[®] 5218-PEG on CO₂ Separation, *Chem. Eng. Technol.*, 42(4), 744–752.
- Cavallo, C., Agostini, M., Genders, J. P., Abdelhamid, M. E. and Matic, A. (2019) A free-standing reduced graphene oxide aerogel as supporting electrode in a fluorine-free Li₂S₈ catholyte Li-S battery, *J. Power Sources*, 416, 111–117.
- Chae, I. S., Lee, J. H., Hong, J., Kang, Y. S. and Kang, S. W. (2014) The platform effect of graphene oxide on CO₂ transport on copper nanocomposites in ionic liquids, *Chem. Eng. J.*, 251, 343–347.

- Chai, S. H., Fulvio, P. F., Hillesheim, P. C., Qiao, Z. A., Mahurin, S. M. and Dai, S. (2014) 'Brick-and-mortar' synthesis of free-standing mesoporous carbon nanocomposite membranes as supports of room temperature ionic liquids for CO₂-N₂ separation, *J. Memb. Sci.*, 468, 73–80.
- Chen, C. C., Qiu, W., Miller, S. J. and Koros, W. J. (2011) Plasticization-resistant hollow fiber membranes for CO₂/CH₄ separation based on a thermally crosslinkable polyimide, *J. Memb. Sci.*, 382, 212–221.
- Chen, H., Johnson, J. K. and Sholl, D. S. (2006) Transport diffusion of gases is rapid in flexible carbon nanotubes, *J. Phys. Chem. B*, 110(5), 1971–1975.
- Chen, Y., Li, C., Tu, J. and An, L. (2012) Synthesis of short multi-walled carbon nanotubes by molecular self-assembly, *New Carbon Mater.*, 27(6), 416–420.
- Chi, C., Wang, X., Peng, Y., Qian, Y., Hu, Z., Dong, J. and Zhao, D. (2016) Facile preparation of graphene oxide membranes for gas separation, *Chem. Mater.*, 28(9), 2921–2927.
- Choi, S. H., Kim, J. H. and Lee, Y. (2013) Pilot-scale multistage membrane process for the separation of CO₂ from LNG-fired flue gas, *Sep. Purif. Technol.*, 110, 170–180.
- Chowdhury, S., Parshetti, G. K. and Balasubramanian, R. (2015) Post-combustion CO₂ capture using mesoporous TiO₂/graphene oxide nanocomposites, *Chem. Eng. J.*, 263, 374–384.
- Chung, T. S., Jiang, L. Y., Li, Y. and Kulprathipanja, S. (2007) Mixed matrix membranes (MMMs) comprising organic polymers with dispersed inorganic fillers for gas separation, *Prog. Polym. Sci.*, 32(4), 483–507.
- Compañ, V., Castillo, L. F., Hernández, S. I., López-González, M. and Riande, E. (2010) Crystallinity effect on the gas transport in semicrystalline coextruded films based on linear low density polyethylene, *J. Polym. Sci. Part B Polym. Phys.*, 48(6), 634–642.
- Cong, H., Zhang, J., Radosz, M. and Shen, Y. (2007) Carbon nanotube composite membranes of brominated poly(2,6-diphenyl-1,4-phenylene oxide) for gas separation, *J. Memb. Sci.*, 294, 178–185.
- Cote, L. J., Kim, J., Tung, V. C., Luo, J., Kim, F. and Huang, J. (2010) Graphene oxide as surfactant sheets, *Pure Appl. Chem.*, 83(1), 95–110.
- Cui, Y., Kundalwal, S. I. and Kumar, S. (2016) Gas barrier performance of graphene/polymer nanocomposites, *Carbon*, 98, 313–333.

- Czyperek, M., Zapp, P., Bouwmeester, H. J. M., Modigell, M., Ebert, K., Voigt, I., Meulenbergh, W. A., Singheiser, L. and Stöver, D. (2010) Gas separation membranes for zero-emission fossil power plants: MEM-BRAIN, *J. Memb. Sci.*, 359, 149–159.
- Dai, Y., Ruan, X., Yan, Z., Yang, K., Yu, M., Li, H., Zhao, W. and He, G. (2016) Imidazole functionalized graphene oxide/PEBAX mixed matrix membranes for efficient CO₂ capture, *Sep. Purif. Technol.*, 166, 171–180.
- Dai, Z., Noble, R. D., Gin, D. L., Zhang, X. and Deng, L. (2016) Combination of ionic liquids with membrane technology: A new approach for CO₂ separation, *J. Memb. Sci.*, 497, 1–20.
- Das, R., Ali, M. E., Hamid, S. B. A., Ramakrishna, S. and Chowdhury, Z. Z. (2014) Carbon nanotube membranes for water purification: A bright future in water desalination, *Desalination*, 336, 97–109.
- Dasgupta, A., Rajukumar, L. P., Rotella, C., Lei, Y. and Terrones, M. (2017) Covalent three-dimensional networks of graphene and carbon nanotubes: synthesis and environmental applications, *Nano Today*, 12, 116–135.
- Deng, L. and Hägg, M. B. B. (2014) Carbon nanotube reinforced PVAm/PVA blend FSC nanocomposite membrane for CO₂/CH₄ separation, *Int. J. Greenh. Gas Control*, 26, 127–134.
- Deng, L., Kim, T.-J. and Hägg, M. B. (2009) Facilitated transport of CO₂ in novel PVAm/PVA blend membrane, *J. Memb. Sci.*, 340, 154–163.
- Dixon, T., Romanak, K., Neades, S. and Chadwick, A. (2013) Getting science and technology into International Climate Policy: Carbon dioxide capture and storage in the UNFCCC, *Energy Procedia*, 37, 7590–7595.
- Dong, G., Hou, J., Wang, J., Zhang, Y., Chen, V. and Liu, J. (2016) Enhanced CO₂/N₂ separation by porous reduced graphene oxide/Pebax mixed matrix membranes, *J. Memb. Sci.*, 520, 860–868.
- Dong, G., Li, H. and Chen, V. (2011) Plasticization mechanisms and effects of thermal annealing of Matrimid hollow fiber membranes for CO₂ removal, *J. Memb. Sci.*, 369, 206–220.
- Dong, G., Zhang, X., Zhang, Y. and Tsuru, T. (2018) Enhanced permeation through CO₂-stable dual-inorganic composite membranes with tunable nanoarchitected channels, *ACS Sustain. Chem. Eng.*, 6(7), 8515–8524.

- Dong, H., Wu, L., Zhang, L., Chen, H. and Gao, C. (2015) Clay nanosheets as charged filler materials for high-performance and fouling-resistant thin film nanocomposite membranes, *J. Memb. Sci.*, 494, 92–103.
- Dreyer, D. R., Park, S., Bielawski, C. W. and Ruoff, R. S. (2010) The chemistry of graphene oxide, *Chem. Soc. Rev.*, 39, 228–240.
- Ebrahimi, S., Mollaiy-Berneti, S., Asadi, H., Peydayesh, M., Akhlaghian, F. and Mohammadi, T. (2016) PVA/PES-amine-functional graphene oxide mixed matrix membranes for CO₂/CH₄ separation: Experimental and modeling, *Chem. Eng. Res. Des.*, 109, 647–656.
- El-Nagar, G. A., Derr, I., Fetyan, A. and Roth, C. (2017) One-pot synthesis of a high performance chitosan-nickel oxyhydroxide nanocomposite for glucose fuel cell and electro-sensing applications, *Appl. Catal. B Environ.*, 204, 185–199.
- Emadzadeh, D., Lau, W. J., Matsuura, T., Rahbari-Sisakht, M. and Ismail, A. F. (2014) A novel thin film composite forward osmosis membrane prepared from PSf–TiO₂ nanocomposite substrate for water desalination, *Chem. Eng. J.*, 237, 70–80.
- Espeso, J., Lozano, A. E., Campa, J. G. and Abajo, J. (2006) Effect of substituents on the permeation properties of polyamide membranes, *J. Memb. Sci.*, 280, 659–665.
- Fathizadeh, M., Aroujalian, A. and Raisi, A. (2012) Effect of lag time in interfacial polymerization on polyamide composite membrane with different hydrophilic sub layers, *Desalination*, 284, 32–41.
- Favre, E. (2011) Membrane processes and postcombustion carbon dioxide capture: Challenges and prospects, *Chem. Eng. J.*, 171(3), 782–793.
- Favre, E., Bounaceur, R. and Roizard, D. (2009) Biogas, membranes and carbon dioxide capture, *J. Memb. Sci.*, 328(1–2), 11–14.
- Feng, C., Khulbe, K. C. and Matsuura, T. (2010) Recent progress in the preparation, characterization, and applications of nanofibers and nanofiber membranes via electrospinning/interfacial polymerization, *J. Appl. Polym. Sci.*, 115(2), 756–776.
- Feng, S., Ren, J., Hua, K., Li, H., Ren, X. and Deng, M. (2013) Poly(amide-12-b-ethylene oxide)/polyethylene glycol blend membranes for carbon dioxide separation, *Sep. Purif. Technol.*, 116, 25–34.
- Francisco, G. J., Chakma, A. and Feng, X. (2007) Membranes comprising of alkanolamines incorporated into poly(vinyl alcohol) matrix for CO₂/N₂ separation, *J. Memb. Sci.*, 303, 54–63.

- Freeman, B., Hao, P., Baker, R., Kniep, J., Chen, E., Ding, J., Zhang, Y. and Rochelle, G. T. (2014) Hybrid membrane-absorption CO₂ capture process, *Energy Procedia*, 63, 605–613.
- Freger, V. (2005) Kinetics of film formation by interfacial polycondensation, *Langmuir*, 21(5), 1884–1894.
- Gadipelli, S. and Guo, Z. X. (2015) Graphene-based materials: Synthesis and gas sorption, storage and separation, *Prog. Mater. Sci.*, 69, 1–60.
- Gao, H., Bai, L., Han, J., Yang, B., Zhang, S. and Zhang, X. (2018) Functionalized ionic liquid membranes for CO₂ separation, *Chem. Commun.*, 54(90), 12671–12685.
- Ge, L., Zhu, Z. and Rudolph, V. (2011) Enhanced gas permeability by fabricating functionalized multi-walled carbon nanotubes and polyethersulfone nanocomposite membrane, *Sep. Purif. Technol.*, 78(1), 76–82.
- Ghosh, A. K. and Hoek, E. M. V. (2009) Impacts of support membrane structure and chemistry on polyamide–polysulfone interfacial composite membranes, *J. Memb. Sci.*, 336, 140–148.
- Ghosh, A. K., Jeong, B. H., Huang, X. and Hoek, E. M. V. (2008) Impacts of reaction and curing conditions on polyamide composite reverse osmosis membrane properties, *J. Memb. Sci.*, 311, 34–45.
- Gibbins, J. and Chalmers, H. (2008) Carbon capture and storage, *Energy Policy*, 36(12), 4317–4322.
- Gilani, N., Towfighi, J., Rashidi, A., Mohammadi, T., Omidkhah, M. R. and Sadeghian, A. (2013) Investigation of H₂S separation from H₂S/CH₄ mixtures using functionalized and non-functionalized vertically aligned carbon nanotube membranes, *Appl. Surf. Sci.*, 270, 115–123.
- Goh, P. S. and Ismail, A. F. (2015) Graphene-based nanomaterial: The state-of-the-art material for cutting edge desalination technology, *Desalination*, 356, 115–128.
- Goh, P. S., Ismail, A. F. and Hilal, N. (2016) Nano-enabled membranes technology: Sustainable and revolutionary solutions for membrane desalination?, *Desalination*, 380, 100–104.
- Goh, P. S., Ismail, A. F. and Ng, B. C. (2014) Directional alignment of carbon nanotubes in polymer matrices: Contemporary approaches and future advances, *Compos. Part A Appl. Sci. Manuf.*, 56, 103–126.

- Goh, P. S., Ismail, A. F., Sanip, S. M., Ng, B. C. and Aziz, M. (2011) Recent advances of inorganic fillers in mixed matrix membrane for gas separation, *Sep. Purif Technol.*, 81(3), 243–264.
- Goh, P. S., Ng, B. C., Ismail, A. F., Aziz, M. and Hayashi, Y. (2012) Pre-treatment of multi-walled carbon nanotubes for polyetherimide mixed matrix hollow fiber membranes, *J. Colloid Interface Sci.*, 386, 80–87.
- Goh, P. S., Ng, B. C., Ismail, A. F., Aziz, M. and Sanip, S. M. (2010) Surfactant dispersed multi-walled carbon nanotube/polyetherimide nanocomposite membrane, *Solid State Sci.*, 12, 2155–2162.
- Gómez-Navarro, C., Meyer, J. C., Sundaram, R. S., Chuvilin, A., Kurasch, S., Burghard, M., Kern, K. and Kaiser, U. (2010) Atomic structure of reduced graphene oxide, *Nano Lett.*, 10(4), 1144–1148.
- Gudarzi, M. M. and Sharif, F. (2011) Self assembly of graphene oxide at the liquid–liquid interface: A new route to the fabrication of graphene based composites, *Soft Matter*, 7(7), 3432–3440.
- Guo, X., Huang, H., Ban, Y., Yang, Q., Xiao, Y., Li, Y., Yang, W. and Zhong, C. (2015) Mixed matrix membranes incorporated with amine-functionalized titanium-based metal-organic framework for CO₂/CH₄ separation, *J. Memb. Sci.*, 478, 130–139.
- Habibiannejad, S. A., Aroujalian, A. and Raisi, A. (2016) Pebax-1657 mixed matrix membrane containing surface modified multi-walled carbon nanotubes for gas separation, *RSC Adv.*, 6(83), 79563–79577.
- He, Y., Wang, Y., Zhang, L., Teng, B. and Fan, M. (2015) High-efficiency conversion of CO₂ to fuel over ZnO/g-C₃N₄ photocatalyst, *Appl. Catal. B Environ.*, 168–169, 1–8.
- Hillock, A. M. W., Miller, S. J. and Koros, W. J. (2008) Crosslinked mixed matrix membranes for the purification of natural gas: Effects of sieve surface modification, *J. Memb. Sci.*, 314, 193–199.
- Hu, H., Zhang, T., Yuan, S. and Tang, S. (2017) Functionalization of multi-walled carbon nanotubes with phenylenediamine for enhanced CO₂ adsorption, *Adsorption*, 23, 73–85.
- Huang, Y., Wang, X., Jin, X. and Wang, T. (2014) Study on the PMMA/GO nanocomposites with good thermal stability prepared by in situ Pickering emulsion polymerization, *J. Therm. Anal. Calorim.*, 117(2), 755–763.

- Hung, W. S., Lai, C. L., An, Q., De Guzman, M., Shen, T. J., Huang, Y. H., Chang, K. C., Tsou, C. H., Hu, C. C. and Lee, K. R. (2014) A study on high-performance composite membranes comprising heterogeneous polyamide layers on an electrospun substrate for ethanol dehydration, *J. Memb. Sci.*, 470, 513–523.
- Hussain, A., Farrukh, S. and Minhas, F. T. (2015) Two-stage membrane system for post-combustion CO₂ capture application, *Energy & Fuels*, 29(10), 6664–6669.
- Iarikov, D. D. and Oyama, S. T. (2011) *Review of CO₂/CH₄ separation membranes*. in Oyama, S. T. and Stagg-Williams, S. M. (eds.) *Membrane science and technology*. Cambridge: Elsevier, 91–115.
- Iijima, S. (1991) Helical microtubules of graphitic carbon, *Nature*, 354(6348), 56–58.
- Inagaki, M., Kang, F., Toyoda, M. and Konno, H. (2014) *Nanoporous carbon membranes and webs*, in Inagaki, M., Kang, F., Toyoda, M. and Konno, H. (eds.) *Advanced materials science and engineering of carbon*. Boston: Butterworth-Heinemann, 215–236.
- Ismail, A. F., Rahim, N. H., Mustafa, A., Matsuura, T., Ng, B. C., Abdullah, S. and Hashemifard, S. A. (2011) Gas separation performance of polyethersulfone/multi-walled carbon nanotubes mixed matrix membranes, *Sep. Purif Technol.*, 80, 20–31.
- Jadav, G. L. and Singh, P. S. (2009) Synthesis of novel silica-polyamide nanocomposite membrane with enhanced properties, *J. Memb. Sci.*, 328, 257–267.
- Jeffery, A. A., Rao, S. R. and Rajamathi, M. (2017) Preparation of MoS₂-reduced graphene oxide (rGO) hybrid paper for catalytic applications by simple exfoliation–costacking, *Carbon*, 112, 8–16.
- Ji, J. and Mehta, M. (2001) Mathematical model for the formation of thin-film composite hollow fiber and tubular membranes by interfacial polymerization, *J. Memb. Sci.*, 192, 41–54.
- Jimenez-Solomon, M. F., Gorgojo, P., Munoz-Ibanez, M. and Livingston, A. G. (2013) Beneath the surface: Influence of supports on thin film composite membranes by interfacial polymerization for organic solvent nanofiltration, *J. Memb. Sci.*, 448, 102–113.
- Jimenez-Solomon, M. F., Song, Q., Jelfs, K. E., Munoz-Ibanez, M. and Livingston, A. G. (2016) Polymer nanofilms with enhanced microporosity by interfacial polymerization, *Nat. Mater.*, 15(7), 760–767.

- Kanehashi, S., Aguiar, A., Lu, H. T., Chen, G. Q. and E. Kentish, S. (2018) Effects of industrial gas impurities on the performance of mixed matrix membranes, *J. Memb. Sci.*, 549, 686–692.
- Kar, S., Bindal, R. C. and Tewari, P. K. (2012) Carbon nanotube membranes for desalination and water purification: Challenges and opportunities, *Nano Today*, 7(5), 385–389.
- Kausar, A. (2016) Investigation on nanocomposite membrane of multiwalled carbon nanotube reinforced polycarbonate blend for gas separation, *J. Nanomater.*, 2016, 1–9.
- Kenarsari, S. D., Yang, D., Jiang, G., Zhang, S., Wang, J., Russell, A. G., Wei, Q. and Fan, M. (2013) Review of recent advances in carbon dioxide separation and capture, *RSC Adv.*, 3(45), 22739–22773.
- Khan, M. M., Filiz, V., Bengtson, G., Shishatskiy, S., Rahman, M. M., Lillepaerg, J. and Abetz, V. (2013) Enhanced gas permeability by fabricating mixed matrix membranes of functionalized multiwalled carbon nanotubes and polymers of intrinsic microporosity (PIM), *J. Memb. Sci.*, 436, 109–120.
- Khan, Z. U., Kausar, A. and Ullah, H. (2016) A review on composite papers of graphene oxide, carbon nanotube, polymer/GO, and polymer/CNT: Processing strategies, properties, and relevance, *Polym. Plast. Technol. Eng.*, 55(6), 559–581.
- Khulbe, K. C., Feng, C. Y. and Matsuura, T. (2008) *Synthetic polymeric membranes: Characterization by atomic force microscopy*, in Pasch, H., Alig, I., Janca, J., and Kulicke, W. M. (eds.) *Springer laboratory*. Berlin, Heidelberg: Springer.
- Kiadehi, A. D., Jahanshahi, M., Rahimpour, A. and Ghoreyshi, S. A. A. (2015a) The effect of functionalized carbon nano-fiber (CNF) on gas separation performance of polysulfone (PSf) membranes, *Chem. Eng. Process. Process Intensif.*, 90, 41–48.
- Kiadehi, A. D., Rahimpour, A., Jahanshahi, M. and Ghoreyshi, A. A. (2015b) Novel carbon nano-fibers (CNF)/polysulfone (PSf) mixed matrix membranes for gas separation, *J. Ind. Eng. Chem.*, 22, 199–207.
- Kim, E. S. and Deng, B. (2011) Fabrication of polyamide thin-film nano-composite (PA-TFN) membrane with hydrophilized ordered mesoporous carbon (H-OMC) for water purifications, *J. Memb. Sci.*, 375, 46–54.

- Kim, J., Cote, L. J., Kim, F., Yuan, W., Shull, K. R. and Huang, J. (2010) Graphene oxide sheets at interfaces, *J. Am. Chem. Soc.*, 132(23), 8180–8186.
- Kim, J., Fu, Q., Scofield, J. M. P., Kentish, S. E. and Qiao, G. G. (2016) Ultra-thin film composite mixed matrix membranes incorporating iron(iii)–dopamine nanoparticles for CO₂ separation, *Nanoscale*, 8(15), 8312–8323.
- Kim, S. W., Kim, T., Kim, Y. S., Choi, H. S., Lim, H. J., Yang, S. J. and Park, C. R. (2012) Surface modifications for the effective dispersion of carbon nanotubes in solvents and polymers, *Carbon*, 50, 3–33.
- Kim, T. J., Baoan, L. I. and Hägg, M. B. (2004) Novel fixed-site-carrier polyvinylamine membrane for carbon dioxide capture, *J. Polym. Sci. Part B Polym. Phys.*, 42(23), 4326–4336.
- Kim, W. and Nair, S. (2013) Membranes from nanoporous 1D and 2D materials: A review of opportunities, developments, and challenges, *Chem. Eng. Sci.*, 104, 908–924.
- Klaysom, C., Hermans, S., Gahlaut, A., Van Craenenbroeck, S. and Vankelecom, I. F. J. (2013) Polyamide/Polyacrylonitrile (PA/PAN) thin film composite osmosis membranes: Film optimization, characterization and performance evaluation, *J. Memb. Sci.*, 445, 25–33.
- Koolivand, H., Sharifa, A., Chehrazi, E., Kashani, M. R. and Paran, S. M. R. (2016) Mixed-matrix membranes comprising graphene-oxide nanosheets for CO₂/CH₄ separation: A comparison between glassy and rubbery polymer matrices, *Polym. Sci. Ser. A*, 58(5), 801–809.
- Kratochvil, A. M. and Koros, W. J. (2008) Decarboxylation-induced cross-linking of a polyimide for enhanced CO₂ plasticization resistance, *Macromolecules*, 41(21), 7920–7927.
- Lalia, B. S., Kochkodan, V., Hashaikeh, R. and Hilal, N. (2013) A review on membrane fabrication: Structure, properties and performance relationship, *Desalination*, 326, 77–95.
- Lannoy, C. F., Soyer, E. and Wiesner, M. R. (2013) Optimizing carbon nanotube-reinforced polysulfone ultrafiltration membranes through carboxylic acid functionalization, *J. Memb. Sci.*, 447, 395–402.
- Lau, W. J., Gray, S., Matsuura, T., Emadzadeh, D., Paul Chen, J. and Ismail, A. F. (2015) A review on polyamide thin film nanocomposite (TFN) membranes: History, applications, challenges and approaches, *Water Res.*, 80, 306–324.

- Lau, W. J., Ismail, A. F., Misdan, N. and Kassim, M. A. (2012) A recent progress in thin film composite membrane: A review, *Desalination*, 287, 190–199.
- Leung, D. Y. C., Caramanna, G. and Maroto-Valer, M. M. (2014) An overview of current status of carbon dioxide capture and storage technologies, *Renew. Sustain. Energy Rev.*, 39, 426–443.
- Li, F., Jiang, X., Zhao, J. and Zhang, S. (2015) Graphene oxide: A promising nanomaterial for energy and environmental applications, *Nano Energy*, 16, 488–515.
- Li, S., Wang, Z., Yu, X., Wang, J. and Wang, S. (2012) High-performance membranes with multi-permselectivity for CO₂ separation, *Adv. Mater.*, 24(24), 3196–3200.
- Li, S., Wang, Z., Zhang, C., Wang, M., Yuan, F., Wang, J. and Wang, S. (2013) Interfacially polymerized thin film composite membranes containing ethylene oxide groups for CO₂ separation, *J. Memb. Sci.*, 436, 121–131.
- Li, T., Pan, Y., Peinemann, K. V. and Lai, Z. (2013) Carbon dioxide selective mixed matrix composite membrane containing ZIF-7 nano-fillers, *J. Memb. Sci.*, 425–426, 235–242.
- Li, X., Ma, L., Zhang, H., Wang, S., Jiang, Z., Guo, R., Wu, H., Cao, X., Yang, J. and Wang, B. (2015) Synergistic effect of combining carbon nanotubes and graphene oxide in mixed matrix membranes for efficient CO₂ separation, *J. Memb. Sci.*, 479, 1–10.
- Li, Y., Su, Y., Dong, Y., Zhao, X., Jiang, Z., Zhang, R. and Zhao, J. (2014) Separation performance of thin-film composite nanofiltration membrane through interfacial polymerization using different amine monomers, *Desalination*, 333, 59–65.
- Liang, C. Y., Uchytel, P., Petrychkovych, R., Lai, Y. C., Friess, K., Sipek, M., Mohan Reddy, M. and Suen, S. Y. (2012) A comparison on gas separation between PES (polyethersulfone)/MMT (Na-montmorillonite) and PES/TiO₂ mixed matrix membranes, *Sep. Purif. Technol.*, 92, 57–63.
- Lim, D. W., Chyun, S. A. and Suh, M. P. (2014) Hydrogen storage in a potassium-ion-bound metal-organic framework incorporating crown ether struts as specific cation binding sites, *Angew. Chemie Int. Ed.*, 53(30), 7819–7822.
- Lin, H. and Freeman, B. D. (2005) Materials selection guidelines for membranes that remove CO₂ from gas mixtures, *J. Mol. Struct.*, 739, 57–74.

- Lin, R., Ge, L., Liu, S., Rudolph, V. and Zhu, Z. (2015) Mixed-matrix membranes with metal–organic framework-decorated CNT fillers for efficient CO₂ separation, *ACS Appl. Mater. Interfaces*, 7(27), 14750–14757.
- Lind, M. L., Ghosh, A. K., Jawor, A., Huang, X., Hou, W., Yang, Y. and Hoek, E. M. V. (2009) Influence of zeolite crystal size on zeolite-polyamide thin film nanocomposite membranes, *Langmuir*, 25(17), 10139–10145.
- Lindau, J., Jönsson, A. S. and Wimmerstedt, R. (1995) The influence of a low-molecular hydrophobic solute on the flux of polysulphone ultrafiltration membranes with different cut-off, *J. Memb. Sci.*, 106, 9–16.
- Liu, X. Q., Shen, S. Q., Wen, R., Yang, W., Xie, B. H. and Yang, M. B. (2013) Reinforcement and plasticization of PMMA grafted MWCNTs for PVDF composites, *Compos. Part B Eng.*, 53, 9–16.
- Liu, X., Wang, M., Zhang, S. and Pan, B. (2013) Application potential of carbon nanotubes in water treatment: A review, *J. Environ. Sci.*, 25(7), 1263–1280.
- Liu, Y., He, B., Li, J., Sanderson, R. D., Li, L. and Zhang, S. (2011) Formation and structural evolution of biphenyl polyamide thin film on hollow fiber membrane during interfacial polymerization, *J. Memb. Sci.*, 373, 98–106.
- Louie, J. S., Pinnau, I. and Reinhard, M. (2008) Gas and liquid permeation properties of modified interfacial composite reverse osmosis membranes, *J. Memb. Sci.*, 325, 793–800.
- Lua, A. C. and Shen, Y. (2013) Preparation and characterization of polyimide–silica composite membranes and their derived carbon–silica composite membranes for gas separation, *Chem. Eng. J.*, 220, 441–451.
- Ma, P. C., Siddiqui, N. A., Marom, G. and Kim, J. K. (2010) Dispersion and functionalization of carbon nanotubes for polymer-based nanocomposites: A review, *Compos. Part A Appl. Sci. Manuf.*, 41(10), 1345–1367.
- Majumdar, D., Baugh, N. and Bhattacharya, S. K. (2017) Ultrasound assisted formation of reduced graphene oxide-copper (II) oxide nanocomposite for energy storage applications, *Colloids Surfaces A Physicochem. Eng. Asp.*, 512, 158–170.
- Mallakpour, S., Abdolmaleki, A. and Borandeh, S. (2014a) *l*-Phenylalanine amino acid functionalized multi walled carbon nanotube (MWCNT) as a reinforced filler for improving mechanical and morphological properties of poly(vinyl alcohol)/MWCNT composite, *Prog. Org. Coatings*, 77(11), 1966–1971.

- Mallakpour, S. and Zadehnazari, A. (2014b) A facile, efficient, and rapid covalent functionalization of multi-walled carbon nanotubes with natural amino acids under microwave irradiation, *Prog. Org. Coatings*, 77(3), 679–684.
- McCoy, T. M., Pottage, M. J. and Tabor, R. F. (2014) Graphene oxide-stabilized oil-in-water emulsions: pH-controlled dispersion and flocculation, *J. Phys. Chem. C*, 118(8), 4529–4535.
- Merkel, T. C., He, Z., Pinnau, I., Freeman, B. D., Meakin, P. and Hill, A. J. (2003) Effect of nanoparticles on gas sorption and transport in poly(1-trimethylsilyl-1-propyne), *Macromolecules*, 36(18), 6844–6855.
- Merkel, T. C., Lin, H., Wei, X. and Baker, R. (2010) Power plant post-combustion carbon dioxide capture: An opportunity for membranes, *J. Memb. Sci.*, 359, 126–139.
- Misdan, N., Lau, W. J., Ismail, A. F. and Matsuura, T. (2013) Formation of thin film composite nanofiltration membrane: Effect of polysulfone substrate characteristics, *Desalination*, 329, 9–18.
- Moore, T. T. and Koros, W. J. (2005) Non-ideal effects in organic-inorganic materials for gas separation membranes, *J. Mol. Struct.*, 739, 87–98.
- Moors, M., Visart de Bocarmé, T. and Kruse, N. (2009) C₂H₂ interaction with Ni nanocrystals: Towards a better understanding of carbon nanotubes nucleation in CVD synthesis, *Ultramicroscopy*, 109(5), 381–384.
- Nakao, S. (1994) Determination of pore size and pore size distribution, *J. Memb. Sci.*, 96, 131–165.
- Namvar-Mahboub, M., Pakizeh, M. and Davari, S. (2014) Preparation and characterization of UZM-5/polyamide thin film nanocomposite membrane for dewaxing solvent recovery, *J. Memb. Sci.*, 459, 22–32.
- Nasir, R., Mukhtar, H., Man, Z., Dutta, B. K., Shaharun, M. S. and Abu Bakar, M. Z. (2015) Mixed matrix membrane performance enhancement using alkanolamine solution, *J. Memb. Sci.*, 483, 84–93.
- Offeman, R. D. and Ludvik, C. N. (2011) A novel method to fabricate high permeance, high selectivity thin-film composite membranes, *J. Memb. Sci.*, 380, 163–170.
- Olajire, A. A. (2010) CO₂ capture and separation technologies for end-of-pipe applications – A review, *Energy*, 35(6), 2610–2628.

- Ostwal, M., Singh, R. P., Dec, S. F., Lusk, M. T. and Way, J. D. (2011) 3-Aminopropyltriethoxysilane functionalized inorganic membranes for high temperature CO₂/N₂ separation, *J. Memb. Sci.*, 369, 139–147.
- Patel, N. P., Miller, A. C. and Spontak, R. J. (2004) Highly CO₂-permeable and -selective membranes derived from crosslinked poly(ethylene glycol) and its nanocomposites, *Adv. Funct. Mater.*, 14(7), 699–707.
- Peng, F., Pan, F., Sun, H., Lu, L. and Jiang, Z. (2007) Novel nanocomposite pervaporation membranes composed of poly(vinyl alcohol) and chitosan-wrapped carbon nanotube, *J. Memb. Sci.*, 300, 13–19.
- Petersen, J. and Peinemann, K. V. (1997) Novel polyamide composite membranes for gas separation prepared by interfacial polycondensation, *J. Appl. Polym. Sci.*, 63(12), 1557–1563.
- Peyravi, M., Jahanshahi, M., Rahimpour, A., Javadi, A. and Hajavi, S. (2014) Novel thin film nanocomposite membranes incorporated with functionalized TiO₂ nanoparticles for organic solvent nanofiltration, *Chem. Eng. J.*, 241, 155–166.
- Pires, J. C. M., Martins, F. G., Alvim-Ferraz, M. C. M. and Simões, M. (2011) Recent developments on carbon capture and storage: An overview, *Chem. Eng. Res. Des.*, 89(9), 1446–1460.
- Powell, C. E. and Qiao, G. G. (2006) Polymeric CO₂/N₂ gas separation membranes for the capture of carbon dioxide from power plant flue gases, *J. Memb. Sci.*, 279, 1–49.
- Qin, G., Cao, X., Wen, H., Wei, W. and Diniz, J. C. (2017) Fine ultra-micropore control using the intrinsic viscosity of precursors for high performance carbon molecular sieve membranes, *Sep. Purif. Technol.*, 177, 129–134.
- Quan, S., Li, S. W., Xiao, Y. C. and Shao, L. (2017) CO₂-selective mixed matrix membranes (MMMs) containing graphene oxide (GO) for enhancing sustainable CO₂ capture, *Int. J. Greenh. Gas Control*, 56, 22–29.
- Rehman, R. U., Rafiq, S., Muhammad, N., Khan, A. L., Rehman, A. U., Tingting, L., Saeed, M., Jamil, F., Ghauri, M., Ur Rehman, R., Rafiq, S., Muhammad, N., Khan, A. L., Ur Rehman, A., Tingting, L., Saeed, M., Jamil, F., Ghauri, M. and Gu, X. (2017) Development of ethanolamine-based ionic liquid membranes for efficient CO₂/CH₄ separation, *J. Appl. Polym. Sci.*, 134(44), 45395.

- Reijerkerk, S. R., Nijmeijer, K., Ribeiro, C. P., Freeman, B. D. and Wessling, M. (2011) On the effects of plasticization in CO₂/light gas separation using polymeric solubility selective membranes, *J. Memb. Sci.*, 367, 33–44.
- Rekha Panda, S. and De, S. (2014) Effects of polymer molecular weight, concentration, and role of polyethylene glycol as additive on polyacrylonitrile homopolymer membranes, *Polym. Eng. Sci.*, 54(10), 2375–2391.
- Ren, X., Chen, C., Nagatsu, M. and Wang, X. (2011) Carbon nanotubes as adsorbents in environmental pollution management: A review, *Chem. Eng. J.*, 170, 395–410.
- Rezakazemi, M., Ebadi Amooghin, A., Montazer-Rahmati, M. M., Ismail, A. F. and Matsuura, T. (2014) State-of-the-art membrane based CO₂ separation using mixed matrix membranes (MMMs): An overview on current status and future directions, *Prog. Polym. Sci.*, 39(5), 817–861.
- Rezakazemi, M., Heydari, I. and Zhang, Z. (2017) Hybrid systems: Combining membrane and absorption technologies leads to more efficient acid gases (CO₂ and H₂S) removal from natural gas, *J. CO₂ Util.*, 18, 362–369.
- Robeson, L. M. (1991) Correlation of separation factor versus permeability for polymeric membranes, *J. Memb. Sci.*, 62, 165–185.
- Robeson, L. M. (2008) The upper bound revisited, *J. Memb. Sci.*, 320, 390–400.
- Roussanaly, S., Anantharaman, R., Lindqvist, K., Zhai, H. and Rubin, E. (2016) Membrane properties required for post-combustion CO₂ capture at coal-fired power plants, *J. Memb. Sci.*, 511, 250–264.
- Sadeghian, Z. (2009) Large-scale production of multi-walled carbon nanotubes by low-cost spray pyrolysis of hexane, *New Carbon Mater.*, 24(1), 33–38.
- Saedi, S., Madaeni, S. S., Seidi, F., Shamsabadi, A. A. and Laki, S. (2013) Synthesis and application of a novel amino-starch derivative as a new polymeric additive for fixed facilitated transport of carbon dioxide through an asymmetric polyethersulfone (PES) membrane, *Int. J. Greenh. Gas Control*, 19, 126–137.
- Saedi, S., Madaeni, S. S., Seidi, F., Shamsabadi, A. A. and Laki, S. (2014) Fixed facilitated transport of CO₂ through integrally-skinned asymmetric polyethersulfone membrane using a novel synthesized poly (acrylonitrile-co-N, N-dimethylaminopropyl acrylamide), *Chem. Eng. J.*, 236, 263–273.
- Saha, N. K. and Joshi, S. V. (2009) Performance evaluation of thin film composite polyamide nanofiltration membrane with variation in monomer type, *J. Memb. Sci.*, 342, 60–69.

- Salih, A. A. M., Yi, C., Peng, H., Yang, B., Yin, L. and Wang, W. (2014) Interfacially polymerized polyetheramine thin film composite membranes with PDMS inter-layer for CO₂ separation, *J. Memb. Sci.*, 472, 110–118.
- Samanta, A., Zhao, A., Shimizu, G. K. H. H., Sarkar, P. and Gupta, R. (2012) Post-combustion CO₂ capture using solid sorbents: A review, *Ind. Eng. Chem. Res.*, 51(4), 1438–1463.
- Sanders, D. F., Smith, Z. P., Guo, R., Robeson, L. M., McGrath, J. E., Paul, D. R. and Freeman, B. D. (2013) Energy-efficient polymeric gas separation membranes for a sustainable future: A review, *Polymer*, 54(18), 4729–4761.
- Sanip, S. M., Ismail, A. F., Goh, P. S., Soga, T., Tanemura, M. and Yasuhiko, H. (2011) Gas separation properties of functionalized carbon nanotubes mixed matrix membranes, *Sep. Purif. Technol.*, 78(2), 208–213.
- Sazali, N., Salleh, W. N. W., Ismail, A. F., Wong, K. C. and Iwamoto, Y. (2019) Exploiting pyrolysis protocols on BTDA-TDI/MDI (P84) polyimide/nanocrystalline cellulose carbon membrane for gas separations, *J. Appl. Polym. Sci.*, 136, 46901.
- Scholes, C. A., Chen, G. Q., Stevens, G. W. and Kentish, S. E. (2010) Plasticization of ultra-thin polysulfone membranes by carbon dioxide, *J. Memb. Sci.*, 346, 208–214.
- Scofield, J. M. P., Gurr, P. A., Kim, J., Fu, Q., Kentish, S. E. and Qiao, G. G. (2016) Development of novel fluorinated additives for high performance CO₂ separation thin-film composite membranes, *J. Memb. Sci.*, 499, 191–200.
- Seah, C. M., Chai, S. P. and Mohamed, A. R. (2011) Synthesis of aligned carbon nanotubes, *Carbon*, 49(14), 4613–4635.
- Seman, M. N. A., Khayet, M. and Hilal, N. (2010) Nanofiltration thin-film composite polyester polyethersulfone-based membranes prepared by interfacial polymerization, *J. Memb. Sci.*, 348, 109–116.
- Shahid, S., Nijmeijer, K., Nehache, S., Vankelecom, I., Deratani, A. and Quemener, D. (2015) MOF-mixed matrix membranes: Precise dispersion of MOF particles with better compatibility via a particle fusion approach for enhanced gas separation properties, *J. Memb. Sci.*, 492, 21–31.

- Shen, J. N., Yu, C. C., Ruan, H. M., Gao, C. J. and Van der Bruggen, B. (2013) Preparation and characterization of thin-film nanocomposite membranes embedded with poly(methyl methacrylate) hydrophobic modified multiwalled carbon nanotubes by interfacial polymerization, *J. Memb. Sci.*, 442, 18–26.
- Shen, Y., Wang, H., Liu, J. and Zhang, Y. (2015) Enhanced performance of a novel polyvinyl amine/chitosan/graphene oxide mixed matrix membrane for CO₂ capture, *ACS Sustain. Chem. Eng.*, 3(8), 1819–1829.
- Shen, Y., Wang, H., Zhang, X. and Zhang, Y. (2016) MoS₂ nanosheets functionalized composite mixed matrix membrane for enhanced CO₂ capture via surface drop-coating method, *ACS Appl. Mater. Interfaces*, 8(35), 23371–23378.
- Shokrollahzadeh, S. and Tajik, S. (2018) Fabrication of thin film composite forward osmosis membrane using electrospun polysulfone/polyacrylonitrile blend nanofibers as porous substrate, *Desalination*, 425, 68–76.
- Singsang, W., Panapoy, M. and Ksapabutr, B. (2014) Facile one-pot synthesis of freestanding carbon nanotubes on cellulose-derived carbon films for supercapacitor applications: effect of the synthesis temperature, *Energy Procedia*, 56(2014), 439–447.
- Sitter, K., Dotremont, C., Genné, I. and Stoops, L. (2014) The use of nanoparticles as alternative pore former for the production of more sustainable polyethersulfone ultrafiltration membranes, *J. Memb. Sci.*, 471, 168–178.
- Song, J., Wang, L., Feng, S., Zhao, J. and Zhu, Z. (2009) Growth of carbon nanotubes by the catalytic decomposition of methane over Fe-Mo/Al₂O₃ catalyst: effect of temperature on tube structure, *New Carbon Mater.*, 24(4), 307–313.
- Song, X., Zhou, Q., Zhang, T., Xu, H. and Wang, Z. (2016) Pressure-assisted preparation of graphene oxide quantum dot-incorporated reverse osmosis membranes: antifouling and chlorine resistance potentials, *J. Mater. Chem. A*, 4(43), 16896–16905.
- Song, Y., Sun, P., Henry, L. and Sun, B. (2005) Mechanisms of structure and performance controlled thin film composite membrane formation via interfacial polymerization process, *J. Memb. Sci.*, 251, 67–79.
- Songolzadeh, M., Soleimani, M., Takht Ravanchi, M. and Songolzadeh, R. (2014) Carbon dioxide separation from flue gases: A technological review emphasizing reduction in greenhouse gas emissions, *Sci. World J.*, 2014, 1–34.

- Sorribas, S., Gorgojo, P., Téllez, C., Coronas, J. and Livingston, A. G. (2013) High flux thin film nanocomposite membranes based on metal–organic frameworks for organic solvent nanofiltration, *J. Am. Chem. Soc.*, 135(40), 15201–15208.
- Spitalsky, Z., Tasis, D., Papagelis, K. and Galiotis, C. (2010) Carbon nanotube-polymer composites: Chemistry, processing, mechanical and electrical properties, *Prog. Polym. Sci.*, 35(3), 357–401.
- Sridhar, S., Smitha, B., Mayor, S., Prathab, B. and Aminabhavi, T. M. M. M. (2007) Gas permeation properties of polyamide membrane prepared by interfacial polymerization, *J. Mater. Sci.*, 42(22), 9392–9401.
- Stramel, A. A., Gupta, M. C., Lee, H. R., Yu, J. and Edwards, W. C. (2010) Pulsed laser deposition of carbon nanotube and polystyrene–carbon nanotube composite thin films, *Opt. Lasers Eng.*, 48(12), 1291–1295.
- Sun, D., Kang, S., Liu, C., Lu, Q., Cui, L. and Hu, B. (2016) Effect of zeta potential and particle size on the stability of SiO₂ nanospheres as carrier for ultrasound imaging contrast agents, *Int. J. Electrochem. Sci.*, 11(10), 8520–8529.
- Sun, H., Wang, T., Xu, Y., Gao, W., Li, P. and Niu, Q. J. (2017) Fabrication of polyimide and functionalized multi-walled carbon nanotubes mixed matrix membranes by in-situ polymerization for CO₂ separation, *Sep. Purif. Technol.*, 177, 327–336.
- Sun, X., Zhang, M., Guo, R., Luo, J. and Li, J. (2015) CO₂-facilitated transport performance of poly(ionic liquids) in supported liquid membranes, *J. Mater. Sci.*, 50, 104–111.
- Surapathi, A., Chen, H. yan, Marand, E., Karl Johnson, J. and Sedlakova, Z. (2013) Gas sorption properties of zwitterion-functionalized carbon nanotubes, *J. Memb. Sci.*, 429, 88–94.
- Swain, S. S., Unnikrishnan, L., Mohanty, S. and Nayak, S. K. (2017) Carbon nanotubes as potential candidate for separation of H₂-CO₂ gas pairs, *Int. J. Hydrogen Energy*, 42(49), 29283–29299.
- Tahri, N., Jedidi, I., Cerneaux, S., Cretin, M. and Ben Amar, R. (2013) Development of an asymmetric carbon microfiltration membrane: Application to the treatment of industrial textile wastewater, *Sep. Purif. Technol.*, 118, 179–187.

- Tan, G. Y. E., Oh, P. C., Lau, K. K. and Low, S. C. (2019) Dispersion of titanium(IV) oxide nanoparticles in mixed matrix membrane using octaisobutyl polyhedral oligomeric silsesquioxane for enhanced CO₂/CH₄ separation performance, *Chinese J. Polym. Sci.*, 37(7), 654-663.
- Taniguchi, I., Duan, S., Kazama, S. and Fujioka, Y. (2008) Facile fabrication of a novel high performance CO₂ separation membrane: Immobilization of poly(amidoamine) dendrimers in poly(ethylene glycol) networks, *J. Memb. Sci.*, 322, 277–280.
- Teipel, U. and Mikonsaari, I. (2004) Determining contact angles of powders by liquid penetration, *Part. Part. Syst. Charact.*, 21(4), 255–260.
- Thakker, M., Karde, V., Shah, D. O., Shukla, P. and Ghoroi, C. (2013) Wettability measurement apparatus for porous material using the modified Washburn method, *Meas. Sci. Technol.*, 24(12), 125902.
- Tian, L., Meziani, M. J., Lu, F., Kong, C. Y., Cao, L., Thorne, T. J. and Sun, Y.-P. (2010) Graphene oxides for homogeneous dispersion of carbon nanotubes, *ACS Appl. Mater. Interfaces*, 2(11), 3217–3222.
- Tin, P. S., Chung, T. S., Liu, Y., Wang, R., Liu, S. L. and Pramoda, K. P. (2003) Effects of cross-linking modification on gas separation performance of Matrimid membranes, *J. Memb. Sci.*, 225, 77–90.
- Vakharia, V., Salim, W., Wu, D., Han, Y., Chen, Y., Zhao, L. and Ho, W. S. W. (2018) Scale-up of amine-containing thin-film composite membranes for CO₂ capture from flue gas, *J. Memb. Sci.*, 555, 379–387.
- Vanherck, K., Koeckelberghs, G. and Vankelecom, I. F. J. (2013) Crosslinking polyimides for membrane applications: A review, *Prog. Polym. Sci.*, 38(6), 874–896.
- Wan Azelee, I., Goh, P. S., Lau, W. J., Ismail, A. F., Rezaei-DashtArzhandi, M., Wong, K. C. and Subramaniam, M. N. (2017) Enhanced desalination of polyamide thin film nanocomposite incorporated with acid treated multiwalled carbon nanotube-titania nanotube hybrid, *Desalination*, 409, 163–170.
- Wan, W., Zhang, R., Li, W., Liu, H., Lin, Y., Li, L. and Zhou, Y. (2016) Graphene-carbon nanotube aerogel as an ultra-light, compressible and recyclable highly efficient absorbent for oil and dyes, *Environ. Sci. Nano*, 3, 107–113.

- Wang, L., Fang, M., Liu, J., He, J., Deng, L., Li, J. and Lei, J. (2015) The influence of dispersed phases on polyamide/ZIF-8 nanofiltration membranes for dye removal from water, *RSC Adv.*, 5(63), 50942–50954.
- Wang, M., Wang, Z., Li, N., Liao, J., Zhao, S., Wang, J. and Wang, S. (2015) Relationship between polymer–filler interfaces in separation layers and gas transport properties of mixed matrix composite membranes, *J. Memb. Sci.*, 495, 252–268.
- Weng, T. H., Tseng, H. H. and Wey, M. Y. (2009) Preparation and characterization of multi-walled carbon nanotube/PBNPI nanocomposite membrane for H₂/CH₄ separation, *Int. J. Hydrogen Energy*, 34(20), 8707–8715.
- Wessling, M., Lidon Lopez, M. and Strathmann, H. (2001) Accelerated plasticization of thin-film composite membranes used in gas separation, *Sep. Purif. Technol.*, 24, 223–233.
- Wong, K. C., Goh, P. S. and Ismail, A. F. (2016) Effect of PMMA-MWNTs loading on CO₂ separation performance of thin film nanocomposite membrane, *J. Teknol.*, 78(12), 2180–3722.
- Wong, K. C., Goh, P. S. and Ismail, A. F. (2017) Highly permeable and selective graphene oxide-enabled thin film nanocomposite for carbon dioxide separation, *Int. J. Greenh. Gas Control*, 64, 257–266.
- Wong, K. C., Goh, P. S., Ng, B. C. and Ismail, A. F. (2015) Thin film nanocomposite embedded with polymethyl methacrylate modified multi-walled carbon nanotubes for CO₂ removal, *RSC Adv.*, 5(40), 31683–31690.
- Wu, D., Huang, Y., Yu, S., Lawless, D. and Feng, X. (2014) Thin film composite nanofiltration membranes assembled layer-by-layer via interfacial polymerization from polyethylenimine and trimesoyl chloride, *J. Memb. Sci.*, 472, 141–153.
- Wu, H., Li, X., Li, Y., Wang, S., Guo, R., Jiang, Z., Wu, C., Xin, Q. and Lu, X. (2014) Facilitated transport mixed matrix membranes incorporated with amine functionalized MCM-41 for enhanced gas separation properties, *J. Memb. Sci.*, 465, 78–90.
- Wu, H., Tang, B. and Wu, P. (2013) Optimization, characterization and nanofiltration properties test of MWNTs/polyester thin film nanocomposite membrane, *J. Memb. Sci.*, 428, 425–433.

- Wu, J. K., Ye, C. C., Liu, T., An, Q. F., Song, Y. H., Lee, K. R., Hung, W. S. and Gao, C. J. (2017) Synergistic effects of CNT and GO on enhancing mechanical properties and separation performance of polyelectrolyte complex membranes, *Mater. Des.*, 119, 38–46.
- Xia, J., Chung, T. S., Li, P., Horn, N. R. and Paul, D. R. (2012) Aging and carbon dioxide plasticization of thin polyetherimide films, *Polymer*, 53(10), 2099–2108.
- Xie, K., Fu, Q., Qiao, G. G. and Webley, P. A. (2019) Recent progress on fabrication methods of polymeric thin film gas separation membranes for CO₂ capture, *J. Memb. Sci.*, 572, 38–60.
- Xu, J., Wang, Z., Qiao, Z., Wu, H., Dong, S., Zhao, S. and Wang, J. (2019) Post-combustion CO₂ capture with membrane process: Practical membrane performance and appropriate pressure, *J. Memb. Sci.*, 581, 195–213.
- Yang, Y. K., China, P. R., Xie, X. L., China, P. R. and Mai, Y. W. (2011) *Functionalization of carbon nanotubes for polymer nanocomposites*, in McNally, T. and Pötschke, P. (eds.) *Polymer–Carbon Nanotube Composites*. Cambridge: Woodhead Publishing, 55–91.
- Yanilmaz, M., Lu, Y., Dirican, M., Fu, K. and Zhang, X. (2014) Nanoparticle-on-nanofiber hybrid membrane separators for lithium-ion batteries via combining electrospraying and electrospinning techniques, *J. Memb. Sci.*, 456, 57–65.
- Yao, J. and Wang, H. (2014) Zeolitic imidazolate framework composite membranes and thin films: synthesis and applications, *Chem. Soc. Rev.*, 43(13), 4470–4493.
- Yave, W., Car, A., Funari, S. S., Nunes, S. P. and Peinemann, K. V. (2010a) CO₂-philic polymer membrane with extremely high separation performance, *Macromolecules*, 43, 326–333.
- Yave, W., Car, A., Peinemann, K. V., Shaikh, M. Q., Rätzke, K. and Faupel, F. (2009) Gas permeability and free volume in poly(amide-b-ethylene oxide)/polyethylene glycol blend membranes, *J. Memb. Sci.*, 339, 177–183.
- Yave, W., Car, A., Wind, J. and Peinemann, K. V. (2010b) Nanometric thin film membranes manufactured on square meter scale: ultra-thin films for CO₂ capture, *Nanotechnology*, 21(39), 395301.
- Yazici, E., Yanik, S. and Yilmaz, M. B. (2017) Graphene oxide nano-domain formation via wet chemical oxidation of graphene, *Carbon*, 111, 822–827.

- Yeo, Z. Y., Chew, T. L., Zhu, P. W., Mohamed, A. R. and Chai, S. P. (2012) Conventional processes and membrane technology for carbon dioxide removal from natural gas: A review, *J. Nat. Gas Chem.*, 21(3), 282–298.
- Yi, C., Wang, Z., Li, M., Wang, J. and Wang, S. (2006) Facilitated transport of CO₂ through polyvinylamine/polyethylene glycol blend membranes, *Desalination*, 193(1–3), 90–96.
- Yin, J. and Deng, B. (2015) Polymer-matrix nanocomposite membranes for water treatment, *J. Memb. Sci.*, 479, 256–275.
- Yin, J., Kim, E. S., Yang, J. and Deng, B. (2012) Fabrication of a novel thin-film nanocomposite (TFN) membrane containing MCM-41 silica nanoparticles (NPs) for water purification, *J. Memb. Sci.*, 423–424, 238–246.
- Yin, X., Wang, J., Chu, N., Yang, J., Lu, J., Zhang, Y. and Yin, D. (2010) Zeolite L/carbon nanocomposite membranes on the porous alumina tubes and their gas separation properties, *J. Memb. Sci.*, 348, 181–189.
- Ying, Y., Liu, D., Ma, J., Tong, M., Zhang, W., Huang, H., Yang, Q. and Zhong, C. (2016) A GO-assisted method for the preparation of ultrathin covalent organic framework membranes for gas separation, *J. Mater. Chem. A*, 4(35), 13444–13449.
- Yoon, K., Hsiao, B. S. and Chu, B. (2009) Formation of functional polyethersulfone electrospun membrane for water purification by mixed solvent and oxidation processes, *Polymer*, 50(13), 2893–2899.
- Yu, S., Ma, M., Liu, J., Tao, J., Liu, M. and Gao, C. (2011) Study on polyamide thin-film composite nanofiltration membrane by interfacial polymerization of polyvinylamine (PVAm) and isophthaloyl chloride (IPC), *J. Memb. Sci.*, 379, 164–173.
- Yu, X., Wang, Z., Wei, Z., Yuan, S., Zhao, J., Wang, J. and Wang, S. (2010) Novel tertiary amino containing thin film composite membranes prepared by interfacial polymerization for CO₂ capture, *J. Memb. Sci.*, 362, 265–278.
- Yu, X., Wang, Z., Zhao, J., Yuan, F., Li, S., Wang, J. and Wang, S. (2011) An effective method to improve the performance of fixed carrier membrane via incorporation of CO₂-selective adsorptive silica nanoparticles, *Chinese J. Chem. Eng.*, 19(5), 821–832.

- Yuan, F., Wang, Z., Li, S., Wang, J. and Wang, S. (2012a) Formation–structure–performance correlation of thin film composite membranes prepared by interfacial polymerization for gas separation, *J. Memb. Sci.*, 421–422, 327–341.
- Yuan, F., Wang, Z., Yu, X., Wei, Z., Li, S., Wang, J. and Wang, S. (2012b) Visualization of the formation of interfacially polymerized film by an optical contact angle measuring device, *J. Phys. Chem. C*, 116(21), 11496–11506.
- Yuan, S., Wang, Z., Qiao, Z., Wang, M., Wang, J. and Wang, S. (2011) Improvement of CO₂/N₂ separation characteristics of polyvinylamine by modifying with ethylenediamine, *J. Memb. Sci.*, 378, 425–437.
- Yue, Y. N., Zeng, S., Wang, H., Wang, S., Wang, H. and Lu, J. X. (2018) One-pot synthesis of *D*-phenylalanine-functionalized multiwalled carbon nanotubes: A metal-free chiral material for the asymmetric electroreduction of aromatic ketones, *ACS Appl. Mater. Interfaces*, 10(27), 23055–23062.
- Zahri, K., Wong, K. C., Goh, P. S. and Ismail, A. F. (2016) Graphene oxide/polysulfone hollow fiber mixed matrix membranes for gas separation, *RSC Adv.*, 6(92), 89130–89139.
- Zhang, C., Ren, L., Wang, X. and Liu, T. (2010) Graphene oxide-assisted dispersion of pristine multiwalled carbon nanotubes in aqueous media, *J. Phys. Chem. C*, 114(26), 11435–11440.
- Zhang, H., Zheng, J., Zhao, Z. and Han, C. C. (2013) Role of wettability in interfacial polymerization based on PVDF electrospun nanofibrous scaffolds, *J. Memb. Sci.*, 442, 124–130.
- Zhang, J., Xin, Q., Li, X., Yun, M., Xu, R., Wang, S., Li, Y., Lin, L., Ding, X., Ye, H. and Zhang, Y. (2019) Mixed matrix membranes comprising aminosilane-functionalized graphene oxide for enhanced CO₂ separation, *J. Memb. Sci.*, 570–571, 343–354.
- Zhang, K. and Choi, H. J. (2015) Fabrication and viscoelastic characteristics of amino-functionalized multi-walled carbon nanotube/poly(methyl methacrylate) nanocomposites, *Compos. Struct.*, 125, 170–175.
- Zhang, K., Lim, J. Y. and Choi, H. J. (2009) Amino functionalization and characteristics of multi-walled carbon nanotube/poly(methyl methacrylate) nanocomposite, *Diam. Relat. Mater.*, 18, 316–318.

- Zhang, Y., Sunarso, J., Liu, S. and Wang, R. (2013) Current status and development of membranes for CO₂/CH₄ separation: A review, *Int. J. Greenh. Gas Control*, 12, 84–107.
- Zhao, J., Wang, Z., Wang, J. and Wang, S. (2006) Influence of heat-treatment on CO₂ separation performance of novel fixed carrier composite membranes prepared by interfacial polymerization, *J. Memb. Sci.*, 283, 346–356.
- Zhao, J., Wang, Z., Wang, J. and Wang, S. (2012) High-performance membranes comprising polyaniline nanoparticles incorporated into polyvinylamine matrix for CO₂/N₂ separation, *J. Memb. Sci.*, 403–404, 203–215.
- Zhao, L., Cheng, C., Chen, Y. F., Wang, T., Du, C. H. and Wu, L. G. (2015) Enhancement on the permeation performance of polyimide mixed matrix membranes by incorporation of graphene oxide with different oxidation degrees, *Polym. Adv. Technol.*, 26(4), 330–337.
- Zou, J. and Ho, W. S. W. (2006) CO₂-selective polymeric membranes containing amines in crosslinked poly(vinyl alcohol), *J. Memb. Sci.*, 286, 310–321.