RATCHETTING OF COMPOSITE PIPES

KHAIRUL SALLEH BIN BASARUDDIN

Submitted in partial fulfillment of the requirements for the degree of Master in Engineering (Mechanical)

Faculty of Mechanical Engineering University Technology Malaysia

OCTOBER 2007

This study is especially dedicated to my beloved Mommy and Daddy Brothers and Sisters, Beloved wife, *Norhayati Nor Hakimi* for everlasting love, care, and supports.....

ACKNOWLEDGMENT

First and foremost, I would like to express my utmost gratitude to my Creator, Allah s.w.t for His Rahmah and Rahim in making me a person that I am today. May His Grace is blessed upon all other Muslim and human being also.

With the accomplishment of this project, the author would like to extend the special and greatest gratitude to the project supervisor, Assoc. Prof. Dr. Amran Ayob of Faculty of Mechanical Engineering, Universiti Teknologi Malaysia for his enthusiastic effort and concern. With his invaluable advice, guidance and encouragement, the author was able to complete this project.

The author gratefully acknowledges the cooperation of En. Abdul Shukor, En. Mohd. Fadzli, En. Mohd Rizal, En. Ahmad Zahran, Mr. Chan, Ms. Sew Suh Fen and friends during the data collection.

Deepest thanks to the author's wife and family especially for their encouragement and support in life. Without them the author would not be able to complete the project.

ABSTRACT

The uniaxial ratchetting characteristics of fibre glass reinforced epoxy laminate have been investigated in the present project. The specimens were subjected to cyclic axial stress with a constant mean stress of 40 MPa and a varying amplitude stress of 26.67 MPa and 53.33 MPa. Tests were also performed on 50 mm diameter, Glass fibre Reinforced Epoxy (GRE) straight pipe. The pipe was subjected to a constant internal pressure of 1.875 MPa and a cyclic axial load. The finite element model in ABAQUS has also been simulated in similar loading case. The comparisons between experiment and simulation results were observed. The effect of fibre orientation on the rate of ratchetting was also investigated at the present project. The uniaxial and biaxial ratchetting strain was observed to increase with a number of cycles but decreased the rate of ratchetting. The specimen showed no further ratchetting rate and exhibited shakedown after some strain accumulation. On the basis of experiment and simulation, it appears that ratchetting would occur in the circumferential direction for a composite pipe subjected to constant internal pressure and cyclic displacement with no ratchetting observed in axial direction. A direction in fibre orientation seemed to have effect on the rate of ratchetting. Thus, the increasing of fibre angle from the axial load axis will increase the rate of ratchetting.

ABSTRAK

Perilaku ratchetting satu paksi ke atas laminat fibre glass reinforced epoxy telah dikaji dalam projek ini. Spesimen ini dikenakan tegasan paksi berkitar pada tegasan min malar 40 MPa dan tegasan amplitud 26.67 MPa dan 53.33 MPa. Ujian ke atas paip lurus jenis *Glassfiber Reinforced Epoxy (GRE)* berdiameter 50 mmm turut dijalankan. Paip ini telah dikenakan tekanan dalaman 1.875 MPa secara malar dan kitaran terikan paksi. Simulasi kaedah unsur tak terhingga menggunakan ABAQUS juga telah dilakukan dengan aplikasi beban yang sama. Perbandingan keputusan daripada eksperimen-eksperimen dan simulasi-simulasi turut dianalisis. Kesan arah orientasi fiber ke atas kadar ratchetiing juga dikaji dalam projek ini. Terikan ratchettting sepaksi dan dwipaksi menunjukkan pertambahan dengan bilangan kitaran tetapi kadar ratchetting berkurang. Spesimen menunjukkan tiada lanjutan ratchetting dan berlaku shakedown selepas beberapa pengumpulan terikan. Berdasarkan eksperimen dan simulasi, ia menunjukkan ratchetting hanya berlaku dalam arah lilitan paip komposit tersebut apabila dikenakan tekanan dalaman secara malar dan kitaran terikan paksi dengan tiada ratchetting berlaku dalam arah paksi paip. Arah dalam orientasi fiber juga memberi kesan ke atas kadar ratchetting. Pertambahan sudut fiber dari paksi arah beban akan meningkatkan kadar ratchetting.

TABLE OF CONTENTS

CHAPTER DESCRIPTION

PAGE

i
ii
iii
iv
v
vi
vii
X
xi
XV

INTRODUCTION 1 1 Introduction 1.1 1 1.2 Problem of Interest 2 **Research Objectives** 3 1.3 Scopes of Research 3 1.4

2	LIT	ERATURE REVIEW	4
	2.1	Uniaxial and Biaxial Ratchetting	4
	2.2	Ratchetting at the Material Level	6
	2.3	Ratchetting at the Structural Level	8
	2.4	Ratchetting Boundary	11

2.5	Experimental Techniques on Ratchetting Behaviour	12
2.6	Evaluation of Constitutive Models	14

3 **BASIC THEORIES** 15 3.1 15 The Elastic Stress-Strain Relationship 3.2 **Stress Categories** 16 3.2.1 Primary Stress 17 3.2.2 Secondary Stress 17 3.2.3 Peak Stress 17 3.3. Failure Theories 18 3.3.1 Maximum Shear Stress Yield Criterion (Tresca Yield Criterion) 18 3.3.2 Distortion Energy Criteria (von Mises Yield Criterion) 19 The Theory of Plasticity 3.4 19 Theory of Ratchetting and Low Cycle Failure 3.5 23 3.5.1 Ratchetting 23 3.5.2 Shakedown 25 3.5.3 Reverse Plasticity 26 3.6 The Prandtl-Reuss Equations 26

4	FOR	MULA	FION OF RATCHETTING	29
	4.1	Theor	etical Formulation	29
	4.2	Const	itutive Modeling	34
		4.2.1	Chaboche Model	35
		4.2.2	Guionnet Model	35
		4.2.3	Ohno Model	36
		4.2.4	Dafalias-Popov Model	36
		4.2.5	Parameters of the Models	37

5	VER	IFICATION OF RATCHETTING ON METALLIC PIPES	38
	5.1	Experiment	38
	5.2	Theoretical Calculation	42
	5.3	FEM	44
	5.4	Discussion	49

6	BASIC	C THEORY OF COMPOSITE MATERIALS	50
	6.1	Introduction	50
	6.2	Composite Mechanics	51
		6.2.1 Elastic Properties	51
		6.2.2 Material Response	52
	6.3	Failure Theories	53
		6.3.1 Maximum Stress Theory	53
		6.3.2 Maximum Strain Theory	54
		6.3.3 Deviatoric Strain Energy Theory (Tsai-Hill)	54
	6.4	Glass fiber Reinforced Epoxy (GRE) Pipe	56

7	UNIA	AXIAL RATCHETTING OF COMPOSITE LAMINATE	57
	7.1	Introduction	57
	7.2	Materials and Specimens	58
	7.3	Test Parameters	60
		7.3.1 Monotonic Tensile Test	60
		7.3.2 Loads	61
	7.4	Finite Element Models	63
		7.4.1 Geometry and model	63
		7.4.2 Material Properties	68
		7.4.3 Mesh	69
		7.4.4 Steps	71
		7.4.5 Loads and Boundary conditions	72
	7.5	Experimental Procedure	74
	7.6	Results and Discussions	75

8	BIA	XIAL RATCHETTING OF COMPOSITE PIPE	82
	8.1	Introduction	82
	8.2	Materials and Specimens	83
	8.3	Test Parameters	83
		8.3.1 Stress-strain characteristic	83
		8.3.1 Pressure Test	84
	8.4	Finite Element Models	85
		8.4.1 Onset of Ratchetting	86
		8.4.1.1 Loads	86
		8.4.1.2 Simulation	87
		8.4.1.3 Results	98
		8.4.2 Rate of Ratchetting	99
	8.5	Experimental setup	99
		8.5.1 Jig preparation	99
		8.5.2 Experimental procedure	100
	8.6	Results and Discussions	102

9	PAR	AMETRIC STUDY ON RATCHETTING OF COMPOSITE	111
	9.1	Introduction	111
	9.2	Stress-strain characteristic	111
	9.3	Uniaxial Ratchetting Rate	114
	9.4	Results and Discussions	115
10	CON	CLUSIONS	117

REFERENCES	119

APPENDICES

Х

124

LIST OF TABLES

TABLE	TITLE	PAGE
5.1	Axial and hoop strains recorded with internal	40
	$Pressure = 10.913 \text{ MN/m}^2$	
5.2	Axial and hoop strains recorded in ABAQUS.	45
5.3	Summary result for ratchetting (increment of strain)	47
	per cycle.	
7.1	Properties of unidirectional lamina specimen.	59
7.2	Results of uniaxial ratchetting.	75
8.1	The constant internal pressure values	85
8.2	Result of biaxial ratchetting.	101
9.1	Load application for uniaxial ratchetting test	114
9.2	Rachetting rate of uniaxial test result in μ	114

LIST OF FIGURES

FIGURE	TITLE	PAGE
21	Ratchetting response of pipe under constant pressure	and
	cyclic bending load of 200 kN	5
2.2	(a) Uniaxial ratchetting of annealed copper	c
	subjected to stress cycles with zero mean stress.	7
	(b) Cyclic hardening of annealed coppper subjected	
	to strain cycles.	7
2.3	(a) Uniaxial ratchetting of carbon steel subjected to	
	stress cycles with mean stress.	8
	(b) Cyclic softening and hardening of carbon steel	
	subjected to stress cycles with mean stress.	8
2.4	Force-displacement response in cyclic elbow test.	10
2.5	Axial and hoop strain responses in the cycling bendir	ıg
	of elbow experiment at extrados, intrados and flank.	11
2.6	Bree diagram, showing elastic, shakedown, reverse	
	plasticity and ratcheting regions.	12
2.7	Elbow testing fixture.	13
2.8	Typical strain response, hoop gaugeon elbow.	13
3.1	Tresca and von Mises failure criterion	19
3.2	Stress-Strain Curve for Uniaxial Loading.	21
3.3	Isotropic Hardening.	21
3.4	Bauschinger Effect for Uniaxial Loading.	22
3.5	Kinematic Hardening.	22
3.6	Ratchetting behaviour	24
3.7	Phenomenon of ratchetting.	25

3.8	Phenomenon of shakedown.	25
3.9	Phenomenon of reverse plasticity.	26
3.10	Mohr's circles for stress and plastic strain increment.	28
4.1	The axial stress/strain relationship during axial	
	strain cycling of the cylinder.	30
5.1	Uniaxial stress/strain characteristic of the mild steel	
	for the experimental work.	39
5.2	Schematic test set-up	40
5.3	Ratchetting response of pipe (a) Hoop direction;	
	(b) axial direction.	42
5.4	Finite element model (a) Shell elements	
	(b) Loads and Boundary conditions	44
5.5	Contour of Von Mises Stress; (a) In tension	
	(b) In compression.	45
5.6	Ratchetting response recorded in ABAQUS	
	(a) hoop direction; (b) axial direction.	47
5.7	Hoop strain vs axial strain results obtained from	
	ABAQUS.	48
6.1	Unidirectional fiber-reinforced composite.	51
6.2	Stress-Strain curve of an idealized fiber-reinforced	
	composite.	52
6.3	An orthotropic material.	53
6.4	Maximum Stress Theory, Maximum Strain Theory	
	and Tsai-Hill failure surfaces in stress space.	55
7.1	Geometry (units: mm) and photo of the specimen.	58
7.2	Specimen geometries and tensile properties formula.	59
7.3	[±45°] angle ply specimen for determination of in	
	plane lamina shear properties.	59
7.4	Monotonic stress-strain curve of the specimen.	61
7.5	The diagrams of input stress σ vs <i>t</i> under the stress	

	cycling.	62
7.6	Uniaxial cyclic stress test.	63
7.7	Creating laminate plate model (part-1).	65
7.8	Creating rigid body (dummy) model (part-2).	66
7.9	Joint the parts.	68
7.10	Define the material properties.	69
7.11	Discretized the elements model.	71
7.12	Set-up the loading steps.	71
7.13	Determination of loads and boundary conditions.	73
7.14	Setup of the experimental apparatus and gauge position.	74
7.15	Sketch of uniaxial ratchetting testing system.	75
7.16	Axial strain vs cycle.	78
7.17	von Mises stress contour.	79
7.18	Axial strain contour.	80
7.19	Uniaxial ratchetting strains result.	81
8.1	The winding angle of the pipe specimen (GRE).	83
8.2	Test set-up (a) Pipe connect to hydraulic pump	
	(b) Gauges connect to data Logger	84
8.3	The proportionality between internal pressure and	
	hoop strain.	85
8.4	Creating a pipe model (part-1).	88
8.5	Creating rigid body (dummy) model (part-2).	90
8.6	Joint the parts.	91
8.7	Define the material properties.	92
8.8	Discretized the elements model.	94
8.9	Set-up the loading steps.	94
8.10	Determination of loads and boundary conditions.	97
8.11	Onset of biaxial ratchetting test.	98
8.12	Components and jig for experimental setup.	100
8.13	Ratchetting test set-up.	101

8.14	The schematic layout set-up for ratchetting experiment.	101
8.15	Graph of hoop strain vs cycles.	104
8.16	Graph of axial strain vs cycles.	105
8.17	The von Mises stress contour.	106
8.18	The hoop strain contour.	108
8.19	The axial strain contour.	109
8.20	The hoop ratchetting strain.	110
8.21	The hoop ratchetting strain rate.	110
9.1	Fiber orientation of composite.	112
9.2	Monotonic tensile test curve for laminate $\pm 30^{\circ}$ fiber	
	angle.	113
9.3	Monotonic tensile test curve for laminate $\pm 45^{\circ}$ fiber	
	angle.	113
9.4	Monotonic tensile test curve for laminate $\pm 60^{\circ}$ fiber	
	angle.	114
9.5	Effect of fiber orientation to ratchetting rate.	116

NOMENCLATURE

SYMBOL

DEFINITION

S_m	mean stress
σ	stress tensor
$\sigma_{_0}$	size of the yield surface
α	center of the yield surface
S	deviatoric stress tensor
a	center of the yield surface in the deviatoric space
Н	plastic modulus
P_{ij}	spherical stress tensor
$\sigma_{\scriptscriptstyle m}$	hydrostatic stress
e _m	corresponding volumetric strain
$d\lambda$	instantaneous non-negative constant
ε^{P}	plastic strain
\mathcal{E}^{R}	ratchet strain
$darepsilon^{e}$	elastic strain increment
$darepsilon^p$	plastic strain increment
$d\varepsilon^{^{T}}$	total strain increment
σ	stress
$\sigma_{_y}$	yield stress
$\sigma_{_e}$	equivalent stress
$d\varepsilon_p$	equivalent plastic strain increment
n	$\sigma_{_{y}}/\sigma_{_{ heta}}$

E	Young modulus
ν	Poisson ratio
d	cylinder diameter
t	wall thickness
p	pressure
W	load

SUBSCRIPTS

R	radial direction
θ	hoop direction

 ϕ axial direction

CHAPTER 1

INTRODUCTION

1.1 Introduction

Piping networks are often employed in various industrial applications. Generally, piping systems in heavy industries such as power plants, offshore platforms, marines etc. are designed for normal operation loads (pressure) along with cyclic loads, such as earthquake. Cyclic excursions into the plastic range can lead to degradation and failure of such piping due to accumulation of deformation. The strain accumulation induced by cyclic loading is called ratchetting. Ratchetting can be either due to thermal processes or due to mechanical cyclic loading. In the present project, however, only mechanical ratchetting has been investigated.

Prevention of ratchetting is a difficult problem in the design of a component subjected to cyclic loads that may lead to inelastic deformation. During such loading, material and structural aspects interact. Large deformation of a piping system is possible under combination of primary (constant) and secondary (cyclic) loads. In such a case, a small amount of plastic strain, which is not reversed in each cycle, may lead to unacceptably large accumulated strain.

1.2 Problem of Interest

There are numerous studies on ratchetting behaviour. In the last two decades, uniaxial and biaxial ratchetting behaviours were studied experimentally and theoretically by some researchers, as reviewed by Ohno (1997), Bari and Hassan (2002) and Abdel-Karim (2005) and recently done by Chen et al. (2004), Kang et al. (2004), Feaugas and Gaudin (2004), Mayama et al. (2004), Vincent et al. (2004), Abdel-Karim (2005), Gupta et al. (2005), Johansson et al. (2005), Khoei and Jamali (2005), Yaguchi and Takahashi (2005) and so on. The existing results showed that the ratchetting varies depending on the material type. Based on the Armstrong–Frederick non-linear kinematic hardening rule (1996), many constitutive models have been constructed to simulate the uniaxial and biaxial ratchetting. Examples of these models have been created by Chaboche and Nouailhas (1989), Ohno and Wang (1993), Chaboche (1994), Delobelle et al. (2002), Gao et al. (2003), Vincent et al. (2004), Yaguchi and Takahashi (2005), Chen et al. (2004) and so on. The above-referred works were only focused on the ratchetting behaviour and its constitutive model on metallic material.

Ratchetting behaviour has also been observed in polymer materials, such as epoxy resin and Chen and Hui (2005) conducted series tests to study the ratchetting behaviour of PTFE under cyclic compression load, where the effects of loading rate, mean stress and stress amplitude on the ratchetting behaviour were discussed.

However, researches on ratchetting behaviour of composite materials are still relatively few. More investigations are necessary for in-depth understanding of the ratcheting phenomenon of these materials. More recently, composite pipes has further gained its importance in the offshore oil and gas industry due to its light-weight, corrosion resistance, and the new invention of Tension Leg Platforms (TLPs) for deepwater oil and gas exploration and production. Since the composite pipe is very important in the design and assessment of structure components, it is necessary to examine the ratchetting response of composite pipe. In order to understand the ratchetting behaviour for composite pipe, an experimental and simulation study was performed based on the similar experiment set-up for metallic material which already investigated previously.

1.3 Research Objectives

The objectives of this research project are:

- a) To derive the mathematical model for ratchetting rate of metallic material.
- b) To obtain the ratchetting rate of metallic material using finite element program (ABAQUS).
- c) To investigate the ratchetting behaviour of fibre glass reinforced epoxy plate and pipe experimentally.
- d) Validate the experiment results with finite element program (ABAQUS).
- e) To investigate the effect of fibre direction to ratchetting rate of composite materials.

1.4 Scope of Research

In this work, the main objective is to investigate the ratchetting behaviour of fibre glass reinforced epoxy. First, the dependence of the ratchetting of metallic materials on mean stress, stress amplitude and stress ratio are observed. When the ratchetting response of a metallic material is sufficiently understood and simulated, the ratchetting of the fibre glass reinforced epoxy are investigated in similar loading cases by performing a systematic experiment and simulation. Then, the verification between experiment and finite element simulation is discussed in detail. Finally, the effect of fibre direction to ratchetting rate of composite material is investigated.