

SYNTHESIS AND CHARACTERIZATION OF MOLYBDENUM CARBIDE
FROM OIL PALM FROND BASED ACTIVATED CARBON FOR CARBON
DIOXIDE REDUCTION

MOHD KHAIRUL ASYRAF B. AMAT MUSTAJAB

A thesis submitted in fulfilment of the
requirements for the award of the degree of
Doctor of Philosophy (Chemistry)

Faculty of Science
Universiti Teknologi Malaysia

MARCH 2017

For my beloved family & friends.....

To my beloved family that never stopped supporting, guiding and believe in countless ways, both direct and indirect. I was going to start listing them all, but realized they are just too many to do that justice - so please accept the fact that you are all mentioned in my daily prayer of thanks to a loving ALLAH s.w.t. Who will convey that thanks in His own way back to you.

ACKNOWLEDGEMENT

In the name of Allah, the most gracious and the most merciful

This thesis may possibly not be completed with the help of others. Firstly, I would like to express my deepest appreciation to my supervisor, Prof. Dr. Abdul Rahim Yacob for the support, guidance and enthusiasm. His tireless advice, insightful criticisms and patient encouragement have facilitated me to accomplish my mission effectively.

Beside that, I would also approach to thank to all the lecturers and staff in Department of Chemistry, especially to Physical Chemistry Lab II and Ibnu Sina Institute for the diligent advices, suggestions and solutions right the way through this research.

I would also like to show my appreciation to my research team, including postgraduate and undergraduate students, in favor of their supports, ideas and be of assistances to me in order to complete my project. Special thanks to all my colleagues for all those times, ears, advices and efforts. Before I disregard, thanks for MOSTI for the financial support through National Science Fellowship and UTM GUP (Q.J.130000.2526.04H98).

Last but certainly not least, I would like to express my gratitude to my dearly loved family members, my father, Mr. Amat Mustajab B. Omar, my mother, Mrs. Latifah Bte. Badri, my lovely wife, Nor Suryani Zabidi, my daughter, Nur Asyrani Humairah and my siblings, Mohd Khairul Lufti, Khairul Nizawati, Nurul Nadia and Muhammad Amirul Fitri. Thanks for all the love, faith, support, motivation and encouragement that help me to keep on reaching my dreams.

ABSTRACT

Energy-efficient technique is one of the vital keys to sustainable development in manufacturing processes. Microwave technique is an attractive approach in manufacturing as this technique offers several advantages such as rapid process and low energy requirement. In this study, microwave induced technique was applied to the preparation of activated carbons and molybdenum carbides. The activated carbons were prepared using oil palm fronds and activated using potassium hydroxide and phosphoric acid solutions at different concentrations. The products were then characterized using Fourier transform infrared spectroscopy (FTIR), nitrogen gas adsorption analysis and scanning electron microscopy (SEM). The results indicated that the highest surface area obtained by activation using phosphoric acid was 638.14 m²/g. However, the activated carbons prepared using a potassium hydroxide showed low surface areas for all samples. In the production of molybdenum carbide and potassium doped molybdenum carbide via microwave induced alloying, the prepared activated carbons were mixed with a 1 M molybdenum solution followed by the microwave-induced technique. All the prepared samples were chemically characterized using X-ray diffraction analysis (XRD), nitrogen gas adsorption analysis, SEM, energy dispersive X-ray (EDX), ammonia-temperature-programmed desorption analysis (TPD-NH₃), acidic titration method and electron spin resonance (ESR) spectroscopy. XRD analysis indicated that the perfect ratio for the preparation of molybdenum carbide is 2 Mo: 7 C. Nitrogen gas analysis showed that molybdenum carbide and potassium doped molybdenum carbide had surface areas of 95.0537 and 61.9302 m²/g, respectively. The ESR spectroscopy indicated the presence of a singlet peak at g-value of 1.9723 in the ESR spectra of potassium doped molybdenum carbide; this suggested that an electron was donated from potassium to the surface of molybdenum carbide. TPD-NH₃ indicated the presence of weak, moderate and strong acid sites for the molybdenum carbide and potassium doped molybdenum carbide. However, the addition of potassium decreased the amount of acid sites for the molybdenum carbide. The prepared carbides were evaluated as catalysts in the reduction reactions of carbon dioxide that were conducted using in-house modified reactor. The product was then characterized using FTIR. In the catalytic application, the molybdenum carbide showed a higher activity compared to the potassium doped molybdenum carbide. This was probably caused by the potassium moiety which poisoned the reaction while blocking the active sites. To better understand the reaction, kinetic analysis was carried out for the hydrogenation of carbon dioxide via molybdenum carbide. Results suggested an optimum temperature of 450°C, second order reaction, and the activation energy of 34.27 kJ/mol. In addition, thermodynamic parameters were also calculated using the Eyring equation and it was revealed that the values of ΔH^\ddagger , ΔS^\ddagger and ΔG^\ddagger were +40.04 kJ/mol, -1478.4 J/mol K and +1108.7 kJ/mol, respectively. These parameters proved that this reaction is not spontaneous and it is endothermic in nature with associative reaction mechanism.

ABSTRAK

Teknik cekap tenaga adalah salah satu kunci penting untuk pembangunan lestari dalam proses pembuatan. Teknik gelombang mikro merupakan pendekatan yang menarik kerana teknik ini menawarkan beberapa kelebihan seperti proses yang pesat dan keperluan tenaga rendah. Dalam kajian ini, teknik gelombang mikro teraruh telah digunakan untuk menyediakan karbon diaktifkan dan molibdenum karbida. Karbon-karbon teraktif telah disediakan dengan menggunakan pelepah kelapa sawit dan diaktifkan dengan menggunakan larutan kalium hidroksida dan asid fosforik pada kepekatan berlainan. Produk-produk kemudiannya dicirikan menggunakan spektroskopi inframerah transformasi Fourier (FTIR), analisis penjerapan gas nitrogen dan mikroskopi imbasan elektron (SEM). Keputusan menunjukkan bahawa luas permukaan yang paling tinggi yang diperolehi dengan pengaktifan menggunakan asid fosforik ialah $638.14 \text{ m}^2/\text{g}$. Walau bagaimanapun, karbon diaktifkan yang disediakan menggunakan kalium hidroksida menunjukkan luas permukaan yang rendah untuk semua sampel. Dalam penyediaan molibdenum karbida dan molibdenum karbida terdopkan kalium melalui pengalioian gelombang mikro teraruh, karbon diaktifkan yang telah disediakan dicampur dengan larutan molibdenum 1 M diikuti oleh teknik gelombang mikro teraruh. Semua sampel yang telah disediakan dicirikan secara kimia menggunakan analisis pembelauan sinar-X (XRD), analisis penjerapan gas nitrogen, SEM, serakan tenaga sinar-X (EDX), analisis suhu yang diprogram penjerapan gas ammonia (TPD-NH₃), kaedah titratan berasid dan spektroskopi resonans spin elektron (ESR). Analisis XRD menunjukkan bahawa nisbah yang sempurna untuk menyediakan molibdenum karbida ialah 2 Mo: 7 C. Analisis gas nitrogen menunjukkan karbida molibdenum dan molibdenum karbida terdopkan kalium mempunyai luas permukaan masing-masing 95.0537 dan $61.9302 \text{ m}^2/\text{g}$. Spektroskopi ESR menunjukkan kehadiran puncak tunggal di nilai-g 1.9723 bagi molibdenum karbida terdopkan kalium; ini mencadangkan elektron disumbangkan daripada kalium ke permukaan molibdenum karbida. Analisa TPD-NH₃ menunjukkan kehadiran tapak asid yang lemah, sederhana dan kuat bagi molibdenum karbida dan kalium terdopkan molibdenum karbida. Walau bagaimanapun, penambahan kalium telah mengurangkan jumlah tapak asid untuk molibdenum karbida itu. Karbida-karbida yang telah disediakan dinilai sebagai pemangkin di dalam tindak balas penurunan karbon dioksida yang telah dijalankan menggunakan reaktor diubahsuai di dalam makmal. Produk yang terhasil kemudiannya dicirikan menggunakan FTIR. Dalam aplikasi bermangkin, karbida molibdenum menunjukkan aktiviti yang lebih tinggi berbanding dengan molibdenum karbida terdopkan kalium. Ini mungkin disebabkan oleh moiety kalium telah meracuni tindak balas, pada masa yang sama menghalang tapak aktif. Untuk lebih memahami tindak balas, analisis kinetik telah dijalankan untuk penghidrogenan karbon dioksida melalui molibdenum karbida. Keputusan mencadangkan suhu optimum adalah 450°C , tindak balas peringkat kedua, dan tenaga pengaktifan kira-kira 34.27 kJ/mol . Tambah lagi, parameter termodinamik juga telah dikira dengan menggunakan persamaan Eyring dan didapati bahawa nilai ΔH^\ddagger , ΔS^\ddagger dan ΔG^\ddagger adalah masing-masing $+40.04 \text{ kJ/mol}$, -1478.4 J/mol K dan $+1108.7 \text{ kJ/mol}$. Parameter-parameter ini membuktikan bahawa tindak balas ini tidak spontan dan endotermik secara semula jadi dengan mekanisme tindak balas yang berseketu.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENTS	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xiii
	LIST OF FIGURES	xv
	LIST OF SYMBOLS	xix
	LIST OF ABBREVIATIONS	xx
	LIST OF APPENDICES	xxi
1	INTRODUCTION	1
	1.1 Background of research	1
	1.2 Research Problems	4
	1.3 Research Objectives	4
	1.4 Research Scope	5
	1.5 Significant of Research	6
2	LITERATURE REVIEW	8
	2.1 Activated Carbon	8
	2.2 Transition Metal Carbides	12
	2.3 Microwave energy for production of material	15
	2.4 Carbon Dioxide as Valuable Resources	18
	2.4.1 Introduction	18

2.4.2	Reverse Water-Gas Shift Reaction	20
2.5	Catalytic Application of Molybdenum Carbide	24
2.6	Effect of Metal Promoter to The Activity of The Catalyst	26
2.7	Kinetic and Thermodynamic Analysis of The Reaction	31
3	EXPERIMENTAL	36
3.1	Introduction	36
3.2	Materials	36
3.3	Experiments Section	38
3.3.1	Preparation of Activated Carbon from Oil Palm frond via Microwave Induced Heating.	38
3.3.1.1	Preparation of Activated Carbon Using Waste Oil Palm Frond Activated Using Potassium Hydroxide	39
3.3.1.2	Preparation of Activated Carbon Using Waste Oil Palm Frond activated Using Phosphoric Acid	41
3.3.2	Preparation of Molybdenum Carbide via Microwave Induced Alloying (MIA)	42
3.3.3	Preparation of Potassium Doped Molybdenum Carbide	43
3.4	Characterization Techniques for the Raw Oil Palm Frond, Prepared Activated Carbon, Prepared Molybdenum Carbide and Potassium Doped Molybdenum Carbide	43
3.5	Catalytic Activities of The Prepared Molybdenum Carbide and Potassium Doped Molybdenum Carbide for the Carbon Dioxide Reduction	46

4	PREPARATION AND CHARACTERIZATION OF ACTIVATED CARBON AND POTASSIUM DOPED ACTIVATED CARBON FROM WASTES OIL PALM FROND VIA MICROWAVE INDUCED ACTIVATION	49
4.1	Introduction	49
4.2	Characterization of Waste Oil Palm Frond Activated Carbon prepared by Microwave Induced Potassium Hydroxide activation	49
4.2.1	Themogravimetric Analysis of Raw Oil Palm Frond	50
4.2.2	Analysis of Functional Groups via Fourier Transform Infrared Spectroscopy (FTIR)	52
4.2.3	Determination of Surface Area of The Prepared Activated Carbon via Nitrogen gas Adsorption Analysis	56
4.2.4	Analysis of Surface Morphology via Field Emission Scanning Electron Microscopy-Energy Dispersive X-Ray (FESEM-EDX)	57
4.3	Characterization of Waste Oil Palm Frond Activated Carbon prepared by Microwave Induced Phosphoric acid Activation.	65
4.3.1	Identification of Organic Functional Groups In The Raw Oil Palm Frond and Produced Activated Carbon by Fourier Transform Infrared (FT-IR)	65
4.3.2	Determination of Surface Area of The Prepared Activated Carbon via Nitrogen gas Adsorption Analysis.	68
4.3.3	Surface Morphology Characterization of The Prepared Activated Carbon via Field Emission Scanning Electron Microscopy	72
4.4	Conclusion	74

5	PREPARATION AND CHARACTERIZATION OF MOLYBDENUM CARBIDE AND POTASSIUM DOPED MOLYDENUM CARBIDE VIA MICROWAVE INDUCED ALLOYING	75
5.1	Introduction	75
5.2	Preparation of Molybdenum Carbide via Microwave Induced Alloying	75
5.2.1	Structure Characterization for The Prepared Molybdenum Carbide at Different Ratio of Molybdenum by X-ray Diffraction Analysis	76
5.2.2	Structure Characterization for The Prepared Molybdenum Carbide at Different Ratio of Carbon by X-ray Diffraction Analysis	79
5.2.3	Surface Morphology Characterization by Scanning Electron Microscope	84
5.3	Preparation of Potassium Doped Molybdenum Carbide	86
5.4	Analysis of Surface Properties for Prepared Molybdenum Carbide and Potassium Doped Molybdenum Carbide via Nitrogen gas Adsorption Analysis	89
5.5	Characterization of Prepared Molybdenum Carbide and Potassium Doped Molybdenum Carbide via Electron Spin Resonance Spectrometer	93
5.6	Investigation of Acidity Properties of The Prepared Molybdenum Carbide and Potassium Doped Molybdenum Carbide	98
5.7	Conclusion	101
6	APPLICATION OF THE PREPARED MOLYBDENUM CARBIDE AND POTASSIUM DOPED MOLYBDENUM CARBIDE AS AN HETEROGENEOUS CATALYST FOR HYDROGENATION OF CARBON DIOXIDE	103
6.1	Introduction	103

6.2	Hydrogenation of Carbon Dioxide via the Prepared Molybdenum Carbide and Potassium Doped Molybdenum Carbide	104
6.2.1	The Activity and Effectiveness of the Prepared Molybdenum Carbide for the Hydrogenation of Carbon Dioxide	104
6.2.2	The Activity and Effectiveness of the Prepared Potassium Doped Molybdenum Carbide for The Hydrogenation of Carbon Dioxide	109
6.2.3	Proposed Reaction Mechanism and Schematic Model of Mechanism for the Carbon Dioxide Hydrogenation via the Prepared Molybdenum Carbide	114
6.2.4	Reuseablility of the Prepared Molybdenum Carbide as a Catalyst in the Hydrogenation of Carbon Dioxide	116
6.3	Analysis of Kinetic for the Hydrogenation of Carbon Dioxide via the Prepared Molybdenum Carbide	119
6.3.1	The Effect of Time on the Hydrogenation of Carbon Dioxide, Catalyzed by the Prepared Molybdenum Carbide	119
6.3.2	Kinetic Analysis of Hydrogenation of Carbon Dioxide via the Prepared Molybdenum Carbide	122
6.4	Thermodynamic Analysis of Hydrogenation of Carbon Dioxide via the Prepared Molybdenum Carbide	125
6.5	Analysis of Kinetic for the Hydrogenation of Carbon Dioxide, Catalyzed by Potassium Doped Molybdenum Carbide	132
6.6	Conclusion	134

7	CONCLUSIONS AND RECOMMENDATIONS	135
7.1	Conclusions	135
7.2	Recommendations	138
	REFERENCES	139
Appendices	A-C	169-172

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	List of pores with their specific measurement	9
2.2	List of the published papers with specific molybdenum sources	14
2.3	List of literature papers regarding the application of microwave heating technique	17-18
2.4	List of barriers, strategic goals and industrial opportunities for utilization of CO ₂	20
2.5	Lists of published papers regarding the RWGS reaction	21-23
2.6	Lists of published papers regarding the molybdenum carbide as a catalyst	25-26
2.7	Lists of published papers regarding the doped-catalyst	28-30
2.8	Lists of published papers regarding kinetic approach for the reaction	31-33
2.9	The equation with their liner form and list of constants	34
3.1	Sample notations for the prepared potassium doped activated carbon	40
3.2	Sample notations for the prepared activated carbon	41
3.3	List of the ratio for preparation of molybdenum carbide	42
4.1	List all the absorption peaks with a specific functional group for raw oil-palm frond and prepared activated carbons	55-56
4.2	Elemental analysis via EDX for raw oil palm frond and the prepared samples	64-65
4.3	List all the absorption peaks with a specific functional group for raw oil-palm frond and prepared activated carbons	68-69

5.1	Elemental analysis via energy dispersive X-ray for K-Mo ₂ C	89
5.2	Surface properties of Mo ₂ C and KMo ₂ C	89
5.3	Result of TPD-NH ₃ for molybdenum carbide and potassium doped molybdenum carbide	99
5.4	The acidic properties of the catalysts	101
6.1	Lists of published papers regarding deactivation of catalyst by alkali metal	113
6.2	Reaction order and specific integrated kinetic equation for this reaction	123
6.3	Value of thermodynamic parameters for this analysis	131

LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
3.1	Flow chart of research activities	37
3.2	The schematic diagram of modified microwave oven	40
3.3	Sample tube for ESR investigation	46
3.4	Arrangement of catalyst in a glass tube	47
3.5	Schematic diagram for the in-house built reactors	48
4.1	TGA/DTG curves of raw oil palm frond	51
4.2	FTIR spectra for ROPF, C-OPF, AC-COM, C1%, C2%, C3%, C4%, C5%, C6%, C7%, C8%, C9% and C10%.	54
4.3	Single point BET surface area of ROPF, C-OPF, prepared carbons and commercial activated carbon	57
4.4	FESEM Micrograph for ROPF (1000x magnification)	59
4.5	FESEM Micrograph for C-OPF (1000x magnification)	59
4.6	FESEM Micrograph for C1% with magnification of 2000x	60
4.7	FESEM Micrograph for C2% with magnification of 2000x	60
4.8	FESEM Micrograph for C3% with magnification of 2000x	61
4.9	FESEM Micrograph for C4% with magnification of 2000x	61
4.10	FESEM Micrograph for C5% with magnification of 2000x	61
4.11	FESEM Micrograph for C6% with magnification of 2000x	62
4.12	FESEM Micrograph for C7% with magnification of 2000x	62
4.13	FESEM Micrograph for C8% with magnification of 2000x	62
4.14	FESEM Micrograph for C9% with magnification of 2000x	63
4.15	FESEM Micrograph for C10% with magnification of 2000x	63
4.16	FTIR spectra for ROPF, AC-P10%, AC-P20%, AC-P30%, AC-P40%, AC-P50%, AC-P60%, AC-P70% and AC-P80% respectively	67

4.17	Single point BET surface area of oil palm frond (OPF), prepared activated carbons and commercial activated carbon	70
4.18	Adsorption-desorption isotherms plot for AC-P60%	71
4.19	BJH Pore distribution plot for AC-P60%	72
4.20	FESEM Micrograph for oil-palm frond with magnification of 2500x	73
4.21	FESEM Micrograph for AC-P40% with magnification of 5000x	74
4.22	FESEM Micrograph for AC-P60% with magnification of 5000x	74
4.23	FESEM Micrograph for AC-P70% with magnification of 5000x	74
5.1	XRD patterns for a) 0.5:7, b) 1.0:7, c) 1.5:7, d) 2.0:7, e) 2.5:7 and f) 3.0:7 prepared molybdenum carbides respectively	78
5.2	Peak analysis for a) 23.3 ° (orthorhombic MoO ₃), b) 25.9 ° (tetragonal MoO ₂) and c) 39.7 ° (hexagonal Mo ₂ C)	79
5.3	The XRD diffractograms for synthesized ratio of a) 2:3, b) 2:4, c) 2:5, and d) 2:6	82
5.4	The XRD diffractograms for synthesized ratio of a) 2:7, b) 2:8, c) 2:9 and d) 2:10	82
5.5	Peak analysis for a) 23.3 ° (orthorhombic MoO ₃), b) 25.9 ° (tetragonal MoO ₂) and c) 39.7 ° (hexagonal Mo ₂ C)	83
5.6	SEM Micrograph of prepared Mo ₂ C at ratio 2.0:7 at 500x magnification	85
5.7	SEM Micrograph of prepared Mo ₂ C at ratio 2.0:7 at 4000x magnification	85
5.8	Element mapping for prepared Mo ₂ C, which are (a) molybdenum and (b) carbon	86
5.9	XRD diffractogram for potassium doped molybdenum carbide	87
5.10	The SEM micrograph for the potassium doped molybdenum carbide	88
5.11	Adsorption-desorption isotherms of nitrogen gas for (a) K-Mo ₂ C and (b) Mo ₂ C	90
5.12	DFT Pore Distribution plot for Mo ₂ C	91
5.13	DFT Pore Distribution plot for K-Mo ₂ C	91
5.14	BJH Pore Distribution plot for Mo ₂ C	92
5.15	BJH Pore Distribution plot for K-Mo ₂ C	92

5.16	ESR spectra of (a) non doped molybdenum carbide and (b) potassium doped molybdenum carbide	95
5.17	Proposed model for interaction of the donated electron from potassium on Mo ₂ C surface	96
5.18	Change of ESR signal for potassium doped molybdenum carbide within 30 minutes of UV irradiation	97
5.19	Proposed model for interaction of the donated electron from potassium to hydrogen molecule at surface of Mo ₂ C	98
5.20	TPD-NH ₃ spectra for (a) Mo ₂ C and (b) K-Mo ₂ C	99
6.1	Infrared spectra of the collected products at temperatures (a) 100°C, (b) 150°C, (c) 200°C and (d) 250°C respectively	106
6.2	Infrared spectra of the collected products at temperatures (a) 300°C, (b) 350°C, (c) 400°C, (d) 450°C and 500°C respectively	106
6.3	Percentage conversion of carbon dioxide at different temperature for Mo ₂ C catalyst	107
6.4	Infrared spectra of the collected products at temperatures (a) 100°C, (b) 150°C, (c) 200°C and (d) 250°C respectively	109
6.5	Infrared spectra of the collected products at temperatures (a) 300°C, (b) 350°C, (c) 400°C (d) 450°C and (e) 500°C respectively	110
6.6	Percentage conversion of carbon dioxide at different temperature for K-Mo ₂ C catalyst	111
6.7	The proposed models to represent the poisoning effect of potassium in the molybdenum carbide, which are (a) reducing surface area and (b) donated electrons occupied the oxygen-vacancy cavity	114
6.8	The model of schematic mechanism for this reaction	115
6.9	The reusability of the prepared molybdenum carbide in the hydrogenation of carbon dioxide at temperature 350°C	117
6.10	The reusability of the prepared molybdenum carbide in the hydrogenation of carbon dioxide at temperature 400°C	117
6.11	The reusability of the prepared molybdenum carbide in the hydrogenation of carbon dioxide at temperature 450°C	118
6.12	Percentage conversion of carbon dioxide catalyzed by prepared	

	molybdenum carbide at different temperatures for 60 minutes	120
6.13	Zero order graph	123
6.14	First order graph	124
6.15	Second order graph	124
6.16	Graph of Arrhenius Law for zero order reaction	126
6.17	Graph of Arrhenius Law for first order reaction	126
6.18	Graph of Arrhenius Law for second order reaction	126
6.19	A model of an activation energy profile for this reaction	127
6.20	Graph of Eyring equation for zero order reaction	128
6.21	Graph of Eyring equation for first order reaction	129
6.22	Graph of Eyring equation for second order reaction	129
6.23	Graph of van't Hoff for zero order reaction	129
6.24	Graph of van't Hoff for first order reaction	130
6.25	Graph of van't Hoff for second order reaction	130
6.26	Comparison of catalyst's activity towards time of reaction at temperature 400°C	133
6.27	Analysis of kinetic for the hydrogenation of carbon dioxide catalyzed by the prepared Mo ₂ C and K-Mo ₂ C	134

LIST OF SYMBOLS

$^{\circ}\text{C}$	-	degree Celsius
μm	-	micrometer
nm	-	nanometer
cm	-	centimetre
g	-	gram
ID	-	internal diameter
K	-	Kelvin
mL	-	milliliter
θ	-	Half angle of diffraction beam
λ	-	Wavelength

LIST OF ABBREVIATIONS

BET	-	Brunauer-Emmett-Teller
DTA	-	Differential thermal analysis
TGA	-	Thermogravimetry analysis
EDX	-	Energy Dispersive X-ray analysis
DFT	-	Density Functional Theory
FTIR	-	Fourier Transformation Infrared
ESR	-	Electron Spin Resonance
TPD	-	Temperature Programmed Desorption
SEM	-	Scanning Electron Microscope
NA	-	nitrogen adsorption
XRD	-	X-ray Diffraction
FESEM	-	Field Emission Scanning Electron Microscope
XRD	-	X-Ray Diffraction
KBr	-	Potassium Bromide
TMC		Transition Metal Carbide
MIA		Microwave Induced Alloying
AHM		Ammonium Hepta Molybdate

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	XRD Peaks assignment for all prepared molybdenum carbide	169
B	ESR spectra for UV irradiation of potassium doped molybdenum carbide (Subsection 5.5, Figure 5.18)	171
C	Calibration curve for prediction of mole of carbon monoxide	172

CHAPTER I

INTRODUCTION

1.1 Background of Research

The future of the materials, manufacturing technology depends on three major ideas; energy efficiency, sustainability and economic viability. Among of these ideas, energy efficiency is the top priority for the growth of this industry as researches spend a lot of time and energy to find and introduce any new energy efficient manufacturing technology as a conventional heating method waste a huge amount of energy, therefore affected the environment. Introduction of microwave technique nowadays seems like a promising solution as this technology offers several advantages such as rapid processing, energy efficient process and reduced cost of operation. In addition, the microwave method also opens new edge of knowledge, especially on the interaction of this energy to the atomic structure of the starting material which could be a reason for the rising interest. Since the first report of this technology in 1971, significant and positive rising numbers of publications were shown for the past few decades. Thus, in this research, application of microwave heating was fully utilized, especially in the preparation of activated carbon and molybdenum carbide.

Recently, microwave induced activation or microwave heating has been introduced in the preparation of activated carbon. This new technology is applied as the carbonaceous material known as a microwave absorbent. Beside faster time of preparation and energy efficient method, another reason could be the intention of selecting this kind of heating method is the prepared activated carbon has a higher surface area and pore volume (Tan *et al.*, 2008). These two properties are highly

required for the best activated carbon, therefore, microwave energy is proven to achieve this result. Thus, in this study, the activated carbon was prepared via Microwave Induced Activation technique using waste oil palm frond as a carbon source and two activation agents, which are potassium hydroxide and phosphoric acid respectively.

A number of methods were proposed for molybdenum carbide synthesis and each process has its own characteristics of powder produced; Combustion Synthesis (CS), Self-propagating High Temperature Synthesis (SHS), Direct Carburization, Field Activated combustion method. However, the major drawback of these methods is it requires long time of combustion and high energy preparation. Thus, many researchers suggested the easier, faster and energy saving ideas for transition metal carbides synthesis and microwave looks promising. (Lu *et al.*, (2012) had successfully prepared tungsten carbide/ carbon composite by the Microwave Heating (MH) technique. This method offers numerous advantages compared to other access method, for instance, it can be rapidly synthesized in one-step process, and thus it is economical and can be synthesized at lower temperature. In addition, Kitchen *et al.*, (2014) underlined that strong coupling of carbon with microwave is the key of success of this application. Thus, in this research, the molybdenum carbides were prepared via Microwave Induced Alloying.

TMC especially Mo_2C were studied for their reactivity on oxidation, hydrogen transfer reaction such as hydrogenation, isomerization, desulfurization and methanation. In this case, many researches proved that the catalytic behavior of TMCs matched and some time, exceeding the best-known precious noble metal in hydrogen transfer reaction. Compared to metal sulfides, metal carbide possesses superior hydrogen adsorption, activation and transfer capabilities, and then it has prospective application in CO hydrogenation reactions (Fang *et al.*, 2009). Besides that, molybdenum carbide is also active in various reactions, such as decomposition of formic acid (Flaherty *et al.*, 2010), water gas shift (WGS) react to produce hydrogen (Moon, 2009) and hydrogenation reaction (Liu *et al.*, 2014, Xu *et al.*, 2014, Pang *et al.*, 2012 and Aoki *et al.*, 2013).

Carbon dioxide, known as greenhouse gas, mainly generated from the combustion reaction of organic compound. Previously, this gas always considers as waste product as well as contributing to global warming, however, this image has turned drastically as great resources, plus business opportunity since researcher found that recycling of CO₂ via catalytic conversion reaction is the promising method to reduce total contents of CO₂ in the atmosphere and generate valuable product such as methane and methanol (Centi & Perathoner 2004, De Falco *et al.*, 2013, Wang & Gong 2011 and Kaiser *et al.*, 2013). On the other hand, the recycling idea opens new dimensions of research and technology regarding catalyst to handle this reaction perfectly.

In this study, Microwave Induced Alloying (MIA) is introduced using simple modified household microwave oven to prepare the activated carbon from the waste oil palm frond and also, molybdenum carbide and potassium doped molybdenum carbide. In addition, this study also explores the effect of potassium as a dopant to the properties of the molybdenum carbide as well as for the reaction. Several literature papers suggested the potassium as a dopant initiated significant influence to the surface and catalytic properties of the molybdenum carbide (Chiang *et al.*, 2012, Kotarba *et al.*, 2004 and Pistonesi *et al.*, 2012). Therefore, for the preparation of potassium doped molybdenum carbide, the unwashed activated carbon prepared via potassium hydroxide were used as this preparation tends to manipulate the potassium residues which always remained as impurities in the preparation of activated carbon.

Consequently, the best prepared molybdenum carbide and potassium doped molybdenum carbide were applied as a catalyst for the hydrogenation of CO₂. Catalyst performance in terms of capability and reactivity to convert CO₂ become the Key Performances Index (KPI) to evaluate the quality of this catalyst, thus hopefully contribute to knowledge's world.

1.2 Research Problems

This research is purposely to introduce another edge of knowledge for the preparation of the molybdenum carbide. To date, the widespread method to prepare the molybdenum carbide is the temperature-programmed reduction using hydrocarbon as a carbon source. However, Liang *et al.*, (2002) explained that this technique has several drawbacks such as high temperature of preparation, the carburization processes must be carefully controlled, prepared carbide surface is contaminated by polymeric carbon and furthermore blocks and covers the active site. Thus, to elucidate this problem, the application of the activated carbon has been approached as a carbon source for this research. Activated carbon generally has a high surface area and well-developed pores might help in term of enhancing the surface area of the product as well as absorption capability. These two characters are obliging for this catalyst, especially this catalyst was tested to the gaseous reaction.

Secondly, there is a limited number of the published paper regarding the kinetic and thermodynamic for the carbon dioxide hydrogenation via molybdenum carbide as a catalyst. Thus, this fact opens the opportunity for this study to introduce and suggest new ideas to understand and explore this area. The majority of the published literature discussed more specific to the activity of the catalyst and proposing a kinetic model to represent their work. However, no specific links to incorporate the kinetic and thermodynamic of the reaction as these two subjects are supposed to be a connected. As the kinetic purposely to study the effectiveness of the catalyst, the thermodynamic approach is compulsory to prove this reaction is workable and conducted by the catalyst.

1.3 Research Objectives

The objectives of this research are listed below:

1. To prepare and characterize the activated carbon via Microwave Induced Alloying technique.
2. To prepare and characterize molybdenum carbide and potassium doped molybdenum carbide via Microwave Induced Alloying technique.
3. To determine the activity of nano molybdenum carbide and potassium doped molybdenum carbide in the CO₂ hydrogenation reaction.
4. To study the mechanism of CO₂ hydrogenation reaction catalyzed by prepared nano molybdenum carbide and potassium doped molybdenum carbide.
5. To analyze the kinetic and thermodynamic parameters of carbon dioxide hydrogenation via the prepared molybdenum carbide.

1.4 Research Scope

The scope of the study is divided into 4 major stages. The first stage is the preparation of activated carbon using waste oil palm frond. This stage introduced Microwave Induced Activation technique to prepare the activated carbon. At this stage, two different sources of activating agents were used, which were potassium hydroxide and phosphoric acid respectively. The prepared activated carbons were characterized using Fourier transform infrared, nitrogen gas adsorption analysis and field emission scanning electron microscope –energy dispersive X-ray.

The second stage of this research is the preparation of molybdenum carbide and potassium doped molybdenum carbide. For this stage, ammonium hepta molybdate was used as a metal precursor while the prepared activated carbons plays role as carbon sources. Selection of the activated carbon was based on highest surface area obtained by nitrogen gas adsorption analysis. Microwave induced alloying technique was introduced to substitute the conventional carburization process of preparation molybdenum carbide. For the potassium doped molybdenum carbide, the prepared potassium doped activated carbon was applied as a carbon source, which was previously activated using the known amount of the potassium hydroxide. The prepared carbon with the highest amount of potassium was applied as a carbon

precursor for the preparation of potassium doped molybdenum carbide. The physicochemical properties of the prepared molybdenum carbide and potassium doped molybdenum carbide was characterized via X-ray diffraction analysis, scanning electron microscope (SEM), temperature programmed desorption, acid-titration method, electron spin resonance and nitrogen gas adsorption Analysis.

The third stage of this research is the prepared molybdenum carbide and potassium doped molybdenum carbide were applied as a catalyst for CO₂ hydrogenation. The main objectives are to find out the activity, selectivity and stabilities of the prepared molybdenum carbide and potassium doped molybdenum carbide as a catalyst for this reaction. Furthermore, the mechanism of this reaction was proposed at the end of this project.

Lastly, the kinetic and thermodynamic parameters for hydrogenation of carbon dioxide were analyzed. The analysis of kinetic employed basic graphical method to identify the reaction order and rate. In addition, the activation energy was also calculated using the Arrhenius Law. Then, for the thermodynamic analysis, the acknowledged equations, Eyring equation and van't Hoff equation were used to calculate the thermodynamic parameters which are entropy, enthalpy and the Gibbs free energy of activation.

1.5 Significance of Research

This study expectantly can contribute to the knowledge's world by applying the Green Chemistry principle as a main inspiration to conduct this research. To date, in the preparation of materials, researchers nowadays always find the right technique to prepare their material at the same time, try to minimize the energy required. Generally, the main problem of the heat source from the conventional oven is the heat loss to the environment could make the reaction requires more time for the heat transfers. Thus, in this research, the application of the microwave energy purposely to

REFERENCES

- Ahmad, M. A., Ahmad Puad, N. A., and Bello, O. S. (2014). Kinetic, Equilibrium and Thermodynamic Studies of Synthetic Dye Removal Using Pomegranate Peel Activated Carbon Prepared By Microwave-Induced KOH Activation. *Water Resources and Industry*, 6, 18–35.
- Alslaibi, T. M., Abustan, I., Ahmad, M. A., and Foul, A. A. (2013). A Review: Production Of Activated Carbon From Agricultural Byproducts Via Conventional And Microwave Heating. *Journal of Chemical Technology And Biotechnology*, 88, 1183–1190.
- Aoki, Y., Tominaga, H., and Nagai, M. (2013). Hydrogenation of CO on Molybdenum and Cobalt Molybdenum Carbide Catalysts - Mass and Infrared Spectroscopy Studies. *Catalysis Today*, 215, 169–175.
- Ardakani, S. J., Liu, X., and Smith, K. J. (2007). Hydrogenation and Ring Opening of Naphthalene on Bulk and Supported Mo₂C Catalysts. *Applied Catalysis A: General*, 324, 9–19.
- Bania, K. K., Bharali, D., Viswanathan, B., and Deka, R. C. (2012). Enhanced Catalytic Activity of Zeolite Encapsulated Fe (III) -Schiff-Base Complexes for Oxidative Coupling of 2-Naphthol. *Inorganic Chemistry*, 51, 1657–1674.
- Bassyouni, F. A., Abu-Bakr, S. M., and Rehim, M. A. (2012). Evolution of Microwave Irradiation and Its Application in Green Chemistry and Biosciences. *Research on Chemical Intermediates*, 38, 283–322.
- Bastos, L. C. A., Monteiro, W. R., Zacharias, M. A., Da Cruz, G. M., and Rodrigues, J. A. J. (2008). Preparation and Characterization of Mo/W Bimetallic Carbides by Using Different Synthesis Methods. *Catalysis Letters*, 120, 48–55.
- Bej, S. K., Bennett, C. A., and Thompson, L. T. (2003). Acid and Base Characteristics of Molybdenum Carbide Catalysts. *Applied Catalysis A: General*, 250, 197–208.

- Bhaskar, T., Reddy, K. R., Kumar, C. P., Murthy, M. R. V. S., and Chary, K. V. R. (2001). Characterization and Reactivity of Molybdenum Oxide Catalysts Supported on Zirconia. *Applied Catalysis A: General*, 211, 189–201.
- Bhavani, A. G., Kim, W. Y., and Lee, J. S. (2013). Barium Substituted Lanthanum Manganite Perovskite for CO₂ Reforming of Methane. *ACS Catalysis*, 3, 1537–1544
- Blasco, T., Botella, P., Concepción, P., López Nieto, J. M., Martínez-Arias, A., and Prieto, C. (2004). Selective Oxidation of Propane to Acrylic Acid on K-Doped MoVSbo Catalysts: Catalyst Characterization and Catalytic Performance. *Journal of Catalysis*, 228 (2), 362–373.
- Bogdal, D., and Prociak, A., (2007). Microwave Synthesis of Polymeric Materials: Scale Up and Commercial Aspects. *Chemistry Today*, 25 (3), 44–44
- Büchel, R., Baiker, A., and Pratsinis, S. E. (2014). Effect of Ba and K Addition and Controlled Spatial Deposition of Rh in Rh/Al₂O₃ Catalysts for CO₂ Hydrogenation. *Applied Catalysis A: General*, 477, 93–101.
- Busca, G. (2009). Bases and Basic Materials in Industrial and Environmental Chemistry: A Review of Commercial Processes. *Industrial and Engineering Chemistry Research*, 48 (14), 6486–6511
- Bustamante, F., Enick, R. M., Cugini, A. V., Killmeyer, R. P., Howard, B. H., Rothenberger, K. S., Ciocco, M.V., Morreale, B.D., Chattopadhyay, S., and Shi, S. (2004). High-Temperature Kinetics of the Homogeneous Reverse Water-Gas Shift Reaction. *American Institute of Chemical Engineers Journal*, 50(5), 1028–1041.
- Bustamante, F., Enick, R., Rothenberger, K., Howard, B., Cugini, A., Ciocco, M., and Morreale, B. (2002). Kinetic Study of the Reverse Water Gas Shift Reaction in High-Temperature, High-Pressure Homogeneous Systems. *ACS Division of Fuel Chemistry*, 47 (2), 663–664.
- Calafat, A., Vivas, F., and Brito, J. L. (1998). Effects of Phase Composition and of Potassium Promotion on Cobalt Molybdate Catalysts For The Synthesis of Alcohols From CO₂ And H₂. *Applied Catalysis A: General*, 172, 217–224.
- Centi, G., and Perathoner, S. (2004). Heterogeneous Catalytic Reactions with CO₂: Status and Perspectives. *Studies in Surface Science And Catalysis*, 153, 1–8

- Chang, Y. A., Toth, L. E., and Tyan, Y. S. (1971). On The Elastic and Thermodynamic Properties of Transition Metal Carbides. *Metallurgical Transactions*, 2(1), 315–320.
- Chary, K. V. R., Bhaskar, T., Kishan, G., and Reddy, K. R. (2001). Characterization and Reactivity of Molybdenum Oxide Catalysts Supported on Niobia. *The Journal of Physical Chemistry B*, 105(19), 4392–4399
- Chaudhury, S., Mukerjee, S. K., Vaidya, V. N., and Venugopal, V. (1997). Kinetics and Mechanism of Carbothermic Reduction of MoO_3 to Mo_2C . *Journal of Alloys and Compounds*, 261, 105–113.
- Chen, A., Wang, Q., Li, Q., Hao, Y., Fang, W., and Yang, Y. (2008). Direct Synthesis of Methanethiol From H_2S -Rich Syngas Over Sulfided Mo-Based Catalysts. *Journal of Molecular Catalysis A: Chemical*, 283, 69–76.
- Chen, C. S., and Cheng, W. H. (2002). Study on the Mechanism of CO Formation in Reverse Water Gas Shift Reaction over Cu/SiO_2 Catalyst By Pulse Reaction, TPD And TPR. *Catalysis Letters*, 83, 121–126.
- Chen, C. S., Cheng, W. H., and Lin, S. S. (2004). Study of Iron-Promoted Cu/SiO_2 Catalyst on High Temperature Reverse Water Gas Shift Reaction. *Applied Catalysis A: General*, 257, 97–106.
- Chen, C., Cheng, W., and Lin, S. (2003). Study of Reverse Water Gas Shift Reaction by TPD, TPR and CO_2 Hydrogenation over Potassium-Promoted Cu/SiO_2 Catalyst. *Applied Catalysis A: General*, 238, 55–67.
- Chen, C.-S., Cheng, W.-H., and Lin, S.-S. (2000). Mechanism of CO Formation in Reverse Water – Gas Shift Reaction over $\text{Cu}/\text{Al}_2\text{O}_3$ Catalyst. *Catalysis Letters*, 68, 45–48.
- Chen, J. G. (1996). Carbide And Nitride Overlayers on Early Transition Metal Surfaces: Preparation, Characterization, and Reactivities. *Chemical Reviews*, 96(4), 1477–1498.
- Chen, L., Li, J., and Ge, M. (2011). The Poisoning Effect of Alkali Metals Doping over Nano $\text{V}_2\text{O}_5\text{-WO}_3/\text{TiO}_2$ Catalysts On Selective Catalytic Reduction Of NO_x by NH_3 . *Chemical Engineering Journal*, 170(2-3), 531–537.
- Chen, W. H., Cheng, T. C., Hung, C. I., and Lin, B. J. (2012). Chemical Reactions and Kinetics of A Low-Temperature Water Gas Shift Reaction Heated By Microwaves. *International Journal of Hydrogen Energy*, 37 (1), 276–289.

- Chen, Y. (2011). Facile Synthesis and Thermal Stability of Nanocrystalline Molybdenum Carbide. *Materials Sciences And Applications*, 2, 1313–1316.
- Chiang, S. W., Chang, C. C., Shie, J. L., Chang, C. Y., Ji, D. R., and Tseng, J. Y. (2012). Synthesis of Alcohols and Alkanes over Potassium and Vanadium Promoted Molybdenum Carbides. *Journal of the Taiwan Institute of Chemical Engineers*, 43(6), 918–925.
- Choi, J.-S., Bugli, G., and Djéga-Mariadassou, G. (2000). Influence of the Degree of Carburization on the Density of Sites And Hydrogenating Activity Of Molybdenum Carbides. *Journal of Catalysis*, 193 (2), 238–247.
- Choudhary, V. R. and Karkamkar, A. J. (2003). Temperature-Programmed Desorption of Water And Ammonia on Sulphated Zirconia Catalysts For Measuring Their Strong Acidity and Acidity Distribution. *Journal of Chemical Sciences*, 115 (4), 281–286.
- Church, R.H. (1993). Dielectric Properties of Low Loss Minerals. USBOM Report of Investigations, No. 9194.
- Conner, W. C., and Falconer, J. L. (1995). Spillover in Heterogeneous Catalysis. *Chemical Reviews*, 95(3), 759–788.
- Covington, L., Munirathinam, K., Islam, A. W., and Roberts, K. L. (2012). Synthesis and Characterization of Nanostructured Molybdenum and Tungsten Carbide Materials, and Study Of Diffusion Model. *Polish Journal of Chemical Technology*, 14, 28–34.
- Curtin, D., Selles, F., Wang, H., Biederbeck, V. O., and Campbell, C. A. (1998). Carbon Dioxide Emissions and Transformation of Soil Carbon And Nitrogen During Wheat Straw Decomposition. *Soil Science Society of America Journal*, 62, 1035–1041.
- Dąbrowski, A., Podkościelny, P., Hubicki, Z., and Barczak, M. (2005). Adsorption of Phenolic Compounds by Activated Carbon—A Critical Review. *Chemosphere*, 58(8), 1049–1070.
- Dasril, R.S.D. (2007). *Preparation and Characterization of Tungsten Carbide from Carbon of Palm Kernel Shell*. Master thesis, Universiti Teknologi Malaysia, Johor Bahru.
- Dastgheib, S. A., Karanfil, T., and Cheng, W. (2004). Tailoring Activated Carbons for Enhanced Removal of Natural Organic Matter from Natural Waters. *Carbon*, 42, 547–557.

- Davtyan, D., Manukyan, K., Mnatsakanyan, R., and Kharatyan, S. (2010). Reduction of MoO_3 by Zn: Reducer Migration Phenomena. *International Journal Of Refractory Metals And Hard Materials*, 28, 601–604.
- Daza, Y. A., Kent, R. A., Yung, M. M., and Kuhn, J. N. (2014). Carbon Dioxide Conversion by Reverse Water Gas Shift Chemical Looping on Perovskite-Type Oxides. *Industrial and Engineering Chemistry Research*, 53, 5828–5837
- De Falco, M., Iaquaniello, G., and Centi, G. (2013). *CO₂: A Valuable Source of Carbon*. London, UK: Springer
- De, M., and Kunzru, D. (2005). Effect of Calcium and Potassium on $\text{V}_2\text{O}_5/\text{ZrO}_2$ Catalyst for Oxidative Dehydrogenation of Propane: A Comparative Study. *Catalysis Letters*, 102(3-4), 237–246.
- Debecker, D. P., Stoyanova, M., Rodemerck, U., and Gaigneaux, E. M. (2011). Preparation of $\text{MoO}_3/\text{SiO}_2\text{-Al}_2\text{O}_3$ Metathesis Catalysts via Wet Impregnation with Different Mo Precursors. *Journal of Molecular Catalysis A: Chemical*, 340, 65–76.
- Demirbas, A., and Arin, G. (2002). An Overview of Biomass Pyrolysis. *Energy Sources*, 24(5), 471–482.
- Díaz Barriga Arceo, L., Orozco, E., Mendoza-León, H., Palacios González, E., Leyte Guerrero, F., and Garibay Febles, V. (2007). Nanostructures Obtained From A Mechanically Alloyed and Heat Treated Molybdenum Carbide. *Journal of Alloys and Compounds*, 434-435, 799–802.
- Dondur, V., Rakić, V., Damjanović, L., and Auroux, A. (2005). Comparative Study of the Active Sites In Zeolites by Different Probe Molecules. *Journal of the Serbian Chemical Society*, 70 (3), 457–474.
- Dorner, R. W., Hardy, D. R., Williams, F. W., and Willauer, H. D. (2010a). Heterogeneous Catalytic CO_2 Conversion to Value-Added Hydrocarbons. *Energy and Environmental Science*, 3, 884.
- Dorner, R. W., Hardy, D. R., Williams, F. W., and Willauer, H. D. (2010b). K And Mn Doped Iron-Based CO_2 Hydrogenation Catalysts: Detection Of KAlH_4 As Part of the Catalyst's Active Phase. *Applied Catalysis A: General*, 373, 112–121.

- Dry, M. E., Shingles, T., Boshoff, L. J., and Oosthuizen, G. J. (1969). Heats of Chemisorption on Promoted Iron Surfaces And The Role Of Alkali In Fischer-Tropsch Synthesis. *Journal of Catalysis*, 15 (2), 190–199.
- Ebadzadeh, T., and Marzban-Rad, E. (2009). Microwave Hybrid Synthesis of Silicon Carbide Nanopowders. *Materials Characterization*, 60 (1), 69–72.
- Enthaler, S., Von Langermann, J., and Schmidt, T. (2010). Carbon Dioxide and Formic Acid—the Couple for Environmental-Friendly Hydrogen Storage? *Energy and Environmental Science*, 3, 1207.
- Esler, M. B., Griffith, D. W., Wilson, S. R., and Steele, L. P. (2000). Precision Trace Gas Analysis by FT-IR Spectroscopy. 1. Simultaneous Analysis of CO₂, CH₄, N₂O, and CO in Air. *Analytical Chemistry*, 72(1), 206–215.
- Essaki, K., Rees, E. J., and Burstein, G. T. (2010). Synthesis of Nanoparticulate Tungsten Carbide under Microwave Irradiation. *Journal of the American Ceramic Society*, 93 (3), 692–695.
- Fang, K., Li, D., Lin, M., Xiang, M., Wei, W., and Sun, Y. (2009). A Short Review of Heterogeneous Catalytic Process for Mixed Alcohols Synthesis via Syngas. *Catalysis Today*, 147 (2), 133–138.
- Faye, J., Capron, M., Takahashi, A., Paul, S., Katryniok, B., Fujitani, T., and Dumeignil, F. (2014). Effect of Oxomolybdate Species Dispersion on Direct Methanol Oxidation to Dimethoxymethane over MoO_x/TiO₂ Catalysts. *Energy Science and Engineering*, 1, 1–11.
- Ferri, D., Burgi, T., and Baiker, A. (2002). Probing Boundary Sites on A Pt/Al₂O₃ Model Catalyst By CO₂ Hydrogenation and In Situ ATR-IR Spectroscopy of Catalytic Solid-Liquid Interfaces. *Physical Chemistry Chemical Physics*, 4(12), 2667–2672.
- Fidalgo, B., and Menéndez, J. A. (2012). Study of Energy Consumption In A Laboratory Pilot Plant for the Microwave-Assisted CO₂ Reforming Of CH₄. *Fuel Processing Technology*, 95, 55–61.
- Fidalgo, B., Domínguez, A., Pis, J. J., and Menéndez, J. A. (2008). Microwave-Assisted Dry Reforming of Methane. *International Journal of Hydrogen Energy*, 33, 4337–4344.

- Flaherty, D. W., Berglund, S. P., and Mullins, C. B. (2010). Selective Decomposition of Formic Acid on Molybdenum Carbide: A New Reaction Pathway. *Journal of Catalysis*, 269 (1), 33–43.
- Foo, K. Y., and Hameed, B. H. (2012). Preparation, Characterization and Evaluation of Adsorptive Properties of Orange Peel Based Activated Carbon via Microwave Induced K_2CO_3 Activation. *Bioresource Technology*, 104, 679–686.
- Fukui, K., Kanayama, K., Katoh, M., Yamamoto, T., and Yoshida, H. (2009). Synthesis of Indium Tin Oxide Powder By Solid-Phase Reaction With Microwave Heating. *Advanced Powder Technology*, 20 (5), 488–492.
- Furimsky, E. (2003). Metal Carbides and Nitrides as Potential Catalysts for Hydroprocessing. *Applied Catalysis A: General*, 240 (1-2), 1–28.
- Galadima, A., Wells, R. P. K., and Anderson, J. A. (2012). N-Alkane Hydroconversion Over Carbided Molybdena Supported On Sulfated Zirconia. *Applied Petrochemical Research*, 1 (1), 35–43.
- Galambos, M., Fábrián, G., Simon, F., Ćirić, L., Forró, L., Korecz, Rockenbauer, A., Koltai, J., Zólyomi, Rusznyák, A., Kürti, J., Nemes, N.M., Dóra, B., Peterlik, H., Pfeiffer, R., Kuzmany, H., and Pichler, T. (2009). Identifying The Electron Spin Resonance of Conduction Electrons In Alkali Doped SWNCTs. *Physica Status Solidi (B) Basic Research*, 246 (11), 2760–2763.
- Galema, S. A. (1997). Microwave Chemistry. *Chemical Society Reviews*, 26 (3), 233–238.
- Galvan, D., Orives, J. R., Coppo, R. L., Silva, E. T., Angilelli, K. G., and Borsato, D. (2013). Determination of the Kinetics and Thermodynamics Parameters of Biodiesel Oxidation Reaction Obtained From An Optimized Mixture of Vegetable Oil and Animal Fat. *Energy and Fuels*, 27 (11), 6866–6871.
- Gao, J., Wang, Y., Ping, Y., Hu, D., Xu, G., Gu, F., and Su, F. (2012). A Thermodynamic Analysis of Methanation Reactions of Carbon Oxides for the Production of Synthetic Natural Gas. *RSC Advances*, 2, 2358–2368
- Gao, L., and Seegopaul, P. (2001). *US Patent No. 09/412, 1725*. Retrieved on October 10, 2016, from <https://www.google.ch/patents/US6207609>
- Gao, Q., Zhang, C., Xie, S., Hua, W., Zhang, Y., Ren, N., Xu, H., and Tang, Y. (2009). Synthesis Of Nanoporous Molybdenum Carbide Nanowires Based On

- Organic - Inorganic Hybrid Nanocomposites With Sub-Nanometer Periodic Structures. *Chemistry Of Materials*, 21, 5560–5562.
- Gattrell, M., Gupta, N., and Co, A. (2006). A Review of the Aqueous Electrochemical Reduction of CO₂ to Hydrocarbons at Copper. *Journal of Electroanalytical Chemistry*, 594 (1), 1–19.
- Gavrilyuk, A. I., and Afanasiev, M. M. (2009). ESR Study of Photoinjection of Hydrogen in Nanostructured MoO₃ Thin Films. *Solar Energy Materials And Solar Cells*, 93, 280–288.
- Gentleman, A. S., Addicoat, M. A., and Metha, G. F. (2011). A Density Functional Theory Investigation of The Bimetallic Clusters Nb₂Rh And NbRh₂ and The Complexes They Form With CO. *Australian Journal Of Chemistry*, 64, 1554–1559.
- Glasnov, T. N., and Kappe, C. O. (2007). Microwave-Assisted Synthesis under Continuous-Flow Conditions. *Macromolecular Rapid Communications*, 28, 395–410.
- Goguet, A., Meunier, F. C., Tibiletti, D., Breen, J. P., and Burch, R. (2004). Spectrokinetic Investigation of Reverse Water-Gas-Shift Reaction Intermediates over a Pt/CeO₂ Catalyst. *Journal of Physical Chemistry B*, 108, 20240–20246.
- Graves, C., Ebbesen, S. D., Mogensen, M., and Lackner, K. S. (2011). Sustainable Hydrocarbon Fuels by Recycling CO₂ And H₂O With Renewable or Nuclear Energy. *Renewable and Sustainable Energy Reviews*, 15 (1), 1–23.
- Griessacher, T., Antrekowitsch, J., and Steinlechner, S. (2012). Charcoal from Agricultural Residues as Alternative Reducing Agent in Metal Recycling. *Biomass and Bioenergy*, 39, 139–146.
- Guil-López, R., Nieto, E., Botas, J. A., and Fierro, J. L. G. (2012). On The Genesis of Molybdenum Carbide Phases During Reduction-Carburization Reactions. *Journal of Solid State Chemistry*, 190, 285–295.
- Guo, R., Wang, Q., Pan, W., Zhen, W., Chen, Q., Ding, H., Yang, N., and Lu, C. (2014). The Poisoning Effect of Na and K on Mn/TiO₂ Catalyst for Selective Catalytic Reduction of NO with NH₃: A Comparative Study. *Applied Surface Science*, 317, 111–116.

- Guo, Z., Xiong, J., Yang, M., Song, X., and Jiang, C. (2008). Effect of Mo₂C on the Microstructure and Properties of WC-TiC-Ni Cemented Carbide. *International Journal of Refractory Metals And Hard Materials*, 26, 601–605.
- Haimour, N. M., and Emeish, S. (2006). Utilization of Date Stones for Production of Activated Carbon Using Phosphoric Acid. *Waste Management*, 26(6), 651–660.
- Hameed, B. H., Din, A. T. M., and Ahmad, A. L. (2007). Adsorption of Methylene Blue onto Bamboo-Based Activated Carbon: Kinetics And Equilibrium Studies. *Journal of Hazardous Materials*, 141(3), 819–25.
- Han, J., Duan, J., Chen, P., Lou, H., Zheng, X., and Hong, H. (2011). Nanostructured Molybdenum Carbides Supported on Carbon Nanotubes As Efficient Catalysts For One-Step Hydrodeoxygenation and Isomerization of Vegetable Oils. *Green Chemistry*, 13, 2561.
- Han, J., Duan, J., Chen, P., Lou, H., Zheng, X., and Hong, H. (2012). Carbon-Supported Molybdenum Carbide Catalysts for the Conversion of Vegetable Oils. *Chemsuschem*, 5 (4), 727–733.
- Hanapi, S. Z., Masrom, N. I., and Yacob, A. R. (2010). Tungsten Carbide Synthesis by Microwave-Induced Alloying Using Phosphoric Acid Activated Palm Kernel Shell Carbon. *Journal of Materials Science and Engineering*, 4 (12), 68–73.
- Haque, K. E. (1999). Microwave Energy for Mineral Treatment Processes—A Brief Review. *International Journal of Mineral Processing*, 57 (1), 1–24.
- Haque, M. M., Tejero, J., Bayachou, M., Wang, Z. Q., Fadlalla, M., and Stuehr, D. J. (2013). Thermodynamic Characterization Of Five Key Kinetic Parameters That Define Neuronal Nitric Oxide Synthase Catalysis. *FEBS Journal*, 280, 4439–4453.
- Hesas, R. H., Arami-Niya, A., Wan Daud, W. M. A., and Sahu, J. N. (2013). Preparation and Characterization of Activated Carbon from Apple Waste by Microwave-Assisted Phosphoric Acid Activation: Application in Methylene Blue Adsorption. *Bioresources*, 8, 2950–2966.
- Hino, S., Ichikawa, T., and Kojima, Y. (2010). Thermodynamic Properties of Metal Amides Determined by Ammonia Pressure-Composition Isotherms. *Journal of Chemical Thermodynamics*, 42, 140–143.

- Hirose, T., Ozawa, Y., and Nagai, M. (2011). Preparation of A Nickel Molybdenum Carbide Catalyst and Its Activity in The Dry Reforming Of Methane. *Chinese Journal of Catalysis*, 32(5), 771–776.
- Hoffmann, F. M., Yang, Y., Paul, J., White, M. G., and Hrbek, J. (2010). Hydrogenation of Carbon Dioxide by Water: Alkali-Promoted Synthesis Of Formate. *Journal of Physical Chemistry Letters*, 1, 2130–2134.
- Horikoshi, S., and Serpone, N. (2014). Role of Microwaves in Heterogeneous Catalytic Systems. *Catalysis Science and Technology*, 4, 1197–1210.
- Hu, F., Cui, G., Wei, Z., and Shen, P.K. (2008). Improved Kinetics of Ethanol Oxidation on Pd Catalysts Supported on Tungsten Carbide/Carbon Nanotubes. *Electrochemistry Communications*, 10, 1303–1306
- Hu, H., Zhao, Z., Zhou, Q., Gogotsi, Y., and Qiu, J. (2012). The Role of Microwave Absorption on Formation Of Graphene From Graphite Oxide. *Carbon*, 50(9), 3267–3273.
- Hu, Z., and Srinivasan, M. P. (2001). Mesoporous High-Surface-Area Activated Carbon. *Microporous And Mesoporous Materials*, 43, 267–275.
- Huang, C.-C., Li, H.-S., and Chen, C.-H. (2008). Effect of Surface Acidic Oxides of Activated Carbon on Adsorption Of Ammonia. *Journal of Hazardous Materials*, 159 (2-3), 523–7.
- Hyeon, T., Fang, M., and Suslick, K. S. (1996). Nanostructured Molybdenum Carbide: Sonochemical Synthesis and Catalytic Properties. *Journal of the American Chemical Society*, 118(18), 5492–5493.
- Impert, O., Katafias, A., Fenska, J., and Kita, P. (2012). Kinetics and Mechanism of Electron Transfer Processes in A Hydrogen Peroxide-Trispyridylruthenate(II) System. *Transition Metal Chemistry*, 37, 7–16.
- Jacob, J., Chia, L. H. L., and Boey, F. Y. C. (1995). Thermal and Non-Thermal Interaction of Microwave Radiation with Materials. *Journal of Materials Science*, 30, 5321–5327.
- Jacobs, G., Williams, L., Graham, U., Thomas, G.A., Sparks, D.E., and Davis, B.H. (2003). Low Temperature Water-gas Shift: In Situ DRIFTS – Reaction Study of Ceria Surface Area on the Evolution of Formates on Pt/CeO₂ Fuel Processing Catalysts for Fuel Cell Applications. *Applied Catalysis A: General*, 252, 110–118

- Jaroniec, M., Gadkaree, K. P., and Choma, J. (1996). Relation Between Adsorption Potential Distribution and Pore Volume Distribution for Microporous Carbons. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 118(3), 203–210.
- Ji, Y., Li, T., Zhu, L., Wang, X., and Lin, Q. (2007). Preparation of Activated Carbons by Microwave Heating KOH Activation. *Applied Surface Science*, 254, 506–512.
- Jia, L., Gao, J., Fang, W., and Li, Q. (2009). Carbon Dioxide Hydrogenation to Methanol over the Pre-Reduced $\text{LaCr}_{0.5}\text{Cu}_{0.5}\text{O}_3$ Catalyst. *Catalysis Communications*, 10 (15), 2000–2003.
- Jin, Y., Liu, Y., Wang, Y., and Ye, J. (2010). Synthesis of (Ti, W, Mo, V) (C, N) Nanocomposite Powder from Novel Precursors. *International Journal of Refractory Metals And Hard Materials*, 28 (4), 541–543.
- Jones, D. A., Lelyveld, T. P., Mavrofidis, S. D., Kingman, S. W., and Miles, N. J. (2002). Microwave Heating Applications In Environmental Engineering—A Review. *Resources, Conservation And Recycling*, 34, 75–90.
- Kaiser, P., Unde, R. B., Kern, C., and Jess, A. (2013). Production of Liquid Hydrocarbons with CO_2 as Carbon Source Based On Reverse Water-Gas Shift and Fischer-Tropsch Synthesis. *Chemie Ingenieur Technik*, 85 (4), 489–499.
- Kalderis, D., Bethanis, S., Paraskeva, P., and Diamadopoulos, E. (2008). Production of Activated Carbon from Bagasse And Rice Husk By A Single-Stage Chemical Activation Method At Low Retention Times. *Bioresource Technology*, 99, 6809–6816.
- Kang, Y. H., Shiue, A., Hu, S. C., Huang, C. Y., and Chen, H. T. (2010). Using Phosphoric Acid-Impregnated Activated Carbon to Improve the Efficiency of Chemical Filters for The Removal of Airborne Molecular Contaminants (AMCs) In The Make-Up Air Unit (MAU) Of A Cleanroom. *Building and Environment*, 45(4), 929–935.
- Kaur, N., and Ali, A. (2015). Biodiesel Production via Ethanolysis of Jatropha Oil Using Molybdenum Impregnated Calcium Oxide As Solid Catalyst. *RSC Advance*, 5 (18), 13285–13295.

- Kerry Yu, K. M., and Tsang, S. C. (2011). A Study of Methyl Formate Production from Carbon Dioxide Hydrogenation in Methanol over A Copper Zinc Oxide Catalyst. *Catalysis Letters*, 141, 259–265.
- Kharaji, A G., Takassi, M. A., and Shariati, A. (2012). Activity And Stability Of Fe-V₂O₅/ γ -Al₂O₃ Nanocatalyst In The Reverse Water Gas Shift (RWGS) Reaction, *International Conference on Environmental Science and Technology*, 10–12 March 2012, Chennai, India, 118–123.
- Kharaji, A. G., Shariati, A., and Takassi, M. A. (2013). A Novel γ -Alumina Supported Fe-Mo Bimetallic Catalyst for Reverse Water Gas Shift Reaction. *Chinese Journal of Chemical Engineering*, 21(9), 1007–1014.
- Kharissova, O. V., Kharisov, B. I., and Valdés, J. J. R. (2010). Review: The Use of Microwave Irradiation in the Processing of Glasses and Their Composites. *Industrial and Engineering Chemistry Research*, 49, 1457–1466.
- Kim, D. H., Park, J. L., Park, E. J., Kim, Y. D., and Uhm, S. (2014). Dopant Effect of Barium Zirconate-Based Perovskite-Type Catalysts for the Intermediate-Temperature Reverse Water Gas Shift Reaction. *ACS Catalysis*, 4, 3117–3122.
- Kim, K., Hong, K., Kim, S., and Lee, J. L. (2012). Doping Mechanism And Electronic Structure of Alkali Metal Doped Tris (8-Hydroxyquinoline) Aluminum. *Journal of Physical Chemistry C*, 116, 9158–9165.
- Kim, S. S., Park, K. H., and Hong, S. C. (2013). A Study of the Selectivity Of The Reverse Water-Gas-Shift Reaction Over Pt/TiO₂ Catalysts. *Fuel Processing Technology*, 108, 47–54.
- Kitchen, H. J., Vallance, S. R., Kennedy, J. L., Tapia-Ruiz, N., Carassiti, L., Harrison, A., Whittaker, A.G., Drysdale, T.D., Kingman, S.W., and Gregory, D. H. (2014). Modern Microwave Methods in Solid-State Inorganic Materials Chemistry: From Fundamentals to Manufacturing. *Chemical Reviews*, 114, 1170–1206.
- Kitchin, J. R., Nørskov, J. K., Barteau, M. A., and Chen, J. G. (2005). Trends in The Chemical Properties of Early Transition Metal Carbide Surfaces: A Density Functional Study. *Catalysis Today*, 105, 66–73.
- Knozinger, H., Ertl, G., and Weitkamp, J. (1999). *Preparation of Solid Catalysts*. London, UK: Willey-VCH.

- Kojima, R., and Aika, K. (2001). Molybdenum Nitride and Carbide Catalysts for Ammonia Synthesis. *Applied Catalysis A: General*, 219(1-2), 141–147.
- Koós, Á., Barthos, R., and Solymosi, F. (2008). Reforming of Methanol on A K-Promoted Mo₂C/Norit Catalyst. *Journal of Physical Chemistry C*, 112, 2607–2612.
- Kotarba, A., Adamski, G., Piskorz, W., Sojka, Z., Sayag, C., and Djéga-Mariadassou, G. (2004). Modification of Electronic Properties of Mo₂C Catalyst by Potassium Doping: Impact on the Reactivity In Hydrodenitrogenation Reaction Of Indole. *The Journal of Physical Chemistry B*, 108(001), 2885–2892.
- Kowalik, P., Próchniak, W., and Borowiecki, T. (2011). The Effect of Alkali Metals Doping on Properties of Cu/ZnO/Al₂O₃ Catalyst for Water Gas Shift. *Catalysis Today*, 176, 144–148.
- Kugler, E. L., Clark, C. H., Wright, J. H., Dadyburjor, D. B., Hanson, J. C., Song, Z., Cai, T., and Hrbek, J. (2006). Preparation, Interconversion and Characterization of Nanometer-Sized Molybdenum Carbide Catalysts. *Topics in Catalysis*, 39, 257–262.
- Kuśmierz, M. (2008). Kinetic Study on Carbon Dioxide Hydrogenation over Ru/ γ -Al₂O₃ Catalysts. *Catalysis Today*, 137 (2–4), 429–432.
- Lapuerta, M., Hernández, J. J., and Rodríguez, J. (2004). Kinetics of Devolatilisation of Forestry Wastes from Thermogravimetric Analysis. *Biomass and Bioenergy*, 27 (4), 385–391.
- Lee, J. (1987). Molybdenum Carbide Catalysts I: Synthesis of Unsupported Powders. *Journal of Catalysis*, 106(1), 125–133.
- Lee, J. S., Locatelli, S., Oyama, S. T., and Boudart, M. (1990). Molybdenum Carbide Catalysts 3: Turnover Rates For The Hydrogenolysis Of N-Butane. *Journal of Catalysis*, 125 (1), 157–170.
- Lee, J., Kim, S., and Kim, Y. (1995). Electronic And Geometric Effects of Alkali Promoters in CO Hydrogenation Over K/Mo₂C Catalysts. *Topics in Catalysis*, 2 (1-4), 127–140.
- Lee, J.-S., Kim, J.-E., and Kang, M.-S. (2011). Hydrogen Production from Steam Reforming over SnO₂-K₂O/Zeolite Y Catalyst. *Bulletin of the Korean Chemical Society*, 32 (6), 1912–1920.

- Leitenburg, C. D., Trovarelli, A., and Kač, J. (1997). A Temperature-Programmed and Transient Kinetic Study Of CO₂ Activation And Methanation over CeO₂ Supported Noble Metals. *Journal of Catalysis*, 166, 98–107.
- Lente, G., Fábrián, I., and Poë, A. J. (2005). A Common Misconception about The Eyring Equation. *New Journal of Chemistry*, 29, 759–760.
- Li, G., Hou, H., and Lin, R. (2011). Rapid Synthesis of Mordenite Crystals by Microwave Heating. *Solid State Sciences*, 13(3), 662–664.
- Li, J.-M., Liu, J., Ren, L.-W., Liu, Q.-L., Zhao, Z., Wei, Y.-C., Duan, A.-J., and Jiang, G.-Y. (2014). Selective Oxidation of Ethane to Aldehydes over Potassium-Promoted SBA-15-Supported Molybdenum Oxide Catalysts. *Acta Physico-Chimica Sinica*, 30(9), 1736–1744.
- Li, S., Sung Lee, J., Hyeon, T., and Suslick, K. S. (1999). Catalytic Hydrodenitrogenation of Indole over Molybdenum Nitride and Carbides with Different Structures. *Applied Catalysis A: General*, 184(1), 1–9.
- Liang, C., Ding, L., Wang, A., Zhiqiang, M., Qiu, J., and Zhang, T. (2009). Microwave-Assisted Preparation and Hydrazine Decomposition Properties of Nanostructured Tungsten Carbides on Carbon Nanotubes. *Industrial and Engineering Chemistry Research*, 48, 3244–3248.
- Liang, C., Ying, P., and Li, C. (2002). Nanostructured β -Mo₂C Prepared by Carbothermal Hydrogen Reduction on Ultrahigh Surface Area Carbon Material. *Chemistry Of Materials*, 14 (7), 3148–3151.
- Lietti, L., Forzatti, P., Ramis, G., Busca, G., and Bregani, F. (1993). Potassium Doping of Vanadia/Titania De-Noxing Catalysts: Surface Characterisation And Reactivity Study. *Applied Catalysis B: Environmental*, 3 (1), 13–35.
- Lillo-Ródenas, M. A., Cazorla-Amorós, D., and Linares-Solano, A. (2003). Understanding Chemical Reactions Between Carbons And NaOH and KOH: An Insight into the Chemical Activation Mechanism. *Carbon*, 41(2), 267–275.
- Lim, H.-W., Park, M.-J., Kang, S.-H., Chae, H.-J., Bae, J. W., and Jun, K.-W. (2009). Modeling of the Kinetics For Methanol Synthesis Using Cu/ZnO/Al₂O₃/ZrO₂ Catalyst: Influence of Carbon Dioxide During Hydrogenation. *Industrial and Engineering Chemistry Research*, 48(23), 10448–10455.

- Lin, S. S. Y., Thomson, W. J., Hagensen, T. J., and Ha, S. Y. (2007). Steam Reforming of Methanol Using Supported Mo₂C Catalysts. *Applied Catalysis A: General*, 318, 121–127.
- Linthorst, J. A. (2010). An Overview: Origins and Development of Green Chemistry. *Foundations of Chemistry*, 12, 55–68.
- Liu, C., Cundari, T. R., and Wilson, A. K. (2011). Reaction Mechanism of The Reverse Water Gas Shift Reaction Using First-Row Middle Transition Metal Catalysts L'M (M = Fe, Mn, C): A Computational Study. *Inorganic Chemistry*, 50, 8782–8789.
- Liu, C., Lin, M., Fang, K., Meng, Y., and Sun, Y. (2014). Preparation of Nanostructured Molybdenum Carbides for CO Hydrogenation. *RSC Advances*, 4, 20948–20954.
- Liu, C., Munjanja, L., Cundari, T. R., and Wilson, A. K. (2010). Theoretical Studies on the Catalysis of the Reverse Water-Gas Shift Reaction Using First-Row Transition Metal Beta-Diketiminato Complexes. *The Journal of Physical Chemistry. A*, 114, 6207–6216
- Liu, L., and Zachariah, M. R. (2013). Enhanced Performance of Alkali Metal Doped Fe₂O₃ and Fe₂O₃/Al₂O₃ Composites as Oxygen Carrier Material in Chemical Looping Combustion. *Energy and Fuels*, 27, 4977–4983
- Liu, P., and Rodriguez, A. (2003). Catalytic Properties of Mo Carbide, Nitride and Phosphide: A Theoretical Study. *Catalyst Letter*, 91, 247–252.
- Liu, P., and Rodriguez, J. A. (2006). Water-Gas-Shift Reaction on Molybdenum Carbide Surfaces: Essential Role of the Oxycarbide. *The Journal of Physical Chemistry B*, 110(39), 19418–19425.
- Liu, Q.-S., Zheng, T., Wang, P., and Guo, L. (2010). Preparation and Characterization of Activated Carbon From Bamboo By Microwave-Induced Phosphoric Acid Activation. *Industrial Crops and Products*, 31, 233–238.
- Liu, W., Soneda, Y., Kodama, M., Yamashita, J., and Hatori, H. (2008). Preparation and Characterization Of Molybdenum Carbides/Carbon Composites With High Specific Surface Area. *Materials Letters*, 62, 2766–2768.
- Liu, X., Ardakani, S. J., and Smith, K. J. (2011). The Effect of Mg and K Addition to A Mo₂C/HY Catalyst for the Hydrogenation and Ring Opening Of Naphthalene. *Catalysis Communications*, 12 (6), 454–458

- Lu, B., and Kawamoto, K. (2013). Preparation of Monodispersed NiO Particles in SBA-15, and Its Enhanced Selectivity for Reverse Water Gas Shift Reaction. *Journal of Environmental Chemical Engineering*, 1 (3), 300–309.
- Lu, J. L., Li, Z. H., Jiang, S. P., Shen, P. K., and Li, L. (2012). Nanostructured Tungsten Carbide/Carbon Composites Synthesized by a Microwave Heating Method as Supports of Platinum Catalysts for Methanol Oxidation. *Journal of Power Sources*, 202, 56–62.
- Lua, A. C., and Yang, T. (2004). Effect Of Activation Temperature On The Textural and Chemical Properties Of Potassium Hydroxide Activated Carbon Prepared From Pistachio-Nut Shell. *Journal of Colloid and Interface Science*, 274(2), 594–601.
- Lv, Y., Zhang, F., Dou, Y., Zhai, Y., Wang, J., Liu, H., Xia, Y., Tu, B., and Zhao, D. (2012). A Comprehensive Study on KOH Activation of Ordered Mesoporous Carbons and Their Supercapacitor Application. *Journal of Materials Chemistry*, 22, 93–99.
- Maestri, M., and Reuter, K. (2012). Molecular-Level Understanding of WGS and Reverse WGS Reactions on Rh Through Hierarchical Multiscale Approach. *Chemical Engineering Science*, 74, 296–299.
- Mangun, C. L., Benak, K. R., Economy, J., and Foster, K. L. (2001). Surface Chemistry, Pore Sizes And Adsorption Properties of Activated Carbon Fibers and Precursors Treated With Ammonia. *Carbon*, 39 (12), 1809–1820.
- Manukyan, K., Aydinyan, S., Aghajanyan, A., Grigoryan, Y., Niazyan, O., and Kharatyan, S. (2012). Reaction Pathway in The $\text{MoO}_3+\text{Mg}+\text{C}$ Reactive Mixtures. *International Journal of Refractory Metals and Hard Materials*, 31, 28–32.
- Marsh, H., and Rodríguez-Reinoso, F. (2006). *Activated Carbon*. Oxford, UK: Elsevier
- Matějová, L., Kočí, K., Reli, M., Čapek, L., Hospodková, A., Peikertová, P., Matěj, Z., Obalová, L., Wach, A., Kuśtrowski, P., and Kotarba, A. (2014). Preparation, Characterization and Photocatalytic Properties of Cerium Doped TiO_2 : on the Effect of Ce Loading on the Photocatalytic Reduction of Carbon Dioxide. *Applied Catalysis B: Environmental*, 152-153, 172–183.

- Matsuoka, K., Yamagishi, Y., Yamazaki, T., Setoyama, N., Tomita, A., and Kyotani, T. (2005). Extremely High Microporosity and Sharp Pore Size Distribution of a Large Surface Area Carbon Prepared in the Nanochannels of Zeolite Y. *Carbon*, 43, 876–879.
- Medford, A. J., Vojvodic, A., Studt, F., Abild-Pedersen, F., and Norskov, J. K. (2012). Elementary Steps of Syngas Reactions on Mo₂C (001): Adsorption Thermochemistry and Bond Dissociation. *Journal of Catalysis*, 290, 108–117.
- Mehta, V. P., and Van Der Eycken, E. V. (2011). Microwave-Assisted C–C Bond Forming Cross-Coupling Reactions: An Overview. *Chemical Society Reviews*, 40 (10), 4925–4936.
- Menéndez, J. A., Arenillas, A., Fidalgo, B., Fernández, Y., Zubizarreta, L., Calvo, E. G., and Bermúdez, J. M. (2010). Microwave Heating Processes Involving Carbon Materials. *Fuel Processing Technology*, 91(1), 1–8.
- Meredith, R. (1998). *Engineers' Handbook of Industrial Microwave Heating*. London, UK: The Institution of Electrical Engineers
- Mile, B., Rowlands, C. C., Sillman, P. D., and Yacob, A. R. (1995). The EPR Spectrum and Structure of The Mixed Alkali Metal Trimer Cluster Na₂Li Prepared Using A Rotating Cryostat. *Chemical Physics Letter*, 236, 603 – 608.
- Mohammed, M. A A, Salmiaton, A., Wan Azlina, W. A K. G., and Mohamad Amran, M. S. (2012). Gasification of Oil Palm Empty Fruit Bunches: A Characterization and Kinetic Study. *Bioresource Technology*, 110, 628–636.
- Molina-Sabio, M., Gonzalez, M. T., Rodriguez-Reinoso, F., and Sepúlveda-Escribano, A. (1996). Effect of Steam and Carbon Dioxide Activation in the Micropore Size Distribution Of Activated Carbon. *Carbon*, 34 (4), 505–509.
- Mondal, A., Agrawal, D., and Upadhyaya, A. (2010). Microwave Sintering of Refractory Metals / Alloys : W, Mo, Re, W-Cu, W-Ni-Cu And W-Ni-Fe Alloys. *Journal of Microwave Power and Electromagnetic Energy*, 44 (1), 28–44.
- Montanari, T., Castoldi, L., Lietti, L., and Busca, G. (2011). Basic Catalysis and Catalysis Assisted By Basicity: FT-IR And TPD Characterization of Potassium-Doped Alumina. *Applied Catalysis A: General*, 400(1-2), 61–69.

- Monteverdi, S., Mercy, M., Molina, S., Bettahar, M. M., Puricelli, S., Bégin, D., Maréché, F., and Furdin, F. (2002). Study of Unsupported and Active Carbon Supported Beta-Mo₂C Prepared From MoCl₅ Precursor. *Applied Catalysis A: General*, 230, 99–110.
- Moon, D. J. (2009). Low Temperature WGS Catalysts for Hydrogen Station and Fuel Processor Applications. *Catalysis Surveys from Asia*, 13(3), 191–204.
- Moon, D. J., and Ryu, J. W. (2004). Molybdenum Carbide Water--Gas Shift Catalyst for Fuel Cell-Powered Vehicles Applications. *Catalysis Letters*, 92(1), 17–24.
- Morales, B. Y. F., and Weckhuysen, B. M. (2006). Promotion Effects in Co-Based Fischer – Tropsch Catalysis. *Catalysis*, 19(I), 1–40.
- Mordenti, D., Brodzki, D., and Djéga-Mariadassou, G. (1998). New Synthesis of Mo₂C 14 nm in Average Size Supported on a High Specific Surface Area Carbon Material. *Journal of Solid State Chemistry*, 141 (1), 114–120.
- Moshtaghioun, B. M., Poyato, R., Cumbreira, F. L., De Bernardi-Martin, S., Monshi, A., Abbasi, M. H., Karimzadeh, F., and Dominguez-Rodriguez, A. (2012). Rapid Carbothermic Synthesis of Silicon Carbide Nano Powders by Using Microwave Heating. *Journal of the European Ceramic Society*, 32 (8), 1787–1794.
- Nagai, M., and Kurakami, T. (2005). Reverse Water Gas Shift Reaction over Molybdenum Carbide. *Journal of Chemical Engineering of Japan*, 38, 807–812.
- Nagai, M., and Matsuda, K. (2006). Low-Temperature Water–Gas Shift Reaction over Cobalt–Molybdenum Carbide Catalyst. *Journal of Catalysis*, 238 (2), 489–496.
- Nagai, M., Zahidul, A. M., Kunisaki, Y., and Aoki, Y. (2010). Water-Gas Shift Reactions on Potassium- and Zirconium-Promoted Cobalt Molybdenum Carbide Catalysts. *Applied Catalysis A: General*, 383 (1-2), 58–65.
- Nicula, R., Stir, M., Ishizaki, K., Català-Civera, J.-M., and Vaucher, S. (2009). Rapid Nanocrystallization of Soft-Magnetic Amorphous Alloys Using Microwave Induction Heating. *Scripta Materialia*, 60 (2), 120–123.
- Nikoo, M. K., and Amin, N. A. S. (2011). Thermodynamic Analysis of Carbon Dioxide Reforming Of Methane In View Of Solid Carbon Formation. *Fuel Processing Technology*, 92, 678–691.

- Niwa, M., and Katada, N. (2013). New Method For The Temperature- Programmed Desorption (TPD) Of Ammonia Experiment For Characterization Of Zeolite Acidity: A Review. *Chemical Record*, 13, 432–455.
- Oghbaei, M., and Mirzaee, O. (2010). Microwave Versus Conventional Sintering: A Review of Fundamentals, Advantages And Applications. *Journal of Alloys and Compounds*, 494, 175–189.
- Ogo, S., Kabe, R., Hayashi, H., Harada, R., and Fukuzumi, S. (2006). Mechanistic Investigation Of CO₂ Hydrogenation By Ru (II) and Ir(III) Aqua Complexes Under Acidic Conditions: Two Catalytic Systems Differing in the Nature of the Rate Determining Step. *Dalton Transactions*, 39, 4657–4663.
- Olah, G. A., Goeppert, A., and Prakash, G. K. S. (2009). Chemical Recycling Of Carbon Dioxide To Methanol And Dimethyl Ether: From Greenhouse Gas to Renewable, Environmentally Carbon Neutral Fuels And Synthetic Hydrocarbons. *Journal of Organic Chemistry*, 74, 487–498.
- Omae, I. (2012). Recent Developments in Carbon Dioxide Utilization for the Production of Organic Chemicals. *Coordination Chemistry Reviews*, 256 (13-14), 1384–1405.
- Onda, A., Ochi, T., and Yanagisawa, K. (2008). Selective Hydrolysis of Cellulose into Glucose over Solid Acid Catalysts. *Green Chemistry*, 10(10), 1033–1037.
- Osepchuk, J. M. (1984). A History of Microwave Heating Applications. *IEEE Transactions on Microwave Theory And Techniques*, 32(9), 1200–1224
- Oshikawa, K., Nagai, M., and Omi, S. (2001). Characterization of Molybdenum Carbides for Methane Reforming By TPR, XRD, and XPS. *Journal of Physical Chemistry B*, 105, 9124–9131.
- Oshima, K., Shinagawa, T., Nogami, Y., Manabe, R., Ogo, S., and Sekine, Y. (2014). Low Temperature Catalytic Reverse Water Gas Shift Reaction Assisted by an Electric Field. *Catalysis Today*, 232, 27–32.
- Ouerfelli, J., Srivastava, S. K., Bernède, J. C., and Belgacem, S. (2008). Effect of Microwaves on Synthesis of MoS₂ And WS₂. *Vacuum*, 83, 308–312.
- Oxley, J. D., Mdleleni, M. M., and Suslick, K. S. (2004). Hydrodehalogenation with Sonochemically Prepared Mo₂C and W₂C. *Catalysis Today*, 88, 139–151.

- Oyama, S. T. (1996). *Introduction to the Chemistry Of Transition Metal Carbides And Nitrides*. Dordrecht, Netherlands: Springer.
- Padmavathi, C., Upadhyaya, A., and Agrawal, D. (2011). Effect of Microwave and Conventional Heating on Sintering Behavior and Properties of Al-Mg-Si-Cu Alloy. *Materials Chemistry and Physics*, 130, 449–457
- Pakhare, D., and Spivey, J. (2014). A Review of Dry CO₂ Reforming of Methane over Noble Metal Catalysts. *Chemical Society Reviews*, 43, 7813–7837
- Pan, L. F., Li, Y. H., Yang, S., Liu, P. F., Yu, M. Q., and Yang, H. G. (2014). Molybdenum Carbide Stabilized on Graphene with High Electrocatalytic Activity for Hydrogen Evolution Reaction. *Chem. Commun.*, 50, 13135–13137.
- Pan, R., Wu, Y., Wang, Q., and Hong, Y. (2009). Preparation and Catalytic Properties of Platinum Dioxide Nanoparticles: A Comparison between Conventional Heating and Microwave-Assisted Method. *Chemical Engineering Journal*, 153(1–3), 206–210.
- Pang, M., Li, C., Ding, L., Zhang, J., Su, D., Li, W., and Liang, C. (2010). Microwave-Assisted Preparation of Mo₂C/CNTs Nanocomposites As Efficient Electrocatalyst Supports For Oxygen Reduction Reaction. *Industrial and Engineering Chemistry Research*, 49, 4169–4174.
- Pang, M., Liu, C., Xia, W., Muhler, M., and Liang, C. (2012). Activated Carbon Supported Molybdenum Carbides as Cheap and Highly Efficient Catalyst in The Selective Hydrogenation of Naphthalene to Tetralin. *Green Chemistry*, 14, 1272–1276.
- Park, J. R., Kwak, B. K., Park, D. S., Kim, T. Y., Yun, Y. S., and Yi, J. (2012). Effect of Acid Type in WO_x Clusters on the Esterification of Ethanol with Acetic Acid. *Korean Journal of Chemical Engineering*, 29(12), 1695–1699.
- Parlett, C. M. A., Wilson, K., Lee, A. F., Lee, A. F., and Wilson, K. (2013). Hierarchical Porous Materials: Catalytic Applications. *Chemical Society Reviews*, 42, 3876–3893.
- Parviz, D., Kazemeini, M., Rashidi, A. M., and Jafari Jozani, K. (2010). Synthesis And Characterization Of MoO₃ Nanostructures by Solution Combustion Method Employing Morphology and Size Control. *Journal of Nanoparticle Research*, 12, 1509–1521.

- Patel, A., and Brahmkhatri, V. (2013). Kinetic Study of Oleic Acid Esterification Over 12-Tungstophosphoric Acid Catalyst Anchored to Different Mesoporous Silica Supports. *Fuel Processing Technology*, 113, 141–149.
- Patel, M., and Subrahmanyam, J. (2008). Synthesis Of Nanocrystalline Molybdenum Carbide (Mo_2C) By Solution Route. *Materials Research Bulletin*, 43, 2036–2041.
- Patt, J., Moon, D. J., Phillips, C., and Thompson, L. (2000). Molybdenum Carbide Catalysts for Water--Gas Shift. *Catalysis Letters*, 65 (4), 193–195.
- Patterson, P. (2003). Carbon Monoxide Hydrogenation over Molybdenum and Tungsten Carbides. *Applied Catalysis A: General*, 251(2), 449–455.
- Pekridis, G., Kalimeri, K., Kaklidis, N., Vakouftsi, E., Iliopoulou, E. F., Athanasiou, C., and Marnellos, G. E. (2007). Study of the Reverse Water Gas Shift (RWGS) Reaction over Pt in A Solid Oxide Fuel Cell (SOFC) Operating Under Open and Closed-Circuit Conditions. *Catalysis Today*, 127, 337–346.
- Peng, Y., Li, J., Chen, L., Chen, J., Han, J., Zhang, H., and Han, W. (2012). Alkali Metal Poisoning Of A $\text{CeO}_2\text{-WO}_3$ Catalyst Used In The Selective Catalytic Reduction Of NO_x With NH_3 : An Experimental And Theoretical Study. *Environmental Science and Technology*, 46, 2864–2869.
- Peng, Y., Li, J., Huang, X., Li, X., Su, W., Sun, X., Wang., D., and Hao, J. (2014). Deactivation Mechanism of Potassium on the $\text{V}_2\text{O}_5/\text{CeO}_2$ Catalysts for SCR Reaction: Acidity, Reducibility and Adsorbed- NO_x . *Environmental Science and Technology*, 48 (8), 4515–4520.
- Pereira, J.J., Bari, M.A., Begum, R.A., Raja Zainal Abidin, R.D.Z., and Jaafar, A.H. (2012). The Role of CO_2 Emission in Energy Demand and Supply. *American Journal of Applied Sciences*, 9 (5), 641–646.
- Peters, M., Köhler, B., Kuckshinrichs, W., Leitner, W., Markewitz, P., and Müller, T. E. (2011). Chemical Technologies for Exploiting and Recycling Carbon Dioxide into The Value Chain. *Chemsuschem*, 4, 1216–1240.
- Pielaszek, J., Mierzwa, B., Medjahdi, G., Marêché, J. F., Puricelli, S., Celzard, A., and Furdin, G. (2005). Molybdenum Carbide Catalyst Formation From Precursors Deposited on Active Carbons: XRD Studies. *Applied Catalysis A: General*, 296, 232–237.

- Pierson, H.O. (1993). *Handbook of Carbon, Graphite, Diamonds and Fullerenes: Properties, Processing and Application*. New Jersey: Noyes Publication
- Pistonesi, C., Pronsato, M. E., Bugyi, L., and Juan, A. (2012). The Adsorption of CO on Potassium Doped Molybdenum Carbide Surface: An Ab-Initio Study. *Catalysis Today*, 181 (1), 102–107.
- Polshettiwar, V., and Varma, R. (2010). Fundamentals of Aqueous Microwave Chemistry. *Aqueous Microwave Assisted Chemistry*, (7), 1–9.
- Porosoff, M. D., Yang, X., Boscoboinik, J. A., and Chen, J. G. (2014). Molybdenum Carbide as Alternative Catalysts To Precious Metals For Highly Selective Reduction of CO₂ to CO. *Angewandte Chemie - International Edition*, 53, 6705–6709.
- Prahas, D., Kartika, Y., Indraswati, N., and Ismadji, S. (2008). Activated Carbon From Jackfruit Peel Waste By H₃PO₄ Chemical Activation: Pore Structure and Surface Chemistry Characterization. *Chemical Engineering Journal*, 140 (1–3), 32–42.
- Praliaud, H., Primet, M., and Martin, G. (1983). Physico-Chemical Properties of Potassium-Promoted Ni/SiO₂ Catalysts. *Applications Of Surface Science*, 17, 107–123.
- Preiss, H., Meyer, B., and Olschewski, C. (1998). Preparation of Molybdenum and Tungsten Carbides from Solution Derived Precursors. *Journal of Materials Science*, 33(3), 713–722.
- Pronsato, M. E., Pistonesi, C., Juan, A., Farkas, A P., Bugyi, L., and Solymosi, F. (2011). Density Functional Theory Study of Methyl Iodide Adsorption and Dissociation on Clean and K-Promoted B-Mo₂C Surfaces. *The Journal of Physical Chemistry C*, 115, 2798–2804.
- Putluru, S. S. R., Jensen, A. D., Riisager, A., and Fehrmann, R. (2012). Alkali Resistivity of Cu Based Selective Catalytic Reduction Catalysts: Potassium Chloride Aerosol Exposure and Activity Measurements. *Catalysis Communications*, 18, 41–46.
- Quadrelli, E. A., Centi, G., Duplan, J. L., and Perathoner, S. (2011). Carbon Dioxide Recycling: Emerging Large-Scale Technologies with Industrial Potential. *Chemsuschem*, 4, 1194–1215.
- Radovic, L.R. (2001). *Chemistry and Physics Of Carbon*. New York, USA: Marcel Dekker Inc.

- Rafatullah, M., Ahmad, T., Ghazali, A., Sulaiman, O., Danish, M., and Hashim, R. (2012). Oil Palm Biomass as a Precursor of Activated Carbons: A Review. *Critical Reviews In Environmental Science And Technology*, 43(11), 1117–1161.
- Razali, N. A. M., Lee, K. T., Bhatia, S., and Mohamed, A. R. (2012). Heterogeneous Catalysts for Production of Chemicals Using Carbon Dioxide as Raw Material: A Review. *Renewable and Sustainable Energy Reviews*, 16 (7), 4951–4964.
- Rebrov, E. V., Kuznetsov, S. A., De Croon, M. H. J. M., and Schouten, J. C. (2007). Study of the Water-Gas Shift Reaction on Mo₂C/Mo Catalytic Coatings for Application In Microstructured Fuel Processors. *Catalysis Today*, 125, 88–96.
- Riedel, T., Schaub, G., Jun, K., and Lee, K. (2001). Kinetics of CO₂ Hydrogenation on K-Promoted Fe Catalyst. *Industrial and Engineering Chemistry Research*, 40 (2), 1355–1363.
- Roberts, B. A., and Strauss, C. R. (2005). Toward Rapid, “Green”, Predictable Microwave-Assisted Synthesis. *Accounts Of Chemical Research*, 38 (8), 653–61.
- Rodríguez-Reinoso, F. (1998). The Role of Carbon Materials in Heterogeneous Catalysis. *Carbon*, 36(3), 159–175.
- Rong, H., Liu, Z., Wu, Q., Pan, D., and Zheng, J. (2010). Formaldehyde Removal by Rayon-Based Activated Carbon Fibers Modified by P-Aminobenzoic Acid. *Cellulose*, 17, 205–214.
- Ryu, Z., Zheng, J., Wang, M., and Zhang, B. (1999). Characterization of Pore Size Distributions on Carbonaceous Adsorbents By DFT. *Carbon*, 37, 1257–1264.
- Saghafi, M., Ataie, A., and Heshmati-Manesh, S. (2011). Effects of Mechanical Activation of MoO₃/C Powder Mixture in the Processing of Nano-Crystalline Molybdenum. *International Journal of Refractory Metals and Hard Materials*, 29, 419–423
- Saito, M., and Anderson, R. B. (1980). The Activity of Several Molybdenum Compounds for the Methanation of CO. *Journal of Catalysis*, 63 (2), 438–446.
- Salahudin, S., Abdullah, M., and Newaz, N. (2013). Emissions: Sources, Policies and Development in Malaysia. *International Journal of Education and Research*, 1(7), 1–12.

- Schaefer, M.D. (1999). *Microwave Tempering of Shrimp with Susceptors*. Master thesis, Virginia Polytechnic Institute and State University, Virginia.
- Schaidle, J. A., Schweitzer, N. M., Ajenifujah, O. T., and Thompson, L. T. (2012). On The Preparation of Molybdenum Carbide-Supported Metal Catalysts. *Journal of Catalysis*, 289, 210–217.
- Scheffe, J. R., and Steinfeld, A. (2012). Thermodynamic Analysis of Cerium-Based Oxides for Solar Thermochemical Fuel Production. *Energy and Fuels*, 26, 1928–1936.
- Schill, L., Putluru, S. S. R., Jacobsen, C. F., Hansen, C. H., Fehrmann, R., and Jensen, A. D. (2012). Ethanol-Selective Catalytic Reduction of NO by Ag/Al₂O₃ Catalysts: Activity and Deactivation by Alkali Salts. *Applied Catalysis B: Environmental*, 127, 323–329.
- Schneider, J., Jia, H., Muckerman, J. T., and Fujita, E. (2012). Thermodynamics and Kinetics of CO₂, CO, and H⁺ Binding to the Metal Centre of CO₂ Reduction Catalysts. *Chemical Society Reviews*, 41, 2036–2051
- Schweitzer, N. M., Schaidle, J. A., Ezekoye, O. K., Pan, X., Linic, S., and Thompson, L. T. (2011). High Activity Carbide Supported Catalysts for Water Gas Shift. *Journal of the American Chemical Society*, 133, 2378–2381.
- Shafeeyan, M. S., Daud, W. M. A. W., Houshmand, A., and Shamiri, A. (2010). A Review on Surface Modification of Activated Carbon for Carbon Dioxide Adsorption. *Journal of Analytical and Applied Pyrolysis*, 89 (2), 143–151.
- Shariati, Ahmad and Khariji, A. G. (2012). Selectivity and Performance of Ni-Mo/Al₂O₃ Catalyst for Methanol Production with Reverse Water Shift (RWGS) Reaction. *Journal of American Science*, 8 (3), 2012.
- Shou, H., and Davis, R. J. (2013). Multi-Product Steady-State Isotopic Transient Kinetic Analysis of CO Hydrogenation over Supported Molybdenum Carbide. *Journal of Catalysis*, 306, 91–99.
- Shouman, M. A., Fathy, N. A., Khedr, S. A., and Attia, A. A. (2013). Comparative Biosorption Studies of Hexavalent Chromium Ion onto Raw and Modified Palm Branches. *Advances in Physical Chemistry*, 2013, 1–9.
- Simon, F., Galambos, M., Quintavalle, D., Náfrádi, B., Forró, L., Koltai, J., Zólyomi, V., Kürti, J., Nemes, N.M., Rummeli, M.H., Kuzmany, H., and Pichler, T. (2008). Electron Spin Resonance in Alkali Doped SWCNTs. *Physica Status Solidi (B) Basic Research*, 245(10), 1975–1978.

- Song, C. (2006). Global Challenges and Strategies for Control, Conversion and Utilization of CO₂ for Sustainable Development Involving Energy, Catalysis, Adsorption and Chemical Processing. *Catalysis Today*, 115, 2–32.
- Spencer, M. S. (1995). On The Activation Energies of the Forward and Reverse Water-Gas Shift Reaction. *Catalysis Letters*, 32, 9–13.
- Sych, N. V., Trofymenko, S. I., Poddubnaya, O. I., Tsyba, M. M., Sapsay, V. I., Klymchuk, D. O., and Puziy, A. M. (2012). Porous Structure and Surface Chemistry of Phosphoric Acid Activated Carbon from Corncob. *Applied Surface Science*, 261, 75–82.
- Szymańska-Kolasa, A., Lewandowski, M., Sayag, C., and Djéga-Mariadassou, G. (2007). Comparison of Molybdenum Carbide And Tungsten Carbide For The Hydrodesulfurization Of Dibenzothiophene. *Catalysis Today*, 119(1–4), 7–12.
- Tan, I. A. W., Ahmad, A. L., and Hameed, B. H. (2008). Adsorption of Basic Dye On High-Surface-Area Activated Carbon Prepared From Coconut Husk: Equilibrium, Kinetic And Thermodynamic Studies. *Journal of Hazardous Materials*, 154, 337–346.
- Taratanov, N. A., Yurkov, G. Y., Fionov, A. S., Koksharov, Y. A., Popkov, O. V., and Kolesov, V. V. (2009). Creation and Physical Properties of the Molybdenum-Containing Polyethylene-Based Nanomaterials. *Journal of Communications Technology and Electronics*, 54, 937–946.
- Tham, Y. J., Latif, P. A., Abdullah, A. M., Shamala-Devi, A., and Taufiq-Yap, Y. H. (2011). Performances Of Toluene Removal By Activated Carbon Derived From Durian Shell. *Bioresource Technology*, 102(2), 724–728.
- Thostenson, E. T., and Chou, T.-W. (1999). Microwave Processing: Fundamentals And Applications. *Composites Part A: Applied Science and Manufacturing*, 30, 1055–1071.
- Tominaga, H., and Nagai, M. (2005). Density Functional Study of Carbon Dioxide Hydrogenation on Molybdenum Carbide and Metal. *Applied Catalysis A: General*, 282, 5–13.
- Tong, L., Li, X., Hua, R., Li, X., Zheng, H., Sun, J., Zhang, J., Lihong, C., and Chen, B. (2015). Comparative Study on Upconversion Luminescence and Temperature Sensing of α - and β -NaYF₄:Yb³⁺/Er³⁺ nano-/micro-Crystals

- Derived from A Microwave-Assisted Hydrothermal Route. *Journal of Luminescence*, 167, 386–390.
- Tsai, J. H., Chiang, H. M., Huang, G. Y., and Chiang, H. L. (2008). Adsorption Characteristics of Acetone, Chloroform and Acetonitrile on Sludge-Derived Adsorbent, Commercial Granular Activated Carbon and Activated Carbon Fibers. *Journal of Hazardous Materials*, 154, 1183–1191.
- Tsuchiya, K., Huang, J. Di, and Tominaga, K. I. (2013). Reverse Water-Gas Shift Reaction Catalyzed by Mononuclear Ru Complexes. *ACS Catalysis*, 3(Entry 4), 2865–2868.
- Tsuji, M., Miyao, T., and Naito, S. (2000). Remarkable Support Effect of ZrO₂ Upon the CO₂ Reforming Of CH₄ Over Supported Molybdenum Carbide Catalysts. *Science*, 69, 195–198.
- Upadhyaya, A., Tiwari, S. K., and Mishra, P. (2007). Microwave Sintering of W–Ni–Fe Alloy. *Scripta Materialia*, 56 (1), 5–8.
- Vaidhyathan, B., Balaji, K., and Rao, K. J. (1998). Microwave-Assisted Solid-State Synthesis of Oxide Ion Conducting Stabilized Bismuth Vanadate Phases. *Chemistry of Materials*, 10 (11), 3400–3404.
- Vallance, S. R., Kingman, S., and Gregory, D. H. (2007). Ultra-Rapid Processing Of Refractory Carbides; 20s Synthesis of Molybdenum Carbide, Mo₂C. *Chemical Communications (Cambridge, England)*, (1), 742–744.
- Vasenin, N. T., Anufrienko, V. F., Ismagilov, I. Z., Larina, T. V., Paukshtis, E. A., Matus, E. V., Tsikoza, L.T., Kerzhentsev, M.A., and Ismagilov, Z. R. (2005). Effect of Thermal Treatment on States of Molybdenum In Mo/H-ZSM-5 Catalyst For Methane Dehydroaromatization: ESR And UV-VIS Study. *Topics in Catalysis*, 32, 61–70.
- Villa, A., Campisi, S., Giordano, C., Otte, K., and Prati, L. (2012). Mo and W Carbide: Tunable Catalysts for Liquid Phase Conversion of Alcohols. *ACS Catalysis*, 2, 1377–1380.
- Vitale, G., Frauwallner, M. L., Scott, C. E., and Pereira-Almao, P. (2011). Preparation and Characterization of Low-Temperature Nano-Crystalline Cubic Molybdenum Carbides and Insights on Their Structures. *Applied Catalysis A: General*, 408(1-2), 178–186.

- Vo, D. V. N., and Adesina, A. A. (2011). Fischer-Tropsch Synthesis over Alumina-Supported Molybdenum Carbide Catalyst. *Applied Catalysis A: General*, 399(1-2), 221–232.
- Vo, D.V. N., and Adesina, A. A. (2012). A Potassium-Promoted Mo Carbide Catalyst System for Hydrocarbon Synthesis. *Catalysis Science and Technology*, 2, 2066–2076.
- Volpe, L. E. O. (1985). Compounds of Molybdenum Surface Area and Tungsten With High Specific. *Journal of Solid State Chemistry*, 59, 348–356.
- Wang, H. M., Wang, X. H., Zhang, M. H., Du, X. Y., Li, W., and Tao, K. Y. (2007). Synthesis of Bulk and Supported Molybdenum Carbide By A Single-Step Thermal Carburization Method. *Chemistry of Materials*, 19, 1801–1807.
- Wang, J., and Kaskel, S. (2012). KOH Activation of Carbon-Based Materials for Energy Storage. *Journal of Materials Chemistry*, 22, 23710–23725.
- Wang, J., Ji, S., Yang, J., Zhu, Q., and Li, S. (2005). MoC and MoC/AlO Catalysts for NO Direct Decomposition. *Catalysis Communications*, 6(6), 389–393.
- Wang, L., Liu, H., Liu, Y., Chen, Y., and Yang, S. (2013). Effect of Precipitants on Ni-CeO₂ Catalysts Prepared by a Co-Precipitation Method for the Reverse Water-Gas Shift Reaction. *Journal of Rare Earths*, 31 (10), 969–974.
- Wang, W., and Gong, J. (2011). Methanation of Carbon Dioxide: An Overview. *Frontiers of Chemical Engineering in China*, 5 (1), 2–10.
- Wang, W., Wang, S., Ma, X., and Gong, J. (2011). Recent Advances in Catalytic Hydrogenation of Carbon Dioxide. *Chemical Society Reviews*, 40, 3703–3727.
- Wienold, J., Jentoft, R. E., and Ressler, T. (2002). Structural Investigation of the Thermal Decomposition of Ammonium Heptamolybdate by In-Situ XAFS and XRD. *European Journal of Inorganic Chemistry*, 1058–1071.
- Willauer, H. D., Ananth, R., Olsen, M. T., Drab, D. M., Hardy, D. R., and Williams, F. W. (2013). Modeling and Kinetic Analysis of CO₂ Hydrogenation Using a Mn and K-Promoted Fe Catalyst in A Fixed-Bed Reactor. *Journal of CO₂ Utilization*, 3-4, 56–64.
- Wolden, C. A., Pickerell, A., Gawai, T., Parks, S., Hensley, J., and Way, J. D. (2011). Synthesis of B-Mo₂C Thin Films. *Applied Materials and Interfaces*, 3, 517–521.

- Woodruff, D.P. And King, D.A. (1993). *The Chemical Physics of Solid Surfaces, Coadsorption, Promoters and Poisons*. (6th ed.) Amsterdam, Netherlands: Elsevier
- Wu, Q., Christensen, J. M., Chiarello, G. L., Duchstein, L. D. L., Wagner, J. B., Temel, B., Grundwaldt. J.-D., and Jensen, A. D. (2013). Supported Molybdenum Carbide for Higher Alcohol Synthesis From Syngas. *Catalysis Today*, 215, 162–168.
- Xiang, M., Li, D., Zou, J., Li, W., Sun, Y., and She, X. (2010). XPS Study Of Potassium-Promoted Molybdenum Carbides for Mixed Alcohols Synthesis via CO Hydrogenation. *Journal of Natural Gas Chemistry*, 19(2), 151–155.
- Xiang, M., Wu, D., Zou, J., Li, D., Sun, Y., and She, X. (2011). Catalytic Performance of Fe Modified K/MO₂C Catalyst for CO Hydrogenation. *Journal of Natural Gas Chemistry*, 20 (5), 520–524.
- Xiao, T., Wang, H., Da, J., Coleman, K., and Green, M. (2002). Study of The Preparation and Catalytic Performance of Molybdenum Carbide Catalysts Prepared With CH/H Carburizing Mixture. *Journal of Catalysis*, 211, 183–191.
- Xiong, J., Liu, X., and Liang, L. (2015). Experimental Study on the Pore Structure Characteristics of the Upper Ordovician Wufeng Formation Shale in The Southwest Portion of The Sichuan Basin, China. *Journal of Natural Gas Science and Engineering*, 22, 530–539.
- Xu, W., Ramirez, P. J., Stacchiola, D., and Rodriguez, J. A. (2014). Synthesis of α -MoC_{1-x} and β -MoC_y Catalysts For CO₂ Hydrogenation By Thermal Carburization of Mo-Oxide in Hydrocarbon And Hydrogen Mixtures. *Catalysis Letters*, 144, 1418–1424.
- Yacob, A. R., Mustapha, N., Amat Mustajab, M. K. A., and Al Swaidan, H. M. (2010). Physical Activation of Saudi Arabia Date Palm Tree's Foliar, Frond and Thorn. *2010 International Conference on Mechanical, Industrial, and Manufacturing Technologies*. 17-19 September 2010, Chongqing, China, 551–557
- Yagmur, E., Ozmak, M., and Aktas, Z. (2008). A Novel Method for Production of Activated Carbon from Waste Tea by Chemical Activation with Microwave Energy. *Fuel*, 87, 3278–3285.

- Yamada, S., Takasu, A., and Kawamura, K. (2013). The Effect of Microwave Irradiation on the Kinetics and Activation Thermodynamics of Ring-Opening Polymerization of E-Caprolactone. *Journal of Polymer Science Part A: Polymer Chemistry*, 51 (17), 3732–3739.
- Yang, K., Peng, J., Srinivasakannan, C., Zhang, L., Xia, H., and Duan, X. (2010). Preparation of High Surface Area Activated Carbon from Coconut Shells Using Microwave Heating. *Bioresource Technology*, 101(15), 6163–6169.
- Yang, Z., Cai, P., Shi, L., Gu, Y., Chen, L., and Qian, Y. (2006). A Facile Preparation of Nanocrystalline Mo₂C from Graphite or Carbon Nanotubes. *Journal of Solid State Chemistry*, 179(1), 29–32.
- Yao, Z., and Shi, C. (2009). Development of a Catalytic Cycle in Molybdenum Carbide Catalyzed NO/CO Reaction. *Catalysis Letters*, 130 (1-2), 239–245.
- Yao, Z., Lai, Z., Zhang, X., Peng, F., Yu, H., and Wang, H. (2011) Structural Stability and Mutual Transformations of Molybdenum Carbide, Nitride and Phosphate. *Material Research Bulletin*, 46, 1938–1941.
- Zaman, S., and Smith, K. J. (2012). A Review of Molybdenum Catalysts for Synthesis Gas Conversion to Alcohols: Catalysts, Mechanisms and Kinetics. *Catalysis Reviews*, 54, 41–132.
- Zhang, C., Liu, F., Zhai, Y., Ariga, H., Yi, N., Liu, Y., Asakura, K., Flytzani-Stephanopoulos, M., and He, H. (2012). Alkali-Metal-Promoted Pt/TiO₂ Opens A More Efficient Pathway to Formaldehyde Oxidation At Ambient Temperatures. *Angewandte Chemie - International Edition*, 51, 9628–9632.
- Zhang, H., Bhat, V. V., Feng, P. X., Contescu, C. I., and Gallego, N. C. (2012). Effect of Potassium-Doping on The Microstructure Development In Polyfurfuryl Alcohol - Derived Activated Carbon. *Carbon*, 50 (14), 5278–5285.
- Zhang, X., Dai, B., Zhu, A., Gong, W., and Liu, C. (2002). The Simultaneous Activation of Methane And Carbon Dioxide to C₂ Hydrocarbons Under Pulse Corona Plasma Over La₂O₃/γ-Al₂O₃ Catalyst. *Catalysis Today*, 72 (3–4), 223–227.
- Zhang, X., Lee, C., Mingos, D. M. P., and Hayward, D. O. (2003). Carbon Dioxide Reforming of Methane with Pt Catalysts Using Microwave Dielectric Heating. *Catalysis Letters*, 88(3-4), 129–139.

- Zhu, Q., Chen, Q., Yang, X., and Ke, D. (2007). A New Method for The Synthesis Of Molybdenum Carbide. *Materials Letters*, 61 (29), 5173–5174.
- Zhu, Y., Zhang, S., Ye, Y., Zhang, X., Wang, L., Zhu, W., Cheng, F., and Tao, F. (2012). Catalytic Conversion of Carbon Dioxide to Methane on Ruthenium-Cobalt Bimetallic Nanocatalysts and Correlation Between Surface Chemistry of Catalysts Under Reaction Conditions And Catalytic Performances. *ACS Catalysis*, 2, 2403–2408.
- Zlotorzynski, A. (1995). The Application of Microwave Radiation to Analytical and Environmental Chemistry. *Critical Reviews In Analytical Chemistry*, 25 (1), 43–76.
- Zugic, B., Zhang, S., Bell, D. C., Tao, F., and Flytzani-Stephanopoulos, M. (2014). Probing The Low-Temperature Water-Gas Shift Activity of Alkali-Promoted Platinum Catalysts Stabilized on Carbon Supports. *Journal of the American Chemical Society*, 136, 3238–3245.