

EFFECT OF GARNET WASTE ON THE PROPERTIES OF FOAMED  
CONCRETE

IBRAHIM MAGIRA TOM

A project report submitted in partial fulfillment of the  
requirements for the award of the degree of  
Master of Engineering (Structure)

Faculty of Civil Engineering  
Universiti Teknologi Malaysia

JANUARY 2017

## ACKNOWLEDGEMENT

First and above all, I praise Allah, the almighty for providing me this opportunity and granting me the capability to pursue my study up to this level. This thesis appears in its current form due to the assistance and guidance of several people. I would therefore like to offer my deepest gratitude to all of them.

**Associate Professor Dr. A. Aziz Saim**, my esteemed supervisor, my cordial thanks for accepting me as your student, your warm encouragement, thoughtful guidance, critical comments, and physical assistance since the initial until the final phase of this study. I do not have enough words to express my deep and sincere appreciation.

My sincerest gratitude to **Professor Mohd Warid Hussin** and **Dr. Mohd Azreen Mohd Ariffin** for making available the most important material (garnet waste) used in this study. I am also indebted and very thankful to **Assoc. Prof. Dr. Tan Cher Siang** and **Dr. Shek Poi-Ngian** for their contribution with the necessary instrument and materials (foam generator and synthetic foaming agent) in making this study possible.

Finally, I must express my heartfelt gratitude to my parents: **Alhaji Magira Tom** and **Hajja Hauwa Shetima** and to my wife **Maimuna Ahmad Tom** and to my entire family members for providing me with unfailing support and encouragement throughout my years of study. This accomplishment would not have been possible without them.

## ABSTRACT

The research is aimed to produce foamed concrete blocks viable for non-structural applications. This paper reports the studied effect of garnet waste on the properties of foamed concrete. Garnet waste was used to replace fine aggregates (sand) at different percentages (20%, 40%, 60%, 80% and 100%). The various mixes were checked for fresh properties (workability and plastic density of mortar and foamed concrete) and consequent compressive strength test was carried out on cube and block specimens. The results have shown increment in workability with respect to increase in garnet content. The best replacement producing the best compressive strength is that containing 20% spent garnet waste replacing fine aggregates (sand). The mix has added up to 15 % in cube compressive strength and 12% in block compressive strength. However, replacing 100% fine aggregates (sand) with spent garnet waste for foamed concrete is not possible due to probable chemical reaction between synthetic foaming agent and garnet waste disallowing proper bond between cement and garnet waste.

## ABSTRAK

Penyelidikan ini bertujuan menghasilkan blok konkrit berbusa sesuai untuk penggunaan bukan struktur. Kesan bahan buangan 'garnet' kepada sifat-sifat konkrit berbusa dikaji. 'Garnet' digunakan sebagai pengganti batu baur halus pada peratus yang berbeza (20%, 40%, 60%, 80% dan 100%). Pelbagai campuran ini diuji keboleherjaan dan ketumpatan plastik bagi mortar dan konkrit berbusa manakala ujian kekuatan mampatan di jalankan kepada specimen kiub dan juga blok. Keputusan menunjukkan peningkatan keboleherjaan apabila terdapat pertambahan kandungan 'garnet'. Campuran 20% 'garnet' menggantikan pasir menghasilkan kekuatan mampatan yang terbaik. Campuran ini juga berupaya meningkatkan kekuatan mampatan sehingga 15% kepada kiub dan 12% kepada blok. Bagaimanapun penggantian 100% batu baur halus dengan 'garnet' tidak dapat menghasilkan konkrit berbusa. Ini mungkin disebabkan tindakbalas kimia diantara agen busa sintetik dan 'garnet' yang tidak membolehkan ikatan sebenar antara simen dan garnet.

## TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	<b>DECLARATION</b>	ii
	<b>DEDICATION</b>	iii
	<b>ACKNOWLEDGMENT</b>	iv
	<b>ABSTRACT</b>	v
	<b>ABSTRAK</b>	vi
	<b>TABLE OF CONTENTS</b>	vii
	<b>LIST OF TABLES</b>	xi
	<b>LIST OF FIGURES</b>	xiii
	<b>LIST OF ABBREVIATIONS</b>	xvi
	<b>LIST OF SYMBOLS</b>	xvii
	<b>LIST OF APPENDICES</b>	xviii
<b>1</b>	<b>INTRODUCTION</b>	<b>1</b>
	1.1 Background	1
	1.2 Problem Statement	2
	1.3 Aim	3
	1.4 Objectives	3
	1.5 Scope of Study	3
	1.6 Significance of Study	4
<b>2</b>	<b>LITERATURE REVIEW</b>	<b>5</b>
	2.1 Foamed concrete	5
	2.1.1 Method of foaming in foamed concrete production.	6

	2.1.1.1	Pre-foamed method	6
	2.1.1.2	Inline system wet method	7
	2.1.1.3	Incline system dry method	7
	2.1.2	Characteristics governing the properties of foamed concrete.	8
	2.1.2.1	Compressive strength	8
	2.1.2.2	Tensile strength	9
	2.1.2.3	Thermal conductivity	9
	2.1.2.4	Thermal expansion	9
	2.1.2.5	Shrinkage property	10
	2.1.3	Constituents of foamed concrete	10
	2.1.3.1	Cement	11
	2.1.3.2	Fine aggregate	11
	2.1.3.3	Water	12
	2.1.3.4	Foaming agent	12
	2.1.4	Advantages of foamed concrete	14
	2.1.5	Replacement materials for foamed concrete	14
2.2		Garnet	15
	2.2.1	Crystal chemistry of garnet	15
	2.2.2	Chemical composition of garnet	16
	2.2.3	Physical properties of garnet	17
2.3		Compressive strength of foamed concrete	17
2.4		Water absorption of foamed concrete	21
2.3		Shrinkage of foamed concrete	23
<b>3</b>		<b>METHODOLOGY</b>	<b>27</b>
	3.1	Introduction	27
	3.2	Experimental program	28
	3.2.1	Experimental program phase 1	28
	3.2.2	Experimental program phase 2	29
	3.3	Material selection	30
	3.3.1	Cement	30
	3.3.2	Fine aggregate	32
	3.3.3	Water	33

3.3.4	Garnet waste	34
3.3.5	Foaming agent	35
3.4	Material and specimen preparation	35
3.4.1	Sieve analysis	36
3.4.2	Mould preparation	37
3.4.2.1	Mould preparation phase 1	37
3.4.2.2	Mould preparation phase 2	38
3.4.3	Foam generation	39
3.4.4	Mortar mixing	41
3.4.5	Foamed concrete mixing	42
3.4.6	Placing process	44
3.4.7	Curing process	44
3.5	Test methods	45
3.5.1	Fresh state	45
3.5.1.1	Flow table test	46
3.5.1.2	Inverted slump test	47
3.5.1.3	Plastic density test	48
3.5.2	Hardened state	48
3.5.2.1	Cube compressive strength test	49
3.5.2.2	Block compressive strength test	50
<b>4</b>	<b>RESULTS AND ANALYSIS</b>	<b>51</b>
4.1	Introduction	51
4.2	Fresh properties	51
4.2.1	Flow table test	52
4.2.2	Inverted slump test	57
4.2.3	Plastic density test	62
4.3	Hardened properties	66
4.3.1	Cube compressive strength test	67
4.3.2	Block compressive strength test	72
<b>5</b>	<b>CONCLUSION AND RECOMMENDATIONS</b>	<b>75</b>
5.1	Introduction	75
5.2	Conclusion	75

	x
5.3 Recommendations	76
<b>REFERENCES</b>	<b>77</b>
<b>APPENDICES A-C</b>	<b>83-86</b>

**LIST OF TABLES**

<b>TABLE NO.</b>	<b>TITLE</b>	<b>PAGE</b>
2.1	Typical properties of foamed concrete	8
2.2	Typical mix details for foamed concrete	10
2.3	Chemical composition of garnet waste	16
2.4	Physical properties of garnet waste	17
2.5	(Test Result) F.C. Mix - 1 (Cement: Fly Ash in 1:1 Ratio)	20
2.6	(Test Result) F.C. Mix - 2 (Cement: Fly Ash: Sand in 1:0.5:1.5 Ratio)	20
3.1	Mechanical and physical requirements of cement	31
3.2	Chemical requirements of cement	31
3.3	Foamed concrete mix design A	43
3.4	Foamed concrete mix design B	43
4.1	Flow table test results for foamed concrete mixes with 0.7 w/c	52
4.2	Flow table test results for foamed concrete mixes with 0.65 w/c	52
4.3	Inverted slump test results for foamed concrete mixes with 0.7 w/c.	57
4.4	Inverted slump test results for foamed concrete mixes with 0.65 w/c	57
4.5	Plastic density test results for foamed concrete mixes with 0.7 w/c	62
4.6	Plastic density test results for foamed concrete mixes with 0.65 w/c	62
4.7	Cube compressive strength for foamed concrete mixes with 0.7 w/c	67

4.8	Cube compressive strength for foamed concrete mixes with 0.65 w/c	67
4.8	Block compressive strength for foamed concrete mixes with 0.7 w/c	72

## LIST OF FIGURES

FIGURE NO.	TITLE	PAGE
2.1	Basic constituents of foamed concrete	11
2.2	Foam generation	13
2.3	Compressive strength development of 1/2 (binders/sand) foamed concrete mix	18
2.4	Compressive strength development of 1/3 (binders/sand) foamed concrete mix	18
2.5	Effect of FAcoarse fine aggregate on 100mm cube sealed-cured compressive strength development	19
2.6	Effect of Dry Density on Percentage Water Absorption	21
2.7	Effect of Dry Density on Water Absorption	22
2.8	Variation of water absorption with different dry density and mixes	23
2.9	Influence of FAcoarse and FA fine on early age drying shrinkage strain of foamed concrete (mixes 5–10) A	24
2.10	Influence of FAcoarse and FA fine on early age drying shrinkage strain of foamed concrete (mixes 5–10) B	24
2.11	Relation between shrinkage strains with age of concrete for 0% to 60% of PFA replacement (b/s= 1/2)	25
2.12	Relation between shrinkage strains with age of concrete for 0% to 60% of PFA replacement (b/s= 1/3)	26
3.1	Research methodology flow chart	27
3.2	Flow chart of the experimental program phase 1	28
3.3	Flow chart of the experimental program phase 2	29
3.4	Cement	30
3.5	Fine aggregate	32

3.6	Water	33
3.7	Spent garnet waste SW104	34
3.8	Synthetic based foaming agent	35
3.9	Grading curve for utilized fine aggregate	36
3.10	Plywood cube mould preparation	37
3.11	Plywood block mould preparation	38
3.12	Foam generator	39
3.13	Foam mix component	40
3.14	Mortar mixing	41
3.15	Foamed concrete mixing	42
3.16	Placing process	44
3.17	Curing process	45
3.18	Flow table test apparatus	46
3.19	Inverted slump test apparatus	47
3.20	Plastic density test apparatus	48
3.21	Compression test machine	49
4.1	Flow of mortar for foamed concrete mixes with 0.7 w/c ratio	53
4.2	Flow of mortar for foamed concrete mixes with 0.65 w/c ratio	54
4.3	Cone flow for NFC mortar mix sample C	56
4.4	Cone flow for MFC mortar mix sample B1	56
4.5	Cone flow for MFC mortar mix sample B5	56
4.6	Slump flow of foamed concrete mixes with 0.7 w/c ratio	58
4.7	Slump flow of foamed concrete mixes with 0.65 w/c ratio	59
4.8	Slump flow for NFC mortar mix sample C	61
4.9	Slump flow for MFC mortar mix sample B1	61
4.10	Slump flow for MFC mortar mix sample B5	61
4.11	Plastic and hardened density of foamed concrete mixes with 0.7 w/c	63
4.12	Plastic and hardened density of foamed concrete mixes with 0.65 w/c	64
4.13	Failure criteria for MFC mix sample B5	66
4.14	Cube compressive strength for foamed concrete mixes with 0.7 w/c	68
4.15	Cube compressive strength for foamed concrete mixes with 0.65 w/c	69

4.16	Failure and crack pattern of NFC sample C likewise MFC sample B1, B2 and B3	71
4.17	Block compressive strength for foamed concrete	73
4.18	Failure and crack pattern concrete NFC mix sample C, and MFC mix sample B1	74

## LIST OF ABBREVIATIONS

BS	-	British standard
ASTM	-	American society of testing and materials
MS	-	Malaysian standard
NFC	-	Normal foamed concrete
MFC	-	Modified foamed concrete
MMHE	-	Malaysian Marine and Heavy Engineering
LWC	-	Lightweight concrete
C	-	Control mix
B1	-	20% spent garnet waste replacement by fine aggregate
B2	-	40% spent garnet waste replacement by fine aggregate
B3	-	60% spent garnet waste replacement by fine aggregate
B4	-	80% spent garnet waste replacement by fine aggregate
B5	-	100% spent garnet waste replacement by fine aggregate

**LIST OF SYMBOLS**

w/c	-	water to cement ratio
b/s	-	binder to sand ratio
°C	-	degree celcius
ppm	-	parts per million
μm	-	micro meter
MPa	-	Mega-pascal
Psi	-	pounds per square inch
mm	-	milli-meter
ml	-	milli-liter
sec	-	seconds
min	-	minutes
kg	-	Kilogram
kg/m <sup>3</sup>	-	Kilogram per meter cube
N	-	Newton
N/mm <sup>2</sup>	-	Newton per millimeter square
kN/mm <sup>2</sup>	-	Kilo newton per millimeter square
W/mK	-	watts per meter kelvin

**LIST OF APPENDICES**

<b>APPENDIX</b>	<b>TITLE</b>	<b>PAGE</b>
A	Example of mix design calculation for foamed concrete	83
B	Sieve analysis test result table	85
C	Crack assessment (BS EN 12390-3 2001)	86

## **CHAPTER 1**

### **INTRODUCTION**

#### **1.1 Background**

For ages and eras, construction has been a premier component in the way of human advancement and how human life courses are been perceived. Rightly, it could be said that the contemporary world is at a construction age. Concrete however, is the largest and universally utilized construction material in all kinds of modern construction (M. S. Shetty 2005). By far, it remains the prime element in all civil engineering constructions and technology due to nothing more than the following sub structural properties. The mould capability and flexibility of it materials likewise the immense durability over compression as well as sighting of reinforcing and pre-stressing system which served to make up for it depressed durability over tension is contributing largely to its epidemic utilization.

Subsequent to the invention of concrete in the construction industry, it has been a prime course to advance this material in a feasible and a sustainable manner. Through this course, substantial innovations and improvements have been made. Foamed concrete been one of these ample developments, it dates back to the primitive years of concrete technology which was during the very early 1920's. However, the application of this material in actual construction was done about five decades thereafter its invention (M. H. Thakrele 2014). During its primitive period of application, it was employed as a void filling material likewise in ground related engineering applications.

Foamed concrete just as the name implies, is a porous concrete that is highly flow-able and self-compacting. This type of concrete possesses extraordinary properties, it is incredibly light in weight set against the conventional concrete. Its thermal insulating properties are exceptional (M. R. Jones and A. McCarthy 2005). Foamed concrete is an aerated like concrete that is mainly composed of cement, water, fine aggregates and a foaming agent. These constituents when blended together form a chemical reaction through which literally millions of equally sized bubbles are formed. These may be as a result of air or gas formation with the mortar mixture (A.A. Hilal et al. 2014). With properties like such, it has amassed the interest of many engineers for different engineering applications.

Having considered the growing demand of foamed concrete in the construction of lightweight structures, it has become a liability upon engineers and researchers to improve this material in such a way that it becomes environmentally sustainable without altering its strength and durability (M.I. Khan 2014). In the race to achieve this course, different types of waste materials have been used. It has also been a practice to inculcate Pozzolans into foamed concrete. These materials be it manmade admixtures or natural Pozzolans possess their own peculiar benefits to concrete (S.K. Lim et al. 2013). By far, it remains clear that the inculcation of Pozzolans in foamed concrete not just promotes sustainability but also improves and enhances the properties of foamed concrete.

## **1.2 Problem Statement**

In the current construction industry, the primary employment of foamed concrete is for non-load bearing applications. According to (A.A. Hilal et al. 2014), the major factor preventing foamed concrete to be used as a load bearing material is the awfully low attainment of mechanical strength. Meanwhile, (H. Awang and M.H. Ahmad 2014) revealed that the generic cause for the increment in drying shrinkage of foamed concrete is nothing other than the excessive usage of cement and the emphatically low modulus of elasticity. The basis of this research study is to counter

and improve the properties of foamed concrete using fine spent garnet waste with regards to the problems stated.

### **1.3 Aim**

The aim of this research work is to evaluate the properties of foamed concrete modified with fine spent garnet waste, which may be suitable for non-structural applications.

### **1.4 Objectives**

- i. To produce modified foamed concrete (MFC) blocks using spent garnet waste as replacement for sand.
- ii. To investigate and compare the fresh properties as well as strength development (Compressive) of modified foamed concrete (MFC) with that of Normal Foamed concrete (NFC).

### **1.5 Scope of Study**

In order to define the precise focus of this research work, the very few boundaries need to be addressed. Some limitations are set in this research work in order to avert a wider scope of study resulting into unfocused research. These factors are listed below:

- i. The study is limited to foamed concrete with density  $1600 \text{ kg/m}^3$  only.
- ii. The type of foaming agent to be used for producing foamed concrete will be an unstable synthetic based foaming agent.

- iii. The mixing of (MFC) and (NFC) paste containing the synthetic based foaming agent will be done only using a pan concrete mixer.
- iv. The optimum mix with highest compressive strength is determined after 7 days of curing inside water.

## 1.6 Significance of Study

Taking into consideration the growing concern on the issue of global warming, concrete technology researchers revealed that the substitution of cement in concrete lessens the amount of carbon (CO<sub>2</sub>) emanation thereby depreciating the extent of greenhouse gas emission.

Furthermore, using foamed concrete can offers more to sustainability compared to other concrete types. Where it is possible to make concrete without coarse aggregates and to substitute sand either fully or partially with waste materials or by products (M. R. Jones and A. McCarthy 2005). Correspondingly, substituting sand with coarse spent garnet waste will also conserves energy and depreciates the amount of carbon emanation. It will contribute to the sustainability of the environment as well as reduce the rise in construction cost.

Taking into contemplation the findings of (M. R. Jones and A. McCarthy 2005) on the viability of applying foamed concrete as a load bearing structural material. Provided that foamed concrete can achieve strength of 25 Mpa. Partially judging, it may be used for structural applications. Additionally, the observations of (M.W. Hussin 2016) on the chemical compositions of spent garnet waste have shown that the material contains a considerable percentage of silicate and aluminate, which in turn bequeaths garnet waste with cementing properties. This research work however, employs the use of fine spent garnet waste, which will expectedly increase the workability, elasticity and strength parameters of foamed concrete and thereby contribute to the escalated demand for low weight constructions.

## REFERENCES

A. Altarhuni Eyman. (2011) "Mechanical and physical properties of clay sand foamed concrete". Universiti Tun Hussein Onn Malaysia.

ACI Manual Of Concrete Practice. (1989). 1st ed. Detroit, Mich.: The Institute, 1989. Print.

Alridge D. (2005). "Introduction to foamed concrete: what, why, how? Use of foamed concrete in construction". University of Dundee, Scotland, UK:Thomas Telford., pp 1-14.

Ash Sinha, Martyn Lightfoot. (2013). "Introduction to an Alternative Blasting Media" Greenblast – Using recycled glass for pressure blasting steel surfaces and the waste produced in firing heavy clay constructed products – ECO/11/304498/S12.626414.

ASTM C136-05 "Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates." American Society for Testing and Materials.

ASTM C140 – 11a "Standard Test Methods for Sampling and Testing Concrete Masonry Units and Related Units" American Society for Testing and Materials.

ASTM CI437-01 "Standard Test Method for Flow of Hydraulic Cement Mortar." American Society for Testing and Materials.

ASTM C1611 (2014) "Standard Test Method for slump flow of self consolidating concrete" American Society for Testing and Materials.

ASTM 270 "Standard specification for mortar for unit masonry" American Society for Testing and Materials.

ASTM C869 (2014). Standard Specification for Foaming Agents Used in Making Preformed Foam for Cellular Concrete. American Society for Testing and Materials.

Balčiūnaitė, I. A. Kleišmantas, et al. (2015). "Chemical composition of rare garnets, their colours and gemmological characteristics." *chemija* 26(1): 18-24.

Baxter, E. F., M. J. Caddick, et al. (2013). "Garnet: common mineral, uncommonly useful." *Elements* 9(6): 415-419.

Bertaut, F., F. Forrat, et al. (1956). "Etude par diffraction de neutrons du grenat ferrimagnétique  $Y_3Fe_5O_{12}$ ." *Comptes Rendus Hebdomadaires Des Seances De L Academie Des Sciences* 243(13): 898-901.

Brady, K. C and Jones, M. R (2001). "Specification for Foamed Concrete". TRL Limited, pp A5-A6.

British Standards Institution (1976). "Specifications for Building Sands from Natural Sources". London : BS 1200.

British Standards Institution (1983). "Specification for High Alumina Cement". London : BS 915.

British Standards Institution (1992). "Specification for Aggregates from Natural Sources for Concrete". London: BS 882.

British Cement Association. (1994) "Foamed Concrete Composition and Properties". London. pp. 165-168.

British Standards Institution (1996). "Specification for Portland Cement". London : BS 12.

BS EN 12350-5: (2000) "Testing fresh concrete - Part 5: Flow table test," European Committee for Standardization.

BS EN 12390-1: (2003) "Testing hardened concrete – Compressive strength of test specimens. British standard institution.

BS EN 12390-3: (2003) "Testing hardened concrete – Compressive strength of test specimens. British standard institution.

BS EN 12390-4: (2003) "Testing hardened concrete – Compressive strength of test specimens. British standard institution.

BS EN 197-1: (2000) " specification Portland cement (ordinary and rapid-hardening). British standard institution.

Hanizam Awang and Muhammad Hafiz Ahmad (2014) "Durability Properties of Foamed Concrete with Fiber Inclusion" International Journal of Civil, Environmental, Structural, Construction and Architectural Engineering Vol:8, No:3, 2014.

Geller, S. (1967). "Crystal chemistry of the garnets." *Zeitschrift für Kristallographie-Crystalline Materials* 125(1-6): 1-47.

Geller, S. and M. Gilileo (1957). "The crystal structure and ferrimagnetism of yttrium-iron garnet,  $Y_3Fe_2(FeO_4)_3$ ." *Journal of Physics and Chemistry of Solids* 3(1): 30-36.

- Hanizam Awang et al. (2012) “Effect of additives on mechanical and thermal properties of lightweight foamed concrete” *advances in Applied Science Research*: 3 (5):3326-3338.
- Hanizam Awang et. al, (2013) “Mechanical and Durability Properties of Fibre Lightweight Foamed Concrete” *Australian Journal of Basic and Applied Sciences*, ISSN 1991-8178.
- Hilal Ameer A et. al, (2014) “The use of additives to enhance properties of pre-foamed foamed concrete” *IJET* 7.4 286-293. Web.
- Imtiaz Khan, Mohammad. (2014) “ Experimental investigation on mechanical characterization of fiber reinforced foamed concrete” *The graduate faculty of the university if Akron*: n, pag. Print.
- Jones M. R. and A. McCarthy. (2005) “Preliminary views on the potential of foamed concrete as structural material” *Magazine of concrete research* 57.1: 21-31. Web.
- Josef Hadipramana et al. (2014). “The Energy Absorption of Modified Foamed Concrete with Rice Husk Ash Subjected to Impact Loading” *ARPJ Journal of Engineering and Applied Sciences*. ISSN 1819-6608.
- Kearsley, E.P& Wainwrightb, P.J (2001). *Porosity and Permeability of Foamed Concrete*. *Cement and Concrete Research* 31. 805–812.
- Khalid Ali M. Gelim. (2011). “Mechanical and physical properties of fly ash foamed Concrete” *University Tun Hussein Onn Malaysia*.
- Koh Heng Boon et al. (2006) “Compressive strength and shrinkage of foamed concrete containing pulverized fly ash” *CONCET 2006*, Print.

- Kunhanandan Nambiar, E.K.& Ramamurthy K (2006). Influence of Filler type on The Properties of Foam Concrete. *Cement & Concrete Composites* 28 .475– 480.
- Lim Siong Kang et. al, (2014) “Fresh and hardened properties of light weight foamed concrete with palm oil fuel ash as a filler” *International journal of Civil, Environmental*: pag. Print.
- Maheshkumar H. Thakrele. (2014) “experimental study on foam concrete” *International Journal of Civil, Structural, Environmental and Infrastructure Engineering*. ISSN(P): 2249-6866.
- Mohamad Noridah. (2010) “The structural behavior of precast lightweight foamed concrete sandwich panel as load bearing wall” *Universiti Teknologi Malaysia*: n. pag. Print.
- Mohd Warid Hussin. (2016) “X-ray Efflorence of Spent garnet waste” *Ikram chemist, Malaysia johor*: p. 1.
- MS 552 part 1: (2003) specification Portland cement (ordinary and rapid-hardening): second revision.
- Neville Adam M. *Properties Of Concrete*. 1st ed. Harlow: Longman, 1995. Print.
- Nielsen, J. and E. Dearborn (1958). "The growth of single crystals of magnetic garnets." *Journal of Physics and Chemistry of Solids* 5(3): 202-207.
- Othuman Md Azree and Y.C. Wang (2010) “Elevated temperature and thermal properties of lightweight foamed concrete” *construction and building materials* 25.2: 705-716. Web.
- Portland Cement Association (1980), “Special Concrete, Mortars and Products’, ISBN 0-471- 67432-X.

Shetty, M. S (2005). "Concrete Technology". 1st ed. Ram Nagar, New Delhi: S. Chand, Print.